

AD-A042 447

HARRY DIAMOND LABS ADELPHI MD
RARE-EARTH ION-HOST LATTICE INTERACTIONS. 4. PREDICTING SPECTRA--ETC(U)
JUN 77 C A MORRISON, N KARAYIANIS

F/G 7/2

UNCLASSIFIED

HDL-TR-1816

NL

| OF |

AD
A042447



END
DATE
FILMED

8-77

DDC

HDL-TR-1816

12
J

AD A 042447

Rare-Earth Ion-Host Lattice Interactions
4. Predicting Spectra and Intensities
of Lanthanides in Crystals

HDL-TR-1816—Rare-Earth Ion-Host Lattice Interactions 4. Predicting Spectra and Intensities of Lanthanides in Crystals
by Clyde A. Morrison, Nick Karayannis, and Donald E. Wortman

June 1977

DDC
RECEIVED
AUG 5 1977
A

DDC FILE COPY



U.S. Army Materiel Development
and Readiness Command
HARRY DIAMOND LABORATORIES
Adelphi, Maryland 20783

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

Citation of manufacturers' or trade names does not constitute an official indorsement or approval of the use thereof.

Destroy this report when it is no longer needed. Do not return it to the originator.

AD42 210

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 14 HDL-TR-1816	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER 9
4. TITLE (and Subtitle) 6 Rare-Earth Ion-Host Lattice Interactions, 4. Predicting Spectra and Intensities of Lanthanides in Crystals.	5. TYPE OF REPORT & PERIOD COVERED Technical Report.	
7. AUTHOR(s) 19 Clyde A. Morrison, Nick/Karayianis Donald E. Wortman		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Harry Diamond Laboratories 2800 Powder Mill Road Adelphi, MD 20783		8. CONTRACT OR GRANT NUMBER(s) 16 DA: AT161102AH46
11. CONTROLLING OFFICE NAME AND ADDRESS Commander US Army Electronics Command Fort Monmouth, NJ 07703	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Program Ele: 6.11.02.A	
14. MONITORING AGENCY NAME & ADDRESS (If different from Controlling Office) 12 23 p.	12. REPORT DATE 11 June 1977	13. NUMBER OF PAGES 27
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		15. SECURITY CLASS. (of this report) Unclassified
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
18. SUPPLEMENTARY NOTES HDL Project: 308737 DRCMS Code: 611102.11.H46H1		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Lanthanides Spectra Intensities		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The spectra of Nd ³⁺ and Er ³⁺ in CaWO ₄ are reanalyzed by using free-ion wave functions to determine new phenomenological crystal field parameters, B _{km} . Ratios of [b _{km} ^l (Er)/b _{km} (Nd)] ^{1/k} are shown to be approximately independent of k and m, where b _{km} = B _{km} [⟨r ^k ⟩ _{HF} (1 - σ _k)] ⁻¹ . This result reinforces the previous assumption that derived B _{km} may be factored according to B _{km} = τ ^{-k} ⟨r ^k ⟩ _{HF} (1 - σ _k) A _{km} with the lattice sums, A _{km} , impurity		

DDC
 RECORDED
 AUG 5 1977
 RECEIVED

163 050

LB

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

ion independent. Certain assumptions regarding excited radial wave functions in addition to these results lead to theoretical τ and $\langle r \rangle \langle r^k \rangle_{4f, n\ell / \Delta n\ell}$ values for $n\ell = 5d, 5g$ for all the lanthanides. Together with $\langle r^k \rangle_{HF}$ and σ_k values obtained from the literature, one may derive B_{km} and calculate theoretical electric dipole oscillator strengths for any lanthanide-host combination where the A_{km} are determined by a lattice sum over the host's constituent ions. Tables required for performing these calculations are given.

ACCESSION IN	
NTIS	Write Section <input checked="" type="checkbox"/>
DOC	Write Section <input type="checkbox"/>
UNANNOUNCED	<input type="checkbox"/>
JUSTIFICATION	
BY	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. CODE OR SPECIAL
A	

UNCLASSIFIED

2 SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

CONTENTS

	<u>Page</u>
1. INTRODUCTION	5
2. DERIVING CRYSTAL FIELD PARAMETERS	8
3. CALCULATING ELECTRIC DIPOLE INTENSITIES	13
4. DISCUSSION AND CONCLUSIONS	18
ACKNOWLEDGEMENT	20
LITERATURE CITED	20
APPENDIX A.--HYDROGEN-LIKE WAVE FUNCTIONS AND EXPECTATION VALUES	23
DISTRIBUTION	25

TABLES

I. Values for r_{km} in Units of \AA^k where $\langle r^k \rangle_{\text{HF}} = \sum_m r_{km} N^m$	9
II. Values for τ , $\langle r^k \rangle_{\text{HF}}$ (\AA^k) and σ_k in $\rho_k = \tau^{-k} \langle r^k \rangle_{\text{HF}}$ ($1 - \sigma_k$) where Derived Crystal Field Parameters are Given by $B_{km} = \rho_k A_{km}$ for Ground f^N Configurations of Triply Ionized Lanthanides	9
III. Phenomenological B_{km} for Nd^{3+} and Er^{3+} in CaWO_4 and Calculated $b_{km} = B_{km} [\langle r^k \rangle_{\text{HF}} (1 - \sigma_k)]^{-1}$	11
IV. Ratio of Freeman and Watson Hartree-Fock Expectation Values for Several Triply Ionized Lanthanide Ground f^N Configurations	15
V. Ratio of Grossgut's Hartree-Fock Expectation Values for Ce, Pr, and Nd Ground f^N Configurations	16
VI. Best-Fit Exponential Factors in $\psi_{4f} \sim \exp[-\gamma(N)r]$ and ψ_{5d}	16
VII. Energies in 10^3 cm^{-1} for 4f, 5d, and 5g, Differences $\Delta_{5d} = E_{5d} - E_{4f}$ (and similarly for 5g), and Ratios for the Triply-Ionized Lanthanides	17
VIII. Normalized $\langle r \rangle \langle r^k \rangle / \Delta_{5d}$ Values for Triply-Ionized Lanthanides	18

1. INTRODUCTION

In the first three reports of this series,¹⁻³ a method was established for predicting the crystal field parameters, B_{km} , of triply ionized lanthanides in crystals. These B_{km} for even-k define the crystal field that determines the observed Stark splittings. A rationale was given for factoring the B_{km} of the lanthanide ions in a given host according to

$$B_{km} = \langle r^k \rangle (1 - \sigma_k) A_{km} , \quad (1)$$

where the A_{km} are coefficients in the spherical tensor decomposition of the electrostatic field at the impurity ion site and are specifically impurity ion independent. Thus, it was argued, one can calculate the A_{km} by performing a lattice summation over the constituent ions of a given host material and determine the B_{km} for any lanthanide according to equation (1). If variations from host to host in the radial integrals⁴ $\langle r^k \rangle$ and shielding factors⁵ σ_k can be assumed small, then, presumably, B_{km} can be derived for any impurity ion-host system once $\langle r^k \rangle$ and σ_k are known for the lanthanides in some convenient host.

Phenomenological B_{km} for even-k determined by the effective spin-orbit Hamiltonian (ESOH) procedure⁶ for six lanthanides in

¹N. Karayianis and C. A. Morrison, *Rare Earth Ion-Host Lattice Interactions, 1. Point Charge Lattice Sum in Scheelites*, Harry Diamond Laboratories TR-1648 (October 1973).

²N. Karayianis and C. A. Morrison, *Rare Earth Ion-Host Crystal Interactions, 2. Local Distortion and Other Effects in Reconciling Lattice Sums and Phenomenological B_{km}* , Harry Diamond Laboratories TR-1682 (January 1975).

³R. P. Leavitt, C. A. Morrison, and D. E. Wortman, *Rare Earth Ion-Host Crystal Interactions, 3. Three-Parameter Theory of Crystal Fields*, Harry Diamond Laboratories TR-1673 (June 1975).

⁴A. J. Freeman and R. E. Watson, *Phys. Rev.*, 127 (15 September 1962), 2058.

⁵P. Erdős and J. H. Kang, *Phys. Rev. B*, 6 (1 November 1972), 3393.

⁶N. Karayianis, *J. Chem. Phys.*, 53 (15 September 1970), 2460.

CaWO₄ were used³ to test this premise. It was concluded that the simplest, nontrivial forms for the $\langle r^k \rangle$ and A_{km} in equation (1) are

$$\langle r^k \rangle = \tau^{-k} \langle r^k \rangle_{HF} \quad (2)$$

and

$$A_{km} = A_{km}(q\eta) , \quad (3)$$

so that derived (as opposed to phenomenological) $B_{km}(\tau; q\eta)$ for even- k are functions of the three parameters, τ , q , and η . The τ parameter in this theory corrects for inadequacies in Hartree-Fock radial wave functions, and the values of τ which were found to be about 0.75 are consistent with the τ necessary to adjust Pr³⁺ Hartree-Fock values for Slater integrals to empirical values.² The q parameter is the effective charge on the anion in the covalent radical of the scheelite-type crystals considered (for example, the effective oxygen charge in the WO₄²⁻ radical in CaWO₄), and η is the ratio of the effective distance of that charge from the cation to the anion-cation nuclear distance as determined by x-ray or neutron diffraction. This so-called three-parameter theory of crystal fields was implemented³ to determine how well one can fit derived to phenomenological B_{km} for the six lanthanides Nd, Tb, Dy, Ho, Er, and Tm in CaWO₄. It is important to establish how well the electrostatic field of the host material can be represented by the $A_{km}(q\eta)$, because, if the A_{km} for even- k are adequate to predict the B_{km} , then the A_{km} for odd- k --important in intensity calculations--also may be presumed adequate. It is presently impractical to obtain the latter by any other method.

²N. Karayianis and C. A. Morrison, *Rare Earth Ion-Host Crystal Interactions, 2. Local Distortion and Other Effects in Reconciling Lattice Sums and Phenomenological B_{km}* , Harry Diamond Laboratories TR-1682 (January 1975).

³R. P. Leavitt, C. A. Morrison, and D. E. Wortman, *Rare Earth Ion-Host Crystal Interactions, 3. Three-Parameter Theory of Crystal Fields*, Harry Diamond Laboratories TR-1673 (June 1975).

Point charge lattice sums $A_{km}(q\eta)$ were performed,³ and τ , q , and η were varied to fit derived to phenomenological B_{km} independently for the six ions in CaWO_4 . It was then shown, by fixing the effective oxygen charge to $q = -1.09$ and its fractional distance from tungsten to $\eta = 0.977$, that a best τ for each of the six lanthanides could be determined that gives substantially the same fit to phenomenological B_{km} as previously obtained when τ , q , and η were varied independently. The fact that fits to the B_{km} of each ion could be made with the same A_{km} $(-1.09, 0.977)$ represents a qualified success for the theory, but the rms deviations remaining between derived and phenomenological B_{km} are still too large, ranging from 13 (for Er) to 135 cm^{-1} (for Tb), to give one confidence in the predicting capabilities of the theory.

ont from p. 5

→ In this report, the latest values for quantities necessary to derive the B_{km} are used in an attempt to isolate the source of these large discrepancies. A new analysis using free-ion wave functions is performed on the spectra of Nd and Er in CaWO_4 to determine more accurate τ factors for these ions. A linear interpolation to all the lanthanides of these τ , along with smoothed values for Freeman and Watson's⁴ $\langle r^k \rangle_{\text{HF}}$ and linearly interpolated values for the σ_k of Erdős and Kang,⁵ are used to determine ρ_k , where

$$\rho_k(\tau) = \tau^{-k} \langle r^k \rangle_{\text{HF}} (1 - \sigma_k), \quad (4)$$

so that

$$B_{km}(\tau; q\eta) = \rho_k(\tau) A_{km}(q\eta). \quad (5)$$

³R. P. Leavitt, C. A. Morrison, and D. E. Wortman, *Rare Earth Ion-Host Crystal Interactions*, 3. Three-Parameter Theory of Crystal Fields, Harry Diamond Laboratories TR-1673 (June 1975).

⁴A. J. Freeman and R. E. Watson, *Phys. Rev.*, **127** (15 September 1962), 2058.

⁵P. Erdős and J. H. Kang, *Phys. Rev. B*, **6** (1 November 1972), 3393.

Values are derived also for quantities necessary for calculating transition probabilities such as $\langle r^p \rangle_{4f, n\ell}$ for $p = 1, 3, 5$, and 7 and $\Delta_{n\ell} = E_{n\ell} - E_{4f}$ for $n\ell = 5d$ and $5g$.

The results given in this report set the stage for calculating spectra and electric dipole transition probabilities effectively from first principles for all the lanthanides. These calculations will be performed for many of the current experimental host materials to establish an initial competency in predicting potential laser properties of new materials. Results of this project will be the topic of subsequent reports in this series. While it may be overly optimistic to expect that one can accurately predict spectra once the crystal coordinates of the host material are known, it is hoped that some guidance can be given as to which materials show greatest promise as laser materials.

2. DERIVING CRYSTAL FIELD PARAMETERS

The first step in deriving the ρ_k for the lanthanides according to equation (4) requires a determination of $\langle r^k \rangle_{HF}$ and σ_k . We have obtained fifth-degree polynomial expressions in N that fit the values of $\langle r^k \rangle_{HF}$ calculated by Freeman and Watson⁴ for Ce, Pr, Nd, Sm, Dy, Er, and Yb to better than 0.24 percent accuracy. Letting

$$\langle r^k \rangle_{HF} = \sum_{m=0}^5 r_{km} N^m, \quad (6)$$

where N is the number of f electrons for a given triply ionized lanthanide, one gets values for the r_{km} given in table I. These

⁴A. J. Freeman and R. E. Watson, *Phys. Rev.*, 127 (15 September 1962), 2058.

TABLE I. VALUES FOR r_{km} IN UNITS OF \AA^k

WHERE $\langle r^k \rangle_{HF} = \sum_m r_{km} N^m$

m	r_{2m}	r_{4m}	r_{6m}
0	3.79955(-1)	3.45431(-1)	6.56496(-1)
1	-5.13951(-2)	-9.04155(-2)	-2.36090(-1)
2	8.32091(-3)	1.78303(-2)	5.12945(-2)
3	-8.92996(-4)	-2.05603(-3)	-6.15291(-3)
4	5.02302(-5)	1.20584(-4)	3.69091(-4)
5	-1.12879(-6)	-2.78753(-6)	-8.64990(-6)

NOTE: Numbers in parentheses are powers of 10.

formulas give values for $Gd(N = 7)$ of $\langle r^k \rangle_{HF} = 0.223, 0.124,$ and 0.148 in units of \AA^k for $k = 2, 4,$ and $6,$ respectively, whereas Freeman and Watson obtain $0.220, 0.119,$ and 0.138 by their Hartree-Fock method.* The differences between corresponding values indicate the degree of accuracy that one may expect in extending the polynomial fits to the lanthanides for which radial integrals were not obtained by Freeman and Watson. For completeness, table II gives the $\langle r^k \rangle_{HF}$ for all the triply ionized lanthanides calculated from equation (6) by using the r_{km} values in table I.

TABLE II. VALUES FOR $\tau, \langle r^k \rangle_{HF} (\text{\AA}^k)$ AND σ_k IN $\rho_k = \tau^{-k} \langle r^k \rangle_{HF} (1 - \sigma_k)$ WHERE DERIVED CRYSTAL FIELD PARAMETERS ARE GIVEN BY $B_{km} = \rho_k A_{km}$ FOR GROUND f^N CONFIGURATIONS OF TRIPLY IONIZED LANTHANIDES

Ion	N	τ	$\langle r^2 \rangle_{HF}$	$\langle r^4 \rangle_{HF}$	$\langle r^6 \rangle_{HF}$	ρ_2	ρ_4	ρ_6	ρ_2	ρ_4	ρ_6
Ce	1	0.7693	0.3360	0.2709	0.4659	0.6757	0.0254	-0.0422	0.1841	0.7536	2.3417
Pr	2	0.7597	0.3041	0.2213	0.3459	0.6667	0.0272	-0.0421	0.1756	0.6464	1.8754
Nd	3	0.7500	0.2803	0.1882	0.2715	0.6578	0.0290	-0.0420	0.1706	0.5776	1.5897
Pm	4	0.7403	0.2621	0.1655	0.2247	0.6488	0.0308	-0.0418	0.1679	0.5339	1.4213
Sm	5	0.7306	0.2472	0.1488	0.1929	0.6398	0.0327	-0.0417	0.1668	0.5049	1.3210
Eu	6	0.7210	0.2347	0.1353	0.1686	0.6309	0.0345	-0.0415	0.1666	0.4836	1.2503
Gd	7	0.7113	0.2232	0.1237	0.1477	0.6220	0.0363	-0.0414	0.1668	0.4656	1.1873
Tb	8	0.7016	0.2129	0.1131	0.1287	0.6130	0.0381	-0.0413	0.1673	0.4990	1.1232
Dy	9	0.6919	0.2033	0.1037	0.1119	0.6041	0.0399	-0.0411	0.1681	0.4341	1.0614
Ho	10	0.6823	0.1945	0.0954	0.0981	0.5951	0.0418	-0.0410	0.1692	0.4217	1.0119
Er	11	0.6726	0.1865	0.0883	0.0874	0.5861	0.0436	-0.0408	0.1706	0.4126	0.9826
Tm	12	0.6629	0.1790	0.0820	0.0787	0.5772	0.0454	-0.0407	0.1722	0.4053	0.9649
Yb	13	0.6532	0.1717	0.0753	0.0681	0.5683	0.0472	-0.0406	0.1737	0.3938	0.9120

Values for the σ_k were obtained by linear interpolation by using the Erdős and Kang⁵ values for Pr and Tm. One gets

*Multiply the values of Freeman and Watson, which are in atomic units, by $(0.529172)^k$ to obtain \AA^k units, where the angstrom unit $\text{\AA} = 10^{-8}$ cm.

⁵P. Erdős and J. H. Kang, Phys. Rev. B, 6 (1 November 1972), 3393.

$$\sigma_2 = 0.6846 - 0.00895N , \quad (7a)$$

$$\sigma_4 = 0.02356 + 0.00182N , \quad (7b)$$

$$\sigma_6 = -0.04238 + 0.00014N , \quad (7c)$$

which generate the values given in table II.

Values for the τ given in table II are calculated by the formula

$$\tau = 0.75(1.0387 - 0.0129N) , \quad (8)$$

which was obtained by a linear interpolation of values obtained for Nd^{3+} and Er^{3+} in CaWO_4 as follows: Free-ion basis wave functions⁷ for the lowest 14 and 10 multiplets, respectively, for Nd and Er were obtained by using the "free-ion" parameters of Carnall, Fields, and Rajnak.⁷ Crystal field subspaces for S_4 symmetry were then set up and diagonalized for the crystal field Hamiltonian

$$H_x = \sum_{km} B_{km}^+ \sum_i C_{km}(\hat{r}_i) ,$$

where the C_{km} are unnormalized spherical harmonics. By varying the B_{km} and the multiplet centroids, fits of 4.56 and 3.80 cm^{-1} rms were obtained,⁸ respectively, to 51 (out of 64) and 38 (out of 58) experimentally identified Stark levels of Nd and Er. These parameters are given in table III, columns 2 and 4. If the phenomenological B_{km} are factorable according to equations (4) and (5) where the A_{km} are impurity ion independent, then b_{km} , defined by

$$b_{km} = B_{km} \left[\langle r^k \rangle_{\text{HF}} (1 - \sigma_k) \right]^{-1} , \quad (9)$$

⁷W. T. Carnall, P. R. Fields, and K. Rajnak, *J. Chem. Phys.*, **49** (1968), 4424.

⁸D. E. Wortman, C. A. Morrison and N. Karayianis, *Rare Earth Ion-Host Lattice Interactions*, 5. Lanthanides in CaWO_4 , Harry Diamond Laboratories TR-1794 (June 1977).

by using the $\langle r^k \rangle_{HF}$ and σ_k values from table II, and evaluated for two different ions, will be related according to

$$\left[b_{km}(Er)/b_{km}(Nd) \right]^{1/k} = \tau_{Nd}/\tau_{Er} \quad (10)$$

independently of k and m . The b_{km} and τ_{Nd}/τ_{Er} values given in table III demonstrate the approximate constancy in the latter values with the possible exception of the value calculated from b_{20} . Giving double weight to the 4,4 and 6,4 components, we obtain approximately

$$\tau_{Er} = \tau_{Nd}/1.115 \quad (11)$$

from the average of the values in table III, column 6.

TABLE III. PHENOMENOLOGICAL B_{km} FOR Nd^{3+} AND Er^{3+} IN $CaWO_4$ AND CALCULATED

$$b_{km} = B_{km} \left[\langle r^k \rangle_{HF} (1 - \sigma_k) \right]^{-1}$$

km	Nd		Er		$\left[b_{km}(Er)/b_{km}(Nd) \right]^{1/k} = \tau_{Nd}/\tau_{Er}$	Nd (derived)	
	B_{km}	b_{km}	B_{km}	b_{km}		$B_{km}(0.752, -1.15, 0.962)$	ΔB_{km}
20	503	5244	433	5610	1.0343	393	110
40	-878	-4806	-655	-7756	1.1271	-1062	184
44	1042	5703	809	9580	1.1385	1119	77
60	-3.84	-13.57	-2.56	-28.14	1.1293	5.58	9
664	905	3199	546	6002	1.1106	734	171
164	238	841	156	1715	1.1261	41	197
					1.115 weighted av		141 rms

NOTE: Appropriate values are used from table II. Derived $B_{km}(1/q, n)$ and absolute differences between derived and phenomenological values for Nd are given in the last two columns.

To obtain values for each τ , we performed a lattice sum over the $CaWO_4$ ion setting, in units of proton charge, $q_{Ca} = +2$ and $q_W = -2 - 4q$ and varied the oxygen charge, q , its effective fractional distance from

tungsten, η , and τ_{Nd} to obtain a best fit to the phenomenological B_{km} of Nd. The resulting values for τ , q , and η , which are

$$\tau_{Nd} = 0.75 , \quad (12a)$$

$$q = -1.150 , \quad (12b)$$

$$\eta = 0.962 , \quad (12c)$$

gave a fit of 141 cm^{-1} rms between derived (table III, column 7) and phenomenological (table III, column 2) B_{km} for Nd^{3+} in $CaWO_4$. This "fit" is worse than that obtained to the phenomenological B_{km} resulting from the inherently less-accurate ESOH method.³ Assuming a linear variation for τ over the lanthanides, equations (12a) and (11) give equation (8) and the calculated values for τ in table II, column 3. According to equation (4), one may then calculate the values for ρ_k given in the last three columns of table II.

The main ingredients for deriving B_{km} for any lanthanide-host combination have thus been obtained, provided that one assumes that the τ , $\langle r^k \rangle_{HF}$, and σ_k are approximately host independent. The final task in deriving B_{km} in a given host, under these assumptions, is to develop an adequate model of the particular host material for calculating the A_{km} --the q, η model assumed in the three-parameter theory is but an initial effort in this direction. The large discrepancy of 141 cm^{-1} rms between derived and phenomenological B_{km} for Nd^{3+} in $CaWO_4$ suggests that further theoretical work is required to determine the ultimate validity of this theoretical approach.

³R. P. Leavitt, C. A. Morrison, and D. E. Wortman, *Rare Earth Ion-Host Crystal Interactions, 3. Three-Parameter Theory of Crystal Fields*, Harry Diamond Laboratories TR-1673 (June 1975).

3. CALCULATING ELECTRIC DIPOLE INTENSITIES

To calculate electric dipole intensities,⁹ one must know A_{km}^+ values for odd- k , r^k expectation values between the ground $4f$ and excited $n\ell$ configurations, where $\ell + 3 = \text{odd}$, and energy differences between the configurations $\Delta_{n\ell} = E_{n\ell} - E_{4f}$. Specifically, the matrix element $M_{\mu}(ij)$ that determines the electric dipole intensity of polarization μ between the states i and j in the ground f^N configuration is given by

$$M_{\mu}(ij) = \sum_{Jkmn\ell} A_{km}^+ \langle r \rangle_{4f,n\ell} \langle r^k \rangle_{4f,n\ell} \Delta_{n\ell}^{-1} \langle i | U_{m+\mu}^{(J)} | j \rangle$$

$$\times \{ [3][\ell][J] \}^{1/2} \langle 3(0)1(0) | \ell(0) \rangle \langle \ell(0)k(0) | 3(0) \rangle$$

$$\{ W(3k31; \ell J) \langle k(m)1(\mu) | J(m+\mu) \rangle ,$$
(13)

where

$U^{(J)}$ is a unit spherical tensor for N equivalent electrons,¹⁰

$$[x] \equiv 2x + 1,$$

$\langle j_1(m_1)j_2(m_2) | j(m) \rangle$ is a Clebsch-Gordan coefficient,¹¹

and $W(abcd;ef)$ is a Racah coefficient.¹¹

The oscillator strength P_{μ} of the transition is given by^{9,12}

$$P_{\mu} = \chi \left[\frac{4\pi m}{e} \nu_{ij} / \hbar \right] M_{\mu}^2(ij) ,$$
(14)

⁹B. R. Judd, *Phys. Rev.*, 127 (1 August 1962), 750. Note that our A_{km}^+ are Judd's A_{km} .

¹⁰C. W. Nielson and G. F. Koster, *Spectroscopic Coefficients for the p^n , d^n and f^n Configurations*, The MIT Press, Cambridge, MA (1963).

¹¹M. Rotenberg, R. Bivins, N. Metropolis, and J. K. Wooten, *The 3-j and 6-j Symbols, The Technology Press, Cambridge, MA (1959)*. See their p. 1, eq. (1.1) to relate Clebsch-Gordan coefficients to 3-j symbols and p. 13, eq. (2.1) to relate Racah coefficients to 6-j symbols.

¹²M. J. Weber, T. E. Varitimos and B. H. Matsinger, *Phys. Rev. B*, 8 (1 July 1973), 47.

where, in terms of the refractive index n , $\chi = n(n^2 + 2)^2/9$, m_e is the electron mass, ν_{ij} is the frequency of the radiation, and \hbar is Planck's constant divided by 2π .

As is customary, we assume that mixing between the 4f and the excited 5d and 5g configurations is primarily responsible for electric dipole transitions. To obtain approximate values for the radial integral between these configurations, we assume orthogonalized hydrogen-like radial wave functions. The wave functions are defined by comparing expectation values with experimental and theoretical data from the literature wherever possible.

We choose 4f, 5d, and 5g normalized wave functions as follows:

$$\psi_{4f} = W_{4f} r^4 \exp(-yr) , \quad (15a)$$

$$\psi_{5d} = W_{5d} (r^5 + Ar^4 + Br^3) \exp(-xr) , \quad (15b)$$

$$\psi_{5g} = W_{5g} (r^5 + Cr^4) \exp(-xr) , \quad (15c)$$

where

$$\int_0^\infty dr \psi_i \psi_j = \delta_{ij} . \quad (16)$$

From equation (16), the normalizations and the coefficients A, B, and C are defined in terms of y and x (see app A).

To determine y as a function of N , the number of electrons in the ground f^N configuration of a triply ionized lanthanide, ratios of $\langle r^5 \rangle_{4f,4f} / \langle r^3 \rangle_{4f,4f} = 39/y^2$ were adjusted to fit similar ratios calculated by Freeman and Watson using their Hartree-Fock wave functions.⁴ The quadratic relationship

$$y(N) = 5.53358 + 0.228834N - 0.00482594N^2 \text{ \AA}^{-1} \quad (17)$$

⁴A. J. Freeman and R. E. Watson, *Phys. Rev.*, 127 (15 September 1962), 2058.

gives fits of 1.03 percent or better to the eight calculated ratios of Freeman and Watson, as shown in table IV.

TABLE IV. RATIO OF FREEMAN AND WATSON HARTREE-FOCK EXPECTATION VALUES FOR SEVERAL TRIPLY IONIZED LANTHANIDE GROUND f^N CONFIGURATIONS

N	$\langle r^5 \rangle_{4f,4f} / \langle r^3 \rangle_{4f,4f}$ (\AA^2)	γ_{HF} (\AA^{-1})	$\gamma(N)$ (\AA^{-1})	$39[\gamma(N)]^{-2}$ (\AA^2)
1	1.20136	5.69850	5.75759	1.17648
2	1.08628	5.99263	5.97194	1.09354
3	1.00510	6.22944	6.17665	1.02225
5	0.90346	6.57004	6.55710	0.90707
7	0.81256	6.92778	6.89895	0.81941
9	0.76492	7.14052	7.20219	0.75186
11	0.70666	7.42873	7.46682	0.69951
13	0.65160	7.73645	7.69284	0.65901

NOTE: Effective hydrogenic wave function exponent in $\psi_{4f} \sim \exp(-\gamma_{HF}r)$, quadratic best fit $\gamma(N) = 5.53358 + 0.228834N - 0.00482594N^2$, and corresponding ratios assuming $\psi_{4f} \sim \exp[-\gamma(N)r]$.

To determine x , calculated ratios of $\langle r^5 \rangle_{4f,5d} / \langle r^3 \rangle_{4f,5d}$ were fit to similar ratios calculated from Grossgut's¹³ wave functions for Ce^{3+} , Pr^{3+} , and Nd^{3+} . A linear variation of x according to

$$x(N) = 2.48605 + 0.044175N \text{ \AA}^{-1} \quad (18)$$

gives a fit to Grossgut's ratios of 2.00 percent or better as shown in table V.

The complete set of calculated γ , x , and expectation values for all the triply ionized lanthanides is given in table VI where columns b, c, d, and e are normalized to column a for each N.

¹³P. Grossgut, *Analytical Wave Functions and Oscillator Strengths for Ce^{3+} , Pr^{3+} , Nd^{3+} and Cu^{2+}* , Ph.D Dissertation, Texas Christian University (1971) (University Microfilms, Ann Arbor MI, No. 72-7621).

TABLE V. RATIO OF GROSSGUT'S HARTREE-FOCK EXPECTATION VALUES FOR Ce, Pr, AND Nd GROUND f^N CONFIGURATIONS

N	$\langle r^5 \rangle_{4f,5d} / \langle r^3 \rangle_{4f,5d}$ (\AA^2)	x_{HF} (\AA^{-1})	$x(N)$ (\AA^{-1})	$r^5 / \langle r^3 \rangle_{x(N)}$ (\AA^2)
1	2.20785	2.55597	2.53023	2.23898
2	2.19145	2.52291	2.57440	2.13541
3	2.01422	2.64432	2.61858	2.03955

NOTE: "Effective" hydrogenic wave-function exponent in $\psi_{5d} \sim \exp(-x_{\text{HF}}r)$ assuming $\psi_{4f} \sim \exp(-y(N)r)$ with $y(N)$ from table IV, linear best fit $x(N) = 2.48605 + 0.044175 N$, and ratio of expectation values calculated with $x(N)$ for comparison with Grossgut's values.

TABLE VI. BEST-FIT EXPONENTIAL FACTORS IN $\psi_{4f} \sim \exp[-y(N)r]$ AND ψ_{5d}

N	$y(N)$ (\AA^{-1})	$x(N)$ (\AA^{-1})	a (\AA^*)	b (\AA)	c (1)	d (\AA)	e (\AA^*)
1	5.75759	2.53023	0.11491	2.23898	0.202621	0.766971	3.28281
2	5.97194	2.5744	9.40786E-2	2.13541	0.188527	0.671099	2.7013
3	6.17665	2.61858	8.03255E-2	2.03955	0.177361	0.596127	2.26565
4	6.3717	2.66275	6.93901E-2	1.9512	0.168458	0.536615	1.93289
5	6.5571	2.70693	6.06361E-2	1.86996	0.161347	0.488805	1.67449
6	6.73285	2.7511	5.35826E-2	1.79534	0.155688	0.450039	1.47102
7	6.89895	2.79528	4.78655E-2	1.72685	0.151232	0.418399	1.30892
8	7.05539	2.83945	4.32078E-2	1.66396	0.147794	0.392475	1.17853
9	7.20218	2.88363	3.93978E-2	1.60621	0.145236	0.371216	1.07288
10	7.33933	2.9278	3.62731E-2	1.55314	0.143456	0.35383	0.986835
11	7.46682	2.97197	3.37077E-2	1.50434	0.142378	0.339716	0.916565
12	7.58465	3.01615	3.16041E-2	1.45944	0.141947	0.328415	0.859198
13	7.69284	3.06032	0.029886	1.41808	0.142127	0.319578	0.812554

NOTE:

$\psi_{5d} \sim \exp[-x(N)r]$ from tables IV and V and calculated expectation values and ratios from these wave functions.

*Multiply by corresponding values in column "a" to obtain $\langle r \rangle \langle r^k \rangle$ values:

a: $\langle r \rangle_{4f,5d} \langle r^k \rangle_{4f,5d}$

b: $\langle r \rangle_{4f,5d} \langle r^k \rangle_{4f,5d} / (\text{values in col. a})$

c: $\langle r \rangle_{4f,5d} \langle r^k \rangle_{4f,5d} / (\text{values in col. a})$

d: $\langle r \rangle_{4f,5d} \langle r^k \rangle_{4f,5d} / (\text{values in col. a})$

e: $\langle r \rangle_{4f,5d} \langle r^k \rangle_{4f,5d} / (\text{values in col. a})$

The final factors required for electric dipole intensity calculations are the energy differences $\Delta_{n\ell} = E_{n\ell} - E_{4f}$ for $n\ell = 5d$ and

5g.¹⁴⁻¹⁶ Table VII is self-explanatory as to the origin of the values we have chosen. With these Δ_{nl} and the $\langle r \rangle \langle r^k \rangle$ of table VI, we obtain the final normalized factors of $\langle r \rangle \langle r^k \rangle / \Delta_{nl}$ given in table VIII. These values should be multiplied by the corresponding factor in table VI, column a, for each N if intensity comparisons between ions are to be made.

TABLE VII. ENERGIES IN 10^3 cm^{-1} FOR 4f, 5d, AND 5g, DIFFERENCES $\Delta_{5d} = E_{5d} - E_{4f}$ (AND SIMILARLY FOR 5g), AND RATIOS FOR THE TRIPLY-IONIZED LANTHANIDES

Ion	$(-E_{4f})^a$	$(-E_{5d})^b$	$(-E_{5g})^c$	$(\Delta_{5d})^d$	$(\Delta_{5g})^e$	Δ_{5g}/Δ_{5d}
Ce	296.5	246.8	74.0	49.7*	222.5	4.48
Pr	314.4	253.2	76.0	61.2*	238.4	3.90
Nd	325.2	254.8	76.4	70.4	248.8	3.53
Pm	328.2	256.6	77.0	71.6	251.2	3.51
Sm	330.8	258.3	77.5	72.5	253.3	3.49
Eu	341.0	260.0	78.0	81.0	263.0	3.25
Gd	353.8	261.5	78.4	92.3*	275.4	2.98
Tb	318.6	263.5	79.0	55.1	239.6	4.35
Dy	331.9	265.3	79.6	66.6	252.3	3.79
Ho	341.6	267.0	80.1	74.6	261.5	3.51
Er	342.6	268.7	80.6	73.9	262.0	3.55
Tm	343.2	270.5	81.2	72.7	262.0	3.60
Yb	352.1	272.2	81.7	79.9	270.4	3.38

*Measured values. See footnote a below.

^aK. L. Vander Sluis and L. J. Nugent, *J. Chem. Phys.*, **60** (1974), 1928, table II.

^bCalculated by subtracting col. d from col. a so that $-E_{5d} = -E_{5f} - \Delta_{5d}$.

^cCalculated by $-E_{5g} = 0.3(-E_{5d})$, which gives $E_{5g}(\text{Nd}) = -76,400 \text{ cm}^{-1}$ —a value similar to that obtained from the Lu III spectrum from V. Kaufman and J. Sugar, *J. Opt. Soc. Am.*, **61** (1971), 1693, as follows: From $E_{6s} = (E_{6s} - E_{5g}) - 9R/(n_{5g}^*)^2$, $E_{6s} = -169,049$ and $E_{6s} - E_{5g} = -129,107$ in units of 10^3 cm^{-1} , then $n_{5g}^* = 4.9726$. Thus, $T_{5g} = 16R/(n_{5g}^*)^2 = 71,000 \text{ cm}^{-1} \sim -E_{5g}$ for all the lanthanides.

^dK. L. Vander Sluis and L. J. Nugent, *J. Chem. Phys.*, **60** (1974), 1927, table I.

^eCalculated by subtracting col. c from col. a so that $\Delta_{5g} = -E_{4f} + E_{5g}$.

¹⁴K. L. Vander Sluis and L. J. Nugent, *J. Chem. Phys.*, **60** (1 March 1974), 1927; *J. Opt. Soc. Am.*, **64** (May 1974), 687.

¹⁵V. Kaufman and J. Sugar, *J. Opt. Soc. Am.*, **61** (1971), 1693.

¹⁶J. Sugar and J. Reader, *J. Chem. Phys.*, **59** (15 August 1973), 2083.

TABLE VIII. NORMALIZED $\langle r \rangle \langle r^k \rangle / \Delta_{5k}$ VALUES FOR TRIPLY-IONIZED LANTHANIDES

N	Ion	a*	b*	c*	d*	e*
1	Ce	2.01207	4.50499	0.0910822	0.344768	1.475690
2	Pr	1.63399	3.48924	0.0790669	0.281454	1.132910
3	Nd	1.42045	2.89709	0.0712982	0.239639	0.910776
4	Pm	1.39665	2.72514	0.0670561	0.213604	0.769400
5	Sm	1.37931	2.57925	0.0636956	0.192967	0.661045
6	Eu	1.23457	2.21647	0.0591970	0.171118	0.559324
7	Gd	1.08342	1.87091	0.0549235	0.151952	0.475365
8	Tb	1.81488	3.01990	0.0616965	0.163839	0.491978
9	Dy	1.50150	2.41173	0.0575626	0.147127	0.425224
10	Ho	1.34048	2.08196	0.0548590	0.135308	0.377375
11	Er	1.35318	2.03565	0.0543490	0.129668	0.349847
12	Tm	1.37552	2.00748	0.0541681	0.125325	0.327876
13	Yb	1.25156	1.77482	0.0525539	0.118170	0.300456

NOTE:

Normalized by using Δ_{5k} ($k = d, g$) from table VII and $\langle r \rangle \langle r^k \rangle$ from table VI.

*Multiply by corresponding values in table IV, col. a, and divide by 100 to obtain actual values.

^aNormalized $\langle r \rangle \langle r^3 \rangle / \Delta_{5d}$

^bNormalized $\langle r \rangle \langle r^5 \rangle / \Delta_{5d}$

^cNormalized $\langle r \rangle \langle r^3 \rangle / \Delta_{5g}$

^dNormalized $\langle r \rangle \langle r^5 \rangle / \Delta_{5g}$

^eNormalized $\langle r \rangle \langle r^7 \rangle / \Delta_{5g}$

4. DISCUSSION AND CONCLUSIONS

It is important to note that the ostensibly superior method described in this report of using free-ion wave functions to determine phenomenological B_{km} for Nd^{3+} in CaWO_4 resulted in a fit (141 cm^{-1} compared with 101 cm^{-1} rms) between phenomenological and derived B_{km} inferior to that obtained previously³ (by using Russell-Saunders wave functions in the ESOH method). This result does not indicate that the discrepancy in the fits is necessarily due to

³R. P. Leavitt, C. A. Morrison, and D. E. Wortman, Rare Earth Ion-Host Crystal Interactions, 3. Three-Parameter Theory of Crystal Fields, Harry Diamond Laboratories TR-1673 (June 1975).

incorrect phenomenological B_{km} , but that further theoretical work probably is required to determine more accurate values for derived B_{km} .

On the other hand, a comparison of the Nd results with phenomenological B_{km} determined for Er^{3+} in CaWO_4 , also using free-ion wave functions, resulted in an approximate constancy with respect to k and m in values for $[b_{km}(\text{Er})/b_{km}(\text{Nd})]^{1/k}$. Thus, the crucial assumption in the theory remains so far intact--that the A_{km} are impurity ion independent. Without this assumption, it would be very difficult to continue the search for a theoretical model to predict impurity ion spectra.

There are several areas for improvements in the theory that readily come to mind. First, better values for $\langle r^k \rangle$ and σ_k may be determined by including electron correlations¹⁷ and relativistic corrections¹⁸ in the radial wave functions--effects neglected in the Hartree-Fock approximation. Second, one may determine the homogeneous dielectric effect of placing the impurity ion in a host environment and also the wave-function overlap effects (which, incidently, might in part be contained implicitly in the dielectric calculation). Third, and probably most important, the dipolar (and possibly higher multipolar) contributions to the A_{km} in the host material should be considered, since their contribution has already been shown to be substantial.¹⁹

The ρ_k (table II) and $\langle r \rangle \langle r^k \rangle / \Delta$ values (table VIII), while probably not sufficient for predicting accurate spectra and electric dipole

¹⁷J. C. Morrison, *J. Phys. B: Atom. Molec. Phys.*, 6 (November 1973), 2205.

¹⁸W. B. Lewis, *Relativistic Calculations of $\langle r^{-3} \rangle$ and Other $\langle r^n \rangle$ Parameters Encountered in Magnetic Resonance of Rare-Earth Ions and Atoms*, Proc. XVth Congress A.M.P.E.R.E., Bucharest, Rumania (1 to 5 September 1970), (Publishing House of Academy of Socialist Republic of Rumania, 1971).

¹⁹C. A. Morrison, *Solid State Commun.*, 18 (1976), 153.

intensities, nevertheless will be used exclusively in the following 10 reports in this series to interpret and predict spectra for the lanthanides in CaWO_4 , LiYF_4 , YVO_4 , YPO_4 , YAsO_4 , $\text{Y}_2\text{SiBe}_2\text{O}_7$, $\text{Y}_3\text{Al}_5\text{O}_{12}$ (YAG), $\text{Y}_3\text{Ga}_5\text{O}_{12}$ (YGaG), YAlO_3 , and $\text{LnP}_5\text{O}_{14}$, where Ln is any of the lanthanides. These calculations will enable one to identify the specific areas of deficiency in the present theory by comparing the predictions with the mass of reported data in the literature.

~~~~~

ACKNOWLEDGEMENT

The authors thank Richard P. Leavitt for help with the computer calculations, Robert Rosen for obtaining from H. M. Crosswhite (formerly of Johns Hopkins University) the computer tape of the coefficients of fractional parentage, and computer experts in the Management Information Systems Branch of the Harry Diamond Laboratories.

~~~~~

LITERATURE CITED

- (1) N. Karayianis and C. A. Morrison, Rare Earth Ion-Host Lattice Interactions, 1. Point Charge Lattice Sum in Scheelites, Harry Diamond Laboratories TR-1648 (October 1973).
- (2) N. Karayianis and C. A. Morrison, Rare Earth Ion-Host Crystal Interactions, 2. Local Distortion and Other Effects in Reconciling Lattice Sums and Phenomenological B_{km} , Harry Diamond Laboratories TR-1682 (January 1975).
- (3) R. P. Leavitt, C. A. Morrison, and D. E. Wortman, Rare Earth Ion-Host Crystal Interactions, 3. Three-Parameter Theory of Crystal Fields, Harry Diamond Laboratories TR-1673 (June 1975).
- (4) A. J. Freeman and R. E. Watson, Phys. Rev., 127 (15 September 1962), 2058.

LITERATURE CITED (Cont'd)

- (5) P. Erdős and J. H. Kang, Phys. Rev. B, 6 (1 November 1972), 3393.
- (6) N. Karayianis, J. Chem. Phys., 53 (15 September 1970), 2460.
- (7) W. T. Carnall, P. R. Fields, and K. Rajnak, J. Chem. Phys., 49 (1968), 4424.
- (8) D. E. Wortman, C. A. Morrison and N. Karayianis, Rare Earth Ion-Host Lattice Interactions, 5. Lanthanides in CaWO_4 , Harry Diamond Laboratories TR-1794 (June 1977).
- (9) B. R. Judd, Phys. Rev., 127 (1 August 1962), 750. Note that our A_{km} are Judd's A_{km} .
- (10) C. W. Nielson and G. F. Koster, Spectroscopic Coefficients for the p^n , d^n and f^n Configurations, The MIT Press, Cambridge, MA (1963).
- (11) M. Rotenberg, R. Bivins, N. Metropolis, and J. K. Wooten, The 3-j and 6-j Symbols, The Technology Press, Cambridge, MA (1959). See their p. 1, eq (1.1) to relate Clebsch-Gordan coefficients to 3-j symbols and p. 13, eq. (2.1) to relate Racah coefficients to 6-j symbols.
- (12) M. J. Weber, T. E. Varitimos and B. H. Matsinger, Phys. Rev. B, 8 (1 July 1973), 47.
- (13) P. Grossgut, Analytical Wave Functions and Oscillator Strengths for Ce^{3+} , Pr^{3+} , Nd^3 and Cu^{2+} , Ph.D Dissertation, Texas Christian University (1971) (University Microfilms, Ann Arbor MI, No. 72-7621).
- (14) K. L. Vander Sluis and L. J. Nugent, J. Chem. Phys., 60 (1 March 1974), 1927; J. Opt. Soc. Am., 64 (May 1974), 687.
- (15) V. Kaufman and J. Sugar, J. Opt. Soc. Am., 61 (1971), 1693.
- (16) J. Sugar and J. Reader, J. Chem. Phys., 59 (15 August 1973), 2083.
- (17) J. C. Morrison, J. Phys. B: Atom. Molec. Phys., 6 (November 1973), 2205.
- (18) W. B. Lewis, Relativistic Calculations of $\langle r^{-3} \rangle$ and Other $\langle r^n \rangle$ Parameters Encountered in Magnetic Resonance of Rare-Earth Ions and Atoms, Proc. XVIth Congress A.M.P.E.R.E., Bucharest, Rumania (1 to 5 September 1970), (Publishing House of Academy of Socialist Republic of Rumania, 1971).
- (19) C. A. Morrison, Solid State Commun., 18 (1976), 153.

APPENDIX A.--HYDROGEN-LIKE WAVE FUNCTIONS AND EXPECTATION VALUES

From equation (16) in the main body of the report for $i = j$, one obtains

$$W_{4f} = \frac{2y^4}{3} \left(\frac{y}{35} \right)^{\frac{1}{2}}, \quad (A-1)$$

$$W_{5d} = \frac{2x^5}{45} \left(\frac{2x}{7} \right)^{\frac{1}{2}} \left[1 + A \frac{2x}{5} + (A^2 + 2B) \frac{2x^2}{45} + AB \frac{x^2}{45} + B^2 \frac{x^4}{315} \right]^{\frac{1}{2}}, \quad (A-2)$$

$$W_{5g} = \frac{2x^5}{45} \left(\frac{2x}{7} \right)^{\frac{1}{2}} \left[1 + C \frac{2x}{5} + C^2 \frac{2x^2}{45} \right]^{\frac{1}{2}}. \quad (A-3)$$

From the same equation for $i \neq j$, one has

$$C = - \frac{9}{y + x}, \quad (A-4)$$

$$A = \left[\frac{8}{5} \left(\frac{x}{y + x} \right)^2 \left(2 + C \frac{x}{2} \right) - 1 - C \frac{x}{5} \right] \quad (A-5)$$

$$\times \left[\left(1 + C \frac{2x}{9} \right) \frac{x}{5} + C \frac{8}{5} \left(\frac{x}{y + x} \right)^2 \left(2 + C \frac{x}{2} \right) \right]^{-1},$$

$$B = -C^2 \frac{8}{9} \left(1 - \frac{a}{C} \right), \quad (A-6)$$

all in terms of the exponential factors y and x , respectively, for the 4f and both the 5d and 5g wave functions. The required r^p expectation values in these states are given by

$$\langle r^p \rangle_{4f,4f} = W_{4f}^2 \frac{(8+p)!}{(2y)^{9+p}}, \quad (A-7)$$

$$\langle r^p \rangle_{4f,5d} = W_{4f} W_{5d} \left[\frac{(9+p)!}{(y+x)^{10+p}} + A \frac{(8+p)!}{(y+x)^{9+p}} + B \frac{(7+p)!}{(y+x)^{8+p}} \right], \quad (A-8)$$

APPENDIX A

$$\langle r^p \rangle_{4f,5g} = W_{4f} W_{5g} \left[\frac{(9+p)!}{(y+x)^{10+p}} + C \frac{(8+p)!}{(y+x)^{9+p}} \right]. \quad (\text{A-9})$$

Thus, all of the normalizations of the radial wave functions, as well as the coefficients A, B, and C defining them (according to eq (15a) to (15c)), are given once y and x are determined. From table VI in the main body of the report, one has for Nd, for example,

$$\psi_{4f}(\text{Nd}) \sim r^4 \exp(-6r), \quad (\text{A-10})$$

$$\psi_{5d}(\text{Nd}) \sim (r^5 - 3r^4 + 2r^3) \exp(-3r), \quad (\text{A-11})$$

$$\psi_{5g}(\text{Nd}) \sim (r^5 - r^4) \exp(-3r). \quad (\text{A-12})$$

In retrospect, it might have been better to choose the ψ_{5g} wave function as pure hydrogenic as $\psi_{5g} \sim r^5 \exp(-xr)$ and to throw the deviation from hydrogen-like behavior in the ψ_{4f} wave function, because the former--being farther removed from the core--is expected to be more hydrogen-like. However, since the wave functions are used to calculate only ratios of expectation values that are important in determining relative electric dipole intensities, the ratios are not expected to be sensitive to this choice.

A further question that may legitimately be asked is why all three radial wave functions were chosen mutually orthogonal. It is true that hydrogenic radial wave functions are orthogonal either within an "n" shell $\langle \psi_{n\ell} \psi_{n\ell'} \rangle = \delta_{\ell\ell'}$, or between different n shells if ℓ and ℓ' are equal, $\langle \psi_{n\ell} \psi_{n'\ell} \rangle = \delta_{nn'}$. Thus, ψ_{4f} is required to be orthogonal to ψ_{5f} and not to ψ_{5d} or ψ_{5g} . However, since the electron orbital angular momentum ℓ is not a good quantum number so close to the core electrons, an orthogonality between the approximating radial wave functions is probably more valid than if such a condition were not imposed.

DISTRIBUTION

DEFENSE DOCUMENTATION CENTER
CAMERON STATION, BUILDING 5
ALEXANDRIA, VA 22314
ATTN DDC-TCA (12 COPIES)

COMMANDER
USA RSCH & STD GP (EUR)
BOX 65
FPO NEW YORK 09510
ATTN LTC JAMES M. KENNEDY, JR.
CHIEF, PHYSICS & MATH BRANCH

COMMANDER
US ARMY MATERIEL DEVELOPMENT
& READINESS COMMAND
5001 EISENHOWER AVENUE
ALEXANDRIA, VA 22333
ATTN DRXAM-TL, HQ TECH LIBRARY
ATTN DRCDE, DIR FOR DEV & ENGR

COMMANDER
USA ARMAMENT COMMAND
ROCK ISLAND, IL 61201
ATTN DR SAR-ASF, FUZE DIV
ATTN DR SAR-RDF, SYS DEV DIV - FUZES

COMMANDER
USA MISSILE & MUNITIONS
CENTER & SCHOOL
REDSTONE ARSENAL, AL 35809
ATTN ATSK-CTD-F

DIRECTOR
DEFENSE NUCLEAR AGENCY
WASHINGTON, DC 20305
ATTN APTL, TECH LIBRARY

DIRECTOR OF DEFENSE RES AND
ENGINEERING
WASHINGTON, DC 20301
ATTN TECHNICAL LIBRARY (3C128)

OFFICE, CHIEF OF RESEARCH,
DEVELOPMENT, & ACQUISITION
DEPARTMENT OF THE ARMY
WASHINGTON, DC 20310
ATTN DAMA-ARZ-A, CHIEF SCIENTIST
DR. M. E. LASSER
ATTN DAMA-ARZ-B, DR. I. R. HERSHNER

COMMANDER
US ARMY RESEARCH OFFICE (DURHAM)
PO BOX 12211
RESEARCH TRIANGLE PARK, NC 27709
ATTN DR. ROBERT J. LONTZ
ATTN DR. CHARLES BOGOSIAN

COMMANDER
ARMY MATERIALS & MECHANICS RESEARCH
CENTER
WATERTOWN, MA 02172
ATTN DRXMR-TL, TECH LIBRARY BR

COMMANDER
NATICK LABORATORIES
NATICK, MA 01762
ATTN DRXRES-RTL, TECH LIBRARY

COMMANDER
USA FOREIGN SCIENCE & TECHNOLOGY CENTER
FEDERAL OFFICE BUILDING
220 7TH STREET NE
CHARLOTTESVILLE, VA 22901
ATTN DRXST-BS, BASIC SCIENCE DIV

DIRECTOR
USA BALLISTICS RESEARCH LABORATORIES
ABERDEEN PROVING GROUND, MD 21005
ATTN DRXBR, DIRECTOR, R. EICHELBERGER
ATTN DRXBR-TB, FRANK J. ALLEN
ATTN DRXBR, TECH LIBRARY

COMMANDER
USA ELECTRONICS COMMAND
FORT MONMOUTH, NJ 07703
ATTN DRSEL-GG, TECHNICAL LIBRARY
ATTN DRSEL-CT-L, B. LOUIS
ATTN DRSEL-CT-L, DR. E. SCHIEL
ATTN DRSEL-CT-L, DR. HIESLMAIR
ATTN DRSEL-CT-L, J. STROZYK
ATTN DRSEL-CT-L, DR. E. J. TEBO
ATTN DRSEL-CT-L, DR. R. G. BUSER
ATTN DRSEL-WL-S, J. CHARLTON

COMMANDER
USA ELECTRONICS COMMAND
FORT BELVOIR, VA 22060
ATTN DRSEL-NV, NIGHT VISION LABORATORY
ATTN DRSEL-NV, LIBRARY

COMMANDER
USA ELECTRONICS COMMAND
WHITE SANDS MISSILE RANGE, NM 88002
ATTN DRSEL-BL, LIBRARY

DIRECTOR
DEFENSE COMMUNICATIONS ENGINEER CENTER
1860 WIEHLE AVE
RESTON, VA 22090
ATTN PETER A. VENA

COMMANDER
USA MISSILE COMMAND
REDSTONE ARSENAL, AL 35809
ATTN DRSMI-RB, REDSTONE SCIENTIFIC
INFO CENTER
ATTN DRSMI-RR, DR. J. P. HALLOWES
ATTN DRCPM-HEL, W. B. JENNINGS
ATTN DRSMI-RR, T. HONEYCUTT

COMMANDER
EDGEWOOD ARSENAL
EDGEWOOD ARSENAL, MD 21010
ATTN SAREA-TS-L, TECH LIBRARY

DISTRIBUTION (Cont'd)

COMMANDER
FRANKFORD ARSENAL
BRIDGE & TACONY STREETS
PHILADELPHIA, PA 19137
ATTN K1000, TECH LIBRARY

COMMANDER
PICATINNY ARSENAL
DOVER, NJ 07801
ATTN SARFA-TS-T-S, TECH LIBRARY

COMMANDER
USA TEST & EVALUATION COMMAND
ABERDEEN PROVING GROUND, MD 21005
ATTN TECH LIBRARY

COMMANDER
USA ABERDEEN PROVING GROUND
ABERDEEN PROVING GROUND, MD 21005
ATTN STEAP-TL, TECH LIBRARY, BLDG 305

COMMANDER
WHITE SANDS MISSILE RANGE, NM 88002
ATTN DRSEL-WL-MS, ROBERT NELSON

COMMANDER
GENERAL THOMAS J. RODMAN LABORATORY
ROCK ISLAND ARSENAL
ROCK ISLAND, IL 61201
ATTN SWERR-PL, TECH LIBRARY

COMMANDER
USA CHEMICAL CENTER & SCHOOL
FORT MC CLELLAN, AL 36201

COMMANDER
NAVAL ELECTRONICS LABORATORY CENTER
SAN DIEGO, CA 92152
ATTN TECH LIBRARY

COMMANDER
NAVAL SURFACE WEAPONS CENTER
WHITE OAK, MD 20910
ATTN CODE 730, LIBRARY DIV

DIRECTOR
NAVAL RESEARCH LABORATORY
WASHINGTON, DC 20390
ATTN CODE 2620, TECH LIBRARY BR
ATTN CODE 5554, DR. LEON ESTEROWITZ

COMMANDER
NAVAL WEAPONS CENTER
CHINA LAKE, CA 93555
ATTN CODE 753, LIBRARY DIV

COMMANDER
AF CAMBRIDGE RESEARCH LABORATORIES, AFSC
L. G. HANSCOM FIELD
BEDFORD, MA 01730
ATTN TECH LIBRARY

DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS
WASHINGTON, DC 20234
ATTN LIBRARY

DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS
BOULDER, CO 80302
ATTN LIBRARY

DIRECTOR
LAWRENCE RADIATION LABORATORY
LIVERMORE, CA 94550
ATTN DR. MARVIN J. WEBER
ATTN DR. HELMUT A. KOEHLER

NASA GODDARD SPACE FLIGHT CENTER
GREENBELT, MD 20771
ATTN CODE 252, DOC SECT, LIBRARY

NATIONAL OCEANIC & ATMOSPHERIC ADM
ENVIRONMENTAL RESEARCH LABORATORIES
BOULDER, CO 80302
ATTN LIBRARY, R-51, TECH REPORTS

CARNEGIE MELLON UNIVERSITY
SCHENLEY PARK
PITTSBURGH, PA 15213
ATTN PHYSICS & EE
DR. J. O. ARTMAN

UNIVERSITY OF MICHIGAN
COLLEGE OF ENGINEERING NORTH CAMPUS
DEPARTMENT OF NUCLEAR ENGINEERING
ANN ARBOR, MI 48104
ATTN DR. CHIHIRO KIKUCHI

DIRECTOR
ADVISORY GROUP ON ELECTRON DEVICES
201 VARICK STREET
NEW YORK, NY 10013
ATTN SECTRY, WORKING GROUP D

CRYSTAL PHYSICS LABORATORY
MASSACHUSETTS INSTITUTE OF TECHNOLOGY
CAMBRIDGE, MA 02139
ATTN DR. A. LINZ
ATTN DR. H. P. JENSSSEN

CENTER FOR LASER STUDIES
UNIVERSITY OF SOUTHERN CALIFORNIA
LOS ANGELES, CA 90007
ATTN DR. L. G. DE SHAZER

OFFICE OF NAVAL RESEARCH
ARLINGTON, VA 22217
ATTN DR. V. O. NICOLAI

DISTRIBUTION (Cont'd)

HARRY DIAMOND LABORATORIES
ATTN LOWREY, AUSTIN, III, COL, COMMANDER/
FLYER, I.N./LANDIS, P.E./
SOMMER, H./OSWALD, R.B.
ATTN CARTER, W.W., DR., TECHNICAL
DIRECTOR/MARCUS, S.M.
ATTN KIMMEL, S., PAC
ATTN CHIEF, 0021
ATTN CHIEF, 0022
ATTN CHIEF, LAB 100
ATTN CHIEF, LAB 200
ATTN CHIEF, LAB 300
ATTN CHIEF, LAB 400
ATTN CHIEF, LAB 500
ATTN CHIEF, LAB 600
ATTN CHIEF, DIV 700
ATTN CHIEF, DIV 800
ATTN CHIEF, LAB 900
ATTN CHIEF, LAB 1000
ATTN RECORD COPY, BR 041
ATTN HDL LIBRARY (3 COPIES)
ATTN CHAIRMAN, EDITORIAL COMMITTEE
ATTN CHIEF, 047
ATTN TECH REPORTS, 013
ATTN PATENT LAW BRANCH, 071
ATTN GIDEP OFFICE, 741
ATTN LANHAM, C., 0021
ATTN FARRAR, R., 350
ATTN GLEASON, T., 540
ATTN KARAYIANIS, N., 320 (10 COPIES)
ATTN KULPA, S., 320
ATTN LEAVITT, R., 320
ATTN MORRISON, C., 320 (10 COPIES)
ATTN NEMARICH, J., 320
ATTN SCALES, J., III, 540
ATTN WORTMAN, D., 320 (10 COPIES)
ATTN SATTLER, J., 320
ATTN WEBER, B., 320
ATTN SIMONIS, G., 320