

AD-A044594

RIA-77-U1115



ADA 044594

TECHNICAL LIBRARY

AMMRC CTR 77-17

DEVELOPMENT OF OXYNITRIDE MATERIALS FOR CERAMIC TOOL BITS

June 1977

Thomas Vasilos

AVCO Systems Division
Lowell, MA. 01851

FINAL REPORT

CONTRACT NUMBER DAAG46-77-C-0005

Approved for public release; distribution unlimited.

Prepared for

ARMY MATERIALS AND MECHANICS RESEARCH CENTER
Watertown, Massachusetts 02172

The findings in this report are not to be construed as an official Department of the Army position, unless so designated by other authorized documents.

Mention of any trade names or manufacturers in this report shall not be construed as advertising nor as an official indorsement or approval of such products or companies by the United States Government.

DISPOSITION INSTRUCTIONS

Destroy this report when it is no longer needed.
Do not return it to the originator.


UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AMMRC CTR 77-17	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Development of Oxynitride Materials for Ceramic Tool Bits		5. TYPE OF REPORT & PERIOD COVERED Final Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Thomas Vasilos		8. CONTRACT OR GRANT NUMBER(s) DAAG46-77-C-0005
9. PERFORMING ORGANIZATION NAME AND ADDRESS		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS D/A Project: 1T162105A1184 AMCMS Code: 62105A Agency Accession: BA OF 4764
11. CONTROLLING OFFICE NAME AND ADDRESS Army Materials and Mechanics Research Center Watertown, Massachusetts 02172		12. REPORT DATE June 1977
		13. NUMBER OF PAGES 13
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15e. DECLASSIFICATION/DOWNGRADING SCHEDULE -
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Ceramics Sialons Tool Bits Machining		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) SIALON ceramic compositions were prepared by hot pressing mixtures of silicon nitride, silica and aluminum nitride. Dense microstructures were obtained and X-ray diffraction analyses were performed. Transverse bend strength measurements were performed at room temperature and 1300°C for the various compositions. Cutting tool evaluation tests were performed against hardened tool steel, cast iron and a specialty alloy René 41.		

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)



UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

TABLE OF CONTENTS

	<u>Page</u>
I. INTRODUCTION	1
II. RESULTS AND DISCUSSION	2
III. CONCLUSIONS AND RECOMMENDATIONS	12
REFERENCES	13

LIST OF TABLES

	<u>Page</u>
Table I SIALON Billet Fabrication Conditions	3
Table II Bend Strength Results for SIALON Compositions	8
Table III René 41 Alloy-Cutting Tool Evaluation	11

LIST OF FIGURES

	<u>Page</u>
Figure 1 Photomicrograph of Polished Section of Billet No. 1928 (Comp. 1)	6
Figure 2 Photomicrograph of Polished Section of Billet No. 1922 (Comp. 2)	6
Figure 3 Photomicrograph of Polished Section of Billet No. 1923 (Comp. 3)	6
Figure 4 Cutting Tool Evaluation Against 4340 Steel	9
Figure 5 Cutting Tool Evaluation Against Cast Iron	10

I. INTRODUCTION

Oxynitride ceramic materials of the SIALON variety are the subject of a number of investigations concerned with their preparation and evaluation as materials for advanced turbine engine components. Jack¹ has reported the stability of alumina-rich SIALON compositions in contact with iron-rich melts and there are indications that a number of Japanese scientists are investigating their potential as cutting tool materials.²

Recent work³ has also demonstrated that alumina containing SIALON compositions possess mechanical bend strength properties rivaling those of the best hot pressed fine-grained pure alumina compositions, e.g., $\sim 50,000$ psi at 1200°C .




The fine-grain size character of these SIALON materials coupled with good mechanical properties and good corrosion resistance enhances their prospects as cutting tool materials.

It is recognized, however, that SIALON compositions are likely to be multi-phase, in view of recent findings.^{4,5} The major phase resulting from the reaction of Al_2O_3 and Si_3N_4 , for example, is a solid solution based on an expanded β - Si_3N_4 structure and labeled β' . The solubility limit at 1750°C of Al_2O_3 in Si_3N_4 has been estimated to be about 67 percent. However, several investigators who have reacted mixtures of Al_2O_3 and Si_3N_4 report the presence of other phases beside the β' phase.^{6,7}

Also, recent reports^{8,9,10} of phase equilibrium studies in the system Si_3N_4 - Al_2O_3 - AlN - SiO_2 have shown that single phase β' solid solutions do not exist for any appreciable extent between Si_3N_4 and Al_2O_3 . Rather extensive β' solid solutions are found along the line extending from Si_3N_4 toward the composition $\text{AlN} \cdot \text{Al}_2\text{O}_3$.

This project was concerned with the development and evaluation of a family of SIALON (oxynitride) ceramics for use as ceramic tool bit materials.

Three compositions were selected to cover a range of alumina content and they are represented by the following formulas:



Raw materials included AME controlled phase grade silicon nitride, 5 μm particle size fused silica from Harbison Walker Co., and fine particle aluminum nitride from Shieldalloy Corp.

Alumina contents beyond these levels were thought likely to show significant multi-phase content and remain to be investigated because of the added complexity.

Billets of these compositions were fabricated into 2" x 2" x $\frac{1}{2}$ " thick shapes and the resulting material characterized by metallographic and X-ray diffraction procedures.

Four-point transverse bend tests were performed to establish a property-microstructure composition relationship, and selected compositions were evaluated as cutting tool insert materials.

II. RESULTS AND DISCUSSION

Billets based on compositions described above were fabricated by hot pressing mixtures of silicon nitride, aluminum nitride and silica in graphite dies in a flowing atmosphere of N_2 gas at temperatures ranging from 1550 - 1750°C. Above 1700°C some decomposition was observed in the form of sample bloating and temperatures in subsequent trials were maintained below this level.

Table I provides data on the sialon billet fabrication conditions and

Table I - Sialon Billet Fabrication Conditions

<u>Run No.</u>	<u>Material Composition</u>	<u>Temp. °C</u>	<u>Pressure psi</u>	<u>Time (min.)</u>	<u>Billet Density, gm/cc</u>
1911	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃	1550	3000	120	2.6
1913	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃	1650	3000	120	2.8
1913	Repress	1750	3000	120	Bloated specimen Low density
1914	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃ plus 2 wt. % MgO	1700	3000	120	3.10
1915	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃ plus 2 wt. % MgO	1600	3000	120	3.19
1916	No. 2 (Si ₃ N ₄) ₂ Al ₂ O ₃	1650	3000	120	2.91
1920	No. 3 (Si ₃ N ₄) Al ₂ O ₃	1750	3000	120	Bloated Low Density
1921	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃ plus 2 wt. % MgO	1550	3000	120	3.16
1922	No. 2 (Si ₃ N ₄) ₂ Al ₂ O ₃ plus 1 wt. % MgO	1600	3000	120	3.15
1923	No. 3 (Si ₃ N ₄) Al ₂ O ₃ No MgO	1600	3000	120	3.13
1924	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃ plus 1 wt. % MgO	1600	3000	120	3.16

Table I concluded

Run No.	Material Composition	Temp. °C	Pressure psi	Time (min.)	Billet Density, gm/cc
1925	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃ plus 1 wt. % MgO	1600	3000	120	3.16
1926	No. 3 (Si ₃ N ₄) Al ₂ O ₃ No MgO	1600	3000	120	3.12
1928	No. 1 (Si ₃ N ₄) ₅ Al ₂ O ₃ plus 1 wt. % MgO	1600	3000	120	3.14
1930	No. 3 (Si ₃ N ₄) Al ₂ O ₃ plus 1 wt. % MgO	1600	3000	120	3.13
1934	No. 3 (Si ₃ N ₄) Al ₂ O ₃ plus 1 wt. % MgO	1600	3000	120	3.11

results of densification. To facilitate densification for Compositions 1 and 2, $(\text{Si}_3\text{N}_4)_5\text{Al}_2\text{O}_3$ and $(\text{Si}_3\text{N}_4)_2\text{Al}_2\text{O}_3$, respectively, a 1 wt. % MgO additive was found to be very effective. Otherwise, decomposition at higher temperatures precluded the attainment of high densification without an additive.

Composition No. 3, on the other hand, did not require an additive for identical process conditions as indicated by Run No. 1923. An MgO additive of 1% did not significantly alter the degree of densification as revealed in runs 1930 and 1934. The action of the MgO in the SIALON compositions is probably similar to its action in silicon nitride in providing a low temperature liquid phase which enhanced densification by a solution reprecipitation mechanism.

Microstructure and X-ray examinations were conducted on the fabricated billets and Figures 1, 2, and 3 show representative microphotographs of polished sections of samples of the three selected compositions. Figures 1 and 2 (Compositions 1 and 2) show essentially completely dense microstructures with some observable second phase constituent. Figure 3 (Composition 3 - Billet 1923) shows a small amount of residual porosity as well as second phase constituent. This latter composition contained no MgO additive as a densification aid since sufficiently high densities were attained without it.

X-ray diffraction analyses were performed and revealed the presence of two major phases, i.e., β' phase and α phase of silicon nitride. Crystalline silica and/or silicon oxynitride phases (Si_2ON_2) were not detected. The possibility of an AlN polytype exists. Two high intensity lines were found as an indication of the presence of aluminum nitride, but the absence of a third intense "d" line at 2.372 probably precludes its actual presence. Other lines observed which could not be indexed included:



Plate 6129-6

250X

Figure 1. Photomicrograph of Polished Section of Billet No. 1928 (Comp. 1)



Plate 6129-4

250X

Figure 2. Photomicrograph of Polished Section of Billet No. 1922 (Comp. 2)




Plate 6129-5

250X

Figure 3. Photomicrograph of Polished Section of Billet No. 1923 (Comp. 3)

<u>d Spacing</u>	<u>Intensity I/I_{max}</u>
2.747	7
2.238	14
2.110	17
1.622	7
1.608	11
1.584	17
1.419	9

Bend test bars were prepared and measurements were performed at room and elevated temperatures for the three compositions. The results are provided in Table II. These results show that Composition 1 is strongest at room temperature by a reasonably large margin, e.g., about 20% over Compositions 2 and 3. On the other hand, the elevated temperature strength for Compositions 1 and 2 are comparable but somewhat lower than that for Composition 3, which may be a function of the MgO additive in Compositions 1 and 2 providing more liquid phase.

For the bar size and span to thickness ratio observed, the strength properties of these compositions are somewhat lower at room temperature than a 99% pure fine grained (1-3 μm size) hot pressed alumina tool. However, at 1300°C, the strength properties observed for these SIALON compositions appear definitely superior to hot pressed alumina.

Samples of these compositions were prepared into cutting tool inserts (SNG 432 designation) and evaluated at Metcut Corp. in Cincinnati, Ohio in a series of performance tests.

Evaluations were performed with hardened steel (50 R_C), cast iron and a specialty alloy René 41. The results for the first two cases are plotted in Figures 4 and 5 and show that the SIALON compositions are not very effective for use against a hardened steel. In addition, a hot pressed silicon nitride composition (Norton HS130) fared no better. A standard hot pressed alumina base cutting tool, Type NPCA2 based on an 80% Al₂O₃ and 20% TiC composition,

Table II - Bend Strength Results for Sialon Compositions

(Sample size 1 3/4" x 2" x .1")

<u>Composition & Billet No.</u>	<u>Temp.</u>	<u>Four Point Bend Strength Kpsi</u>	<u>Elastic Modulus psi</u>
<u>Composition No. 1</u>			
1928-1	R.T.	58.9	42.8 x 10 ⁶
1928-2	"	72.0	
1928-3	"	45.2	
1928-4	"	60.5	
<u>Composition No. 1</u>			
1928-5	1300°C	42.4	Av. 39.6
1928-6	"	37.8	
1928-7	"	36.2	
1928-8	"	41.5	
<u>Composition No. 2</u>			
1922-1	R.T.	52.4	41.9 x 10 ⁶
1922-2	"	42.7	
1922-3	"	50.0	
1922-4	"	47.5	
<u>Composition No. 2</u>			
1922-5	1300°C	38.5	Av. 39.0
1922-6	"	42.0	
1922-7	"	37.2	
1922-8	"	38.1	
<u>Composition No. 3</u>			
1923-1	R.T.	44.7	38.5 x 10 ⁶
1923-2	"	46.1	
1923-3	"	48.5	
1923-4	"	42.5	
<u>Composition No. 3</u>			
1923-5	1300°C	45.5	Av. 44.1
1923-6	"	42.9	
1923-7	"	41.8	
1923-8	"	46.1	

Figure 4. CUTTING TOOL EVALUATION AGAINST 4340 STEEL

Turning 4340 Steel Quenched and Tempered 50 R_C

Tool Material: Sialon Comp. 1 & 2, Hot Pressed Silicon Nitride
(Alumina Ceramic NPC A-2 in SNG-432 Configuration)

Feed: .005 in/rev.
Depth of Cut: .050"
Cutting Fluid: Dry

Tool Life End Point: .015" Uniform Wear
.030" Localized Wear or Chipping




Figure 5. CUTTING TOOL EVALUATION AGAINST CAST IRON

Turning Class 30 Gray Cast Iron 187 BHN

Tool Materials: Sialon Comp. No. 1 and Hot Pressed Silicon Nitride
in SNG 432 Configuration

Feed: .005 in/rev.


Depth of Cut: .050"

Cutting Fluid: Dry

Tool Life End Point: .015" Uniform Wear

.030" Localized Wear or

Chipping



was superior by a factor of about 10 to 1 at a cutting speed of 800 surface feet per minute.

Against cast iron, however, (Figure 5) SIALON and silicon nitride (HS 130) compositions were very effective. The performance life of the hot pressed silicon nitride at 3500 sfm was exceptional. These lifetimes are considered superior to hot pressed alumina base (Al_2O_3/TiC (Avco Act I)) compositions, although no tests were actually performed. A data point for hot pressed alumina is provided in Figure 5 based on earlier work on part of Contractor. Also a data point for NPCA2 is provided on the plot. The behavior is considered peculiar in view of the relatively poor performance against silicon nitride tests against the smooth finish of the hard steel. It is considered that cutting tool-steel stock reactions are possible, e.g., iron silicide formation at the interface leading to adherence and chip formation.

In the case of cast iron where an irregular and intermittent surface is presented to the cutting tool, impact resistance may be the important parameter and silicon nitride compositions are known to excel in this connection.

Testing with René 41 alloy did not reveal very promising behavior for either the hot pressed silicon nitride or the SIALON composition selected (No. 1), although the latter was superior. In both instances, low cutting speeds had to be employed and the results are tabulated below.

Table III. René 41 Alloy-Cutting Tool Evaluation

<u>Tool Composition</u>	<u>Cutting Speed (sfm)</u>	<u>Tool Life (min.)</u>
SIALON 1	100	1 2/3
SIALON 1	50	6
H.P. Silicon Nitride	100	1/2
H.P. Silicon Nitride	50	3/4

Again early chipping failures were observed that may have been reaction related.

III. CONCLUSIONS AND RECOMMENDATIONS

In the limited evaluation conducted, hot pressed, dense SIALON and silicon nitride compositions have shown excellent performance behavior as a tool material for cast iron. Their performance against hardened steel and the specialty alloy René 41 was not particularly promising, however.

Failure mechanisms may be chemical reaction related, but this remains to be determined by reaction product studies.

It is recommended that a complete assessment of these nitride compositions against cast irons and other tool compositions be determined to establish the potential for their usage in production machining operations.

REFERENCES

1. K. Jack, SIALON Presentation at Materials Sciences Dept. Seminar, M.I.T., Cambridge, MA. (May 1974).
2. R. Fulrath, Private Communication (1976).
3. Unpublished Work, Avco Systems Division (1976).
4. Jack, K.H. and W.I. Wilson, "Ceramics Based on the SIALON and Related Systems," *Nature Phys. Sci.*, 238, 8028 (1972).
5. Oyama, Y., "Solid Solutions in the System Si_3N_4 - Ga_2O_3 - Al_2O_3 ," *Japanese Journal of Applied Physics*, 12, 500 (1973).
6. Lange, F.F., "Fabrication, Microstructure and Selected Properties of SIALON Compositions," Final Report, Nav. Air Syst. Command, Contract N00019-73-C-0208 (February 1974).
7. Drew, P. and M.H. Lewis, "The Microstructure of Silicon Nitride/Aluminum Ceramics," *J. Mat. Sci.*, 9, 1833 (1974).
8. Jack, K.H., "SIALONS and Related Nitrogen Ceramics," *J. Mat. Sci.*, 11, 1135-1158 (1976).
9. Gauckler, L.J., et al, *J. Am. Ceram. Soc.*, 58, 346 (1975).
10. Layden, G.K., "Process Development for Pressureless Sintering of SIALON Ceramic Components," Final Report, Naval Air Systems Command Contract N00019-75-C-0232 (February 3, 1976).

DISTRIBUTION LIST

No. of Copies	To
1	Office of the Director, Defense Research and Engineering, The Pentagon, Washington, D. C. 20301
12	Commander, Defense Documentation Center, Cameron Station, Building 5, 5010 Duke Street, Alexandria, Virginia 22314
1	Metals and Ceramics Information Center, Battelle Columbus Laboratories, 505 King Avenue, Columbus, Ohio 43201
	Chief of Research and Development, Department of the Army, Washington, D. C. 20310
2	ATTN: Physical and Engineering Sciences Division
	Commander, Army Research Office, P. O. Box 12211, Research Triangle Park, North Carolina 27709
1	ATTN: Information Processing Office
	Commander, U. S. Army Materiel Development and Readiness Command, 5001 Eisenhower Avenue, Alexandria, Virginia 22333
1	ATTN: DRCLDC, Mr. R. Zentner
1	DRCSA-S, Dr. R. B. Dillaway, Chief Scientist
	Commander, U. S. Army Electronics Research and Development Command, Fort Monmouth, New Jersey 07703
1	ATTN: DRSEL-GG-DD
1	DRSEL-GG-DM
	Commander, U. S. Army Missile Research and Development Command, Redstone Arsenal, Alabama 35809
1	ATTN: Technical Library
1	DRSMI-RSM, Mr. E. J. Wheelahan
	Commander, U. S. Army Armament Research and Development Command, Rock Island, Illinois 61201
2	ATTN: Technical Library
1	DRSAR-SC, Dr. C. M. Hudson
1	DRSAR-PPW-PB, Mr. Francis X. Walter
	Commander, U. S. Army Natick Research and Development Command, Natick, Massachusetts 01760
1	ATTN: Technical Library
	Commander, U. S. Army Satellite Communications Agency, Fort Monmouth, New Jersey 07703
1	ATTN: Technical Document Center

No. of Copies	To
2	Commander, U. S. Army Tank-Automotive Research and Development Command, Warren, Michigan 48090 ATTN: DRDTA-Research Library Branch
1	Commander, Aberdeen Proving Ground, Maryland 21005 ATTN: STEAP-TL, Bldg. 305
1	Commander, Frankford Arsenal, Philadelphia, Pennsylvania 19137 ATTN: Library, H1300, B1. 51-2
1	SARFA-L300, Mr. J. Corrie
1	Commander, Harry Diamond Laboratories, 2800 Powder Mill Road, Adelphi, Maryland 20783 ATTN: Technical Information Office
1	Commander, Picatinny Arsenal, Dover, New Jersey 07801 ATTN: SARPA-RT-S
1	SARPA-FR-M-D, PLASTEC, A. M. Anzalone
4	Commander, Redstone Scientific Information Center, U. S. Army Missile Research and Development Command, Redstone Arsenal, Alabama 35809 ATTN: DRSMI-RBLD, Document Section
1	Commander, Watervliet Arsenal, Watervliet, New York 12189 ATTN: SARWV-RDT, Technical Information Services Office
1	Commander, U. S. Army Foreign Science and Technology Center, 220 7th Street, N. E., Charlottesville, Virginia 22901 ATTN: DRXST-SD2
1	Director, Eustis Directorate, U. S. Army Air Mobility Research and Development Laboratory, Fort Eustis, Virginia 23604 ATTN: Mr. J. Robinson, SAVDL-EU-SS
1	Librarian, U. S. Army Aviation School Library, Fort Rucker, Alabama 36360 ATTN: Building 5907
1	Commander, U. S. Army Engineer Waterways Experiment Station, Vicksburg, Mississippi 39180 ATTN: Research Center Library
1	Naval Research Laboratory, Washington, D. C. 20375 ATTN: Dr. J. M. Krafft - Code 8430
1	Chief of Naval Research, Arlington, Virginia 22217 ATTN: Code 471

No. of Copies	To
	Air Force Materials Laboratory, Wright-Patterson Air Force Base, Ohio 45433
2	ATTN: AFML/MXE/E. Morrissey
1	AFML/LC
1	AFML/LLP/D. M. Forney, Jr.
1	AFML/MBC/Mr. Stanley Schulman
	National Aeronautics and Space Administration, Washington, D. C. 20546
1	ATTN: Mr. B. G. Achhammer
1	Mr. G. C. Deutsch - Code RR-1
	National Aeronautics and Space Administration, Marshall Space Flight Center, Huntsville, Alabama 35812
1	ATTN: R-P&VE-M, R. J. Schwinghamer
1	S&E-ME-MM, Mr. W. A. Wilson, Building 4720
1	The Charles Stark Draper Laboratory, 68 Albany Street, Cambridge, Massachusetts 02139
1	Mechanical Properties Data Center, Belfour Stulen, Inc., 13917 W. Bay Shore Drive, Traverse City, Michigan 49684
	Director, Army Materials and Mechanics Research Center, Watertown, Massachusetts 02172
2	ATTN: DRXMR-PL
1	DRXMR-AG
1	DRXMR-PR
1	DRXMR-CT
1	DRXMR-X
1	DRXMR-AP
1	DRXMR-E
1	DRXMR-EO
47	Author

Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DEVELOPMENT OF OXYNITRIDE MATERIALS FOR CERAMIC TOOL BITS Thomas Vasilos, AVCO Systems Division, Lowell Industrial Park, Lowell, Massachusetts 01851 Final Report AMRC CTR 77-17, June 1977, 13 pp - illus - tables, Contract DAAG46-77-C-0005, D/A Project: IT162105A1184, AMCMS Code: 62105A, Agency Accession: BA OF 4764. SIALON ceramic compositions were prepared by hot pressing mixtures of silicon nitride, silica and aluminum nitride. Dense microstructures were obtained and X-ray diffraction analyses were performed. Transverse bend strength measurements were performed at room temperature and 1300°C for the various compositions. Cutting tool evaluation tests were performed against hardened tool steel, cast iron and a specialty alloy René 41.	AD UNCLASSIFIED UNLIMITED DISTRIBUTION Key Words Ceramics SIALONS Tool Bits Machining	Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DEVELOPMENT OF OXYNITRIDE MATERIALS FOR CERAMIC TOOL BITS Thomas Vasilos, AVCO Systems Division, Lowell Industrial Park, Lowell, Massachusetts 01851 Final Report AMRC CTR 77-17, June 1977, 13 pp - illus - tables, Contract DAAG46-77-C-0005, D/A Project: IT162105A1184, AMCMS Code: 62105A, Agency Accession: BA OF 4764. SIALON ceramic compositions were prepared by hot pressing mixtures of silicon nitride, silica and aluminum nitride. Dense microstructures were obtained and X-ray diffraction analyses were performed. Transverse bend strength measurements were performed at room temperature and 1300°C for the various compositions. Cutting tool evaluation tests were performed against hardened tool steel, cast iron and a specialty alloy René 41.	AD UNCLASSIFIED UNLIMITED DISTRIBUTION Key Words Ceramics SIALONS Tool Bits Machining
Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DEVELOPMENT OF OXYNITRIDE MATERIALS FOR CERAMIC TOOL BITS Thomas Vasilos, AVCO Systems Division, Lowell Industrial Park, Lowell, Massachusetts 01851 Final Report AMRC CTR 77-17, June 1977, 13 pp - illus - tables, Contract DAAG46-77-C-0005, D/A Project: IT162105A1184, AMCMS Code: 62105A, Agency Accession: BA OF 4764. SIALON ceramic compositions were prepared by hot pressing mixtures of silicon nitride, silica and aluminum nitride. Dense microstructures were obtained and X-ray diffraction analyses were performed. Transverse bend strength measurements were performed at room temperature and 1300°C for the various compositions. Cutting tool evaluation tests were performed against hardened tool steel, cast iron and a specialty alloy René 41.	AD UNCLASSIFIED UNLIMITED DISTRIBUTION Key Words Ceramics SIALONS Tool Bits Machining	Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 DEVELOPMENT OF OXYNITRIDE MATERIALS FOR CERAMIC TOOL BITS Thomas Vasilos, AVCO Systems Division, Lowell Industrial Park, Lowell, Massachusetts 01851 Final Report AMRC CTR 77-17, June 1977, 13 pp - illus - tables, Contract DAAG46-77-C-0005, D/A Project: IT162105A1184, AMCMS Code: 62105A, Agency Accession: BA OF 4764. SIALON ceramic compositions were prepared by hot pressing mixtures of silicon nitride, silica and aluminum nitride. Dense microstructures were obtained and X-ray diffraction analyses were performed. Transverse bend strength measurements were performed at room temperature and 1300°C for the various compositions. Cutting tool evaluation tests were performed against hardened tool steel, cast iron and a specialty alloy René 41.	AD UNCLASSIFIED UNLIMITED DISTRIBUTION Key Words Ceramics SIALONS Tool Bits Machining