

AD-A047 272

OGDEN AIR LOGISTICS CENTER HILL AFB UTAH PROPELLANT L--ETC F/G 21/8.2
MINUTEMAN STAGE I MOTOR RELIABILITY IMPROVEMENT PROGRAM SURVEIL--ETC(U)
OCT 77 J A THOMPSON
MANCP-379(77)

UNCLASSIFIED

NL

| OF |
ADA047272

1



END
DATE
FILMED
1 -78
DDC

~~DDC~~/TISIR

P
B.S.

HEADQUARTERS
OGDEN AIR LOGISTICS CENTER
UNITED STATES AIR FORCE
HILL AIR FORCE BASE, UTAH 84406

AD A 0 47272

FINAL RIP REPORT
MINUTEMAN STAGE I
MOTOR RELIABILITY
IMPROVEMENT PROGRAM
SURVEILLANCE

DDC
RECEIVED
DEC 5 1977
H

PROPELLANT LABORATORY SECTION

MANCP REPORT

NR 379 (77)

OCTOBER 1977

APPROVED FOR PUBLIC RELEASE, DISTRIBUTION UNLIMITED

AD No. _____
DDC FILE COPY

MINUTEMAN STAGE I
MOTOR RELIABILITY
IMPROVEMENT PROGRAM
SURVEILLANCE

Author

John A. Thompson
JOHN A. THOMPSON, Chemist
Component & Combustion Test Unit

Engineering & Statistical Review By

John K. Scambia
JOHN K. SCAMBIA, Project Engineer
Service Engineering

Dan L. Petersen
DAN L. PETERSEN, Mathematician
Data Analysis Unit

Recommended Approval By

Leonidas A. Brown
LEONIDAS A. BROWN, Chief
Component & Combustion Test Unit

Ronald F. Larsen
RONALD F. LARSEN, Chief
Physical & Mechanical Test Unit

Approved By

Don F. Woods
DON F. WOODS, Chief
Propellant Laboratory Section

October 1977

Industrial Products & Ldg Gear Division
Directorate of Maintenance
Ogden Air Logistics Center
United States Air Force
Hill Air Force Base, Utah 84406

(See 1473)

ABSTRACT

This report contains data and test results from the fourth time testing of the Minuteman Stage I Reliability Improvement Program (RIP) Surveillance. Thiokol (see TWR-7300) had tested and reported on this program for eight years up through 30 June 1973. The responsibility was then turned over to the propellant Laboratory (MANCP) at OO-ALC.

In this report, Thiokol's data with the data from four years of testing in MANCP's laboratory were combined and regression analyses made by MANCP's statistical group.

The purpose of testing is to provide early warning if any serious degradation trends occur in the components being evaluated. The regressions show little or no change in trends from those previously established and are in good agreement with TWR-7300 data. Therefore, based on this analysis the service life of these components may be extended for at least two years beyond the last data point.

This constitutes final reporting on the lab. testing program on component materials from the RIP Surveillance Program.

ACCESSION for		<input checked="" type="checkbox"/>
NTIS	White Section	<input type="checkbox"/>
DDC	Buff Section	<input type="checkbox"/>
UNANNOUNCED JUSTIFICATION _____		
BY _____		
DISTRIBUTION/AVAILABILITY CODES		
Dist.	AVAIL. CODE	SPECIAL
A		

TABLE OF CONTENTS

	<u>Page</u>
Abstract	ii
List of Figures	iv
Introduction	
Purpose	1
Background	1
Statistical Analysis	4
Test Results	5
Conclusions	6
Recommendations	7
Table 1	8
Distribution List	21
DD 1473	22

LIST OF FIGURES

<u>Figure Nr</u>			<u>Page</u>
1	RS-1	Tenshear Tensile Adhesion 0° Angle	9
2	RS-1	Tenshear Tensile Adhesion 45° Angle	10
3	RS-4	Tensile Adhesion	11
4	RS-5	Tensile Strength	12
5	RS-12	Tensile Strength	13
6	RS-14	Tensile Strength	14
7	RS-19A	Tensile Strength	15
8	RS-21	Tensile Strength	16
9	RS-5	Elongation	17
10	RS-12	Elongation	18
11	RS-19A	Elongation	19
12	RS-21	Elongation	20

INTRODUCTION

A. PURPOSE:

Quality assurance testing was conducted by Thiokol for eight years on the RIP program to evaluate the effects of aging on components. Since July of 1973, testing has been performed by the Propellant Laboratory (MANCP) at OO-ALC.

Evaluation of the test data should provide early warning if serious degradation trends occur. Annual evaluation of the components provide data that can be put into engineering reliability and service life predictions. Testing was performed in accordance with MEMEP Project M72632-SMP116P.

B. BACKGROUND:

The Minuteman Stage 1 Reliability Improvement Program (RIP) Surveillance program was conducted from its inception through 30 June 1973 by Thiokol/Wasatch Division under SAMSO direction (TWR-7300, 15 Nov 1974). On 1 July 1973, responsibility for testing was turned over to Ogden Air Logistics Center, Hill Air Force Base, Utah.

1. The primary program objectives were:
 - a. Demonstrate that the various components and subsystems meet the service life requirements specified by the motor model specifications.
 - b. Evaluate the storage behavior of components and subsystems so that the start of ageout in the operational force can be predicted or demonstrated in time to take corrective action.

c. Identify and verify failure modes in sufficient time to allow orderly replacement or rework of the missile force.

In addition, major program tasks were to evaluate the storage behavior of the RIP Stage I Minuteman motors under environmental conditions representative of the operational concept, and ultimately to aid in predicting the usable life of the operationally deployed motors.

2. Major tasks were:

a. Subject full scale motors to various simulated operational storage conditions and conduct tests and inspections to determine possible degradation due to storage.

b. Conduct thorough laboratory accelerated aging programs to support the full scale motor program.

c. Provide planning necessary for integrating operational and development motor surveillance programs as data becomes available from operational agencies.

d. Correlate and evaluate all data to establish criteria for determining modes of possible degradation due to aging.

e. Suggest means for reducing or preventing such degradation.

f. Evaluate the effects of aging on motor performance.

g. Provide meaningful estimates of the service life of stage one motors.

3. Component and laboratory specimens were stored at simulated in-situ conditions and elevated temperatures to induce accelerated

aging. Laboratory specimens were selected to evaluate the performance of suspected significant characteristics of the materials under study.

The objectives of the component and laboratory aging effort are:

a. Evaluate the aging characteristics of components materials and interfaces affecting the performance of a complete motor.

b. Evaluate the effects of interaction (by migration of materials that interface in the motor assembly).

c. Correlate accelerated aging results with ambient aging results to allow extrapolation of aging trends when insufficient ambient aging data are available.

d. Provide aging data to predict motor and component storage life.

e. Evaluate test specimens and test techniques for improvement of overall surveillance quality.

Component and laboratory specimens prepared by Thiokol were tested by this laboratory. The results are shown in the figures and are included with the results from TWR-7300 report. The testing at this time does not cover the full range of component testing reported in TWR-7300.

4. The RIP Program is now completed as the specimens that were available for the program have essentially been expended. This document is the final report on the laboratory RIP testing.

STATISTICAL ANALYSIS

In order to evaluate aging trends, the regression model $Y = a + bX$ was employed to evaluate latest test results with respect to past data. Each regression was plotted to display individual test points with a least squares trend line through them. A tolerance band is given to indicate that at ninety percent confidence ninety percent of any data sampling can be expected to be within this interval. A dashed three sigma (three standard deviation) band parallels the least squares trend line. These bands are extrapolated twenty-four months beyond the age of the test materials the time they were last tested. Regression data at ages eight and upward represent MANCP laboratory testing while previous data were generated by Thiokol.

To obtain an overall view of which materials and test parameters have significant aging trends, a table of significance of regression slopes is given, see Table 1. Statements of significance are given at the five percent level. For those regression parameters having established failure criteria, a one-sided regression analysis was used.

TEST RESULTS

A. TENSILE ADHESION:

Tenshear (RS-1) tensile adhesion specimen data shows a statistically significant increase for both the 0° and 45° angle tensile testing (Figures 1 and 2). For both regressions the slope of the curve is gradual. The failure mode for the 0° testing was about 10% cohesive in the propellant and 90% adhesive propellant to liner; and for the 45° testing 100% adhesive propellant to liner.

Regression analysis for RS-4 shows a statistically significant gradual increase for maximum stress (Figure 3). The failure mode was determined by examination of the surface area with the aid of a microscope. The failure mode was about 60% cohesive in the adhesive material, 35% adhesive to the fiber, and 5% fiber failure.

B. TENSILE STRENGTH:

The regression for RS-12 shows a statistically significant gradual decrease Figure 5. The regressions for RS-5, RS-14, RS-19A and RS-21 do not show a statistically significant trend (Figures 4, 6, 7 & 8).

C. ELONGATION:

RS-5, RS-12 and RS-19A show no statistically significant trends (Figures 9 thru 11). RS-21 shows a statistically significant gradual increase (Figure 12).

CONCLUSIONS

The program objectives were to evaluate component and laboratory specimens stored at simulated in-situ conditions and elevated temperatures. The following conclusions are results derived from laboratory testing and analyses.

a. The component materials show little or no aging trends in laboratory testing. From this same testing and visual examination little or no aging is evident in the interfaces. From the analysis of laboratory testing, aging of the component material and interfaces would not affect motor performance at this time, however, evaluating whole motor performance requires engineering input and judgement.

b. Migration of material and interaction of material at the interfaces was not detected with the component materials tested.

c. There were not sufficient specimens available to run both the accelerated and ambient aging tests. Only ambient testing was done; therefore, a correlation could not be accomplished.

d. The regressions show little or no change in trends and are in good agreement with TWR-7300 data. Therefore, the service life of these components may be extended for at least two years beyond the last data point.

e. The test specimens were satisfactory except for specimens RS-19A and RS-21. Specimens RS-19A and RS-21 were very soft and it was very difficult to hold them in the jaws. This type specimen should be bonded to wood or metal end tabs and an appropriate jaw used.

RECOMMENDATIONS

Since this is the last time for testing on the RIP program it is recommended that component testing be started as soon as possible from motors in the dissection program. It is expected that the new dissection of motors will start in the first part of 1978. Data from this new dissection program should be correlated with the data previously obtained in the RIP program and other dissected motor data.

TABLE 1

Significance of Regression Slopes

		<u>Slope</u>	<u>Significance of Slope</u>	<u>t-Value</u>	<u>DF</u>
RS-1	Adhesion at 0 deg.	+	S*	5.14	32
RS-1	Adhesion at 45 deg.	+	S*	3.63	32
RS-4	Tensile adhesion (SM)	+	S*	2.03	55
RS-5	Tensile strength (SM)	+	NS	0.59	80
RS-12	Tensile strength (SM)	-	S	2.12	105
RS-14	Tensile strength (SM)	-	NS	0.01	36
RS-19A	Tensile strength (SM)	-	NS*	0.32	61
RS-21	Tensile strength (SM)	+	NS	1.51	103
RS-5	Elongation (er)	+	NS	0.92	59
RS-12	Elongation (er)	-	NS	1.23	88
RS-19A	Elongation (er)	+	NS	0.52	72
RS-21	Elongation (er)	+	S	3.37	87


* Single sided regression analysis employed when a failure criteria is used.

DF = Degrees of freedom

S = Significant

NS = Not significant

Y = (131.798767) + (0.141867) * X
 F = 26.460662 SIGNIFICANCE OF F = 0.141867
 R = 0.678602 SIGNIFICANCE OF R = SIGNIFICANT
 t = 5.143991 SIGNIFICANCE OF t = SIGNIFICANT
 N = 33 DEGREES OF FREEDOM = 31
 STORAGE COND = 70 DGRS F TEST COND = AMB TEMP/RH PN-4327




RS-1 (TENSHEAR) ADHESION AT 0 DEG ANGLE. FAILURE CRITERION. 10 PSI

Figure 1

F = 4.126564
 R = 0.266444
 C = 2.031394
 N = 56
 STORAGE COND = 70 DGRS F
 TEST COND = AMB TEMP/RH
 PN-4327

Y = (424.523925) + (1.010145) * X
 SIGNIFICANCE OF F = 164.090393
 SIGNIFICANCE OF R = 0.497267
 SIGNIFICANCE OF C = 159.616271
 DEGREES OF FREEDOM = 54



RS-4 TENSILE ADHESION (SM). FAILURE CRITERION: 25 PSI

Figure 3


Y = (1722.086914) + (0.380530) * X
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF t = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 79

STORAGE COND = 70 DGRS F
 TEST COND = AMB TEMP/RH

PN-4327

F = 0.343610
 R = 0.065808
 t = 0.586183
 N = 81


QY = 222.106140
 SB = 0.649166
 SF = 223.022949



R5-5 TENSILE STRENGTH (SM)

Figure 4

$Y = (25463.125000) + (-0.065479) * X$
 F = 0.000063
 R = -0.001338
 U = 0.007917
 N = 37
 STORAGE COND = 70 DGRS F
 TEST COND = AMB TEMP/RH
 DEGREES OF FREEDOM = 35
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF U = NOT SIGNIFICANT
 OY = 1762.807128
 SB = 8.270957
 SE = 1787.811035
 PN-4327




RS-14 TENSILE STRENGTH (SM)

Figure 6

F = 0.102127
 R = -0.041222
 C = 0.319573
 N = 62
 STORAGE COND = 70 DGRS F
 TEST COND = AMB TEMP/RH
 PN-4327


Y = (278.116699) + (-0.079552) * X
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF C = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 60

S_y = 66.229217
 S_b = 0.248932
 S_f = 66.722106



Y = (9476.445312) + (3.489807) * X
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF t = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 102
 TEST COND = AMB TEMP/RH
 STORAGE COND = 70 DGRS F
 PN-4327


F = 2.272075
 R = 0.147614
 t = 1.507340
 N = 104



RS-21 TENSILE STRENGTH (SM)

Figure 8

F = 0.045035
 R = 0.119835
 Q = 0.919250
 N = 60
 STORAGE COND = 70 DGRS F
 TEST COND = AMB TEMP/RH
 Y = (2.046727) + (0.001729) * X
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF Q = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 50
 C.V. = 0.505920
 S.W. = 0.001680
 ST = 0.500580
 PN-4327



RS-5 ELONGATION (ER). FAILURE CRITERION. 0.36 PERCENT STRAIN

Figure 9

Y = (1.103706) + (-0.000672) * X
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF t = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 87
 TEST COND = AMB TEMP/RH

F = 1.514221
 R = -0.130794
 t = 1.230536
 N = 89
 STORAGE COND = 70 DGRS F

Qy = 0.194615
 Sp = 0.000546
 Sf = 0.194049

PN-4327





Figure 10

$Y = (30.716766) + (0.021210) * X$
 SIGNIFICANCE OF F = NOT SIGNIFICANT
 SIGNIFICANCE OF R = NOT SIGNIFICANT
 SIGNIFICANCE OF U = NOT SIGNIFICANT
 DEGREES OF FREEDOM = 71
 STORAGE COND = 70 DGRS F TEST COND = AMB TEMP/RH
 QY = 14.473094
 SP = 0.040986
 SI = 14.547252




RS-19A ELONGATION (ER)

Figure 11

Y = (0.513655) + (0.000785) * X
 SIGNIFICANCE OF F = SIGNIFICANT
 SIGNIFICANCE OF R = SIGNIFICANT
 SIGNIFICANCE OF L = SIGNIFICANT
 DEGREES OF FREEDOM = 88
 STORAGE COND = 70 DGRS F TEST COND = AMB TEMP/RH
 PN-4327

F = 11.356685
 R = 0.341541
 L = 3.369968
 N = 88

QY = 0.084654
 Sg = 0.000233
 Sf = 0.080024



RS-21 ELONGATION (ER)

Figure 12

DISTRIBUTION

NR
COPIES

OOALC

MMWRME	1
MMWRMT	1
DDC (TISIR) Cameron Station, Alexandria, VA 22314	2
SAMSO, Norton AFB, CA 92409 MNNP	1
TWR Systems, Norton AFB, CA 92409 Attn: Mr. J. C. Metcalf, Bldg. 523/315	1
AFFRO, Thiokol Chemical Corporation Wasatch Division P. O. Box 524 Brigham City, UT 84302 (Cy to R. E. Keating)	2
AFRPL (MKPE) Edwards AFB, CA 93523	1
SAC (LGMB) Offutt AFB, NE 68113	1
U. S. Naval Ordnance Station, Indian Head, MD 20640 Attn: Dr. James H. Wiegand Fleet Support Dept., Propulsion System Development Division, Code FS7	1
CPIA, Johns Hopkins University Attn: Dr. P. L. Nichols Applied Physics Laboratory Johns Hopkins Road Laurel, MD 20810	1
Naval Plant Branch Representative Attn Mr. David W. Pratt P. O. Box 157, Bacchus Works Magna, UT 84044	1

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER MANCP -379 (77) ✓	2. GOVT ACCESSION NO. 9 Final	3. RECIPIENT'S CATALOG NUMBER RIP rept.
4. TITLE (and Subtitle) 6 Minuteman Stage I Motor Reliability Improvement Program Surveillance.		5. TYPE OF REPORT & PERIOD COVERED Test Results - Semi Annual
7. AUTHOR(s) 10 John A. Thompson		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS Propellant Lab Section Directorate of Maintenance OO-ALC Hill AFB, Utah 84406		8. CONTRACT OR GRANT NUMBER(s)
11. CONTROLLING OFFICE NAME AND ADDRESS Service Engineering Division Directorate of Materiel Management OO-ALC Hill AFB, Utah 84406		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS MMEMP Project M82934C-WNL1751
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE 11 Oct 77
		13. NUMBER OF PAGES 28 (12) 27p.
		15. SECURITY CLASS. (of this Report) Unclassified
16. DISTRIBUTION STATEMENT (of this Report) Approved for Public Release, Distribution Unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Solid Propellant Minuteman		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) This report contains data and test results from the fourth time testing of the Minuteman Stage I Reliability Program (RIP) Surveillance. Thiokol (see TWR-7300) had tested and reported on this program for eight years up through 30 June 1973. The responsibility was then turned over to the Propellant Laboratory (MANCP) at OO-ALC. In this report, Thiokol's data with the data from four years of testing in MANCP's laboratory were combined and regression analyses made by MANCP's		

407387

Ince

→ next page

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

statistical group.

The purpose of testing is to provide early warning if any serious degradation trends occur in the components being evaluated. The regressions show little or no change in trends from those previously established and are in good agreement with TWR-7300 data. Therefore, based on this analysis the service life of these components may be extended for at least two years beyond the last data point.

This constitutes final reporting on the laboratory testing program on component materials from the RIP Surveillance Program.

