

AD-A056 298

RHODE ISLAND UNIV KINGSTON DEPT OF OCEAN ENGINEERING
RAMAN SPECTRA OF POSSIBLE CORROSION PRODUCTS OF IRON.(U)
JUN 78 R J THIBEAU, C W BROWN

F/G 7/4

N00014-76-C-0889

UNCLASSIFIED

TR-3


NL

| OF |

AD
A056298



END
DATE
FILMED
8-78
DDC



AD A056298

AD No. _____
NC FILE COPY

LEVEL II

(12)

(14) TR-3

(6) RAMAN SPECTRA OF POSSIBLE CORROSION
PRODUCTS OF IRON.

TECHNICAL REPORT NUMBER 3

(9) Interim rept.

(15) CONTRACT NUMBER: N00014-76-C-0889

SUBMITTED TO:

DEPARTMENT OF THE NAVY
OFFICE OF NAVAL RESEARCH
METALLURGY PROGRAM - CODE 471

PREPARED BY:

(10) RICHARD J. / THIBEAU AND CHRIS W. / BROWN
DEPARTMENT OF CHEMISTRY

AND

ROBERT H. / HEIDERSBACH
DEPARTMENT OF OCEAN ENGINEERING

UNIVERSITY OF RHODE ISLAND
KINGSTON, RHODE ISLAND 02881

(12) 16p.

(11) JUNE 1978

DDC
RECEIVED
JUL 17 1978
E

DISTRIBUTION STATEMENT A
Approved for public release;
Distribution Unlimited

78 06 30 055

407892

CL

RAMAN SPECTRA OF POSSIBLE CORROSION
PRODUCTS OF IRON

TECHNICAL REPORT NUMBER 3

CONTRACT NUMBER: N00014-76-C-0889

SUBMITTED TO:

DEPARTMENT OF THE NAVY
OFFICE OF NAVAL RESEARCH
METALLURGY PROGRAM - CODE 471

PREPARED BY:

RICHARD J. THIBEAU AND CHRIS W. BROWN
DEPARTMENT OF CHEMISTRY

AND

ROBERT H. HEIDERSBACH
DEPARTMENT OF OCEAN ENGINEERING

UNIVERSITY OF RHODE ISLAND
KINGSTON, RHODE ISLAND 02881

JUNE 1978

ACCESSION for	
NTIS	White Section ☒
DOC	Buff Section ☐
UNANNOUNCED	☐
JUSTIFICATION.....	
BY.....	
DISTRIBUTION/AVAILABILITY CODES	
Dist.	AVAIL. and/or SPECIAL
A	

DISTRIBUTION STATEMENT A
Approved for public release; Distribution Unlimited

78 06 20 055

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical report no. 3	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Raman Spectra of Possible Corrosion Products of Iron		5. TYPE OF REPORT & PERIOD COVERED Interim Report, 1978
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) R. Heidersbach, C. Brown and R. Thibeau		8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0889
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Ocean Engineering University of Rhode Island Kingston, Rhode Island 02881		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, Virginia 22217		12. REPORT DATE June 1978
		13. NUMBER OF PAGES Thirteen (13)
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; its distribution is unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Iron, raman spectra, corrosion products, oxidation, ferric oxide, ferrous oxide, magnetite, ferric oxyhydroxide, surface films		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Raman spectra of FeO , Fe_3O_4 , $\alpha\text{-Fe}_2\text{O}_3$, $\alpha\text{-FeOOH}$, and $\gamma\text{-FeOOH}$, the common products of iron oxidation, have been measured. The spectra of FeO and Fe_3O_4 appear to be identical. Armco iron oxidized in air at 250°C was examined by Raman spectroscopy after varying periods of exposure and the surface film was found to contain Fe_3O_4 and $\alpha\text{-Fe}_2\text{O}_3$. α This manuscript has been submitted for publication in Applied Spectroscopy.		

INTRODUCTION

Laser Raman spectroscopy can be used for in situ analysis of corrosion product films on metal surfaces in gaseous and aqueous environments (1). The technique can provide quick and unambiguous identification of compounds present in surface films as thin as 50 Å (2). Since water and most gases give very weak Raman spectra, there is little spectral interference by the corrosive environment, and metal samples can be examined undisturbed while corrosion proceeds.

In order to identify compounds resulting from metal oxidation it is, of course, necessary to have spectra of the pure compounds available for reference. There can be considerable variation in the intensity of Raman scattering from one compound to another. For in situ Raman spectroscopy to be a useful technique in the study of thin corrosion films, the corrosion products must have reasonably strong spectra. Very few spectra of structural metal oxides have been published, so the first step in such a study must be to record spectra of the compounds of interest.

Iron is by far the most important metal for corrosion research. The thin oxide films it forms in most environments allow its use under nearly all conditions imaginable; however, the composition of such films is not well understood. There is experimental evidence evidence that the products of iron oxidation in air and in pure oxygen are FeO, Fe₃O₄, α-Fe₂O₃, γ-Fe₂O₃, α-FeOOH, and γ-FeOOH (3-7). The products of aqueous corrosion have been reported as Fe₃O₄, γ-Fe₂O₃, α-FeOOH, and γ-FeOOH (8-11). To use Raman spectroscopy to analyze surface films on iron, spectra of these compounds are required but only that of α-Fe₂O₃ is available in the literature (12). In this study, we have recorded Raman spectra of polycrystalline samples of the above named iron compounds and used them to identify corrosion product films to demonstrate the capability of this experimental technique in characterizing oxide films on iron surfaces.

EXPERIMENTAL

Several oxides of iron are readily available as reagent grade powders. Ferrous oxide, FeO , was purchased from Pfaltz and Bauer, Inc., Fe_3O_4 , from Amend Drug and Chemical Company, and $\alpha\text{-Fe}_2\text{O}_3$, from Alfa Products, Inc.

Crystalline $\alpha\text{-FeOOH}$ was precipitated by hydrolysis of 0.1 M ferric oxalate solution at the initial pH of 6.5 (adjusted by the addition of 1 M NaHCO_3 solution) (13,14). The solution was held at 100°C for 45 minutes and allowed to cool. The resulting precipitate was washed with distilled water, separated from the solution by centrifugation, and dried at room temperature.

Hydrolysis of a ferrous chloride solution formed $\gamma\text{-FeOOH}$. A solution of 20 g $\text{FeCl}_2 \cdot 4\text{H}_2\text{O}$ in 500 ml of water was added to 100 ml of 2 M hexamethylenetetramine solution, giving a blue-green $\text{Fe}(\text{OH})_2$ precipitate. To this was added 100 ml of 1 M NaNO_2 solution and the mixture was held at 60°C for three hours (15,16). After cooling, the rust-colored precipitate was removed by filtration, washed with water, and dried at 100°C . The identity and purity of the compounds synthesized were confirmed by their infrared absorption spectra (17).

Raman spectra were recorded with a Spex Industries Model 1401 double monochromator using a photon counting detection system. A Coherent Radiation Laboratories Model 52 argon ion laser was used as the excitation source. Both the 488.0 and 514.5 nm wavelength laser lines were used and the power at the sample was approximately 500 mW. In the sample compartment of the spectrometer, the ion compounds, in the form of KBr-iron oxide pellets, were held at a 20° angle from the vertical laser beam. The angle of incidence of the beam has a strong effect on the intensity of the Raman scattered light collected from a flat, opaque surface, so the angle was chosen to give the most intense spectra possible (2). To examine surface films on Armco iron samples, the same arrangement was used. Flat, rectangular iron samples were held at the same 20° angle from the incident beam.

Armco iron samples were mechanically polished and washed with distilled water before being placed in a preheated laboratory furnace. After high temperature exposure for a specified time, the samples were allowed to cool to room temperature and Raman spectra of their surfaces were recorded.

RESULTS AND DISCUSSION

In addition to identifying specific compounds, vibrational Raman spectra can be used to identify different crystalline forms of the same compound. This is a valuable asset in the study of iron oxidation because nearly all the oxides of iron can exist as two or more polymorphs. The spectra of the two most common forms of FeOOH are shown in Figure 1. Although their chemical compositions are the same, different crystal structures and, therefore, different bonding and symmetry cause very different Raman spectra. The strong bands at 397 ($\alpha\text{-FeOOH}$) or 252 cm^{-1} ($\gamma\text{-FeOOH}$) immediately identify the two oxyhydroxides; no other iron oxide has been found to have bands at these positions.

The Raman bands observed from iron oxides are listed in Table I. As shown in Figure 2, the spectra recorded from FeO and Fe_3O_4 samples are identical. The samples consist of two distinct compounds, as confirmed by their X-ray diffraction patterns, but the spectra are the same. It may be that the vibrations which cause Raman bands in Fe_3O_4 are due to Fe-O bonds which are nearly identical to those of FeO , but we believe a more likely explanation is that the FeO , which is unstable at temperatures below 570°C (18), is decomposed by the laser. The problem of sample decomposition is a common one when opaque samples are examined using relatively intense laser excitation. Visible light is strongly absorbed by black FeO , and heating due to the absorption of the excitation beam may transform it into Fe_3O_4 and Fe , the stable species at room temperature. Both Fe_3O_4 and FeO are black and present problems with decomposition in the laser beam. After a period of exposure, spectral intensity decreases and the surface of a pellet of either compound may be visibly changed. The

Decomposition due to the excitation beam seems to be less of a problem with the red-brown compounds, α - and γ -FeOOH and α -Fe₂O₃. Probably because decomposition is slower and absorption is less, the red-brown compounds give more intense spectra than Fe₃O₄. The difference in spectral intensity is demonstrated in Figure 3, which shows the spectrum of a mixture of 90% Fe₃O₄ and 10% α -Fe₂O₃ by weight. In spite of the concentration difference, the bands due to ferric oxide, α -Fe₂O₃, are as strong as those of Fe₃O₄. Because of the wide variation in spectral intensities among these compounds, it is not possible to determine exactly a single minimum concentration necessary to observe the spectrum of a minor component in a mixture. As little as 5% α -Fe₂O₃ can be identified in Fe₃O₄ but, in a mixture with Fe₃O₄ as the minor component, at least 30% Fe₃O₄ is required before it can be seen in α -Fe₂O₃. The intensities of the FeOOH spectra are midway between Fe₃O₄ and α -Fe₃O₄ so their minimum detectable concentrations are between 5 and 30%.

Due to the simplicity and relatively large spacing of bands in the Raman spectra of iron oxides, identification of compounds in a mixture is not difficult. Unlike the broad, overlapping bands of infrared spectra of these compounds (19), the relatively narrow Raman bands allow immediate identification of compounds in a mixture.

As an example of the ability of Raman spectroscopy to characterize corrosion product films on iron surfaces, we have examined polished Armco iron plates which were oxidized in air in a laboratory oven. Spectra resulting from oxidation at 250°C are shown in Figure 4. The Raman spectra identify the surface film as Fe₃O₄ and α -Fe₂O₃. The Fe₃O₄ bands at 616 and 663 cm⁻¹ can be seen in all three spectra, while at first only the strongest Fe₂O₃ bands can be seen. After 217 hours of exposure all seven bands of α -Fe₂O₃ are visible. Bands due to both compounds increase in intensity throughout the exposures, indicating that both the Fe₃O₄ and α -Fe₂O₃ layers are thickening.

Raman spectra of surface films as thin as 50 Å on a metal surface have been reported (2), but the minimum film thickness necessary for compound identification depends on the Raman scattering strength of the film. After oxidation under conditions similar to those reported here, Poling (19) found an oxide film thickness of approximately 500 Å for a 50 hour exposure at 250°C. An α -Fe₂O₃ film of 100-200 Å is probably necessary as a minimum before spectra useful for identification can be obtained with a single scan; for a thinner film the bands are not discernible above the noise. For other compounds, the minimum film thickness can vary greatly, depending on Raman scattering characteristics.

CONCLUSIONS

Raman spectra of the oxides of iron can be obtained with little difficulty using conventional instrumentation. The spectra can be used to identify the compounds and to specify which polymorphs of the compounds are present in thin films on iron surfaces. Spectra of thin surface films are identical to those of the pure compounds comprising the films.

There is considerable variation in intensity of Raman scattering from these oxides. The black compounds, FeO and Fe₃O₄, give weak spectra, whereas those that are lighter in color, α -Fe₂O₃, α -FeOOH, and γ -FeOOH, give stronger spectra. Decomposition of samples in the laser beam is a problem with FeO and Fe₃O₄ and, possibly, the use of techniques to minimize decomposition such as rotating the sample or using different wavelength excitation might give stronger spectra. These two oxides have been found to give identical spectra. While the reason for this is not known, it is proposed that the FeO is decomposing in the laser beam to give the more stable Fe₃O₄.

ACKNOWLEDGEMENT

The authors thank the Department of the Navy, Office of Naval Research, for the support of this research under Contract N00014-76-C-0889. We also thank Mr. J. Kolts of the Armco Steel Corporation, Middletown, Ohio, for supplying the Armco iron.

REFERENCES

1. E. S. Reid, R. P. Cooney, P. J. Hendra, and M. Fleischmann, J. Electroanal. Chem., 80, 405 (1977).
2. R. G. Greenler and T. L. Slager, Spectrochim. Acta., 29A, 193 (1973).
3. D. E. Daview, U. R. Evans, and J. N. Agar, Proc. Roy. Soc. (A), 225, 443 (1954).
4. M. H. Daview, M. T. Simnad, and C. E. Birchenall, J. Metals, 3, 889 (1951).
5. E. J. Caule, K. H. Buob, and M. Cohen, J. Electrochem. Soc., 108, 829 (1961).
6. P. B. Sewell and M. Cohen, J. Electrochem. Soc., 111, 508 (1964).
7. P. B. Sewell, C. D. Stockbridge, and M. Cohen, J. Electrochem. Soc., 108, 933 (1961).
8. M. Cohen, J. Electrochem. Soc., 121, 191C (1974).
9. J. L. Ord and D. J. DeSmet, J. Electrochem. Soc., 123, 1876 (1976).
10. N. Sato, T. Noda, and K. Kudo, Electrochim. Acta., 19, 471 (1974).
11. M. J. Graham and M. Cohen, Corrosion, 32, 432 (1976).
12. I. R. Beattie and T. R. Gilson, J. Chem. Soc. A, 1970, 980.
13. H. B. Weiser and W. O. Milligan, Chem. Rev., 25, 1 (1939).
14. K. J. Gallagher and D. N. Phillips, Trans. Faraday Soc., 64, 785 (1968).
15. T. Ishikawa and K. Inouye, Bull. Chem. Soc. Japan, 45, 2350 (1972).
16. O. Baudisch and W. H. Albrecht, J. Amer. Chem. Soc., 54, 943 (1932).
17. A. Z. Goldfarb, M. S. Thesis, University of Rhode Island (1978).
18. J. W. Mellor, A Comprehensive Treatise on Inorganic and Theoretical Chemistry, Longmans, Green, and Co., London, 1934, Vol. XIII, P. 706.
19. G. W. Poling, J. Electrochem. Soc., 116, 958 (1969).


TABLE I


Frequencies Of Iron Oxide Raman Bands


<u>Compound</u>		<u>Band Positions (cm⁻¹)</u>				
α -FeOOH	goethite	298	397	414	474	550
γ -FeOOH	lepidocrocite	252	380			
FeO	wüstite	616	663			
Fe ₃ O ₄	magnetite	616	663			
α -Fe ₂ O ₃	hematite	227	245	293	298	414
		501	612			


FIGURE CAPTIONS

- Figure 1 Raman spectra of α - and γ -FeOOH in KBr pellets. The apparent band marked with an asterisk is a grating ghost.
- Figure 2 Raman spectra of reagent grade FeO, Fe₃O₄, and α -Fe₂O₃ in KBr pellets. Features marked with an asterisk are due to grating ghosts.
- Figure 3 Raman spectrum of a mixture of 90% Fe₃O₄ and 10% α -Fe₂O₃ by weight in a KBr pellet.
- Figure 4 Raman spectra of the surface of Armco iron oxidized in air at 250°C for 50, 217, and 380 hours. Full scale on the 50 and 217 hour spectra is 1000 counts/sec., for the 380 hour spectrum it is 3000 counts/sec.









C
July 1977

SUPPLEMENTARY DISTRIBUTION LIST

Technical and Summary Reports

Dr. T. R. Beck
Electrochemical Technology Corporation
10035 31st Avenue, NE
Seattle, WA 98125

Professor I. M. Bernstein
Carnegie-Mellon University
Schenley Park
Pittsburgh, PA 15213

Professor H. K. Birnbaum
University of Illinois
Department of Metallurgy
Urbana, IL 61801

Dr. Otto Buck
Rockwell International
1049 Camino Dos Rios
P.O. Box 1085
Thousand Oaks, CA 91360

Dr. David L. Davidson
Southwest Research Institute
8500 Culebra Road
P.O. Drawer 28510
San Antonio, TX 78284

Dr. D. J. Duquette
Department of Metallurgical Engineering
Rensselaer Polytechnic Institute
Troy, NY 12181

Professor R. T. Foley
The American University
Department of Chemistry
Washington, DC 20016

Mr. G. A. Gehring
Ocean City Research Corporation
Tennessee Avenue & Beach Thorofare
Ocean City, NJ 08226

Dr. J. A. S. Green
Martin Marietta Corporation
1450 South Rolling Road
Baltimore, MD 21227

Professor R. H. Heidersbach
University of Rhode Island
Department of Ocean Engineering
Kingston, RI 02881

Professor H. Herman
State University of New York
Material Sciences Division
Stony Brook, NY 11794

Professor J. P. Hirth
Ohio State University
Metallurgical Engineering
Columbus, OH 43210

Dr. D. W. Hoepfner
University of Missouri
College of Engineering
Columbia, MO 65201

Dr. E. W. Johnson
Westinghouse Electric Corporation
Research and Development Center
1310 Beulah Road
Pittsburgh, PA 15235

Dr. F. Mansfield
Rockwell International Science Center
1049 Camino Dos Rios
P.O. Box 1085
Thousand Oaks, CA 91360

Professor A. E. Miller
University of Notre Dame
College of Engineering
Notre Dame, IN 46556

Dr. Jeff Perkins
Naval Postgraduate School
Monterey, CA 93940

Professor H. W. Pickering
Pennsylvania State University
Department of Material Sciences
University Park, PA 16802

C
July 1977

SUPPLEMENTARY DISTRIBUTION LIST
(Continued)

Dr. William R. Prindle
National Academy of Sciences
National Research Council
2101 Constitution Avenue
Washington, DC 20418

Professor R. W. Staehle
Ohio State University
Department of Metallurgical Engineering
Columbus, OH 43210

Dr. Barry C. Syrett
Stanford Research Institute
333 Ravenswood Avenue
Menlo Park, CA 94025

Dr. R. P. Wei
Lehigh University
Institute for Fracture and
Solid Mechanics
Bethlehem, PA 18015

Professor H. G. F. Wilsdorf
University of Virginia
Department of Materials Science
Charlottesville, VA 22903

BASIC DISTRIBUTION LIST

October 1976

Technical and Summary Reports		
<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>
Defense Documentation Center Cameron Station Alexandria, Virginia 22314	(12)	Naval Construction Battalion Civil Engineering Laboratory Port Hueneme, California 93043 Attn: Materials Division (1)
Office of Naval Research Department of the Navy Attn: Code 471 (1) Code 102 (1) Code 470 (1)		Naval Electronics Laboratory Center San Diego, California 92152 Attn: Electron Materials Sciences Division (1)
Commanding Officer Office of Naval Research Branch Office 495 Summer Street Boston, Massachusetts 02210	(1)	Naval Missile Center Materials Consultant Code 3312-1 Point Mugu, California 93041 (1)
Commanding Officer Office of Naval Research Branch Office 536 South Clark Street Chicago, Illinois 60605	(1)	Commanding Officer Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910 Attn: Library (1)
Office of Naval Research San Francisco Area Office 760 Market Street, Room 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	(1)	David W. Taylor Naval Ship R&D Center Materials Department Annapolis, Maryland 21402 (1)
Naval Research Laboratory Washington, D.C. 20390 Attn: Code 6000 (1) Code 6100 (1) Code 6300 (1) Code 6400 (1) Code 2627 (1)		Naval Undersea Center San Diego, California 92132 Attn: Library (1)
Naval Air Development Center Code 302 Warminster, Pennsylvania 18974 Attn: Mr. F. S. Williams	(1)	Naval Underwater System Center Newport, Rhode Island 02840 Attn: Library (1)
Naval Air Propulsion Test Center Trenton, New Jersey 08628 Attn: Library	(1)	Naval Weapons Center China Lake, California 93555 Attn: Library (1)
		Naval Postgraduate School Monterey, California 93940 Attn: Mechanical Engineering Dept. (1)
		Naval Air Systems Command Washington, D.C. 20360 Attn: Code 52031 (1) Code 52032 (1) Code 320 (1)

BASIC DISTRIBUTION LIST (Cont'd)

October 1976

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Naval Sea System Command Washington, D.C. 20362 Attn: Code 035	(1)	NASA Headquarters Washington, D.C. 20546 Attn: Code RRM	(1)
Naval Facilities Engineering Command Alexandria, Virginia 22331 Attn: Code 03	(1)	NASA Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135 Attn: Library	(1)
Scientific Advisor Commandant of the Marine Corps Washington, D.C. 20380 Attn: Code AX	(1)	National Bureau of Standards Washington, D.C. 20234 Attn: Metallurgy Division Inorganic Materials Division	(1) (1)
Naval Ship Engineering Center Department of the Navy CTR BG #2 3700 East-West Highway Prince Georges Plaza Hyattsville, Maryland 20782 Attn: Engineering Materials and Services Office, Code 6101	(1)	Defense Metals and Ceramics Information Center Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201	(1)
Army Research Office Box CM, Duke Station Durham, North Carolina 27706 Attn: Metallurgy & Ceramics Div.	(1)	Director Ordnance Research Laboratory P.O. Box 30 State College, Pennsylvania 16801	(1)
Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 Attn: Res. Programs Office (AMDMR-P)	(1)	Director Applied Physics Laboratory University of Washington 1013 Northeast Fortieth Street Seattle, Washington 98105	(1)
Air Force Office of Scientific Research Bldg. 410 Bolling Air Force Base Washington, D.C. 20332 Attn: Chemical Science Directorate Electronics and Solid State Sciences Directorate	(1) (1)	Metals and Ceramics Division Oak Ridge National Laboratory P.O. Box X Oak Ridge, Tennessee 37380	(1)
Air Force Materials Lab (LA) Wright-Patterson AFB Dayton, Ohio 45433	(1)	Los Alamos Scientific Laboratory P.O. Box 1663 Los Alamos, New Mexico 87544 Attn: Report Librarian	(1)
		Argonne National Laboratory Metallurgy Division P.O. Box 229 Lemont, Illinois 60439	(1)

BASIC DISTRIBUTION LIST (Cont'd)

October 1976

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Brookhaven National Laboratory Technical Information Division Upton, Long Island New York 11973 Attn: Research Library	(1)		
Library Building 50 Room 134 Lawrence Radiation Laboratory Berkeley, California	(1)		