


LEVEL

12
NW

DDC FILE COPY AD A062968

⑥ HIGH DURABILITY MISSILE DOMES

Raytheon Company
Research Division
Waltham, MA 02154



⑩

R. /Gentilman, E. /Maguire J. /Pappis

⑪

December 1978

This document has been approved
for public release and sale; its
distribution is unlimited.

⑨

Interim Technical Report for Period 1 October 1977-30 September 1978

12 N00014-76-C-9635

Prepared for

OFFICE OF NAVAL RESEARCH
Department of the Navy
Arlington, VA 22217

⑭ S-0421

Organization

No. of
Copies

Organization

No. of
Copies

Dr. L.M. Gillin
Aeronautical Research Laboratory
P.O. Box 4331
Fisherman's Bend
Melbourne, VIC 3001
AUSTRALIA

(1)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) HIGH DURABILITY MISSILE DOMES		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report 1 Oct 1977 - 30 Sept 1978
		6. PERFORMING ORG. REPORT NUMBER S-2439
7. AUTHOR(s) R. Gentilman E. Maguire J. Pappis		8. CONTRACT OR GRANT NUMBER(s) N00014-76-C-0635
9. PERFORMING ORGANIZATION NAME AND ADDRESS Raytheon Company Research Division Waltham, MA 02154		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research Department of the Navy Arlington, VA 22217		12. REPORT DATE December 1978
		13. NUMBER OF PAGES 20
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Spinel Magnesium Aluminum Oxide Hot Forging IR Domes		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Small hemispherical domes were fabricated from discs of polycrystalline (MgO·Al ₂ O ₃) and single crystal (MgO·3.5 Al ₂ O ₃) spinel by hot forging. Applied stresses of 70-105 MN/m ² at ~1775° C produced deformations of up to 1 cm in ~ 4 hrs. After polishing, the forged domes exhibited generally excellent quality. Some localized regions of optical scatter in the single crystal forgings have been identified as containing alumina precipitates. The present results demonstrate successfully the feasibility of fabricating full-size IR domes by hot forging. This will be the object of future work.		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

FOREWORD

This report was prepared by Raytheon Company, Research Division Waltham, Mass., under Contract No. N00014-76-C-0635, entitled, "High Durability Missile Domes." This work is administered under the direction of the Office of Naval Research, Material Sciences Division, Arlington, Virginia. Dr. Arthur M. Diness is the project scientist.

The work was carried out at Raytheon Research Division, Advanced Materials Department. Dr. J. Pappis is the department manager. Dr. Richard Gentilman is the principal investigator. Experimental work was performed by Mr. Edward Maguire.

This is the Interim Technical Report for Contract N00014-76-C-0635. covers the period 1 October 1977 to 30 September 1978. The report was given the Raytheon internal number S-2439.




TABLE OF CONTENTS

<u>Sec.</u>		<u>Page</u>
1.0	INTRODUCTION	1
2.0	EXPERIMENTAL PROCEDURE	5
3.0	RESULTS AND DISCUSSION	8
4.0	SUMMARY	18
	REFERENCES	20

LIST OF ILLUSTRATIONS

<u>No.</u>		<u>Page</u>
1	Schematic of Press Forging Technique	6
2	Furnace Assembly	7
3	Deformation Vs Time at Several Temperatures	11
4	Deformation Vs Time at Several Stress Levels	12
5	Press Forged Domes of Spinel	13
6	Press Forged Domes of Spinel	14
7	Press Forged Domes of Spinel	15
8	400X SEM Photos of Polished Dome	16
9	2000X SEM Photos of Polished Dome	17
10	Phase Diagram for the System $\text{MgO} \cdot \text{Al}_2\text{O}_3$	19

1.0 INTRODUCTION

Heat seeking missiles designed for air-to-air engagements face severe operational hazards that either reduce their effectiveness or raise the overall system's cost. The missiles are carried unprotected in exposed positions on aircraft. The infrared transparent dome can be broken during routine handling, pitted by sand and debris during takeoff and landing, or eroded by water droplet impact in flight through rain squalls. These problems are becoming increasingly severe as airspeeds are increased and as the introduction of terrain avoidance radar allows supersonic flight at very low altitudes.

Impact damage that leaves the dome intact but roughens the originally polished outer surface will degrade seeker performance in two ways. First, the minimum resolvable target size will be increased. In the current operational air-to-air missile, this factor is not critical. However, in the designs under consideration for the next generation missiles, seeker resolution will be severely affected by dome erosion. Second, roughening of the dome increases the amount of sunlight scattered into the seeker optics, raising the noise level in the infrared detection system and thus limiting the ability to detect targets. While these effects have not been well characterized, it is of considerable concern in current development of seekers designed for head-on approach.

Finally, immediately after missile launch, high tensile stresses are generated in the dome due to transient nonuniform aerodynamic heating of the dome. The severity of these stresses depends on the nature of the dome material (its thermal conductivity, heat capacity, and thermal expansion coefficient) and on the specific aerodynamic flight regime. For a next generation missile launch at Mach 1.5 with a powered flight lasting 2.0 sec, significant tensile stresses develop at the inside dome surface during the missile's acceleration, reaching a maximum of approximately 12,000 psi just after the

end of the powered flight. However, the fracture strength of magnesium fluoride is only 10,000 psi at 450° C, the approximate average temperature of the dome during flight at the time of the maximum thermally induced stress.

Early forms of infrared missiles operated at short infrared wavelengths where fused silica domes could be used. This material has a very high resistance to thermal shock but suffers from rain erosion. Magnesium fluoride domes have provided higher strength, adequate resistance to rain erosion (for current applications), transparency in the 3 to 5 μm atmospheric window, and the ability to withstand the thermal shock of current missiles in subsonic launch. However, magnesium fluoride domes are predicted to fail in either supersonic launch of current missiles or subsonic launch of the next generation designs and also to be adversely affected by rain during supersonic captive carry.

The need for a new, more durable missile dome is clear. New missile designs are being compromised by the lack of a dome material with the required strength, hardness, and thermal conductivity that can be produced at an acceptable cost. However, there are several highly durable crystalline oxide materials (Table 1) that are transparent at ultraviolet, visible, and infrared wavelengths out to 5 μm that will serve the optical needs of future seeker designs. Specifically, spinel has become a leading candidate material for future air-to-air missile domes.

The particular dome shape of interest during this investigation is a hemispherical shell approximately 70 mm diameter and 3 mm thick. One approach proposed for the fabrication of such a shape from refractory oxides is to press forge flat plates at high temperatures. Work reported in the literature by Heuer, Hwang and Mitchell^{1,2} and by Becher³ showed that single crystals of spinel could be deformed plastically in compression. The experiments reported here were attempted to see if this plastic deformation

TABLE 1

INFRARED TRANSMITTING MATERIALS RANKED ACCORDING TO
THERMAL SHOCK RESISTANCE AT 450° C

<u>Material</u>	<u>Absorption Between 4-5 μ in 2 mm T = 450° C</u>	<u>Resistance to Thermal Stress (σ-K/αE) RT</u>	<u>R. T. Fracture Strength (psi)</u>	<u>Knoop Hardness</u>	<u>Crystal Structure</u>
Si	40%	296	60	9,000	1150
Ge	60%	88	25	13,500	690
Al ₂ O ₃	8%	47	21	50,000	2200
MgAl ₂ O ₄	3%	22	11	28,000	1700
MgO	<1%	29	8	23,000	900
Y ₂ O ₃	<1%	25	7	28,000	800
ZnS	Transparent	26	6	15,000	356
CdS	Transparent	19	6	8,000	130
ZnSe	Transparent	23	5.5	7,500	150
MgF ₂	<1%	19.4	3.2	22,000	576

process could be utilized where the stress applied was not simple compression. Also, it was desired to determine the feasibility of using polycrystalline as well as single-crystal spinel.

Spinel of excellent optical quality is available in both single-crystal and polycrystalline form. The selections made were single-crystal boules of alumina-rich spinel, generally 1 MgO to 3.5 Al_2O_3 , grown by a Verneuil technique* and plates of polycrystalline spinel of 1:2 :: MgO: Al_2O_3 stoichiometry produced by a fusion casting process.⁴ The alumina-rich material has a lower yield stress than the stoichiometric 1:1 composition. As a preliminary step toward full-sized IR domes, experiments were size limited by the diameter of available single crystals of spinel, slightly over 3.2 cm. But the validity of the concept could be demonstrated by forging domes of smaller diameter but comparable curvature.

The present hot forging work was begun in 1977, with studies of simple beam deformation of alumina-rich spinel in three-point bending. During 1978, the technical feasibility of forging flat discs into hemispherical shells was demonstrated successfully.

* Adolf Meller Co., Providence, RI.

2.0 EXPERIMENTAL PROCEDURE

Figure 1 shows schematically the press forging technique employed to form hemispherical dome shapes from flat plates of spinel. The plates, 2.62 - 2.86 cm diameter and 0.19 cm thick, were set into a hemispherical cavity in a graphite die and loaded at their center points by a matching hemispherical graphite punch. The radius of curvature was approximately 1.2 cm. Spacers of Grafoil 0.04 cm thick, between the spinel plate and the graphite die faces reduced interactions to a minimum.

Loaded in this manner, with the edge simply supported and the force applied at the center, the maximum stress developed is determined by⁵

$$\sigma = \frac{3(1+\mu)P}{2\pi t^2} \left(\frac{1}{\mu+1} + \log_e \frac{r}{r_o} - \frac{1-\mu}{1+\mu} \frac{r_o^2}{4r^2} \right)$$

where σ = maximum stress

μ = Poisson's ratio

P = central load

t = thickness of plate

r = radius of plate

r_o = radius of central loaded area

As the plate deforms, the radius of the central loaded area increases. This was taken into account and the load increased when necessary to maintain any given stress level. The loads that were applied produced maximum stresses in the plates of 525-1050 kg/cm² (7.5-15 ksi).

In Figure 2 the furnace assembly is shown with the graphite die in place. The load was applied to the top punch by weights suspended below the furnace. This loading was static with incremental changes to maintain a given stress level as deformation proceeded. The extent of deformation




Figure 1. Schematic Diagram in Cross-Section of Hot Forging a Spinel Disk into a Hemispherical Dome Shape




Figure 2. Furnace Assembly.

was monitored on a dial indicator. A graphite heating element provided temperatures of 1750° -1800° C in an atmosphere of helium.

3.0 RESULTS AND DISCUSSION

In the course of the experiments reported here, twenty-six (26) runs were made with single-crystal spinel and seven (7) runs with polycrystalline plates. A summary of these forging runs is presented in Table 2. Data were selected from these to illustrate the effects of temperature and pressure on deformation rates. In Figure 3, deformation is seen to take place more rapidly as temperature is increased. These spinel plates were subjected to a stress of 875 kg/cm^2 (12.5 ksi). Some deformation is shown at zero time because the load was applied throughout the heatup portion of the cycle while time was measured from the point at which a given temperature level was reached. Data for polycrystalline plates indicates lower rates under comparable temperature and pressure conditions. Pressure was the variable in Figure 4. As expected, the deformation was accelerated by increasing pressure. Good results were obtained at temperatures of 1750° to 1780° C and pressures of $700\text{-}1050 \text{ kg/cm}^2$ (10-15 ksi).

A number of the domes produced are shown in Figures 5, 6, and 7. There was no difficulty with gross defects such as cracks or tears. Surfaces did suffer some degradation as a result of contact with graphite. However, the surfaces were easily restored by polishing and as the polished domes in these photos demonstrate, the optical quality was excellent.

Some domes appeared to have cloudy areas that were not removed by surface polishing. Under the optical microscope, these areas were seen to contain numerous small crystals. Figure 8 shows SEM photos at 400X magnification of a clear area and a cloudy area of typical domes. The latter area is examined more closely in Figure 9 at 2000X. An x-ray microprobe was used to analyze the spots marked by the white dots in the lower photo. The

TABLE 2

SUMMARY OF SPINEL HOT FORGING RUNS

Run No.	Sample		Temp. ° C	Max. Stress	Time hr	Deformation cm	Loss %	Comments
	Diam. cm	Thickness cm		Kg/cm ²				
20	2.78	0.19	1750	1120	5.5	0.32	6.2	cracked
21	2.78	0.09	1775	1050	8.0	0.68	---	cracked
22	2.78	0.25	1850	700	6.0	1.40	---	broken
23	2.78	0.19	1800	1050	2.5	1.20	---	broken
24	2.78	0.19	1800	700	----	----	---	broken
25	2.78	0.19	1775	1050	8.0	0.38	12.3	OK
26	2.78	0.20	1750	1260	12.0	0.71	23.8	broken
27	2.78	0.20	1750	980	12.0	0.46	34.3	OK
28	2.78	0.21	1780	1050	4.5	1.09	---	broken
29	2.78	0.19	1760	1050	6.0	0.42	9.2	OK
30	2.78	0.19	1750	1050	12.5	0.41	22.5	OK
31	2.78	0.20	1800	1050	8.0	0.45	44.2	OK
32	2.78	0.19	1780	840	7.5	0.53	31.9	OK
33	1.90	0.19	1775	1050	4.0	0.50	11.3	OK
34	1.90	0.20	1785	1050	7.0	0.50	5.0	OK
35	2.60	0.19	1775	1050	11.0	0.59	3.5	OK
36	2.60	0.18	1770	1050	31.5	0.72	2.4	OK
37	2.60	0.19	1760	1050	6.0	0.94	3.8	OK
38	2.60	0.19	1765	1050	5.8	0.90	2.0	OK
39	2.60	0.19	1775	1050	6.2	0.91	1.3	OK
42	2.85	0.20	----	1050	----	----	---	broken, polyxtal
43	2.85	0.20	1780	875	8.0	1.09	4.7	OK, poly- xtal
44	2.60	0.20	1770	875	6.0	0.77	2.5	OK
45	2.60	0.21	1800	875	2.5	0.84	6.1	OK
46	2.60	0.20	1780	875	5.0	0.93	5.7	OK
47	2.60	0.19	1780	875	3.5	0.90	9.1	OK

TABLE 2 (Cont'd)

Run No.	Sample		Temp ° C	Max. Stress Kg/cm ²	Time hr	Deformation cm	Loss %	Comments
	Diam. cm	Thickness cm						
48	2.53	0.20	1790	875	8.0	0.82	4.8	polyxtal some cracks
49	2.53	0.20	1720	875	---	----	---	polyxtal broken
50	2.53	0.20	1775	700	8.5	0.79	3.8	polyxtal OK
51	2.53	0.18	1750	700	8.5	0.70	4.3	polyxtal OK
52	2.53	0.19	1775	700	11.5	0.72	3.8	polyxtal OK
53	2.60	0.20	1785	1050	5.5	0.37	---	OK
54	2.60	0.19	1785	1050	3.8	0.89	2.9	OK




Figure 3. Deformation Vs Time at Several Temperatures.




Figure 4. Deformation Vs Time at Several Stress Levels.




Figure 5. Press Forged Domes of Spinel.



Figure 6. Press Forged Domes of Spinel.

PBN-78-765






Figure 7. Press Forged Domes of Spinel.



400 X SEM CLEAR AREA




400 X SEM CLOUDY AREA

Figure 3. 400X SEM Photos of Polished Dome.



2000 X SEM



2000 X SEM WITH MARKERS

Figure 9. 2000X SEM Photos of Polished Dome.

three individual grains were identified as Al_2O_3 while the background matrix was spinel. It appears that some precipitation/recrystallization of alumina had occurred. This behavior was seen in domes press forged from plates of single-crystal spinel but not polycrystalline ones. A check of the phase equilibria of the system (Figure 10) provides an explanation for the difference in behavior. In the case of 3.5 to 1 single-crystal material, the forging temperatures of $1750^\circ - 1800^\circ \text{C}$ placed the piece in a region where two phases, spinel and alumina, can exist. Under the same conditions, 2 to 1 polycrystalline material is within the single-phase spinel area.

4.0 SUMMARY

The concept of press forging hemispherical dome shapes from flat plates of magnesium aluminate spinel has been demonstrated. Small domes, 2.54 cm in diameter and 0.76 cm high, were fabricated from both single-crystal and polycrystalline material. Excellent optical quality was maintained. The only potential problem was presented by precipitation/recrystallization of Al_2O_3 in single-crystal 3.5:1 spinel. This work is being pursued toward the fabrication of larger-sized domes.




Figure 10. Phase Diagram for the System MgO-Al₂O₃.

REFERENCES

1. L. Hwang, A. H. Heuer and T. E. Mitchell, Deformation of Ceramic Materials, New York:Plenum Press 1975, pp 257-270.
2. T. E. Mitchell, L. Hwang and A. H. Heuer, "Deformation in Spinel," J. Materials Science 11, 264-272 (1976).
3. P. F. Becher, "Press-Forged Al_2O_3 -Rich Spinel Crystals for IR Applications," Am. Ceram. Soc. Bull. 56 (11) 1015-1017 (1977).
4. R. L. Gentilman, E. A. Maguire and J. Pappis, "Transparent Fusion-Cast Polycrystalline Spinel," (to be published).
5. F. B. Seely and J. O. Smith, Advanced Mechanics of Materials, 2nd ed., New York: John Wiley and Sons 1952, p. 227.

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Defense Documentation Center Cameron Station Alexandria, Virginia 22314	(12)	Naval Construction Battalion Civil Engineering Laboratory Port Hueneme, California 93043 Attn: Materials Division	(1)
Office of Naval Research Department of the Navy Attn: Code 471 Code 102 Code 470	(1) (1) (1)	Naval Electronics Laboratory Center San Diego, California 92152 Attn: Electron Materials Sciences Division	(1)
Commanding Officer Office of Naval Research Branch Office 495 Summer Street Boston, Massachusetts 02210	(1)	Naval Missile Center Materials Consultant Code 3312-1 Point Mugu, California 93041	(1)
Commanding Officer Office of Naval Research Branch Office 536 South Clark Street Chicago, Illinois 60605	(1)	Commanding Officer Naval Surface Weapons Center White Oak Laboratory Silver Spring, Maryland 20910 Attn: Library	(1)
Office of Naval Research San Francisco Area Office 760 Market Street, Room 447 San Francisco, California 94102 Attn: Dr. P. A. Miller	(1)	David W. Taylor Naval Ship R&D Center Materials Department Annapolis, Maryland 21402	(1)
Naval Research Laboratory Washington, D.C. 20390 Attn: Code 6000 Code 6100 Code 6300 Code 6400 Code 2627	(1) (1) (1) (1) (1)	Naval Undersea Center San Diego, California 92132 Attn: Library	(1)
Naval Air Development Center Code 302 Warminster, Pennsylvania 18974 Attn: Mr. F. S. Williams	(1)	Naval Underwater System Center Newport, Rhode Island 02840 Attn: Library	(1)
Naval Air Propulsion Test Center Trenton, New Jersey 08628 Attn: Library	(1)	Naval Weapons Center China Lake, California 93555 Attn: Library	(1)
		Naval Postgraduate School Monterey, California 93940 Attn: Mechanical Engineering Dept.	(1)
		Naval Air Systems Command Washington, D.C. 20360 Attn: Code 52031 Code 52032 Code 320	(1) (1) (1)

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Naval Sea System Command Washington, D.C. 20362 Attn: Code 035	(1)	NASA Headquarters Washington, D.C. 20546 Attn: Code RRM	(1)
Naval Facilities Engineering Command Alexandria, Virginia 22331 Attn: Code C3	(1)	NASA Lewis Research Center 21000 Brookpark Road Cleveland, Ohio 44135 Attn: Library	(1)
Scientific Advisor Commandant of the Marine Corps Washington, D.C. 20380 Attn: Code AX	(1)	National Bureau of Standards Washington, D.C. 20234 Attn: Metallurgy Division	(1)
Naval Ship Engineering Center Department of the Navy CFR BG #2 3700 East-West Highway Prince Georges Plaza Hyattsville, Maryland 20782 Attn: Engineering Materials and Services Office, Code 6101	(1)	Inorganic Materials Division Defense Metals and Ceramics Information Center Battelle Memorial Institute 505 King Avenue Columbus, Ohio 43201	(1)
Army Research Office Box CM, Duke Station Durham, North Carolina 27706 Attn: Metallurgy & Ceramics Div.	(1)	Director Ordinance Research Laboratory P.O. Box 30 State College, Pennsylvania 16801	(1)
Army Materials and Mechanics Research Center Watertown, Massachusetts 02172 Attn: Res. Programs Office (AMXMR-P)	(1)	Director Applied Physics Laboratory University of Washington 1013 Northeast Fortieth Street Seattle, Washington 98105	(1)
Air Force Office of Scientific Research Bldg. 410 Bolling Air Force Base Washington, D.C. 20332 Attn: Chemical Science Directorate Electronics and Solid State Sciences Directorate	(1)	Metals and Ceramics Division Oak Ridge National Laboratory P.O. Box X Oak Ridge, Tennessee 37380	(1)
Air Force Materials Lab (LA) Wright-Patterson AFB Dayton, Ohio 45433	(1)	Los Alamos Scientific Laboratory P.O. Box 1663 Los Alamos, New Mexico 87544 Attn: Report Librarian	(1)
		Argonne National Laboratory Metallurgy Division P.O. Box 229 Lemont, Illinois 60439	(1)

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Brookhaven National Laboratory Technical Information Division Upton, Long Island New York 11973 Attn: Research Library	(1)		
Library Building 50 Room 134 Lawrence Radiation Laboratory Berkeley, California	(1)		

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Dr. W.F. Adler Effects Technology Inc. 5383 Hollister Avenue P.O. Box 30400 Santa Barbara, CA 92105	(1)	Professor A.H. Heuer Case Western Reserve University University Circle Cleveland, OH 44106	(1)
Dr. G. Bansal Battelle 505 King Avenue Columbus, OH 43201	(1)	Dr. R. Hoagland Battelle 505 King Avenue Columbus, OH 43201	(1)
Dr. R. Bratton Westinghouse Research Lab. Pittsburgh, PA 15235	(1)	Dr. R. Jaffee Electric Power Research Institute Palo Alto, CA	(1)
Dr. A.G. Evans Rockwell International P.O. Box 1085 1049 Camino Dos Rios Thousand Oaks, CA 91360	(1)	Dr. P. Jorgensen Stanford Research Institute Foulter Laboratory Menlo Park, CA 94025	(1)
Mr. E. Fisher Ford Motor Co. Dearborn, MI	(1)	Dr. R.N. Katz Army Materials and Mechanics Research Center Watertown, MA 02171	(1)
Dr. P. Cielisse University of Rhode Island Kingston, RI 02881	(1)	Dr. H. Kirchner Ceramic Finishing Company P.O. Box 498 State College, PA 16801	(1)
Dr. M.E. Guldén International Harvester Company Solar Division 2200 Pacific Highway San Diego, CA 92138	(1)	Dr. B. Koepke Honeywell, Inc. Corporate Research Center 500 Washington Avenue, South Hopkins, MN 55343	(1)
Dr. D.P.H. Hasselman Montana Energy and MHD Research and Development Institute P.O. Box 3809 Butte, Montana 59701	(1)	Mr. Frank Koubek Naval Surface Weapons Center White Oak Laboratory Silver Spring, MD 20910	(1)
Mr. G. Hayes Naval Weapons Center China Lake, CA 93555	(1)	E. Krafft Carborundum Co. Niagara Falls, NY	(1)

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Dr. F.F. Lange Rockwell International P.O. Box 1085 1049 Camino Dos Rios Thousand Oaks, CA 91360	(1)	Dr. J. Ritter University of Massachusetts Department of Mechanical Engineering Amherst, MA 01002	(1)
Dr. J. Lankford Southwest Research Institute 8500 Culebra Road San Antonio, TX 78284	(1)	Professor R. Roy Pennsylvania State University Materials Research Laboratory University Park, PA 16802	(1)
Library Norton Company Industrial Ceramics Division Worcester, MA 01606	(1)	Dr. R. Ruh AFML Wright-Patterson AFB Dayton, OH 45433	(1)
State University of New York College of Ceramics at Alfred University Attn: Library Alfred, NY 14802	(1)	Mr. J. Schudlies AIResearch Phoenix, AZ	(1)
Dr. L. Hench University of Florida Ceramics Division Gainesville, FL 32601	(1)	Professor G. Sines University of California, Los Angeles Los Angeles, CA 90024	(1)
Dr. N. MacMillan Materials Research Laboratory Pennsylvania State University College Park, PA 16802	(1)	Dr. N. Tallan AFML Wright-Patterson AFB Dayton, OH 45433	(1)
Mr. F. Markerian Naval Weapons Center China Lake, CA 93555	(1)	Dr. T. Vasilos AVCO Corporation Research and Advanced Development Division 201 Lowell Street Wilmington, MA 01887	(1)
Dr. Perry A. Miles Raytheon Company Research Division 28 Seyon Street Waltham, MA 02154	(1)	Mr. J.D. Walton Engineering Experiment Station Georgia Institute of Technology Atlanta, GA 30332	(1)
Mr. R. Rice Naval Research Laboratory Code 6360 Washington, D.C. 20375	(1)	Dr. S.M. Widerhorn Inorganic Materials Division National Bureau of Standards Washington, DC 20234	(1)

<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>
Dr. S.A. Bortz IITRI 10 W. 35th Street Chicago, IL 60616	(1)	Major W. Simmons Air Force Office of Scientific Research Building 410 Bolling Air Force Base Washington, DC 20332	(1)
Mr. G. Schmitt Air Force Materials Laboratory Wright-Patterson AFB Dayton, OH 45433	(1)	Dr. P. Becher Naval Research Laboratory Code 6362 Washington, DC 20375	(1)
Dr. D.A. Shockey Stanford Research Institute Poulter Laboratory Menlo Park, CA 94025	(1)	Mr. L.B. Weckesser Applied Physics Laboratory Johns Hopkins Road Laurel, MD 20810	(1)
Dr. W.G.D. Frederick Air Force Materials Laboratory Wright-Patterson AFB Dayton, OH 45433	(1)	Mr. D. Richardson Air Research Manufacturing Company 4023 36th Street P.O. Box 5217 Phoenix, AZ 85010	(1)
Dr. P. Land Air Force Materials Laboratory Wright-Patterson AFB Dayton, OH 45433	(1)	Dr. H.E. Bennett Naval Weapons Center Code 3818 China Lake, CA 93555	(1)
Mr. K. Letson Redstone Arsenal Huntsville, AL 35809	(1)	Mr. G. Denman Air Force Materials Laboratory Code LPJ Wright-Patterson AFB Dayton, OH 45433	(1)
Dr. S. Freiman Naval Research Laboratory Code 6363 Washington, DC 20375	(1)	Dr. D. Godfrey Admiralty Materials Laboratory Pelle, Dorset BH16 6JU UNITED KINGDOM	(1)
Director Materials Sciences Defense Advanced Research Projects Agency 1400 Wilson Boulevard Arlington, VA 22209	(1)	Dr. N. Corney Ministry of Defense The Adelphi John Adam Street London WC2N 6BB UNITED KINGDOM	(1)
Dr. James Pappis Raytheon Company Research Division 28 Seyon Street Waltham, MA 02154	(1)		