

AD-A075 953


WATKINS-JOHNSON CO SCOTTS VALLEY CA
HIGH CONTRAST CRT.(U)
AUG 79 G A HOLMQUIST

F/G 9/1


UNCLASSIFIED

DAAB07-77-C-2639
DELET-TR-77-2639-4 NL

1 OF 1
AD
A075953



END
DATE
FILMED
11-79
DDC





12
B.S.

LEVEL III

Research and Development Technical Report

DELET - TR - 77 - 2639 - 4

HIGH CONTRAST CRT

Dr. Glenn A. Holmquist
Watkins-Johnson Company
440 Mt. Hermon Rd.
Scotts Valley, California 95066

August, 1979

Fourth Interim Report for 1 June - 30 September 1978

DISTRIBUTION STATEMENT

Approved for public release; distribution unlimited

D D C
RECEIVED
OCT 31 1979
RECEIVED
A

Prepared for:

ELECTRONICS TECHNOLOGY AND DEVICES LABORATORY

ERADCOM

US ARMY ELECTRONICS RESEARCH AND DEVELOPMENT COMMAND
FORT MONMOUTH, NEW JERSEY 07703

79 10 31 006

AD A 075953

DDC FILE COPY

NOTICES

Disclaimers

The citation of trade names and names of manufacturers in this report is not to be construed as official Government indorsement or approval of commercial products or services referenced herein.

Disposition

Destroy this report when it is no longer needed. Do not return it to the originator.

**HIGH CONTRAST CRT
FOURTH INTERIM REPORT
1 JUNE THROUGH 30 SEPTEMBER 1978**

**Contract No. DAAB 07-77-C-2639
File No. 672705A 1L162705AH94 D1 08**

**Prepared By:
Glenn A. Holmquist**

**For
U.S. Army Electronics Technology & Devices Laboratory
Electronics Research and Development Command
Fort Monmouth, New Jersey 07703**

**Watkins-Johnson Company
3333 Hillview Avenue
Palo Alto, California 94304**

TABLE OF CONTENTS

<u>Section</u>	<u>Description</u>	<u>Page</u>
1.0	CONFERENCES	1
2.0	INTRODUCTION	1
2.1	Background	1
2.2	Statement of the Problem	1
2.3	Technical Guidelines	2
2.3.1	Scope	2
2.3.2	Applicable Documents	2
2.3.3	Requirements	2
3.0	TECHNICAL APPROACH (TUBE DESIGN)	5
4.0	THE THIN FILM PHOSPHOR SCREEN	5
5.0	THIN FILM PHOSPHOR SCREEN FABRICATION AND MEASUREMENT	6
6.0	PARALLEL TUBE PROGRAM	8
7.0	CONCLUSIONS	9
8.0	PROGRAM FOR NEXT INTERIM PERIOD	9

Accession For	
NTIS GR&I	<input checked="" type="checkbox"/>
DDC TAB	<input type="checkbox"/>
Unannounced Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or special
A	

LIST OF ILLUSTRATIONS
AND TABLES

<u>Figure No.</u>	<u>Description</u>	<u>Page</u>
1	Schematic of High Contrast CRT	11
2	Schematic of High Contrast Two-Color Screen	12
3	Demountable Brightness Data	13
4	CRT Test Data	14
5	CRT Test Data	15
6	CRT #2 Data	16

<u>Table No.</u>	<u>Description</u>	
1	Faceplate Data #18-21	7
2	Brightness Data CRT #1, 2, and 3	10

1.0

CONFERENCES

5 July 1978 at Watkins-Johnson Company in Scotts Valley, California. This is a report on a conference held at Watkins-Johnson Company to review the progress on this program.

Personnel Present

Mr. Norman H. Lehrer

Mr. John L. Turner

Lockheed Research Laboratory

Dr. Grant Maple

Dr. Robert Buchanan

ERADCOM

Dr. Elliott Schlam

The progress of the publication of interim reports was reviewed and time commitments were made. The exerciser was operational and a demonstration was held. Dr. Schlam indicated that some modifications be made to increase the versatility of the exerciser. These modifications are listed in Section 6.0.

2.0

INTRODUCTION

2.1

Background

Development of the high contrast two-color tube, the objective of this program, encompasses the fabrication of the screens and their assembly into the completed tube. The screens are being made by the Lockheed Palo Alto Research Laboratory under sub-contract from Watkins-Johnson Company. Watkins-Johnson will assemble the completed screens into finished tubes.

The preliminary work to determine the optimum parameters for phosphor deposition on the screens has been completed. In this interim four screens are fabricated and characterized. The work on sixteen additional screens is begun. Data from three complete CRT's are determined and analyzed.

2.2

Statement of the Problem

The basic objective of this program is the ability to display information generated by various electronic systems with suitable high resolution in two colors with its legibility maintained under ambient illumination ranging from 10^4 to 10^{-3} fc.

Existing color tubes cannot satisfy the above requirement. Such tubes which employ aperture masks are severely limited in brightness and resolution by the aperture mask. Their brightness is

2.2

Continued

limited because the aperture mask transmission is only 15-20%, therefore wasting 80-85% of the current. The wide spacing between holes degrades the resolution below that required in most military systems. Furthermore, the color purity of such tubes is influenced by their position with respect to the earth's magnetic field and it is therefore impractical to incorporate them in airborne systems.

The use of color penetration phosphors overcomes some of the problems of mask type tubes. The color purity is no longer affected by the tube orientation and the resolution is higher than that which can be achieved with a mask type tube. Conventional color penetration tubes which employ powdered phosphors can not be used for daylight (high brightness) viewing because of their high reflectivity and low brightness particularly in red, which produces a washed-out low contrast display. The reflectivity of the phosphor is high because of its particulate nature. The brightness of the red is low because of most of the light generated by the red phosphor is scattered by the green phosphor before it reaches the faceplate of the CRT.

2.3

Technical Guidelines

2.3.1

Scope

These technical guidelines outline a program leading to the design and fabrication of a very high contrast CRT. The screen phosphors of this CRT are to be of the transparent film type and backed by a black light absorption coating. Therefore, a prime objective of this program is the incorporation of a phosphor-screen technology that will result in transparent film phosphors deposited on a substrate-faceplate which is an integral part of the CRT envelope. It is furthermore intended that the phosphor screen incorporate a two layer, penetration type multi-color structure. The phosphored faceplate is to be attached to available tube envelopes in a manner consistent with economical CRT manufacturing methods.

2.3.2

Applicable Documents

MIL-E-1 Manual

MIL-STD-1311A

2.3.3

Requirements

2.3.3.1

General

This program shall be directed toward the development of a high contrast CRT based on the use of high efficiency transparent phosphors. This capability is intended to be accomplished by the deposition of transparent phosphor layers on a suitable substrate that will be bonded to a standard CRT envelope in an economical manner. This program is intended to accomplish this by an extension of avail-

2.3.3.1

Continued

able phosphor techniques to CRT sizes now used in military equipment. Areas of investigation and performance will include, but not necessarily be limited to, the features outlined in the following paragraphs.

2.3.3.2

Detailed Program Objectives

2.3.3.2.1

Phosphor Screen Characteristics

- 1) Luminescent Material - The luminescent material shall be one that has a demonstrated high cathodoluminescent efficiency in transparent form. Since it is intended that bi-layer films be used, the demonstrated efficiency should be with various colors, particularly red and green. It is not intended that phosphor development per se, be part of this program.
- 2) Phosphor Persistence - The transparent phosphors used in the CRT screen should have persistence in the range of JEDEC designations "medium short" to "medium". Trade-offs of persistence with other phosphor properties and characteristics should be determined.
- 3) Physical Characteristics - It is intended that a bi-layer type of phosphor screen shall be used in the CRT. In that event, each phosphor layer shall be transparent and may or may not be separated by a transparent dielectric layer.
- 4) Light Absorbing Layer - A requirement of this program is that the phosphor screens be backed, on the electron gun side, with a uniform light absorbing coating that can be effectively penetrated by the electron beam. Specular reflection from this coating, on the phosphor side, should be no greater than 1%. Diffuse reflectance shall be no greater than 0.25%. This coating shall not cause any substantial reduction in electron-current or electron-energy into the phosphor screen.
- 5) Phosphor Electrode - The phosphor electrode shall be a thin aluminum film, behind the black coating of 2.3.3.2.1-4, and electrically insulated from all other tube electrodes by means sufficient to withstand the operating levels within the tube without electrical breakdown or appreciable leakage current.

2.3.3.2.1 Continued

- 6) Phosphor Screen Substrate - The phosphor screen substrate shall be capable of withstanding all necessary fabrication techniques of the transparent film screen without change of shape or curvature that would degrade the end result of a completed CRT.

2.3.3.2.2 CRT Characteristics

The goal of this program is a CRT that is physically and electrically replaceable with a currently existing CRT. To this effect, the envelope, deflection angle and means, focusing means, and biasing should duplicate a Dumont KC3055 (formally KC2626) CRT used in the AN/A PR-39. It is accepted that an improved electron gun may be used with this phosphor screen. To this effect, it is desirable that the final CRT be electrically interchangeable with the KC3055, as closely as possible, so that power supplies driving the KC3055 need not be replaced.

2.3.3.2.3 CRT Contrast

It is necessary that the CRT be legible in direct sunlight under its normal mode of operation, without the use of added contrast enhancement devices. Specific quantitative criteria to satisfy this requirement should be developed so that optical instrumentation tests may be used for its verification.

2.3.3.2.4 Faceplate Characteristics

The faceplate size should be directed to the above CRT. The faceplates shall be bonded to the tube envelope by conventional means or use of graded seals. Glass-to-metal seals are undesirable. This program is not intended to support special envelope development.

2.3.3.2.5 Phosphor Voltage Range

The CRT should operate within conventional limits of anode potential. In no case should this potential exceed 20 kV. In the penetration screen configuration, anode potential shifts to achieve color changes should be minimized.

2.3.3.2.6 Resolution

A line width, taken at the half amplitude point of the spot distribution, of 0.012 inches or better is desirable. The line width should not exceed 0.016 inches.

2.3.3.2.7 Display Luminance

The CRT is to operate under ambient illumination from 10^4 to 10^{-3} fc. The CRT luminance is to be uniformly adjustable to provide satisfactory legibility under these conditions.

2.3.3.2.8 Writing Speed

A minimum writing rate of 50,000 in/sec for a single trace for all color fields is desirable.

2.3.3.2.9 Phosphor Maintenance

The transparent phosphors shall have high maintenance under normal modes of operation consistent with paragraph 2.3.3.2.3, and burn sensitivity tests shall be conducted on the screens incorporated into the CRT.

2.3.3.2.10 Reliability Consideration

Since the CRT's developed under this program are intended for tactical and airborne applications, adequate consideration must be given throughout the development program to the reliability of this tube for such environments. As an objective, the CRT should be able to pass the physical tests for CRT's specified in MIL-E-1.

2.3.3.2.11 Environmental Testing

Environmental testing of the CRT's will not be part of this program.

2.3.3.2.12 Program Emphasis

The program emphasizes the investigative areas outlined in paragraphs 2.3.3.2.1-1, 2.3.3.2.1-4, 2.3.3.2.2, 2.3.3.2.3, and 2.3.3.2.7.

3.0 TECHNICAL APPROACH (TUBE DESIGN)

Figure 1 is a schematic of the proposed high contrast multicolor CRT. The physical dimensions are identical with that of the existing CRT (Dumont KC3055). The high contrast tube will employ a Laminarflo Gun. This gun offers advantages over the crossover gun and is described in Reference 1. The phosphor screen incorporates a black backed multilayer bicolor transparent phosphor film deposited on a substrate which is bonded to the CRT funnel. The details of this screen are described further in this report. In operation, the color of the display can be controlled by selection of the beam potential. At about 10 kV, the display will be red, at 15-20 kV the display will be green. With the exception of the focus and anode potentials, the operating voltage will be the same as the existing CRT.

4.0 THE THIN FILM PHOSPHOR SCREEN

Figure 2 is a schematic representation of the two-color high contrast film to be employed in this program. As shown in the illustration, the two-color phosphor is supported on a transparent substrate which forms the faceplate of the CRT.

4.0

Continued

The green-luminescent film is immediately adjacent to the substrate. The red-luminescent film resides on top of the green one. The opaque layer is deposited on the other face of the red phosphor film. Finally, a thin conducting aluminum layer covers the opaque layer.

In operation, the red phosphor layer absorbs most or all of the electron beam energy at potentials below 10 kV. At high potentials, for example, at 20 kV, most of the electron beam is absorbed in the green phosphor. At intermediate potentials, some electrons are absorbed by both layers, depending upon the exact value of the potential. (A mathematical description of the optimum film thickness is given in the proposal). Therefore, at low beam energies, only the red phosphor is excited and the display appears red. At high beam energies, the green-luminescent material is more excited and the display appears green. Various mixtures of the two colors are obtained at intermediate values of the potential. Note that since the luminous efficiency of the red is much lower than that of the green, it is important that the red be placed closest to the electron gun to prevent color contamination of the red by the green. If the green film were closest to the gun, it would not be possible to excite the red without getting some color contamination from the green phosphor.

The operation of this screen in high ambient lighting conditions was discussed in our proposal, P-4583.

5.0

THIN FILM PHOSPHOR SCREEN FABRICATION AND MEASUREMENT

Four faceplates were completed early in the interim. 1720 glass was the substrate material. Table 1 lists the thickness of the thin films. In each case the lanthanum oxysulfide films were heat treated for 60 minutes at 870°C. This treatment is necessary to promote atomic mass transport with subsequent ordering to increase the cathodoluminescent efficiency of the film. Optical data was determined and is listed in Table 1.

The cathodoluminescent data was determined with Lockheeds demountable system and is displayed on the graph in Figure 3. Brightness was measured at the beam current of 5 μ A at a series of anode potentials.

The cathodoluminescent efficiency of each film varies as indicated by the spread of the data. This is to be expected as the time-temperature treatment for crystal ordering, hence efficiency improvement, is not optimized. The La₂O₂S film is sputter deposited and in "crystalline disarray".

Faceplate Number	THICKNESS Angstroms			Al	REFLECTANCE Percent	
	La ₂ O ₃ Terbium Activated	La ₂ O ₃ Europium Activated			Specular	Diffuse
18	8800	4100		600	6.24	1.37
19	8800	4000		1000	6.66	--
20	8800	4000		500	7.35	0.87
21	8800	4000		500	6.74	1.91

TABLE 1 - Faceplate Data #18-21

5.0

Continued

The heat treatment for complete ordering is an hour at 1050°C; however, the glass substrate would melt at this temperature. The compromise treatment is one hour at 870°C. The "crystalline disarray" varies in extent so the incomplete ordering at 870°C varies in extent with a resulting variation in film efficiencies as observed in Figure 3.

In September, the end of this interim, the subcontract on phase II became effective, the deposition of phosphor films on sixteen faceplates (1720 glass) began. The duplication of the characteristics of film #18 was pursued.

6.0

PARALLEL TUBE PROGRAM

The exerciser is an electronic system that can drive these high contrast tubes in TV modes of operation. The exerciser was completed and demonstrated full screen raster operation at 10, 15 and 18 kV screen potential. These accelerating potentials correspond to red, yellow and green color displays respectively. Dr. Schlam requested that the following modifications be made:

- 1) Disable the vertical scan deflection leaving a horizontal line display.
- 2) Provide variable intensity control.
- 3) Allow tube interchangeability.

The vertical scan was easily disabled; moreover, a dc power supply was to be installed to allow deflection of the horizontal line to any desired location on the screen. The variable intensity control was provided by relocating the appropriate potentiometer to the front panel. The last request is accommodated by the use of connectors.

The basic problem with the faceplate-funnel frit seal is the thermal expansion compatibility of the glasses used. Typical CRT glass is soft glass. The 1720 glass faceplate is hard glass. A graded transition flame seal is one answer. This answer is not conducive to a high yield for a production tube. A hard glass (3320) funnel was the next logical answer. Watkins-Johnson has standard 7720 (nonex) hard glass headers that are compatible with 3320 glass. The evolution of the optimum choice of glass components was complete; 1720 glass faceplates, 3320 funnels and 7720 headers.

In the meantime, the third CRT was completed. An Einzel lens laminar flow gun was used. The Einzel gun electrical requirements are most compatible with those of the monochrome tube that is to be replaced. The brightness was measured for different grid drives

6.0

Continued

for each of four anode potentials. All data was determined at a writing speed of 5000 inches per second and a 60 hertz refresh rate as described in the second triannual report (ECOM-77-2639-2).

The data for the first three CRTs is listed in Table 2 and displayed in Figures 4 to 6. The brightness is approximated as a liner function of grid drive within the scatter of points for the data for these tubes. The slope of the linear approximation will indicate the efficiency of the phosphor in the ideal case. These devices are not perfect; they are not ideal. They are in fact new, first of their kind of devices.

The gradual increase in the brightness per volt grid drive data for increasing anode potential is shown in the family of curves for CRT #2 (Figure 6). Figures 4 and 5 compare data for the three tubes at anode potentials of 10, 15, and 18 kV.

The brightness per volt drive ratio at 10 kV is greatest for CRT #3, smaller for #2 and least for #1. However, at anode potentials of 15 kV and greater this ratio is greatest for #2, smaller for #3 and least for #1. This change in order is possibly due to either a difference in the individual electron gun operating characteristics or a difference in the efficiency of the phosphor.

7.0

CONCLUSIONS

Limited conclusions can be drawn from this initial data: this approach produces a viable cathode ray tube; the maximum light output achievable (peak line brightness) is 26 fc at 10 kV anode potential (red) and 345 fc at 18 kV anode potential (green).

8.0

PROGRAM FOR NEXT INTERIM PERIOD

Complete faceplate fabrication next interim.

Fabricate CRTs with the four faceplates.

Anode Potential (kV)	Grid Drive			Peak Line Brightness		
	(S/N 1)	(S/N 2)	(S/N 3)	(S/N 1)	(S/N 2)	(S/N 3)
10	10	10	10	1.5	1.6	6
10	20	20	20	3.7	5.3	8.5
10	30	30	30	6.4	8.8	10
10	46.5	42.1	40	7.9	11.8	17
10	--	--	50	--	--	26
15	10	10	10	4.3	10.7	9 (14kV)
15	20	20	20	20	47.5	31 (14kV)
15	30	30	30	43	88.5	59 (14kV)
15	45	45	40	60	125.0	68 (14kV)
15	--	--	50	--	--	105 (14kV)
18	10	10	10	7.7	31.4	17
18	20	20	20	37	153	81
18	30	30	30	73	260	130
18	49.5	45.2	40	95	345	--
18	--	--	--	--	--	--
20	10	10	--	26	40	--
20	20	20	--	62	202	--
20	30	30	--	94	340	--
20	45.5	45.6	--	--	445	--

Bipotential gun S/N 1 and 2
 Einzel gun S/N 3

TABLE 2 - Brightness data for CRT's #1, 2, and 3




Figure 1. Schematic of High Contrast CRT




Figure 2. Schematic of High Contrast Two-Color Screen




Figure 3 - Demountable Brightness Data.




Figure 4 - CRT Test Data




Figure 5 - CRT Test Data.




Figure 6 - CRT #2 Data.

**ELECTRONICS TECHNOLOGY AND DEVICES LABORATORY
DISTRIBUTION LIST**

101	Defense Documentation Center Attn: DDC-TCA Cameron Station (Bldg. 5) Alexandria, VA 22314	012	Alexandria, VA 22314	212	Command, Control & Communications Div. Development Center Marine Corps Development & Educ. Comd. Quantico, VA 22134	001	Quantico, VA 22134
103	Code R123, Tech Library DCA Defense Comm. Engrg. Ctr. 1800 Wiehle Avenue Reston, VA 22090	001	Reston, VA 22090	301	Rome Air Development Center Attn: Documents Library (TILD) Griffiss AFB, NY 13441	001	Griffiss AFB, NY 13441
104	Defense Communications Agency Technical Library Center Code 205 (P.A. Tolovi) Washington, D.C. 20305	001	Washington, D.C. 20305	307	Air Force Geophysics Lab/SULL Attn: S-29 Hanscom AFB, MA 01831	001	Hanscom AFB, MA 01831
200	Office of Naval Research Code 427 Arlington, VA 22217	001	Arlington, VA 22217	314	Hq. Air Force Systems Command Attn: DLCA Andrews AFB Washington, D.C. 20331	001	Washington, D.C. 20331
203	GIDEP Engineering & Support Dept. TE Section P.O. Box 398 Norco, CA 91760	001	Norco, CA 91760	403	CDR, MIRCOM Redstone Scientific Info. Center Attn: Chief, Document Section Redstone Arsenal, AL 35809	001	Redstone Arsenal, AL 35809
205	Director Naval Research Laboratory Attn: Code 2627 Washington, D.C. 20375	001	Washington, D.C. 20375	405	Commander U.S. Army Aeromedical Research Lab Attn: Library Fort Rucker, AL 36362	001	Fort Rucker, AL 36362
206	Commander Naval Ocean Systems Center Attn: Library San Diego, CA 92152	001	San Diego, CA 92152	406	Commandant U.S. Army Aviation Center Attn: ATZQ-D-MA Fort Rucker, AL 36362	001	Fort Rucker, AL 36362
207	CDR, Naval Surface Weapons Center White Oak Laboratory Attn: Library Code WX-21 Silver Spring, MD 20919	001	Silver Spring, MD 20919	407	Director, Ballistic Missile Defense Advanced Technology Center Attn: ATC-R, P.O. Box 1500 Huntsville, AL 35807	001	Huntsville, AL 35807
210	Commandant, Marine Corps Hq. U.S. Marine Corps Attn: Code LMC Washington, D.C. 20380	002	Washington, D.C. 20380	417	Commander U.S. Army Intelligence Center & School Attn: ATSI-CD-MD Fort Huachuca, AZ 85613	002	Fort Huachuca, AZ 85613
211	Hq. U.S. Marine Corps Attn: Code INTS Washington, D.C. 20380	001	Washington, D.C. 20380	418	Commander Hq. Fort Huachuca Attn: Technical Reference Div. Fort Huachuca, AZ 85613	001	Fort Huachuca, AZ 85613

419	Commander U.S. Army Electronic Proving Ground Attn: STEEP-MT 002 Fort Huachuca, AZ 85613	507	CDR, AVRADCOM Attn: DRSAV-E P.O. Box 209 001 St. Louis, MO 63166
437	Deputy for Science & Technology Office, Assist. Sec. Army (R&D) 001 Washington, D.C. 20310	511	Commander ARRADCOM Attn: DRDAR-LCA-PD 002 Dover, NJ 07801
438	HQDA (DAMA-ARZ-D/DR. F. D. Verderame) 001 Washington, D.C. 20310	512	Commander ARRADCOM Attn: DRDAR-LCN-S 001 Dover, NJ 07801
455	Commandant U.S. Army Signal School Attn: ATZ-HET-L 001 Fort Gordon, GA 30905	513	Commander ARRADCOM Attn: DRDAR-TSS-#59 001 Dover, NJ 07801
470	Director of Combat Developments U.S. Army Armor Center Attn: ATZK-CD-MS 002 Fort Knox, KY 40121	515	Project Manager, REMBASS Attn: DRCPM-RBS 002 Fort Monmouth, NJ 07703
475	CDR. Harry Diamond Laboratories Attn: Library 2800 Powder Mill Road 001 Adelphi, MD 20783	517	Commander U.S. Army Satellite Communications Agcy. Attn: DRCPM-SC-3 002 Fort Monmouth, NJ 07703
477	Director U.S. Army Ballistic Research Labs Attn: DRXBR-LB 001 Aberdeen Proving Ground, MD 21005	518	TRI-TAC Office Attn: TT-SE 001 Fort Monmouth, NJ 07703
481	Harry Diamond Laboratories, DA Attn: DELHD-RCB (Dr. J. Nemarich) 2800 Powder Mill Road 001 Adelphi, MD 20783	519	CDR, U.S. Army Avionics Lab AVRADCOM Attn: DAVAA-D 001 Fort Monmouth, NJ 07703
482	Director U.S. Army Materiel Systems Analysis ACTV Attn: DRXSY-T 001 Aberdeen Proving Ground, MD 21005	520	Project Manager, Firefinder Attn: DRCPM-FF 001 Fort Monmouth, NJ 07703
483	Director U.S. Army Materiel Systems Analysis ACTV Attn: DRXSY-MP 001 Aberdeen Proving Ground, MD 21005	521	Commander Project Manager, Sotas DRCPM-STA 001 Fort Monmouth, NJ 07703
499	CDR, TARCOM Attn: DRDTA-RH 001 Warren, MI 48090	522	Commander Aviation Flight Test Activity Attn: DELAF-CO 001 Lakehurst NAEC, NJ 08733

531 CDR, U.S. Army Research Office
Attn: DRXRO-IP
P.O. Box 1221
001 Research Triangle Park, NC 27709

532 CDR, U.S. Army Research Office
Attn: DRXRO-PH
(Dr. R. J. Lontz)
P.O. Box 12211
001 Research Triangle Park, NC 27709

533 Commandant
U.S. Army INST. for
Military Assistance
Attn: ATSU-CTD-MO
001 Fort Bragg, NC 28307

537 CDR, U.S. Army Tropic Test Center
Attn: STETC-MO-A (Tech Library)
Drawer 942
001 Fort Clayton, Canal Zone 09827

543 Division Chief
Meteorology Division
Counterfire Department
002 Fort Sill, OK 73503

554 Commandant
U.S. Army Air Defense School
Attn: ATSA-CD-MC
001 Fort Bliss, TX 79916

555 Commander
U.S. Army Nuclear & Chemical Agency
7500 Backlick Rd., Bldg. 2073
001 Springfield, VA 22150

556 HQ. TCATA
Technical Information Center
Attn: Mrs. Ruth Reynolds
001 Fort Hood, TX 76544

563 Commander, DARCOM
Attn: DRCDE
5001 Eisenhower Ave.
001 Alexandria, VA 22333

564 CDR. U.S. Army Signals Warfare Lab
Attn: DELSW-OS
Vint Hill Farms Station
001 Warrenton, VA 22186

568 Commander
U.S. Army Mobility EQP RES & DEV CMD
Attn: DRDME-R
001 Fort Belvoir, VA 22060

569 Commander
U.S. Army Engineer Topographic Labs
Attn: ETL-TD-EA
001 Fort Belvoir, VA 22060

572 Commander
U.S. Army Logistics Center
Attn: ATCL-MC
002 Fort Lee, VA 22801

579 CDR, PM Concept Analysis Centers
Attn: DRCPM-CAC
Arlington Hall Station
001 Arlington, VA 22212

602 CDR, Night Vision & Electro-Optics Lab
ERADCOM
Attn: DELNV-D
001 Fort Belvoir, VA 22060

603 CDR, Atmospheric Sciences Lab
ERADCOM
Attn: DELAS-SY-S
001 White Sands Missile Range, NM 88002

604 Chief
OFC of Missile Electronic Warfare
Electronic Warfare Lab, ERADCOM
001 White Sands Missile Range, NM 88002

606 Chief
Intel Materiel Dev. & Support Office
Electronic Warfare Lab, ERADCOM
001 Fort Meade, MD 20755

607 CDR, Harry Diamond Laboratories
Attn: DELHD-CO
2800 Powder Mill Road
001 Adelphi, MD 20783

608 Commander
ARRADCOM
DRDAR-TSB-S
001 Aberdeen Proving Ground, MD 21005

609 CDR, ERADCOM
Attn: DRDEL-CG; -CD; -CS (in turn)
2800 Powder Mill Road
001 Adelphi, MD 20783

612 CDR, ERADCOM
Attn: DRDEL-CT
2800 Powder Mill Road
001 Adelphi, MD 20783

613	CDR, ERADCOM Attn: DRDEL-PAO 2800 Powder Mill Road 001 Adelphi, MD 20783	700	CINDAS Purdue Industrial Research Park 2595 Yeager Road 001 W. Lafayette, IN 47096
617	CDR, ERADCOM Attn: DRDEL-AQ 2800 Powder Mill Road 001 Adelphi, MD 20783	701	MIT - Lincoln Laboratory Attn: Library (RM A-082) P.O. Box 73 002 Lexington, MA 02173
619	CDR, ERADCOM Attn: DRDEL-PA; -ILS; -ED (in turn) 2800 Powder Mill Road 001 Adelphi, MD 20783	703	NASA Scientific & Tech Info Facility Baltimore/Washington Intl. Airport 001 P.O. Box 8757, MD 240
662	HQS, Harry Diamond Laboratories Attn: DELHD-TD (Dr. W.W. Carter) 2800 Powder Mill Road 001 Adelphi, MD 20783	704	National Bureau of Standards Bldg. 225, Rm. A-331 Attn: Mr. Leedy 001 Washington, D.C. 20231
680	Commander U.S. Army Electronics R&D Command 000 Fort Monmouth, NJ 07703	705	Advisory Group on Electron Devices 201 Varick Street, 9th Floor 002 New York, NY 10014
	1 DRDEL-SA 1 DELEW-D 3 DELCS-D 1 DELET-D 1 DELET-DD 2 DELET-DT 5 DELET-BD 1 DELSD-D 1 DELSD-AS 1 DELSD-L (Tech Lab) 2 DELSD-L-S (STINFO) 25 Originating Office	706	Advisory Group on Electron Devices Attn: Secy, Working Group D (Lasers) 201 Varick Street 002 New York, NY 10014
681	Commander U.S. Army Communications R&D Command 000 Fort Monmouth, NJ 07703	707	TACTEC Batelle Memorial Institute 505 King Avenue 001 Columbus, OH 43201
	1 DRDCO-COM-RO 1 USMC-LNO 1 ATFE-LO-EC	709	Plastics Tech. Eval. Center Picatinny Arsenal, Bldg. 176 Attn: Mr. A. M. Anzalone 001 Dover, NJ 07801
682	Commander U.S. Army Communications & Electronics Materiel Readiness Command 000 Fort Monmouth, NJ 07703	711	Metals and Ceramics Inf. Center Batelle 505 King Avenue 001 Columbus, OH 43201
	1 DRSEL-PL-ST 1 DRSEL-MA-MP 2 DRSEL-PA		Dr. Robert Trimmier Sperry Flight Systems Mail Station 109B 21111 N. 19th Avenue Phoenix, AZ 85027
			Mr. Robert Perutz LORAL Electronics Systems 999 Central Park Avenue 001 Yonkers, NY 10704