

LEVEL IV

ARO 14998.3-P
12
P.S.

ADA081575

STUDY OF THE PHASE TRANSITION IN NIOBIUM DIOXIDE

FINAL REPORT

P. M. Raccah

FEBRUARY 1, 1980

DEPARTMENT OF THE ARMY

DTIC
ELECTE
FEB 27 1980
S D C

DAAG2977 G0084

UNIVERSITY OF ILLINOIS AT CHICAGO CIRCLE
CHICAGO, IL 60680

DDC FILE COPY

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED

80 2 25 038

PII Redacted

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER DAAG2977 G0084	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) STUDY OF THE PHASE TRANSITION IN NIOBIUM DIOXIDE.	5. TYPE OF REPORT & PERIOD COVERED Final Report 4/1/77 - 9/30/79	6. PERFORMING ORG. REPORT NUMBER 3-46-32-59-3-68
7. AUTHOR(s) P. M. Raccah	8. CONTRACT OR GRANT NUMBER(s) DAAG2977 G0084	
9. PERFORMING ORGANIZATION NAME AND ADDRESS University of Illinois at Chicago Circle Department of Physics, Box 4348 Chicago, IL 60680	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 11/1 1 2 88	
11. CONTROLLING OFFICE NAME AND ADDRESS U.S. Army Research Office Post Office Box 12211 Research Triangle Park, NC 27709	12. REPORT DATE February 1, 1980	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) GOV. ING. 17-12-5784	13. NUMBER OF PAGES 12	15. SECURITY CLASS. (of this report)
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES 18 APR 1980 19 147 18.3-1		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Mode Softening Structural Phase Transition IT IS SHOWN		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) We show that it is indeed possible to use underdamped hard modes of high symmetry to determine quantitatively the temperature dependence of the order parameter in a structural phase transition (SPT). The example chosen is that of the SPT in NbO_2 .		

ABSTRACT

We show that it is indeed possible to use underdamped hard modes of high symmetry to determine quantitatively the temperature dependence of the order parameter in a structural phase transition (SPT). The example chosen is that of the SPT in NbO_2 .

Accession For	
NTIS GRA&I	☒
DDC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Available for special
A	

Light scattering methods have proven to be very effective in the study of phase transitions⁽¹⁾. Soft mode Raman spectroscopy in particular has been extensively used because it allows a direct determination of the temperature dependence of the order parameter $\eta(T)$ which is the physical quantity of interest. This method should be quite general as any structural phase transition (SPT) can be described in terms of one or more unstable "soft" optical phonons. Experimentalists, however, have found that it had obvious limitations, namely that the "soft" mode cannot always be identified, can be overdamped or can be masked by the splitting of some other mode. Recently, Petzelt and Dvorak⁽²⁾ have proposed that for non-degenerate modes

$$\Delta\omega(T) = \omega_h(T) - \omega_h(T_c) \propto \eta^2(T)$$

where $\omega_h(T)$ is the frequency of a "hard" Raman mode at various temperatures and T_c is the critical temperature. This elegant result, derived from a simple group-theoretical analysis, suggests that the much simpler hard mode Raman spectroscopy (HMS) can be used when soft mode Raman spectroscopy (SMS) is impossible.

We report here the first quantitative verification of the above relationship. We show that in at least one SPT, that exhibited by NbO_2 , it holds true quite far away from T_c despite the fact that Petzelt and Dvorak⁽²⁾ had limited their treatment to lowest coupling terms and consequently to T near T_c . Moreover, we confirm the interesting results of Pynn and

Axe⁽³⁾ who had determined in the case of NbO_2 that the critical exponent β , away from T_c , had the value 0.19 ± 0.02 which is significantly different from the usual value of 0.5.

NbO_2 exhibits a semiconductor to metallic transition at $T_c = 809^\circ\text{C}$ which has been widely investigated⁽⁴⁾. Extensive structural studies^(3,4,5) have been carried out and, because Mukamel⁽⁶⁾ had pointed out that the SPT could be described by a four-component order parameter, Pynn and Axe⁽³⁾ have carried out a special study of the critical exponent β . It showed that over a range of temperatures from near T_c down to 400°C below T_c the value of β is 0.19 ± 0.02 as stated above. However, within 7°C of T_c it is 0.4 ± 0.05 exhibiting a quite unusual crossover. The earlier work of Shapiro, et al⁽⁵⁾ had already indicated that the "soft" mode could be overdamped. Our preliminary Raman study apparently confirmed this (Fig.1) since the only soft mode manifestation which we observed was an increase in the Rayleigh scattering which augments with temperature as one approaches T_c . This difficulty motivated us in testing the suggestion made by Petzelt and Dvorak⁽²⁾.

The oriented single crystals used in these studies were grown by a method described elsewhere⁽⁷⁾. A special furnace was built which allowed for data collection in the back-scattering configuration while the sample was heated under a protective gettered atmosphere (10^{-3} torrs Ar/H_2 in conjunction with tantalum sample holders). The temperature stability of the furnace was of the order of $\pm 1^\circ\text{C}$ while the reported sample

4

temperature, which was measured by a chromel-alumel thermocouple and compared to a calibrated optical pyrometer at high temperatures, is estimated to be accurate to within only about $\pm 5^\circ\text{C}$. The $5145 \text{ \AA}$ line of an Ar^+ ion laser was used to excite the spectra with the laser power at the sample kept below 100mW in order to minimize laser heating. The scattered light was analyzed by a one-meter Jarrell-Ash double monochromator and detected by an RCA (31034-04) cooled photomultiplier. Phase sensitive detection was used to separate the signal due to the Raman scattered light from the signal due to the light emitted by the furnace.

The modes of A_{1g} symmetry were judged to be particularly desirable for this study as they have the same symmetry as the soft mode and are more likely to be strongly coupled to it⁽⁸⁾. The Raman spectrum of NbO_2 exhibits two strong A_{1g} modes at 168 and 347 cm^{-1} at room temperature. While similar results have been obtained for both of these modes as a function of temperature, only the results for the mode at 168 cm^{-1} will be presented here.

Part of the Raman spectrum of NbO_2 , including the first A_{1g} mode, is shown in Fig. 1 for three different temperatures. The broadening of the central line, evident in Fig. 1, was shown to be reversible and, therefore, probably corresponds to the contribution of the overdamped soft phonon rather than to an extraneous cause. This broadening of the central peak made the precise determination of the frequencies of the hard

A_{1g} photon particularly difficult, since it also became increasingly broadened with temperature. The complex line-shape was analyzed by obtaining a least squares fit to an equation for the intensity of the form

$$I(\omega) = S\gamma^2\omega(\bar{n}(\omega)+1) / (\omega^2+\gamma^2) + A/[(\omega-\omega_h(T))^2 + \beta^2].$$

S and γ are the mode strength and damping constant respectively for the Debye function representing the soft mode contribution while A is the mode strength and β the damping constant for the Lorentzian representing the hard mode (A_{1g}) contribution. $\bar{n}(\omega) = [\exp(\hbar\omega/kT) - 1]^{-1}$ is the usual Bose-Einstein factor evaluated at ω . The results for $\omega_h(T)$ for the A_{1g} mode at 168 cm^{-1} (room temperature) are shown in Fig. 2. They were fitted using the equation

$$\Delta\omega(T) = \omega_h(T) - \omega_h(T_c) = \alpha(T_c - T)^\beta$$

where $\omega_h(T_c)$, α , and β were parameters left to adjust while T_c was taken to be 809°C . The optimum values returned by the curve fitting for $\omega_h(T_c)$ and β , averaged over four different runs, are:

$$\omega_h(T_c) = 131 \pm 0.6 \text{ cm}^{-1} \text{ and } \beta = 0.39 \pm 0.05.$$

The data in Fig. 2 replotted in the coordinates $\Delta\omega$ vs. $(T_c - T)^{0.39}$ are shown in Fig. 3.

Now over part of the range of temperature which has been explored in the present work, the results of Pynn and Axe⁽³⁾ indicate that the temperature dependence of the order parameter is of the form

$$\eta(T) \propto (T_c - T)^{0.19}.$$

Thus it follows that over an extended range of temperature from near T_c down to 770°C below T_c the present results are in excellent agreement with the previous results of Pynn and Axe⁽³⁾ if one assumes

$$\Delta\omega(T) \sim \eta^2(T).$$

This result is doubly important, first because it verifies the suggestion of Petzelt and Dvorak in a particularly unusual case and, second, because it seems to extend the validity of the relationship $\Delta\omega(T) \propto \eta^2(T)$ to quite far away from T_c .

In conclusion, we have established that HMS can be successfully used to determine the temperature dependence of the order parameter in materials where SMS is not possible. Taking into consideration the fact that NbO_2 is a particularly unfavorable case, both because the measurements had to be carried out in back scattering and the transition temperature is very high, the above result seems to open a whole new dimension in the Raman spectroscopic investigation of SPT critical phenomena.

The results reported above are, in fact, extremely general. Since they were obtained, we have been able to do further work under ONR sponsorship and it has become clear that: 1) in NbO_2 the mode we have been following is, in fact, interactive. While anharmonic coupling with the soft mode gives rise to the effect we have observed and makes the hard mode frequency vary

like the square of the order parameter, at higher temperature direct coupling prevails. This is best represented by a bilinear coupling term. It means, in effect, that at high temperature we have the emergence of a dynamic central peak. In work done since the end of the present funding period and under a different sponsorship (ONR), we have been able to analyze this central peak. The total work is to be published soon as one or two papers with proper credits to the funding origin. 2) the phenomena which we have begun to analyze here is, in fact, of great generality and present features similar to that which occur in linear organic conductors, in ferroelectrics of the improper type, in spin glasses transformations, in valence fluctuations, in polyacetylene, in brief, in all phenomena where the driving mechanism involves the generation and propagation of an excitation in the presence of disorder.

Conclusions

At this stage of our understanding of the phase transition mechanism in NbO_2 we can clearly make a connection between the polaron mediated field switching, which we had originally used to analyze the early switching measurements, and the light scattering results. These results show that optical phonons are interacting with a lower excitation that may simply be a sea of polarons and that this interaction drives the transition.

References

1. J. F. Scott, Rev.Mod.Phys. 46, 83 (1974).
2. J. Petzelt and V. Dvorak, J.Phys. C 9, 1571 (1976)
and J.Phys. C 9, 1587 (1976).
3. R. Pynn and J. D. Axe, J.Phys. C 9, L199 (1976).
4. For recent references see R. Pynn, J. D. Axe and
P. M. Raccah, Phys. Rev. B 17, 2196 (1978).
5. S. M. Shapiro, J. D. Axe, G. Shirane and P. M. Raccah,
Solid State Commun. 15, 377 (1974).
6. D. Mukamel and S. Krinsky, Phys. Rev. B 13, 5065 (1976).
7. S. H. Shin, T. H. Halpern and P. M. Raccah, Mat. Res.
Bull. 10, 1061 (1975).
8. J. L. Birman, Phys. Lett. A 45, 196 (1973).

Figure Captions

- Fig.1 Representative low frequency Stokes Raman spectrum of the $A_1 + E$ modes of NbO_2 at three different temperatures. The spectra taken at $T = 515^\circ\text{C}$ and $T = 714^\circ\text{C}$ have been displaced vertically for clarity. The feature labelled G is of instrumental origin.
- Fig.2 The peak position of the A_{1g} Raman line at 168 cm^{-1} (room temperature) versus temperature.
- Fig.3 $\Delta\omega(T) = \omega_h(T) - \omega_h(T_c)$ versus $(T_c - T)^\beta$ with $T_c = 809^\circ\text{C}$, $\omega_h(T_c) = 131\text{ cm}^{-1}$ and $\beta = 0.393$ for the A_{1g} Raman line at 168 cm^{-1} (room temperature).




Fig. 1




Fig. 2




Fig. 3

VITA

PAUL M. RACCAH

Academic Rank: Professor of Physics

PII Redacted

Research Interest: Synthesis and experimental investigation of materials useful to electronic device applications and catalysis. The methods used are X-ray diffraction, optical spectroscopy, transport measurements, magnetic measurements and calorimetry.

Education: Ph.D., University of Rennes, 1962
National Engineering Degree, University of Lyon, 1959
National Competitive Examination (Engineering Schools), Sorbonne, 1956
Baccalaureate, 1953

Experience:

9/76 to present	Professor of Physics, Head, Department of Physics, University of Illinois at Chicago Circle
1973-9/76	Professor of Physics, Belfer Graduate School of Science, Yeshiva University
1972-9/76	Director of the Maxwell R. Maybaum Institute for Material Sciences and Quantum Electronics
1971-1973	Associate Professor of Physics, Belfer Graduate School of Science, Yeshiva University
1964-1971	Solid State Division of Massachusetts Institute of Technology Lincoln Laboratory Working in the electronics materials group with John B. Goodenough
1962-1964	Group leader at C.A.E. (European Subsidiary of T.R.W.)

PUBLICATIONS OF PAUL M. RACCAH

1. "Determination of the Activity of Iron in Solid Wustite", P. M. Raccach and P. Vallet, Comp. Ren., Vol. 253, P. 2682 (1961).
2. "On Some Thermodynamical Properties of Wustite, Strictly Regular Solid Solution of Iron and Oxygen", P. M. Raccach and P. Vallet, Comp. Ren., Vol. 254, p. 1038 (1962).
3. "On the Application of C. Wagner's Theory to Solid Wustite", P. M. Raccach and P. Vallet, Comp. Ren., Vol. 254, p. 2555 (1962).
4. "New Isotherms of Solid Wustite", P. M. Raccach and P. Vallet, Comp. Ren., Vol. 255, p. 1919 (1962).
5. "Contributions to the Study of Thermodynamic Properties of Iron Protoxide", P. M. Raccach, Thesis, Category B., Order Number 8, Serial Number 7, Rennes, (1962).
6. "Thermodynamic Properties of Wustite", P. Vallet, M. Kleman and P. M. Raccach, Comp. Ren., Vol. 256, p. 136 (1963).
7. "Thermodynamic Quantities of Wustite and Magnetite", P. Vallet, C. Carel and P. M. Raccach, Comp. Ren., Vol. 258, p. 4028 (1964).
8. "Complex vs. Band Formation in Perovskite Oxides", J. B. Goodenough and P. M. Raccach, Journal of Applied Physics, Vol. 36, p. 1031 (1965).
9. "Contribution to the Study of Thermodynamic Properties of Iron Protoxide", P. Vallet and P.M. Raccach, Mem. So. Rev. Met., Vol. 62, p. 1 (1965).
10. "Preparation and Paramagnetism of the Rare Earth Trifluorides", S. Kern and P. M. Raccach, Journal of Physics and Chemistry of Solids, Vol. 26, p. 1625 (1965).
11. "Crystallographic Study of Chromium Spinel", P. M. Raccach, R. J. Bouchard and A. Wold, Journal of Applied Physics, Vol. 37, p. 1436 (1966).
12. "Anomaly in the X-ray Scattering of ZnSe", P. M. Raccach and R. J. Arnott, Physical Review, Vol. 148, p. 904 (1966).
13. "Low Temperature Crystallographic and Magnetic Study of LaCoO_3 ", N. Menyuk, K. Dwight, and P. M. Raccach, Journal of Physics and Chemistry of Solids, Vol. 28, p. 549 (1967).
14. "Comparison of the Theoretical O^{2-} Form Factors with Experiment", P. M. Raccach and R. J. Arnott, Physical Review, Vol. 153, p.1028 (1967).

15. "First-Order Localized Electron⁺collective-Electron Transition in LaCoO_3 ", P. M. Raccach and J. B. Goodenough, Physical Review, Vol. 155, p. 932 (1967).
16. "Magnetic and Structural Study of the Spinel MnYb_2S_4 ", J. M. Longo and P. M. Raccach, Bulletin Mat. Res., Vol. 2, p. 541 (1967).
17. "The Crystal Structure of Neodymium Monotellurooxide - $\text{Nd}_2\text{O}_2\text{Te}$ ", P. M. Raccach, J. M. Longo and H. A. Eick, Inorganic Chemistry, Vol. 6, p. 1471 (1967).
18. "A Localized-Electron to Collective-Electron Transition in the System $(\text{La}, \text{Sr}) \text{CoO}_3$ ", P. M. Raccach and J. B. Goodenough, Journal of Applied Physics, Vol. 39, p. 1209 (1968).
19. "Magnetic Properties of SrRuO_3 and CaRuO_3 ", J. M. Longo, P. M. Raccach and J. B. Goodenough, Journal of Applied Physics, Vol. 39, p. 1327 (1968).
20. "Magnetic Properties of $\text{La}_{0.5}\text{Sr}_{0.5}\text{CoO}_3$ Near its Curie Temperature", N. Menyuk, P. M. Raccach and K. Dwight, Physical Review, Vol. 166, p. 510 (1968).
21. " $\text{Pb}_2\text{M}_2\text{O}_{7-x}$ (M is Ru, Ir, Re) - Preparation and Properties of Oxygen Deficient Pyrochlores", J. M. Longo, P. M. Raccach and J. B. Goodenough, Mat. Res. Bull., Vol. 4, p.191 (1969).
22. "Meaning of an Anomaly in the Scattering of ZnSe", P. M. Raccach, in Electronic Structures in Solids, Plenum Press, 1969.
23. "Absolute Measurement of the Aluminum Form-Factor", P. M. Raccach and V. E. Henrich, Physical Review, Vol. 184, p. 607 (1969).
24. "Experimental Comparison of the Hartree-Fock and Slater Exchange Potentials in Aluminum from the Charge Density Point", P. M. Raccach and V. E. Henrich, International Journal of Quantum Chemistry, Vol. III, p. 797 (1970).
25. "Simple Model Potential Approach to the X-ray Form-Factor in Aluminum", P. Ascarelli and P. M. Raccach, Physics Letters, Vol. 31A, p.549 (1970).
26. "Comparison of Theoretical and Experimental Charge Densities for C, Si, Ge and ZnSe", P. M. Raccach, R. N. Euwema, D. J. Stukel and T. C. Collins, Physical Review, Vol. B1, p. 756 (1970).
27. "Magnetic Susceptibility of Euopium Trifluoride", S. Kern, P. M. Raccach and A. Tveten, Journal of Physics and Chemistry of Solids, Vol. 31, pp. 2639-2642 (1970).
28. "Phase Transitions in Perovskite-Like Compounds of the Rare Earth", S. Geller and P. M. Raccach, Physical Review, Vol. 82, p. 1167 (1970).

29. "Raman Study of the Semi-Conductor-Metal Transition in Ti_2O_3 ", A. Mooradian and P. M. Raccach, Proceedings of the Semi-Conductor Conference, Boston, (1970).
30. "Semi-Conductor-Metal Transition in Ti_2O_3 ", H. J. Zeiger, T. A. Kaplan and P. M. Raccach, Physical Review Letters, Vol. 26, p. 1328 (1971).
31. "Raman Study of the Semi-Conductor-Metal Transition in Ti_2O_3 ", A. Mooradian and P. M. Raccach, Physical Review B, Vol. 3, p. 4253 (1971).
32. "Preparation and Structure of a Pyrochlore and Perovskite in the $BiRhO_{3+x}$ System", J. M. Longo, P. M. Raccach, J. A. Kafalas and J. W. Pierce, Materials Research Bulletin, Vol. 7, p. 137 (1972).
33. "Experimental Charge Density of Copper", R. J. Temkin, V. E. Henrich and P. M. Raccach, Physical Review B, Vol. 6, p. 3572 (1972).
34. "The Structure of La_2CuO_4 and $LaSrVO_4$ ", J. M. Longo and P. M. Raccach, Journal of Solid State Chemistry, Vol. 6, pp. 526-531 (1973).
35. "Experimental and Theoretical Charge Density of Aluminum", R. J. Temkin, V. E. Henrich and P. M. Raccach, Solid State Communications, Vol. 13, pp. 811-814 (1973) Pergamon Press.
36. "Effect of Hydrostatic Pressure on Photoconductivity and Electroluminescence of Gap:N", M. I. Wolfe, H. Kressel, T. Halpern and P. M. Raccach, Applied Physics Letters, Vol. 24 (1974).
37. "Neutron Scattering Study of the Structure Phase Transition in NbO_2 ", S. M. Shapiro, J. D. Axe, G. Shirane and P. M. Raccach, Solid State Communications, Vol. 15, p. 377 (1974).
38. "Electron Transport in Single Crystals of Niobium Dioxide", G. Belanger, G. Perluzzo, J. Destry and P. M. Raccach, Canadian Journal of Physics, Vol. 52, p. 2272 (1974).
39. "Reflectivity, Resonance, Raman Scattering and Energy Level Structure in Ti_2O_3 ", S. H. Shin, F. Pollak, T. Halpern and P. M. Raccach, Solid State Communications, Vol. 16, p. 687 (1975).
40. "Metal-Oxide (MOX) Subnanosecond Transient Suppressors", G. K. Gaule, P. R. Laplante, S. H. Shin, T. Halpern and P. M. Raccach, Proceedings of the 25th Electronics Component Conference of IEEE, p. 390 (1975).
41. "Crystal Growth and Study of the Stoichiometry of NbO_2 ", S. H. Shin, T. H. Halpern and P. M. Raccach, Materials Research Bulletin, Vol. 10, p. 1061 (1975).
42. "Effects of Uniaxial Stress on the Raman Frequencies of Ti_2O_3 and Al_2O_3 ", S. H. Shin, F. Pollak and P. M. Raccach, Third International Conference on Light Scattering in Solids, Brazil, 1975.

43. "Epitaxial Technology for Low Cost Solar Cells", H. Kressel, R. V. D'Aiello, P. H. Robinson, P. M. Raccach and F. H. Pollak, Proceedings of the First ERDA Semiannual Solar Photovoltaic Conversion Program Conference, Los Angeles, California 1975, (JPL Document 5040-13) p. 368.
44. "Electroreflectance Study of the Defect States in Reduced n-type Titanium Dioxide", S. S. M. Lu, F. H. Pollak and P. M. Raccach, National Bureau of Standards, Special Publication 455, pp. 125-131, Washington D. C., (1976).
45. "Assessment of Pyroelectric Materials for Vidicon Applications", M. I. Bell and P. M. Raccach, IEDM Technical Digest, 1975 Edition, pp. 70-73, Institute of Electrical and Electronics Engineers, New York, New York.
46. "Anomalous Scattering and Asymmetrical Line Shapes in Raman Spectra of Orthorhombic KNbO_3 ", A. M. Quittet, M. I. Bell, M. Krauzman and P. M. Raccach, Physical Review B, Vol. 14, No. 11, pp. 5068-5072 (December, 1976).
47. "Reflectivity and Optical Constants of Ti_2O_3 , NbO_2 and $\text{Nb}_{1-x}\text{Ti}_x\text{O}_2$ ", S. S. M. Lu, S. H. Shin, F. H. Pollak and P. M. Raccach, Proceedings of Thirteenth International Conference on the Physics of Semi-conductors, p. 330, Tipografia Marves, Rome, Italy (1976).
48. "Piezo-modulated Spectroscopic Investigation of N and N-N Pairs in GaP", F. H. Pollak, R. S. Bauer, R. D. Burnham and P. M. Raccach, Il Nuovo Cimento, Vol. 39B, No. 2, pp. 437-441 (1976).
49. "Variations in Stoichiometry in $\text{Hg}_{1-x}\text{Cd}_x\text{Te}$ Using Electrolyte Electroreflectance: A Topographical Investigation", P. E. Vanier, F. H. Pollak, P. M. Raccach, Applied Optics, Vol. 16, No. 11, pp. 2858-2860 (November, 1977).
50. "Investigation of the Topographical Features of Surface Carrier Concentration in Si Solar Cell Materials Using Electrolyte Electroreflectance", F. H. Pollak, C. E. Okeke and P. M. Raccach, Proceedings of the Conference on Solar Cell High Efficiency and Radiation Damage, National Aeronautics and Space Administration Conference Publication No. 2020, pp. 81-90, NASA Scientific and Technical Information Office (1977).
51. "High-speed, High-current Field Switching of NbO_2 ", S. H. Shin, T. Halpern and P. M. Raccach, Journal of Applied Physics, Vol. 48, No. 7, pp. 3150-3153 (July, 1977).
52. "Topographical Investigation of the Variation in Stoichiometry in $\text{Ga}_{1-x}\text{Al}_x\text{As}$ and Carrier Concentration in GaAs Using Electroreflectance", F. H. Pollak, C. E. Okeke, P. E. Vanier and P. M. Raccach, Proceedings of the Device Research Conference, Cornell (June 1977).

53. "Polarization-Dependent Reflectivity and Optical Constants of Ti_2O_3 in the Range 0.7-10 eV", S. S. M. Lu, F. H. Pollak and P. M. Raccah, Physical Review B, Vol. 17, No. 4, pp. 1970-1975 (February 1978).
54. "Structural Fluctuations in NbO_2 at High Temperatures", R. Pynn, A. D. Axe and P. M. Raccah, Physical Review B, Vol. 17, No. 5 pp. 2196-2205 (March, 1978).
55. "Determination of the Temperature Dependence of the Order Parameter by Hard Mode Raman Spectroscopy", M. Nisar, V. J. Tekippe, and P. M. Raccah, (Accepted for publication in Solid State Communications, December, 1978).
56. "Study of the Interface Changes During Operation of nCdTe-Electrolyte Solar Cells", C. Vásquez-López, F. Sánchez-Sinencio, J. S. Helman, J. L. Peña, Lastras-Martínez and P. M. Raccah, J. Appl. Phys., Vol. 50, No. 8, pp. 5391-5396 (August 1979).
57. "Variations in Carrier Concentration in Elemental and Compound Semiconductors Utilizing Electrolyte Electroreflectance: A Topographical Investigation", F. H. Pollak, C. E. Okeke, P. E. Vanier and P. M. Raccah, Journal of Applied Physics, Vol. 50, No. 8, pp. 5375-5380 (August 1979).
58. "Current Controlled Liquid Phase Epitaxial Growth of $Hg_{1-x}Cd_xTe$ ", P. E. Vanier, F. H. Pollak and P. M. Raccah, Journal of Electronic Materials, Vol. 9, No. 1, (1980).