

AD-A085 963

NAVAL WEAPONS CENTER CHINA LAKE CA

F/6 7/4

SPECTRA OF PRESSED DISKS OF ALKALI HALIDE WHISKER CRYSTALS INCO--ETC(U)


APR 80 M E HILLS A L OLSEN

UNCLASSIFIED NWC-TP-6185

NL

[or]
[or]
[or]

END
DATE
FILMED
8-80
DTIC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

12
P.S.

NWC-TP-8185

LEVEL II

6 **Spectra of Pressed Disks of Alkali Halide
Whisker Crystals Incorporating
Foreign Ions.**

9 *Research rept.*

10 by
Marion E. Hills
Allen L. Olsen
Research Department

DTIC
ELECTE
JUN 26 1980
S D C

11 APR 1984

12 15

ADA 085963

**NAVAL WEAPONS CENTER
CHINA LAKE, CALIFORNIA 93555**



Approved for public release; distribution unlimited.

DDC FILE COPY

403 019
80 6 23 072 *mt*

Naval Weapons Center

AN ACTIVITY OF THE NAVAL MATERIAL COMMAND

FOREWORD

This report describes a method for the growth of whisker crystals of ionic compounds and for obtaining spectra of foreign ions incorporated in alkali halides without the necessity of growing large single crystals. The work was funded under Task area ZR02402.

This report was reviewed for technical accuracy by William R. McBride.


Approved by
E. B. ROYCE, *Head*
Research Department

Under authority of
W. B. HAFF
CAPT., U. S. Navy
Commander

Released for publication by
R. M. HILLYER
Technical Director
30 April 1980

NWC Technical Publication 6185

Published by.....Technical Information Department
Collation Cover, 7 leaves
First Printing 120 unnumbered copies



UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NWC TP 6185	2. GOVT ACCESSION NO. AD-A085 963	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) SPECTRA OF PRESSED DISKS OF ALKALI HALIDE WHISKER CRYSTALS INCORPORATING FOREIGN IONS		5. TYPE OF REPORT & PERIOD COVERED Research Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Marian E. Hills Allen L. Olsen		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Naval Weapons Center China Lake, CA 93555		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS Task area ZR02402
11. CONTROLLING OFFICE NAME AND ADDRESS Naval Weapons Center China Lake, CA 93555		12. REPORT DATE April 1980
		13. NUMBER OF PAGES 12
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Crystal Growth Whiskers Spectra Alkali Halides		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) See back of form.		

DD FORM 1473
1 JAN 73EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-LF 014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

(U) *Spectra of Pressed Disks of Alkali Halide Whisker Crystals Incorporating Foreign Ions*, by Marian E. Hills and Allen L. Olsen. China Lake, Calif., Naval Weapons Center, April 1980. 12 pp. (NWC TP 6185, publication UNCLASSIFIED.)

(U) Alkali halide whisker crystals of KCl, KBr, KI, and NaCl were grown readily by allowing aqueous solutions of the salts to pass through porous glass. Whisker crystals of alkali halides doped with MnO_4^- , ClO_4^- , and ClO_3^- were also grown; not all dopants were used with all host lattices. The whisker crystals may be pressed into disks suitable for obtaining optical spectra. The absorption bands in the spectra of disks pressed from doped whisker crystals were sharper than the spectra of disks pressed from a mechanical mixture of the alkali halide and the dopant. The versatility of the porous glass technique for the growth of whisker crystals is clearly demonstrated.

MnO₄⁻, ClO₄⁻
and ClO₃⁻

Accession For	
NTIS GRA&I	☒
DDC TAB	☐
Unannounced	
Justification	
By _____	
Distribution/_____	
Availability Codes	
Dist	Avail and/or special
A	

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

The feed solutions were unsaturated aqueous solutions of the alkali halides, either pure or containing small amounts of the ion of interest. The composition of the pure solutions employed is shown in Table 1.

TABLE 1. Composition of Pure Alkali Halide Feed Solutions.

Salt	Grams of salt/ 100 grams solution	Percent of saturation at 20°C
NaCl	20	76
KCl	19	76
KBr	32	82
KI	40	68

The whisker crystals were pressed into disks 7/8-inch in diameter under vacuum and at a pressure of 133,000 psi.⁵ Some whisker crystals were pressed into disks in the condition in which they were harvested and some were broken up by vibrating them together with three 5/32-inch steel balls in a capsule for one minute.

The infrared spectra were run on a Perkin-Elmer Model 137, 221, or 621 spectrophotometer and the ultraviolet and visible spectra on a Perkin-Elmer Model 202 or a Cary Model 14R spectrophotometer.

RESULTS AND DISCUSSION

Alkali halide whisker crystals grow readily on porous glass, particularly silicone rubber coated porous glass (Figure 2). The formation on a porous glass tube of a whisker-crystal covering a centimeter thick in 24 hours is not unusual.

A photomicrograph of alkali halide whiskers is shown in Figure 3. The visual clarity (transmission) of pressed disks of alkali halide whiskers is shown in Figure 4. The photographs of the disks were taken shortly after they were pressed and indicate that better quality disks can be obtained from broken whiskers (those shaken with steel balls) than can be obtained from unbroken whiskers. The ultraviolet spectra of disks of pressed whiskers show good transmission into the ultraviolet region; the ultraviolet spectrum of a potassium bromide disk is shown in Figure 5.

⁵ Allen L. Olsen. "Potassium Bromide Pellet Technique," *Anal. Chem.*, Vol. 31, No. 2 (February 1956), pp. 321-22.




FIGURE 3. Photomicrograph of Potassium Bromide Whiskers. The magnification is about 160X, which corresponds to 6.25 $\mu\text{m}/\text{mm}$.




FIGURE 2. Whisker Crystals of Potassium Bromide Growing on Tube Shown in Figure 1.




FIGURE 4. Pressed Disks of Alkali Halide Whiskers. Disks shown in the upper row were pressed from whiskers broken with steel balls prior to pressing. These disks show greater clarity than those pressed from unbroken whiskers (bottom row).




FIGURE 5. Ultraviolet Spectrum of a Disk Pressed From Potassium Bromide Whiskers.

Whisker crystals were grown from various alkali halide solutions containing small amounts of permanganate, perchlorate, chlorate, sulfate, chromate, dichromate, lead, or ammonium ions. Sharp absorption bands in the spectra of pressed disks were found which could be associated with permanganate, perchlorate, or chlorate ions. The infrared spectra for these are shown in Figures 6-8. For purposes of comparison spectra are also shown for disks pressed from a physical mixture of Harshaw KBr powder and small quantities of potassium permanganate, potassium perchlorate, or potassium chlorate. Figure 9 shows the spectra of perchlorate ion in potassium chloride, potassium bromide, and potassium iodide.

The spectrum for perchlorate agrees with that obtained by Hisatsune and Linnehan⁶ after they had heated pressed disks of $\text{ClO}_4:\text{KCl}$ to change the broad band near 1120 cm^{-1} to a pair of sharp bands at 1133 and 1119 cm^{-1} for use in their study of the kinetics of the decomposition of the perchlorate ion.

⁶ I. C. Hisatsune and D. G. Linnehan. "Thermal Decomposition of the Perchlorate Ion in a Potassium Chloride Matrix," *J. Phys. Chem.*, Vol. 74, No. 23 (1970), pp. 4091-95.




FIGURE 6. Infrared Spectra of Pressed Disks. Upper Curve: Potassium bromide whiskers grown from solution containing a small amount of potassium permanganate. Lower Curve: Mechanical mixture of Harshaw potassium bromide powder and a small amount of potassium permanganate.




FIGURE 7. Infrared Spectra of Pressed Disks. Upper Curve: Potassium bromide whiskers grown from solution containing a small amount of potassium perchlorate. Lower Curve: Mechanical mixture of Harshaw potassium bromide powder and a small amount of potassium perchlorate.




FIGURE 8. Infrared Spectra of Pressed Disks. Upper Curve: Potassium bromide whiskers grown from solution containing a small amount of potassium chlorate. (Growth tube may have been slightly contaminated with ammonium ions.) Lower Curve: Mechanical mixture of Harshaw potassium bromide powder and a small amount of potassium chlorate.




FIGURE 9. Infrared Spectra of Pressed Disks of Whisker Crystals Grown From Solutions Containing Small Amounts of Potassium Perchlorate.

Some KBr from the same supply used to make feed solutions was ground by hand in an agate mortar, sieved (particle sizes ranged from 44 μm to 74 μm), and pressed into a disk; its IR spectrum showed some bands. Heating the KBr near its melting point or fusion before grinding and pressing resulted in the reduction of some of the impurity bands. The extent of impurity bands in pressed KBr disks varied from bottle to bottle of material used to prepare feed solutions, even for the same manufacturer. Since some impurity bands appeared both in disks pressed from the bulk KBr and whisker KBr, it appears that recrystallization at room temperature did not remove the source(s) of all the impurity bands.

X-ray measurements of a few of the KBr whiskers showed that they had grown in the $\langle 100 \rangle$ direction. This is the same as the reported behavior for KBr⁷ grown on cellophane.

Whiskers were grown from aqueous KCl-KBr solutions. X-ray diffraction patterns showed that the whiskers were mixed crystals and not a mechanical mixture of KCl whiskers and KBr whiskers. Solubility data show that potassium chloride and potassium bromide form a completely miscible system at room temperature. Attempts to press KCl-KBr whiskers into disks were not successful; the disks cracked in a radial pattern.

CONCLUSIONS

For some ionic compounds whisker crystals can be grown readily from porous glass in such quantities as to make them useful for pressed pellet work. The pellets may be used:

1. To obtain spectra of ions in various crystal lattices.
2. To obtain some indication of the solubility of ions in various lattices by optical means without the necessity to grow large single crystals of the material.
3. To obtain specimens for use in kinetics studies.

ACKNOWLEDGMENT

The authors thank Gerald B. Ansell and Lohr A. Burkardt for the X-ray determinations.

⁷ B. E. Powell and Byron M. McKibben. "Alkali-Halide Filamentary Crystals," *J. Cryst. Growth*, Vol. 8 (1971), pp. 276-78.

NWC TP 6185

INITIAL DISTRIBUTION

- 1 Director of Navy Laboratories
- 7 Naval Air Systems Command
 - AIR-30212 (2)
 - AIR-330 (1)
 - AIR-4115 (1)
 - AIR-536 (1)
 - AIR-950D (2)
- 4 Chief of Naval Operations
- 2 Chief of Naval Material
 - MAT-03 (1)
 - MAT-03PB (1)
- 6 Naval Sea Systems Command
 - SEA-03 (1)
 - SEA-033 (1)
 - SEA-0331 (1)
 - SEA-0332 (1)
 - SEA-99612 (2)
- 8 Chief of Naval Research, Arlington
 - ONR-100 (1)
 - ONR-102 (1)
 - ONR-401 (1)
 - ONR-420 (1)
 - ONR-439 (1)
 - ONR-460 (1)
 - ONR-472 (1)
 - ONR-473 (1)
- 1 Naval Ocean Systems Center, San Diego (Technical Library)
- 1 Naval Ordnance Station, Indian Head (Technical Library)
- 1 Naval Postgraduate School, Monterey (Technical Library)
- 1 Naval Research Laboratory (Technical Library)
- 1 Naval Surface Weapons Center, White Oak (Technical Library)
- 1 Naval Weapons Support Center, Crane (Research and Development Department)
- 1 Office of Naval Research Branch Office, Boston
- 1 Office of Naval Research Branch Office, Chicago
- 1 Office of Naval Research Branch Office, Pasadena
- 1 Pacific Missile Test Center, Point Mugu (Technical Library)
- 1 Army Missile Research and Development Command, Redstone Arsenal (Redstone Scientific Information Center, Chief Document Section)
- 1 Air Force Flight Test Center, Edwards Air Force Base (Technical Library)
- 2 Rome Air Development Center, Hanscom Air Force Base
 - Solid State Sciences Division
 - C. S. Sahagian (1)
 - Technical Library (1)
- 1 Wright-Patterson Air Force Base (Technical Library)
- 1 Deputy Director of Defense Research and Engineering

- 1 Defense Advanced Research Projects Agency, Arlington
- 12 Defense Technical Information Center
- 1 Goddard Space Flight Center, Greenbelt (Technical Library)
- 1 Lewis Research Center, NASA, Cleveland (Technical Library)
- 1 National Bureau of Standards, Boulder (Paul M. Gruzensky)
- 1 National Oceanic and Atmospheric Administration, Boulder (Technical Library)
- 1 Atlantic Research Corporation, Alexandria, VA
- 1 Battelle Memorial Institute, Columbus, OH
- 1 Chemical Propulsion Information Agency, Applied Physics Laboratory, Laurel, MD
- 1 Harshaw Chemical Company, Cleveland, OH
- 1 IIT Research Institute, Chicago, IL (Technical Library)
- 1 Jet Propulsion Laboratory, CIT, Pasadena, CA (Technical Library)
- 1 Los Alamos Scientific Laboratory, Los Alamos, NM (Technical Library)
- 1 Oregon State University, Corvallis, OR (Chemistry Department, William J. Fredericks)
- 1 SRI International, Menlo Park, CA (Technical Library)
- 1 The Aerospace Corporation, Los Angeles, CA (Technical Library)
- 1 Thiokol Chemical Corporation, Elkton, MD (Technical Library)

