

AD-A087 229

AIR FORCE GEOPHYSICS LAB HANSCOM AFB MA
DETECTION OF PROTONS IN CR-39 PLASTIC TRACK DETECTOR. (U)
DEC 79 Y V RAO, A DAVIS, R C FILZ
UNCLASSIFIED AFGL-TR-79-0297

F/6 14/2

NL

1 OF 1
AD
A087229



END
DATE
FILMED
9-80
DTIC

LEVEL II

14
9 AEGI-TR-79-0297, AFGL-ERP-6987
ENVIRONMENTAL RESEARCH PAPERS (NO. 698)



12
B.S.

ADA 087229

6
**Detection of Protons in
CR-39 Plastic Track Detector.**

10
Y. V. RAO
A. DAVIS
R. C. FILZ
P. J. McNULTY
D. SHIRKEY

11 11 Dec 1979

12 11

DTIC
ELECTE
S JUL 30 1980 D
E

Approved for public release; distribution unlimited.

16
17
SPACE PHYSICS DIVISION PROJECT 2311 G1
AIR FORCE GEOPHYSICS LABORATORY
HANSCOM AFB, MASSACHUSETTS 01731

AIR FORCE SYSTEMS COMMAND, USAF



409578


80 7 28 028

FILE COPY

This report has been reviewed by the ESD Information Office (OI) and is releasable to the National Technical Information Service (NTIS).

This technical report has been reviewed and is approved for publication.

FOR THE COMMANDER



Chief Scientist

Qualified requestors may obtain additional copies from the Defense Documentation Center. All others should apply to the National Technical Information Service.

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER AFGL-TR-79-0297	2. GOVT ACCESSION NO. AD-A082229	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) DETECTION OF PROTONS IN CR-39* PLASTIC TRACK DETECTOR	5. TYPE OF REPORT & PERIOD COVERED Scientific. Interim.	
	6. PERFORMING ORG. REPORT NUMBER ERP No. 688 ✓	
7. AUTHOR(s) Y. V. Rao ** A. Davis** R. C. Filz	P. J. McNulty *** D. Shirkey***	8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Air Force Geophysics Laboratory (PHG) ✓ Hanscom AFB Massachusetts 01731	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 61102F 2311G102	
11. CONTROLLING OFFICE NAME AND ADDRESS Air Force Geophysics Laboratory (PHG) Hanscom AFB Massachusetts 01731	12. REPORT DATE 11 December 1979	
	13. NUMBER OF PAGES 12	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release, distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES * Registered Trade Mark, Pittsburgh Plate Glass. ** Physics Research Division, Emmanuel College, Lexington, Mass. *** Physics Department, Clarkson College of Technology, Potsdam, N.Y.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Energetic proton detector Plastic track detector CR-39		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) CR-39 plastic is used as a detector to observe monoenergetic protons. Several samples of CR-39 were exposed to protons of energies 1.5 MeV, 2.2 MeV, 3.2 MeV and 4.3 MeV. After etching measurements were carried out on track diameters produced by protons in all samples. The diameter distributions clearly show an excellent energy resolution of protons of different energies. From our preliminary analysis of data, it appears that the response function for registering protons in CR-39 may be a lot less complicated than in cellulose nitrate.		

DD FORM 1473 1 JAN 73 EDITION OF 1 NOV 68 IS OBSOLETE

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Preface

It is a pleasure to thank Drs. Norman Rohrig and Steve Marino of Brookhaven National Laboratory for help with proton irradiations.

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DDC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	<input type="checkbox"/>
By _____	
Distribution/	
Security Codes	
Dist	Mail and/or special
A	

PRECEDING PAGE BLANK-NONE

Contents

1. INTRODUCTION	7
2. EXPERIMENTAL DETAILS	8
3. RESULTS	8

Illustrations

1. The Diameter Distribution of the Etch Pits of Protons (17 hour etch)	9
2. The Diameter Distribution of the Etch Pits of Protons (30 hour etch)	10
3. Etch Pit Diameter (D) as a Function of Proton Energy (E). The parameter on each curve represents etching time	10
4. Etch Pit Diameter (D) as a Function of Amount of Bulk Material Removed From One Surface (Vgt)	11
5. Tracks of 1.5 MeV Normal Incidence Protons in CR-39. The etching time was 30 hours	11
6. Tracks of 2.2 MeV Normal Incidence Protons in CR-39. The etching time was 30 hours	12

Detection of Protons in CR-39* Plastic Track Detector

1. INTRODUCTION

In recent years Solid State Nuclear Track Detectors have found widespread application.¹ The production of tracks by energetic ions in insulating materials is a widely used technique for detection and identification of these ions. The use of these detectors has been shown to be very successful in the study of very heavy primary cosmic rays and the recording of fission fragments. Also, there have been some investigations exploring the possibility of their application to detect protons. Cellulose Nitrate plastic has been employed as a detector to record protons, however, CN suffers from being inhomogeneous and anisotropic with regard to its physical characteristics. These defects manifest themselves in non-geometrical track profiles, differences in sensitivity in a given sheet, and variations in bulk etch rate. The use of plastic sheet cast from CR-39 monomer (allyl diglycol carbonate) with excellent etching properties, high sensitivity and high uniformity as a nuclear track detector was reported recently.² This material was found to

(Received for publication 3 December 1979)

*Registered Trade Mark, Pittsburgh Plate Glass.

1. Fleischer, R. L., Price, P. B., and Walker, R. M. (1975) Nuclear Tracks in Solids, University of California Press, Berkeley.
2. Cartwright, B. G., Shirk, E. K., and Price, P. B. (1978) Nucl. Instr. Methods 153:457.

have a lower detection threshold ($Z/\beta = 9$) than cellulose nitrate ($Z/\beta = 30$) and a smaller variation of response (~ 1 percent) to particles of a given ionization rate than Lexan polycarbonate (~ 3 to 8 percent). Commercially available CR-39 is capable of recording protons of 1 MeV and below as well as 6 MeV alpha particles. In this work, an attempt is made to investigate further the properties of CR-39 as a nuclear track detector with particular reference to the detection of protons.

2. EXPERIMENTAL DETAILS

For this study, Polytech CR-39 (1500 μ thick) was used. Samples of size (2.5 \times 2.5) cm were cut out and exposed to a beam of protons from the Van de Graaf generator at Brookhaven National Laboratory. The beam was tuned to four different energies (1.5 MeV, 2.2 MeV, 3.2 MeV and 4.3 MeV). The corresponding fluences were: 2.8×10^5 particles/cm², 0.44×10^6 particles/cm², 0.67×10^6 particles/cm² and 0.91×10^6 particles/cm². All irradiations were carried out in such a manner that particles are nearly normally incident to the surface of the plastic sheet. After irradiation the samples were etched in a solution of 6.25N NaOH at 50°C for different durations. The samples were suspended by means of nichrome wires in polyethylene vessels containing etchant. Temperature control was achieved by placing the polyethylene containers into a regulated water bath. Samples were selected from all four irradiations and etched in four different batches for 7 hours, 17 hours, 30 hours and 48 hours. In order to distinguish the background against tracks of protons, a virgin sample of CR-39 was always etched with each batch. All measurements were made on Koristka R4 microscope using 80 Zeiss objective and X10 wide field American Optical eyepiece. A total of 1000 tracks were measured to obtain data on track diameters.

3. RESULTS

In Figures 1 and 2 the distributions of track diameters for protons are shown. The sheets were etched for 17 hours and 30 hours. In the case of the 17 hour etch, there is some spread in track diameter distribution for 4.3 MeV protons. This may be of statistical nature and/or spread in the beam energy. The superior properties of CR-39 as a track detector is clearly demonstrated in Figure 2. Here, the energy resolution for protons is excellent. Once again the peak in track diameter distribution for 4.3 MeV protons is very broad. Figure 3 shows etch pit diameter as a function of proton energy. The samples etched for 48 hours show a maximum slope thereby indicating a better resolution. Figure 4 shows etch pit

diameter as a function of amount of bulk material removed from one surface. From our preliminary data, it appears that the dependence of etch pit diameter on the amount of bulk material removed from one surface seems to be less complicated than in CN. Particle identification by measurements of etch pit diameter was first suggested by Somogyi.³ Recently, Somogyi and Szalay⁴ discussed the kinetics of track diameter growth in considerable detail. In principle the method should work with particles incident at arbitrary angles on a solid surface, but in practice it is much simpler if the detector can be positioned such that particles are nearly normally incident. For tracks with large cone angles such as protons, the diameter is a more sensitive function of ionization rate than is track length. Finally, Figures 5 and 6 show tracks of 1.5 MeV and 2.2 MeV protons.




Figure 1. The Diameter Distribution of the Etch Pits of Protons (17 hour etch)

3. Somogyi, G. (1966) Nucl. Instr. Methods 42:312.

4. Somogyi, G., and Szalay, S.A. (1973) Nucl. Instr. Methods 109:211.




Figure 2. The Diameter Distribution of the Etch Pits of Protons (30 hour etch)




Figure 3. Etch Pit Diameter (D) as a Function of Proton Energy (E). The parameter on each curve represents etching time




Figure 4. Etch Pit Diameter (D) as a Function of Amount of Bulk Material Removed From One Surface (Vgt)




Figure 5. Tracks of 1.5 MeV Normal Incidence Protons in CR-39. The etching time was 30 hours




Figure 6. Tracks of 2.2 MeV Normal Incidence Protons in CR-39. The etching time was 30 hours