



Unclassified

18 AR 01

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

LEVEL II

READ INSTRUCTIONS BEFORE COMPLETING FORM

REPORT DOCUMENTATION PAGE

1. REPORT NUMBER <b>19</b> 14709.4-C		2. GOVT ACCESSION NO. AD-A096 032		3. RECIPIENT'S CATALOG NUMBER	
4. TITLE (and Subtitle) Study of Polymeric Nematic Phases,			5. TYPE OF REPORT & PERIOD COVERED Final Report 5/1/77 through 11/30/80		
7. AUTHOR(s) W. R. Krigbaum			8. CONTRACT OR GRANT NUMBER(s) DAAG 29-77-G-0148		
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry Duke University Durham, North Carolina 27706			10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 11-13-F-681		
1. CONTROLLING OFFICE NAME AND ADDRESS Research Triangle Institute			12. REPORT DATE February 12, 1981		
13. NUMBER OF PAGES 6			15. SECURITY CLASS. (of this report) Unclassified		
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office) 9 Final Rept. 17, 18, 77-34 7/01/77			15a. DECLASSIFICATION/DOWNGRADING SCHEDULE		
6. DISTRIBUTION STATEMENT (of this Report)					
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)					
18. SUPPLEMENTARY NOTES					
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Polymeric nematic, persistence length, electrohydrodynamic instabilities.					
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) An experimental determination of the persistence length of an aromatic polyamide-hydrazide, X-500, was undertaken to compare values obtained by light scattering, intrinsic viscosity, and small angle x-ray diffraction. Corrections for molecular weight heterogeneity are well known and should be applied. The status of the treatment excluded volume effects for non-gaussian wormlike chains is not currently adequate.					

AD A 096 032

DTIC FILE COPY

DTIC ELECTE  
MAR 6 1981  
S D A

118225

81 3 2 111

20. Abstract continued

We were unsuccessful in an attempt to obtain experimental values of the entropy changes at the crystal-nematic and nematic-isotropic transitions for a thermotropic nematic polymer. This arose from the difficulty in identifying the nematic phase in highly viscous thermotropic polymers. Investigations of flow instabilities created by an electric field indicates this procedure may furnish a convenient conformatory test for thermotropic nematic phases.

APPROVED FOR	
DATE	
BY	
REVISIONS	
1	
2	
3	
4	
5	
6	
7	
8	
9	
10	
11	
12	
13	
14	
15	
16	
17	
18	
19	
20	
21	
22	
23	
24	
25	
26	
27	
28	
29	
30	
31	
32	
33	
34	
35	
36	
37	
38	
39	
40	
41	
42	
43	
44	
45	
46	
47	
48	
49	
50	
51	
52	
53	
54	
55	
56	
57	
58	
59	
60	
61	
62	
63	
64	
65	
66	
67	
68	
69	
70	
71	
72	
73	
74	
75	
76	
77	
78	
79	
80	
81	
82	
83	
84	
85	
86	
87	
88	
89	
90	
91	
92	
93	
94	
95	
96	
97	
98	
99	
100	

Study of Polymeric Nematic Phases

Final Report

W. R. Krigbaum  
Department of Chemistry  
Duke University  
Durham, North Carolina 27706

February 12, 1981

to

U. S. Army Research Office

Grant DAAG 29-77-G-0148

5/1/77 through 11/30/80

Duke University

Approved for Public Release  
Distribution Unlimited

Report Number ~~1981~~-KGBM

TF 1 DL

THE VIEW, OPINIONS, AND/OR FINDINGS CONTAINED IN THIS REPORT ARE THOSE OF THE AUTHOR(S) AND SHOULD NOT BE CONSTRUED AS AN OFFICIAL DEPARTMENT OF THE ARMY POSITION, POLICY, OR DECISION, UNLESS SO DESIGNATED BY OTHER DOCUMENTATION.

We proposed to investigate two aspects of nematic phases formed from semi-flexible chain polymers.

1. An experimental determination of the critical chain extension required for the formation of a nematic phase.

2. An investigation of the structure of the nematic phase by a thermodynamic study of the nematic  $\rightarrow$  isotropic transition in thermotropic nematic polymers.

Early work of Onsager<sup>1</sup> and Isihara<sup>2</sup> had demonstrated that the origin of the nematic phase in low molecular weight nematics lies in the asymmetric (rodlike or disklike) character of the molecules. The lattice model treatment of Flory<sup>3</sup> showed that rodlike polymers must have a critical axial ratio, and semi-flexible polymers must have a critical chain extension ratio, if a lyotropic nematic phase is to be formed at a given polymer concentration. We proposed to test these predictions by measuring the persistence length of several semi-flexible polymers. This turned out to be a rather popular idea, and results from other laboratories were reported for poly(p-benzamide),<sup>4,5</sup> poly(p-phenylene terephthalamide),<sup>5,6</sup> and a (polyamide hydrazide).<sup>7</sup> These were all polymers we had proposed to study. Examination of these results, and the more extensive collection of data for the polyisocyanates, led us to the conclusion that values obtained by different methods by the same polymer were too discordant. We, in connection with Professor Ciferri's group at the University of Genoa, undertook to determine the persistence length of a single polymer, a polyamide hydrazide, by a variety of techniques, using light scattering,<sup>8</sup> intrinsic viscosity,<sup>9</sup> and small angle x-ray diffraction.<sup>10</sup> It is clear that poor solubility of this class of polymer makes any type of physical chemical measurement difficult. Part of the discordant results is certainly due to neglect of heterogeneity corrections when different averages, such as  $\langle s^2 \rangle_z$  and  $\langle M \rangle_w$ , are combined. A second, and more fundamental, difficulty

is that there is no adequate treatment of excluded volume effects for semi-flexible chains consisting of two few links to behave in a gaussian manner.

The second problem we proposed to investigate involved whether semi-flexible chain polymers in the nematic phase are fully extended, as assumed in his theoretical treatment by Flory.<sup>3</sup> If this is the case, we would expect a much larger change in the entropy at the nematic  $\rightarrow$  isotropic transition for semi-flexible chain polymers, as compared to low molecular weight compounds. We proposed to perform DSC measurements at the thermotropic transition of the Tennessee Eastman copolyesters. A study<sup>11</sup> was performed of the co[poly(ethylene terephthalate)-p-oxybenzoate] containing 30 mole percent oxybenzoate units; however, further work in this laboratory showed<sup>12</sup> that this polymer did not form a thermotropic nematic phase. We believe the original objective is worth further effort, and a number of polymers are being synthesized in an effort to find a suitable candidate giving a thermotropic nematic  $\rightarrow$  isotropic transition without an intervening biphasic region.

Our difficulty with the T2/30 copolymer led to an effort to find more reliable tests for the nematic phase. That misidentification arose from a small amount of polymer having a higher melting point. When most of the polymer was molten, this crystalline remnant made the fluid phase birefringent. Low molecular weight nematic phases are recognized by the appearance of threadlike structures in the microscope. These features are often missing in polymeric nematics, unless the molecular weight is quite low. A second diagnostic test involves DSC. However, this can be difficult to interpret if there are polymorphic modifications with different melting temperatures. Also, some nematogens exhibit a biphasic structure over a wide temperature range, and the enthalpy change associated with the transition to the isotropic phase occurs over such a span of temperature as to be lost if the DSC instrument does not have high sensitivity and a stable baseline. It is our opinion that x-ray diffraction

does not permit a very certain identification of a nematic phase in polymers. The effect of electric or magnetic fields appeared to offer promise. The need to maintain a high sample temperature for thermotropic nematogens led us to the conclusion that electrical field effects could be more easily investigated. We found<sup>13,14</sup> that application of an electric field led to flow instabilities, and that the hydrodynamic flows became organized in well known patterns, even for polymeric nematics. We were able to observe Williams domains and the variable grating mode patterns, but not chevrons or the dynamic scattering mode. As might be expected from the high melt viscosity, the formation time for these structures is of the order of an hour for polymers, as compared to tenths or hundredths of a second for low molecular weight nematics. We also observed a high field turbulence which appeared to be characteristic of the nematic phase, and had a formation time on the order of a minute. This has the desired features of a confirmatory test for thermotropic polymeric nematic phases.

There are a number of questions concerning electric field effects which we hope to answer by future work. We need to demonstrate whether this test is universal or, if not, the types of structures for which it is applicable. Secondly, all of our work has involved direct exposure of the polymers to the electrodes. Hence, we do not know whether we are dealing with an electric field effect, or whether charge injection at the electrode is essential for the process. Finally, insulated electrodes may allow application of the same procedure to lyotropic nematics. The high conductivity of most of the solvents prevents examination of this category using exposed electrodes.

### References

1. L. Onsager, Am. N.Y. Acad. Sci. 51, 627 (1949).
2. A. Isihara, J. Chem. Phys. 19, 1142 (1951).
3. P. J. Flory, Proc. Royal Soc. A234 60, 73 (1956).
4. V. N. Tsvetkov, G. I. Kudriatsev, I. N. Shtennikova, T. V. Peker, E. N. Zamarova, V. D. Kalmykova, and A. V. Volokhina, Eur. Polym. J. 12, 517 (1976).
5. A. Arpin and G. Strazielle, Polymer 18, 597 (1977).
6. V. N. Tsvetkov, I. N. Shtennikova, T. V. Peker, G. I. Kudriatsev, A. V. Volokhina, and V. D. Kalmykova, Eur. Polym. J. 13, 455 (1977).
7. V. N. Tsvetkov, G. I. Kudriatsev, N. A. Mikhailova, A. V. Volokhina, and V. D. Kalmykova, Dokl. Phys. Chem. (English translation) 235, 817 (1977).
8. E. Bianchi, A. Ciferri, A. Tealdi, and W. R. Krigbaum, J. Polym. Sci., Polym. Phys. Ed., 17 2091 (1979).
9. E. Bianchi, A. Ciferri, J. Preston, and W. R. Krigbaum, (Accepted for publication in J. Polym. Sci., Polym. Phys. Ed.)
10. W. R. Krigbaum and S. Sasaki, (manuscript submitted for publication in J. Polym. Sci., Polym. Phys. Ed.)
11. W. R. Krigbaum and F. Salaris, J. Polym. Sci., Polym. Phys. Ed. 16 883 (1978).
12. H. J. Lader and W. R. Krigbaum, J. Polym. Sci., Polym. Phys. Ed., 17 1661 (1979).
13. W. R. Krigbaum, H. J. Lader and A. Ciferri, Macromolecules 13 554 (1980).
14. W. R. Krigbaum and H. J. Lader, Mol. Cryst. Liq. Cryst. 67, 87 (1980).

Publication and Manuscripts Resulting from Work Supported  
on ARO Grant DAAG-77-G-0148

1. W. R. Krigbaum and F. Salaris, "Thermodynamics of Nematic Phases Formed From Semiflexible Chain Polymers", J. Polym. Sci., Polym. Phys. Ed., 16, 883 (1978).
2. E. Bianchi, A. Ciferri, A. Tealdi and W. R. Krigbaum, "Light Scattering Study of an Aromatic Polyamide-Hydrazide Polymer", J. Polym. Sci., Polym. Phys. Ed., 17, 209 (1979).
3. W. R. Krigbaum, H. J. Lader, and A. Ciferri, "Electrohydrodynamic Instabilities in Thermotropic Nematic Polymers", Macromolecules, 13, 554 (1980).
4. W. R. Krigbaum and H. J. Lader, "Electric Field-Induced Flow Instabilities in Low Molecular Weight and Polymeric Nematics", Mol. Cryst. Liq. Cryst., 62, 87 (1980).
5. E. Bianchi, A. Ciferri, and W. R. Krigbaum, "A Study of the Molecular Conformation of an Aromatic Polyamide-Hydrazide by Intrinsic Viscosity", (accepted for publication in J. Polym. Sci., Polym. Phys. Ed.)
6. W. R. Krigbaum and A. Sasaki, "Determination of the Persistence Length of an Aromatic Polyamide-Hydrazide by Small Angle X-ray Diffraction", (manuscript submitted for publication in J. Polym. Sci., Polym. Phys. Ed.).