

AD-A107 675

PENNSYLVANIA UNIV PHILADELPHIA DEPT OF CHEMISTRY

F/G 11/9

RECENT ADVANCES IN THE CHEMISTRY AND PHYSICS OF POLYACETYLENE: --ETC(U)

NOV 81 A G MACDIARMID, A J HEEGER

N00014-81-K-0648

UNCLASSIFIED

TR-81-13

1 OF 1

40A

1076%



END
DATE
FILMED
1.82
DTIC

unclassified

LEVEL

13

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report No. 81-13	2. GOVT ACCESSION NO. AD-A107 675	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Recent Advances in the Chemistry and Physics of Polyacetylene: Solitons as a Means of Stabilizing Carbonium Ions and Carbanions in Doped (CH) _x		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
7. AUTHOR(s) A.G. MacDiarmid and A.J. Heeger *		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS * Departments of Chemistry and Physics University of Pennsylvania Philadelphia, Pa. 19104		8. CONTRACT OR GRANT NUMBER(s) N00014-81-K-0648
11. CONTROLLING OFFICE NAME AND ADDRESS Department of the Navy Office of Naval Research Arlington, Va. 22217		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR-356-602-4-13-91
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE November 11, 1981
		13. NUMBER OF PAGES 14
		15. SECURITY CLASS. (of this report) unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Distribution unlimited; approved for public release		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) N.R.L. Memorandum Depart. 4662, 1981, "Proceedings of the Molecular Electronic Devices Workshop", p.208.		
18. SUPPLEMENTARY NOTES 81 11 20 611 S		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) semiconducting polymer; polyacetylene; (CH) _x ; doped; chemically; electrochemically; semiconductor-metal transition; organic metals; qualitative summary; soliton concept of bonding; Curie and Pauli magnetic susceptibilities; infrared spectra; absorption; EPR spectral data; n-doped; sodium		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) Crystalline, silvery films of the flexible, semiconducting polymer, "polyacetylene," (CH) _x , can be doped readily, either chemically or electrochemically, to give a series of either p-type or n-type semiconductors. As doping proceeds, their conductivity increases rapidly (over twelve orders of magnitude in certain cases). At a few mole percent dopant concentration, they undergo a semiconductor-metal transition and are converted to silvery-golden films of "organic metals." A qualitative summary of the most important experiments leading to the "soliton" concept of bonding in the semiconducting material will be pre-		

DTIC
ELECTE
NOV 23 1981

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE

S/N 0102-LF-014-6601

unclassified

(OVER)

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

270975

AD A107 675

DTIC FILE COPY

20. sented. This will stress, in particular, the change in Curie and Pauli magnetic susceptibilities of the $(CH)_x$ as it is doped p-type in a controlled, homogeneous fashion with AsF_5 or I_2 through the semiconducting to the metallic regime. Correlations between observed and calculated infrared spectra of doped $(CH)_x$ and $(CD)_x$ will also be described. Absorption and epr spectral data will be presented which will show that similar effects are observed when $(CH)_x$ is n-doped with a species such as sodium.

Acquisition For	
☒ ☐ ☐ ☐	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A	20

DTIC
ELECTE
NOV 23 1981
S D D

OFFICE OF NAVAL RESEARCH

Contract No. N00014-81-K-0648

Task No. 356-602

TECHNICAL REPORT NO. 81-13

Recent Advances in the Chemistry and Physics of
Polyacetylene: Solitons as a Means of Stabilizing
Carbonium Ions and Carbanions in Doped $(CH)_x$

by

A.G. MacDiarmid and A.J. Heeger*

N.R.L. Memorandum Report 4662, 1981,
"Proceedings of the Molecular Electronic .
Devices Workshop" p.208

4-11 5810

Departments of Chemistry and Physics*
University of Pennsylvania
Philadelphia, Pa. 19104

November 11, 1981

Reproduction in whole or in part is permitted for any
purpose of the United States Government.

Approved for public release; distribution unlimited.

Workshop on "Molecular" Electronic Devices, Naval Research Laboratory, Wash. D.C.
March 23-24, 1981

RECENT ADVANCES IN THE CHEMISTRY AND PHYSICS OF POLYACETYLENE: SOLITONS AS A
MEANS OF STABILIZING CARBONIUM IONS AND CARBANIONS IN DOPED $(CH)_x$

A. G. MacDiarmid⁺ and A. J. Heeger⁺⁺, Laboratory for Research on the Structure
of Matter, Department of Chemistry⁺ and Department of Physics,⁺⁺ University of
Pennsylvania, Philadelphia, PA 19104

INTRODUCTION

There exists a new class of electronic materials formed as quasi-one-dimensional organic polymers, which have the properties of semiconductors or metals when suitably doped with donor or acceptor species. The prototype example of these conducting polymers is polyacetylene, the simplest conjugated polymer, which consists of parallel chains of CH groups as shown in Figure 1.¹

Both the cis- and trans-forms (see Figure 1) can be prepared as silvery, flexible films, which can be made either free-standing or on a variety of substrates, such as glass or metal, with thicknesses varying from 10^{-5} to 0.5 cm. The trans-isomer is the thermodynamically stable form; complete isomerization from cis- to trans- $(CH)_x$ can be accomplished after synthesis by heating the film to temperatures above 150°C for a few minutes. Electron-microscopy




Figure 1. Cis and trans isomers of $(CH)_x$.

studies show that the as-formed $(CH)_x$ films consist of randomly oriented fibrils (typical fibril diameter $\sim 200\text{\AA}$). The films can be stretch-oriented in excess of three times their original length with concomitant partial alignment of the fibrils. The bulk density is 0.4 g/cm^3 , compared with 1.2 g/cm^3 as obtained by flotation techniques. Therefore, the polymer fibrils fill only about one third of the total volume and the effective surface area is quite high ($\sim 60\text{ m}^2/\text{g}$). X-ray studies show that the $(CH)_x$ films are highly crystalline.

Recent studies have demonstrated that, after synthesis, $(CH)_x$ films can be chemically doped at room temperature with a variety of donors or acceptors to form n - or p -type semiconductors.¹ (See Table I) Doping to high levels (above $\sim 1\%$) results in a semiconductor-metal transition giving a whole new class of metals with a wide range of electronegativity. Moreover, the existing experimental data already show that these materials have potential for use in a number of areas of future technology. Experimental studies at the University of Pennsylvania have demonstrated that doped polyacetylene might be useful in such diverse applications as: (1) the replacement of increasingly scarce conventional conductors by synthetic metals; (2) the development of lightweight, high-energy-density batteries; and (3) low-cost solar photovoltaic materials.

The electrical conductivity of polyacetylene can be varied in a controlled manner over thirteen orders of magnitude through chemical or electrochemical doping; results for three typical dopants are shown in Figure 2.¹ Values greater than $3 \times 10^3\ \Omega^{-1}\text{cm}^{-1}$ have already been achieved with only partially aligned




Figure 2. Electrical conductivity of doped trans-(CH)_x film as a function of dopant concentration.

TABLE I

Examples of p- and n-Type Doping of (CH)_xSelected Dopants for (CH)_x

<u>p-Type Dopants</u>	<u>(ohm⁻¹cm⁻¹ at 25°C)</u>
<u>cis</u> -(CH) _x	1.7 x 10 ⁻⁹
<u>trans</u> -(CH) _x	4.4 x 10 ⁻⁵
<u>cis</u> -(CHI _{0.30}) _x	5.5 x 10 ²
<u>trans</u> -(CHI _{0.20}) _x	1.6 x 10 ²
<u>cis</u> -[CH(IBr) _{0.15}] _x	4.0 x 10 ²
<u>cis</u> -[CH(AsF ₅) _{0.10}] _x	1.2 x 10 ³
<u>cis</u> -[CH(PF ₆) _{0.033}] _x	2.5 x 10 ¹
<u>cis</u> -[CH(H ⁺ AsF ₆ ⁻) _{0.1}] _x	7 x 10 ²
<u>cis</u> -[CH(H ₃ O ⁺ ClO ₄ ⁻) _{0.127}] _x	1.2 x 10 ³
<u>cis</u> -[CH(ClO ₄) _{0.065}] _x	9.7 x 10 ²
<u>cis</u> -[CH(H ₃ O ⁺ HSO ₄ ⁻) _{0.106}] _x	1.2 x 10 ³
<u>n-Type Dopants</u>	
<u>cis</u> -[Li _{0.30} (CH)] _x	2.0 x 10 ²
<u>cis</u> -[Na _{0.21} (CH)] _x	2.5 x 10 ¹
<u>cis</u> -[K _{0.16} (CH)] _x	5.0 x 10 ¹
<u>trans</u> -[Na _{0.28} (CH)] _x	8.0 x 10 ¹
<u>cis</u> -[ⁿ Bu ₄ N] _{0.03} (CH)] _x	1.0

Cis or trans refers to the principal isomeric species before doping.

samples, and analysis of the transport (electrical conductivity and related properties) and optical data implies that a further increase of at least one order of magnitude should be possible.

In simple terms, one may regard the bonding in $(CH)_x$ as being derived from the linking together of sp^2 hybridized (CH) units, the fourth carbon valence electron being in a p_π orbital perpendicular to the plane of the $(CH)_x$ molecule. A diagrammatic representation of the energy levels (band diagram) associated with the overlapping molecular orbitals of π symmetry formed by joining (CH) units together is given in Figure 3. The species depicted range from $(CH)_2$, i.e., $H_2C=CH_2$, to $(CH)_x$. The filled π molecular orbitals correspond to the valence band, the empty π^* orbitals to the conduction band, and the $\pi \rightarrow \pi^*$ transition energy to the band gap in a semiconductor or insulator. If all the C-C bonds were of equal length, having a bond order of 1.5 (one σ bond and half-filled π bond), $(CH)_x$ would be a metal with zero band gap; if the band gap were large, the resulting material would be an insulator. In the case of trans- $(CH)_x$, where the C-C bond length alternation is small, a band gap of approximately 1.5 eV results; the pure material is therefore a semiconductor.¹

The carriers (electrons and/or [positive] holes) generated by the doping of $(CH)_x$ result from charge transfer. Charge transfer occurs from polymer to acceptor (A) with the polymer chain acting as a poly(cation) in the presence of an A^- species. For a donor (M), the polymer chain acts as a poly(anion) in the presence of M^+ species. The A^- or M^+ ions reside between polymer chains. Reversible doping can be carried out electrochemically,² and chemical compensation has been demonstrated. For example, after doping and subsequent chemical compensation, the optical absorption spectrum converts back to that of the undoped polymer.³ Therefore, since the anisotropic optical properties of the undoped polymers are characteristic of the quasi-one-dimensional $(CH)_x$ chains,




Figure 3. Diagrammatic representation of the energy levels (band diagram) associated with the overlapping of molecular orbitals of π symmetry formed by joining (CH) units together.

the reversibility implies that the $(CH)_x$ chains remain intact in the doped polymer.

In $trans-(CH)_x$, three main electronic regimes are observed: (1) the semiconducting regime where the dopant concentration is small ($<0.1\%$) and the properties are similar to those of a doped semiconductor; (2) the metallic regime where the dopant concentration is $>6\%$ and the electronic properties (i.e., conductivity, thermoelectric power, absorption and reflectance spectra, specific heat, magnetic susceptibility, etc.) are characteristic of a metal;¹ and (3) the transitional region where the properties are intermediate between those of the semiconducting and metallic limits.⁴ This intermediate regime is in many ways the most interesting; for example, although the electrical conductivity is high, there appears to be no Pauli susceptibility suggesting the possibility of a non-traditional transport mechanism.⁴ However, since this transitional regime is not well understood, the present discussion will be limited primarily to the semiconducting regime and to the soliton concepts which are relevant to dilute doping.

SEMICONDUCTING REGIME: SOLITONS IN POLYACETYLENE

If the bond lengths in pure $trans-(CH)_x$ were uniform, the polymer would be a quasi-one-dimensional metal with a half-filled band. Such a system is unstable with respect to a dimerization distortion (the Peierls instability) in which adjacent CH groups move towards each other, forming alternately short (or double) bonds and long (or single) bonds, thereby lowering the energy of the system and opening the semiconductor band gap. Clearly, by symmetry, one could interchange the double and single bonds without changing the energy. Thus, there are two lowest-energy states, A and B, having two distinct bonding structures as shown in Figure 4. This twofold degeneracy leads to the existence of nonlinear topological excitations, bond-alternation domain walls or solitons, which appear to be responsible for many of the remarkable properties of $(CH)_x$.

When a single chain of $cis-(CH)_x$ begins to isomerize, the isomerization process can, in principal, commence at different parts of the chain, one having configuration (A), the other, configuration (B). When these two different configurations meet, a free radical is produced as shown schematically in Figure 4.




Figure 4. Formation of a neutral soliton by joining together the two lowest energy states, (A) and (B) of $trans-(CH)_x$.

This has been confirmed experimentally - when pure cis-(CH)_x, possessing no free spins, undergoes isomerization, approximately one in 3000 of the (CH) units in the resulting trans-(CH)_x is in the form shown in Figure 4 with an unpaired spin and a Curie law magnetic susceptibility. This species is actually a valid excited state of trans-(CH)_x, which could be formed in principal, for example, if trans-(CH)_x could be heated to a sufficiently high temperature without thermal decomposition. It would be expected that this free spin could be readily ionized leaving behind a positive charge. This has indeed been observed. Thus if (CH)_x is carefully and slowly oxidized by, for example, AsF₅, a stabilized carbonium ion is formed; the Curie spins originally present decrease almost to zero, and the conductivity of the material increases greatly.

If, for simplicity, it is first assumed that the unpaired spin resides completely on one (CH) unit, it may be regarded as being located in a non-bonding π molecular orbital, since it is not formally involved in π bonding to either of the adjacent (CH) units. Since a non-bonding π molecular orbital will lie midway between the π and π^* molecular orbitals, it is apparent that the energy level giving rise to this free spin will fall in the center of the band gap as shown in Figure 5. This localized non-bonding state formed at the boundary between the two degenerate phases (A and B) has been termed a "neutral soliton." Analogously, when this electron is removed, as described earlier, to give a carbonium ion, a mid-gap "positive soliton" is produced, as shown in Figure 6. Alternatively, if an electron is added to a neutral soliton as, for example, in the n-doping of (CH)_x by sodium to produce a stabilized carbanion, the mid-gap state is doubly occupied and a "negative soliton" is generated as depicted in Figure 7.

The presence of neutral solitons induced as defects during isomerization is a fortunate accident, for the number of thermally induced neutral soliton excitations in undoped (CH)_x would be far too small to be observable. In this context, however, it must be stressed that it is not necessary to first have neutral solitons in order to obtain positive (or negative) solitons. For example, it has been shown experimentally⁴ that on careful p-doping of (CH)_x with AsF₅




Figure 5. Diagrammatic representation of a neutral soliton (free radical located on a non-bonding π molecular orbital) in trans-(CH)_x.




Figure 6. Diagrammatic representation of a positive soliton (carbonium ion located on a non-bonding π molecular orbital) in trans-(CH)_x.




Figure 7. Diagrammatic representation of a negative soliton (carbanion located on a non-bonding π molecular orbital) in trans-(CH)_x.

that: (i) the original free Curie spins in (CH)_x decrease as indicated above and (ii) even though the amount of dopant species is far in excess of that necessary to remove the original free spins, no additional Curie spins appear. This is consistent with the generation of charged solitons according to the doping model shown in Figure 8.

In the previous discussion, it has been assumed that a soliton has been localized on a single (CH) unit. Detailed calculations have shown that minimization of the total energy spreads the soliton over a region of about 15 (CH) units.⁵ Thus, for example, in the case of a positive soliton, although the




Figure 8. Diagrammatic representation of p-type doping of trans-(CH)_x with no production of Curie or Pauli spins.

maximum charge density is adjacent to the counter anion, A⁻, ~85% of the charge is spread out symmetrically on either side over ~15 (CH) units. This is qualitatively understandable, since it is recognized from symmetry considerations that the positive soliton formally located on a single (CH) unit will actually have some interaction with the p_z orbitals on the adjacent (CH) units. This delocalizes the non-bonding mid-gap state over many bond-lengths as shown schematically in Figure 9(b). It is apparent that considerable bond length distortion will be involved near the center of the soliton, since these bonds alone are responsible for adjusting the bond lengths of segment (A) with those of segment (B) (Figure 9(a)) in which the relative positions of the formally single and double bonds are reversed. Since the energy to distort a bond is proportional to the square of the distortion, it is apparent that if the distortion were spread out over several bonds, the distortional energy required would be less. Hence, the system is stabilized if the bond distortion is taken up by several bonds as shown diagrammatically in Figure 9(b) to produce a positive soliton or domain wall, which separates (A) type domains from (B) type domains. We note that within these domain walls (particularly near the center), the C-C bond lengths tend to become very nearly equal. It might at first be thought that the greatest stabilization would result if the distortion were spread out over the whole chain. This, however, is not the case because of the Peierls distortion stabilizing energy, which, for a hypothetical 1-dimensional molecule, predicts that a single-double bond alternating structure has a lower total energy and thus, is more stable than one consisting totally of equal (bond order 1.5) linkages. These two opposing distortional effects involving bond lengths result in the soliton domain walls in (CH)_x being extended to approximately 15 (CH) units.




Figure 9. Diagrammatic representation of the delocalization of a positive soliton in $\text{trans}-(\text{CH})_x$: (a) charge localized on one (CH) unit; (b) charge localized over ~ 15 (CH) units.

Conductivity-temperature studies show that the conduction process in $(\text{CH})_x$ in the semiconducting regime proceeds by a hopping mechanism.⁶ Although this may involve movement of a positive or negative soliton along a chain, recent calculations predict that an interchain hopping mechanism involving the "capture" of a mobile electron from a neutral soliton in one chain by a relatively non-mobile positive (or negative) soliton in an adjacent chain may be the dominant mechanism. The experimental results for undoped $\text{trans}-(\text{CH})_x$ are in excellent agreement with this inter-soliton hopping theory.

Implicit to the whole concept of soliton doping in $(\text{CH})_x$ in the semiconducting regime is that as doping proceeds, there is no increase in the number of free spins (neutral solitons). This is consistent with measurements on carefully doped $(\text{CH})_x$.⁴ In this respect, the behavior of $(\text{CH})_x$ is exactly the opposite of that found during the doping of a classical semiconductor such as silicon, in which the number of unpaired spins increases as doping proceeds. This phenomenon in $(\text{CH})_x$ is due to the unique symmetry of the material in the trans form

as shown in Figure 10. Thus if a perfect (diamagnetic) trans-(CH)_x sequence were treated with two p-type dopant species, A, and two electrons were removed from two different filled π orbitals, then two unpaired electrons would be found (associated with two positive holes in the valence band), provided no change in the direction of bond alternation had occurred. However, as noted above, the production of unpaired electrons is not observed experimentally. If, however, a rearrangement of electrons occurs as shown in Figure 10 with a concomitant rearrangement of formally single and double C-C bonds, the positive holes will rise out of the valence band as shown. Since (A) and (B) segments of (CH)_x are energetically identical and since the "rising" of positive holes results^x in stabilization of a system,^{*} the formation of mid-gap positive solitons is favored energetically as compared to positive holes in the valence band. As noted previously, the positive charge is not localized on just one (CH) unit as shown in Figures 9 and 10 but is actually spread over approximately 15 (CH) units, the magnitude of the charge on each (CH) unit diminishing with increasing distance from the counter anion, A⁻, adjacent to the chain. Thus, the observation that the Curie susceptibility of trans-(CH)_x decreases on careful p-doping due to the conversion of neutral solitons to positive solitons and that additional positive solitons are formed with no production of Curie spins is consistent with the soliton concept of doping.

Spectroscopic evidence for the mid-gap soliton state is obtained from the change in the absorption spectrum of trans-(CH)_x as a result of doping. The intensity of the band gap transition at approximately 1.5 eV decreases as a new transition, turning on at approximately 0.75 eV, appears and increases in intensity during doping. Further strong evidence for the formation of solitons during p-doping is obtained from the infrared spectra of both trans-(CH)_x and trans-(CD)_x doped to the semiconducting regime.⁸ The soliton infrared active vibrational modes in (CH)_x appear at 1385 cm⁻¹ and 900 cm⁻¹; the corresponding modes in the deuterated material occur at 800 cm⁻¹ and 1100 cm⁻¹, respectively. These modes are predicted both for (CH)_x and (CD)_x within a few percent accuracy by calculations based on the soliton theory.

CONCLUSION

In conclusion, experimental and theoretical evidence obtained to date is consistent with the soliton concept of bonding in parent (CH)_x and (CH)_x doped within the semiconducting regime. The solitons in trans-(CH)_x are proving to be fascinating to both chemists and physicists. To the physicists, they represent non-linear topological excitations resulting from the fundamental broken symmetry of the trans-(CH)_x chain. As a result, the study of polyacetylene is leading to a deeper understanding of such esoteric concepts as fractional charge and particle confinement. To the chemists, solitons represents a fundamental mechanism for stabilization of the carbonium ion and the carbanion. In effect, the switch in bond alternation and the associated distortions provide a kind of "solvation" energy which acts to stabilize and delocalize the added charge on the chain. In this sense, the existence of solitons is fundamentally responsible

*Electrons may be regarded as analogous to billiard balls - a system is stabilized by their rolling downhill! Positive holes may be regarded as analogous to balloons - a system is stabilized by their floating upwards!




Figure 10. Diagrammatic representation of the formation of a positive soliton on p-doping $\text{trans}-(\text{CH})_x$.

for the ease with which polyacetylene can be doped, n-type or p-type, through charge transfer.

Although results of detailed calculations have been presented to describe the transition from isolated solitons at low dopant concentrations to the metallic state at high dopant concentration, much remains to be done. Heavily doped $(\text{CH})_x$ exhibits the electronic properties of a true metal. Above ~6% doping, $(\text{CH})_x$ displays high conductivity,⁶ a Pauli temperature independent paramagnetic susceptibility,⁴ a linear dependence on temperature of the thermopower⁹ and low temperature heat capacity,¹⁰ the infrared properties of a metal,¹ etc. There is strong evidence leading to the conclusion that in this metallic regime, the C-C bond lengths have become equal since (for both p- and n-doped $(\text{CH})_x$) the band gap (π - π^*) transition disappears.³ At this degree of doping, the solitons may be regarded as having overlapped with each other to form a conduction band which fills in the semiconductor band gap. On heavy doping, $(\text{CH})_x$ becomes a metal, not a degenerate semiconductor, as does a classical semiconductor such as Si, in which the band gap remains even after it is heavily doped to concentrations well above the semiconductor-metal transition. In a general sense, the implied change from bond-alternating to nearly uniform bond structure is consistent with the soliton doping mechanism. However, a detailed understanding of the transition to metallic behavior is lacking. The intermediate transition regime remains as the least well understood aspect of the problem and presents an exciting challenge for continued study.

ACKNOWLEDGMENT

This work was supported jointly by the Office of Naval Research and the Defense Advanced Research Projects Agency (through a grant monitored by the Office of Naval Research) and the National Science Foundation Materials Research Program (Grant No. DMR 7923647).

REFERENCES

1. A. G. MacDiarmid and A. J. Heeger, "Organic Metals and Semiconductors: The Chemistry of Polyacetylene, $(\text{CH})_x$, and its Derivatives," Synthetic Metals, **1**, 101-118 (1979/80).
2. D. F. MacInnes, Jr., M. A. Druy, P. J. Nigrey, D. P. Nairns, A. G. MacDiarmid, and A. J. Heeger, "Organic Batteries: Reversible n- and p-Type Electrochemical Doping of Polyacetylene, $(\text{CH})_x$," J.C.S. Chem. Comm. 317 (1981).
3. T. C. Clarke and G. B. Street, "The Chemical Nature of Polyacetylene Doping," Synthetic Metals **1**, 119-131 (1979/80); T.-C. Chung, A. Feldblum, A. J. Heeger, and A. G. MacDiarmid, "Experimental Studies of Sodium-Doped Polyacetylene: Optical and ESR Results for Metallic $[\text{CHNa}]_x$," J. Chem. Phys., in press, (1981).
4. S. Ikehata, J. Kaufer, T. Woerner, A. Pron, M. A. Druy, A. Sivak, A. J. Heeger, and A. G. MacDiarmid, "Solitons in Polyacetylene: Magnetic Susceptibility," Phys. Rev. Lett. **45**, 1123 (1980).

5. W. P. Su, J. R. Schrieffer, and A. J. Heeger, "Soliton Excitations in Polyacetylene," Phys. Rev. B 22, 2099 (1980).
6. Y.-W. Park, A. J. Heeger, M. A. Druy, and A. G. MacDiarmid, "Electrical Transport in Doped Polyacetylene," J. Chem. Phys. 73, 946 (1980).
7. N. Suzuki, M. Ozaki, S. Etemad, A. J. Heeger, and A. G. MacDiarmid, "Solitons in Polyacetylene: Effects of Dilute Doping on Optical Absorption Spectra," Phys. Rev. Lett. 45, 1209 (1980).
8. S. Etemad, A. Pron, A. J. Heeger, and A. G. MacDiarmid, "Infrared Active Vibrational Modes of Charged Solitons in $(CH)_x$ and $(CD)_x$," J. Chem. Phys., in press (1981).
9. Y.-W. Park, A. Denenstein, C. K. Chiang, A. J. Heeger, and A. G. MacDiarmid, "Semiconductor-Metal Transition in Doped $(CH)_x$: Thermoelectric Power," Sol. State Comm. 29, 747 (1979).
10. D. Moses, A. Denenstein, A. Pron, A. J. Heeger, and A. G. MacDiarmid, "Specific Heats of Pure and Doped Polyacetylene," Sol. State Comm. 36, 219 (1980).

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Western Regional Office Attn: Dr. R. J. Marcus 1030 East Green Street Pasadena, California 91106	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Eastern Regional Office Attn: Dr. L. E. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Naval Weapons Center Attn: Dr. A. B. Amster, - Chemistry Division China Lake, California 93555	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Commander, Naval Air Systems Command Attn: Code 3100 (E. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
		Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

TECHNICAL REPORT DISTRIBUTION LIST, GENNo.
Copies

Mr. James Kelley
DTNSRDC Code 281
Annapolis, Maryland 21402

1

Mr. A. M. Annaloue
Administrative Librarian
PLASTEC/ARRADCOM
Bldg 3401
Dover, New Jersey 07801

1

TECHNICAL REPORT DISTRIBUTION LIST, 3568

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Dr. C. L. Shilling Union Carbide Corporation Chemical and Plastics Tarrytown Technical Center Tarrytown, New York	1	Dr. E. Fischer, Code 2853 Naval Ship Research and Development Center Annapolis Division Annapolis, Maryland 21402	1
Dr. R. Soulen Contract Research Department Pennwalt Corporation 900 First Avenue King of Prussia, Pennsylvania 19406	1	Dr. Martin H. Kaufman, Head Materials Research Branch (Code 4542) Naval Weapons Center China Lake, California 93555	1
Dr. A. G. MacDiarmid University of Pennsylvania Department of Chemistry Philadelphia, Pennsylvania 19174	1	Dr. C. Allen University of Vermont Department of Chemistry Burlington, Vermont 05401	1
Dr. H. Allcock Pennsylvania State University Department of Chemistry University Park, Pennsylvania 16802	1	Professor R. Drago Department of Chemistry University of Illinois Urbana, Illinois 61801	1
Dr. M. Kenney Case-Western University Department of Chemistry Cleveland, Ohio 44106	1		
Dr. R. Lenz University of Massachusetts Department of Chemistry Amherst, Massachusetts 01002	1	COL R. W. Bowles, Code 100M Office of Naval Research 800 N. Quincy Street Arlington, Virginia 22217	1
Dr. M. David Curtis University of Michigan Department of Chemistry Ann Arbor, Michigan 48105	1	Professor T. Katz Department of Chemistry Columbia University New York, New York 10027	1
NASA-Lewis Research Center Attn: Dr. T. L. Sarafini, MS 49-1 21000 Brookpark Road Cleveland, Ohio 44135	1	Professor James Chien Department of Chemistry University of Massachusetts Amherst, Massachusetts 01002	1
Dr. J. Griffith Naval Research Laboratory Chemistry Section, Code 6120 Washington, D.C. 20375	1	Professor Malcolm B. Polk Department of Chemistry Atlanta University Atlanta, Georgia 30314	1
Dr. G. Goodman Globe-Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1	Dr. G. Bryan Street IBM Research Laboratory, K32/281 San Jose, California 95193	1