

AD A108870

DTIC FILE COPY

OFFICE OF NAVAL RESEARCH

Contract N00014-80-C-0538

Task No. NR-051-736

TECHNICAL REPORT NO. 6

SIMS STUDIES ON ANOMALOUS BEHAVIOR OF PHORPHORUS
AND OTHER IMPLANTS IN SILICON

BY

Paul K. Chu, Dachang Zhu , and George H. Morrison*

Department of Chemistry
Cornell University
Ithaca, N. Y. 14853

December 17, 1981

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited.

DTIC
ELECTE
DEC 28 1981
S D D

81 12 28 018

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report No. 6	2. GOVT ACCESSION NO. AD-A108 870	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) SIMS Studies on Anomalous Behavior of Phosphorus and Other Implants in Silicon		5. TYPE OF REPORT & PERIOD COVERED Interim Technical Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) Paul K. Chu, Dachang Zhu, George H. Morrison		8. CONTRACT OR GRANT NUMBER(s) N00014-80-C-0538
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry Cornell University Ithaca, New York		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 051-736
11. CONTROLLING OFFICE NAME AND ADDRESS ONR (472) 800 N. Quincy St., Arlington, Va. 22217		12. REPORT DATE December 17, 1981
		13. NUMBER OF PAGES 18
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release: distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Prepared for publication in RADIATION EFFECTS		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) secondary ion mass spectrometry, ion implantation, depth profiles, phosphorus, silicon, ion microprobe		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A phosphorus implant in p-type silicon was analyzed by SIMS, and both the implant profile and the matrix signal were observed to exhibit some anomalous behavior. Further studies revealed the same behavior in other implants. This phenomenon was observed when an n-type dopant was implanted into a p-type matrix, or vice versa. However, some exceptions arose, making the interpretation difficult. The use of matrix signal normalization was adopted and found to improve the results. ←		

SIMS STUDIES ON ANOMALOUS BEHAVIOR OF PHOSPHORUS
AND OTHER IMPLANTS IN SILICON

by

Paul K. Chu, Dachang Zhu¹, and George H. Morrison*

Department of Chemistry
Cornell University
Ithaca, N. Y. 14853

1. Permanent address:

Dachang Zhu
Dept. of Chemistry
Fudan University
Shanghai
People's Republic of China

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A	

1. INTRODUCTION

Ion implantation has rapidly become a common and important doping technique for semiconductor materials because it offers advantages over conventional diffusion methods. Since the electrical properties depend on the concentration and location of the implanted species, ion implant distributions have been studied by both theoretical and empirical methods.¹⁻⁷ Of all the experimental techniques presently available, secondary ion mass spectrometry (SIMS) is one of the most widely used because it offers exceptional depth resolution and sensitivity.

We recently examined several phosphorus implants in silicon and found, for the case of p-type silicon, that the phosphorus implant profile was not the symmetrical Gaussian distribution predicted by the LSS theory⁵. In addition, the intensity of the silicon matrix signal did not remain constant throughout the depth profile. This discovery prompted further investigation with a series of implants. While some exceptions were noted, this work led to the general conclusion that polarity differences between the implanted species and the bulk matrix doping species would significantly alter the results of SIMS analysis of ion implanted silicon.

2. EXPERIMENTAL

Sample Preparation.

The p-type silicon and n-type silicon were purchased commercially and supplier polished. The samples were cut and mounted on aluminum discs with conductive silver paint for ion implantation and SIMS analysis.

Ion Implantation.

Ion implantation was performed on an Accelerators Inc. 300R ion implanter employing a hot filament ion source. Prior to implantation, each sample was cleaned with acetone and methanol. The focused ion beam was rastered over an area of about 27 cm^2 with the dose rate kept below 0.5 Amp/cm^2 to insure room temperature implantation. The implantation parameters for each sample are listed in Table 1.

SIMS Measurements.

SIMS analyses were done using a CAMECA IMS-300 ion microscope⁸. An oxygen primary beam ($O_2^+/O^+ = 10$), accelerated at 14.5 KeV and impinging at 57° incidence for negative secondary ions, and at 5.5 KeV and 33° for positive secondary ions was used. A primary current of 200nA was rastered over an area of $500 \times 500 \mu m^2$ yielding a flat crater bottom. All analyses were performed at a residual pressure of 10^{-7} Torr, and with the electrostatic analyzer tuned to maximum sensitivity for a 4.5 KeV sample voltage. The CAMECA IMS-300 was interfaced to a Digital Equipment Corp. PDP 11/20 minicomputer for data acquisition and manipulation, and a GT-40 for display. The projected range, R_p , and the standard deviation of the assumed Gaussian distribution, σ , were calculated by the computer. The depth of the craters were measured by a Talystep stylus device with a resolution of 50-100 Å. Normalization was accomplished by the computer performing a point by point ratio of two profiles.

3. RESULTS AND DISCUSSION

A 200 KeV 2×10^{15} atoms/cm² phosphorus implant in p-type silicon (100) originally doped with boron at a level of 10^{15} atoms/cm³ was analyzed by SIMS using negative secondary ion detection. As shown in Figure 1, the phosphorus profile was found to be asymmetrical with the trailing edge falling off much more rapidly than the leading edge. In addition, the silicon matrix signal, which would be expected to be flat, exhibited an anomalous depression just after the peak of the implant. However, a phosphorus implant in n-type Si (100) gave the expected symmetrical Gaussian P^- profile and constant Si^- signal.

Since the effect was observed when phosphorus, an n-type dopant, was implanted into a bulk p-type doped silicon matrix, boron, a p-type dopant, was implanted into a bulk n-type doped silicon matrix to check if a similar effect would result. Figure 2 gives the result showing again the distortion of the expected Gaussian. Once again, boron implanted into p-type silicon did not show this anomaly.

There have been a number of studies on the influence of implant induced damage and diffusion on implant distributions⁹⁻¹⁶. This phenomenon, however, seems to follow principally from the difference in polarity between the implanted element and the original bulk dopant. To further check this, a vapor epitaxial silicon layer deposited on an n-type Si(100) substrate was implanted with phosphorus. As shown in Figure 3, this implant did not show the anomaly.

It has been reported¹⁷ that the use of an oxygen leak during SIMS analysis serves to amorphize the crystalline or damaged region by forming an oxide layer. The same experiments mentioned previously were repeated under a 10^{-4} Torr oxygen backfill. No change in the results was observed. Moreover, there was further evidence that matrix damage was not responsible for this behavior. Those implants which gave anomalous results were annealed by heating under a slow nitrogen flow for 20 minutes at 800°C . Previous studies have shown that this is sufficient to anneal out implant damage without significantly altering the shape of the implant concentration profile. Annealing had no detectable corrective effect on the observed anomaly.

In an attempt to discover the degree of this polarity offset, a set of phosphorus implants in p-type silicon (100) were made to measure the effect of the implant dosage. The results revealed that the degree of asymmetry of the Gaussian implant profile and the amount of distortion from the ideal constant matrix signal were positively related to the implant fluences.

The study was then extended to include the remaining implants as shown in Table 1. In addition to phosphorus, five elements, nitrogen, arsenic, chlorine, bromine, and iodine showed this anomalous behavior in p-type silicon. Figure 4 gives the nitrogen profile (SiN^- was monitored for sensitivity) and Figure 5 shows the results of the bromine implant.

(Chlorine gave results similar to nitrogen while iodine was much like bromine). Interestingly enough, fluorine did not exhibit any deviation from the expected Gaussian. Gallium and indium also gave symmetrical

peaks with no Si signal variations.

These results, particularly the fluorine data, indicate that while a polarity difference between the implant ion and substrate is a necessary condition for this anomalous behavior, it is not a sufficient one. The issue is further clouded by the observation that, due to their strong electron affinities, the halogen elements are sometimes regarded as p-type dopants. Therefore, other factors are also contributing to this effect.

This phenomenon can have two origins, an intrinsic problem of the implant and substrate, or a SIMS phenomenon, or both. One common SIMS artifact is charging. To be sure that there was no charging effect at the implant produced n-p junction during ion bombardment, the surface of the implant sample was physically connected to the sample mount using conductive silver paint. The sample holder with attached sample was then coated with a thin, vapor deposited layer of gold to insure good electrical conduction. These samples showed no decrease in the severity of the observed anomaly. To further investigate if this anomaly was instrument dependent, a phosphorus implant in p-type silicon (100) was analyzed using a CAMECA-IMS-3f instrument. Similar effects were observed.

Although no definitive explanation of this effect could be deduced, it is still important from a practical viewpoint. In semiconductor device fabrication, the mean depth and degree of spreading of an ion implant are very important. These parameters can be predicted by the LSS Theory to within $\pm 20\%$. Using SIMS analysis, these values can be determined with a precision of 5% and 10% for the mean depth and standard deviation of the Gaussian, respectively. However, due to this anomalous behavior, the experimental values of these parameters are quite different from those predicted by the LSS Theory.

Further, owing to their inherent ability to inject an accurately known quantity of a given ion species into a selected host, implants also function as calibration standards for the quantification of many surface techniques including SIMS. There are two ways to calculate the concentration

at the peak of an implant. The first ¹⁸ assumes the Gaussian profile as an ideal Gaussian distribution to calculate the peak concentration, given the standard deviation of the Gaussian and the implant fluence. The second method ¹⁹ ignores the actual experimental distribution and instead uses the construct of the hypothetical equivalence. While the distortion of the implant profile observed will have no effect on quantification based on the second method, it will lead to errors using the first method. Hence, for both quantitative and qualitative (i.e. mean depth, etc.) analyses, correction of this anomaly is important.

This can be accomplished quite well by normalizing the phosphorus implant profile to the matrix silicon profile point by point. Figure 6 shows the result of this procedure. The normalized phosphorus profile is given as well as the phosphorus implant profile as observed and the observed ²⁸Si profile. It is immediately apparent that the normalized profile agrees much better with the symmetrical LSS Gaussian distribution. Table 2 lists the mean depths or ranges, R_p , and standard deviations, σ , calculated from both the original and normalized phosphorus profiles as well as the values predicted by the LSS Theory. It shows a significant improvement in the data. This improvement also carries over into quantitative analysis. For the observed phosphorus implant profile, the difference between the peak concentrations yielded by methods 1 and 2 is 11%. However, after applying the ratio correction method, this difference is reduced to 3.7%, indicative of the closer agreement to a Gaussian distribution required by quantitative method one.

Thus, application of this correction method can improve both the external ¹⁹ and internal ²⁰ calibration methods when this anomaly is encountered.

ACKNOWLEDGEMENTS

Acknowledgement is given to W.C. Harris, Jr. for his assistance in manuscript preparation.

This work was supported by the National Science Foundation, the Office of Naval Research, and the Cornell Materials Science Center. The use of the ion implantation facilities of the National Research and Resource for Submicron Structures at Cornell University is acknowledged.

REFERENCES

1. J.W. Mayer, L. Erikson, and J.A. Davies, Ion Implantation in Semiconductors (Academic Press, New York, 1970).
2. R. Collins and G. Carter, Rad. Eff., 26, 181 (1975).
3. V. V. Yudin, App. Phys., 15, 223 (1978)
4. D.P. Leta, G.H. Morrison, G.H. Harris, and C.A. Lee, Int. J. of Mass Spect. & Ion Phys., 34, 147 (1980).
5. J. Lindhard, M.Scharff, and H.E. Schiott, Mat. Fys. Medd, Dan. Vid. Selsk, 33 (1963).
6. J.F. Gibbons, W.F. Johnson, and S. Mybroie, Projected Range Statistics (Whitney, Stroudsburg, Pa., 1975).
7. B. S. Harwell, Ion Implantation Range Data for Silicon and Germanium Device Technologies (Research Studies Press Inc., 1977).
8. G.H. Morrison & G. Slodzian, Anal. Chem., 47, 932A (1975).
9. P. Blood, G. Dearnaley, and M.A. Wilkins, Rad. Eff., 21, 245 (1974).
10. K. Seshan and J. Washburn, Rad. Eff., 26, 31 (1975).
11. M. Miyao, N. Yoshihiro, T. Tokuyama, and T. Mitsuishi, J. App. Phys., 49, 2573 (1978).
12. K. Seshan and J. Washburn, Rad. Eff., 37, 147 (1978).
13. A. Schmidt and G. Schorer, App. Phys., 22, 137 (1980).

14. T. Hirao, K. Inoue, Y. Yaegashi, and S. Takayanagi, Jap. J. of App. Phys., 18, 647 (1979).
15. A. Desalvo, R. Galloni, R. Rosa, and F. Zignani, J. App. Phys., 51, 1994 (1980).
16. W.K. Hofker, H.W. Werner, D.P. Oosthoek, and H.A.M. deGrefte, App. Phys., 2, 265 (1973).
17. K. Tsunoyama, T. Suzuki, and T. Ohashi, Jap. J. of App. Phys., 15, 349 (1976).
18. R.G. Wilson, G. R. Brewer, Ion Beams with Applications to Ion Implantation (John Wiley and Sons, New York, 1973) p. 279.
19. D.P. Leta and G.H. Morrison, Anal. Chem., 52, 514 (1980).
20. D.P. Leta and G.H. Morrison, Anal. Chem., 52, 277 (1980).

Table 1: Implantation Parameters.

Implant Element	Matrix	Fluence	Energy	Source
^{11}B	n-Si, p-Si	1.0×10^{15}	100KV	BF_3 gas
^{14}N	n-Si, P-Si	5.0×10^{15}	200KV	N_2 gas
^{31}P	n-Si, p-Si	$2.0-4.0 \times 10^{15}$	200KV	PF_5 gas
^{19}F	n-Si, p-Si	2.0×10^{14}	200KV	PF_5 gas
^{35}Cl	n-Si, p-Si	2.0×10^{14}	200KV	NaCl solid
^{81}Br	n-Si, p-Si	2.0×10^{14}	300KV	Br_2 gas
^{127}I	n-Si, p-Si	5.0×10^{14}	250KV	CsI solid
^{69}Ga	n-Si, p-Si	2.0×10^{14}	250KV	GaAs solid
^{75}As	n-Si, p-Si	1.0×10^{15}	250KV	GaAs solid
^{115}In	n-Si, P-Si	5.0×10^{14}	250KV	In solid

Table 2. σ and R_p values for the uncorrected, normalized and theoretical phosphorus profiles (values in parentheses are the % error calculated from the theoretical values).

	<u>Uncorrected</u>	<u>Normalized</u>	<u>Theoretical</u>
σ (Å)	566 (-27%)	692(-11%)	775
R_p (Å)	2337 (-8.0%)	2463(-2.3%)	2539

CAPTIONS

Figure 1 Depth profile of ^{31}P implanted Si, showing the anomalous asymmetry and matrix signal non-uniformity.

Figure 2 Depth profile of ^{11}B implanted Si showing asymmetry.

Figure 3 Depth profile of ^{31}P implanted into intrinsic Si. No anomalous behavior is seen.

Figure 4 Depth profile of ^{14}N implanted Si. Asymmetry is not apparent, but the matrix Si^- signal still exhibits the anomaly.

Figure 5 Depth profile of ^{79}Br implanted Si. Similar anomaly is observed.

Figure 6 Depth profile of ^{31}P implanted Si, with the P^-/Si^- ratio profile also shown. Normalized profile is more symmetrical.

FIGURE 1




FIGURE 2




FIGURE 3




FIGURE 4




FIGURE 5





FIGURE 6



TECHNICAL REPORT DISTRIBUTION LIST, 051C

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. M. B. Denton Department of Chemistry University of Arizona Tucson, Arizona 85721	1	Dr. John Duffin United States Naval Postgraduate School Monterey, California 93840	1
Dr. R. A. Osteryoung Department of Chemistry State University of New York at Buffalo Buffalo, New York 14214	1	Dr. G. M. Hieftje Department of Chemistry Indiana University Bloomington, Indiana 47401	1
Dr. R. R. Kovalski Department of Chemistry University of Washington Seattle, Washington 98105	1	Dr. Victor L. Rehn Naval Weapons Center Code 3813 China Lake, California 93555	1
Dr. S. P. Perone Department of Chemistry Purdue University Lafayette, Indiana 47907	1	Dr. Christie G. Enke Michigan State University Department of Chemistry East Lansing, Michigan 48824	1
Dr. D. L. Venezky Naval Research Laboratory Code 6130 Washington, D.C. 20375	1	Dr. Kent Eisentraut, MBT Air Force Materials Laboratory Wright-Patterson AFB, Ohio 45433	1
Dr. H. Freiser Department of Chemistry University of Arizona Tucson, Arizona 85721	1	Walter G. Cox, Code 3632 Naval Underwater Systems Center Building 148 Newport, Rhode Island 02840	1
Dr. Fred Saalfeld Naval Research Laboratory Code 6110 Washington, D.C. 20375	1	Professor Isiah M. Warner Texas A&M University Department of Chemistry College Station, Texas 77840	1
Dr. H. Chernoff Department of Mathematics Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Professor George H. Morrison Cornell University Department of Chemistry Ithaca, New York 14853	1
Dr. K. Wilson Department of Chemistry University of California, San Diego La Jolla, California	1	Professor J. Janata Department of Bioengineering University of Utah Salt Lake City, Utah 84112	1
Dr. A. Zirino Naval Undersea Center San Diego, California 92132	1	Dr. Carl Heller Naval Weapons Center China Lake, California 93555	1
		Dr. L. Jarvis Code 6100 Naval Research Laboratory Washington, D.C. 20375	1

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Branch Office Attn: Dr. George Sandoz 536 S. Clark Street Chicago, Illinois 60605	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Area Office Attn: Scientific Dept. 715 Broadway New York, New York 10003	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
ONR Western Regional Office 1030 East Green Street Pasadena, California 91106	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
ONR Eastern/Central Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Office of Naval Research Attn: Dr. Richard S. Miller 800 N. Quincy Street Arlington, Virginia 22217	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Ship Research and Development Center Attn: Dr. G. Bosmajian, Applied Chemistry Division Annapolis, Maryland 21401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Dr. Rudolph J. Marcus Office Naval Research Scientific Liaison Group- Amer. Embassy APO San Francisco 96503	1	Mr. James Kelley DTNSRDC Code 2803 Annapolis, Maryland 21402	1