

Resolution Test Chart

12

ADA112208

DTIC FILE COPY

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER Technical Report #9	2. GOVT ACCESSION NO. AD-A112208	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) Studies of Elastic Properties of Stretch Films of Polycarbonate by Brillouin Scattering	5. TYPE OF REPORT & PERIOD COVERED Technical Report	
	6. PERFORMING ORG. REPORT NUMBER	
7. AUTHOR(s) Quan-L. Liu and C. H. Wang	8. CONTRACT OR GRANT NUMBER(s) N00014 79C 0507 Serial RC-607	
9. PERFORMING ORGANIZATION NAME AND ADDRESS Department of Chemistry University of Utah Salt Lake City, Utah 84112	10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS	
11. CONTROLLING OFFICE NAME AND ADDRESS Office of Naval Research 800 N. Quincy St., Arlington, VA. 22217	12. REPORT DATE February 22, 1982	
	13. NUMBER OF PAGES 13	
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)	15. SECURITY CLASS. (of this report) Unclassified	
	15a. DECLASSIFICATION/DOWNGRADING SCHEDULE	
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release, distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES  Prepared for publication in Macromolecules		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)  Brillouin Scattering Polycarbonate films Elastic constants Chain morphology		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)  > Results of the Brillouin scattering study of polycarbonate (PC) films stretched at a temperature slightly above T <sub>g</sub> are reported. The elastic constants C <sub>11</sub> , C <sub>13</sub> , C <sub>33</sub> , and C <sub>44</sub> are determined as a function of stretched ratio. Using the affine orientational model recently developed by Wang and Cavanaugh, the orientation parameter is obtained as a function of stretched ratio. The changes in the elastic constants and the orientation parameter are discussed in terms of chain morphology. The results in PC films are found to be significantly different from other polymer films, such		

DTIC  
SELECTED  
MAR 19 1982  
H

DD FORM 1473  
1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE  
S/N 0102-LF-014-6601

82 03 20 112

as poly(ethylene terephthalate) and isotactic polypropylene, recently investigated in this laboratory. The reason for the difference is discussed.

<b>Accession For</b>	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Distribution/	
Date	
A	



TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 472 800 North Quincy Street Arlington, Virginia 22217	2	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 1211 Research Triangle Park, N.C. 27709	1
ONR Branch Office Attn: Dr. George Sandoz 536 S. Clark Street Chicago, Illinois 60605	1	Naval Ocean Systems Center Attn: Mr. Joe McCartney San Diego, California 92152	1
ONR Area Office Attn: Scientific Dept. 715 Broadway New York, New York 10003	1	Naval Weapons Center Attn: Dr. A. B. Amster, Chemistry Division China Lake, California 93555	1
ONR Western Regional Office 1030 East Green Street Pasadena, California 91106	1	Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko Port Hueneme, California 93401	1
ONR Eastern/Central Regional Office Attn: Dr. L. H. Peebles Building 114, Section D 666 Summer Street Boston, Massachusetts 02210	1	Department of Physics & Chemistry Naval Postgraduate School Monterey, California 93940	1
Director, Naval Research Laboratory Attn: Code 6100 Washington, D.C. 20390	1	Dr. A. L. Slafkosky Scientific Advisor Commandant of the Marine Corps (Code RD-1) Washington, D.C. 20380	1
The Assistant Secretary of the Navy (RE&S) Department of the Navy Room 4E736, Pentagon Washington, D.C. 20350	1	Office of Naval Research Attn: Dr. Richard S. Miller 800 N. Quincy Street Arlington, Virginia 22217	1
Commander, Naval Air Systems Command Attn: Code 310C (H. Rosenwasser) Department of the Navy Washington, D.C. 20360	1	Naval Ship Research and Development Center Attn: Dr. G. Boswain, Applied Chemistry E Annapolis, Maryland 21401	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12	Naval Ocean Systems Center Attn: Dr. S. Yamamoto, Marine Sciences Division San Diego, California 91232	1
Dr. Fred Saalfeld Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1

TECHNICAL REPORT DISTRIBUTION LIST, GENNo.  
Copies

Dr. Rudolph J. Marcus  
Office of Naval Research  
Scientific Liaison Group  
American Embassy  
APO San Francisco 96503 1

Mr. James Kelley  
DTNSRDC Code 2803  
Annapolis, Maryland 21402 1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No. Copies</u>		<u>No. Copies</u>
Dr. Stephen H. Carr Department of Materials Science Northwestern University Evanston, Illinois 60201	1	Picatinny Arsenal Attn: A. M. Anzalone, Building 3401 SMUPA-FR-M-D Dover, New Jersey 07801	1
Dr. M. Broadhurst Bulk Properties Section National Bureau of Standards U.S. Department of Commerce Washington, D.C. 20234	2	Dr. J. K. Gillham Department of Chemistry Princeton University Princeton, New Jersey 08540	1
Professor G. Whitesides Department of Chemistry Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Douglas Aircraft Co. Attn: Technical Library Cl 290/36-84 AUTO-Sutton 3855 Lakewood Boulevard Long Beach, California 90846	1
<del>Professor J. Wang Department of Chemistry University of Utah Salt Lake City, Utah 84112</del>	1	Dr. E. Baer Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. V. Stannett Department of Chemical Engineering North Carolina State University Raleigh, North Carolina 27607	1	Dr. K. D. Pae Department of Mechanics and Materials Science Rutgers University New Brunswick, New Jersey 08903	1
Dr. D. R. Uhlmann Department of Metallurgy and Material Science Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	NASA-Lewis Research Center Attn: Dr. T. T. Serofini, MS-49-1 21000 Brookpark Road Cleveland, Ohio 44135	1
Naval Surface Weapons Center Attn: Dr. J. M. Augl, Dr. B. Hartman White Oak Silver Spring, Maryland 20910	1	Dr. Charles H. Sherman Code TD 121 Naval Underwater Systems Center New London, Connecticut	1
Dr. G. Goodman Globe Union Incorporated 5757 North Green Bay Avenue Milwaukee, Wisconsin 53201	1	Dr. William Risen Department of Chemistry Brown University Providence, Rhode Island 02192	1
Professor Hatsuo Ishida Department of Macromolecular Science Case-Western Reserve University Cleveland, Ohio 44106	1	Dr. Alan Gent Department of Physics University of Akron Akron, Ohio 44304	1

TECHNICAL REPORT DISTRIBUTION LIST, 356A

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Mr. Robert W. Jones Advanced Projects Manager Hughes Aircraft Company Mail Station D 132 Culver City, California 90230	1	Dr. T. J. Reinhart, Jr., Chief Composite and Fibrous Materials Branch Nonmetallic Materials Division Department of the Air Force Air Force Materials Laboratory (AFSC) Wright-Patterson AFB, Ohio 45433	1
Dr. C. Giori IIT Research Institute 10 West 35 Street Chicago, Illinois 60616	1	Dr. J. Lando Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1
Dr. M. Litt Department of Macromolecular Science Case Western Reserve University Cleveland, Ohio 44106	1	Dr. J. White Chemical and Metallurgical Engineering University of Tennessee Knoxville, Tennessee 37916	1
Dr. R. S. Roe Department of of Materials Science and Metallurgical Engineering University of Cincinnati Cincinnati, Ohio 45221	1	Dr. J. A. Manson Materials Research Center Lehigh University Bethlehem, Pennsylvania 18015	1
Dr. Robert E. Cohen Chemical Engineering Department Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. R. F. Helmreich Contract RD&E Dow Chemical Co. Midland, Michigan 48640	1
Dr. T. P. Conlon, Jr., Code 3622 Sandia Laboratories Sandia Corporation Albuquerque, New Mexico	1	Dr. R. S. Porter Department of Polymer Science and Engineering University of Massachusetts Amherst, Massachusetts 01002	1
Dr. Martin Kaufmann, Head Materials Research Branch, Code 4542 Naval Weapons Center China Lake, California 93555	1	Professor Garth Wilkes Department of Chemical Engineering Virginia Polytechnic Institute and State University Blacksburg, Virginia 24061	1
Professor S. Senturia Department of Electrical Engineering Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1	Dr. Kurt Baum Fluorochem Inc. 6233 North Irwindale Avenue Azusa, California 91702	1
		Professor C. S. Paik Sung Department of Materials Sciences and Engineering Room 8-109 Massachusetts Institute of Technology Cambridge, Massachusetts 02139	1

OFFICE OF NAVAL RESEARCH  
Contract N00014 79C 0507  
Serial RC-607

Technical Report No. 9

Studies of Elastic Properties of Stretch Films  
of Polycarbonate by Brillouin Scattering

By

Quan-L. Liu and C. H. Wang

Department of Chemistry  
University of Utah  
Salt Lake City, Utah 84112

Prepared for Publication  
in  
Macromolecules

February 22, 1982

Reproduction in whole or in part is permitted for any purpose of the  
United States Government.

This document has been approved for public release; its distribution is unlimited.

Studies of Elastic Properties of  
Stretch Films of Polycarbonate by Brillouin Scattering

Quan-L. Liu\* and C. H. Wang  
Department of Chemistry  
University of Utah  
Salt Lake City, Utah 84112

\*On leave from the graduate school of the University of Science and  
Technology of China, Beijing, China.

### Abstract

Results of the Brillouin scattering study of polycarbonate (PC) films stretched at a temperature slightly above  $T_g$  are reported. The elastic constants  $C_{11}$ ,  $C_{13}$ ,  $C_{33}$ , and  $C_{44}$  are determined as a function of stretched ratio. Using the affine orientational model recently developed by Wang and Cavanaugh, the orientation parameter is obtained as a function of stretched ratio. The changes in the elastic constants and the orientation parameter are discussed in terms of chain morphology. The results in PC films are found to be significantly different from other polymer films, such as poly(ethylene terephthalate) and isotactic polypropylene, recently investigated in this laboratory. The reason for the difference is discussed.

## Introduction

Viscoelastic properties of polymers are affected by externally applied perturbations. The external perturbations, such as stretching or extrusion, induce a preferred orientation of polymer chain segments along the deformation axis.

The increased chain orientation occurs in both the crystalline and amorphous regions. In some cases, reorganization of the semicrystalline structure with replacement of lamellae by fibrous elements may also occur. One manifestation of this is an increase in the elastic (stiffness) constant along the axis of stretching, but Young's modulus perpendicular to the stretching axis or shear modulus about the axis may not be significantly affected. However, in polymers, such as poly(ethylene terephthalate)<sup>1</sup>, polyethylene<sup>2</sup>, polyamides (Nylon 6-6)<sup>1</sup>, and other semicrystalline polymers<sup>3</sup>, an increase in Young's modulus with orientation has been found. These studies are carried out using low frequency acoustic or ultrasonic techniques. The results may be due in part to the reorganization of the crystal structure and in part to the stretching of many of the intercrystalline tie molecules. In any case, a full description of the anisotropic elastic property of the solid polymer will require separate specification of the orientation of crystalline and amorphous regions.<sup>4</sup>

In recent years, Wang and coworkers have used the Raman and Brillouin light scattering technique to study the effect of chain orientation of hydrostatically extruded rods<sup>5-7</sup> and stretched films.<sup>8-10</sup> Although Brillouin scattering has been used in this laboratory during the past years mainly in the study of high frequency viscoelasticity in amorphous polymers,<sup>11,12</sup> the development of multi-pass, high-contrast Fabry-perot interferometry<sup>13</sup> has prompted the application of the Brillouin scattering technique to study the semicrystalline polymer solids.<sup>14</sup> Using Brillouin scattering information about the hypersonic velocity and attenuation coefficient in a polymer

medium which remains in thermodynamic equilibrium can be obtained. Moreover, as noted previously,<sup>8</sup> Brillouin scattering has an advantage in the study of solid state polymers in which the shape and size of the sample are relatively unimportant. This reduces the amount of sample preparation efforts which were substantial in the previous experiments. Our recent work on polymer films also demonstrates that the hypersonic (both the longitudinal and transverse) behavior across the surface of an extruded rod or an oriented film can be mapped accurately using a relatively simple scattering geometry.<sup>8-10</sup>

In this paper, we report results of the Brillouin scattering study of stretched polycarbonate films. Due to its high impact strength and modulus characteristics, as well as excellent thermal stability, and complete transparency, polycarbonate (PC) derived from bisphenol-A is one of the most important polymers suitable for application. A detailed account of the chemical and physical properties of PC can be found in refs. 15-17. Brillouin scattering spectra of PC were reported previously by Durvasula and Gammon<sup>18,19</sup> and by Patterson<sup>14</sup> as a function of temperature. By comparing the Brillouin data with the ultrasonic results, Patterson has noticed a considerable dispersion in the longitudinal phonon velocity below the glass transition temperature ( $T_g \approx 150^\circ\text{C}$ ). Velocity dispersion in the transverse shear wave below  $T_g$  was also found by Durvasula and Gammon,<sup>19</sup> but these authors were uncertain about the origin of the dispersion. They even hinted a possibility of an error in the low frequency shear modulus data, due to a very large (two order of magnitude) drop of the shear velocity value above  $T_g$ , which does not appear in the hypersonic shear velocity result. Another independent ultrasonic study as a function of temperature will be useful to resolve this uncertainty. It is hoped that efforts in this direction will be carried out shortly.

We have studied the hypersonic velocities in PC films stretched slightly above  $T_g$  in various directions on the film surface. From the velocity data, we have

determined for the first time the elastic constants  $C_{11}$ ,  $C_{33}$ ,  $C_{13}$  and  $C_{44}$  as a function of stretch ratio. Using the affine orientation model recently developed by Wang and Cavanaugh,<sup>6,20</sup> we have also obtained the orientation parameter. The result is then compared with that obtained using the Moseley model.<sup>21</sup> We have discussed the change in the orientation parameter in terms of chain morphology.

### Experimental

Polycarbonate resin was purchased from the Aldrich Chemical Company as amorphous clear nuggets ( $\overline{M}_w = 20,000$  to  $25,000$ ; density  $1.20$ ,  $T_m = 267^\circ\text{C}$ ;  $T_g = 150^\circ\text{C}$ ;  $N_D^{20} = 1.5850$ ).<sup>22</sup> Preparation of the PC film samples was similar to that described in ref. 8. Films were melt cast in a hydraulic press, fitted with polished heated copper plates. The films were melt cast at a temperature of  $270^\circ\text{C}$  and at a pressure of  $0.5$  metric tons, jointly applied for two minutes. The hot films were then quenched in ice water to maximize optical quality by increasing the content of the amorphous phase. The PC films having a good optical quality, unblemished surface and uniform thickness were selected for further experimentation.

The films were then uniaxially stretched in a silicone oil bath at a temperature slightly above  $T_g$  ( $152$ - $153^\circ\text{C}$ ) using a manually operated puller. The draw was about  $100\%$  per minute. In addition to the unstretched film, six specimens with stretch ratios ( $R_S$ ) of  $1.8$ ,  $2.9$ ,  $4.1$ ,  $5.0$ ,  $6.1$ , and  $8.1$  were prepared for Brillouin scattering.

The densities of the film samples were measured with a floatation method. An aqueous solution of calcium chloride with a density of about  $1.22 \text{ g/cm}^3$  was used. The density of the film was found to be unaffected by stretching. At room temperature ( $22^\circ\text{C}$ ), a value of  $1.1983 \pm 0.0005 \text{ g/cm}^3$  was measured for all film samples. This result suggests that the presence of partial crystallization as reported by Patterson,<sup>14</sup> has only a negligible effect on the density, if any.

A five - pass Fabry-perot interferometer was used to resolve the Brillouin scattering spectra for films of various stretch ratios at several orientation angles. The overall finesse of the optical instrument was about 55. The free spectral range used was about 23 GHz. An argon ion laser (spectra-physics 165) with a single mode operation at about  $4880 \text{ \AA}$  was used to excite the Brillouin scattering spectrum. The optical setup and electronics used in this work was similar to that reported in refs. 8-10.

For the angular dependent measurement to obtain the velocity contour, the scattering geometry as shown in Fig. 1 in ref. 9 was used. A least squares fitting program was used to fit the Christoffer equation<sup>23</sup> to the velocity contours to obtain the elastic constants and to obtain the orientation parameter as a function of stretch ratio.

### Results and Discussion

In an optically isotropic medium, the hypersonic velocity  $V_B$  is related to the Brillouin frequency shift  $f_B$  (in Hz) by

$$V_B = f_B \lambda_i / 2n \sin (\theta/2) \quad (1)$$

where  $\lambda_i$  is the incident wavelength,  $n$  is the index of refraction, and  $\theta$  is the scattering angle. Equation (1) needs to be modified for an anisotropic medium. However, the birefringence in the index of refraction in the oriented PC film is small,  $[(n_{||} - n_{\perp})/n_{||}] < 10^{-3}$ ;  $n_{||}$  and  $n_{\perp}$  being the indecies parallel and perpendicular to the orientation axis; the sound velocity deduced for the shear wave from Eq. (1) will yield a result with an accuracy not limited by the anisotropy in the index of

refraction, but by other factors such as the broad width and weak intensity of the spectral peak. Nevertheless, the sound velocity from the longitudinal phonon reported in this work is accurate to better than 1% and that from the transverse phonon, to 5%.

It has been shown previously<sup>8,24</sup> that when the scattering geometry is at 90° and the film bisects the angle made by the incident and scattering beams, the hypersonic velocity-frequency relationship given in Eq. (1) reduces to

$$V_S = f_B \lambda_i / \sqrt{2} \quad (2)$$

It should be noted that in this scattering geometry, the index of refraction does not enter Eq. (2) and for that reason it is a very useful scattering geometry for obtaining the sound velocity by Brillouin scattering from samples whose index of refraction is difficult to measure. All Brillouin spectra reported in this work was obtained using this scattering geometry.

The Brillouin spectral data in all PC films were obtained using the Vv configuration. The Vv spectra displays clear features due to scattering from longitudinal and transverse acoustic waves. The longitudinal and transverse waves are in general mixed, except for the cases when the scattering vector  $q$  is parallel to or perpendicular to the orientation axis. The scattering vector  $q$  corresponds to the phonon propagation direction.

Shown in Fig. 1 are the hypersonic velocity curves as a function of stretch ratio obtained from the Brillouin spectral lines using Eq. (2) for various orientation angles  $\alpha$ . The orientation angle  $\alpha$  is defined as the angle between  $q$  and the direction of the stretching axis. It is important to note that both the

longitudinal and transverse acoustic components are observed also in the unstretched PC film at  $\alpha = 0$  and  $90^\circ$ . This result contrasts with the other polymer films we have previously studied.<sup>8-10, 20</sup> In those films, the transverse components do not appear in the pure mode directions ( $\alpha=0^\circ$  and  $90^\circ$ ) under the same laser excitation intensity. They appear only in the directions at which the transverse and longitudinal modes become mixed.

For the film samples, the intensity of the QL and QT Brillouin lines associated with the scattering vector  $q$  in the film face (the  $x$ - $z$  plane,  $z$  being the stretching direction of the film), it can be shown<sup>25</sup> that the scattering factor<sup>26</sup> (proportional to the intensity) for an one-phase medium is given as function of  $\alpha$  by

$$\beta_m = (\rho V_{m,\alpha}^2)^{-1} [(p_{11} U_x \sin\alpha + p_{13} U_z \cos\alpha) \cos^2\alpha + (p_{33} U_z \cos\alpha + p_{31} U_x \sin\alpha) \sin^2\alpha] \quad (3)$$

when  $U_x$  and  $U_z$  are the components of the displacement eigenvector for the wave propagating in the  $x$ - $z$  plane. These are related to the elastic constants and the angle  $\alpha$  by

$$(C_{11} \sin^2\alpha + C_{44} \cos^2\alpha - \rho V_{m,\alpha}^2) U_x = [(C_{13} + C_{44}) \sin\alpha \cos\alpha] U_z \quad (4)$$

where the subscript  $m$  refers to the QL or QT wave and  $\rho V_{m,\alpha}^2$  is determined at each angle.  $p_{ij}$ 's are the Pockel photoelastic coefficients.

The ratio of the scattering factors  $\rho_B = \beta(QT)/\beta(QL)$  has been studied in ref. 25 for polypropylene. When this ratio is plotted as a function of  $\alpha$ , it reaches a maximum at  $45^\circ$  for each film, but decreases to nearly zero at  $\alpha=0^\circ$  and  $90^\circ$ .<sup>25</sup> Shown in Fig. 2

is the intensity ratio of  $\rho_{\beta}$  as a function of  $\alpha$  for PC films with different stretch ratios. One notes clearly that the maximum value of  $\rho_{\beta}$  occurs approximately at  $\alpha=45^{\circ}$  and the value of maximum of  $\rho_{\beta}$  increases with the draw ratio consistent with the result previously found in polypropylene; however, the  $\rho_{\beta}$  values for PC films at  $\alpha=0^{\circ}$  and  $90^{\circ}$  are still substantial in contrast to the result found in polypropylene.

Two possible mechanisms are believed to be responsible for the large intensity of the shear mode in the unoriented film as well as in the oriented films in the pure mode configurations ( $\alpha=0^{\circ}$  and  $90^{\circ}$ ). One is due to dynamic coupling of the polarizability anisotropy to the shear motion in the amorphous region, similar to the mechanism found to be responsible for the appearance of the transverse shear mode in supercooled liquids and glasses consisting of small optically anisotropic molecules.<sup>27-29</sup> The other is random orientation of crystallites in the PC films due to partial crystallization. The partial crystallinity will enhance scattering of the shear modes. In combination with the above mentioned mechanism, shear wave is expected to scatter light more strongly in the pure mode directions in a semicrystalline than in an amorphous film sample, despite the fact that the degree of birefringent in PC films is not large enough to affect the values of sound velocity. Durvasula and Gammon<sup>19</sup> have estimated the strain - optical coefficient  $(p_{44}/p_{12})^2$  to be about  $10^{-2}$  which is comparable to the  $(p_{44}/p_{12})^2$  value ( $\approx 7 \times 10^{-2}$ ) found in fused silica<sup>29</sup>, and nearly two orders of magnitude larger than the value of PMMA.<sup>30</sup> Patterson has attributed this to angular correlation of phenyl groups between neighboring chains in PC;<sup>14</sup> however, it will be difficult to account for the small strain-optical coefficient found in polystyrene using the same mechanism. The large  $(p_{44}/p_{12})^2$  value found in PC is more likely associated with the chain rigidity due to the incorporation of the phenyl groups in the chain backbone. It would be useful to study the effect of chemical structure on the behavior of the shear mode so that the origin of the large

strain-optical coefficient in PC may be clarified.

One notes in Fig. 1 that at  $\alpha=0^\circ$ , the hypersonic velocity increases with increasing  $R_S$ , approaching a plateau value at  $R_S=5.0$ . On the other hand, at  $\alpha=90^\circ$ , the velocity decreases with increasing  $R_S$ , also approaching a plateau value at  $R_S=5.0$ . As noted above,  $\alpha=0^\circ$  and  $90^\circ$  correspond to two pure longitudinal mode directions, despite the fact that scattering from the shear mode also appears in these directions. However, as shown in Fig. 1, the transverse wave velocity (observed at  $\alpha=0^\circ$ ) is insensitive to stretching.

The change of hypersonic velocities with stretching is more clearly illustrated in terms of polar plots of the sound velocity versus the sound propagation direction. Shown in Fig. 3 are the polar plots for an unstretched ( $R_S=1.0$ ) and for a stretched ( $R_S=5.0$ ) film. The polar plot shows two concentric circles in the unstretched film, indicating a perfect acoustic isotropy for both the longitudinal and transverse waves on the film surface. However, the circles are distorted in the stretched film, as shown in the  $R_S=5.0$  film. Maximum quasi-longitudinal and quasi-transverse sound velocities are found at  $\alpha=45^\circ$ ; the velocities at  $\alpha=0^\circ$  are larger than those at  $\alpha=90^\circ$ .

The shape of those velocity contour maps is associated with the change of elastic constants of the films as a result of stretching. This can be analyzed in terms of the Christoffel equation<sup>23</sup> for the propagation of acoustic waves in an anisotropic medium. The elastic constant matrix for an uniaxial oriented sample is given by

$$C_{ij} = \begin{bmatrix} C_{11} & C_{12} & C_{13} & 0 & 0 & 0 \\ & C_{11} & C_{13} & 0 & 0 & 0 \\ & & C_{33} & 0 & 0 & 0 \\ & & & C_{44} & 0 & 0 \\ & & & & C_{44} & 0 \\ & & & & & C_{66} \end{bmatrix} \quad (5)$$

where  $C_{66} = \frac{1}{2} (C_{11} - C_{12})$ . The Christoffer equation which relates the velocities and elastic constants for the acoustic waves propagating on the film surface is given by<sup>9</sup>

$$2\rho V_{\pm}^2 = (C_{11} \ell_x^2 + C_{33} \ell_z^2 + C_{44}) \pm \{(C_{11} \ell_x^2 + C_{33} \ell_z^2 + C_{44})^2 - 4[(C_{11} \ell_x^2 + C_{44} \ell_z^2)(C_{44} \ell_x^2 + C_{33} \ell_z^2) - \ell_x^2 \ell_z^2 (C_{13} + C_{44})^2]\}^{\frac{1}{2}} \quad (6)$$

where  $\ell_x = q_x/|q| = \sin \alpha$  and  $\ell_z = q_z/|q| = \cos \alpha$ , are the direction cosines of the scattering vector in the film. The quasilongitudinal (QL) and quasitransverse (QT) phonons are associated with the plus and the minus roots, respectively. Knowing the density data and the hypersonic velocities as a function of  $\alpha$ , one can calculate the elastic constants as a function of  $R_S$  using Eq. (6). We have used a least squares computer fitting the program to include all experimental data in this calculation. The results for elastic constants  $C_{11}$ ,  $C_{33}$ ,  $C_{13}$  and  $C_{44}$  obtained from the calculation are shown in Fig. 4 and also in Table I. The elastic constant  $C_{66}$  (or  $C_{12}$ ) is not shown as it cannot be determined by the Brillouin scattering technique.

Although the behavior of the elastic constants in the PC films as the films are stretched is similar to that found in other polymer films,<sup>8,9,20</sup> there are some significant differences. For example, although the  $C_{33}$  values for the unstretched poly-(ethylene terephthalate) (PET) and polypropylene (PP) films are lower than that for the PC film, as those films are stretched to  $R_S=5.0$  they become 4-5 times greater than the values of the unstretched films. On the other hand, the  $C_{33}$  value for PC only increases 23% from the unstretched value at  $6.48 \times 10^{10}$  dyne/cm<sup>2</sup> to the maximum value for the film stretched to  $R_S=5.0$  at  $7.95 \times 10^{10}$  dyne/cm<sup>2</sup>. More interestingly, above  $R_S=5.0$ ,  $C_{33}$  shows a decrease rather than an increase found in other films.

The behavior of the elastic constants in the stretched films is closely associated with the increased chain segment orientation. A simplified model proposed by Moseley has related the sonic velocity of the oriented polymers to the orientation parameter  $\langle P_2 \rangle$  by <sup>21</sup>

$$\langle P_2 \rangle \equiv \frac{1}{2} \langle 3\cos^2\theta - 1 \rangle = 1 - (C_{33}^u / C_{33}) (\rho / \rho^o) \quad (7)$$

where  $C_{33}^u$  and  $\rho^o$  are the elastic constant and density of the unextruded sample, respectively. The orientation parameter calculated according to Eq. (7) is shown in Fig. 4 and also in Table II (designated as  $f$ ) as a function of stretch ratio.

In order to derive Eq. (7), Moseley has assumed that acoustic waves propagate in an oriented fiber in a way similar to the current conducted through parallel circuits and that for an oriented sample,  $C_{33} \gg C_{11}$ . However, even though the  $C_{33}$  value may be several times larger than the  $C_{11}$  value, the maximum  $C_{33}$  value for highly oriented polymer ( $\langle P_2 \rangle \approx 1$ ) is far from infinity to be neglected. Furthermore, the propagation of sound waves cannot be treated in a manner like current flowing in a parallel electronic circuit. Assuming that affine orientation of polymer chains occur when the films are stretched, i.e., the combined intermolecular effect such as partial crystallization and chain reorientation can be approximated as the rotational transformation of the strain tensor, Wang and Cavanaugh have shown that the elastic constants  $C_{11}$ ,  $C_{33}$  and  $C_{13}$  of an oriented film are rigorously related to the orientation parameter  $\langle P_2 \rangle$  by <sup>6</sup>

$$C_{11} = (\lambda + 2\mu)(1 - \langle P_2 \rangle) + C_{11}^o \langle P_2 \rangle \quad (8)$$

$$C_{33} = (\lambda + 2\mu)(1 - \langle P_2 \rangle) + C_{33}^o \langle P_2 \rangle \quad (9)$$

and

$$C_{13} = \mu(1 - \langle P_2 \rangle) + C_{13}^o \langle P_2 \rangle \quad (10)$$

where  $\lambda$  and  $\mu$  are the two Lamé constants for the unoriented isotropic films;

$C_{11}^\circ$ ,  $C_{33}^\circ$  and  $C_{13}^\circ$  are the elastic constants of the oriented films when  $\langle P_2 \rangle = 1$ .

One notes in Fig. 4 that  $C_{11}$  of the stretched film is less than  $C_{11}^u$ , where  $C_{11}^u (= \lambda + 2\mu)$  is the  $C_{11}$  (or  $C_{33}$ ) value of an unoriented film. On the other hand, as the film is stretched,  $C_{33}$  becomes greater than  $(\lambda + 2\mu)$ .

To obtain the orientation parameter from the experimentally determined elastic constants using Eqs. (8) - (9), we need to determine the intrinsic elastic constants  $C_{11}^\circ$ ,  $C_{33}^\circ$  and  $C_{13}^\circ$  for the perfectly oriented units. To do this, we set  $C_{11}^\circ = A C_{11}^u$  and  $C_{33}^\circ = B C_{11}^u$ , where A and B are fitting parameters which are less and greater than unity, respectively. According to Ref. 20, the  $C_{13}^\circ$  values are related to  $C_{11}^\circ$  and  $C_{33}^\circ$  by

$$C_{33}^\circ = (\lambda + 2\mu) \left( \frac{15}{4} - \frac{3}{4} B - 2A \right) - 2\mu \quad (11)$$

Equation (11) is the result of Eqs. (8) - (10), together with the assumption that  $C_{44}$  remains unchanged as the films are stretched, i.e.  $C_{44}^\circ = \mu$ . This is justified by the present experimental result (see Fig. 3). Having obtained Eq. (11), we then make an initial guess of the values A and B. The A and B values, along with the measured unoriented elastic constants, determine a full set of initial constants for the calculation. The value of  $\langle P_2 \rangle$  for each sample can then be calculated according to Eqs. (8) - (10) and a least squares program. The calculated  $C_{11}$ ,  $C_{33}$  and  $C_{13}$  values are compared with the experimental results; the process is repeated, varying A and B so that the difference between the experiment results and the calculated values is minimized.

The orientation parameters  $\langle P_2 \rangle$  calculated according to this method are shown in Table II and also plotted as a function of stretch ratio ( $R_S$ ) in Fig. 5. One

notes that for all stretched films, the  $\langle P_2 \rangle$  value calculated using the method of Wang and Cavanaugh is always less than that obtained by Moseley's model (Eq. (7)). Clearly Moseley has overestimated the value of  $C_{33}^0$  in his theory.

The best values calculated using Eqs. (8) - (10) are also plotted in Fig. 4 as well as tabulated in Table I. Except for a small discrepancy in the  $C_{13}$  values at large  $R_S$  values, they compare well with the experimental values. The small discrepancy in  $C_{13}$  indicates the orientation of PC films is not completely affine. However, in view of the  $C_{11}$  and  $C_{33}$  results, the agreement between theory and experiment is sound. Not only is the decrease in  $C_{11}$  accounted for, but also the increase as well as the subsequent decrease of  $C_{33}$  at  $R_S > 5.0$  are correctly predicted by the theory, thus indicating that the variation of the elastic constants of the stretched PC films is mainly due to the induced orientation of the polymer chains. However, comparing with other polymer films such as PET<sup>9</sup> and PP<sup>7,9,10</sup> films, the induced chain orientation in PC is quite small. In the present PC films, at low  $R_S$ ,  $\langle P_2 \rangle$  increases slowly with increasing  $R_S$ , reaching a saturated value of about  $\langle P_2 \rangle \approx 0.1$  at  $R_S = 5.0$ .

Like the PET films,<sup>31,32</sup> the PC film may be oriented and crystallized by stretching.<sup>16,17</sup> The induced chain orientation of stretched isotactic polypropylene films is well known,<sup>7</sup> although the stress-induced crystallization is negligible.<sup>33</sup> In PET, Mirra and Stein<sup>31</sup> have shown that the films stretched above  $T_g$  develop a rod-like superstructure oriented in the direction normal to stretching. However, as noted above in both the PET<sup>6</sup> and the isotactic PP films,<sup>20</sup> the elastic constant  $C_{33}$  increases to 4 - 5 times its unstretched value at  $R_S = 5.0$ , whereas in the PC film it only increases about 23% of the initial value. This comparison suggests that there is a fundamental difference between the morphology of PC films and that of PET, despite the fact that the phenyl group in PET is also incorporated into the chain backbone.

Apparently, the stress-induced chain orientation in semicrystalline polymers depends to a large degree on the tie molecules in the amorphous phase. At low  $R_S$ , the stress - induced chain orientation in PET and in PP occurs in the amorphous region with the inter-lamellae strands or tie molecules connecting the neighboring lamellae in the direction of elongation. Clearly, this does not occur in the stretched PC films. In other words, the stress-induced crystallization in amorphous PC does not result in a superstructure like PET. Crystallization only occurs randomly at a local scale. As a result, no spherulite-like aggregate is present in PC to facilitate the orientation of the inter-lamella tie molecules. The difficulty in forming the spherulite structure in PC may be due to its rigid chain backbone.

Finally, one notes that Poisson's ratio ( $\sigma$ ) and Young's modulus (E) of the unoriented film can be readily obtained from the present data. According to the expressions:<sup>23</sup>

$$\sigma = \frac{1}{2} (C_{11}^u - 2 C_{44}^u) / (C_{11}^u - C_{44}^u) \quad (12)$$

and

$$E = 2 C_{44}^u (1 + \sigma) \quad (13)$$

The value of  $\sigma$  found in this study is 0.382, which agrees well with that reported in refs. 14 and 17. However, Young's modulus E calculated according to Eq. (13) in the present work is equal to  $3.38 \times 10^{10}$  dyne/cm<sup>2</sup>. This is 35% higher than the  $2.5 \times 10^{10}$  dyne/cm<sup>2</sup> value measured at low frequency (reported in refs. 17 and 34). This difference suggests that considerable frequency dispersion may be present in the PC film above  $T_g$ .

### Acknowledgement

We thank Dr. David B. Cavanaugh for technical assistance as well as for the use of the computer programs which he has developed for this Ph.D. dissertation. Financial supports from the Office of Naval Research and NSF Polymer Grant No. DMR 79-12457 are also acknowledged.

### References

1. J. H. Wakelin, E. T. L. Voong, D. J. Montgomery, and J. H. Dusenbury, *J. Appl. Phys.*, 26, 786 (1955)
2. V. B. Gupta and I. M. Ward, *J. Macromol. Sci.-Phy.*, B2, 373 (1967)
3. I. M. Ward, *Mechanical Properties of Solid Polymer*, Chapter 10, Wiley-Interscience, London, (1971)
4. J. D. Ferry, *Viscoelastic Properties of Polymers*, Chapter 16, 3rd Ed. John Wiley & Sons, New York (1980)
5. S. K. Satija and C. H. Wang, *J. Chem. Phys.*, 69, 2739 (1978)
6. C. H. Wang and D. B. Cavanaugh, *J. Appl. Phys.*, 52, 6003 (1981)
7. C. H. Wang and D. B. Cavanaugh, *Macromolecules*, 14, 1061, (1981)
8. C. H. Wang, D. B. Cavanaugh, and Y. Hagashigaki, *J. Polym. Sci. Polym. Phys. Ed.*, 19, 941 (1981)
9. D. B. Cavanaugh and C. H. Wang, *J. Appl. Phys.*, 52, 5998 (1981)
10. D. B. Cavanaugh and C. H. Wang, *J. Appl. Phys.* (in press)
11. Y. Y. Huang and C. H. Wang, *J. Chem. Phys.*, 61, 1868 (1974); *ibid*, 64, 4748 (1976)
12. C. H. Wang, Y.-H. Lin and D. R. Jones, *Molec. Phys.*, 37, 287 (1979)
13. J. R. Sandercock, *Opt. Comm.*, 2, 76 (1970)
14. G. D. Patterson, *J. Polym. Sci. Polym. Phys. Ed.*, 14, 741 (1976)
15. H. F. Mark, N. G. Gaylord and N. M. Bikales, "Encyclopedia of Polymer Science and Technology", 10, 756, John Wiley & Sons, New York (1969)
16. H. Schnell, *Chemistry and Physics of Polycarbonates*, Interscience, New York (1966)
17. W. F. Christopher and D. W. Fox, *Polycarbonates*, Reinhold, New York, (1962)
18. L. N. Durvasula and R. W. Gammon, *J. Opt. Soc. Amer.*, 63, 1308 (1973)
19. L. N. Durvasula and R. W. Gammon, *J. Appl. Phys.*, 50, 4339 (1979)
20. D. B. Cavanaugh and C. H. Wang, *J. Polym. Sci. Polym. Phys. Ed.* (in press)
21. W. N. Moseley, *J. Appl. Polym. Sci.* 3, 266 (1960)
22. Aldrich Chemical Company, 1981-1982 Aldrich Catalog Handbook of Fine Chemicals, Page 783, (1980)
23. B. A. Auld, *Acoustic Fields and Waves in Solid*, Vol. I, Wiley-Interscience, New York, (1973)

24. J. K. Kruger, L. Peetz and M. Pietralla, *Polymer*, 19, 1397 (1978)
25. D. B. Cavanaugh and C. H. Wang, *J. Appl. Phys.* (in press)
26. R. Vacher and L. Boyer, *Phys. Rev.* 13, 6, 693 (1972)
27. G. D. Enright and B. P. Stoicheff, *J. Chem. Phys.*, 64, 3658 (1976)
28. See, for example, Y. Hisashigaki and C. H. Wang, *J. Chem. Phys.*, 74, 3175 (1981) and C. H. Wang, *Mole. Phys.*, 41, 541 (1980) are references cited herein.
29. I. L. Fabelinskii, Molecular Scattering of Light, Plenum Press, New York, (1968)
30. A. Kuski and G. Robertson, Photoelastic Stress Analysis, John Wiley & Sons, New York, (1974)
31. A. Misra and R. S. Stein, *J. Polym. Sci. Polym. Phys.*, 17, 235 (1979)
32. N. G. McCrum, B. E. Read and G. Williams, Anelastic and Dielectric Effects in Polymeric Solids, John Wiley & Sons, New York, (1967)
33. R. J. Samuels, Structural Polymer Properties, Wiley, New York (1976)
34. F. P. Wolf, *Colloid and Polymer Science*, 257, 1253 (1979)

Table I

The elastic constants (in unit of dyne/cm<sup>2</sup> x 10<sup>10</sup>) as a function of stretch ratio  $R_S$  for polycarbonate films.

(a) Experimental values

(b) Calculative values according to the model reported in Ref. 20.

$R_S$	$C_{11}$		$C_{33}$		$C_{44}$		$C_{13}$	
	(a)	(b)	(a)	(b)	(a)	(b)	(a)	(b)
1.00	6.45	6.45	6.48	6.46	1.22	1.22	4.02	3.40
1.80	6.27	6.31	6.81	6.91	1.27	1.22	3.88	3.90
2.92	6.14	6.17	7.37	7.37	1.25	1.22	4.08	3.80
4.06	6.06	6.09	7.69	7.63	1.27	1.22	4.09	3.74
5.00	5.78	5.91	7.95	8.21	1.27	1.22	4.03	3.61
6.14	5.84	5.95	7.81	7.85	1.24	1.22	4.01	3.59
8.14	5.90	5.98	7.34	7.78	1.26	1.22	3.89	3.61

Table II

The orientation parameter as a function of stretch ratio  $R_S$  for polycarbonate films.

$\langle P_2 \rangle$ : Values according to Ref. 20.

$f$  : The values according to Moseley's model.<sup>21</sup>

$R_S$	1.0	1.8	2.9	4.1	5.0	6.1	8.1
$\langle P_2 \rangle$	0.00	0.03	0.05	0.06	0.10	0.10	0.09
$f$	0.00	0.05	0.12	0.13	0.19	0.17	0.16

### Figure Captions

- Figure 1 The hypersonic Velocities ( $V_S$ ) of polycarbonate films at the room temperature potted as a function of stretch ratio  $R_S$  for the different film angles  $\alpha$  ( $0^\circ$ ,  $30^\circ$ ,  $50^\circ$ ,  $90^\circ$ ).  
(L): Longitudinal wave - (T): Transverse wave
- Figure 2 The ratio of scattering factors for the QT and QL modes plotted as a function of  $\alpha$  for several stretched films.  $\circ$ :  $R_S=8.1$ ;  $\bullet$ :  $R_S=5.0$ ;  $\square$ :  $R_S=2.9$ ;  $\blacktriangle$ :  $R_S=1.9$ ;  $\bullet$ :  $R_S=1.0$ .
- Figure 3 Polar plots of sound velocities in polycarbonate films versus the sound propagation direction for two films ( $R_S=1.0$  and  $5.0$ ) S. D. is the stretch direction.  $\bullet$ : experiment data. —: fit to the Christoffel equation.
- Figure 4 Elastic constants  $C_{11}$ ,  $C_{33}$ ,  $C_{13}$ , and  $C_{44}$  of polycarbonate films are plotted versus the stretch ratio ( $R_S$ ). The solid points are the measured values; open points are the fit to the theory (see text).
- Figure 5. The orientation parameter plotted as a function of stretch ratio ( $R_S$ ):  
 $\bullet$  The total orientation parameter  $f$ , according to the Moseley model.  
 $\circ$  The orientation parameter  $\langle P_2 \rangle$ , according to the model by Wang and Cavanaugh<sup>6</sup> (see text).





Figure (1)






Figure (2)




Figure (3)




Figure 14.

**DATE  
FILMED**  
**4-8**