

AD-A119 793

AEROSPACE CORP EL SEGUNDO CA SPACE SCIENCES LAB F/G 20/2
MICROGRAPHIC OBSERVATIONS OF THE CARBONACEOUS MESOPHASE BY A GU--ETC(U)
AUG 82 J L WHITE, M BUECHLER, C B NG F04701-81-C-0082
UNCLASSIFIED TR-0082(2935-02)-2 SD-TR-82-51 NL

1 04 1
AD-A
19793



END
DATE
FILMED
H-02
DTIC

12

AD A119793

Micrographic Observations of the Carbonaceous Mesophase by a Quenching Hot Stage

J. L. WHITE, M. BUECHLER, and C. B. NG
Materials Sciences Laboratory
Laboratory Operations
The Aerospace Corporation
El Segundo, Calif. 90245

30 August 1982

SDTC
SELECTED
SEP 30 1982
H

APPROVED FOR PUBLIC RELEASE;
DISTRIBUTION UNLIMITED

DTIC FILE COPY

Prepared for
SPACE DIVISION
AIR FORCE SYSTEMS COMMAND
Los Angeles Air Force Station
P.O. Box 92960, Worldway Postal Center
Los Angeles, Calif. 90009

005

This report was submitted by The Aerospace Corporation, El Segundo, CA 90245, under Contract No. F04701-81-C-0082 with the Space Division, Deputy for Technology, P.O. Box 92960, Worldway Postal Center, Los Angeles, CA 90009. It was reviewed and approved for The Aerospace Corporation by W. C. Riley, Director, Materials Sciences Laboratory. Lieutenant Steven G. Hancock, SD/YLXT, was the project officer for Mission-Oriented Investigation and Experimentation (MOIE) Programs.

This report has been reviewed by the Public Affairs Office (PAS) and is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nations.

This technical report has been reviewed and is approved for publication. Publication of this report does not constitute Air Force approval of the report's findings or conclusions. It is published only for the exchange and stimulation of ideas.

Steven G. Hancock
Steven G. Hancock, 2nd Lt, USAF
Project Officer

Jim H. Butler
Jim H. Butler, Colonel, USAF
Director of Space Systems Technology

FOR THE COMMANDER

Norman W. Lee, Jr.
Norman W. Lee, Jr., Colonel, USAF
Deputy for Technology

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special



UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER SD-TR-82-51	2. GOVT ACCESSION NO. AD-A22 9793	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) MICROGRAPHIC OBSERVATIONS OF THE CARBONACEOUS MESOPHASE BY A QUENCHING HOT-STAGE		5. TYPE OF REPORT & PERIOD COVERED
7. AUTHOR(s) Jack L. White, Manfred Buechler, Cassandra B. Ng		6. PERFORMING ORG. REPORT NUMBER TR-0082(2935-02)-2
9. PERFORMING ORGANIZATION NAME AND ADDRESS The Aerospace Corporation El Segundo, Calif. 90245		8. CONTRACT OR GRANT NUMBER(s) F04701-81-C-0082
11. CONTROLLING OFFICE NAME AND ADDRESS Space Division Air Force Systems Command Los Angeles, Calif. 90009		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE 30 August 1982
		13. NUMBER OF PAGES 7
		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Mesophase Coalescence Quenching Nematic liquid crystals Hot-stage Petroleum pitch Disclinations		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A hot-stage microscope with quenching capability was employed to relate the observations made at the free surface of a pitch during pyrolysis to the bulk microstructure. Freshly formed mesophase spherules display an "iceberg effect" with only a limited upper segment exposed to view. The mesophase layers tend to lie normal to the free surface, and $\pm 2\pi$ as well as $\pm \pi$ disclinations display discontinuous cores at the free surface; aside from these minor effects, surface observations appear to be representative of events taking place within the bulk mesophase.		

DD FORM 1473
(FACSIMILE)

AEROSPACE FORM 4341-1 REV 8-74

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

MICROGRAPHIC OBSERVATIONS ON THE CARBONACEOUS MESOPHASE
BY QUENCHING HOT STAGE

At the Fourteenth Conference on Carbon, Hoover et al.¹ demonstrated by means of a film that dynamic observations of mesophase behavior were possible with the use of a hot-stage microscope with polarized-light reflected from the free surface of the pyrolyzing liquid. Although these observations confirm and extend the understanding of mesophase behavior as inferred from studies of polished sections of quenched specimens, there remains the question of just how closely the free-surface observations relate to the three-dimensional morphology within the bulk mesophase. For this reason we designed and constructed a hot-stage microscope with a quenching capability,^{2,3} so that a specimen could be pyrolyzed to a point of interest as observed on the free surface, and then quenched to a solidified body that could be sectioned for detailed micrographic study.

Polarized-light micrographs of the free surface and a vertical section through the free surface are compared in Fig. 1 for a specimen of petroleum pitch (Ashland A240) pyrolyzed to approximately 445°C. The spherules at the free surface display an iceberg effect with only a limited upper segment exposed to view at the surface. Thus, most coalescence events begin below the surface and only appear when the coalesced region has reached the surface.

The micrographs also illustrate two further points relating observations on the free surface to those made on polished sections. The polarized-light response on the free surface provides sharper contrast and crisper definition of the extinction contours. Furthermore, the extinction crosses, which

¹D. S. Hoover, A. Davis, A. J. Perrotta, and W. Spackman, Extended Abstracts, 14th Conf. on Carbon, 393 (1979).

²M. Buechler, C. B. Ng, V. L. Weinberg, and J. L. White, Carbon '80, Arbeitskreis Kohlenstoff der Deutsche Keram. Ges., 346 (1980).

³M. Buechler, C. B. Ng, and J. L. White, Extended Abstracts, 15th Conf. on Carbon, 182 (1981).

locate $\pm 2\pi$ disclinations,⁴ usually appear with sharply pinched centers on the free surface and with the broad diffuse centers on polished sections.

The vertical section (Fig. 1) was mapped by polarized-light response⁵ to obtain a structural sketch (Fig. 2). The large spherules display the coarse lamelliform morphology typical of fresh undeformed mesophase, but the layers at the free surface tend to lie normal to this surface. Examination of specimens quenched from various levels of pyrolysis confirmed this tendency but also indicates that this orientation of surface layers is readily disturbed by deformation of the mesophase, e.g., by bubble percolation. The layer curvatures necessary to orient the layers near normal to the free surface usually occur within a few microns of the surface. Thus, the strong contrast of polarized-light observations on the free surface of freshly formed mesophase results from the natural molecular orientation at this surface.

In conventional nematic liquid crystals, the rod-like molecular units tend to lie parallel to an interface (e.g., the interface with a glass cover slide), and the pinched crosses of the polarized-light extinction contours observed on this interface locate $\pm 2\pi$ wedge disclinations with discontinuous cores.⁶ Meyer⁷ has shown that within the bulk nematic liquid crystal, beyond the range of orienting forces near the interface, the molecules comprising the core of a $+2\pi$ wedge disclination tilt toward parallelism with the disclination line to form a core with continuous structure. In the carbonaceous mesophase, the tendency for the mesophase layers to stand normal to the free surface also requires the core of a $+2\pi$ wedge disclination to be discontinuous at the surface, but within bulk mesophase the core can relax to the cup-shaped continuous structure sketched in Fig. 3.

This situation is thus symmetrical with the saddle-shaped continuous structure of the core of -2π wedge disclinations (Fig. 4) deduced from

⁴J. E. Zimmer and J. L. White, *Mol. Cryst. Liq. Cryst.* 38, 177 (1977).

⁵J. Dubois, C. Agace, and J. L. White, *Metallography* 3, 337 (1970).

⁶S. Chandrasekhar, *Liquid Crystals*, Cambridge Univ. Press (1977).

⁷R. B. Meyer, *Phil. Mag.* 27, 405 (1973).



Fig. 1. Polarized-light micrographs of a quenched specimen of mesophase pitch as observed on free surface (upper view) and on a polished vertical section (lower view). Crossed polarizers.




Fig. 2. Structural sketch of mesophase layer orientations in large spherules of lower view in Fig. 1




Fig. 3. Lamelliform model of a $+2\pi$ wedge disclination. A grid placed on a surface defined by the later orientations shows the cup-like structure of the continuous core. The core becomes discontinuous near the intersection with the free surface.




Fig. 4. Lamelliform model of a -2π wedge disclination formed in the mesophase matrix between four carbon filaments of a carbon-carbon composite.⁸ A grid placed on a surface defined by the layer orientations shows the saddle-like structure of the continuous core.

micrographic study of certain fiber-reinforced composites.⁸ Topologically, the carbonaceous mesophase seems to behave as a nematic liquid crystal, but with the vector defining the molecular orientation standing normal to the long dimension of the layer-shaped molecules rather than parallel as in the case of the rod-shaped molecules that comprise conventional nematic liquid crystals.

⁸J. E. Zimmer and J. L. White, Extended Abstracts, 14th Conf. on Carbon, 429 (1979).

LABORATORY OPERATIONS

The Laboratory Operations of The Aerospace Corporation is conducting experimental and theoretical investigations necessary for the evaluation and application of scientific advances to new military space systems. Versatility and flexibility have been developed to a high degree by the laboratory personnel in dealing with the many problems encountered in the nation's rapidly developing space systems. Expertise in the latest scientific developments is vital to the accomplishment of tasks related to these problems. The laboratories that contribute to this research are:

Aerophysics Laboratory: Launch vehicle and reentry aerodynamics and heat transfer, propulsion chemistry and fluid mechanics, structural mechanics, flight dynamics; high-temperature thermomechanics, gas kinetics and radiation; research in environmental chemistry and contamination; cw and pulsed chemical laser development including chemical kinetics, spectroscopy, optical resonators and beam pointing, atmospheric propagation, laser effects and countermeasures.

Chemistry and Physics Laboratory: Atmospheric chemical reactions, atmospheric optics, light scattering, state-specific chemical reactions and radiation transport in rocket plumes, applied laser spectroscopy, laser chemistry, battery electrochemistry, space vacuum and radiation effects on materials, lubrication and surface phenomena, thermionic emission, photosensitive materials and detectors, atomic frequency standards, and bioenvironmental research and monitoring.

Electronics Research Laboratory: Microelectronics, GaAs low-noise and power devices, semiconductor lasers, electromagnetic and optical propagation phenomena, quantum electronics, laser communications, lidar, and electro-optics; communication sciences, applied electronics, semiconductor crystal and device physics, radiometric imaging; millimeter-wave and microwave technology.

Information Sciences Research Office: Program verification, program translation, performance-sensitive system design, distributed architectures for spaceborne computers, fault-tolerant computer systems, artificial intelligence, and microelectronics applications.

Materials Sciences Laboratory: Development of new materials: metal matrix composites, polymers, and new forms of carbon; component failure analysis and reliability; fracture mechanics and stress corrosion; evaluation of materials in space environment; materials performance in space transportation systems; analysis of systems vulnerability and survivability in enemy-induced environments.

Space Sciences Laboratory: Atmospheric and ionospheric physics, radiation from the atmosphere, density and composition of the upper atmosphere, aurorae and airglow; magnetospheric physics, cosmic rays, generation and propagation of plasma waves in the magnetosphere; solar physics, infrared astronomy; the effects of nuclear explosions, magnetic storms, and solar activity on the earth's atmosphere, ionosphere, and magnetosphere; the effects of optical, electromagnetic, and particulate radiations in space on space systems.

END

DATE
FILMED

11-82

DTIC