

12

AD-A133 997

THE EFFECT OF MICROSTRUCTURE ON THE PROPERTIES
OF HIGH STRENGTH ALUMINUM ALLOYS

Final Report on

AFOSR-78-3471

January, 1983

by

Edgar A. Starke, Jr.
Fracture and Fatigue Research Laboratory
Georgia Institute of Technology
Atlanta, Georgia 30332

DTIC
ELECTE
S OCT 24 1983 D

DTIC FILE COPY

This research was sponsored by the Air Force Office of
Scientific Research Directorate of Electronic and Solid
State Sciences under Research Grant Number AFOSR-78-3471.

Approved for Public Release, Distribution Unlimited

83 10 17 164

Abstract

→ This program was initiated in January, 1978, and was concerned with the effect of microstructure on the properties of two different classes of aluminum alloys of current interest to the Air Force: (1) high strength Al-Zn-Mg-X alloys and (2) low density, high modulus Al-Li-X alloys. The program terminated on December 31, 1982. Work prior to 1982 has been described in detail in our Annual Scientific Reports, the last of which was issued in February, 1982. This Final Report will list publications resulting from work on AFOSR Grant No. 78-3471 and summarize results obtained in 1982.

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A	



AIR FORCE OFFICE OF SCIENTIFIC RESEARCH (AFOSR)
 NOTICE OF TRANSMITTAL TO DTIC
 This technical report has been reviewed and approved for public release IAW AFR 190-12.
 Distribution is unlimited.
 MATTHEW J. KERPER
 Chief, Technical Information Division

1. The Microstructure and Properties of An Extruded P/M X7091 Plate (Walker and Starke)

Rapid solidification and powder metallurgy (P/M) consolidation offers a means of producing finer dendrite cells, finer dispersions of intermetallic compounds, fewer undissolved constituents and fewer inhomogeneities when compared with I/M methods. Early feasibility studies on combining age and dispersion hardening alloy additions in 7XXX alloys led to the development of a P/M consolidation process for fabricating high quality, blister free products. Although high axial tensile strength and good stress corrosion cracking resistance were produced, the products were plagued by low fracture toughness, especially in the short transverse direction. Since then, modifications to early fabrication processes have greatly improved fracture toughness and have allowed the production of 7XXX alloys with equal or superior combinations of strength, toughness and SCC resistance when compared with equivalent I/M alloys. To date, the quantitative evaluation of P/M microstructures and the relationship of these microstructures to cyclic stress and strain has been limited.

The purpose of this study was to characterize the microstructure of an extruded PM X7091 plate and to evaluate the alloy's monotonic and cyclic properties. The results were compared with 7XXX I/M alloys. Better combinations of tensile properties were obtained by rapid solidification and P/M consolidation methods. However, anticipated improvement in fatigue crack initiation resistance was not realized due to the presence of oxides along grain boundaries. In order to obtain better fatigue properties, processing procedures that dissociate the boundaries from the oxides should be utilized. A manuscript resulting from this research has been submitted to Powder Metallurgy.

2. The Influence of Grain Structure on the Ductility of the Al-Cu-Li-Mn-Cd Alloy 2020 (Starke and Lin)

The main purpose of adding lithium to aluminum alloys is to obtain a better combination of low density, high elastic modulus, and high strength; properties especially attractive for aerospace applications. The first commercial lithium-containing aluminum alloy was made available by Alcoa in 1958, and designated 2020 by the Aluminum Association. Although 2020 had a room temperature strength comparable to 7075-T6 and an elevated temperature stability higher than other age hardenable aluminum alloys, its low ductility and fracture toughness in the maximum strength temper led to the termination of production in 1969.

The purpose of this research was to study the influence of grain structures, as produced by various TMT's, on the ductility of 2020 plate. Materials having a completely or partially recrystallized structure exhibited elongation between 4 and 8% when aged to peak strength. For both cases the low ductility was associated with (a) planar deformation, (b) random texture, (c) the presence of large intermetallic compounds along the recrystallized grain boundaries, and (d) precipitate-free zones. The first three enhance crack nucleation at high angle grain boundaries, and subsequent crack propagation occurs along the precipitate-free zones. The completely unrecrystallized materials had elongation between 10 and 13% in both longitudinal and transverse directions. The high ductility was associated with a sharp texture and a transgranular fracture mode. The maximum ductility was obtained by reducing the unrecrystallized grain size. The results of this study suggest that improved properties of a 2020-type alloy may be obtained by lowering the Fe and Si contents to remove coarse constituent phases, eliminating Cd, and replacing Mn with Zr in order to obtain a highly texture, unrecrystallized structure. The results of this program were published in Metallurgical Transactions

3. Effects of Precipitation Heat Treatment on the Microstructure, Toughness, and Stress Corrosion Crack Propagation Resistance of Aluminum Alloy 2020 (Rinker and Sanders)

The objective of this research was to determine the effects of precipitation heat treatment on the strength, toughness, microstructure, and stress corrosion resistance of 2020. The peak strength temper and several underaged and overaged conditions were studied. Precipitation strengthening was found to be due to extensive co-precipitation of the θ' (Al_2Cu) and T_1 (Al_2CuLi) phases, confirming the results of previous studies. Although some evidence of δ' precipitation was also found, no significant contribution to strengthening was attributed to this phase.

Fracture toughness was found to decrease markedly with aging to peak strength due to an increasing tendency toward strain localization by the concentration of deformation into intense planar bands and the concomitant decrease in strain hardening capacity. The strength/toughness relationship for several high strength underaged tempers of 2020 was found to be superior to that for the peak strength temper and for standard tempers of other 2XXX alloys. One underaged temper with a yield strength 12% lower than the peak aged temper had 80% higher plane strain fracture toughness and 300% higher crack propagation resistance. The toughness of overaged tempers was found to be much lower than that of underaged tempers having the same yield strength.

The stress corrosion cracking resistance of 2020 in the peak strength temper and several high strength underaged tempers was found to be excellent. Poor SCC resistance was observed for a very underaged temper. A model was developed which associates SCC resistance with the electrochemical potential

difference between grain boundary T_1 precipitates and the interior of grains.
A manuscript is being prepared for submission to Metallurgical Transactions.

PROFESSIONAL PERSONNEL

Dr. Edgar A. Starke, Jr.
Dr. Thomas H. Sanders, Jr.
Dr. Saghana B. Chakraborty
Dr. Fu-Shiong Lin
Dr. M. Marek

GRADUATE STUDENTS

Charles Heikkinen
Paul Niskanen
John Rinker
John A. Walker
Tirumalai Srivatsan

DEGREES GRANTED UNDER AFOSR-78-3471

Fu-Shiong Lin, "Low Cycle Corrosion Fatigue and Crack Propagation of High Strength 7XXX-Type Aluminum Alloys," Doctor of Philosophy, April, 1978.

Bhaskar Sarkar, "Stress Corrosion Characteristics of Al-Zn-Mg Alloys with Copper Additions," Doctor of Philosophy, August, 1979.

John Andrew Walker, "The Microstructure and Properties of Extruded P/M CT91-T7X151," Master of Science in Metallurgy, December, 1980.

Herman Charles Heikkinen, "A Study of the Fatigue Behavior of an Al₂Zn-2Mg-0.1Zr Alloy," Master of Science in Metallurgy, November 1981.

John George Rinker, "Effects of Precipitation Heat Treatment on the Microstructure, Toughness, and Stress Corrosion Crack Propagation Resistance of Aluminum Alloy 2020," Doctor of Philosophy, September, 1982.

PUBLICATIONS UNDER AFOSR-78-3471

Fu-Shiong Lin and E. A. Starke, Jr., "The Effect of Copper Content and Degree of Recrystallization on the Fatigue Resistance of 7XXX-Type Aluminum Alloys, I. Low Cycle Corrosion Fatigue," Mater. Sci. and Engr., 39, 27-41 (1979).

E. E. Underwood and E. A. Starke, Jr., "Quantitative Stereological Methods for Analyzing Important Microstructural Features in Fatigue of Metals and Alloys," in STP 675, ASTM, Philadelphia, PA, 633-682 (1979).

Fu-Shiong Lin and E. A. Starke, Jr., "The Effect of Copper Content and Degree of Recrystallization on the Fatigue Resistance of 7XXX-Type Aluminum Alloys, II. Fatigue Crack Propagation," Mater. Sci. and Engr., 43, No. 1, 65-76 (1980).

Fu-Shiong Lin and E. A. Starke, Jr., "The Effect of Copper Content and Deformation Mode on the Corrosion Fatigue Crack Growth Behavior of Al-6Zn-2Mg-XCu Alloys at Low Stress Intensities," Mater. Sci. and Engr., 45, 153-165 (1980).

E. A. Starke, Jr. and Fu-Shiong Lin, "Microstructure-Environment Influence on the Fatigue Behavior of Aerospace 7XXX Aluminum Alloys," Proceedings Institute of Environmental Sciences, 131-135, Philadelphia, PA (1980).

Fu-Shiong Lin and E. A. Starke, Jr., "Mechanisms of Corrosion Fatigue Crack Propagation of 7XXX Aluminum Alloys in Aqueous Environments," in Hydrogen Effects in Metals, ed. I. M. Bernstein and Anthony W. Thompson, TMS-AIME, 485-492 (1980).

B. Sarkar, M. Marek, and E. A. Starke, Jr., "The Effect of Copper Content and Heat Treatment on the SCC Behavior of Al-6Zn-2Mg-XCu Alloys," Met. Trans. A, 12A, 1939-1943 (1981).

P. Niskanen, T. H. Sanders, Jr., M. Marek, and J. G. Rinker, "The Influence of Microstructure on the Corrosion of Al-Li, Al-Li-Mn, Al-Li-Cu Alloys in 3.5% NaCl Solution," in Aluminum-Lithium Alloys, ed. T. H. Sanders, Jr. and E. A. Starke, Jr., TMS-AIME, 347-376 (1981).

E. A. Starke, Jr., T. H. Sanders, Jr. and I. G. Palmer, "New Approaches to Alloy Development in the Al-Li System," J. of Metals 33, 24-33 (1981).

H. C. Heikkinen, Fu-Shiong Lin and E. A. Starke, Jr., "The Low Cycle Fatigue Behavior of High Strength 7XXX-Type Aluminum Alloys in the T7351 Condition," Mater. Sci. and Engr. 51, 17-23 (1981).

F. S. Lin, S. B. Chakraborty and E. A. Starke, Jr., "Microstructure-Property Relationships of Two Al-3Li-2Cu-0.2Zr-XCd Alloys," Met. Trans. A, 13A, 401-410 (1982).

H. C. Heikkinen, F. S. Lin and E. A. Starke, Jr., "The Relationship Between Microstructure, Cyclic-Stress Strain Response and Fatigue Crack Propagation in Al-Zn-Mg Alloys," Aluminium (in press).

T. H. Sanders, Jr. and P. W. Niskanen, "Microstructure, Mechanical Properties and Corrosion Resistance of Al-Li-X Alloys - An Overview," Res Mechanica Letters 1, 363-370 (1981).

P. Niskanen, T. H. Sanders, Jr., J. G. Rinker and M. Marek, "Corrosion of Aluminum Alloys Containing Lithium," Corrosion Science (in press).

Edgar A. Starke, Jr., "Aluminum-Lithium Alloys," in 1981 Year Book of Science and Technology, McGraw-Hill Company, New York (in press).

H. C. Heikkinen, F. S. Lin, and E. A. Starke, Jr., "The Effect of Environment on the Low Cycle Fatigue Life and Fatigue Crack Propagation Behavior of an Al-6Zn-2Mg-0.1Zr Alloy," in Environmental Degradation of Engineering Materials, ed. M. R. Louthan, Jr., R. P. McNitt and R. D. Sesson, Jr., VPI, Blacksburg, VA, 459-469 (1981).

T. H. Sanders, Jr., and E. A. Starke, Jr., "The Effect of Slip Distribution on the Monotonic and Cyclic Ductility of Al-Li Binary Alloys," Acta Met. 30, 927-939 (1982).

H. C. Heikkinen, E. A. Starke, Jr. and S. B. Chakraborty, "Modification of the Chakraborty Model for Calculating Fatigue Crack Growth Rates," Scripta Met. 16, 571-574 (1982).

E. A. Starke, Jr. and F. S. Lin, "The Influence of Grain Structure on the Ductility of the Al-Cu-Li-Mn-Cd Alloy 2020," Met. Trans. 13A, 2259-2269 (1982).

J. A. Walker and E. A. Starke, Jr., "The Microstructure and Properties of an Extended P/M X7091 Plate," submitted to Powder Metallurgy.

J. R. Pickens and E. A. Starke, Jr., "The Effect of Rapid Solidification on the Microstructures and Properties of Aluminum Powder Metallurgy Alloys," in Proceedings of the Third Conference on Rapid Solidification Processing: Principles and Technologies, NBS, Gaithersburg, MD (in press).

J. C. Williams and E. A. Starke, Jr., "The Use of Thermomechanical Processing in Tailoring and Microstructure and Properties of Titanium and Aluminum Alloys," in Deformation, Processing and Structure, ASM (in press).

C. J. Beevers, R. L. Carlson, K. Bell and E. A. Starke, Jr., "A Model for Fatigue Crack Closure," submitted to Engr. Fract. Mech.

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. AFOSR-TR. 83-0845	2. GOVT ACCESSION NO. AL-4133997	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) THE EFFECT OF MICROSTRUCTURE ON THE PROPERTIES OF HIGH STRENGTH ALUMINUM ALLOYS		5. TYPE OF REPORT & PERIOD COVERED FINAL REPORT 01 JAN 78 -01 JAN 83
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) E. A. STARKE, JR.		8. CONTRACT OR GRANT NUMBER(s) AFOSR-78-3471
9. PERFORMING ORGANIZATION NAME AND ADDRESS Georgia Institute of Technology Atlanta, GA 30332		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS 61102F 2306/A1
11. CONTROLLING OFFICE NAME AND ADDRESS Air Force Office of Scientific Research/NE Building #410 Bolling AFB, DC 20332		12. REPORT DATE 1983
		13. NUMBER OF PAGES 7
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Aluminum alloys, microstructure		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) This program was initiated in January, 1978, and was concerned with the effect of microstructure on the properties of two different classes of aluminum alloys of current interest to the Air Force: (1) high strength Al-Zn-Mg-X alloys and (2) low density, high modulus Al-Li-X alloys. The program terminated on December 31, 1982. Work prior to 1982 has been described in detail in our Annual Scientific Reports, the last of which was issued in February, 1982. This Final Report will list publications resulting from work on		

DD FORM 1473

1 JAN 73

EDITION OF 1 NOV 65 IS OBSOLETE

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

AFOBR Grant No. 78-3471 and summarize results obtained in 1982.

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)