

AD-A138 538 NEW THEORY FOR THICK COMPOSITE-MATERIAL RINGS(U) 1/1
OKLAHOMA UNIV NORMAN SCHOOL OF AEROSPACE MECHANICAL AND
NUCLEAR ENGINEERING C W BERT AUG 83 OU-AMNE-83-4
UNCLASSIFIED N00014-78-C-0647 F/G 13/13 NL


END

DATE

FILED

4 84

DTIC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

AD A138538

Department of the Navy
OFFICE OF NAVAL RESEARCH
Mechanics Division
Arlington, Virginia 22217

Contract N00014-78-C-0647
Project NR 064-609
Technical Report No. 36

Report OU-AMNE-83-4

NEW THEORY FOR THICK, COMPOSITE-MATERIAL RINGS

by

Charles W. Bert

DTIC
S FEB 14 1984 D
P H

August 1983

School of Aerospace, Mechanical and Nuclear Engineering
The University of Oklahoma
Norman, Oklahoma 73019

Approved for public release; distribution unlimited

DTIC FILE COPY

NEW THEORY FOR THICK, COMPOSITE-MATERIAL RINGS*

C.W. Bert**

*School of Aerospace, Mechanical and Nuclear Engineering
The University of Oklahoma, Norman, Oklahoma*

ABSTRACT

A new theory for the in-plane elastic behavior of shear-deformable ring-type structures, i.e., curved beams and complete rings, is presented. This theory falls between Bresse-Timoshenko-type ring theory, in which the shear deformation is assumed to be distributed uniformly through the thickness and corrected by a shear correction factor determined in an *ad hoc* fashion, and two- or three-dimensional elasticity theory. As an example, the theory is applied to the problem of a diametrically loaded thick ring. The predicted normal-stress distribution is in excellent agreement with published results in the literature obtained by photoelastic measurements.



Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution	
Availability Codes	
Dist	
A-1	

* This paper was an invited paper presented at the 17th Israel Conference on Mechanical Engineering, Tel Aviv University, July 12-14, 1983.

** The Benjamin H. Perkinson Professor of Engineering and Goerge L. Cross Research Professor.

NOTATION

A	- stretching stiffness	y	- circumferential position on middle surface
a	- cross-sectional area of ring	z	- outward normal position coordinate
B, B', C	- bending-stretching coupling stiffnesses	α, β	- linear and quadratic coefficients in expansion of V in powers of z
D, F	- bending stiffnesses	γ	- shear strain
E	- Young's modulus	γ^0	- transverse shear strain at z = 0
G	- shear modulus	ϵ	- normal strain
h	- total in-plane depth of ring	ϵ^0	- circumferential normal strain at z = 0
M	- bending moment	θ	- circumferential position angle
N	- circumferential force	κ	- bending curvature change
P	- concentrated force	ν	- Poisson's ratio
p_i	- internal pressure	σ	- normal stress
Q	- shear force	τ	- shear stress
R	- mean radius of ring	ϵ	- cubic coefficient in expansion of V in powers of z
S	- shear stiffness	$(\quad)_{,y}$	- $\partial(\quad)/\partial y$
V	- circumferential displacement		
v	- circumferential displacement of middle surface		
W	- radial displacement		
w	- radial displacement of middle surface		

1. INTRODUCTION

Ring-type structures are an important class of structural elements used as flywheel rims, shell rims, load-calibration rings, elements of transducers, and as circumferential reinforcements for cylindrical shells. Furthermore, the theory of rings can be considered to be a degenerate version of shell theory.

The theory of in-plane vibration of relatively thick circular rings, including transverse shear deformation and rotatory inertia, dates back to the work of Bresse (1859), which predates the classical thin-ring theory of Hoppe (1871) as well as Timoshenko's shear-deformable beam theory (1921). A discussion of some of the large body of ensuing literature was provided by Haines (1974). The pioneering shell theory due to Hildebrand et al. (1949) and the work of Benzley et al. (1973) should also be mentioned. An alternative is to use the two- or three-dimensional theory of elasticity, such as used by Federhofer (1935) and Endo (1972), respectively.

It has long been known that the Bresse-Timoshenko theory suffers from a serious flaw: it is based on the assumption of a uniform distribution of transverse shear strain through the thickness, whereas the actual distribution is that of a distorted parabola. Numerous *ad hoc* approaches, both static and dynamic, have been suggested for determining the so-called shear correction factor to account for the differences between these stress and strain distributions; see, for instance, Mindlin and Deresiewicz (1954) and Cowper (1966).

Only recently was an entirely new theory proposed to allow a more realistic shear strain distribution; it is due to Levinson (1981). This theory and its companion plate theory (Levinson, 1980), as well as analogous earlier theories by Ambartsumyan (1970), Reissner (1975), and Schmidt (1977), were

derived for macroscopically homogeneous material only.

It is well known that transverse shear deformation plays an even more important role in structures composed of fiber-reinforced composite materials than in those of homogeneous material; see, for example, Tarnopol'skii et al. (1965). Dynamic and static derivations of the shear correction factor for a laminate were presented by Yang et al. (1966) and by Whitney (1973) and Bert (1973). The latter work was recently extended to the case of beams laminated of bimodular materials (different elastic properties in tension and compression) by Bert and Gordaninejad (1983).

Levinson's theory of plates was recently extended to laminated plates by Murthy (1981); see also Bert (1983). However, the Levinson theory cannot be extended to ring-type members and still satisfy the requirements of zero shear strain at the intrados and extrados of the ring. This is the motivation for the present theory, in which these zero-shear-strain requirements are satisfied.

Most of the theories of shear-deformable ring mechanics (including Bresse, 1859 and Haines, 1974) are what might be termed first-approximation theories, analogous to Love's first-approximation shell theory (see Kraus, 1967), in which it is assumed in the strain-displacement relations that $z/R \ll 1$. This is analogous to Winkler-Bach curved beam theory (see Seely and Smith, 1952) but in contrast to the shear-deformable ring theory due to Kirkhope (1977).

2. HYPOTHESES

In the present work, the following simplifying assumptions are made:

1. As in other ring theories, thickness normal strain is neglected, i.e., $\epsilon_z = 0$.
2. The shear strain distribution is nonlinear in such a way that the

shear strain vanishes at the intrados and extrados of the ring. This is in contrast to all other ring or curved-beam theories (except elasticity theory) known to the present investigator, and allows accurate predictions without the use of a shear correction factor.

3. The theory is a first-approximation one, i.e., $z/R \ll 1$. This means that the theory should be most applicable to thin rings made of highly shear-deformable material (such as fiber-reinforced composite material).

4. Displacements are assumed to be sufficiently small that linear strain-displacement relations are adequate.

5. The ring cross section may be homogeneous or arbitrarily laminated of linear cylindrically orthotropic elastic material (see Fig. 1).

3. THEORETICAL DERIVATION

The following displacement field is used as the point of departure (Fig. 1):

$$\begin{aligned} V(\theta, z) &= v(\theta) + z\alpha(\theta) + z^2\beta(\theta) + z^3\gamma(\theta) \\ W(\theta, z) &= w(\theta) \end{aligned} \quad (1)$$

The expression for circumferential displacement V contains the same terms used in Levinson's beam theory (1981) plus middle-surface displacement v to account for bending-stretching coupling and the quadratic term, which is now necessary. The expression for radial deflection W is consistent with hypothesis 1.

It is shown in the Appendix that it is not possible to use the displacement field (1) in conjunction with the exact linear strain-displacement relations and still satisfy hypothesis 2. Thus, consistent with hypotheses 3 and 4, the following first-approximation strain-displacement relations are used.

$$\begin{aligned} \epsilon_{\theta} = \epsilon_y &= (W/R) + V_{,y} \quad ; \quad \epsilon_z = W_{,z} \\ \gamma_{\theta z} = \gamma_{yz} &= W_{,y} - (V/R) + V_{,z} \end{aligned} \quad (2)$$

where $(\)_{,y} = \partial(\)/\partial y$, etc. Substituting the displacement field (1) into (2), one obtains the strain field

$$\begin{aligned}\epsilon_y &= [v_{,y} + (w/R)] + z\alpha_{,y} + z^2\beta_{,y} + z^3\gamma_{,y} \quad ; \quad \epsilon_z = 0 \\ \gamma_{yz} &= [w_{,y} - (v/R) + \alpha] + [2\beta - (\alpha/R)]z + [3\gamma - (\beta/R)]z^2 - (\gamma/R)z^3\end{aligned}\quad (3)$$

The material stress-strain relations for each layer in the laminate, in view of hypothesis 5, are

$$\sigma_y = E\epsilon_y \quad ; \quad \tau_{yz} = G\gamma_{yz} \quad (4)$$

In view of the third of (3) and the second of (4), enforcement of vanishing shear strains at the extrados and intrados, i.e., $\tau_{yz}(y, \pm \frac{1}{2}h) = 0$, requires that

$$\begin{aligned}[w_{,y} - (v/R) + \alpha] + [3\gamma - (\beta/R)](h/2)^2 &= 0 \\ [2\beta - (\alpha/R)] - (\gamma/R)(h/2)^2 &= 0\end{aligned}\quad (5)$$

Consistent with hypothesis 3, one can neglect $(1/8)(h/R)^2$ compared with unity. Within this approximation, it can be shown that equations (5) are satisfied if one sets

$$\begin{aligned}\beta &= (\alpha/2R) - (1/6R)[w_{,y} - (v/R) + \alpha] \\ \gamma &= - (4/3h^2)[w_{,y} - (v/R) + \alpha]\end{aligned}\quad (6)$$

Thus, the final expressions for the non-zero strain distributions can be written as

$$\begin{aligned}\epsilon_y &= [v_{,y} + (w/R)] + z\alpha_{,y} + (z^2/6R)[2\alpha_{,y} - w_{,yy} + (v_{,y}/R)] \\ &\quad - (4/3)(z^3/h^2)[w_{,yy} - (v_{,y}/R) + \alpha_{,y}] \\ \gamma_{yz} &= [1 - (1/3)(z/R) - 4(z/h)^2 + (1/6)(z/R)^2 + (4/3)(z^3/Rh^2)] \\ &\quad \cdot [w_{,y} - (v/R) + \alpha] - (\alpha/2)(z/R)^2\end{aligned}\quad (7)$$

The nonlinearity of the strain distributions in (7) is readily apparent.

As is customary, the stress resultants and stress couple are defined as (see Fig. 1)

$$(N, M) \equiv \int_a (1, z) \sigma_y da \quad ; \quad Q \equiv \int_a \tau_{yz} da \quad (8)$$

From the theory of elasticity in plane polar coordinates $(R+z, \theta)$, the circumferential and radial equations of equilibrium for any arbitrary point within the ring are, in the absence of body forces,

$$\begin{aligned} \tau_{\theta z, z} + (\sigma_{\theta, \theta} + 2\tau_{\theta z})/(R+z) &= 0 \\ \tau_{\theta z, \theta} + (R+z)\sigma_{r, z} + \sigma_r - \sigma_{\theta} &= 0 \end{aligned} \quad (9)$$

Multiplying the first of (9) by $(R+z)$, integrating with respect to z , using relations (6), and noting that $\tau_{\theta z}$ vanishes at the intrados and extrados, one has

$$N_{,y} + (Q/R) = 0 \quad (10)$$

Similarly, multiplying the first of (9) by $(R+z)z$ and integrating with respect to z , one obtains

$$M_{,y} - Q = 0 \quad (11)$$

Finally, integrating the second of (9) with respect to z , one finds

$$Q_{,y} - (N/R) + p_i = 0 \quad (12)$$

Substituting the strains (7) into the stress-strain relations (4) and thence into the generalized force definitions (8), one obtains the ring constitutive relations as follows

$$\begin{Bmatrix} N \\ M \end{Bmatrix} = \begin{bmatrix} A & B' \\ B & D \end{bmatrix} \begin{Bmatrix} v_{,y} + (w/R) \\ \alpha_{,y} \end{Bmatrix} - \begin{Bmatrix} C \\ F \end{Bmatrix} (w_{,y} - \frac{v}{R} + \alpha)_{,y} \quad (13)$$

$$Q = S[w_{,y} - (v/R) + \alpha] - S'\alpha \quad (14)$$

where the ring stiffnesses are defined as

$$\begin{aligned} (A, B) &\equiv \int_a (1, z) E \, da \quad ; \quad (C, F) \equiv \int_a (1, z) [(z^2/6R) + (4/3h^2)z^3] E \, da \\ (B', D) &\equiv \int_a (z, z^2) [1 + (z/2R)] E \, da \quad ; \quad S' \equiv (1/2) \int_a (z/R)^2 G \, da \end{aligned} \quad (15)$$

$$S \equiv \int_a [1 - (z/3R) - 4(z/h)^2 + (1/6)(z/R)^2 + (4/3)(z^3/Rh^2)] G \, da$$

Equations (13) and (14) can be written in more compact form as follows:

$$\begin{Bmatrix} N \\ M \end{Bmatrix} = \begin{bmatrix} A & B' \\ B & D \end{bmatrix} \begin{Bmatrix} \epsilon^0 \\ \kappa \end{Bmatrix} - \begin{Bmatrix} C \\ F \end{Bmatrix} \gamma_{,y}^0 \quad (16)$$

$$Q = S\gamma^0 - S'\alpha \quad (17)$$

Substituting the ring constitutive relations (13) and (14) into the equilibrium equations (10)-(12), one obtains the following displacement equations of equilibrium in matrix-differential operator form:

$$\begin{bmatrix} L_{11} & L_{12} & L_{13} \\ L_{21} & L_{22} & L_{23} \\ L_{31} & L_{32} & L_{33} \end{bmatrix} \begin{Bmatrix} v/R \\ \alpha \\ w/R \end{Bmatrix} = \begin{Bmatrix} 0 \\ 0 \\ -p_i \end{Bmatrix} \quad (18)$$

Here,

$$L_{11} \equiv (AR + C)d_y^2 - (S/R) \quad , \quad L_{12} \equiv (B' - C)d_y^2 + (S/R) - (S'/R)$$

$$L_{13} \equiv -CRd_y^3 + (A + S)d_y \quad , \quad L_{21} \equiv (BR + F)d_y^2 + S$$

$$L_{22} \equiv (D - F)d_y^2 - S + S' \quad , \quad L_{23} \equiv -FRd_y^3 + (B - SR)d_y$$

$$\begin{aligned} L_{31} &\equiv -[(A+S) + (C/R)]d_y, & L_{32} &\equiv [S - S' - (B'/R) + (C/R)]d_y, \\ L_{33} &\equiv (SR + C)d_y^2 - (A/R), & d_y &\equiv d(\quad)/dy \end{aligned} \quad (19)$$

4. APPLICATION AND COMPARISON WITH EXPERIMENTAL RESULTS

As an application of the new theory, a diametrically loaded thick circular ring (see Fig. 2) is considered. Application of statics to the free-body diagram shown in Fig. 3 yields the following expressions for the generalized forces:

$$N = -P \cos \theta, \quad Q = -P \sin \theta, \quad M = -M_1 + PR \cos \theta \quad (20)$$

These expressions satisfy the equilibrium equations of the present theory, equations (10)-(12).

Since the problem is statically indeterminate to the first degree, an additional equation relation to deformation is required. From the ring constitutive relation, equation (13), one has

$$\alpha_{,y} = [AM - BN + (AF - BC)(Q_{,y}/S)]/[AD - BB' - (AF - BC)(S'/S)] \quad (21)$$

Integrating symbolically, one obtains

$$\alpha(\theta) = \int_0^\theta \alpha_{,y} R d\theta + \alpha(0) \quad (22)$$

Inserting the appropriate quantities into equation (22) and enforcing the symmetric conditions

$$\alpha(0) = \alpha(\pi/2) = 0 \quad (23)$$

one finds the following expression for the statically indeterminate bending moment:

$$M_1 = (2/\pi)[R + (B/A) - (1/ARS)(AF - BC)]P \quad (24)$$

It is noted that in the case of a homogeneous beam in thin ring theory ($S \rightarrow \infty$), equation (24) reduces to the classical value, $M_1 = (2/\pi)PR$.

The author was not able to locate any experimental stress or deflection data for a circumferentially-wound, fiber-reinforced composite-material ring, which would be the most stringent test for the new theory. However, some photoelastically obtained stress data were reported by Srinath and Acharya (1954) for a very thick ring of homogeneous, isotropic material. Specific data for their ring are listed in Table 1.

For the present special case of a homogeneous, isotropic ring, the ring stiffness parameters can be expressed as follows:

$$\begin{aligned} A/E = h, \quad B/E = 0, \quad B'/E = h^3/24R, \quad C/E = B'/3E, \quad D/E = h^3/12, \\ F/E = D/5E, \quad S/E = (1/3)h/(1+\nu), \quad S'/E = (1/48)(h^3/R^2)/(1+\nu) \end{aligned} \quad (25)$$

It was necessary to normalize the stiffnesses with respect to Young's modulus (E), since the actual value of the Young's modulus was not reported by Srinath and Acharya. The resulting expressions for the circumferential normal stress distribution are given below.

For the actual value of shear stiffness (S):

$$\sigma_y = -525 + 16,015z + 6,548z^2 + 13,195z^3 \quad (26)$$

Here, z and σ_y have units of inches and psi, respectively.

Neglecting transverse shear flexibility ($S \rightarrow \infty$):

$$\sigma_y = -517 + 16,104z + 6,315z^2 - 10,477z^3 \quad (27)$$

It is noted that inclusion of transverse shear deformation results in a more nonlinear stress distribution. A comparison of these predicted results with the reported experimental values is presented in Table 2. Certainly

the results for the new theory (actual S) are encouraging. Also presented is the prediction of Winkler-Bach ring theory, for which the bending stress is given by

$$\sigma_b = (M/he)(e + z)/(R + z) \quad (28)$$

where e is the distance from the centroid of the cross section to the neutral surface and is given by

$$e = R - h \left[\ln \frac{1 + (1/2)(h/R)}{1 - (1/2)(h/R)} \right]^{-1} \quad (29)$$

In the present case, at the horizontal cross section ($\phi = 0$), the bending moment is given by

$$M = P(R - e) - M_1 = [1 - (2/\pi)]P(R - e) \quad (30)$$

The total normal stress at $\phi = 0$ is given by

$$\sigma = - (P/h) + \sigma_b \quad (31)$$

In the numerical example under consideration, equation (31) becomes

$$\sigma = - 437 + 18,835 (0.0099356 + z)/(1.1875 + 2) \quad (32)$$

The numerical values are presented in the next to the last column in Table 2.

There is not a great deal of difference among all four stress distributions listed in Table 2. However, it is emphasized that the material is isotropic with $\nu = 0.35$, thus, the ratio of shear modulus to elastic modulus (G/E) is 0.3704. In contrast, for graphite/epoxy (T300/5208), this ratio is only 0.04368, according to the carefully correlated experimental results due to Knight (1982). Thus, it was decided to repeat the calculation of the present theory for a hypothetical ring constructed of hoop-wound

graphite/epoxy and having the same geometry and loading as previously discussed. The resulting equation, instead of equation (26), is

$$\sigma_y = - 587 + 15,204 z + 8,163 z^2 + 119,000 z^3 \quad (33)$$

This calculation was based upon the following material properties reported by Knight (1982):

Hoop-direction elastic modulus	20.1×10^6 psi
Transverse shear modulus	0.378×10^6 psi

The resulting stress distributions are plotted in Fig. 4, where it is noted that the low shear modulus of the graphite/epoxy causes much higher maximum stresses than are present in the isotropic ring.

5. DISCUSSION

In the development of the equilibrium equations, (10)-(12), the integration method believed to have been originated by Yang (1965) was used. However, this approach leads to equilibrium equations which are only approximate for the present case, although they are exact for the cases of the classical thin and shear deformable theories. More accurate, yet much more complicated, equilibrium equations can be obtained by application of the principle of virtual work, such as used by Kraus (1967) for thin-shell theory. However, in the present case, this approach gives rise to five more generalized forces than the theory presented here. They are of the form

$$\int_{-h/2}^{h/2} (z \tau_{xy}, z^2 \tau_{xy}, z \tau_{yz}, z^2 \tau_{yz}, z^3 \tau_{yz}) dz$$

These are analogous to the higher-order generalized forces obtained by Tiffen and Lowe (1963) and Lo et al. (1977a,b) in their higher-order plate theories. See also the treatise by Librescu (1975). The present approximation is more in keeping with Levinson's plate and beam theories (1980, 1981). Thus, it may be more appropriate to classify the present theory as a more accurate simplified theory rather than as a true higher-order theory. It should be mentioned that Langhaar (1965) pointed out that higher-approximation theories are not necessarily more accurate. He cited the case of a curved cantilever beam for which Love's first-approximation theory (same as Winkler-Bach curved-beam theory) yielded the statically correct force quantities while his second-approximation theory gave results which violated static equilibrium grossly.

6. CONCLUSIONS

The new ring theory presented here has the following advantages:

1. In contrast to other shear-deformable ring theories it does not require separate *ad hoc* determination of a shear correction factor.
2. In contrast to other first-approximation ring theories, it allows for a nonlinear distribution of circumferential displacement through the thickness.
3. Relative to two- or three-dimensional elasticity theory and to higher-order ring theory, it is much simpler and much more amenable to engineering calculations.

ACKNOWLEDGMENTS

The research reported upon here was sponsored by the Office of Naval Research, Mechanics Division. The encouragement of Drs. N.L. Basdekas and Y. Rajapakse is gratefully acknowledged. Also, the author acknowledges helpful discussions with Professor L. Librescu of Tel Aviv University, Professor J.N. Reddy of Virginia Polytechnic Institute, and Professor Eric Reissner of the University of California at San Diego.

REFERENCES

- Ambartsumyan, S.A., 1970. *Theory of Anisotropic Plates* (English translation), Technomic Publishing Co., Stamford, CT.
- Benzley, S.E., J.R. Hutchinson, and S.W. Key, 1973. A dynamic shell theory coupling thickness stress wave effects with gross structural response, *J. Appl. Mech.*, 40, 731-735.
- Bert, C.W., 1973. Simplified analysis of static shear factors for beams of nonhomogeneous cross section, *J. Compos. Matls.*, 7, 525-529.
- Bert, C.W., 1983. Comparison of new plate theories applied to laminated composites, *Mechanics of Composite Materials*, ASME Applied Mechanics Division, Vol. 58, presentation at ASME Winter Annual Meeting, Boston, MA, Nov. 1983.
- Bert, C.W. and F. Gordaninejad, 1983. Transverse shear effects in bimodular composite laminates, presentation at 20th Annual Meeting, Soc. of Engg. Science, Univ. of Delaware, Newark, DE, Aug. 1983; *J. Compos. Matls.*, 17, 232-298.
- Bresse, J.A.C., 1859, 1866. *Cours de mécanique appliquée*, Mallet-Bachelier, Paris; 2nd ed., Gauthier-Villars, Paris.
- Cowper, G.R., 1966. The shear coefficient in Timoshenko's beam theory, *J. Appl. Mech.*, 33, 335-340.
- Endo, M., 1972. Flexural vibrations of a ring with arbitrary cross section, *Bulletin of Japan Soc. of Mech. Engrg.*, 15, 446-454.
- Federhofer, K., 1935. Zweidimensionale theorie der Biegungsschwingungen des kreisringes mit rechteckigem querschnitt, *Sitzungsber. Akad. Wiss., Wien*, 144, 561-577.
- Haines, D.W., 1977. Asymptotic theories for wave propagation and vibrations in elastic rings and helical coils of small pitch, *Int. J. Solids Structures*, 10, 1405-1416.

- Hildebrand, F.B., E. Reissner, and G.B. Thomas, 1949. Notes on the foundations of the theory of small displacements of orthotropic shells, NACA TN 1833.
- Hoppe, R., 1871. Vibration en eines rings in seiner ebene, *J. für reine und angewandte Math. (Crelle's J.)*, 73, 158-170.
- Kirkhope, J., 1977. In-plane vibration of a thick circular ring, *J. Sound and Vibration*, 50, 219-227.
- Knight, M., 1982. Three-dimensional elastic moduli of graphite/epoxy composites, *J. Compos. Matls.*, 16, 153-159.
- Kraus, H., 1967. *Thin Elastic Shells*, Wiley, New York,
- Langhaar, H.L., 1965. Paradoxes in the theories of plates and shells, *Developments in Theoretical and Applied Mechanics*, 2, 1-8 (Proc., 2nd SECTAM), Pergamon, Oxford.
- Levinson, M., 1980. An accurate, simple theory of the statics and dynamics of elastic plates, *Mech. Res. Communications*, 7, 343-350.
- Levinson, M., 1981. A new rectangular beam theory, *J. Sound and Vibration*, 74, 81-87.
- Librescu, L., 1975. *Elastostatics and Kinetics of Anisotropic and Heterogeneous Shell-Type Structures*, Noordhoff International Publishing, Leyden.
- Lo, K.H., R.M. Christensen, and E.M. Wu, 1977a. A high-order theory of plate deformation - part 1: homogeneous plates, *J. Appl. Mech.*, 44, 663-668.
- Lo, K.H., R.M. Christensen, and E.M. Wu, 1977b. A high-order theory of plate deformation - part 2: laminated plates, *J. Appl. Mech.*, 44, 669-676.

- Mindlin, R.D. and H. Deresiewicz, 1954. Timoshenko's shear coefficient for flexural vibrations of beams, *Proc. 2nd U.S. Nat. Congr. Appl. Mech.*, ASME, pp. 175-178.
- Murthy, M.V.V., 1981. An improved transverse shear deformation theory for laminated anisotropic plates, NASA TP-1903.
- Reissner, E., 1975. On transverse bending of plates, including the effect of transverse shear deformation, *Int. J. Solids Structures*, 11, 569-573.
- Schmidt, R., 1977. A refined nonlinear theory of plates with transverse shear deformations, *J. Industrial Math. Soc.*, 27, 23-38.
- Seely, F.B. and J.O. Smith, 1952. *Advanced Mechanics of Materials*, 2nd ed., Wiley, New York.
- Srinath, L.S. and Y.V.G. Acharya, 1954. Stresses in a circular ring, *Applied Scientific Research*, 4, 189-194.
- Tarnopol'skii, Yu.M., A.V. Roze, and V.A. Polyakov, 1965. Shear effects during bending of oriented glass-reinforced plastics, *Polymer Mech.*, 1(2), 31-37.
- Tiffen, R. and P.G. Lowe, 1963. An exact theory of generally loaded elastic plates in terms of moments of the fundamental equations, *Proc., London Math. Soc.*, 13, 653-671.
- Timoshenko, S.P., 1921. On the correction for shear of the differential equation for transverse vibrations of prismatic bars, *Phil. Mag.*, Ser. 6, 41, 744-746.
- Whitney, J.M., 1973. Shear correction factors for orthotropic laminates under static load, *J. Appl. Mech.*, 40, 302-304.

- Yang, P.C., 1965. Elastic wave propagation in heterogeneous cylindrical Shells, *Developments in Mechanics*, 3(2), 215-228 (Proc., 9th Mid-western Mech. Conference, Univ. of Wisconsin, Madison), Wiley, New York.
- Yang, P.C., C.H. Norris, and Y. Stavsky, 1966. Elastic wave propagation in heterogeneous plates, *Int. J. Solids Structures*, 2, 665-684.

APPENDIX

The exact linear strain-displacement relations in shell coordinates are

$$\begin{aligned} \epsilon_{\theta\theta} &= (W + V_{,\theta})/(R + z) \quad ; \quad \epsilon_{zz} = W_{,z} \\ \gamma_{\theta z} &= V_{,z} + (W_{,\theta} - V)/(R + z) \end{aligned} \quad (A-1)$$

Using the displacement field of equations (1) in equations (A-1), one obtains

$$\begin{aligned} \epsilon_{\theta\theta} &= (R+z)^{-1} (w + v_{,\theta} + z \epsilon_{,\theta} + z^2 \epsilon_{,\theta\theta} + z^3 \epsilon_{,\theta\theta\theta}) \\ \epsilon_{zz} &= 0 \quad ; \quad \gamma_{\theta z} = (R+z)^{-1} (w_{,\theta} - v - z \epsilon_{,\theta} - z^2 \epsilon_{,\theta\theta} - z^3 \epsilon_{,\theta\theta\theta}) + \epsilon + 2z \epsilon_{,\theta} + 3z^2 \epsilon_{,\theta\theta} \end{aligned} \quad (A-2)$$

Enforcing $\epsilon_{zz}(\cdot, \pm \frac{1}{2}h) = 0$ thus requires that the following four equations be satisfied:

$$\begin{aligned} w_{,\theta} - v - (h^2/4) \epsilon_{,\theta} &= 0 \\ \epsilon + (h^2/4) \epsilon_{,\theta\theta} &= 0 \quad ; \quad \epsilon_{,\theta} = 0 \quad ; \quad \epsilon + (3h^2/4) \epsilon_{,\theta\theta} = 0 \end{aligned} \quad (A-3)$$

It is obvious that all four of these cannot be satisfied except in the trivial case, $\epsilon = \epsilon_{,\theta} = \epsilon_{,\theta\theta} = 0$ and $w_{,\theta} = v$.

Table 1. Conditions for experiments of Srinath and Acharya (19540)

Dimensional Data		Loading and Material Data
Ring depth	$h = 0.375 \text{ in.}$	Loading $P = 164 \text{ lb/in.}$
Ring mean radius	$R = 1.1875 \text{ in.}$	
Ratio	$h/R = 0.3158$	Poisson's ratio $\nu = 0.35^*$
* Estimated		

Table 2. Numerical results for distribution of circumferential normal stress (psi)

z/h	Present Theory		Winkler-Bach Theory	Measured
	$S \rightarrow \infty$	Actual S		
-0.500	-3,246	-3,371	-3,781	-3,550
-0.233	-1,871	-1,882	-1,765	-1,720
0	-517	-525	-279	Not reported
0.042	-264	-273	-37	-70
0.291	1,301	1,322	1,292	1,300
0.500	2,656	2,809	2,268	2,350




Fig.1 . Coordinates, displacements, forces and moments acting on a differential element of a ring.




Fig. 2. A diametrically loaded thick circular ring.




Fig. 3. Free-body diagram of ring segment.




Fig. 4. Normal-stress distributions for isotropic and graphite/epoxy rings loaded in diametral compression.

PREVIOUS REPORTS ON THIS CONTRACT

Project Rept. No.	Issuing University Rept. No.*	Report Title	Author(s)
1	OU 79-7	Mathematical Modeling and Micromechanics of Fiber Reinforced Bimodulus Composite Material	C.W. Bert
2	OU 79-8	Analyses of Plates Constructed of Fiber-Reinforced Bimodulus Materials	J.N. Reddy & C.W. Bert
3	OU 79-9	Finite-Element Analyses of Laminated Composite-Material Plates	J.N. Reddy
4A	OU 79-10A	Analyses of Laminated Bimodulus Composite-Material Plates	C.W. Bert
5	OU 79-11	Recent Research in Composite and Sandwich Plate Dynamics	C.W. Bert
6	OU 79-14	A Penalty Plate-Bending Element for the Analysis of Laminated Anisotropic Composite Plates	J.N. Reddy
7	OU 79-18	Finite-Element Analysis of Laminated Bimodulus Composite-Material Plates	J.N. Reddy & W.C. Chao
8	OU 79-19	A Comparison of Closed-Form and Finite-Element Solutions of Thick Laminated Anisotropic Rectangular Plates	J.N. Reddy
9	OU 79-20	Effects of Shear Deformation and Anisotropy on the Thermal Bending of Layered Composite Plates	J.N. Reddy & Y.S. Hsu
10	OU 80-1	Analyses of Cross-Ply Rectangular Plates of Bimodulus Composite Material	V.S. Reddy & C.W. Bert
11	OU 80-2	Analysis of Thick Rectangular Plates Laminated of Bimodulus Composite Materials	C.W. Bert, J.N. Reddy, V.S. Reddy, & W.C. Chao
12	OU 80-3	Cylindrical Shells of Bimodulus Composite Material	C.W. Bert & V.S. Reddy
13	OU 80-6	Vibration of Composite Structures	C.W. Bert
14	OU 80-7	Large Deflection and Large-Amplitude Free Vibrations of Laminated Composite-Material Plates	J.N. Reddy & W.C. Chao
15	OU 80-8	Vibration of Thick Rectangular Plates of Bimodulus Composite Material	C.W. Bert, J.N. Reddy, W.C. Chao, & V.S. Reddy
16	OU 80-9	Thermal Bending of Thick Rectangular Plates of Bimodulus Material	J.N. Reddy, C.W. Bert, Y.S. Hsu, & V.S. Reddy
17	OU 80-14	Thermoelasticity of Circular Cylindrical Shells Laminated of Bimodulus Composite Materials	Y.S. Hsu, J.N. Reddy, & C.W. Bert
18	OU 80-17	Composite Materials: A Survey of the Damping Capacity of Fiber-Reinforced Composites	C.W. Bert
19	OU 80-20	Vibration of Cylindrical Shells of Bimodulus Composite Materials	C.W. Bert & M. Kumar
20	VPI 81-11 & OU 81-1	On the Behavior of Plates Laminated of Bimodulus Composite Materials	J.N. Reddy & C.W. Bert
21	VPI 81-12	Analysis of Layered Composite Plates Accounting for Large Deflections and Transverse Shear Strains	J.N. Reddy
22	OU 81-7	Static and Dynamic Analyses of Thick Beams of Bimodular Materials	C.W. Bert & A.D. Tran
23	OU 81-8	Experimental Investigation of the Mechanical Behavior of Cord-Rubber Materials	C.W. Bert & M. Kumar
24	VPI 81.28	Transient Response of Laminated, Bimodular-Material Composite Rectangular Plates	J.N. Reddy
25	VPI 82.2	Nonlinear Bending of Bimodular-Material Plates	J.N. Reddy & W.C. Chao
26	OU 82-2	Analytical and Experimental Investigations of Bimodular Composite Beams	C.W. Bert, C.A. Rebello, & C.J. Rebello
27	OU 82-3	Research on Dynamics of Composite and Sandwich Plates, 1979-81	C.W. Bert
28	OU 82-4 & VPI 82.20	Mechanics of Bimodular Composite Structures	C.W. Bert & J.N. Reddy

*OU denotes the University of Oklahoma; VPI denotes Virginia Polytechnic Institute and State University.

Previous Reports on this Contract - Cont'd

<u>Project Rept. No.</u>	<u>Issuing University Rept. No.</u>	<u>Report Title</u>	<u>Author(s)</u>
29	VPI 82 19	Three-Dimensional Finite Element Analysis of Layered Composite Structures	W.C. Chao, N.S. Putcha, J.N. Reddy
30	OU 82-5	Analyses of Beams Constructed of Nonlinear Materials Having Different Behavior in Tension and Compression	C.W. Bert & F. Gordaninejad
31	VPI 82.31	Analysis of Layered Composite Plates by Three-Dimensional Elasticity Theory	J.N. Reddy & T. Kuppusamy
32	OU 83-1	Transverse Shear Effects in Bimodular Composite Laminates	C.W. Bert & F. Gordaninejad
33	OU 83-2	Forced Vibration of Timoshenko Beams Made of Multi-modular Materials	F. Gordaninejad & C.W. Bert
34	VPI 83.34	Three-Dimensional Analysis of Composite Plates with Material Nonlinearity	T. Kuppusamy, A. Nanda, & J.N. Reddy
35	OU 83-3	A Critical Evaluation of New Plate Theories Applied to Laminated Composites	C.W. Bert

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER OU-AMNE-83-4	2. GOVT ACCESSION NO. AD-A138638	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) NEW THEORY FOR THICK, COMPOSITE-MATERIAL RINGS		5. TYPE OF REPORT & PERIOD COVERED Technical Report No. 36
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) C.W. Bert		8. CONTRACT OR GRANT NUMBER(s) N00014-78-C-0647
9. PERFORMING ORGANIZATION NAME AND ADDRESS School of Aerospace, Mechanical and Nuclear Engineering University of Oklahoma, Norman, OK 73019		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS NR 064-609
11. CONTROLLING OFFICE NAME AND ADDRESS Department of the Navy, Office of Naval Research Mechanics Division (Code 432) Arlington, VA 22217		12. REPORT DATE August 1983
		13. NUMBER OF PAGES 24
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) This document has been approved for public release and sale; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES A preliminary version of this paper was presented as an invited paper at the 17th Israel Conference on Mechanical Engineering, Tel Aviv University, Tel Aviv, Israel, July 12-14, 1983.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Composite materials, moderately thick rings, rings (structural), shear deformable rings, static loading, transverse shear deformation		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A new theory for the in-plane elastic behavior of shear-deformable ring-type structures, i.e., curved beams and complete rings, is presented. This theory falls between Bresse-Timoshenko-type ring theory, in which the shear deformation is assumed to be distributed uniformly through the thickness and corrected by a shear correction factor determined in an <i>ad hoc</i> fashion, and two- or three-dimensional elasticity theory. As an example, the theory is applied to the problem of a diametrically loaded thick ring. The predicted		

DD FORM 1 JAN 73 1473

EDITION OF 1 NOV 65 IS OBSOLETE
S/N 0102-014-6601UNCLASSIFIED
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

20. Abstract - Cont'd

normal-stress distribution is in excellent agreement with published results in the literature obtained by photoelastic measurements.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

MED
-8