

AD-A147 365

MECHANICAL PROPERTY DATA 7050-T736511 ALLOY(U) DAYTON
UNIV OH RESEARCH INST OCT 84 UDR-TM-84-35
F33615-82-C-5102


1/1

UNCLASSIFIED

F/G 11/6

NL





1

UDR-TM-84-35

AD-A147 365

MECHANICAL PROPERTY DATA
7050-T736511 ALUMINUM ALLOY

ALUMINUM EXTRUSION

OCTOBER 1984

Prepared By:

UNIVERSITY OF DAYTON
Research Institute
Dayton, Ohio 45469

F33615-82-C-5102

DTIC
SELECTED
NOV 13 1984
A

This document has been approved
for public release and sale; its
distribution is unlimited.

84 11 09 041

DTIC FILE COPY

This data sheet was prepared by the University of Dayton Research Institute under Contract No. F33615-82-C-5102, under the direction of the Air Force Wright Aeronautical Laboratories, Materials Laboratory, Mr. Neal Ontko, MLSE, Technical Monitor.

Notice

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely related Government procurement operation, the United States Government thereby incurs no responsibility nor any obligation whatsoever; and the fact that the Government may have formulated, furnished, or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication or otherwise as in any manner licensing the holder or any other person or corporation, or conveying any rights or permission to manufacture, use, or sell any potential invention that may be in any way related thereto.

Approved for public release; distribution unlimited.

Copies of this report should not be returned unless return is required by security consideration, contractual obligations, or notice on a specific document.



Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

7050-T736511 Aluminum Alloy Extrusion

Material Description

This 7050 Aluminum Alloy was produced by Martin Marietta in the form of extrusions and heat treated to the T736511 temper. Twelve extrusions were used in obtaining samples for this test program. Due to the large variation in the geometry of the extrusions some variation in test sample length and thickness was required. This is most evident with the tensile samples in the long transverse direction in which both long and short as well as rectangular and round samples were used.

The average chemical composition of these extrusions is as follows:

<u>Chemical Composition</u>	<u>Percent Weight</u>
Silicon	.05
Iron	.11
Copper	2.24
Magnesium	2.29
Nickel	.01
Zinc	6.38
Titanium	.03
Lead	.01
Zirconium	.10
Aluminum	Balance

Processing and Heat Treating

The 7050 Aluminum Alloy was processed and formed into various shapes by extrusion. These extrusions were heat treated to the T736511 temper.

Results

↓ Data from samples of the 12 extrusions are included in this report. The average values for tension, compression, shear and bearing are listed in Table 1 by specimen direction. The elongation data presented was generated from long rectangular samples.

only. The shear results were obtained from the "Amsler" double pin shear fixture.



TABLE 1
ALUMINUM EXTRUSION (7050-T736511) (a)
R.T.

Properties	Plate Direction	
	Longitudinal	Long Transverse
<u>Tension</u>		
TUS, Ksi (MPa)	78.98 (544.6)	77.35 (533.3)
TYS, Ksi (MPa)	69.57 (479.7)	67.19 (463.3)
RA, percent	28.77	26.04
E, 10 ³ Ksi (GPa)	10.37 (71.54)	10.31 (71.05)
e, percent in 2 in ^(b) (50.8 mm)	13.53	13.65
<u>Compression</u>		
CYS, Ksi (MPa)	70.35 (485.1)	69.96 (482.3)
E _c , 10 ³ Ksi (GPa)	10.6 (73.1)	10.84 (74.76)
<u>Shear</u>		
SUS, Ksi (MPa) ^(c)	46.30 (319.3)	44.79 (308.8)
<u>Bearing</u>		
e/D = 1.5		
BUS, Ksi (MPa)	119.7 (825.4)	118.80 (819.4)
BYS, Ksi (MPa)	95.69 (659.6)	95.24 (656.7)
e/D = 2.0		
BUS, Ksi (MPa)	152.4 (1051.0)	153.10 (1056.0)
BYS, Ksi (MPa)	114.90 (792.4)	116.60 (804.1)

- (a) Values are average of triplicate room temperature test conducted on 12 extrusions at the University of Dayton Research Institute under the subject contract.
- (b) Elongation values from long, rectangular samples. Twelve extrusions in longitudinal direction, two extrusions in long transverse direction. Gage section: 2 in long x .5 in wide.
- (c) "Amsler" Double pin shear test conducted on 10 extrusions in the longitudinal direction and 9 extrusions in the long transverse direction.

END

FILMED

12-84

DTIC