

MICROCOPY RESOLUTION TEST CHART  
NATIONAL BUREAU OF STANDARDS-1963-A

(2) *EPH*

AD

Report 2417

AD-A154 985

EVALUATION OF EVAPORATION LOSS OF CHLOROTRIFLUOROETHYLENE  
FLUID IN AN M60 HYDRAULIC FLUID RESERVOIR

December 1984

DTIC  
ELECTE  
JUN 12 1985  
S B D

DTIC FILE COPY

Approved for public release; distribution unlimited.

Belvoir R&D Center



Department of the Army  
US Army Belvoir Research and Development Center  
Fort Belvoir, Virginia 22060-5606

85 5 16 046

**Destroy this report when it is no longer needed.  
Do not return it to the originator.**

---

**The citation in this report of trade names of  
commercially available products does not constitute  
official endorsement or approval of the use of such  
products.**

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER 2417	2. GOVT ACCESSION NO. ADA154985	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) EVALUATION OF EVAPORATION LOSS OF CHLOROTRIFLUORO- ETHYLENE FLUID IN AN M60 HYDRAULIC FLUID RESERVOIR		5. TYPE OF REPORT & PERIOD COVERED Final Report
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) In-Sik Rhee		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Fuels & Lubricants Division, STRBE-VF Materials, Fuels, & Lubricants Laboratory US Army Belvoir Research & Development Center Fort Belvoir, VA 22060-5606		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS IL726733AH20
11. CONTROLLING OFFICE NAME AND ADDRESS		12. REPORT DATE December 1984
		13. NUMBER OF PAGES 20
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) Unclassified
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)		
<div style="border: 1px solid black; padding: 5px; width: fit-content; margin: 0 auto;"> <p><b>DISTRIBUTION STATEMENT A</b> Approved for public release; Distribution Unlimited</p> </div>		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report) Approved for public release; distribution unlimited.		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number)		
Evaporation Semi-opened system Open system	Volatility Hydraulic fluid Closed system	MIL-H-6083 (OHT) Non-flammable hydraulic fluid TGA Chlorotrifluoroethylene (CTFE) M60 hydraulic fluid reservoir
20. ABSTRACT (Continue on reverse side if necessary and identify by block number)		
<p>The objective of this study was to evaluate the potential volatility problem of Chlorotrifluoroethylene (CTFE) fluids if used in the existing hydraulic systems of armored vehicles. Laboratory simulated service evaporation tests were conducted using the actual M60 hydraulic fluid reservoir at 160 °F for 3 wk and an additional 3 wk at 200 °F. The fluids used in these tests were the petroleum-based MIL-H-6083 (OHT) which was selected as the reference fluid and the experimental CTFE fluid which has been chosen as the candidate base material for the non-flammable hydraulic fluid currently under development. The test results showed negligible evaporation loss in both fluids under the conditions of the test performed. Therefore, it is concluded that volatility should not present any problem in the future use of CTFE-base fluids in the existing hydraulic systems.</p>		

DD FORM 1 JAN 73 1473 EDITION OF 1 NOV 68 IS OBSOLETE

UNCLASSIFIED  
SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

# CONTENTS

Section	Title	Page
	TABLES	iv
I	INTRODUCTION	1
II	TEST DETAILS	1
III	RESULTS OF TESTS	3
IV	DISCUSSION	3
V	CONCLUSIONS	6
	APPENDIX	
	THERMOGRAVIMETRIC ANALYSIS (TGA) OF HYDRAULIC FLUID	7

S DTIC ELECTE D

JUN 12 1985

B

Accession For	
NTIS GPA&I	<input checked="" type="checkbox"/>
DTIC TAG	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Special
A-1	

DTIC  
COPY NUMBER  
3

**TABLES**

<b>Table</b>	<b>Title</b>	<b>Page</b>
1	Simulated Service Evaporation Test Results	4
2	Evaporation Loss by Test Methods	5

# EVALUATION OF EVAPORATION LOSS OF CHLOROTRIFLUOROETHYLENE IN AN M60 HYDRAULIC FLUID RESERVOIR

## I. INTRODUCTION

The U.S. Army has used a petroleum-based hydraulic fluid covered by Military Specification MIL-H-6083 (OHT) as a standard operational fluid in all Army ground equipment.<sup>1</sup> During the Middle East conflict of 1973, the OHT fluid caused severe flammability problems in armored vehicles. As an interim solution, the Army developed and subsequently issued a new Military Specification MIL-H-46170 (FRH) to reduce the overall fire threat problem in armored vehicles.<sup>2</sup> Since the fielding of the FRH fluid was only an interim solution, as it is slightly less flammable than the OHT fluid, a program was initiated within the Army to address the development of a non-flammable hydraulic fluid for use in all Army armored vehicles.<sup>3</sup>

Preliminary investigations have focused on the halocarbon-based hydraulic fluid which has no flash or fire point. This fluid is a blend of completely halogenated chlorotrifluoroethylene (CTFE) oligomers and is completely inert to all acids, alkalis, and oxidizing agents. In earlier studies, laboratory screening tests were conducted according to an ASTM method<sup>4</sup> and Thermogravimetric Analysis method (TGA) to assess the high volatility and its potential for problems with use of this candidate hydraulic fluid. Since both test results confirmed that the candidate fluid blend is very volatile, simulated service evaporation tests were conducted to define the extent of this problem using specific components obtained from the existing hydraulic system. These tests were conducted at 160 °F for 3 wk followed by an additional 3 wk at 200 °F using a modified hydraulic fluid reservoir from an M60 A3 main battle tank.

The hydraulic fluids used in these tests were CTFE and OHT fluids. The OHT fluid was used as the reference fluid in this investigation because this fluid has been used successfully for many decades without a major evaporation problem in the field, while also indicating high volatility in the previously mentioned ASTM D972 and TGA tests.

Finally, this report describes the findings and the results of the simulated service evaporation tests.

## II. TEST DETAILS


The simulated service evaporation test apparatus is shown in the figure on the following page. The apparatus consists of an M60 hydraulic fluid reservoir, a stirrer, a temperature monitor, a thermocouple well, a dipstick gage, a support plate for reservoir, and a constant-high-temperature silicone oil bath. The M60 hydraulic fluid reservoir was chosen for use because of its capacity (about 4 gal). Additionally, the M60 tank is commonly used in the Army. For the purpose of this study, several modifications were made to the reservoir. The bottom of the reservoir was welded closed instead of being attached to the hydraulic pump. The top of the reservoir was sealed with a cover in lieu of being attached to the hydraulic riser assembly. A high-speed stirrer (3200 r/min) was mounted on the cover to simulate the turbulent flow and surface agitation normally generated by the hydraulic pump. For testing, the modified reservoir was placed in a silicone oil bath with a support plate as shown in the figure. The test temperature was maintained by the silicone oil bath and was regulated by the electronic temperature monitor. The fluid level in the reservoir was measured by use of a dipstick gage calibrated with 1/16-in increments to show volume capacity.

<sup>1</sup> Military Specification MIL-H-6083 "Hydraulic Fluid, Petroleum Base, for Preservation and Operation."

<sup>2</sup> Military Specification MIL-H-46170, "Hydraulic Fluid, Rust-Inhibited, Fire-Resistant, Synthetic Hydrocarbon Base."

<sup>3</sup> James H. Conley and Martin E. Everett, STATUS OF THE DEVELOPMENT OF A NON-FLAMMABLE HYDRAULIC FLUID FOR ARMORED VEHICLES, MFRADCOM Report 2362, Jun 82.

<sup>4</sup> ASTM 972, "Evaporation Loss of Lubricating Greases and Oils."



Experimental Apparatus.

With the test apparatus, the evaporation tests were conducted at 160°F for 3 wk and an additional 3 wk at 200 °F. Fluids used in these tests were MIL-H-6083 fluid and CTFE fluid which has been chosen as the candidate base material for the non-flammable hydraulic fluid. The MIL-H-6083 fluid was selected as the reference fluid.

For the experiment, the following test procedure was applied to these tests: First, the reservoir was filled with the test fluid to the full mark (i.e., 3.17 gal) indicated on the dip-stick gage. The reservoir was then immersed in a silicone oil bath with a support plate. When the test temperature stabilized at 160 °F, the fluid level was measured again. The test was then continued for 3 wk. At the end of this test period, the fluid level was measured at the test temperature and also at room temperature. Then, an approximate 50-ml sample was collected from the reservoir. The viscosity of this sample was measured by the applicable ASTM method and the fluid condition was observed using the Infrared Spectrophotometer. At the same time, new fluid was evaluated by the same methods. For the follow-up test at 200 °F, new fluid was added to the reservoir to restore the fluid to the initial level before sample collection. The test procedure was the same as before, except that the test temperature was raised to 200 °F.

### III. RESULTS OF TESTS

A summary of the evaporation test results is presented in Table 1. The result obtained for the CTFE fluid shows a 0.58-percent evaporation loss at 160 °F for the first 3-wk (504-h) test period and no further evaporation loss for the next 3-wk test period at 200 °F. In addition, the viscosity did not change during these test periods. Similarly, the OHT fluid showed a 0.56-percent evaporation loss. However, this loss occurred only at the high test temperature. The viscosity of this fluid was slightly decreased during the additional 3-wk test period. It appears the viscosity improver (V.I.) was degraded due to the high test temperature and/or shearing force. The Infrared Spectrophotometer also showed that the V.I improver changed in this test period. The specific gravity of both fluids did not change during the test period. However, the most significant result of these tests was that the evaporation loss of CTFE fluid was almost the same as that of the OHT fluid.

### IV. DISCUSSION

The preliminary evaluation of the candidate fluid was conducted using the ASTM test method used in the previous study. The result showed that the candidate fluid did not meet the initially proposed Army target requirement for the non-flammable hydraulic fluid.<sup>3</sup> In a follow-up test, another assessment of volatility was made using the TGA method to provide more evidence. The test result indicated that the candidate fluid had a higher evaporation rate at a given temperature when compared to the reference OHT fluid. This result substantiated the relative evaporation loss indicated by the ASTM test method. Hence, these results can be considered the true evaporation loss of both fluids in specific open systems because both test methods used the air or purge gas to accelerate the evaporation process. However, the results obtained from the simulated service evaporation tests showed almost no evaporation loss in both fluids. The M60 hydraulic fluid reservoir used in these tests is considered a semi-opened system because a very small venting gap exists between the dipstick gage cap and its tube. For all practical reasons, the hydraulic systems of armored vehicles can be considered a closed system.

<sup>3</sup> James H. Conley and Martin E. Everett. STATUS OF THE DEVELOPMENT OF A NON-FLAMMABLE HYDRAULIC FLUID FOR ARMORED VEHICLES. MERADCOM Report 2362, Jun 82.

Table I. Simulated Service Evaporation Test Results

Hydraulic Fluid	3 Weeks (504 h) at 160 °F				3 Weeks (504 h) at 200 °F				
	Viscosity at <sup>a</sup> 104 °F (cSt)		Specific Gravity <sup>b</sup> at 60 °F (g/cm <sup>3</sup> )		Viscosity at 104 °F (cSt)		Specific Gravity at 60 °F (g/cm <sup>3</sup> )		Total Δ Volume
	Initial	Final	Initial	Final	Initial	Final	Initial	Final	
MIL-H-6083	14.5	14.5	0.881	0.881	14.5	14.2	0.881	0.881	Δ Volume (%)
C.TFE	2.8	2.8	1.871	—	2.8	2.8	—	1.870	0
									-0.56
									-0.58

<sup>a</sup> ASTM D-445, Kinematic Viscosity of Transparent and Opaque Liquids.

<sup>b</sup> ASTM D-2111, Specific Gravity of Halogenated Organic Solvents and Their Admixtures (Method B, specific gravity by means of a hydrometer). Standard deviation is approximately ± 0.005.

<sup>c</sup> The volume was measured at room temperature.

<sup>d</sup> Not determined.

The simulated service evaporation test results were significantly different from those obtained in the two previous test methods. This can be explained best by noting the difference of opened and closed systems. In opened systems, the evaporation loss is directly related to the temperature, time, ratio of evaporation surface area to opening area, mechanical action, and ventilation (air, purge gas). In conditions of an opened system, vapor which escaped from the fluid surface cannot be recovered. Unlike the opened system, the closed system does not permit any evaporation loss to the outside. Once the vapor pressure has been established within the system, the amount of fluid and vapor remain constant at a given temperature, since for every particle that evaporates another condenses at the vapor-filled equilibrium.

In conjunction with the above facts, the test results showed that the M60 hydraulic fluid reservoir performed practically like a closed system, and the two previous tests represented opened systems. As a consequence of these experimental differences, the results obtained from the two previous test methods showed no correlation with those obtained in the simulated service evaporation tests. This simulated service evaporation test provided a realistic field environment.

The vapor pressure of the candidate fluid is about 4-mm Hg at 160 °F.<sup>5</sup> From the information available, it can be concluded that the hydraulic systems of armored vehicles generally operate at or below this temperature.<sup>6</sup> In addition, it is assumed that the actual maintenance interval with fluid replacement is shorter than 500 h.<sup>7</sup> Table 2 summarizes the results of evaporation losses by the different test methods.

Halocarbon Chlorofluoro Carbon Fluids and Lubricants, Halocarbon Products Corporation, 1979.

Test and Demonstration Report, M1 Hydraulic Heat Exchanger Evaluation, Report KZ-79-18322-023, Contract DAAK30-79C-0001, Chrysler Defense, Inc., Nov 81.

Lubrication Order L09-2350-232-12, "Tank, Combat, Full-Tracked: 152-mm Gun Launcher, M60A2," 28 Dec 73.

Table 2. Evaporation Loss by Test Methods

Test Method	Temperature (°F)	Period (h)	Evaporation Loss (%)		Proposed Army Target Requirement
			CTFE	OHT	
STM	158	6	40.8	11.8	≤ 20% in 6 h
GA*	160-200	Straight run	5-12	0-2	N/A
Simulated	160-200	1008	0.58	0.56	N/A

TGA results are shown in the appendix to this report.

## V. CONCLUSIONS

From the results of the simulated service evaporation tests, it can be concluded that the high volatility of fluid observed under standard test conditions in open and ventilated circumstances does not represent a problem under conditions simulating the actual system environment. Although this system is semi-closed, it can be considered closed for all practical purposes as far as fluid losses of CTFE are concerned. The fluid losses of CTFE are comparable to the losses observed with the OHT fluid under identical conditions. Since fluid volatility never surfaced as a field problem for the OHT fluid, no problems would be expected for CTFE fluid either.

## APPENDIX

### THERMOGRAVIMETRIC ANALYSIS (TGA) OF HYDRAULIC FLUID

Sample:

MIL-H-6083 (OHT)


CTFE

Test Conditions:

Heating Rate	10 °C/min
Atmosphere	N <sub>2</sub> @ 50 ml/min
Temperature Scale	50°/in
Span Adjust	20%/in
Suppression	0 mg
Time Constant	1 s
Thermocouple	chromel-alumel

#### Weight Loss of Hydraulic Fluid by TGA

Hydraulic Fluid	Onset Temperature of Evaporation (°C)	50-Percent Weight Loss Over Temperature Range (°C)
CTFE	45	45-120
OHT	63	63-192.5



Thermogravimetric Analysis (TGA) of hydraulic fluids.

**DISTRIBUTION FOR BELVOIR RESEARCH AND DEVELOPMENT CENTER  
REPORT 2417**

No. Copies	Addressee	No. Copies	Addressee
	<b>Department of Defense</b>	1	Commander US Army Tank-Automotive Command ATTN: AMSTA-RG, AMSTA-NS, AMSTA-G, AMSTA-M Warren, MI 48090
1	Director, Technical Information Defense Advanced Research Projects Agency 1400 Wilson Blvd Arlington, VA 22209		
1	Director Defense Nuclear Agency ATTN: TITL Washington, DC 20305	1	HQ, US Army Aviation Research and Development Command ATTN: AMDAD-D 1300 Goodfellow Blvd St. Louis, MO 63120
2	Defense Technical Information Center Cameron Station Alexandria, VA 22314	1	Director Applied Technology Laboratory US Army Research and Technology Laboratories (AVRADCOM) ATTN: DAVDL-ATL-P (Mr. Morrow) Fort Eustis, VA 23604
1	Department of Defense ATTN: DASD (MRAL)-LM (Mr. Dyckman) Washington, DC 20310		
1	Department of Defense Office of Secretary of Defense ATTN: USD (R&E)/RTL (Dr. Young) Washington, DC 20310	1	Commander US Army Natick Research and Development Laboratories ATTN: AMDNA-YEP (Dr. Kaplan) Natick, MA 01760
1	Commander Defense General Supply Center ATTN: DGSC-SSA Richmond, VA 23297	3	US Army Armament Research and Development Center ATTN: AMDAR-LC, AMDAR-SC, AMDAR-AC Dover, NJ 07801
	<b>Department of the Army</b>	1	US Armament Research and Development Center Ballistic Research Laboratory ATTN: AMDAR-BLV Aberdeen Proving Ground, MD 21005
5	HQ, Dept of Army ATTN: DALO-TSE, DALO-SMZ-E, DAMA-WSW, DAMA-ART, DAMA-ARA Washington, DC 20310		
5	Commander US Army Materiel Command ATTN: AMCLD (Mr. Bender) AMCDMR (Mr. Greiner) AMCQA-E AMCDMD-ST (Dr. Haley) 5001 Eisenhower Ave Alexandria, VA 22333	2	Director US Army Materiel Systems Analysis Agency ATTN: AMASY-S, AMASY-L Aberdeen Proving Ground MD 21005

No. Copies	Addressee	No. Copies	Addressee
2	Commander US Army Research Office ATTN: AMXRO-ZC, AMXRO-EG P.O. Box 12211 Research Triangle Park, NC 27709	2	Commander US Army General Material and Petroleum Activity ATTN: STSGP-F, STSGP New Cumberland Army Depot New Cumberland, PA 17070
1	Commander Tobyhanna Army Depot ATTN: SDSTO-TP-S Tobyhanna, PA 18466	1	Commander US Army Materiel Armament Readiness Command ATTN: AMSAR-LEM Rock Island Arsenal, IL 61299
1	Director US Army Materials and Mechanics Research Center ATTN: AMXMR-E Watertown, MA 02172	1	Commander US Army Cold Region Test Center ATTN: STECR-TA APO Seattle 98733
1	Commander US Army Watervliet Arsenal ATTN: SARWY-RDD Watervliet, NY 12189	1	Commander US Army Research and Standardization Group (Europe) ATTN: AMXSN-UK-RA Box 65 FPO NY 09510
1	Commander US Army Foreign Science and Technology Center ATTN: AMXST-MT1 Federal Building Charlottesville, VA 22901	1	Commander US Army Europe and Seventh Army ATTN: AEAGC-FMD APO NY 09403
1	Commander AMC Materiel Readiness Support Activity (MRSA) ATTN: AMXMD-MD Lexington, KY 40511	1	Department of the Army Construction Engineering Research Laboratory ATTN: CERL-ZT P.O. Box 4005 Champaign, IL 61820
1	Commander US Army LEA ATTN: DALO-LEP New Cumberland Army Depot New Cumberland, PA 17070	1	HQ, Dept of Army ATTN: DAEN-RDZ-B Washington, DC 20310
1	HQ, US Army Test and Evaluation Command ATTN: AMSTE-TO-O Aberdeen Proving Ground, MD 21005	1	HQ, 172d Infantry Brigade (Alaska) ATTN: AFZT-DI-L Directorate of Industrial Operations Fort Richardson, AK 99505
1	HQ, US Army Troop Support Command ATTN: AMSTS-MEG (2) AMCPO-PDE (LTC Foster) 1300 Goodfellow Blvd St. Louis, MO 63120	1	Proj Mgr, Abrams Tank System ATTN: AMCMP-GCM-S Warren, MI 48090

No. Copies	Addressee	No. Copies	Addressee
1	Proj Mgr. M60 Tank Development ATTN: AMCPC-M60-E Warren, MI 48090	1	Commander US Army Field Artillery Board ATTN: ATZR-BDPR Fort Sill, OK 73503
1	Prod Mgr. M113/M113A1 Family Vehicles AMCPM-M113 Warren, MI 48090	1	Commander US Army Transportation School ATTN: ATSP-CD-MS Fort Eustis, VA 23604
1	Proj Mgr. Improved Tow Vehicle US Army Tank-Automotive Command ATTN: AMCPC-MV-T Warren, MI 48090	1	Commander US Army Infantry School ATTN: ATSH-CD-MS-M Fort Benning, GA 31905
1	Commander US Army Forces Command ATTN: AFLG-REG, AFLG-POP Fort McPherson, GA 30330	1	Commander US Army Infantry Board ATTN: ATZB-IB-PR-T Fort Benning, GA 31905
1	HQ US Army Training and Doctrine Command ATTN: ATCD-SL Fort Monroe, VA 23651	1	Commander US Army Aviation Center and Fort Rucker ATTN: ATZQ-D Fort Rucker, AL 36362
1	HQ, US Army Armor Center ATTN: ATZK-CD-SB Fort Knox, KY 40121	1	Commander US Army Engineer School ATTN: ATZA-CMD Fort Belvoir, VA 22060
1	Commander US Army Quartermaster School ATTN: ATSM-CD Fort Lee, VA 23801	1	Commander US Army Ordnance Center and School ATTN: ASTL-CDT-MS Aberdeen Proving Ground, MD 21005
2	Commander US Army Armor and Engineer Board ATTN: ATZK-AE-PD, ATZK-AE-CV Fort Knox, KY 40121	1	Proj Mgr. Fighting Vehicle System ATTN: DRCPM-FVS-SE Warren, MI 48090
1	Commander US Army Logistics Center ATTN: ATCL-MS (Marshall) Fort Lee, VA 23801	1	Commander US Army Chemical School ATTN: ATZN-CM-SC Fort McClellan, AL 36205
1	Commander US Army Field Artillery School ATTN: ATSE-CD Fort Sill, OK 73503		

No. Copies	Addressee	No. Copies	Addressee
	<b>Department of the Air Force</b>	5	Matls. Fuels. & Lab Lab. STRBE-V
1	Commander US Air Force Wright Aeronautical Laboratory ATTN: AFWAL/POSL (Mr. Jones) AFWAL/MLSE (Mr. Morris). AFWAL/MLBT Wright-Patterson Air Force Base, OH 45433	20	Fuel & Lab Div. STRBE-VF
		3	Tech Reports Ofc. STRBE-WPG
		3	Security Ofc (for liaison officers). STRBE-S
		2	Tech Library. STRBE-WC
		1	Program Support. STRBE-HR
		1	Public Affairs Ofc. STRBE-I
		1	Ofc of Chief Council. STRBE-L
			<b>Department of the Navy</b>
1	Commander San Antonio Air Logistics Center ATTN: SAALC/SFQ (Mr. Makris) Kelly Air Force Base, TX 78241	1	Commander Naval Air Propulsion Center ATTN: PE-72 (Mr. D'Orazio) P.O. Box 7176 Trenton, NJ 06828
1	Commander Warner Robins Air Logistic Center ATTN: WR-ALC/MMIRAB-1. (Mr. Graham) Robins Air Force Base, GA 31098	1	Chief of Naval Research ATTN: Code 473 Arlington, VA 22217
	<b>Belvoir R&amp;D Center</b>	1	Commander Naval Sea Systems Command Code 05D4 (Mr. Layne) Washington, DC 20362
1	Commander. STRBE-Z Technical Director. STRBE-ZT Assoc Technical Director. STRBE-ZZ Chief Engineer. STRBE-HE Chief Scientist. STRBE-HS Program Planning. STRBE-HP Program Support. STRBE-HR Systems Analysis. STRBE-HA CIRCULATE	1	Commander David Taylor Naval Ship Research and Development Center Code: 2830 (Mr. Bosmajian) Annapolis, MD 21402
1	Chief, Combined Arms Support Lab. STRBE-N Chief, Engineer Support Lab. STRBE-N Chief, Engineer Service Support Lab. STRBE-E Chief, Logistics Support Lab. STRBE-G Chief, Matl. Fuels & Lubricants Lab. STRBE-V Director, Product A&T Direc- torate. STRBE-T CIRCULATE	2	Department of the Navy HQ, US Marine Corps ATTN: LPP, LMM Washington, DC 20380
		1	Commander Naval Materiel Command ATTN: MAT-08E (Dr. Roberts) CP6, Room 606 Washington, DC 20360
		1	Commander Naval Research Laboratory ATTN: Code 6170 (Mr. Ravner) Washington, DC 20375

<b>No. Copies</b>	<b>Addressee</b>
1	Commander Naval Air Systems Command ATTN: Code 5304-C1 (Mr. Weinberg) Washington, DC 20361
1	Commander Naval Air Development Center ATTN: Code 60612 (Mr. Stallings) Warminster, PA 18974
1	Proj Mgr. M60 Tank Development USMC-LNO, US Army Tank-Automotive Command. (TACOM) Warren, MI 48090

**END**

**FILMED**

7-85

**DTIC**