

MICROCOPY RESOLUTION TEST CHART  
 NATIONAL BUREAU OF STANDARDS-1963-A

2

# HIGH RATE LI/SOCl<sub>2</sub> CELLS II. EFFECT OF CATALYST ON CELL PERFORMANCE

BY W. P. KILROY (NSWC) L. PITTS K. M. ABRAHAM (EIC LABS, INC.)

RESEARCH AND TECHNOLOGY DEPARTMENT

APRIL 1985

Approved for public release; distribution is unlimited.

AD-A157 383

DTIC  
ELECTE  
AUG 5 1985  
S A D

DTIC FILE COPY



## NAVAL SURFACE WEAPONS CENTER

Dahlgren, Virginia 22448 • Silver Spring, Maryland 20910

85 7 30 033

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER NSWC TR 85-104	2. GOVT ACCESSION NO. AD-A157 983	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) HIGH RATE Li/SOCl <sub>2</sub> CELLS II. EFFECT OF CATALYST ON CELL PERFORMANCE		5. TYPE OF REPORT & PERIOD COVERED Nov 1983 - Apr 1985
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) William P. Kilroy (NSWC) L. Pitts and K. M. Abraham (EIC Labs, Inc.)		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS Naval Surface Weapons Center (Code R33) Silver Spring, MD 20903-5000 EIC Labs, Inc. Norwood MA 02062		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS
11. CONTROLLING OFFICE NAME AND ADDRESS		12. REPORT DATE April 1985
		13. NUMBER OF PAGES 61
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report)  UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report)  Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Lithium Battery, Catalyst Tetraazaannulene, Thionyl Chloride		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) → Co-TAA catalyst improved the performance and safety of C-size Li/SOCl <sub>2</sub> cells. The catalyst was most effective at high rate or low temperature operation. The presence of water increased the risk of hazards at high rates of discharge. The generation of gases such as COS, CS <sub>2</sub> , HCl, etc. was dependent on the internal temperature. Originator supplied keywords include		


DD FORM 1473  
1 JAN 73EDITION OF 1 NOV 65 IS OBSOLETE  
S/N 0102-LF-014-6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE (When Data Entered)



S/N 0102- LF- 014- 6601

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE(When Data Entered)

FOREWORD

The Li/SOCl<sub>2</sub> battery system has received considerable interest for a number of high rate, high energy Naval applications. However, high rate applications increase the risk of safety hazards to Naval personnel.

To enhance rate capability, a Co-TAA catalyst has been added to Li/SOCl<sub>2</sub> cells. This report examines the effects of this catalyst on the performance, safety, and chemistry of various specially instrumented Li/SOCl<sub>2</sub> cells discharged and forced overdischarged at -12°C and ambient temperatures.

Funding for this work was provided by the NAVSEA High Energy Batteries for Weapons Block Program.

Approved by:

*J. R. Dixon*  
JACK R. DIXON, Head  
Materials Division

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution _____	
Availability Codes	
Dist	Availability
<i>A-1</i>	



CONTENTS

<u>Chapter</u>		<u>Page</u>
1	INTRODUCTION . . . . .	1
2	EXPERIMENTAL . . . . .	3
3	RESULTS . . . . .	5
4	DISCUSSION . . . . .	43
5	CONCLUSIONS . . . . .	49
	REFERENCES . . . . .	51

## ILLUSTRATIONS

<u>Figure</u>		<u>Page</u>
1	DISCHARGE DATA FOR CELL C-A-D-1 AT 0.2A AND 20°C . . . . .	7
2	DISCHARGE DATA FOR CELL C-A-D-2 AT 2.0A AND 20°C . . . . .	8
3	DISCHARGE DATA FOR CELL C-A-D-7 AT 3.0A AND 20°C . . . . .	9
4	DISCHARGE DATA FOR CELL C-A-D-8 AT 4.0A AND 20°C . . . . .	10
5	IR SPECTRUM OF SALTS FROM CELL C-A-D-2 . . . . .	11
6	DISCHARGE DATA FOR CELL C-A-D-10 AT 0.2A AND -12°C . . . . .	13
7	DISCHARGE DATA FOR CELL C-A-D-12 AT 2.0A AND -12°C . . . . .	14
8	DISCHARGE DATA FOR CELL C-A-W-21 AT 5.0A AND 20°C . . . . .	17
9	IR SPECTRUM OF GASES RELEASED FROM CELL C-A-W-21 . . . . .	18
10	DISCHARGE DATA FOR CELL C-A-W-26 AT 4.0A AND -12°C . . . . .	20
11	DISCHARGE DATA FOR CELL C-C-D-1 AT 0.2A AND 20°C . . . . .	22
12	DISCHARGE DATA FOR CELL C-C-D-2 AT 2.0A AND 20°C . . . . .	23
13	DISCHARGE DATA FOR CELL C-C-D-4 AT 3.0A AND 20°C . . . . .	24
14	DISCHARGE DATA FOR CELL C-C-D-8 AT 4.0A AND 20°C . . . . .	25
15	IR SPECTRUM OF GASES RELEASED DURING THE VENTING OF CELL C-C-D-4 . . . . .	27
16	IR SPECTRUM OF GASES RELEASED FROM CELL C-C-D-8 AFTER VENTING . . . . .	28
17	DISCHARGE DATA FOR CELL C-C-D-11 AT 2.0A AND -12°C . . . . .	30
18	DISCHARGE DATA FOR CELL C-C-D-15 AT 3.0A AND -12°C . . . . .	31
19	IR SPECTRUM OF THE CATHODE OF CELL C-C-D-11 . . . . .	32
20	DISCHARGE DATA FOR CELL C-C-W-18 AT 0.2A AND 20°C . . . . .	34
21	DISCHARGE DATA FOR CELL C-C-W-20 AT 2.0A AND 20°C . . . . .	35
22	DISCHARGE DATA FOR CELL C-C-W-21 AT 3.0A AND 20°C . . . . .	36
23	DISCHARGE DATA FOR CELL C-C-W-24 AT 4.0A AND 20°C . . . . .	37
24	GAS IR SPECTRUM FROM CELL C-C-W-24 . . . . .	38
25	DISCHARGE DATA FOR CELL C-C-W-28 AT 2.0A AND -12°C . . . . .	40
26	DISCHARGE DATA FOR CELL C-C-W-31 AT 3.0A AND -12°C . . . . .	41
27	COMPARISON OF CATALYZED (C-C-W-26) AND UNCATALYZED (C-W-25) CATHODE - LIMITED WET CELLS DISCHARGED AT 0.2A AND -12°C . . .	46

## TABLES

<u>Table</u>		<u>Page</u>
1	PERFORMANCE OF CATALYZED LITHIUM-LIMITED DRY CELLS AT 20°C . . .	6
2	PERFORMANCE OF CATALYZED LITHIUM-LIMITED DRY CELLS AT -12°C . . .	12
3	PERFORMANCE OF CATALYZED LITHIUM-LIMITED WET CELLS AT 20°C . . .	16
4	PERFORMANCE OF CATALYZED LITHIUM-LIMITED WET CELLS AT -12°C . . .	19
5	PERFORMANCE OF CATALYZED CATHODE-LIMITED DRY CELLS AT 20°C . . .	21
6	PERFORMANCE OF CATALYZED CATHODE-LIMITED DRY CELLS AT -12°C . . .	29
7	PERFORMANCE OF CATALYZED CATHODE-LIMITED WET CELLS AT 20°C . . .	33
8	PERFORMANCE OF CATALYZED CATHODE-LIMITED WET CELLS AT -12°C . . .	39
9	THE EFFECT OF WATER ON DISCHARGE CAPACITY OF CATALYZED AND UNCATALYZED Li/SOCl <sub>2</sub> CELLS . . . . .	44
10	EFFECT OF CATALYST ON INCREASING THE AVERAGE CELL CAPACITY . . .	44
11	SUMMARY OF THE EFFECT OF WATER ON HAZARDS IN CATALYZED Li/SOCl <sub>2</sub> CELLS DISCHARGED AT A 4.0A RATE . . . . .	47

## CHAPTER 1

## INTRODUCTION

As part of the ongoing High Energy Batteries for Weapons Programs at NSWC, various cell parameters were investigated to examine their effect on the performance, safety, and chemistry of  $\text{Li}/\text{SOCl}_2^{\text{M}}$  cells. This report summarizes the influence of cobalt dibenzo-tetraazaannulene (Co-TAA) catalysis on the discharge and overdischarge chemistry and performance of spirally wound commercial C-size cells.

*Hand on DD473*  
This investigation was undertaken because a recent paper claimed that TAA complexes dramatically enhanced cell performance and altered the electrochemical mechanism so that no  $\text{SO}_2$  gas pressure was generated.<sup>1</sup> An  $\text{SO}_2$  free  $\text{SOCl}_2$  system would offer a significant improvement in safety.

Since this study began, a second report by these authors proposed a different  $\text{SO}_2$  free cell discharge mechanism than the one they first proposed.<sup>2</sup> Although this investigation did not focus on elucidating the reaction mechanism, our data indicate the catalyst does not alter the  $\text{Li}/\text{SOCl}_2$  cell chemistry to produce an  $\text{SO}_2$  free cell.

## CHAPTER 2

## EXPERIMENTAL

The C-size cells were prepared by Hellekens Battery Engineering, Hyde Park, Ma., according to standard manufacturing procedures. The cell specifications and testing procedures have been described in the first report.<sup>3</sup> Cells are classified as Dry and Wet cells. The latter contained 500 ppm added H<sub>2</sub>O.

Cathodes were prepared from Shawinigan acetylene black. In addition to the regular cathodes, cathodes containing 5 weight percent of a tetraazaannulene complex of cobalt (Co-TAA) as a catalyst additive were used. The catalyzed cathodes were prepared by mixing the carbon with the catalyst and the mixture was heat treated at 500°C under inert gas. After cooling, this mixture was made into a paste with water, isopropanol and Teflon binder, followed by drying below 100°C. The mixture was cured by heating to ~275°C under inert gas. At no time was the catalyst heated above 100°C in air. The preparation and application techniques have previously been described in reports<sup>2,4</sup> and a recent patent.<sup>5</sup>

## CHAPTER 3

## RESULTS

The data obtained with the catalyzed Li/SOCl<sub>2</sub> cells are described below. This data can be compared with the uncatalyzed cell data described in the first report.<sup>3</sup>

## CATALYZED LITHIUM-LIMITED CELLS

Dry Cells at 20°C

Catalyzed Li-limited dry cells, labelled C-A-D were overdischarged at 0.2, 2.0, 3.0, and 4.0A at 20°C. None of the cells vented. Cell data are summarized in Table 1. Representative performance data are illustrated in Figures 1 through 4.

Cells C-A-D-1 and C-A-D-2 were manually vented and each cell was analyzed. The IR spectra of the gases released showed only SO<sub>2</sub> and SOCl<sub>2</sub>. GC analyses showed that CO<sub>2</sub> and a trace of COS was present in each cell discharged above the 0.2A rate.

The IR spectra of the salts collected from these cells were identical to the spectrum of salts previously collected from uncatalyzed Li-limited cells. The IR spectrum of salts extracted from cell C-A-D-2 is shown in Figure 5. IR analyses of the cathodes showed only weak absorptions from LiAlCl<sub>4</sub>. Chemical spot tests for S<sub>2</sub>O<sub>4</sub><sup>2-</sup>, S<sub>2</sub>O<sub>3</sub><sup>2-</sup>, S<sup>2-</sup>, SO<sub>3</sub><sup>2-</sup>, and SO<sub>4</sub><sup>2-</sup> were negative.

Dry Cells at -12°C

Table 2 summarizes the data from catalyzed Li-limited cells discharged at -12°C. At this low temperature the capacity is the same as found at room temperature but the mid-discharge voltage is lower. Discharge data are illustrated in Figures 6 and 7. The anode potential of cell C-A-D-12 displays a rise-fall behavior characteristic of the anodic polarization phenomenon previously observed in several cathode limited cells, with the distinction that the lithium anode potential rises presumably from lithium depletion.

TABLE 1. PERFORMANCE OF CATALYZED LITHIUM-LIMITED  
DRY CELLS AT 20°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum Pressure (psig)	Mid-discharge Voltage (V)
C-A-D-1	0.2	0.8	3.24	31	21	3.52
C-A-D-2	2.0	8.0	2.96	67	55	3.40
C-A-D-3	2.0	8.0	2.92	73	52	3.40
C-A-D-4	2.0	8.0	2.92	67	60	3.40
C-A-D-5	2.0	8.0	2.92	60	70	3.40
C-A-D-6	2.0	8.0	3.20	60	50	3.40
C-A-D-7	3.0	11.9	2.92	74	37	3.19
C-A-D-8	4.0	15.8	3.06	117	130 <sup>1</sup>	3.11
C-A-D-9	4.0	15.8	3.24	-	100	3.12

<sup>1</sup>Cell leaked through transducer connection to cell.




FIGURE 1. DISCHARGE DATA FOR CELL C-A-D-1 AT 0.2A AND 20°C




FIGURE 2. DISCHARGE DATA FOR CELL C-A-D-2 AT 2.0A AND 20°C




FIGURE 3. DISCHARGE DATA FOR CELL C-A-D-7 AT 3.0A AND 20°C




FIGURE 4. DISCHARGE DATA FOR CELL C-A-D-8 AT 4.0A AND 20°C




FIGURE 5. IR SPECTRUM OF SALTS FROM CELL C-A-D-2

TABLE 2. PERFORMANCE OF CATALYZED LITHIUM-LIMITED DRY CELLS AT -12°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum** Pressure (psig)	Mid-discharge Voltage (V)
C-A-D-10	0.2	0.8	3.12	-4	0	3.35
C-A-D-11	2.0	8.0	2.46	43	0	3.05
C-A-D-12	2.0	8.0	3.07	43	2.5	3.05
C-A-D-13*	2.0	8.0	3.18	Off-scale	40	3.05

\* Cell was initially charged for 2.58 A-hr.

\*\*The pressure transducer response at -12°C was poor and its measured value may be low.




FIGURE 6. DISCHARGE DATA FOR CELL C-A-D-10 AT 0.2A AND -12°C




FIGURE 7. DISCHARGE DATA FOR CELL C-A-D-12 AT 2.0A AND -12°C

Chemical analyses of the gases, extracted solids and carbon cathode were similar to the cells at 20°C with one exception - no COS was detected.

#### Wet Cells at 20°C

The performance of catalyzed Li-limited wet cells at 20°C are summarized in Table 3. Only the cells overdischarged at 4.0A or higher currents vented. Cell C-A-W-19 vented through the bottom of the cell. The pressure was not recorded on the pressure transducer. The discharge curve for cell C-A-W-21 discharged at 5.0A is shown in Figure 8.

Chemical analyses of overdischarged cells yielded the same results as found in the dry cells at the 0.2 and 2.0A rates. No COS was found at the 0.2A rate. A small amount appears at the 4.0A rate. At the 4.0A rate, the COS is observed as a weak doublet at 2020  $\text{cm}^{-1}$ . At the 5.0A rate, the COS band is appreciable (Figure 9).

#### Wet Cells at -12°C

Cell discharge performance data at -12°C are summarized in Table 4. The discharge data at the 4.0A rate is illustrated in Figure 10. This cell did not vent. IR analysis of the gases released after manual venting showed only  $\text{SO}_2$  and  $\text{SOCl}_2$ . No HCl or COS absorptions were present.

### CATALYZED CATHODE-LIMITED CELLS

#### Dry Cells at 20°C

The performance data for catalyzed cathode-limited dry cells, labelled C-C-D, are shown in Table 5. Performance behavior for representative cells are illustrated in Figures 11 through 14.

Cell C-C-D-2 was manually vented after forced overdischarge and chemically analyzed. IR gas analysis again showed  $\text{SO}_2$  and  $\text{SOCl}_2$ . GC analysis revealed  $\text{CO}_2$  and COS. COS was present in higher quantity than in similarly discharged Li-limited cells. IR analysis of the cathode revealed a new peak at 1015  $\text{cm}^{-1}$  which was not previously observed.

The high rate discharge data obtained at the 3.0A rate (Table 5) indicated that the venting threshold was not reproducible. The pressure in the unvented cells exceeded the pressure in the cell that vented. The pressure curve for cell C-C-D-4, shown in Figure 13, indicates the venting occurred when the internal temperature peaked at 146°C. The temperature drops and then increases rapidly. It may be that another reaction occurs after venting. Cell C-C-D-8 which vented on overdischarge at a 4.0A rate (Figure 14) exhibited no such behavior. After the cell reached 345 psi, the pressure decreases slowly while the temperature curve shows no increase after venting.

TABLE 3. PERFORMANCE OF CATALYZED LITHIUM-LIMITED WET CELLS AT 20°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum Pressure (psig)	Mid-discharge Voltage (V)
C-A-W-14	0.2	0.8	3.32	32	50	3.52
C-A-W-15	0.2	8.0	3.24	63	58	3.40
C-A-W-16	2.0	8.0	3.06	63	55	3.31
C-A-W-17	2.0	8.0	3.18	62	47	3.30
C-A-W-18	2.0	8.0	3.10	70	46	3.30
C-A-W-19*	4.0	15.8	3.02	145 <sup>1</sup>	-	3.15
C-A-W-20*	4.0	15.8	2.88	99 <sup>2</sup>	218	3.10
C-A-W-21*	5.0	20.8	2.90	Off-scale <sup>3</sup>	188	3.08

\*Cell vented

<sup>1</sup>Temperature reached after 7 hours forced overdischarge.

<sup>2</sup>External temperature (cell leaked).

<sup>3</sup>Temperature went off-scale after cell vented.




FIGURE 8. DISCHARGE DATA FOR CELL C-A-W-21 AT 5.0A AND 20°C




FIGURE 9. IR SPECTRUM OF GASES RELEASED FROM CELL C-A-W-21

TABLE 4. PERFORMANCE OF CATALYZED LITHIUM-LIMITED  
WET CELLS AT -12°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum* Pressure (psig)	Mid-discharge Voltage (V)
C-A-W-22	0.2	0.8	3.12	10	-	3.37
C-A-W-23	2.0	8.0	3.35	52	8	2.98
C-A-W-24	2.0	8.0	2.96	41	12	2.98
C-A-W-25	2.0	8.0	3.19	42	10	3.01
C-A-W-26	4.0	15.8	3.12	54	35	2.83

\*The pressure transducer response at -12°C was poor and the pressure value may be low.




FIGURE 10. DISCHARGE DATA FOR CELL C-A-W-26 AT 4.0A AND -12°C

TABLE 5. PERFORMANCE OF CATALYZED CATHODE-LIMITED DRY CELLS AT 20°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum Pressure (psig)	Mid-discharge Voltage (V)
C-C-D-1	0.2	1.0	5.28	37	20	3.52
C-C-D-2	2.0	10.0	4.39	107	68	3.30
C-C-D-3	2.0	10.0	4.24	96	80	3.28
C-C-D-4*	3.0	15.0	3.87	>190	205	3.20
C-C-D-5	3.0	15.0	4.00	116	255	3.20
C-C-D-6	3.0	15.0	3.94	143	247	3.18
C-C-D-7	3.0	15.0	3.98	154	240	3.20
C-C-D-8*	4.0	20.0	3.53	117**	345	3.15
C-C-D-9	4.0	20.0	3.38	148	270	3.10

\* Cells vented.

\*\*Internal thermocouple not positioned in middle of cell.




FIGURE 11. DISCHARGE DATA FOR CELL C-C-D-1 AT 0.2A AND 20°C




FIGURE 12. DISCHARGE DATA FOR CELL C-C-D-2 AT 2.0A AND 20°C




FIGURE 13. DISCHARGE DATA FOR CELL C-C-D-4 AT 3.0A AND 20°C




FIGURE 14. DISCHARGE DATA FOR CELL C-C-D-8 AT 4.0A AND 20°C

Gas analysis of cells C-C-D-4 (tested at 3.0A) and C-C-D-8 (tested at 4.0A) also show differences. A large amount of HCl was found in cell C-C-D-4. Cell C-C-D-8 which exhibited no second reaction after venting contained no HCl but a substantial amount of COS was present with absorptions near  $2065\text{ cm}^{-1}$ . The results can be compared in Figures 15 and 16.

Gas analysis of cell C-C-D-5 which was manually vented showed no HCl to be present.

#### Dry Cells at $-12^{\circ}\text{C}$

The results of cells discharged at  $-12^{\circ}\text{C}$  are summarized in Table 6. Discharge data obtained the 2.0 and 3.0A rates are shown in Figures 17 and 18, respectively.

Chemical analyses were performed on cells discharged at the 0.2, 2.0, and 3.0A rates. The analyses gave the same results as found in the cells discharged at  $20^{\circ}\text{C}$ . The unvented cells showed  $\text{SO}_2$  and  $\text{SOCl}_2$  in the gas phase. The IR band at  $1015\text{ cm}^{-1}$  was again present and is shown in Figure 19.

#### Wet Cells at $20^{\circ}\text{C}$

The discharge data for the wet cells, labelled C-C-W, are summarized in Table 7. Typical performance data obtained at each rate is illustrated in Figures 20 through 23.

IR analyses of the unvented cells discharged at 0.2 and 2.0A rates showed only  $\text{SO}_2$  and  $\text{SOCl}_2$  gases present. Cell C-C-W-21, which displayed two temperature peaks after cell venting, also exhibited HCl in the IR spectrum. These results are similar to the data observed at  $20^{\circ}\text{C}$  for dry cells.

Cell C-C-W-24 displayed the most violent behavior so far (see Figure 23). The discharge curves are very similar to cell C-C-D-4. The internal temperature goes off-scale, but the external temperature shows a drop in temperature after venting and then it too goes off scale. The gas phase IR spectrum for cell C-C-W-24 is shown in Figure 24. In addition to the  $\text{SO}_2$  and  $\text{SOCl}_2$ , there are very strong absorptions for HCl, COS,  $\text{CO}_2$  and a doublet at 1530 and  $1545\text{ cm}^{-1}$  belonging to  $\text{CS}_2$ .

#### Wet Cells at $-12^{\circ}\text{C}$

The data for the catalyzed cathode limited wet cells at  $-12^{\circ}\text{C}$ , labelled C-C-W, are shown in Table 8. Discharge data at the 2.0 and 3.0A rates are illustrated by Figures 25 and 26, respectively.

IR gas analysis of the unvented cells showed only  $\text{SO}_2$  and  $\text{SOCl}_2$  present. The wet cells discharged at 4.0A vented. Vapor phase IR analysis showed the same products as those found in vented cells discussed above.




FIGURE 15. IR SPECTRUM OF GASES RELEASED DURING THE VENTING OF CELL C-C-D-4




FIGURE 16. IR SPECTRUM OF GASES RELEASED FROM CELL C-C-D-8 AFTER VENTING

TABLE 6. PERFORMANCE OF CATALYZED CATHODE-LIMITED  
DRY CELLS AT -12°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum Pressure (psig)	Mid-discharge Voltage (V)
C-C-D-10	0.2	1.0	4.72	4	0	3.18
C-C-D-11	2.0	10.0	3.61	74	32	2.85
C-C-D-12	2.0	10.0	3.42	64	20	2.70
C-C-D-13	3.0	15.0	3.46	-	102	2.85
C-C-D-14	3.0	15.0	3.44	96*	75	2.92
C-C-D-15	3.0	15.0	3.28	131	130	2.90
C-C-D-16	4.0	20.0	2.83	144	-	2.52
C-C-D-17	4.0	20.0	2.64	97*	145	2.40

\*External cell temperature.




FIGURE 17. DISCHARGE DATA FOR CELL C-C-D-11 AT 2.0A AND -12°C




FIGURE 18. DISCHARGE DATA FOR CELL C-C-D-15 AT 3.0A AND -12°C




FIGURE 19. IR SPECTRUM OF THE CATHODE OF CELL C-C-D-11

TABLE 7. PERFORMANCE OF CATALYZED CATHODE-LIMITED  
WET CELLS AT 20°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum Pressure (psig)	Mid-discharge Voltage (V)
C-C-W-18	0.2	1.0	5.18	35	15	3.50
C-C-W-19	2.0	10.0	4.46	76	78	3.30
C-C-W-20	2.0	10.0	4.57	92	74	3.30
C-C-W-21*	3.0	15.0	3.90	143	210	3.20
C-C-W-22	3.0	15.0	3.96	147	216	3.20
C-C-W-23	3.0	15.0	4.05	149	228	3.20
C-C-W-24*	4.0	20.0	3.53	185	315	3.15
C-C-W-25*	4.0	20.0	3.67	185	293	3.10

\*Cells vented.




FIGURE 20. DISCHARGE DATA FOR CELL C-C-W-18 AT 0.2A AND 20°C




FIGURE 21. DISCHARGE DATA FOR CELL C-C-W-20 AT 2.0A AND 20°C




FIGURE 22. DISCHARGE DATA FOR CELL C-C-W-21 AT 3.0A AND 20°C




FIGURE 23. DISCHARGE DATA FOR CELL C-C-W-24 AT 4.0A AND 20°C




FIGURE 24. GAS IR SPECTRUM FROM CELL C-C-W-24

TABLE 8. PERFORMANCE OF CATALYZED CATHODE-LIMITED  
WET CELLS AT -12°C

Cell Number	Discharge Current (A)	Current Density (mA/cm <sup>2</sup> )	Capacity to 0.0V (A-hr)	Maximum Temp. (°C)	Maximum Pressure (psig)	Mid-discharge Voltage (V)
C-C-W-26	0.2	1.0	4.68	0	0	3.27
C-C-W-27	2.0	10.0	3.78	70	-	2.95
C-C-W-28	2.0	10.0	3.96	66	15	2.95
C-C-W-29	3.0	15.0	3.62	84*	110	2.90
C-C-W-30	3.0	15.0	2.86	81*	96	2.72
C-C-W-31	3.0	15.0	2.41	122	110	2.87
C-C-W-32**	4.0	20.0	2.98	132	-	2.89
C-C-W-33**	4.0	20.0	2.48	>185	115	2.70

\* External cell temperature.

\*\*Cell vented.




FIGURE 25. DISCHARGE DATA FOR CELL C-C-W-28 AT 2.0A AND -12°C




FIGURE 26. DISCHARGE DATA FOR CELL C-C-W-31 AT 3.0A AND -12°C

## CHAPTER 4

## DISCUSSION

Table 9 summarizes the effect of water on the average capacities of uncatalyzed and catalyzed cells discharged at a 2.0A rate. Although the averages were limited to a small number of cells, 56 in all, a clear pattern was established. The capacity of uncatalyzed cells, especially Li-limited, decreased when water was present. However, water caused little change in the capacity of the catalyzed cells. The overall effect was less apparent in cathode limited cells, where the capacity decreased ~4 percent in uncatalyzed cells and increased ~7 percent in catalyzed cells, a net change of approximately 11 percent. The most pronounced results occurred in Li-limited cells. One would not expect a cathode catalyst to have any noticeable effect on Li-limited cells where the cell capacity was limited by the amount of lithium. Indeed this was confirmed in the cells without water--the addition of a catalyst did not alter the capacity of Li-limited cells at either 20°C or -12°C. In Li-limited cells containing water, the catalyst had a dramatic effect on cell capacity. Consider the Li-limited cells at -12°C. With or without a catalyst the cell capacity in the dry cell is 2.90 Ahr. Water decreases this capacity ~18 percent in the uncatalyzed cell. A 9 percent increase was observed in the catalyzed cells--a net change of ~27 percent. The conclusion is that although a catalyst has little effect on cell capacity of "dry" Li-limited cells, the cell performance of Li-limited cells that contain moisture can be greatly enhanced by a catalyst. The data indicate this catalyst may serve a dual purpose in the SOCl<sub>2</sub> system by gettering water from the system, thus reducing parasitic corrosion processes at the lithium anode and enhancing the carbon cathodes capacity.

The actual percentage change in the average cell capacity due to addition of the (Co-TAA) catalyst is summarized for both wet and dry cells in Table 10. The most noticeable improvement occurs in: (a) wet Li-limited cells, (b) in carbon-limited cells discharged at high rates at 20°C--a 61.2 percent capacity increase occurs at 3.0A compared to a 20.3 percent increase at the lower 2.0A rate, and (c) dramatic increase in capacity of carbon-limited cells discharged at -12°C even at low rates.

The data indicate the catalyst is most effective on enhancing cell performance at high rates. Two examples can be cited. (a) Catalyzed Li-limited cells were discharged at 20°C at 2.0A and 4.0A rates. The cell capacities (averaged for both wet and dry cells) were identical ( 3.05 Ahr) for both discharge rates. (b) Table 9 shows the average capacity of uncatalyzed cathode limited cells at -12°C is 2.1 Ahr at the 2.0A rate. The same cells containing the catalyst discharged at -12°C but at double the rate, 4.0A, had an even larger average capacity of 2.73 Ahr.

TABLE 9. THE EFFECT OF WATER ON DISCHARGE CAPACITY OF CATALYZED AND UNCATALYZED Li/SOCl<sub>2</sub> CELLS

TEMP. °C	CELL BALANCE*	AVERAGE CAPACITY (Ah) AT 2.0A RATE TO 0.0V			
		UNCATALYZED		CATALYZED	
		DRY	WET	DRY	WET
20	A	2.95	2.63	2.98	3.15
-12	A	2.90	2.37	2.90	3.17
20	C	3.59	3.42	4.32	4.52
-12	C	2.16	2.10	3.52	3.87

\*A - lithium-limited

C - carbon-limited

TABLE 10. EFFECT OF CATALYST ON INCREASING THE AVERAGE CELL CAPACITY

TEMP. °C	DISCHARGE RATE, (A)	CELL* BALANCE	INCREASING IN AVERAGE CELL CAPACITY, %	
			DRY	WET
20	2.0	A	1.0	19.8
20	2.0	C	20.3	32.2
20	3.0	C	61.2	--
-12	2.0	A	0	33.8
-12	2.0	C	63.0	84.3

\*A - lithium-limited


C - carbon-limited

The catalyst also improved the capacity of carbon-limited cells even at the low rates of 0.2A. Similar cells with and without catalyst discharged at 0.2A at  $-12^{\circ}\text{C}$  are illustrated in Figure 27.


Table 11 summarizes the effect of water on cell hazards in catalyzed  $\text{SOCl}_2$  cells discharged at the 4.0A rate. The data show that wet electrolyte cells generated more pressure and were more hazardous than dry cells. Of the 14 cells tested, 5 of the 6 dry cells did not vent and 7 of the 8 wet cells did vent. The wet cell that did not vent was the only Li-limited cell discharged at  $-12^{\circ}\text{C}$ . The wet cathode limited cells discharge at 4.0A had higher internal temperatures. Although catalyzed Li-limited cells performed exceptionally, few of these cells were tested at high rates. The effect of catalyst on Li-limited cells was limited since uncatalyzed Li-limited cells became cathode limited when discharged at 3.0A or higher. Wet catalyzed cathode limited cells discharged at  $-12^{\circ}\text{C}$  at the 3.0A rate exhibited large fluctuations in capacity. This may have arisen from an anodic polarization as cited in the first report. Since this behavior was not observed with the dry cells under similar conditions, water may be a factor in the anodic polarization process.

Generally, wet cells were also observed to develop greater pressures than dry cells during storage.

The data show that cathode limited cells always generated greater internal temperatures than anode limited cells. For example, the average maximum temperature of cathode limited cells discharged at  $20^{\circ}\text{C}$  at 2.0A was  $\sim 101^{\circ}\text{C}$  compared to  $66^{\circ}\text{C}$  recorded in the anode limited cells. The amount of carbeneous gases, such as  $\text{CO}_2$  etc., was generally found in the greatest concentrations in (a) vented cells, (b) cathode limited cells, and (c) cells discharged at high rates. More specifically, cells which exhibited the largest temperature rises produced the most carbeneous gases. Indeed the amount of COS generated was strongly dependent on cell temperature. The anode limited cell, C-A-W-21, discharged at 5.0A recorded high temperatures and significant amounts of COS gas. Carbon disulfide together with large amounts of  $\text{CO}_2$ , HCl, COS (Figure 24) was observed in cell C-C-W-24 which vented violently. However, as Table 11 shows, the cells that vented at high discharge rates generally contained water. These cells also displayed the greatest amounts of HCl gas. As illustrated by the IR spectra in Figure 16, no HCl was observed in a dry cathode limited cell discharged at 3.0A. Still there was a substantial amount of COS.



a.



b.

FIGURE 27a. & b. COMPARISON OF CATALYZED (C-C-W-26) AND UNCATALYZED (C-W-25) CATHODE - LIMITED WET CELLS DISCHARGED AT 0.2A AND -12°C

TABLE 11. SUMMARY OF THE EFFECT OF WATER ON HAZARDS IN CATALYZED Li/SOCl<sub>2</sub> CELLS DISCHARGED AT A 4.0A RATE

<u>CATHODE LIMITED CELLS</u>			
<u>CELL NO.</u>	<u>TEMP. °C</u>	<u>CONDITION</u>	<u>OBSERVATION</u>
C-C-W-24	20	Wet	Vented
C-C-W-25	20	Wet	Vented
C-C-W-32	-12	Wet	Vented
C-C-W-33	-12	Wet	Vented
C-C-D-8	20	Dry	Vented
C-C-D-9	20	Dry	No Venting
C-C-D-16	-12	Dry	No Venting
C-C-D-17	-12	Dry	No Venting
<u>LITHIUM-LIMITED CELLS</u>			
<u>CELL NO.</u>	<u>TEMP. °C</u>	<u>CONDITION</u>	<u>OBSERVATION</u>
C-A-W-21*	20	Wet	Vented
C-A-W-19	20	Wet	Vented
C-A-W-20	20	Wet	Vented
C-A-D-8	20	Dry	No Venting
C-A-D-9	20	Dry	No Venting
C-A-W-26	-12	Wet	No Venting

\*Discharged at 5.0A rate

## CHAPTER 5


## CONCLUSIONS

Improved performance and safety was achieved in C-size Li/SOCl<sub>2</sub> cells using Co-TAA catalyst. The catalyst was most effective at high rates or low temperature operation. Cells discharged at -12°C had larger capacities at the 4.0A rate than uncatalyzed cells at the 2.0A rate. In general, the catalyst increased the cell capacity substantially while enhancing the operating voltage approximately 10 percent. The greatest improvement occurred in cathode-limited cells discharged at high rates at both 20° and -12°C and in wet Li-limited cells. The safety of cell operation was also enhanced by use of the catalyst. For instance, uncatalyzed Li-limited cells became cathode limited at the 3.0A rate. Cathode limited cells are considered more hazardous than Li-limited cells. The use of Co-TAA enabled the lithium-limited cells to remain lithium-limited. The cell discharged at the 5.0A rate remained Li-limited. In addition, there was generally less internal heating in catalyzed cells, especially in the wet cells.

The amounts of COS detected in the gas phase appeared to be dependent on the internal temperature. The greatest concentration of COS was found in cells with highly elevated temperatures. HCl gas was most often found in wet cells with high internal temperatures.

The catalyst served to negate the capacity lowering effect of water. But, at high rates of discharge (4.0A) water increased the likelihood of cell venting.

Previous studies proposed an SO<sub>2</sub> free SOCl<sub>2</sub> discharge mechanism.<sup>1,2</sup> IR analyses of the gas phase of several cells revealed that SO<sub>2</sub> is a major product in catalyzed cells.



REFERENCES

1. Walsh, F., Morris, R. S., and Yaniv, M., "An Improved Li/SOCl<sub>2</sub> Battery," Fall Meeting of the Electrochemical Society, Abstract 33, Washington, DC, Oct 1983.
2. Walsh, F., and Yaniv., M., A Safe TAA-Catalyzed Lithium - Thionyl Chloride Cell, DELET-TR-83-0386-F, May 1984.
3. Kilroy, W. P., Pitts, L., and Abraham, K. M., High Rate Li-SOCl<sub>2</sub> Cells I. Effect of Design Variables, NSWC TR 85-98, Apr 1985.
4. Walsh, F., Morris, R. S., Ayers, K., and Walsh, M., "A Novel Mixed Catalyst for Improved Oxygen Electrode Performance," Fall Meeting of the Electrochemical Society, Abstract 398, Washington, DC, Oct 1983.
5. Walsh, F., and Morris, R. S., "Lithium Oxyhalide Battery with Cathode Catalyst," U.S. Patent No. 4,469,763, 4 Sep 1984.

## DISTRIBUTION

	<u>Copies</u>		<u>Copies</u>
Defense Technical Information Center Cameron Station Alexandria, VA 22314	12	Naval Electronic Systems Command Attn: A. H. Sobel (Code PME 124-31) E. LaNier (PDE 107-5) Washington, DC 20360	1    1
Defense Nuclear Agency Attn: Library Washington, DC 20301	2	Naval Sea Systems Command Attn: F. Romano (Code 63R3) E. Anderson (Code 56Z33) E. Daugherty (Code 06H3) J. Pastine (Code 06R) H. Holter (SEA-06H3) Washington, DC 20362	     1 1 1 1 1
Institute for Defense Analyses R&E Support Division 400 Army-Navy Drive Arlington, VA 22202	1	Strategic Systems Project Office Attn: K. N. Boley (Code NSP 2721) M. Meserole (Code NSP 2722)	   1 1
Naval Material Command Attn: Code 08T223 Washington, DC 20360	1	Department of the Navy Washington, DC 20360	   1
Office of Naval Research Attn: G. Neece (Code ONR 413) J. Smith (Code ONR 413) D. Siegel (Code ONR 251) 800 N. Quincy Street Arlington, VA 22217	1 1 1	Naval Air Development Center Attn: J. Segrest (Code 6012) R. Schwartz (Code 30412) L. B. Hanson (Code 3042) Warminster, PA 18974	    1 1 1
Naval Research Laboratory Attn: A. Simon (Code NRL 6130) R. Nowak (Code 6130) 4555 Overlook Avenue, S.W. Chemistry Division Washington, DC 20375	1 1	Naval Intelligence Support Center Attn: Dr. H. Ruskie (Code 362) Washington, DC 20390	   1
Naval Postgraduate School Attn: Dr. Oscar Biblarz Monterey, CA 93940	1	Naval Ocean Systems Center Attn: J. F. McCartney (Code 7121) Dr. S. Szpak (Code 6343) W. J. Sturgeon (Code 6343) L. Johnson (Code 6343) San Diego, CA 92152	     1 1 1 1
Naval Air Systems Command Attn: Dr. H. Rosenwasser (Code NAVAIR 301C) E. Nebus (Code NAVAIR 5332) P.L. Susha (PMA 264) Washington, DC 20361	1  1 1	U. S. Development and Readiness Command Attn: J. W. Crellin (Code DRCDE-L) 5001 Eisenhower Avenue Alexandria, VA 22333	    1

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Army Material and Mechanical Research Center Attn: J. J. DeMarco Watertown, MA 01272	1	Naval Electronic Systems Command Attn: T. Sliwa (Code NAVELEX-01K) Washington, DC 20360	1
USA Mobility Equipment R and D Command Attn: J. Sullivan (Code DRXFB) Code DRME-EC Electrochemical Division Fort Belvoir, VA 22060	1	Naval Weapons Center Attn: Dr. E. Royce (Code 38) Dr. A. Fletcher (Code 3852) China Lake, CA 93555	1 1
Edgewood Arsenal Attn: Library Aberdeen Proving Ground Aberdeen, MD 21010	1	Naval Weapons Support Center Attn: M. Robertson (Code 305) D. Mains S. Shuler (Code 3054) Electrochemical Power Sources Division Crane, IN 47522	1 1 1
Picatinny Arsenal Attn: Dr. B. Werbel (Code SAROA-FR-E-L-C) A. E. Magistro (Code SARPA-ND-D-B)	1 1	Naval Coastal Systems Center Attn: Library Panama City, FL 32407	1
U. S. Army Dover, NJ 07801		Naval Underwater Systems Center Attn: J. Moden (Code SB332) Newport, RI 02840	1
Harry Diamond Laboratories Attn: J. T. Nelson (Code DELHD-DE-OP) Department of Army Material Chief, Power Supply Branch 2800 Powder Mill Road Adelphi, MD 20783	1	David W. Taylor Naval Ship R & D Center Annapolis Laboratory Annapolis, MD 21402	1
Headquarters, Department of Transportation Attn: R. Potter (Code GEOE-3/61) U. S. Coast Guard, Ocean Engineering Division Washington, DC 20590	1	Air Force Wright Aeronautical Labs Aero Propulsion Laboratory, POOC Attn: W. S. Bishop (Code AFAPL/POE-1) R. Marsh (Code AFWAL-POOC-1) Wright-Patterson AFB, OH 45433	1 1
NASA Headquarters Attn: Dr. J. H. Ambrus Washington, DC 20546	1	Air Force Rocket Propulsion Laboratory Attn: LT. D. Ferguson (Code MKPA) Edwards Air Force Base, CA 93523	1
NASA Lewis Research Center Attn: J. S. Fordyce (Code MS 309-1) M. Reid 2100 Brookpark Road Cleveland, OH 44135	1 1	Headquarters, Air Force Special Communications Center Attn: Library USAFSS San Antonio, TX 78243	1

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Office of Chief of Research and Development Department of the Army Attn: Dr. S. J. Magram Energy Conversion Branch Room 410, Highland Building Washington, DC 20315	1	Frank J. Seiler Research Laboratory, AFSC USAF Academy, CO 80840	1
U.S. Army Research Office Attn: B. F. Spielvogel P.O. Box 12211 Research Triangle Park, NC 27709	1	Department National Defense Attn: Library Defense Research Establishment Ottawa Ottawa, Ontario K1A 0Z4 Canada	1
NASA Scientific and Technical Information Facility Attn: Library P.O. Box 33 College Park, MD 20740	1	NASA Johnson Space Center Attn: Bob Bragg/EPS Houston, TX 77058	1
National Bureau of Standards Metallurgy Division Inorganic Materials Division Washington, DC 20234	1	Department of National Defense Defense Research Establishment Ottawa Attn: W. Adams G. Donaldson Ottawa, Ontario K1A 0Z4 Canada	1 1
U. S. Army Electronics Command Attn: A. J. Legath (Code DRSEL-TL-P) E. Brooks (Code DRSEL-TL-PD) G. DiMasi Dr. W. K. Behl Dr. Sol Gilman (Code DELET-PR) C. Berger M. Salomon E. Reiss Fort Monmouth, NJ 07703	1 1 1 1 1 1 1 1 1	Library of Congress Attn: Gift and Exchange Division Washington, DC 20540	4
Scientific Advisor Attn: Code AX Commandant of the Marine Corps Washington, DC 20380	1	Office of Naval Technology Attn: A. J. Faulstich (MAT072) G. Spaulding (MAT072) 800 N. Quincy Street Arlington, VA 22217	1 1
Air Force of Scientific Research Attn: Directorate of Chemical Science 1400 Wilson Boulevard Arlington, VA 22209	1	Central Intelligence Agency Attn: OTS (C. Sculla) (T. Mahy) Washington, DC 20505	1 1
		ARDC Attn: D. Yedwab LOWSL-LCN Bldg. 61 South Dover, NJ 07801	1
		HQ, U. S. Marine Corps Attn: Lt. Col. W. Lowe (LMA-3) Washington, DC 20380	1

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Missile Systems Safety Attn: Kenn Hill (ESMC/SEM) Patrick AFB, FL 32925	1	U. S. Naval Academy Attn: Dr. G. T. Cheek Chemistry Department Annapolis, MD 21402	1
California Institute of Technology Attn: Library B. Carter R. Somoano H. Frank S. Yen G. Halpert	1 1 1 1 1 1	University of Wisconsin-Milwaukee Attn: Dr. D. Bennett Chemistry Department 3210 N. Cramer St. Milwaukee, Wisconsin 53201	1
Jet Propulsion Laboratory 4800 Oak Grove Drive Pasadena, CA 91109		State University of New York Department of Chemistry Attn: Dr. R. A. Osteryoung Buffalo, NY 14214	1
Johns Hopkins Applied Physics Laboratory Attn: Library M. Uy Howard County Johns Hopkins Road Laurel, MD 20810	1 1	Brookhaven National Laboratory Attn: J. Sutherland Building 815 Upton, NY 11973	1
University of Tennessee Attn: G. Mamantov Department of Chemistry Knoxville, TN 37916	1	Argonne National Laboratory Attn: Dr. E. C. Gay 9700 South Cass Avenue Argonne, IL 60439	1
Applied Research Laboratory Attn: Library Penn State University University Park, PA 16802	1	Lawrence Berkeley Laboratory Attn: F. McLamore University of California Berkeley, CA 94720	1
University of Illinois at Chicago Department of Chemistry Attn: Dr. R. Burns Chicago, IL 60680	1	Oak Ridge National Laboratory Attn: K. Braunstein Oak Ridge, TN 37830	1
Tel-Aviv University Attn: E. Peled Department of Chemistry Tel Aviv, Israel 69978	1	Sandia Laboratories Attn: Sam Levy (Mail Services Section 3154-3) J. T. Cutchen P.O. Box 5800 Albuquerque, NM 87715	1 1
University of California Attn: Dr. R. A. Huggins Dept. Material Science & Engr. Stanford, CA 94305	1	Union Carbide Corporation Battery Products Division Attn: G. E. Blomgren P.O. Box 45035 Westlake, OH 44145	1

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Wilson Greatbatch LTD. Attn: Library R. M. Carey C. Holmes P. Keister 1000 Wehrle Drive Clarence, NY 14030	1 1 1 1	Rockwell International Attn: Dr. Samuel J. Yosim Atomics International Division 8900 DeSoto Avenue Canoga Park, CA 91304	1
Yardney Electric Corporation Attn: Library 82 Mechanic Street Pawcatuck, CT 02891	1	EDO Corporation Attn: E. P. DiGiannantonio Government Products Division 2001 Jefferson Davis Highway Arlington, VA 22202	1
Honeywell Corporate Technology Center Attn: H. V. Venkatesetty 10701 Lyndale Ave. So., Bloomington, MN 55420	1	Globe Union, Inc. Attn: Dr. R. A. Rizzo 5757 N. Green Bay Avenue Milwaukee, WI 53201	1
Honeywell Inc. Mat & Process Eng. K. Y. Kim MN11-1812 600 2nd St. N.E. Hopkins, MN 55343	1	University of Missouri, Rolla Attn: Dr. J. M. Marchello 210 Parker Hall Rolla, MO 65401	1
The Aerospace Corporation Attn: Harlan Bittner Albert Heller P.O. Box 92957 Los Angeles, CA 90009	1 1	RAI Research Corporation Attn: Dr. Carl Perini 225 Marcus Boulevard Hauppauge, NY 11787	1
Honeywell Power Sources Center Attn: Dr. D. L. Chua N. Doddapaneni 104 Rock Road Horsham, PA 19044	1 1	Hellesens Battery Engineering, Inc. Attn: Dr. N. Marincic 1636 Hyde Park Ave. Hyde Park, MA 02136	2
Battelle Memorial Institute Defense Metals & Ceramics Information Center 505 King Avenue Columbus, OH 43201	1	RAY-O-VAC Attn: R. Udell N. Fleischer 630 Forward Drive Madison, WI 53711	1 1
Bell Laboratories Attn: Dr. J. J. Auburn 600 Mountain Avenue Murray Hill, NJ 07974	1	Litton Data Systems Division Attn: Frank Halula, MS 64-61 8000 Woodley Avenue Van Nuys, CA 91409	1
Callery Chemical Company Attn: Library Callery, PA 16024	1	TRW Systems Attn: I. J. Groce G. L. Juvinal Ed Moon, Rm. 2251, Bldg. 01 One Space Park Redondo Beach, CA 90278	1 1 1

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
ALTUS Corporation		GT & E Laboratory	
Attn: Dr. Adrian E. Zolla,	1	Attn: R. McDonald	1
Dr. J. R. Driscoll,	1	F. Dampier	1
Library	1	K. Kliendienst	1
1610 Crane Court		W. Clark	1
San Jose, CA 95112		40 Sylvan Rd.	
		Waltham, MA 02254	
Hyde Park Estates		Hughes Aircraft Company	
Attn: Dr. P. Bro	1	Attn: Dr. L. H. Fentnor	1
Santa Fe, NM 87501		Aerospace Groups	
Catalyst Research Corporation		Missile Systems Group	
Attn: G. Bowser	1	Tucson Engineering Laboratory	
J. Joelson	1	Tucson, AZ 85734	1
A. Schneider	1	Lockheed Missiles and Space	
1421 Clarkview Road		Company, Inc.	
Baltimore, MD 21209		Attn: Library	1
ESB Research Center		Lockheed Palo Alto Research	
Attn: Library	1	Laboratory	
19 W. College Avenue		3251 Hanover Street	
Yardley, PA 19067		Palo Alto, CA 94304	
EIC Corporation		Duracell Int., Inc.	
Attn: G. L. Holleck	1	Attn: B. McDonald	1
S. B. Brummer	1	Battery Division	
K. M. Abraham	25	South Broadway	
111 Downey Street		Tarrytown, NY 10591	
Norwood, MA 02062		Duracell Int., Inc.	
Eagle-Picher Industries, Inc.		Attn: W. Bowden	1
Attn: Robert L. Higgins	1	A. N. Dey	1
J. Dines	1	F. Parsons	1
L. R. Erisman	1	Library	1
Electronics Division		C. Schlaikjer	1
P.O. Box 47		Duracell Research Center	
Joplin, MO 64802		37 A Street	
		Needham, MA 02194	
Foote Mineral Company		Boeing Aerospace Co.	
Attn: H. R. Grady	1	Attn: S. Gross	1
Exton, PA 19341		C. Johnson	1
Gould, Inc.		P.O. Box 3999	
Attn: S. S. Nielsen	1	Seattle, WA 98124	
40 Gould Center		Electrochimica Corporation	
Rolling Meadows, IL 60008		Attn: M. Eisenberg	1
		2485 Charleston Rd.	
		Mt. View, CA 94040	

## DISTRIBUTION (Cont.)

	<u>Copies</u>		<u>Copies</u>
Etron Research Attn: T. Sammells 710 East Ogden Ave. Naperville, IL 60540	1	Moli Energy Limited Attn: Dr. J. A. Stiles 4010 Myrtle Street Burnaby, B.C. V5C 4G2 Canada	1
Saft America, Inc. Attn: Dr. R. J. Staniewicz Dr. K. Press Dr. G. Allvey 107 Beaver Court Cockeysville, MD 21030	1 1 1	ECO Energy Conversion Attn: Dr. F. M. Walsh 225 Needham Street Newton, MA 02164	1
Cordis Corporation Attn: W. K. Jones P.O. Box 525700 Miami, FL 33152	1	Ansum Enterprises, Inc. Attn: Dr. S. P. Wolsky 950 DeSoto Rd. Boca Raton, FL 33432	1
Tadiran Attn: M. Babai P.O. Box 75 Rehouot, Israel	1	Advanced Battery Group Attn: Dr. R. M. Murphy 269 Westwood Rd. Lancaster, NY 14086	1
Power Conversion, Inc. Attn: Dr. T. Reddy 495 Boulevard Elmwood Park, NJ 07407	1	Medtronics, Inc. Attn: Dr. B. Owens Dr. D. Untereker 6700 Shingle Creek Pkwy Brooklyn Center, MN 55430	1 1
Covalent Associates, Inc. Attn: Dr. V. Koch P.O. Box 3129 Saxonville Station Framingham, MA 01701	1	ELTECH Systems Corp. Attn: D. E. Harney Research and Development Center 625 East Street Fairport Harbor, OH 44077	1
Activair-A Division of Duracell, Inc. Attn: Dr. A. Attia 2777 Eagandale Boulevard Eagan, MN 55121	1	Internal Distribution: E231 E232 R33 (W. Kilroy)	9 3 32

**END**

**FILMED**

**9-85**

**DTIC**