



AD-A161 205 ON THE ROLE OF DIMENSIONLESS ELASTIC FRACTURE MECHANICS 1/2
(U) CARNEGIE-MELLON UNIV PITTSBURGH PA DEPT OF
MECHANICAL ENGINEERING G B SINCLAIR 03 JUL 85 SN-85-14
UNCLASSIFIED AFOSR-TR-85-0942 AFOSR-84-0047 F/G 20/11 NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

unclassified

SECURITY CLASS

AD-A161 285

DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS None		
2a. SECURITY CLASSIFICATION AUTHORITY None			3. DISTRIBUTION/AVAILABILITY OF REPORT Unlimited <i>Approved for public release; distribution unlimited.</i>		
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE N/A			5. MONITORING ORGANIZATION REPORT NUMBER(S) AFOSR-TR- 85 - 0942		
4. PERFORMING ORGANIZATION REPORT NUMBER(S) SM 85-14			7a. NAME OF MONITORING ORGANIZATION Air Force Office of Scientific Research DTIC		
6a. NAME OF PERFORMING ORGANIZATION G. B. Sinclair Carnegie-Mellon University		6b. OFFICE SYMBOL (If applicable) N/A	7b. ADDRESS (City, State and ZIP Code) Bolling Air Force Base Washington, D.C. 20332		
6c. ADDRESS (City, State and ZIP Code) Department of Mechanical Engineering Carnegie-Mellon University Pittsburgh, PA 15213		7c. ADDRESS (City, State and ZIP Code) Bolling Air Force Base Washington, D.C. 20332			
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Air Force Office of Scientific Research		8b. OFFICE SYMBOL (If applicable) N/A	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER AFOSR-84-0047		
8c. ADDRESS (City, State and ZIP Code) AFOSR/NA Building 410 Bolling AFB DC 20332		10. SOURCE OF FUNDING NOS.			
		PROGRAM ELEMENT NO. 611024	PROJECT NO. 2307	TASK NO. B2	WORK UNIT NO.
11. TITLE (Include Security Classification) On the role of dimensionless elastic fracture mechanics					
12. PERSONAL AUTHOR(S) G. B. Sinclair					
13a. TYPE OF REPORT Final report		13b. TIME COVERED FROM 1/15/84 TO 1/14/85		14. DATE OF REPORT (Yr., Mo., Day) July 3, 1985	
				15. PAGE COUNT 116	
16. SUPPLEMENTARY NOTATION					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB. GR.	FRACTURE MECHANICS, SIZE EFFECTS, NOTCHED SPECIMENS, STRESS CONCENTRATION, CRACK PROPAGATION		
19. ABSTRACT (Continue on reverse if necessary and identify by block number)					
Dimensionless elastic fracture mechanics (DEFM) - the nondimensionalized counterpart to linear elastic fracture mechanics (LEFM) - predicts size-independent strengths for geometrically similar specimens. This is in contrast to LEFM which has that the stress at fracture reduces as the inverse square root of the in-plane scale factor. It is shown that neither agrees with the data, irrespective of how brittle material response is. Used together with judgement, conceivably a conservative procedure for making strength size predictions is possible. However, both are essentially inadequate, since they lack valid underlying physical reasoning and, even as merely empirically based approaches, are short of sufficient accuracy to be reliable in practice. There is a need, therefore, to critically examine the very foundations of elastic fracture mechanics.					
DTIC FILE COPY					
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT UNCLASSIFIED/UNLIMITED ☒ SAME AS RPT. ☐ DTIC USERS ☐			21. ABSTRACT SECURITY CLASSIFICATION unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL David A. Glasgow, MAJOR, USAF NA			22b. TELEPHONE NUMBER (Include Area Code) (202) 767-4987		22c. OFFICE SYMBOL AFOSR/NA

ON THE ROLE OF DIMENSIONLESS ELASTIC FRACTURE MECHANICS

Final Report on Air Force Office of Scientific

Research Contract No. AFOSR-84-0047

G. B. Sinclair

SM 85-14

July, 1985

Approved for public release;
distribution unlimited.

Department of Mechanical Engineering

Carnegie Institute of Technology

Carnegie-Mellon University

Pittsburgh, Pennsylvania

ON THE ROLE OF DIMENSIONLESS ELASTIC FRACTURE MECHANICS

TABLE OF CONTENTS

Summary	1
Introduction	2
Overview of results obtained in research program	4
Concluding remarks	7
Acknowledgements	9
References	10
Appendices	

CONFIDENTIAL INFORMATION DIVISION

1. Strength size effects for embrittled paper specimens with cracks and semicircular notches in a single edge
2. A pilot experimental study of size effects in the fracture of double-edge-notched aluminum sheet specimens
3. A bibliography of strength size effects for cracked specimens
4. Strength size effects and fracture mechanics: What does the physical evidence say?
5. Some comments on the Griffith-Irwin approach to fracture Mechanics
6. On size effects in fracture

SUMMARY

Dimensionless elastic fracture mechanics (DEFM) - the nondimensionalized counterpart to linear elastic fracture mechanics (LEFM) - predicts size-independent strengths for geometrically similar specimens. This is in contrast to LEFM which has that the stress at fracture reduces as the inverse square root of the in-plane scale factor. It is shown that neither agrees with the data, irrespective of how brittle material response is. Used together with judgement, conceivably a conservative procedure for making strength size predictions is possible. However, both are essentially inadequate, since they lack valid underlying physical reasoning and, even as merely empirically based approaches, are short of sufficient accuracy to be reliable in practices. There is a need, therefore, to critically examine the very foundations of elastic fracture mechanics.

A1
 1
 2
 3
 4
 5
 6
 7
 8
 9
 10
 11
 12
 13
 14
 15
 16
 17
 18
 19
 20
 21
 22
 23
 24
 25
 26
 27
 28
 29
 30
 31
 32
 33
 34
 35
 36
 37
 38
 39
 40
 41
 42
 43
 44
 45
 46
 47
 48
 49
 50
 51
 52
 53
 54
 55
 56
 57
 58
 59
 60
 61
 62
 63
 64
 65
 66
 67
 68
 69
 70
 71
 72
 73
 74
 75
 76
 77
 78
 79
 80
 81
 82
 83
 84
 85
 86
 87
 88
 89
 90
 91
 92
 93
 94
 95
 96
 97
 98
 99
 100
 101
 102
 103
 104
 105
 106
 107
 108
 109
 110
 111
 112
 113
 114
 115
 116
 117
 118
 119
 120
 121
 122
 123
 124
 125
 126
 127
 128
 129
 130
 131
 132
 133
 134
 135
 136
 137
 138
 139
 140
 141
 142
 143
 144
 145
 146
 147
 148
 149
 150
 151
 152
 153
 154
 155
 156
 157
 158
 159
 160
 161
 162
 163
 164
 165
 166
 167
 168
 169
 170
 171
 172
 173
 174
 175
 176
 177
 178
 179
 180
 181
 182
 183
 184
 185
 186
 187
 188
 189
 190
 191
 192
 193
 194
 195
 196
 197
 198
 199
 200
 201
 202
 203
 204
 205
 206
 207
 208
 209
 210
 211
 212
 213
 214
 215
 216
 217
 218
 219
 220
 221
 222
 223
 224
 225
 226
 227
 228
 229
 230
 231
 232
 233
 234
 235
 236
 237
 238
 239
 240
 241
 242
 243
 244
 245
 246
 247
 248
 249
 250
 251
 252
 253
 254
 255
 256
 257
 258
 259
 260
 261
 262
 263
 264
 265
 266
 267
 268
 269
 270
 271
 272
 273
 274
 275
 276
 277
 278
 279
 280
 281
 282
 283
 284
 285
 286
 287
 288
 289
 290
 291
 292
 293
 294
 295
 296
 297
 298
 299
 300
 301
 302
 303
 304
 305
 306
 307
 308
 309
 310
 311
 312
 313
 314
 315
 316
 317
 318
 319
 320
 321
 322
 323
 324
 325
 326
 327
 328
 329
 330
 331
 332
 333
 334
 335
 336
 337
 338
 339
 340
 341
 342
 343
 344
 345
 346
 347
 348
 349
 350
 351
 352
 353
 354
 355
 356
 357
 358
 359
 360
 361
 362
 363
 364
 365
 366
 367
 368
 369
 370
 371
 372
 373
 374
 375
 376
 377
 378
 379
 380
 381
 382
 383
 384
 385
 386
 387
 388
 389
 390
 391
 392
 393
 394
 395
 396
 397
 398
 399
 400
 401
 402
 403
 404
 405
 406
 407
 408
 409
 410
 411
 412
 413
 414
 415
 416
 417
 418
 419
 420
 421
 422
 423
 424
 425
 426
 427
 428
 429
 430
 431
 432
 433
 434
 435
 436
 437
 438
 439
 440
 441
 442
 443
 444
 445
 446
 447
 448
 449
 450
 451
 452
 453
 454
 455
 456
 457
 458
 459
 460
 461
 462
 463
 464
 465
 466
 467
 468
 469
 470
 471
 472
 473
 474
 475
 476
 477
 478
 479
 480
 481
 482
 483
 484
 485
 486
 487
 488
 489
 490
 491
 492
 493
 494
 495
 496
 497
 498
 499
 500
 501
 502
 503
 504
 505
 506
 507
 508
 509
 510
 511
 512
 513
 514
 515
 516
 517
 518
 519
 520
 521
 522
 523
 524
 5



INTRODUCTION

Being able to predict the strength of geometrically-similar cracked specimens of different sizes or scales is a basic requirement for success for any fracture mechanics technology. The prediction contained in LEFM is that the strength reduces as the inverse square-root of the scale factor in the plane of the crack. To see this, consider the example of a pair of scaled single-edge-cracked specimens shown in Fig. 1. Herein Specimen 1 is a strip of indefinite length yet finite width W , weakened by a crack of length a , and subjected to a remote uniform stress σ_1 ; while Specimen 2 is also of indefinite length but has width λW , crack length λa , and applied stress σ_2 . Thus λ is the in-plane scale factor. For Specimen 1 at fracture, LEFM has

$$K_I = \sigma_1^* \sqrt{\pi a} f(a/W) = K_C,$$

where K_I is the stress intensity factor in Mode I, $f(a/W)$ is a finite width correction factor, K_C is the material fracture toughness, and the asterisk atop σ_1 serves to distinguish it as being the applied stress at fracture. Similarly for Specimen 2, provided it is comprised of the same brittle material, at fracture

$$K_I = \sigma_2^* \sqrt{\pi \lambda a} f(\lambda a/\lambda W) = K_C,$$

whence

$$\sigma_1^*/\sigma_2^* = \sqrt{\lambda}. \quad (1)$$

Given that the underlying continuum mechanics does scale, the size effect evident in (1) is somewhat curious and stems from the choice of the stress intensity factor as the parameter governing brittle fracture. The question examined in this research program is how appropriate is such an absence of scaling.




Fig. 1. Scaled pair of single-edge-cracked specimens

The view at the outset of the program was that response should scale unless there are microstructural factors and accompanying lengths involved. To this end, we form dimensionless elastic fracture mechanics simply by replacing K_I by $\bar{K}_I$, the dimensionless stress crack factor. More precisely, in the previous example, we define

$$\bar{K}_I = K_I / \sigma_1 \sqrt{W} = \sqrt{\pi a / W} f(a/W),$$

for Specimen 1, and assume fracture to be controlled by a material fracture stress, σ_c , so that, at fracture

$$\sigma_1^* \bar{K}_I = \sigma_c.$$

Similarly for Specimen 2,

$$\sigma_2^* \bar{K}_I = \sigma_2^* \sqrt{\pi \lambda a / \lambda W} f(\lambda a / \lambda W) = \sigma_c$$

a fracture, whence

$$\sigma_1^* / \sigma_2^* = 1 \tag{2}$$

That is, the strength scales in the dimensionless version, and it is expected that (2) in fact holds unless there are microstructural size effects. With significant caveats, this view remains the same in the light of the physical evidence examined. The limited role, though, that either LEFM or DEFM can play in predicting strength size effects is now understood more fully. We explain why in what follows.

OVERVIEW OF RESULTS OBTAINED IN RESEARCH PROGRAM

One of the first sets of test performed within this program to see which of (1), (2) best applies was on a model material - Xerox paper embrittled by baking. These supported (2) over (1) (refer original proposal). Subsequently

a more comprehensive set of tests on scaled single-edge-cracked specimens made of the same model material have been undertaken and reported in Kondo and Sinclair [1] (copy attached as Appendix 1). In [1], the material is demonstrated to be extremely brittle in good accord with the assumptions underpinning elastic fracture mechanics, and some 244 individual tests are involved enabling the effects of scatter to be gauged and controlled. The results found are summarized below.

Table 1. Fracture stress ratios from [1]

Scale factor, λ	Mean ratio, $\frac{\sigma_1^*}{\sigma_2^*}$	95% confidence limits
1.5	1.011	0.928-1.094
2.0	0.994	0.923-1.065
3.0	1.001	0.910-1.092
4.0	1.047	0.994-1.100

These results demonstrate statistically significant differences between actual physical behavior and that predicted by LEFM, (1), while admitting the possibility that (2) holds within scatter.

Discussion of these results with members of the fracture mechanics community [2] lead to our being directed towards references containing data such that the converse was true, i.e. (1) was supported over (2). The most convincing of such references was the paper by Lubahn and Yukawa [3], and in particular, Irwin's discussion [4] of the same. There, for a wide range of

scale factors, very good agreement with LEFM (1) is exhibited, although the specimens are not perfectly scaled with respect to notch acuity. Too, the response for the most part is quite ductile with the yield region typically being considerably in excess of 2% of the crack length, the limit usually regarded as demarking brittle from ductile behavior (cf. ASTM standards for plane strain fracture toughness testing [5]). This contrasting behavior nonetheless motivated two activities: carrying out our own set of tests on a more ductile material and simultaneously performing an extensive literature search for data bearing on the issue.

The results of the first activity for aluminum sheets are presented in detail in Keremes and Sinclair [6] (attached as Appendix 2). In summary, the 60 double-edge-cracked specimens gave:

$$\lambda = 3, \overline{\sigma_1^*/\sigma_2^*} = 1.014, 95\% \text{ confidence limits} = 0.998-1.029.$$

Thus a physical demonstration of support for (2) over (1), the opposite to the trends reported in [3]. Clearly the situation does not have one simple answer.

An answer of sorts is furnished by the review of some 300 references containing strength size effects data (see bibliography [7], copy attached as Appendix 3). From these references, 100 odd independent sources can be drawn which contain strength dependencies for truly in-plane scaled cracked specimens (with thickness effects controlled). The data from these pertinent references are analyzed at some length in Sinclair and Chambers [8] (Appendix 4). In essence the data show that neither (1) nor (2) holds, irrespective of whether the tests are for very brittle response or quasi-brittle response, for plane strain or plane stress, for valid K_{IC} testing or not, etc. Occasionally the size independent response (2) is found:

far more often there are microstructural size effects so that there is a reduction in strength with size, the same trend as in (1), yet seldom are such effects even roughly tracked by this simple formula. The situation is too complex for such naive predictions (1), (2) of size dependence (independence) to be appropriate.

A partial explanation as to what is going wrong in the classical arguments that linear elastic fracture mechanics is founded on - essentially the thermodynamic argument of Griffith [9] - is given in Sinclair [10] (Appendix 5). A possible explanation of the data itself, based on an extension of that first given by Weiss and Yukawa [11], is given in Sinclair [12] (Appendix 6). Both [10], [12] are at a stage that might best be termed ongoing research at this time. Their full development was not intended to be a part of the one-year research program for which this is the final report, and thus it is not appropriate to discuss them in any detail here. What can be said, however, is that size effects are almost certainly due to microstructure and consequently can be expected to differ from one material to the next, even when response is brittle. Further, for a specific material, they can depend on size itself, typically decreasing with increasing size. Thus there is no one formula like (1) with a single exponent (there one half), but a variety of different exponents which are both material and geometry dependent themselves. Given this far more complex character, (1) is quite inadequate, and the idea that (2) applies unless there are microstructural effects probably true but largely useless. We offer some concluding remarks in the light of these observations next.

CONCLUDING REMARKS

The prediction of strength size effects in fracture mechanics using

either LEFM or DEFM is so naively simple as to be manifestly incomplete. Accordingly both can lead to predictions that are inaccurate to the point of not being acceptable in engineering. Moreover such errors are not necessarily conservative. For example, LEFM is typically nonconservative when testing a specimen larger than the size of the intended application, a situation that can certainly arise in practice, and DEFM is nonconservative in reverse circumstances.

In practice, then, it is preferable, if not necessary, to test on the same size scale as the application. In the event of this being impractical, the following strategy might be adopted. For the most part, the size effects predicted by LEFM are in excess of those for the actual data. Hence when testing small and applying big, LEFM can be used to estimate the reduction in strength and usually will do so conservatively. On the other hand, when testing big and applying small, the LEFM prediction can greatly exceed the strength increases in fact realized. Here, though, it would appear that strength seldom decreases with decreasing size. Consequently, using DEFM will generally be conservative.

A caution on the use of the above is in order. There is really no physical reasoning underlying the scheme; it is merely based on observation of the data. And this data is not always confined within LEFM's prediction of size effects and the size independence of DEFM, so that there is physical evidence of the strategy being nonconservative. Some judgement is therefore required in implementing this essentially empirical approach.

On a more fundamental front, there is reason to be concerned about the very basis of fracture mechanics. These concerns arise because there exist several hundred test results for appropriately brittle behavior *not* agreeing with the LEFM prediction of strength size effects (see [8]). Every one of

these represents data establishing a variation in fracture toughness with size. It follows that fracture toughness is demonstrably *not* a material property. Thus the use of the stress intensity factor as the parameter in and of itself controlling brittle fracture needs serious examination.

Acknowledgements - We are pleased to acknowledge the valuable benefit of discussions during the course of this work with J.H. Griffin of the Department of Mechanical Engineering at Carnegie-Mellon University and with D.A. Glasgow of the Air Force Office of Scientific Research (AFOSR). The financial support of AFOSR is also appreciated.

REFERENCES

1. M. Kondo and G.B. Sinclair, Strength size effects for embrittled paper specimens with cracks and semicircular notches in a single edge. Report SM 85-5, Dept. of Mechanical Engineering, Carnegie-Mellon University (1985).
2. G.B. Sinclair, Dimensionless elastic fracture mechanics: a necessary revision to LEFM? Presentation made to the E24 Committee Meeting, American Society for Testing and Materials, Jacksonville, Florida (1984).
3. J. D. Lubahn and S. Yukawa, Size effects in slow notch-bend tests of a nickel-molybdenum-vanadium steel. *Proceedings of the American Society for Testing and Materials*, Vol. 59, p. 661 (1958).
4. G.R. Irwin, Discussion. *Ibid*, p. 677 (1958).
5. 1982 Annual Book of Standards, Part 10. ASTM, Philadelphia, Pennsylvania (1982).
6. J.J. Keremes and G.B. Sinclair, A pilot experimental study of size effects in the fracture of double-edge-notched aluminum sheet specimens. Report SM 84-26, Dept. of Mechanical Engineering, Carnegie-Mellon University (1984).
7. G.B. Sinclair, A bibliography of strength size effects for cracked specimens. Report SM 85-10, Dept. of Mechanical Engineering, Carnegie-Mellon University (1985).
8. G.B. Sinclair and A.E. Chambers, Strength size effects and fracture mechanics: what does the data say? *Engineering Fracture Mechanics*, under review.
9. A.A. Griffith, The phenomena of rupture and flow in solids. *Philosophical Transactions of the Royal Society (London)*, Vol. 221 A, p. 163 (1920).
10. G.B. Sinclair, Some comments on the Griffith-Irwin approach to fracture mechanics. *Nineteenth Midwestern Mechanics Conference*, Columbus, Ohio, to appear (1985).
11. V. Weiss and S. Yukawa, Critical appraisal of fracture mechanics. *Fracture Toughness Testing and Its Applications*, ASIM STP 381, p. 1 (1965).
12. G.B. Sinclair, On size effects in fracture. *Proceedings of the Tenth Canadian Congress of Applied Mechanics*, London, Ontario, p. A-273 (1985).

STRENGTH SIZE EFFECTS FOR EMBRITTLED PAPER SPECIMENS WITH CRACKS
AND SEMICIRCULAR NOTCHES IN A SINGLE EDGE

M. Kondo and G.B. Sinclair

Report SM 85-5

March 1985

Department of Mechanical Engineering
Carnegie Institute of Technology
Carnegie-Mellon University
Pittsburgh, Pennsylvania

STRENGTH SIZE EFFECTS FOR EMBRITTLED PAPER SPECIMENS
WITH CRACKS AND SEMICIRCULAR NOTCHES IN A SINGLE EDGE

INTRODUCTION

Strength size effects occur when two geometrically similar configurations comprised of the same material but having different sizes fracture at different applied stress levels. Such effects must be limited if the inferred physical measures of stress increase due to the presence of cracks and sharp re-entrant corners in Sinclair and Kondo [1] are to be meaningful. The primary objective of the work reported here is to check for size effects in the model brittle material used in [1].

In this connection we note that there are theories which predict size dependence in brittle materials. For cracked geometries, *linear elastic fracture mechanics* (LEFM) has

$$\sigma_1^*/\sigma_2^* = \sqrt{\lambda}, \quad (1)$$

wherein σ_i^* ($i = 1, 2$) are the applied stresses at fracture in two similar cracked specimens, the second of which has its in-plane dimensions increased by the scale factor λ . Hence LEFM predicts a specific reduction in strength with increase in size for all brittle materials with cracks. For general geometries, *Weibull's statistical approach* [2] leads to

$$\sigma_1^*/\sigma_2^* = (V_1/V_2)^{-1/m}, \quad (2)$$

where V_i is the stressed volume for Specimen i ($i = 1, 2$), and m is a material parameter. For $m > 0$, this also gives rise to a reduction in strength with increasing size, but now different rates of reduction are admitted including the possibility of size independence ($m \rightarrow \infty$). Thus there would seem to be a real need to check what size dependence if any exists for the model brittle material of [1],

especially for cracked specimens.

This report describes three different sets of experiments carried out to this end during the course of the last two years. The first of these examined fracture stress ratios of single-edge cracks with scale factors of $\lambda = 1.5, 2, 3, 4$ (performed in June, 1983), the second concerned more extensive testing of the extreme ($\lambda = 4$) of the first set (October, 1983), and the third looked at a control set of single-edge semicircular notches with $\lambda = 4$ (April, 1984). In what follows we begin by discussing the experimental setup for all three sets in Section 1, then close by presenting attendant results in Section 2 (complete experimental data are furnished in the Appendix).

1. EXPERIMENTAL DESIGN

The model material employed in Sinclair and Kondo [1] is baked Xerox paper. Details of the preparation of this embrittled paper and the fabrication and inspection procedures for specimens made out of it are given in [1], together with the reasons for its use, so that here we merely summarize the key aspects.

This model material has the attribute of readily enabling fabrication of specimens at low cost and with little effort. Suitably heat treated it is very brittle, thereby approximating well the linear elastic response up to the point of fracture sought in [1]. Further its thinness ensures a two-dimensional stress state but it is still sufficiently thick so as to prevent buckling. In all this material represents good compliance with the properties sought in [1], yet also should be one for which LEFM is most applicable.

The embrittled paper specimens for testing size effects are shown in Fig.1 and have actual dimensions as in Table 1 (all are 9 inches long and 0.0035 inches thick). Sets of each specimen type are prepared, inspected for surface nicks or burrs, and checked for evenness of baking. Any not meeting standards are discarded *before* testing. The remainder are pulled in a calibrated Hounsfield tensometer and *all* fracture stress ratios recorded. The sample sizes tested are 77, 30, 30,




Fig. 1. Scaled specimen pairs

30, 77 for $\lambda = 1, 1.5, 2, 3, 4$ respectively for the cracked specimens, and 38 for both $\lambda = 1$ and $\lambda = 4$ for the semicircular notch specimens. Provided approximately normal distributions of the fracture stress ratios result, sample sizes of 30 or larger enable the use of the Central Limit Theorem (see, e.g. Wine [8]; as a check on this requirement histograms of the data are examined). Then the 95% confidence limits in the *mean* fracture stress ratio, $\overline{(\sigma_1^*/\sigma_2^*)}$, can be approximated by $\overline{(\sigma_1^*/\sigma_2^*)} \pm 1.96s/\sqrt{N}$, where s is the *sample* standard deviation in σ_1^*/σ_2^* and N is the sample size. In this way it is hoped to control the scatter sufficiently to resolve the issue at hand.

Table 1. Specimen dimensions (in inches)

Specimen type	Scale factor, λ	Crack length/ notch depth, a	Width, b
Crack	1.0	0.2	0.8
Crack	1.5	0.3	1.2
Crack	2.0	0.4	1.6
Crack	3.0	0.6	2.4
Crack	4.0	0.8	3.2
Notch	1.0	0.3	1.2
Notch	4.0	1.2	4.8

2. RESULTS

The results for the fracture stress ratios for the different specimens are summarized in Table 2. These show that the mean fracture stress ratios differ from unity by no more than 5% and typically by around 2%. The scatter in the experimental ranges is of the order of $\pm 45\%$ about the mean with a maximum deviation

of 62% for the cracked specimens, while the range for the notched specimens is close to $\pm 20\%$. However, since the data are in fact approximately normally distributed (see Appendix), the Central Limit Theorem can be invoked to in effect restrict scatter to about $\pm 8\%$ for $\lambda = 1.5, 2, 3$ and $\pm 5\%$ for $\lambda = 4$ for the cracked specimens, and to about $\pm 3\%$ for the notched specimens. Accordingly the results represent a solid demonstration of *strength size insensitivity* for the model material of [1], even for cracked instances.

Table 2. Fracture stress ratio results

Specimen type	Scale factor λ	Mean ratio (σ_1^*/σ_2^*)	Experimental range	95% confidence limits
Crack	1.5	1.011	0.612-1.539	0.928-1.094
Crack	2.0	0.994	0.680-1.513	0.923-1.065
Crack	3.0	1.001	0.722-1.622	0.910-1.092
Crack	4.0	1.047	0.617-1.536	0.994-1.100
Notch	4.0	1.015	0.851-1.250	0.983-1.047

Comparing the outcomes represented in Table 2 with the LEFM prediction (1), we see, that despite the physical correspondence to the underlying assumptions in elastic fracture mechanics, the data here are in clear disagreement. More precisely, (1) has σ_1^*/σ_2^* equal to 1.22, 1.41, 1.73, 2.00 for $\lambda = 1.5, 2, 3, 4$ whereas experimentally we find (σ_1^*/σ_2^*) of 1.01, 0.99, 1.00, 1.05 respectively. Moreover, for the last two scale factors, not even a single outlier in over 100 tests attained the value predicted by LEFM, while for all λ , the experimental 95% confidence limits excluded the σ_1^*/σ_2^* of (1).

Turning to the Weibull model of strength size effects and fitting (2) to

to the mean values in Table 2 yields $m = 37, -115, 1099, 30$ for $\lambda = 1.5, 2, 3, 4$ for the cracked specimens and $m = 93$ for the notched specimens. These large and varying values are typical of those found when strength response is size independent to all intensive purposes and underscore the disagreement with elastic fracture mechanics here ($m = 2$ in LEFM for the present geometries).

In sum, the strength size *independence* of the given model material required for the study in Sinclair and Kondo [1] to be useful would appear to exist. This size independence differs markedly from the size *dependence* for brittle materials implicit in linear elastic fracture mechanics.

REFERENCES

1. G.B. Sinclair and M. Kondo, "On the stress concentration at sharp re-entrant corners in plates." *International Journal of Mechanical Sciences*, Vol. 26, p.477 (1984).
2. W. Weibull, "A statistical theory of the strength of materials." *Proceedings, Royal Swedish Institute for Engineering Research*, No. 151 (1939).
3. R.L. Wine, *Statistics for Scientists and Engineers*. Prentice-Hall, Englewood Cliffs, New Jersey (1964).

APPENDIX

Here we give the actual experimental data for the fracture stress ratios (Table 3) and histograms of the results for the cracked specimens (Fig. 2). The results for the notched specimens conform more closely to a normal distribution than those in Fig. 2.

Table 3. Fracture stress ratios, σ_1^*/σ_2^*

Cracked specimens						Notched specimens	
$\lambda = 1.5$	$\lambda = 2$	$\lambda = 3$	$\lambda = 4$	$\lambda = 4$	$\lambda = 4$	$\lambda = 4$	$\lambda = 4$
1.195	0.966	1.102	1.092	1.406	1.148	1.047	1.000
0.846	1.085	1.000	0.909	1.148	1.087	1.115	1.070
0.832	0.852	0.813	0.877	1.508	1.359	0.982	0.991
1.226	0.680	0.920	0.935	1.042	0.617	1.041	1.004
0.976	0.878	0.924	0.735	0.840	1.160	1.250	0.896
0.942	1.513	0.850	0.847	0.714	0.794	1.130	0.903
0.984	1.353	1.622	1.385	0.855	0.990	1.056	0.851
1.139	0.810	1.158	1.012	1.033	1.282	0.986	0.912
1.539	1.045	1.130	0.855	1.103	1.022	0.919	
0.838	0.852	0.784	1.364	0.952	0.645	0.979	
1.400	1.121	1.130	1.304	1.307	1.172	1.005	
1.202	1.057	1.021	1.458	1.248	0.787	0.983	
0.790	1.100	0.863	1.267	0.935	0.813	0.949	
1.000	1.245	0.769	1.536	0.820	0.909	1.045	
0.865	0.934	1.255	1.508	0.870	0.621	1.082	
1.157	1.042	1.157	0.952	1.250	0.877	1.169	
0.952	0.785	0.863	1.368	1.364	1.214	1.132	
1.046	1.103	0.925	1.104	1.344		1.000	
0.747	1.000	0.722	1.000	0.847		1.088	
0.833	0.851	0.851	1.000	1.211		0.867	
0.612	0.703	0.722	1.250	1.000		0.936	
1.392	1.243	1.101	0.820	1.043		1.153	
0.924	0.859	0.913	0.840	1.250		0.852	
0.899	0.707	0.869	0.862	0.758		0.991	
1.318	1.101	1.865	0.769	0.654		1.021	
0.874	1.115	0.954	0.909	1.285		1.044	
0.616	0.718	0.735	1.269	0.909		0.969	
1.215	1.106	1.253	0.787	1.309		0.868	
0.815	0.930	0.902	1.211	0.917		1.247	
1.144	1.080	0.865	1.124	0.847		1.054	




Fig. 2. Relative frequencies of fracture stress ratio data for the cracked specimens ($\bar{\sigma} = (\sigma_1^*/\sigma_2^*)$)

**A PILOT EXPERIMENTAL STUDY OF SIZE EFFECTS
IN THE FRACTURE OF DOUBLE-EDGE-NOTCHED
ALUMINUM SHEET SPECIMENS**

J.J. Keremes and G.B. Sinclair

Report SM84-26

November, 1984

Department of Mechanical Engineering
Carnegie Institute of Technology
Carnegie-Mellon University
Pittsburgh, Pennsylvania

A PILOT EXPERIMENTAL STUDY OF SIZE EFFECTS
IN THE FRACTURE OF DOUBLE-EDGE-NOTCHED
ALUMINUM SHEET SPECIMENS

INTRODUCTION

Size effects occur when two different sizes of specimens having the same shape, material, and loading configuration, fracture at different nominal stresses. In this connection, linear elastic fracture mechanics (LEFM) implies that the ratio of nominal stresses at fracture between two cracked specimens is equal to the square root of their scaling factor (λ), the so-called *geometric size effect*. Thus

$$\frac{\sigma_1^*}{\sigma_2^*} = \lambda, \quad (1)$$

where σ_1^* , σ_2^* are the nominal stresses at fracture in Specimens 1, 2 respectively, with Specimen 2 being λ times as big as Specimen 1. Alternatively, a simple Weibull model [1] based on a statistical theory of fracture has that

$$\frac{\sigma_1^*}{\sigma_2^*} = \left(\frac{V_1}{V_2} \right)^{-1/m} \quad (m > 0), \quad (2)$$

where V_1 , V_2 are the respective volumes of Specimens 1, 2, and m is a material parameter found by experimentation. Equation (2) represents a means of fitting *microstructural size effects*. Both (1) and (2) are in agreement with the general trend found in actual data, namely that strength decreases with size. However, there are significant differences between these two: (1) has a fixed dependence for all materials with this dependence being on in-plane dimensions alone, whereas (2) has a size dependency which is material sensitive and which exhibits variations with both in-plane and out-of-plane dimensions. The basis objective here is to experimentally examine for selected configurations whether (1) holds, (2) holds, both hold or neither.

Generally one expects the LEFM prediction, (1), to apply best when the response is brittle. Other components of the research program here at C-MU examine the applicability of (1) in this case. However, there exists claims in the literature (see, for example, Irwin's discussion of Lubahn and

Yukawa [2]) which suggest that (1) holds even with ductile response. As a result we seek to examine the validity of (1) here for a material which exhibits some ductility. There is an extensive literature on this subject and a comprehensive review falls outside the scope of this report. Nonetheless, it would be fair to say even on the basis of a limited review [3-7], that generally size effects do occur in ductile materials with significant stress concentrators, but that these effects do not necessarily adhere to the specific size dependence of (1). This last though may be attributable to scatter in the results. As a consequence a second aim of this experimental study is to control scatter sufficiently to resolve the issue as to which of (1), (2) is most appropriate.

In what follows we first describe a set of experiments designed to meet our two objectives in Section 1, then present the attendant results in Section 2.

1. EXPERIMENTAL DESIGN

In this section we describe the reasons underlying our material selection and the manner in which the tests are performed.

The selection of testing material is governed by the criteria of exhibiting significant ductility and enabling reproducibility. A suitable material should thus have a plastic strain to elastic strain ratio which is at least two at rupture in a uniaxial tension test. In addition, an appropriate material must also allow reproducible results, either by having little inherent scatter or by readily permitting a sufficiently large set of experiments to be performed which will in effect limit scatter.

One material which has the potential of satisfying the above criteria is aluminum in the form of thin sheets. This material can be expected to exhibit some significant ductility; simple tensile tests on straight specimens serve to check this expectation. The thinness of the sheet material, moreover, makes it easy, both from an effort and an economics viewpoint, to manufacture a large number of specimens.

Unfortunately, when obtaining standard sheets it is not generally possible to scale the thickness of the specimens in unison with the rest of the dimensions. As a result we choose to use a single sheet thickness and thereby reduce variations from one manufactured roll to another. Provided this thickness is small enough, a two-dimensional state of stress (plane stress) should still be induced. Observe that when thickness is not scaled, the possibility of buckling is increased with larger in-plane dimensions; thus, the largest specimen is the critical specimen in

which to prevent buckling. To minimize the possibility of buckling in the largest specimen, the thickest freely available commercial sheet is chosen which has a thickness of 0.00093 inches. This selection serves to sufficiently limit buckling here and is still 10^3 times smaller than the smallest of the in-plane dimensions so that a two-dimensional geometry is obtained.



A Hounsfield Tensometer with a light beam spring is used to test the specimens. A checked spring balance is used to calibrate the force measurements of the tensometer. Fine sandpaper placed on the testing grips prevents the specimens from slipping. The grips themselves slide on bars which are dusted with powdered chalk to reduce friction.

A geometric scale factor of 3:1 ($\lambda = 3$) is chosen for the specimens since their size range is restricted by the testing equipment. This scale factor though is large enough to provide observable results between the two sizes of specimens should a size effect exist. Three different shapes of notched specimens are tested (Fig. 1). The two circularly notched specimens serve as a reference for the key geometry in the experiments which is the cracked configuration pair: the sharply notched specimens provide an intervening geometry. The specimens are all double-edge-notched to prevent the bending which would occur in single-notched specimens.



When making the specimens the longest dimension is always parallel to the rolling direction of the aluminum foil. After being manufactured the specimens are examined for defects. All of the specimens judged to be defective are removed from the specimen pool *prior* to testing. The ends of the accepted specimens are then placed into the grips of the tensometer and loaded until fracture occurs. A total of 30 specimens are tested in the tensometer for each particular size and shape of specimen in Fig.1 and *all* results found included. This number of tests enables the use of the central limit theorem which recognizes that more measurements enable us to know the value of the mean better. The theorem in effect states that the standard deviation *in the mean* is equal to the population standard deviation divided by the square root of the sample size. Given a sufficiently large sample size we can reasonably approximate the population standard deviation by s , the *sample* standard deviation; then the approximate 95% confidence limits for the mean fracture stress, $\bar{\sigma}$, are $\bar{\sigma} \pm 1.96s/\sqrt{N}$, where N is the sample size. It is generally accepted that "sufficiently large" in practice means $N \geq 30$ providing that the distribution is not of an unusual shape (see Wine [8]). Histograms are used to check this last point.

2. RESULTS



Here we first present our results and then comment on their relation to existing theories.



Double edge crack specimens



Double edge deep circular notch specimens



Double edge semicircular notch specimens

Fig. 1 Scaled test specimens ($w = 4.50$ in.)

A uniaxial stress (σ) versus strain (ϵ) curve for unnotched straight aluminum sheet specimens is shown in Fig.2. Here σ , ϵ have been normalized by their respective values at yield, σ_y , ϵ_y . This graph has a ratio of 6.3 for the strain at fracture (ϵ_f) divided by the yield point strain (ϵ_y). This value is less than that for bulk aluminum because of the cold-work involved in sheet production and typically less than values for aluminum alloys and mild steel: nonetheless it represents a marked degree of ductility and we can expect the net section stress to exceed the yield stress in our notched specimens - the hallmark of significantly ductile response for such configurations. Indeed this is found to be the case for all notched specimens with typically the ratio of nominal stress to yield stress being 1.8 and ranging from 1.67 to 1.91.

With the thickness used buckling as expected is limited. Only the largest specimens exhibit perceptible buckling. This occurs at the ends of the specimens near the grips in the form of a sinusoid of the order of 3 cycles with an amplitude of about 0.5% of the width. There is buckling in the vicinity of any of the notches.

The results of the notched tensile tests are summarized in Table 1. The results show that all three specimens are basically size independent. While the scatter reflected in the actual untreated experimental ranges might permit an appreciable size effect to be present yet remain undetected, the 95% confidence limits indicate no such possibility with size effects restricted to no more than 3%. These 95% confidence limits are based on the central limit theorem, the use of which is justified by the histograms in the Appendix.

Table 1. The effect of size on the mean fracture stress ratio.

Specimen	(σ_1/σ_2)	Raw experimental range	95% confidence limits
Double-edge crack	1.014	0.924-1.100	0.998-1.029
Double-edge deep circular notch	1.010	0.932-1.139	0.992-1.027
Double-edge semi-circular notch	1.008	0.903-1.096	0.989-1.026




Fig. 2 Stress-strain data for unnotched aluminum sheet

To all intensive purposes, the three types of specimen are size independent. Notched pure aluminum bars tested in Klier and Weiss [9] also show no noticeable size effect which is consistent with the present data. The results do indicate a small increase in the fracture stress with a decrease in size. As remarked earlier, an increase in strength with decrease in size is consistent with other size effect phenomena. It is interesting to note that although the size effect is small it is similar for all three types of notches.

Although we have ductile response here so that LEFM is not appropriate, we can compare with the LEFM prediction (1) to see if it extends into the ductile region as has been suggested by other investigators on occasion. Clearly (1) cannot in general admit to such an extension since here we demonstrate that it is violated, and statistically significantly so. Moreover, the presence of size effects of type (2) cannot alleviate this contradiction.

Applying the simple Weibull model (2) to the three specimens gives a range of values for m from 148-276. The high values of m show that the specimens are practically size insensitive. It should be noted that the value of m with such small size effects is uncertain since in this range of size effects the value of m can change appreciably with a small percentage change in the σ_1/σ_2 ratio. Even so, this value is markedly different from that contained in effect in LEFM (ie. an m of 2 here), underscoring that the LEFM size prediction does not apply here.

REFERENCES

1. W. Weibull, "A Statistical Theory of the Strength of Materials," *Proceedings, Royal Swedish Institute for Engineering Research*, No. 151 (1939).
2. J.D. Lubahn and S. Yukawa, "Size Effects in Slow Notch-Bend Test of a Nickel-Molybdenum-Vanadium Steel," *ASTM Proceedings*, Vol.58, p.551 (1964).
3. V. Weiss, G. Schaeffer, and J. Fehling, "Effect of Section Size on Notch Strength," *Journal of Basic Engineering, Transactions of ASME, Series D*, Vol.88, p.675 (1966).
4. W.F. Brown, J.D. Lubahn, and L.J. Ebert, "Effect of Section Size on the Static Notch Bar Tensile Properties of Mild Steel," *Journal of the American Welding Society, Welding Research Supplement*, Vol.26, p.554 (1947).
5. T.S. DeSisto, F.L. Car, and F.R. Larson, "The Influence of Section Size on the Mechanical Properties and Fracture Toughness of 7075-T6 Aluminum and 6A1-6V-2Sn Titanium and AISI 4340 Steel," *ASTM Proceedings*, Vol.63, p.768 (1963).

6. B.M. Wundt, "A Unified Interpretation of Room Temperature Strength of Notched Specimens as Influenced by Their Size," *ASME Paper No.59- Met- 9*.
7. E.R. Parker, "The Effect of Section Size on the Fracture Strength of Mild Steel," *Fracturing of Metals, American Society of Metals, Vol.40B, p.82 (1948)*.
8. R.L. Wine, *Statistics for Scientist and Engineers*, Prentice-Hall, New Jersey (1964).
9. E.P. Klier and V. Weiss, "The Effect of Section Size on the Notch Strength and Fracture Development in Selected Structural Metals," *ASTM Proceedings, Vol.61, p.1307 (1961)*.

Appendix

Here we furnish the details of the experimental data.

Table 2. < Strength ratios (σ_1^*/σ_2^*) for different specimens shapes.

Specimen number	Double-edge crack specimens	Double-edge deep circular notch specimens	Double-edge deep semicircular notch specimens
1	0.950	1.048	1.017
2	1.038	1.042	0.990
3	0.924	1.016	1.094
4	1.091	1.139	1.032
5	1.025	0.977	1.042
6	1.001	0.938	1.058
7	1.025	1.034	1.073
8	0.979	1.034	1.058
9	1.017	1.015	0.972
10	1.066	1.077	0.929
11	1.016	0.973	0.990
12	1.071	1.044	1.018
13	0.976	0.951	1.087
14	1.018	1.064	1.056
15	1.064	1.008	0.995
16	1.022	0.932	1.096
17	0.961	0.991	1.000
18	0.976	0.947	0.961
19	0.984	0.952	0.952
20	1.028	0.951	1.037
21	0.987	1.021	0.938
22	1.049	1.002	0.903
23	1.028	1.018	0.952
24	0.958	1.076	1.020
25	1.061	1.063	1.021
26	0.976	1.027	0.967
27	1.100	0.973	1.037
28	0.979	0.968	0.998
29	0.993	1.030	0.951
30	1.043	0.981	0.986





Fig. 3 Histograms of the strength ratios in Table 2

Histograms of the data in Table 2 are presented in Fig.3 as evidence that the data approximate a normal distribution permitting the use of the central limit theorem. As further evidence, the standard deviations for the first 15 and second 15 specimens are calculated separately to see if they are numerically consistent with asymptotically approaching a limiting value. These results are given in Table 3 and support the use of the sample standard deviation as an estimate of the corresponding population values.

Table 3. Means and standard deviations of the experimental data in table 2.

Source	Mean	Standard deviation
Double-edge crack		
1st 15 specimens	1.017	0.0464
2nd 15 specimens	1.010	0.0414
All 30 specimens	1.014	0.0434
Double-edge deep circular notch		
1st 15 specimens	1.024	0.0515
2nd 15 specimens	0.995	0.0432
All 30 specimens	1.010	0.0489
Double-edge semicircular notch		
1st 15 specimens	1.027	0.0461
2nd 15 specimens	0.988	0.0490
All 30 specimens	1.008	0.0509

Nominal Breaking stress at
minimum width

1 1/2 by 2 inch specimens

Specimen No.	Double Crack (lb/in ²)	Double 1 1/8 by 1 1/8 (lb/in ²)	Double 1/2 circle (lb/in ²)
1	6038	6796	6850
2	6201	6905	6742
3	6038	6958	7013
4	5875	7284	7068
5	6254	6688	7094
6	6146	6525	7338
7	6200	7175	7500
8	6011	6742	7067
9	6200	6417	6742
10	6255	7175	7392
11	6309	6823	6959
12	6363	6959	7121
13	6255	6580	7500
14	6417	7013	7230
15	6417	6959	7230
16	6257	6752	7246
17	6092	6642	7137
18	6257	6587	6917
19	6092	6642	6862
20	6422	6752	7247
21	6092	6807	6697
22	6422	6862	6807
23	6477	6972	6917
24	6037	7192	7357
25	6587	7082	7192
26	6202	6972	6972
27	6532	6752	7137
28	6257	6752	7142
29	6147	6807	7027
30	6532	6752	6752

Nominal breaking stress at
minimum width

4 1/2 by 6 inch specimens

Specimen No.	Double Crack ($\frac{lb}{in^2}$)	Double $1\frac{1}{8}$ or $1\frac{1}{2}$ ($\frac{lb}{in^2}$)	Double Half Circle ($\frac{lb}{in^2}$)
1	6356	6484	6738
2	5975	6629	6811
3	6538	6847	6411
4	6411	6393	6847
5	6102	6847	6811
6	6138	6956	6938
7	6048	6938	6992
8	6138	6520	6682
9	5787	6320	6938
10	5866	6665	6865
11	6211	7010	7029
12	5939	6665	6992
13	6411	6920	6901
14	6302	6593	6847
15	6029	6901	7265
16	6120	7247	6611
17	6338	6702	7138
18	6411	6956	7119
19	6193	6974	7210
20	6247	7101	6992
21	6175	6665	7138
22	6120	6847	7537
23	6302	6847	7265
24	6302	6683	7210
25	6211	6665	7047
26	6356	6792	7210
27	5939	6938	6883
28	6393	6974	7210
29	6193	6611	7392
30	6266	6883	6847

**A BIBLIOGRAPHY OF STRENGTH SIZE
EFFECTS FOR CRACKED SPECIMENS**

G.B. Sinclair

SM 85-10

May 1985

Department of Mechanical Engineering
Carnegie Institute of Technology
Carnegie-Mellon University
Pittsburgh, Pennsylvania

A BIBLIOGRAPHY OF STRENGTH SIZE EFFECTS FOR CRACKED SPECIMENS

PREFACE

The references gathered here are with a view to providing strength test data for cracked or sharp notch specimens which have their dimensions in the plane of the crack scaled. The first table lists all sources with such in-plane scaling which are used in a survey of this type of data^{*}; the remaining tables are all references with size-effect strength data consulted in the course of compiling Table I but not included therein for various reasons. For Table II, most references either could not be shown to have *all* dimensions effectively scaled or presented data already contained in the references of Table I. For Table III, most results in references were affected to some extent by out-of-plane or thickness effects, since either specimens did not have their thicknesses scaled in concert with their in-plane dimensions or did not consistently maintain a state of plane stress or strain (there are some references, however, which are also listed in Table I because they had both in-plane and thickness size effects). For Table IV, all sources either involved specimens with notches whose acuity was not judged to be sufficient to qualify as cracks or entailed specimens with no notches whatsoever. It should be emphasized that neither Table III nor Table IV approach being comprehensive surveys of their data types - they are simply the test results of their respective natures encountered in assembling Table I. Each table is arranged alphabetically by author (s).

Acknowledgements - The assistance of A. Chambers and R. Pieri in checking citations in this bibliography is much appreciated. The financial support of this study by the Air Force Office of Scientific Research is gratefully acknowledged.

^{*}G.B. Sinclair and A.E. Chambers, "Strength size effects and fracture mechanics: What does the data say?" Report SM 85-12, Dept. of Mechanical Engineering, Carnegie-Mellon University (1985).

I. IN-PLANE SIZE EFFECTS ON STRENGTH: CRACKED OR SHARP NOTCH SPECIMENS

- N.J. I. Adams and H.G. Munro, A single test method for evaluation of the J integral as a fracture parameter. *Engng Fracture Mech.* 6, 119-132 (1974).
- Y. Akita, Scale effects in notch brittleness. *Weld. Res. Suppl.* 32, 475s-480s (1953).
- W.R. Andrews, V. Kumar and M.M. Little, Small-specimen brittle-fracture toughness testing. *Fracture Mechanics: Thirteenth Conference, ASTM STP 743*, 576-598 (1981).
- G. Argy, P.C. Paris, and F. Shaw, Fatigue crack growth and fracture toughness of 5083-0 aluminum alloy. *Properties of Materials for Liquefied Natural Gas Tankage, ASTM STP 579*, 96-137 (1975).
- S. Banerjee, Influence of specimen size and configuration on the plastic zone size, toughness and crack growth. *Engng Fracture Mech.* 15, 343-390 (1981).
- M.N. Bassim and T.R. Hsu, Fracture behavior of coal. *Fracture Problems and Solutions in the Energy Industry, Proc. Fifth Canadian Fracture Conf., Winnipeg, Canada*, 239-247 (1982).
- A.D. Batte, W.S. Blackburn, A. Elsander, T.K. Hellen and A.D. Jackson, A comparison of the J^* integral with other methods of post yield fracture mechanics. *Int. J. Fracture* 21, 49-66 (1983).
- J.A. Begley and J.D. Landes, The J-integral as a fracture criterion. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 1-20 (1972).
- J.A. Begley and P.R. Toolin, Fracture toughness and fatigue crack growth rate properties of Ni-Cr-Mo-V steel sensitive to temper embrittlement. *Int. J. Fracture* 9, 243-253 (1973).
- R.M. Bonesteel, Fracture of thin sections containing surface cracks. *Engng Fracture Mech.* 5, 541-554 (1973).
- A. Boodberg, H.E. Davis, E.R. Parker and G.E. Troxell, Causes of cleavage fracture in ship plate - tests of wide notched plates. *Weld. Res. Suppl.* 27, 186s-199s (1948).
- F.J. Bradshaw and C. Wheeler, The crack resistance of some aluminum alloys and the prediction of thin section failure. Rep. 73191, R. Aircr. Establ, Farnborough (1974).
- W.F. Brown, Jr., J.D. Lubahn and L.J. Ebert, Effects of section size on the static notch bar tensile properties of mild steel plate. *Weld. Res. Suppl.* 26, 554s-559s (1947).
- W.F. Brown, Jr. and J.E. Srawley, Plane strain crack toughness testing of high strength metallic metals. *Plane Strain Crack Toughness Testing of High Strength Metallic Materials, ASTM STP 410*, 1-65 (1966).
- F.E. Buresch, Fracture toughness testing of alumina. *Fracture Mechanics Applied to Brittle Materials, ASTM STP 678*, 151-165 (1979).

C.M. Carman, D.F. Armiento and H. Markus, Crack resistance properties of high strength aluminum alloys. *Proc. First Int. Conf. Fracture*, Sendai, Japan, 2, 995-1038 (1965).

G.G. Chell and A. Davidson, A post-yield fracture mechanics analysis of single edge notched tension specimens *Mater. Sci. Engng* 24, 45-52 (1976).

G.G. Chell and R.S. Gates, A study of failure in the post yield regime using single edge-notched tension specimens *Int. J. Fracture* 14, 233-247 (1978).

G.G. Chell and G.M. Spink, A post yield fracture mechanics analysis of three-point bend specimens and its implications to fracture toughness testing. *Engng Fracture Mech.* 9, 101-121 (1977).

J.L.Christian, W.E. Witzell and A. Hurlich, Evaluation of the effects of specimen configuration and testing variables on crack propagation properties. *Adv. cryogen. Engng* 10, 86-101 (1964).

H.P. Chu, The notch-bend strength of titanium, aluminum, and copper-base alloys in heavy sections. *J. bas. Engng, Trans. Am. Soc. mech. Engrs* 91, 830-840 (1969).

G.A. Clarke, W.R. Andrews, P.C. Paris, and D.W. Schmidt, Single specimen tests for J_{IC} determination. *Mechanics of Crack Growth, ASTM STP 590*, 27-42 (1976).

L.S. Costin, Static and dynamic fracture behavior of oil shale. *Fracture Mechanics Method for Ceramics, Rocks, and Concrete, ASTM STP 745*, 169-184 (1981).

W.J. Crichlow, *The Ultimate Strength of Damaged Structure, Analysis Methods with Correlating Test Data*. Full scale testing of Aircraft Structures, International Series of Monographs in Aeronautics and Astronautics, Pergamon Press (1961).

T.S. DeSisto, F.L. Carr, and F.R. Larson, Influence of section size on mechanical properties and fracture toughness of 7075-T6 aluminum, 6A1-6V-2Sn titanium, and AISI 4340 steel. *Proc. Am. Soc. Test. Mater.* 63, 768-779 (1963).

A. Elsender, A. Poynton and D. Batte, Private communication (1977).

J. Eschweiler and D. Munz, Comparison of fracture toughness of aluminum alloys from short bar and compact specimens. *Int. J. Fracture* 20, R131-R133 (1982).

W.G. Ferguson and M.N. Sargisson, Fracture toughness of Comsteel En25. *Engng Fracture Mech.* 5, 499-508 (1973).

R.G. Forman, Experimental program to determine effect of crack buckling and specimen dimensions on fracture toughness of thin sheet materials. Report AFFDL-TR-65-146, Air Force Flight Dynamics Laboratory, Dayton, Ohio (1966).

A. Frediani, An evaluation of the reliability of fracture mechanics methods. *Engng Fracture Mech.* 14, 289-322 (1981).

C.N. Freed, A.M. Sullivan and J. Stoop, Influence of dimensions of the center-cracked

tension specimen on K_{IC} . *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 98-113 (1972).

W.W. Gerberich, P.L. Hemmings, V.F. Zackay, and E.R. Parker, Interactions between crack growth and strain-induced transformation. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 288-305 (1969).

H.D. Greenberg, E.T. Wessel and W.H. Pryle, Fracture toughness of turbine-generator rotor forgings. *Engng Fracture Mech.* 1, 653-674 (1970).

A. W. Gunderson, Size effects for compact specimens made of a beta-processed mill-annealed plate of Ti-6Al-4V. Air Force Mater. Lab. Rep. AFML-MXE 73-3, Wright-Patterson AFB (1973).

G.S. Hall, S.R. Seagle and H.B. Bomberger, Effect of specimen width on fracture toughness of Ti-6Al-4V plate. *Toughness and Fracture Behaviour of Titanium, ASTM STP 651*, 227-245 (1978).

A.M. Hasofer, A statistical theory of the brittle fracture of steel. *Int. J. Fracture Mech.* 4, 439-452 (1968).

J.R. Hawthorne and T.R. Mager, Relationship between Charpy V and fracture mechanics K_{IC} assessments of A533-B class 2 pressure vessel steel. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 151-163 (1972).

R.H. Heyer and D.E. McCabe, Plane-stress fracture toughness testing using a crack-line-loaded specimen. *Engng Fracture Mech.* 4, 393-412 (1972).

G.H. Hilton, Evaluation of Ti-6Al-4V for specification requirements. *Fracture Prevention and Control*, Am. Soc. Metals, 181-197 (1974).

F.H. Huang and D.S. Gelles, Influence of specimen size and microstructure on the fracture toughness of a martensitic stainless steel. *Engng Fracture Mech.* 19, 1-20 (1984).

C.M. Hudson and P.E. Lewis, NASA-Langley research center's participation in a round-robin comparison between some current crack-propagation prediction methods. *Part-Through Crack Fatigue Life Prediction, ASTM STP 687*, 113-128 (1979).

K. Ikeda, M. Aoki, H. Kikuchi, U. Schieferstein and C. Berger, Fracture toughness of turbine rotor shaft and validity criterion for K_{IC} . *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 687-697 (1977).

M.H. Jones and W.F. Brown, Jr., The influence of crack length and thickness in plane strain fracture toughness tests. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 63-91 (1970).

M.H. Jones, R.T. Bubsey and W.F. Brown, Jr., Sharply notched cylindrical tension specimen for screening plane-strain fracture toughness. Part I: Influence of

fundamental testing variables on notch strength. *Developments in Fracture Mechanics Test Methods Standardization, ASTM STP 632*, 115-134 (1977).

H.-J. Kaiser and K.E. Hagedorn, Prediction of maximum load values of different sized CT-specimens using the J-R-curve concept. *Fracture and the Role of Microstructure, Proc. Fourth European Conf. Fracture*, Leoben, Austria, 1, 76-83 (1982).

M.F. Kaplan, Crack propagation and the fracture of concrete. *J. Am. Concr. Inst.* 58, 591-610 (1961).

J.G. Kaufman, Fracture toughness testing, including screening and quality control testing, in the aluminum industry. *Fracture Prevention and Control*, Am. Soc. Metals, 121-142 (1974).

J.G. Kaufman, Sharp-notch tension testing of thick aluminum alloy plate with cylindrical specimens. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 82-97 (1972).

J.G. Kaufman and F.G. Nelson, More on specimen size effects in fracture toughness testing. *Fracture Toughness and Slow Stable Cracking, ASTM STP 559*, 74-85 (1974).

J.G. Kaufman, G.T. Sha, R.F. Kohm, and R.J. Bucci, Notch-yield ratio as a quality control index for plane-strain fracture toughness. *Cracks and Fracture, ASTM STP 601*, 169-190 (1976).

H.P. Keller and D. Munz, Effect of specimen size on J-integral and stress-intensity factor at the onset of crack extension. *Flaw Growth and Fracture, ASTM STP 631*, 217-231 (1977).

E.P. Klier and V. Weiss, The effect of section size on the notch strength and fracture development in selected structural metals. *Proc. Am. Soc. Test. Mater.* 61, 1307-1323 (1961).

H. Kobayashi, K. Hirano, H. Nakamura and H. Nakazawa, A fractographic study on evaluation of fracture toughness. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 583-592 (1977).

J.M. Krafft, A.M. Sullivan and R.W. Boyle, Effect of dimensions on fast fracture instability of notched sheets. *Proc. Crack Propagation Symposium*, Cranfield, U.K., 8-28 (1961).

A.J. Krasowsky, Yu. A. Kashtalyan and V.N. Krasiko, Brittle-to-ductile transition in steels and the critical transition temperature. *Int. J. Fracture* 23, 297-315 (1983).

P. Kuhn, Residual tensile strength in the presence of through cracks or surface cracks. *Natn. Aeronaut. Space Adm. Tech. Note NASA TN D-5432* (1970).

P. Kuhn, Strength calculations for sheet metal parts with cracks. *Mater. Res. Stands* 8, 9/21-26 (1968).

R.L. Lake, What R-curves can tell us about specimen size effects in the K_{IC} test. *Mechanics of Crack Growth, ASTM STP 590*, 208-218 (1976).

- J.D. Landes and J.A. Begley, Test results from J-integral studies: an attempt to establish a J_{IC} testing procedure. *Fracture Analysis, ASTM STP 560*, 170-186 (1974).
- M.H. Lewis and G. Smith, Fracture mechanisms in Si-Al-O-N ceramics. *Proc. Fourth Int. Conf. Fracture, Waterloo, Canada*, 3, 867-874 (1977).
- W.A. Logsdon, An evaluation of crack growth and fracture properties of AISI 403 modified 12Cr stainless steel. *Engng Fracture Mech.* 7, 23-40 (1975).
- W.A. Logsdon, Elastic plastic (J_{IC}) fracture toughness values: their experimental determination and comparison with conventional linear elastic (K_{IC}) fracture toughness values for five materials. *Mechanics of Crack Growth, ASTM STP 590*, 43-60 (1976).
- W.A. Logsdon and J.A. Begley, Upper shelf temperature dependence of fracture toughness for four low to intermediate strength ferritic steels. *Engng Fracture Mech.* 9, 461-470 (1977).
- J.D. Lubahn, Effect of section size on fracturing. *Proc. 1955 Sagamore Res. Conf., Syracuse, N.Y.*, 143-161 (1955).
- J.D. Lubahn, Experimental determination of energy release rate for notch bending and notch tension. *Proc. Am. Soc. Test. Mater.* 59, 885-913 (1959).
- J.D. Lubahn and S. Yukawa, Size effects in slow notch-bend tests of a nickel-molybdenum-vanadium steel. *Proc. Am. Soc. Test. Mater.* 58, 661-676 (1958).
- B.D. Macdonald, Fracture resistance of a structural steel as characterized by the strength of the plastic stress singularity. *Int. J. Fracture* 20, 179-194 (1982).
- K. Markstrom, Experimental determination of J_C data using different types of specimen. *Engng Fracture Mech.* 9, 637-646 (1977).
- K. Markstrom, On fracture toughness and its size dependence for steels showing thickness delamination. *Engng Fracture Mech.* 4, 593-603 (1972).
- A.J. McEvily, Jr., W. Illg and H.F. Hadrath, Static strength of aluminum alloy specimens containing fatigue cracks. *Natn. Aeronaut. Space Adm. Tech. Note NASA TN 3816* (1956).
- K.R. McKinney and R.W. Rice, Specimen size effects in fracture toughness testing of heterogeneous ceramics by the notch beam method. *Fracture Mechanics Methods for Ceramics, Rocks, and Concrete, ASTM STP 745*, 118-126 (1981).
- I. Milne and P.J. Worthington, The fracture toughness of a low alloy pressure vessel steel in the post yield regime. *Mater. Sci. Engng* 26, 185-193 (1976).
- E.M. Morozov, Some problems in experimental fracture mechanics. *Engng Fracture Mech.* 13, 541-561 (1980).
- H.G. Munro and N.J.I. Adams, Fatigue and fracture of a 200 ksi grade maraging steel proposed for use in military bridging. *Engng Fracture Mech.* 4, 705-715 (1972).

- D. Munz, Minimum specimen size for the application of linear-elastic fracture mechanics. *Elastic-Plastic Fracture, ASTM STP 668*, 406-425 (1979).
- D. Munz, K.H. Galda, and F. Link, Effect of specimen size on fracture toughness of a titanium alloy. *Mechanics of Crack Growth, ASTM STP 590*, 219-234 (1976).
- N. Murayama, A.W. Pense, and R.D. Stout, The fracture toughness of cryogenic steels. *Adv. cryogen. Engng* 22, 27-34 (1977).
- B.K. Neale, An investigation into the effect of thickness on the fracture behaviour of compact tension specimens. *Int. J. Fracture* 14, 203-212 (1978).
- F.G. Nelson and J.G. Kaufman, Fracture toughness of plain and welded 3-in-thick aluminum alloy plate. *Progress in Flaw Growth and Fracture Toughness Testing, ASTM STP 536*, 350-376 (1973).
- F.G. Nelson, P.E. Schilling and J.G. Kaufman, The effect of specimen size on the results of plane-strain fracture-toughness tests. *Engng Fracture Mech.* 4, 33-50 (1972).
- J.C. Newman, Jr., Fracture analysis of various cracked configurations in sheet and plate materials. *Properties Related to Fracture Toughness, ASTM STP 605*, 104-123 (1976).
- T.W. Orange, Fracture toughness of wide 2014-T6 aluminum sheet at -320°F. Natn. Aeronaut. Space Adm. Tech. Note NASA TN D-4017 (1967).
- E.R. Parker, The effect of section size on the fracture strength of mild steel. *Fracturing of Metals*, ASM, Cleveland, Ohio, 82-89 (1948).
- J.S. Pascover, M. Hill, and S.J. Matas, The application of fracture toughness testing to the development of a family of alloy steels. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 310-325 (1965).
- W.F. Payne, Incorporation of fracture information in specifications. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 357-371 (1965).
- P.K. Poulouse, D.L. Jones and H. Liebowitz, A comparison of the geometry dependence of several nonlinear fracture toughness parameters. *Engng Fracture Mech.* 17, 133-151 (1983).
- P.K. Poulouse and H. Liebowitz, A study of the size-effect on plastic energy dissipation and toughness in 2024-T3 aluminum alloy sheets. *Engng Fracture Mech.* 20, 179-185 (1984).
- S.K. Putatunda and S. Banerjee, Effect of size on plasticity and fracture toughness. *Engng Fracture Mech.* 19, 507-529 (1984).
- A.J. Repko, M.H. Jones, and W.F. Brown, Jr., Influence of sheet thickness on sharp-edge-notch properties of a β titanium alloy at room and low temperatures. *Symp. on Evaluation of Metallic Materials in Design for Low-Temperature Service, ASTM STP 302*, 213-229 (1961).

S.T. Rolfe and S.R. Novak, Discussion: M.H. Jones and W.F. Brown, Jr., Closure. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 92-95, 97-101 (1970).

S.T. Rolfe and S.R. Novak, Slow-bend K_{IC} testing of medium-strength high-toughness steels. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 124-159 (1970).

J. Royer, J.M. Tissot, A. Pelissier-Tanon, P. LePoac, and D. Miannay, J-integral determinations and analyses for small test specimens and their usefulness for estimating fracture toughness. *Elastic-Plastic Fracture, ASTM STP 668*, 334-357 (1979).

G. Sachs, B.B. Muvdi, and E.P. Klier, Design properties of high strength steels in the presence of stress concentrations, Part I - Dependence of tension and notch tension properties of high strength steels on a number of factors. Tech. Rep. 56-395, I, Wright Air Development Center, Dayton Ohio (1956).

R.A. Schmidt, Fracture-toughness testing of limestone. *Expl Mech.* 16, 161-167 (1976).

R.A. Schmidt and T.J. Lutz, K_{IC} and J_{IC} of westerly granite - effects of thickness and in-plane dimensions. *Fracture Mechanics Applied to Brittle Materials, ASTM STP 678*, 166-182 (1979).

W.L. Server and R.A. Wullaert, The use of small specimen strength ratio for measuring fracture toughness. *Engng Fracture Mech.* 11, 477-486 (1979).

W.L. Server, R.A. Wullaert, and J.W. Sheckherd, Evaluation of current procedures for dynamic fracture-toughness testing. *Flaw Growth and Fracture, ASTM STP 631*, 446-461 (1977).

W.O. Shabbitts, W.H. Pryle and E.T. Wessel, Heavy section fracture toughness properties of A533, Grade-B, Class-1 steel plate and submerged arc weldment. HSST Tech. Rep. 6, WCAP-7414, Westinghouse Electric Corporation, Pittsburgh, Pennsylvania (1969).

J.L. Shannon, Jr., J.K. Donald and W.F. Brown, Jr., Heavy-section fracture toughness screening specimen. *Developments in Fracture Mechanics Test Methods Standardization, ASTM STP 632*, 96-114 (1977).

P.E. Shearin, A. E. Ruark and R.M. Trimble, Size effects in steels and other metals from slow notch bend tests. *Proc. Fracturing of Metals Seminar*, Chicago, Illinois, 167-188 (1948).

T.T. Shih and G.A. Clarke, Effects of temperature and frequency on the fatigue crack growth rate properties of a 1950 vintage CrMOV rotor material. *Fracture Mechanics, ASTM STP 677*, 125-143 (1979).

W. Soete, An experimental approach to fracture initiation in structural steels. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 1, 775-804 (1977).

Special ASTM Committee, Fracture testing of high-strength sheet materials (Third Report). *Mater. Res. Stands* 1, 877-885 (1961).

Special ASTM Committee, Screening tests for high-strength alloys using sharply notched cylindrical specimens (Fourth Report). *Mater. Res. Stands* 2, 196-203 (1962).

Special ASTM Committee, Progress in measuring fracture toughness and using fracture mechanics (Fifth Report). *Mater. Res. Stands* 4, 107-119 (1964).

E.A. Steigerwald, Crack toughness measurements of high-strength steels. *Review of Developments in Plane Strain Fracture Toughness Testing*, ASTM STP 463, 102-123 (1970).

A.M. Sullivan, C.N. Freed and J. Stoop, Comparison of R-curves determined from different specimen types. *Fracture Toughness Evaluation by R-Curve Methods*, ASTM STP 527, 85-104 (1973).

A.M. Sullivan and J. Stoop, Further aspects of fracture resistance measurement on thin sheet material: yield stress and crack length. *Fracture Toughness and Slow-Stable Cracking*, ASTM STP 559, 99-110 (1974).

J.D.G. Sumpter, Use of scale models to study ductile tearing. *Int. J. Fracture* 23, R121-R124 (1983).

D. Sunamoto, M. Satoh, T. Funada and M. Tomimatsu, Specimen size effect on J-integral fracture toughness. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 267-272 (1977).

H.R. Thomas and D.F. Windenburg, A study of slotted tensile specimens for evaluating the toughness of structural steel. *Weld. Res. Suppl.* 27, 209s-215s (1948).

D.Y. Wang, Plane-stress fracture toughness and fatigue-crack propagation of aluminum alloy wide panels. *Progress in Flaw Growth and Fracture Toughness Testing*, ASTM STP 536, 334-349 (1973).

D.Y. Wang and D.E. McCabe, Investigation of R-curve using comparative tests with center-cracked-tension and crack-line-wedge-loaded specimens. *Mechanics of Crack Growth*, ASTM STP 590, 169-193 (1976)).

S. Wei, Z. Tingshi, G. Daxing, L. Dunkang, L. Poliang and Q. Xiaoyun, Fracture toughness measurement by a cylindrical specimen with ring-shaped crack. *Engng Fracture Mech.* 16, 69-82 (1982).

V. Weiss, G. Schaeffer and J. Fehling, Effect of section size on notch strength. *J. bas. Engng, Trans. Am. Soc. mech. Engrs Ser. D* 88, 675-681 (1966).

V. Weiss, J. Sessler, P. Packman and G. Sachs, The effect of several geometrical variables on the notch tensile strength of 4340 steel sheet heat treated to three strength levels. Wright Air Development Div. Tech. Rep. 60-310, Wright-Patterson AFB (1960).

A.A. Wells, The geometrical size effect in notch brittle fracture. *Trans. NE.Cst Instn Engrs Shipbltrs* 71, 277-290 (1955).

E.T. Wessel, State of the art of the WOL specimen for K_{IC} fracture toughness testing. *Engng Fracture Mech.* 1, 77-103 (1968).

E.T. Wessel, W.G. Clark, Jr. and W.H. Pryle, Fracture mechanics technology applied to heavy section steel structures. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 825-850 (1969).

J.G. Williams and P.D. Ewing, Crack propagation in plates and shells subjected to bending and direct loading. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 119-130 (1969).

W.M. Wilson, R.A. Hechtman and W.H. Bruckner, Cleavage fracture of ship plates as influenced by size effect. *Weld. Res. Suppl.* 27, 200s-207s (1948).

D.H. Winne and B.M. Wundt, Application of the Griffith-Irwin theory of crack propagation to the bursting behavior of disks, including analytical and experimental studies. *Trans. Am. Soc. mech. Engrs* 80, 1643-1655 (1958).

F.J. Witt, Fracture toughness parameters obtained from single small specimen tests. Rep-WCAP-9397, Westinghouse Electric Corporation, Pittsburgh, Pennsylvania (1978).

P.J. Worthington, Private communication.

S. Yukawa, Temperature and microstructure dependence of size effects in notched bend tests of some alloy steels. *Trans. Am. Soc. Metals* 53, 871-881 (1961).

S. Yukawa and J.G. McMullin, Effects of specimen size and notch acuity on the brittle fracture strength of a heat-treated steel. *J. bas. Engng., Trans. Am. Soc. mech. Engrs Ser. D*, 83, 541-544 (1961).

S. Yusuff, Effects of yielding and size upon fracture of plates and pressure cylinders. *Int. J. Fracture Mech.* 8, 129-138 (1972).

S. Yusuff, Fracture phenomena in metal plates. *Aircr. Engng* 34, 140-148 (1962).

C. Zhen-Yuan, Exploring the fracture toughness K_{IE} and K_{IC} of a medium-strength steel plate using the surface-flaw test. *Engng Fracture Mech.* 13, 775-789 (1980).

R.E. Zinkham, Anisotropy and thickness effects in fracture of 7075-T6 and -T651 aluminum alloy. *Engng Fracture Mech.* 1, 275-289 (1968).

R.E. Zinkham and R.J. Baughan, Screening for fracture toughness using the sharp notch tension test. *Engng Fracture Mech.* 9, 147-154 (1977).

II. IN-PLANE SIZE EFFECTS ON STRENGTH: CRACKED OR SHARP NOTCH SPECIMENS

N.J. Adams, Influence of configuration on R-curve shape and G_c when plane stress conditions prevail. *Cracks and Fracture, ASTM STP 601*, 330-345 (1976).

N.P. Allen, Studies of the brittle fracture of steel during the past twenty years. *Proc. First Int. Conf. Fracture*, Sendai, Japan, 2, 941-971 (1965).

W.F. Barclay, Private communication.

C. Bathias, Application of fracture mechanics to aluminum alloys selection. *Engng Fracture Mech.* 10, 267-282 (1978).

R.J. Bucci, P.C. Paris, J.D. Landes and J.R. Rice, J-integral estimation procedures. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 40-69 (1972).

A.J. Carlsson and K.M. Markstrom, Some aspects of non-linear fracture mechanics. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 1, 683-693 (1977).

C.M. Carman, Crack resistance properties of high-strength aluminum alloys. Rep. R-1789, Frankford Arsenal, Philadelphia, PA (1965).

A. Carpinteri, Notch sensitivity in fracture testing of aggregative materials. *Engng Fracture Mech.* 16, 467-481 (1982).

G.G. Chell and I. Milne, A new approach to the analysis of invalid fracture toughness data. *Int. J. Fracture* 12, 164-166 (1976).

E.P. Cox and F.V. Lawrence, Jr., Ductile fracture behaviour of wrought steels. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 529-591 (1980).

D.A. Curry, I. Milne and K.N. Akhurst, Scatter in the cleavage fracture toughness of A533B plate. *Proc. Fourth European Conf. Fracture*, Leoben, Austria 1, 236-243 (1982).

S. Gagger and L.J. Broutman, Fracture toughness of random glass fiber epoxy composites: an experimental investigation. *Flaw Growth and Fracture, ASTM STP 631*, 310-330 (1977).

S.J. Garwood, Measurement of crack growth resistance of A533B wide plate tests. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 271-295 (1980).

R.S. Gates, Some effects of specimen geometry on crack propagation and arrest. *Crack Arrest Methodology and Applications, ASTM STP 711*, 146-160 (1980).

A.A. Griffith, The phenomena of rupture and flow in solids. *Phil. Trans. R. Soc. (Lond.)* 221A, 163-198 (1920).

G.T. Hahn, M. Sarrate and A.R. Rosenfield, Criteria for crack extension in cylindrical pressure vessels. *Int. J. Fracture Mech.* 5, 187-210 (1969).

T.C. Harrison and G.D. Fearnehough, The influence of specimen dimensions on measurements of the ductile crack opening displacement. *Int. J. Fracture Mech.* 5, 383-349 (1969).

- K. Ikeda and H. Kihara, Brittle fracture strength of welded structures. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 851-867 (1969).
- K. Ikeda, Y. Miyagi, M. Aoki and T. Shirakura, Fracture strength of thick 5083-0 aluminum alloy for LNG storage tanks. *Adv. cryogen. Engng* 24, 166-174 (1978).
- G.R. Irwin, Dimensional and geometric aspects of fracture. *Fracture of Engineering Materials*, Ch. 11, Am. Soc. Metals, Metals Park, Ohio (1964).
- G.R. Irwin, Effects of size and shape on the fracture of solids. *Properties of Crystalline Solids, ASTM STP 283*, 118-122 (1961).
- G.R. Irwin, Fracture mode transition for a crack traversing a plate. *J. bas. Engng, Trans. Am. Soc. mech. Engrs Ser. D* 82, 417-425 (1960).
- L.A. James, Specimen size considerations in fatigue crack growth rate testing. *Fatigue Crack Growth Measurement and Data Analysis, ASTM STP 738*, 45-57 (1981).
- F.A. Johnson and J.C. Radon, Mechanical and metallurgical aspects of fracture behaviour of an Al-alloy. *Int. J. Fracture Mech.* 8, 21-36 (1972).
- R.E. Jones, Tensile, fracture toughness and crack growth properties of a roll-extruded HP 9Ni-4Co-25C steel alloy. *Engng Fracture Mech.* 5, 107-117 (1973).
- J.G. Kaufman, Discussion. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 208-209 (1965).
- J.G. Kaufman, Progress in fracture testing of metallic materials. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 3-21 (1970).
- J.G. Kaufman and H.Y. Hunsicker, Fracture toughness testing at ALCOA research laboratories. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 290-308 (1965).
- J.G. Kaufman and R.A. Kelsey, Fracture toughness and fatigue properties of 5083-0 plate and 5183 welds for liquified natural gas applications. *Properties of Materials for Liquified Natural Gas Tankage, ASTM STP 579*, 138-158 (1975).
- J.G. Kaufman, F.G. Nelson, Jr. and M. Holt, Fracture toughness of aluminum alloy plate determined with center-notch tension, single-edge-notch tension and notch-bend tests. *Engng Fracture Mech.* 1, 259-774 (1968).
- J.F. Kiefner, W.A. Maxey, R.J. Eiber, and A.R. Duffy, Failure stress levels of flaws in pressurized cylinders. *Progress in Flaw Growth and Fracture Toughness Testing, ASTM STP 536*, 461-481 (1973).
- H. Kihara, K. Ikeda and H. Iwanga, Brittle fracture initiation of line pipe. Docum. X-371-66, Int. Inst. Weld., Delft, Holland (1966).
- M.O. Lai and W.G. Ferguson, The inadequacy of the plane-strain fracture toughness test requirements. *Engng Fracture Mech.* 13, 285-292 (1980).

- E.Z. Lajtai, Brittle fracture in compression. *Int. J. Fracture* 10, 525-536 (1974).
- J.D. Landes, Ductile and cleavage fracture characterizations in the transition region for steels. Research Rep. 79-1D3-JINTF-R2, Westinghouse Electric Corporation, Pittsburgh, Pennsylvania (1979).
- J.D. Landes and J.A. Begley, Experimental methods for elastic-plastic and post yield fracture toughness measurements. Research Rep. 77-1D3-JINTF-PI, Westinghouse Electric Corporation, Pittsburgh, Pennsylvania (1977).
- J.D. Landes and J.A. Begley, Recent developments in J_{IC} testing. *Developments in Fracture Mechanics Test Methods Standardization, ASTM STP 632*, 57-81 (1977).
- J.D. Landes and J.A. Begley, The effect of specimen geometry on J_{IC} . *Fracture Toughness, Proceedings of the 1971 Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 24-39 (1972).
- J.D. Landes and D.H. Shaffer, Statistical characterization of fracture in the transition region. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 368-382 (1980).
- J. Lebey and R. Roche, Crack propagation initiation in ductile structures. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 47-57 (1977).
- H.W. Liu, Thickness effects on fracture criteria. *Fracture Mechanics of Ductile and Tough Materials and Its Applications to Energy Related Structures*, 189-198 (1981).
- D.E. McCabe and H.A. Ernst, A perspective on R-curves and instability theory. *Fracture Mechanics: Fourteenth Symposium - Volume I: Theory and Analysis, ASTM STP 791*, 561-584 (1983).
- I. Milne, Assessment of failures beyond the linear elastic regime. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 419-426 (1977).
- I. Milne and D.A. Curry, The effect of triaxiality on ductile-cleavage transitions in a pressure vessel steel. *Proc. Third Colloquium Fracture*, London, 39-47 (1980).
- S. Mindess and J.S. Nadeau, Effect of notch width on K_{IC} for mortar and concrete. *Cem. Concr. Res.* 6, 529-534 (1976).
- T. Nakazawa, S. Suzuki, T. Sunami and Y. Sogo, Application of high-purity ferritic stainless steel plates to welded structures. *Toughness of Ferritic Stainless Steels, ASTM STP 706*, 99-122 (1980).
- J.C. Newman, Jr., Fracture of cracked plates under plane stress. *Engng Fracture Mech.* 1, 137-154 (1968).
- S.R. Novak, Resistance to plane-stress fracture (R-curve behavior) of A572 structural steel. *Mechanics of Crack Growth, ASTM STP 590*, 235-242 (1976).
- J.O. Outwater, M.C. Murphy, R.G. Kumble and J.T. Berry, Double torsion technique as a universal fracture toughness test method. *Fracture Toughness and Slow-Stable Cracking, ASTM STP 559*, 127-138 (1974).

G.W. Parry and L. Lazzeri, The application of fracture mechanics to the assessment of failure of cylindrical pressure vessels under yielding conditions. *Engng Fracture Mech.* 1, 519-537 (1969).

A. Penelon, M.N. Bassim, and J.M. Dorlot, Variation of fracture toughness with specimen geometry and loading conditions in welded low alloy steels. *Fracture Mechanics, ASTM STP 677*, 449-462 (1979).

A.W. Pense, R.D. Stout, and B.R. Somers, Fracture toughness of cryogenic alloys. *Adv. cryogen. Engng* 24, 548-559 (1978).

R.W. Peters and P. Kuhn, Bursting strength of unstiffened pressure cylinders with slits. Natn. Aeronaut. Space Adm. Tech. Note NASA TN 3993, Langley Res. Cent. (1957).

D.T. Read and R.P. Reed, Effects of specimen thickness on fracture toughness of an aluminum alloy. *Int. J. Fracture* 13, 201-213 (1977).

P.C. Riccardella and J.L. Swedlow, A combined analytical-experimental fracture study. *Fracture Analysis, ASTM STP 560*, 134-154 (1974).

R. Roberts, G.V. Krishna and G.R. Irwin, Fracture behaviour of bridge steels. *Flaw Growth and Fracture, ASTM STP 631*, 267-284 (1977).

G. Sachs, J.D. Lubahn and L.J. Ebert, The effects of notches of varying depth on the strength of heat treated alloy steels. *Trans. Am. Soc. Metals* 34, 517-539 (1944).

F.R. Schwartzberg, A review of cryogenic fracture toughness behavior. *Adv. cryogen. Engng* 12, 458-472 (1967).

W. Seidl, Method of specific potential energy. *Proc. Int. Conf. Analytical Experimental Fracture Mech.*, Rome, Italy, 815-822 (1980).

D.K. Shetty and A.V. Virkar, Determination of the useful range of crack lengths in double torsion specimens. *J. Am. Ceram. Soc.*, 61, 93-94 (1978).

T.T. Shih and J. Opoku, Application of fracture mechanics to ceramic materials - a state-of-the-art review. *Engng Fracture Mech.* 12, 479-498 (1979).

A. Shukla and W.L. Fournery, Influence of specimen size and stress field on energy loss during a fracture event. *Fracture Mechanics: Fourteenth Symposium - Volume I: Theory and Analysis, ASTM STP 791*, 51-64 (1983).

A.M. Sullivan, J. Stoop and C.N. Freed, Influence of sheet thickness upon the fracture resistance of structural aluminum alloys. *Progress in Flaw Growth and Fracture Toughness Testing, ASTM STP 536*, 323-333 (1973).

M.G. Vassilaros, J.A. Joyce and J.P. Gudas, Effects of specimen geometry on the J_I-R curve for ASTM A533B steel. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 251-270 (1980).

V. Weiss and E.P. Klier, Factors responsible for notch embrittlement of high-strength steels. Final Rep. No. 2, Bur. Aeronautics Contract No. NOas 55-377-c (1955).

V. Weiss, R. Chait and J.G. Sessler, Fracture of ceramics, *Proc. First Int. Conf. Fracture*, Sendai, Japan, 3, 1307-1320 (1965).

V. Weiss and S. Yukawa, Critical appraisal of fracture mechanics. *Fracture Toughness Testing and its Applications*, ASTM STP 381, 1-22 (1965).

R.H. Weitzmann and I. Finnie, Further studies of crack propagation using the controlled crack propagation approach. *Fracture Toughness and Slow- Stable Cracking*, ASTM STP 559, 111-126 1974).

B.M. Wundt, A unified interpretation of room-temperature strength of notched specimens as influenced by their size. *Metals Engng. Conf.*, ASME Paper No. 59-MET-9, Albany, N.Y. (1959).

S. Yukawa, Testing and design considerations in brittle fracture. *Symp. on Evaluation of Metallic Materials in Design for Low-Temperature Service* ASTM STP 302, 193-212 (1961).

III. THICKNESS SIZE EFFECTS ON STRENGTH: CRACKED OR SHARP NOTCH SPECIMENS

- W.R. Andrews, V. Kumar and M.M. Little, Small-specimen brittle-fracture toughness testing. *Fracture Mechanics: Thirteenth Conference, ASTM STP 743*, 576-598 (1981).
- S. Banerjee, Influence of specimen size and configuration on the plastic zone size, toughness and crack growth. *Engng Fracture Mech.* 15, 343-390 (1981).
- W.F. Barclay, Private communication.
- J.D. Barrett, Effect of crack-front width on fracture toughness of Douglas-fir. *Engng Fracture Mech.* 8, 711-717 (1976).
- J.M. Barsom and S.T. Rolfe, K_{IC} transition-temperature behavior of A517-F steel. *Engng Fracture Mech.* 2, 341-357 (1971).
- C. Bathias, Application of fracture mechanics to aluminum alloys selection. *Engng Fracture Mech.* 10, 267-282 (1978).
- A.D. Batte, W.S. Blackburn, A. Elsander, T.K. Hellen and A.D. Jackson, A comparison of the J^* integral with other methods of post yield fracture mechanics. *Int. J. Fracture* 21, 49-66 (1983).
- D.R. Biswas and V.K. Pujari, Verification of the double-torsion equation by using different thickness samples of a machinable glass-ceramic. *Communs Am. Ceram. Soc.* 64, C98-C99 (1981).
- J.I. Bluhm, A model for the effect of thickness on fracture toughness. *Proc. Am. Soc. Test. Mater.* 61, 1324-1331 (1961).
- W.F. Brown, Jr. and J.E. Srawley, Plane strain crack toughness testing of high strength metallic metals. *Plane Strain Crack Toughness Testing of High Strength Metallic Materials, ASTM STP 410*, 1-65 (1966).
- F.E. Buresch, Fracture toughness testing of alumina. *Fracture Mechanics Applied to Brittle Materials, ASTM STP 678*, 151-165 (1979).
- G.G. Chell and R.S. Gates, A study of failure in the post yield regime using single edge-notched tension specimens *Int. J. Fracture* 14, 233-247 (1978).
- G.G. Chell and I. Milne, A new approach to the analysis of invalid fracture toughness data. *Int. J. Fracture* 12, 164-166 (1976).
- E.P. Cox and F.V. Lawrence, Jr., Ductile fracture behavior of wrought steels. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 529-551 (1980).
- W.G. Ferguson and M.N. Sargisson, Fracture toughness of Comsteel En25. *Engng Fracture Mech.* 5, 499-508 (1973).
- A. Frediani, An evaluation of the reliability of fracture mechanics methods. *Engng Fracture Mech.* 14, 289-322 (1981).
- J. Fukakura, The effect of specimen thickness and temperature on plastic yielding and fracture properties of mild steel. *Engng Fracture Mech.* 6, 231-244 (1974).

- S.J. Garwood, Measurement of crack growth resistance of A533B wide plate tests. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 271-295 (1980).
- G. Green and J.F. Knott, On effects of thickness on ductile crack growth in mild steel. *J. Mech. Phys. Solids* 23, 167-183 (1975).
- K.S. Grewal and V. Weiss, The effect of testing system stiffness on fracture behavior of sheet specimens. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 94-104 (1969).
- R.H. Heyer and D.E. McCabe, Crack growth resistance in plane-stress fracture testing. *Engng Fracture Mech.* 4, 413-430 (1972).
- G.H. Hilton, Evaluation of Ti-6Al-4V for specification requirements. *Fracture Prevention and Control*, Am. Soc. Metals, 181-197 (1974).
- F.H. Huang and D.S. Gelles, Influence of specimen size and microstructure on the fracture toughness of a martensitic stainless steel. *Engng Fracture Mech.* 19, 1-20 (1984).
- C.M. Hudson and P.E. Lewis, NASA-Langley research center's participation in a round-robin comparison between some current crack-propagation prediction methods. *Part-Through Crack Fatigue Life Prediction, ASTM STP 687*, 113-128 (1979).
- K. Ikeda and H. Kihara, Brittle fracture strength of welded structures. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 851-867 (1969).
- G.R. Irwin, Effects of size and shape on the fracture of solids. *Properties of Crystalline Solids, ASTM STP 283*, 118-122 (1961).
- G.R. Irwin, Fracture. *Encyclopedia of Physics, Volume 6 - Elasticity and Plasticity*, Springer-Verlag, Berlin, 551-590 (1958).
- G.R. Irwin, Fracture mode transition for a crack traversing a plate. *J. bas. Engng, Trans. Am. Soc. mech. Engrs Ser. D* 82, 417-425 (1960).
- G.R. Irwin, J.A. Kies, and H.L. Smith, Fracture strengths relative to onset and arrest of crack propagation. *Proc. Am. Soc. Test. Mater.* 58, 640-657 (1958).
- F.A. Johnson and J.C. Radon, Fracture energy and crack tunnelling. *J. Testing Evaluation* 4, 209-217 (1976).
- F.A. Johnson and J.C. Radon, Mechanical and metallurgical aspects of fracture behaviour of an Al-alloy. *Int. J. Fracture Mech.* 8, 21-36 (1972).
- M.H. Jones and W.F. Brown, Jr., The influence of crack length and thickness in plane strain fracture toughness tests. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 63-91 (1970).
- H.-J. Kaiser and K.E. Hagedorn, A comparison of different methods for determination of elastic-plastic R curves. *Proc. Third Colloquium Fracture*, London, U.K., 79-86 (1980).

M.F. Kaplan, Crack propagation and the fracture of concrete. *J. Am. Concr. Inst.* 58, 591-610 (1961).

J.G. Kaufman, Discussion. *Fracture Toughness Testing and Its Applications*, ASTM STP 381, 208-209 (1965).

J.G. Kaufman, Progress in fracture testing of metallic materials. *Review of Developments in Plane Strain Fracture Toughness Testing*, ASTM STP 463, 3-21 (1970).

J.G. Kaufman and H.Y. Hunsicker, Fracture toughness testing at ALCOA research laboratories. *Fracture Toughness Testing and Its Applications*, ASTM STP 381, 290-308 (1965).

J.G. Kaufman, R.L. Moore and P.E. Schilling, Fracture toughness of structural aluminum alloys. *Engng Fracture Mech.* 2, 197-210 (1971).

M.O. Lai and W.G. Ferguson, The inadequacy of the plane-strain fracture toughness test requirements. *Engng Fracture Mech.* 13, 285-292 (1980).

H. Liebowitz, J. Eftis and D.L. Jones, Some recent theoretical and experimental developments in fracture mechanics. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 1, 695-723 (1977).

H.W. Liu, Thickness effects on fracture criteria. *Fracture Mechanics of Ductile and Tough Materials and Its Applications to Energy Related Structures*, 189-198 (1981).

Y.W. Mai, A.G. Atkins and R.M. Caddell, Determination of valid R-curves for materials with large fracture toughness to yield strength ratios. *Int. J. Fracture* 12, 391-407 (1976).

G. Marci, J. Eschweiler and T. Fett, Fracture toughness of 7075-T7351 aluminum plates. *Proc. Fourth European Conf. Fracture*, Leoben, Austria, 1, 118-126 (1982).

M.J. May, British experience with plane strain fracture toughness (K_{IC}) testing. *Review of Developments in Plane Strain Fracture Toughness Testing*, ASTM STP 463, 41-62 (1970).

I. Milne and G.G. Chell, Effect of size on the J fracture criterion. *Elastic-Plastic Fracture*, ASTM STP 668, 358-377 (1979).

S. Mindess and J.S. Nadeau, Effect of notch width on K_{IC} for mortar and concrete. *Cem. Concr. Res.* 6, 529-534 (1976).

E.M. Morozov, Some problems in experimental fracture mechanics. *Engng Fracture Mech.* 13, 541-561 (1980).

D. Munz and H.P. Keller, Effect of specimen size on fracture toughness in the ductile brittle transition region of steel. *Proc. Third Colloquium Fracture*, London, U.K., 105-117 (1980).

T. Nakazawa, S. Suzuki, T. Sunami and Y. Sogo, Application of high-purity ferritic

stainless steel plates to welded structures. *Toughness of Ferritic Stainless Steels, ASTM STP 706*, 99-122 (1980).

B.K. Neale, An investigation into the effect of thickness on the fracture behaviour of compact tension specimens. *Int. J. Fracture* 14, 203-212 (1978).

F.G. Nelson, J.G. Kaufman and E.T. Wanderer, Tear tests of 5083 plate and of 5183 welds in 5083 plate and extrusions. *Adv. cryogen. Engng* 15, 91-101 (1970).

J.O. Outwater, M.C. Murphy, R.G. Kumble and J.T. Berry, Double torsion technique as a universal fracture toughness test method. *Fracture Toughness and Slow-Stable Cracking, ASTM STP 559*, 127-138 (1974).

B.K. Parida, Crack edge instability - a criterion for safe crack propagation limit in thin sheets. *Proc. Third Colloquium Fracture*, London, U.K., 307-314 (1980).

J.S. Pascover, M. Hill and S.J. Matas, The application of fracture toughness testing to the development of a family of alloy steels. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 310-323 (1965).

L.P. Pook, Fracture toughness tests on an aluminum alloy using a chevron notch bend specimen. *Int. J. Fracture* 22, R21-R23 (1983).

P.K. Poulouse, D.L. Jones and H. Liebowitz, A comparison of the geometry dependence of several nonlinear fracture toughness parameters. *Engng Fracture Mech.* 17, 133-151 (1983).

S.K. Putatunda and S. Banerjee, Effect of size on plasticity and fracture toughness. *Engng Fracture Mech.* 19, 507-529 (1984).

D.T. Read and R.P. Reed, Effects of specimen thickness on fracture toughness of an aluminum alloy. *Int. J. Fracture* 13, 201-213 (1977).

A.J. Repko, M.H. Jones, and W.F. Brown, Jr., Influence of sheet thickness on sharp-edge-notch properties of a β titanium alloy at room and low temperatures. *Symp. on Evaluation of Metallic Materials in Design for Low-Temperature Service, ASTM STP 302*, 213-229 (1961).

D. Rhodes, L.E. Culver and J.C. Radon, The influence of fracture mode transition on the compliance of thin section fracture specimens. *Proc. Third Colloquium Fracture*, London, U.K., 287-296 (1980).

P.C. Riccardella and J.L. Swedlow, A combined analytical-experimental fracture study. *Fracture Analysis, ASTM STP 560*, 134-154 (1974).

J.C. Ritter, A modified thickness criterion for fracture toughness testing. *Engng Fracture Mech.* 9, 529-540 (1977).

R. Roberts, G.V. Krishna and G.R. Irwin, Fracture behaviour of bridge steels. *Flaw Growth and Fracture, ASTM STP 631*, 267-284 (1977).

S.T. Rolfe and S.R. Novak, Slow-bend K_{IC} testing of medium-strength high-toughness steels. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 124-159 (1970).

S.T. Rolfe and S.R. Novak, Discussion: M.H. Jones and W.F. Brown, Jr., Closure. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 92-95, 97-101 (1970).

A. Savadori, C. Marega and E. Marchetti, Morphology and molecular weight in the high speed fracture mechanics of polypropylene. *Proc. Int. Conf. Analytical Experimental Fracture Mech.*, Rome, Italy, 931-941 (1980).

R.A. Schmidt and T.J. Lutz, K_{IC} and J_{IC} of westerly granite - effects of thickness and in-plane dimensions. *Fracture Mechanics Applied to Brittle Materials, ASTM STP 678*, 166-182 (1979).

F.R. Schwartzberg, A review of cryogenic fracture toughness behavior. *Adv. cryogen. Engng* 12, 458-472 (1967).

W. Seidl, Specimen size effects on the determination of K_{IC} - values in the range of elastic-plastic material behavior. *Engng Fracture Mech.* 12, 581-597 (1979).

J.L. Shannon, Jr., J.K. Donald, and W.F. Brown, Jr., Heavy-section fracture toughness screening specimen. *Developments in Fracture Mechanics Test Methods Standardization, ASTM STP 632*, 96-114 (1977).

J.L. Sliney, Jr., Notch properties of 5 per cent chromium-molybdenum-vanadium steel sheet as affected by heat treatment, test temperature, and thickness. *Proc. Am. Soc. Test. Mater.* 62, 825-836 (1962).

Special ASTM Committee, Fracture testing of high-strength sheet materials, (First Report). *Bull. Am. Soc. Test. Mater.* No. 243, 29-40 (1960).

Special ASTM Committee, Fracture testing of high-strength sheet materials (Second Report). *Bull. Am. Soc. Test. Mater.* No. 244, 18-28 (1960).

J.E. Srawley, Plane strain fracture toughness test on two-inch-thick maraging steel plate at various strength levels. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 131-146 (1969).

J.E. Srawley and C.D. Beachem, Resistance to crack propagation of high-strength sheet materials for rocket motor casings. NRL Rep. 5771, U.S. Naval Research Laboratory (1962).

E.A. Steigerwald, Crack toughness measurements of high-strength steels. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 102-123 (1970).

A.M. Sullivan and J. Stoop, Further aspects of fracture resistance measurement on thin sheet material: yield stress and crack length. *Fracture Toughness and Slow-Stable Cracking, ASTM STP 559*, 99-110 (1974).

A.M. Sullivan, J. Stoop and C.N. Freed, Influence of sheet thickness upon the fracture resistance of structural aluminum alloys. *Progress in Flaw Growth and Fracture Toughness Testing, ASTM STP 536*, 323-333 (1973).

J.L. Swedlow, The thickness effect and plastic flow in cracked plates. ARL Rep. 65-216, Aerospace Research Laboratories, Office of Aerospace Research, USAF, Wright-Patterson, Ohio (1965).

S. Taira and K. Tanaka, Thickness effect of notched metal sheets on deformation and fracture under tension. *Engng Fracture Mech.* 11, 231-249 (1979).

M.G. Vassilaros, J.A. Joyce and J.P. Gudas, Effects of specimen geometry on the J_I -R curve for ASTM A533B steel. *Fracture Mechanics: Twelfth Conference, ASTM STP 700*, 251-270 (1980).

V. Weiss and S. Yukawa, Critical appraisal of fracture mechanics. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 1-22 (1965).

R.H. Weitzmann and I. Finnie, Further studies of crack propagation using the controlled crack propagation approach. *Fracture Toughness and Slow-Stable Cracking, ASTM STP 559*, 111-126 (1974).

E.T. Wessel, W.G. Clark, Jr. and W.H. Pryle, Fracture mechanics technology applied to heavy section steel structures. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 825-850 (1969).

J.G. Williams and P.D. Ewing, Crack propagation in plates and shells subjected to bending and direct loading. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 119-130 (1969).

D.H. Winne and B.M. Wundt, Application of the Griffith-Irwin theory of crack propagation to the bursting behavior of disks, including analytical and experimental studies. *Trans. Am. Soc. mech. Engrs* 80, 1643-1655 (1958).

H. Yoshimura, H. Masumoto and I. Inove, Properties of low-carbon 25Mn-5Cr-INi austenitic steel for cryogenic use. *Adv. cryogen. Engng* 28, 115-125 (1982).

S. Yukawa, Testing and design considerations in brittle fracture. *Symp. on Evaluation of Metallic Materials in Design for Low-Temperature Service, ASTM STP 302*, 193-212 (1961).

R.E. Zinkham, Anisotropy and thickness effects in fracture of 7075-T6 and -T651 aluminum alloy. *Engng Fracture Mech.* 1, 275-289 (1968).

IV. SIZE EFFECTS ON STRENGTH: SMOOTH SPECIMENS

- F.O. Andereg, Strength of glass fiber. *Ind. and Eng Chem* 31, 290 (1939).
- O.L. Anderson, The Griffith criterion for glass fracture. *Conference on Fracture*, Swampscott, Massachusetts 331 (1959).
- G.K. Bansal, W. Duckworth and D.E. Niesz, Strength-size relationships in ceramic materials: investigation of a commercial glass-ceramic. *Ceram. Bull.* 55, 289 (1976).
- G.K. Bansal, W.H. Duckworth, D.E. Niesz, Strength-size relations in ceramic materials: investigation of an alumina ceramic. *J. Am. Ceram. Soc.*, 59, 472 (1976).
- G.K. Bansal and W.H. Duckworth, Effects of specimen size on ceramic strength. *Fracture Mechanics of Ceramics*, Plenum, New York, 3, 189 (1978).
- Bayer and Cooper, Fracture mechanisms in sapphire whiskers. *Proc. Second Int. Conf. Fracture* 372 (1969).
- K.O. Bogardis and R.C. Malcolm, Design stresses for aluminum alloy 5083-0 and 5183 welds at cryogenic temperatures. *ASTM STP* 579, 190 (1974).
- J.D. Buch, Mechanical behaviour model for graphites. *ASTM STP* 605, 127 (1975).
- N. Davidenkov, E. Shevandin and F. Wittmann, The influence of size on the brittle strength of steel. *J. appl. Mech* 14, 63 (1947).
- J.G. Docherty, Bending tests on geometrically similar notched specimens. *Engineering* 133, 645-647 (1932).
- J.G. Docherty, Slow bending tests on large notched bars. *Engineering* 139, 211-213 (1935).
- M.G. Gee, Brittle fracture of hard metals: dependence of strength on defect size distribution. *Int. J. mech Sci* 26, 85-91 (1984).
- T.K. Gupta, Effect of specimen size on the strength degradation of Al_2O_3 subjected to thermal shock. *J. Am. Ceramic Soc. - Discussions and Notes* 58, 158-159 (1975).
- M. Hara, The mechanical strength of damage-free sheet glass. *Proc. First Int. Conf Fracture*, 2, 1193 (1965).
- N. Igata, R.R. Hasiguti and K. Domoto, Micro-plasticity of uranium dioxide at room temperature. *Proc. First Int. Conf. Fracture*, 2, 883 (1965).
- Y. Katayama and Y. Hattori, Effects of specimen size on strength of sintered silicon nitride. *Communs Am Ceram. Soc.* 65, 164-165 (1982).
- E.P. Kennedy and C.R. Kennedy, Dependence of strength on particle size in graphite. *ASTM STP* 743, 576 (1980).
- J.F. Knott, Micro-mechanisms of fracture and the fracture toughness of engineering alloys. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 1, 61 (1977).

- J. Lamon and A.G. Evans, Statistical analysis of bending strengths for brittle solids: a multiaxial failure problem. *J. Am. Ceram. Soc.* 66, 177-182 (1983).
- I. Lyse and C.C. Keyser, Effect of size and shape of test specimen upon the observed physical properties of structural steel. *Proc. ASTM* 34, 202 (1934).
- J.D. Lubahn, Correlation of tests using the congruency principle. *Proc. ASTM* 58, 678 (1958).
- J.D. Lubahn, Room temperature crack propagation and size effect on mild steel. *Weld. Res. Suppl.* 34, 518s (1955).
- C.W. MacGregor and N. Grossman, Dimensional effects in fracture - Influence of size and ratios of combined stresses on transition temperature and effect of combined stresses on fracture strength. *Weld. Res. Suppl.* 31, 20 (1952).
- A.C. MacKenzie, J.W. Hancock and D.K. Brown, On the influence of state of stress on ductile failure initiation in high strength steels. *Engng Fracture Mech.* 9, 167-188 (1977).
- E.R. Parker, The effect of section size on the fracture strength of mild steel. *Fracturing of Metals*, Am. Soc. of Metals 40B, 82 (1948).
- J. Phillips, The failure of steel bars containing blunt notches. *Int. J. Fracture* 22, 163-186 (1983).
- C.W. Richards, Size effect in the tension test of mild steel. *Proc. ASTM* 54, 995 (1954).
- D.G. Rickerby, Weibull statistics for biaxial strength test. *Proc Fourth Int. Conf. Fracture* 2, 1133.
- G. Sachs and J.D. Lubahn, The effect of triaxiality on the technical cohesive strength of steels. *Weld. Res. Suppl.* 25, 53s-64s (1946).
- G. Sachs, J.D. Lubahn and L.J. Ebert, The effects of notches of varying depth on the strength of heat treated low alloy steels. *Trans. ASM* 34, 517 (1945).
- G.G. Trantina and C.A. Johnson, Spin testing of ceramic materials. *Fracture Mechanics of Ceramics*, Plenum, New York, 3, 177-188 (1978).
- O. Vardar and I. Finnie, An analysis of the Brazilian disk fracture test using the Weibull probabilistic treatment of brittle strength. *Int. J. Fracture* 11, 495 (1975).
- W. Weibull, A statistical theory of the strength of materials. *Proceedings, Royal Swedish Institute for Engineering Research*, 151, 5 (1939).
- V. Weiss and J.G. Sessler, Analysis of effects of test temperature on the notch strength of high-strength sheet alloys. *ASTM STP* 302, 3 (1961).
- V. Weiss, Application of Weibull's statistical theory of fracture to sheet specimens. *ASME Paper #62-WA-270*.

T. Williams, and H.F. Hall, The effect of specimen size on tensile properties of coarse-grained medium-carbon steel at low temperatures. *J. Iron Steel Inst.* 193, 56 (1959).

T. Yokobori and M. Ichikawa, Tensile a torsional fracture of low carbon steel at liquid nitrogen temperature. *Proc. First Int. Conf. Fracture* 2, 1039 (1965).

STRENGTH SIZE EFFECTS AND FRACTURE MECHANICS:

WHAT DOES THE PHYSICAL EVIDENCE SAY?

G.B. Sinclair and A.E. Chambers

Department of Mechanical Engineering, Carnegie-Mellon University
Pittsburgh, PA 15213, U.S.A.

Abstract - Being able to predict the strength of geometrically-similar cracked specimens of different sizes or scales is a fundamental requirement for success for linear elastic fracture mechanics (LEFM). The prediction contained in LEFM is that the strength reduces as the inverse square-root of the scale factor in the plane of the crack: here we review how well this prediction actually agrees with the physical evidence. In particular we examine agreement for materials and configurations exhibiting brittle responses - the situations complying best with the underlying linear elastic assumptions in the theory. The data shows that the agreement is not good, even in the most brittle of instances.

STRENGTH SIZE EFFECTS AND FRACTURE MECHANICS:

WHAT DOES THE DATA SAY?

G.B. Sinclair and A.E. Chambers

Department of Mechanical Engineering, Carnegie-Mellon University
Pittsburgh, PA 15213, U.S.A.

Abstract - Being able to predict the strength of geometrically-similar cracked specimens of different sizes or scales is a fundamental requirement for success for linear elastic fracture mechanics (LEFM). The prediction contained in LEFM is that the strength reduces as the inverse square-root of the scale factor in the plane of the crack: here we review how well this prediction actually agrees with the physical evidence. In particular we examine agreement for materials and configurations exhibiting brittle responses - the situations complying best with the underlying linear elastic assumptions in the theory. The data shows that the agreement is not good, even in the most brittle of instances.

INTRODUCTION

Everyday experience indicates that strength, or stress at fracture, does not vary with size - this is reflected in the reporting of ultimate stress values for materials in handbooks. However, when size is reduced below that normally encountered in uniaxial tension tests, increases in strength can occur. Such *strength size effects* are especially prevalent in brittle materials. For example, in Griffith's classical paper [1], the breaking stress of glass fibers increases by 70% on reducing their diameter by an order of magnitude, and increases by an additional factor of 5 or so on reducing diameter by another order of magnitude. Clearly then, strength size effects can be considerable when they do indeed occur, and they need to be taken into account in any theory attempting to predict fracture in such cases.

Turning to the fracture of cracked specimens composed of brittle materials, probably the most accepted theory for treating these configurations is linear elastic fracture mechanics (LEFM). Implicit in LEFM, in the choice of the stress intensity factor as the parameter governing fracture, is a strength size prediction. To see this consider, by way of illustration, the scaled pair of single-edge-cracked specimens sketched in Fig. 1. Herein Specimen 1 is a strip of indefinite length yet finite width W , weakened by a crack of length a , and subjected to a remote uniform stress σ_1 ; while Specimen 2 is also of indefinite length but has width λW , crack length λa , and applied stress σ_2 . Thus λ is the in-plane scale factor and we ignore out-of-plane effects for the present. For Specimen 1 at fracture, LEFM has

$$K_I = \sigma_1^* \sqrt{\pi a} f(a/W) = K_C,$$

where K_I is the stress intensity factor in Mode I, $f(a/W)$ is a finite width correction factor, K_C is the material fracture toughness, and the asterisk atop σ_1 serves to distinguish it as being the applied stress at fracture. Similarly




Fig. 1. Scaled pair of single-edge-cracked specimens

for Specimen 2, provided it is comprised of the same brittle material, at fracture

$$K_I = \sigma_2^* \sqrt{\pi \lambda a} f(\lambda a / \lambda W) = K_c,$$

whence

$$\sigma_1^* / \sigma_2^* = \sqrt{\lambda}. \quad (1)$$

The strength size effect prediction of (1), sometimes termed the *geometric size effect* of LEFM, is certainly in agreement with general trends, *viz.*, strength increasing with decreasing size. The question that arises, though, is *how well* it in fact agrees with physical actuality.

The question is important on two counts. First, the ability to predict when changes are limited to scale alone is quite conceivably the easiest of tests a theory can face, and therefore virtually an essential prerequisite to satisfactory performance in more complex contexts. Second, appreciable changes in size are encountered in engineering. For instance, at the Government Products Division of Pratt and Whitney Aircraft Corporation, tests on 6-inch wide panels have been used to infer what is happening at the necks in "fir trees" which hold blades in high pressure turbine disks, and which can be as small as 1/16 of an inch in width. While there is more than just a size change entailed in this specific application, the scaling factor involved is of the order of 100. In sum then, accurately accounting for scaling is a basic capability for linear elastic fracture mechanics to possess, and one which is required in practice.

To answer the question we have reviewed the open literature, drawing on data furnished in papers in a variety of journals, in ASTM Special Technical Publications and proceedings of other conferences related to fracture mechanics, and occasionally in reports. In performing this search we have been fortunate to be directed to a number of references that provide some experimental support for (1), all of which we of course include here. We have attempted to be as comprehensive as we can in supplementing these references, but nonetheless

are confident that there remain still further references which we have not, to date, found - we would appreciate readers drawing our attention to any such oversights and be happy to include them in an updated version of the present study. We do not anticipate, though, that the amount of pertinent data outstanding is sufficient to significantly alter the overall assessment made on the basis of the extensive survey summarized here.

In answering the question we have also placed the main emphasis on physical data featuring brittle response, since such phenomena are in greatest accord with the assumptions in linear elasticity and consequently can be expected to agree with LEFM best. We have, in addition, tried to isolate the issue as much as possible, by selecting data as close to perfect scaling as can be drawn from a given source and by taking strength estimates from load data wherever we were able, thereby avoiding practically all analysis. And in processing the data we have made an effort to apply reasonable data reduction procedures in a consistent manner. In this way it is hoped to focus simply on what the physical data has to say about the applicability of the LEFM strength size prediction.

In what follows we begin by describing the ground rules for including data relevant to the issue and how such data are then classified. Next we provide the results in summary form (greater detail can be found in the Appendix), and discuss how well theory and practice agree. Finally we offer some concluding remarks on the consequences of the comparison.

SURVEY GUIDELINES

In this section we start by defining strength. We then place limits on any deviations from scaling, including bounds on thickness effects. With this last in place we can distinguish between brittle versus ductile behavior. In all, the intent here is to furnish a reasonable set of rules which can be systematically applied to filter out data not enabling a fair appraisal of the LEFM size

prediction as a result of not conforming to underlying assumptions: we do this either by excluding such data altogether or by separating it into other classes wherein good agreement with fracture mechanics is not necessarily expected.

We define *strength* as the nominal, elastic, net section stress, under monotonic quasi-static loading, at the onset of Mode I crack growth (or further crack growth in the case of flaws that have been previously grown by cyclic loading). With truly brittle response this stress level is usually equal to that required for total fracture; with less brittle behavior it varies somewhat, loads at a 5% secant offset in the load-displacement record being generally preferred but others, such as at "pop-in", being taken when the 5% offset stress is not available. We choose the stress at this point rather than at its maximum because response is likely to be more linear elastic. In the event, however, that only maximum load levels are provided in a given source, we include such data but note the relaxation of our definition. We do this in the interests of admitting as much data as possible that bear on the issue at hand. The attendant hierarchy of preferred sorts of information for deducing strengths from then is: load and geometry, including final pre-crack length, at the onset of crack growth; gross stress then net section stress at the same point; fracture toughness (or stress intensity factor) at crack initiation; resistance curves with discernible proportional small crack growth; followed by the same first four quantities, in order, at maximum load. Only the highest available information type in this ranking is used. No attempts are made to infer strengths from load-displacement products, or their equivalents, unless load or stress alone can be determined.

Preliminary to prescribing limits on departures from perfect scaling, we need to define what we mean by a *crack* and describe the range of acceptable *environments*. Here, with respect to a crack, our first choice is a specimen with a fatigue pre-crack. Again, however, with a view to including all pertinent data, we admit notches whose acuity is such that their local root radius of

of curvature, r , is an order of magnitude less than their total notch depth or crack length, a , *i.e.* notch acuity must satisfy

$$r/a \leq 1/10. \quad (2)$$

Too, we record whenever the situation is not our ideal of pre-crack and compare the two classes of "cracks". Regarding environments, with a view to maintaining as much control as possible, we do not allow data for any that are more corrosive than air. On the other hand some variations in temperature are countenanced, since low temperature response can be quite embrittled and accordingly in good agreement with LEFM assumptions. When comparing scaled specimens at other than room temperature, we allow differences in temperature between sizes of up to 5°K, with the *proviso* that the specimen having the higher stress-intensity-factor value at failure not be at a higher temperature. This stipulation is so as to avoid mixing temperature transition behavior with size effects.

Turning to *scaling*, our first requirement is that specimen type be identical, *e.g.* a compact tension specimen of one size can only be compared with another compact tension specimen of a different size. No exceptions to this restriction are permitted. Our second requirement is that, if cracks are in fact sharp notches, the notch acuity should scale (r/a constant) or at least r should remain constant. Data where r decreases with increasing scale factor, λ , are excluded. Our third requirement is that the crack length, a , to width ratio, W , scale to within 10%. That is

$$0.9 \leq (a_1/W_1)/(a_2/W_2) \leq 1.1 \quad (3)$$

where subscripts refer to specimen. The only exception to (3) entertained is when a/W for a test piece of one size falls between two a/W for a test piece of a second size and the latter are within $\pm 20\%$ of the former; then we interpolate between the pair of a/W for the second size. Our fourth requirement concerns the other in-plane dimension of a specimen - length, span, *etc.* This should scale sufficiently so that a stress intensify factor calculation for the

different sizes remains unaffected by any changes in its value relative to W . Typically this just means that specimens should preserve a length which is as long as, or longer than, W . And our fifth requirement in essence is that thickness effects are to be excluded. One means of ensuring this is to have the thickness, B , scale in concert with λ ; then whatever combination of plane stress and plane strain states is present in one size is conserved in the next. Alternatively test pieces can maintain a state of plane stress or plane strain exclusively by having a fixed B which is relatively small or large, respectively. To this end we define, in a global sense, *plane stress* as being when

$$B/a \leq 0.1, \quad (4)$$

while *plane strain* is taken as being when

$$B/W \geq 0.5, B/a \geq 1.0. \quad (5)$$

The plane stress range is so that the thickness is an order of magnitude less than the smallest of the in-plane dimensions while the plane strain range is motivated by standard specimens in plane strain fracture toughness testing. Clearly, for a fixed B as a , W vary, (4), (5) may exclude quite a number of configurations. To reduce this possibility somewhat we relax (4), (5) to $B/a \leq 0.3$ and $B/W = 0.45$, $B/a \geq 0.9$, respectively. As previously, we separate data that is only admitted by virtue of this relaxation. For convenience we classify specimens with scaled B as plane stress or plane strain depending on which of (4) or (5) they are closest to.

We now consider the crux of the applicability of linear elastic fracture mechanics - namely how *brittle* the response is. Here by brittle we mean in an engineering sense of limited plastic flow rather than from a materials viewpoint of relating microstructural fracture mechanisms. As a result we need to estimate the extent of the yield region induced at failure. In lieu of anything obviously superior, we take the classical measures of yield region radius, r_Y , to this effect.

These are, for plane stress

$$r_Y = \frac{1}{2\pi} \left(\frac{K_I}{\sigma_Y} \right)^2, \quad (6)$$

and for plane strain (from Irwin [2])[†]

$$r_Y = \frac{1}{6\pi} \left(\frac{K_I}{\sigma_Y} \right)^2. \quad (7)$$

In (6), (7), K_I is the Mode I stress intensify factor evaluated at the onset of crack growth, σ_Y the uniaxial yield stress. The factor of 3 difference between (6), (7) is the real reason for our earlier concern to distinguish between plane stress and plane strain. Once r_Y is calculated with the appropriate equation, we regard the response as being brittle provided r_Y is less than 2% of the total crack length, irrespective of whether the specimen in question is in a state of plane stress or plane strain. That is, the *brittle regime* requires that

$$r_Y/a < 0.02. \quad (8)$$

This is essentially the same limit as is prescribed in standards for fracture toughness testing. For specimens with more extensive plastic flow than that permitted in (8) yet short of gross yielding, we term the response brittle-ductile if r_Y is less than 5% of the total crack length, *viz.*, the *brittle-ductile regime* has

$$0.02 \leq r_Y/a < 0.05. \quad (9)$$

This transition class is regarded as one it would seem natural for the practicing engineer to attempt to extend the applicability of LEFM into, given satisfactory performance in the brittle regime. This view is supported to a degree by the large number of articles in the literature that report fracture toughness values in the brittle-ductile regime, implying some sort of use of fracture mechanics is contemplated therein. All other responses are taken as being ductile, *i.e.* the *ductile regime* occurs when

[†]For a recent review of the ability of (6), (7) to be representative of yield region extent see [3], which indicates that, given the wide variety of configurations encountered in testing, they do perform remarkably well.

$$r_Y/a \geq 0.05. \quad (10)$$

We include data from specimens in this range simply for completeness.

In applying all of the foregoing, considerable effort is made to avoid comparing apples with oranges. For example, if we have two fatigue-cracked compact tension specimens comprised of identical materials, each having a counterpart which is perfectly scaled by a common factor λ yet having different a/W , we keep the ratios of the strengths, σ_1^*/σ_2^* , apart. Similarly we do not compare specimens in the brittle regime with those in the brittle-ductile. On the other hand, since the choice of 0.05 in (9), (10) is somewhat arbitrary, we let it shift to as high as 0.08 for a last size in a set that is otherwise brittle-ductile, and conversely to drop to 0.04 for one size in a ductile set. Typically too, we try to err on the side of classifying response as more ductile than it is rather than less. Within these separate classes, for two different sizes we form all possible quotients of the strengths for the small specimen divided by those for the large, σ_1^*/σ_2^* , note the range of these ratios and calculate their mean. In this fashion we hope to, if anything, overestimate the extent of scatter in the data by using extremums, yet reduce the effects of scatter by using means. We also take down the total number of tests involved in producing a mean strength ratio.

Clearly the choice of the above procedures is not unique, merely sensible. Other reasonable approaches certainly exist. A number of these may well fall within the concessions made on our most stringent requirements. Thus by monitoring any differences between the strength size dependence of data complying with our preferred constraints and that for data only admitted as a result of a relaxation, we should be able to assess what, if any, effects such alternative treatments would have. The expectation is that for these and other rational data reduction schemes, while they would give rise to differences in detail for individual comparisons, they would nonetheless yield the same overall appreciation of how well the LEFM size prediction works if consistently applied to *all* the physical evidence.

We apply our set of rules to every one of the references with strength size effect data encountered in our search. Even on the basis of our more generous restrictions, this excludes the data from some because of not scaling properly, not isolating thickness effects, not having sufficient notch sharpness, *etc.* Too, there is quite a bit of duplication in the reporting of data, *e.g.* the well-known appraisal of fracture mechanics by Weiss and Yukawa in STP 381, [4], actually discusses data first furnished elsewhere. In these cases we only cite the original source.[†] A listing of all of the around 300 references checked may be found in the bibliography [5]; the 100 odd references determined as independent sources of admissible data are listed alphabetically by author here [6-136]. We next look to examine the outcome of comparing the data from these sources with the strength size prediction of fracture mechanics.

RESULTS AND DISCUSSION

In this section we begin by reviewing the ramifications of our varying admission standards for data and grouping it accordingly. We then display plots of strength ratio data versus scale factor, together with the LEFM prediction of the same. Finally we introduce measures to quantify agreement and discuss their implications.

Considering the various relaxations in requirements we observe that, for the most part, they are of no consequence because data fall within our most stringent requirements and sharpest classifications. Regarding each of those instances in turn where there are exceptions, we first remark that strength data based on maximum loads/stresses tend to exhibit less of a size effect than that associated with strengths at the onset of crack growth. However, where size effects are distinct for the two strength types, the maximum criterion usually involves large stresses with attendant extensive yielding. Consequently nearly all such data

[†] If the original source is an in-house report with substantially the same authorship as a version in the more open literature, we give the latter because of its greater accessibility. On occasion, when we have not managed to obtain a copy of an original source, we list it together with the reference reporting its data.

falls in the ductile regime and we admit them as such. Second, re notch acuity, we find there is some but little effect due to notch sharpness provided (2) is met; typically notches with less acuity display less in the way of size effects but there is no clear distinction in the range allowed by (2). Hence we use data from both notches and fatigue pre-cracks but, if in fact it is not from the latter, note the notch acuity in the detailed tables in the Appendix. Third, concerning the extended ranges of a/W similarity and B/a , B/W values for avoiding thickness effects, we find no significant differences in strength size effects between data fulfilling our strictest requirements and that only complying with our more generous limits. As a result we combine the two types in what follows. In contrast, there can be variations in strength size effects for sets of scaled specimens that have distinct a/W but are otherwise the same. Consequently we continue to segregate such data in computing mean σ_1^*/σ_2^* and note when this occurs in the tables in the Appendix. These tables give associated sources and are broadly classified as to material type; the bulk of the data presented in the remainder of this section are for steels and aluminum alloys.

Distinguished as to plane strain or plane stress and by brittle, brittle-ductile, ductile regime, Fig. 2 shows test data for strength ratios, σ_1^*/σ_2^* , plotted versus scale factor, λ . The size of the dots reflects the number of tests involved. Also shown is the LEFM prediction (1). Agreement is not great. Even in a best fit sense, the LEFM prediction is generally astray. More precisely, using least squares weighted by the number of tests involved to determine k in

$$\sigma_1^*/\sigma_2^* = \lambda^k, \quad (11)$$

leads to: for plane strain brittle, brittle-ductile, ductile, $k = 0.37, 0.35, 0.22$ respectively while for the corresponding regimes for plane stress $k = 0.49, 0.41, 0.22$ (cf. 0.50). The only category in good agreement with LEFM is plane stress brittle, although naturally one would not expect matching of LEFM and the data in the




Fig. 2. Comparison of test data with LEFM predictions of strength size dependence:
(a) plane strain, brittle




Fig. 2. Comparison of test data with LEFM prediction of strength size dependence:
(b) plane strain, brittle-ductile




Fig. 2. Comparison of test data with LEFM prediction of strength size dependence:

(c) plane strain, ductile




Fig. 2. Comparison of test data with LEFM prediction of strength size dependence:
(d) plane stress, brittle




Fig. 2. Comparison of test data with LEFM prediction of strength size dependence:
(e) plane stress, brittle-ductile




Fig. 2. Comparison of test data with LEFM prediction of strength size dependence
(f) plane stress, ductile

ductile regime. The real point is that no one curve fits any of the data distributions in any of the plots in Fig. 2 well. And this shortcoming cannot simply be dismissed as due to scatter because a significant proportion of the values plotted represent means themselves and, moreover, in over half of the instances where ranges can be calculated from the extreme values of σ_1^*/σ_2^* , these intervals do not even intersect the LEFM prediction irrespective of how brittle response is. We next consider means of quantifying the discrepancies between theory and actuality apparent in Fig. 2.

One way of gauging the effectiveness of the LEFM strength size prediction is to ask how often it does indeed predict the strength of one specimen given the strength of another geometrically similar one. Thus we regard LEFM as providing a *good prediction* if the data are within $\pm 5\%$ of (1), a *useful prediction* if within $\pm 10\%$. Table 1 summarizes the percentages of the data that fall within either of these two ranges, the percentages being arranged under the same separate classes as Fig. 2.[†] In the light of Fig. 2, the unsatisfactory percentages in Table 1 are not unexpected. As before, the ductile regime is worst, but of course could be reasonably discounted in evaluating LEFM's strength size prediction. Somewhat suprisingly, the brittle-ductile regime has higher percentages in some sort of agreement with LEFM than the brittle regime. Nonetheless, neither is very satisfactory with LEFM not being within useful agreement with about half of the data. Furthermore, a lot of what agreement there is comes from limited changes in scale ($\lambda \leq 2$), when there is really very little to predict.

To expand on this last statement, Fig. 3 shows how the percentages with useful and good agreement vary with scale factor. The exact histogram classes in Fig. 3 include their upper marks, and the data are drawn from the plane strain brittle regime. Other data exhibit similar behavior. Evident in Fig. 3 is the falling off

[†]The percentages are weighted by the number of tests involved - no real changes occur if this not done.

Table 1. LEFM strength prediction

Thickness classification	Material response regime	No. of tests involved	% within + 10% of - LEFM	% within + 5% of - LEFM
Plane strain	Brittle	699	37%	18%
	Brittle-ductile	281	44%	23%
	Ductile	1331	15%	5.5%
Plane stress	Brittle	103	44%	26%
	Brittle-ductile	119	55%	40%
	Ductile	663	20%	8.9%

as λ increases of the agreement of the LEFM size prediction with the data. Eventually ($\lambda > 7$), no data are within $\pm 10\%$ of (1). Although there are fewer tests for these higher scale factors, there would seem to be sufficient to show some agreement if indeed it were to be present (the numbers of tests involved within each class, and upon which percentages are based, are given in Fig. 3 in parentheses).

Motivated by a desire to reflect the trend apparent in Fig. 3, we introduce the *size effect*, s , as being the deviation from strength size independence. Thus

$$s = \sigma_1^* / \sigma_2^* - 1 = \sqrt{\lambda} - 1, \quad (12)$$

according to LEFM. Examining whether the data is in useful ($\pm 10\%$) or good ($\pm 5\%$) agreement with s of (12) tends to remove the almost automatic agreement for low λ inherent in our check on strength predictions. The percentages of the data complying to the two degrees with LEFM's *size* prediction are presented in Table 2, simply grouped under brittle, brittle-ductile and ductile since this is the true key to applicability, rather than plane stress versus plane strain. Without the easy acceptance limits for small changes of scale of the measures in Table 1, LEFM is shown to be quite ineffective in its ability to track size dependence in Table 2.

At this point it is natural to ask if perhaps satisfactory performance of linear elastic fracture mechanics requires a more restrictive set of circumstances than even the most applicable admitted here. Two options along these lines are to examine whether or not data stem from valid K_{IC} testing, and to attempt to separate out still more brittle behavior.

Concerning the first, it is not trivial to ascertain whether or not data is from valid K_{IC} tests according to current ASTM standards [137]. The reason for this is that normally insufficient information is given in articles - we did not come across a single paper which gave all the information required to check all of the E399 requirements in [137]. As a result, unless we could detect an aspect which infringed present standards, we simply took it on contributors own statements as




Fig. 3. Strength prediction agreement with varying scale factor for brittle response

Table 2. LEFM size prediction

Material response regime	No. of tests involved	% within + 10% of - LEFM	% within + 5% of - LEFM
Brittle	802	12%	4.2%
Brittle-ductile	400	18%	9.3%
Ductile	1994	4.4%	1.8%

to whether their data is valid K_{IC} or not. The agreement in terms of size effect prediction so as to avoid undue weight to low- λ values, is presented in the top half of Table 3. It would be difficult to argue that there is any significant improvement offered by the valid K_{IC} data over other plane strain brittle data.

Regarding the second, to see if there is a trend towards greater agreement with increasingly brittle response, we merely divide the same data set - plane strain, brittle - into two. We do this by defining a very brittle regime when $0 \leq r_Y/a < 0.01$ and a quasi-brittle regime when $0.01 \leq r_Y/a < 0.02$. Some of the data could not be segregated in this way. The agreement for the remainder, in terms of size effect prediction, is presented in the bottom half of Table 3. Again, it would be hard to establish there being any significant improvement.

In sum then, the physical data is not in satisfactory agreement with the strength size effects prediction of linear elastic fracture mechanics, especially when there are appreciable changes in scale, and this unsatisfactory situation appears to persist even when considerable effort is expended to conform with the assumptions underpinning LEFM.

CONCLUDING REMARKS

The prediction of strength size effects in fracture mechanics concurs with trends in physical data but is so naively simple as to be manifestly incomplete. Accordingly it can lead to predictions that are inaccurate to the point of not being acceptable in engineering. Moreover, such errors are typically not conservative when testing a specimen larger than the size of the intended application. And this situation can certainly arise in practice (recall the turbine disk example in the Introduction).

In practice, then, it is preferable, if not necessary, to test on the same size scale as the application. In the event of this being impractical, the following

Table 3. LEFM size prediction for different types
of brittle response

Classification	No. of tests involved	% within + 10% of - LEFM	% within + 5% of - LEFM
Valid K_{IC}	190	11%	4.7%
Not K_{IC}	509	9.6%	1.4%
Very brittle	158	10%	7.6%
Quasi-brittle	349	9.5%	4.6%

strategy might be adopted. For the most part, the size effects predicted by LEFM are in excess of those for the actual data. Hence when testing small and applying big, LEFM can be used to estimate the reduction in strength and usually will do so conservatively. On the other hand, when testing big and applying small, the LEFM prediction can greatly exceed the strength increases in fact realized. Here, though, it would appear that strength seldom decreases with decreasing size. Consequently, on nondimensionalizing LEFM by dividing the stress intensity factor by the specimen width at the crack to furnish a size independent parameter, allowances for size effects will generally be conservative.

A caution on the use of the above is in order. There is really no physical reasoning underlying the scheme; it is merely based on observation of the data. And this data is not always confined within LEFM's prediction of size effects and size independence so that there is physical evidence of the strategy being nonconservative.[†] Some judgement is therefore required in implementing this essentially empirical approach.

On a more fundamental front, there is reason to be concerned about the very basis of fracture mechanics. These concerns arise because there exist several hundred test results for appropriately brittle behavior *not* agreeing with the LEFM prediction of strength size effects. Every one of these represents data establishing a variation in fracture toughness with size. It follows that fracture toughness is demonstrably *not* a material property. Thus the use of the stress intensity factor as the parameter in and of itself controlling brittle fracture needs serious examination.

Acknowledgements - We are pleased to acknowledge the valuable benefit of discussions during the course of this work with J.H. Griffin of the Department of Mechanical Engineering at Carnegie-Mellon University and with D.A. Glasgow of the Air Force Office of Scientific Research (AFOSR). The financial support of AFOSR is also appreciated.

[†] There are a significant number of points above the LEFM prediction in Fig. 2 with ranges that do not extend down sufficiently to intersect the LEFM prediction, and conversely there are points below size independence ($\sigma_1^*/\sigma_2^* = 1$) with ranges not intersecting the same, although there are no ranges not including $\sigma_1^*/\sigma_2^* = 1$ in the brittle regime.

REFERENCES

1. A.A. Griffith, The phenomena of rupture and flow in solids. *Phil. Trans. R. Soc. (Lond.)* 221A, 163-198 (1920).
2. G.R. Irwin, Linear fracture mechanics, fracture transition and fracture control. *Engng Fracture Mech.* 1, 241-257 (1968).
3. G.B. Sinclair, On yield region estimation for classifying brittle behavior in fracture mechanics. Report SM 85-13, Dept. of Mechanical Engineering, Carnegie-Mellon University (1985).
4. V. Weiss and S. Yukawa, Critical appraisal of fracture mechanics. *Fracture Toughness Testing and Its Applications, ASTM STP 381*, 1-22 (1965).
5. G.B. Sinclair, A bibliography of strength size effects for cracked specimens. Report SM 85-10, Dept. of Mechanical Engineering, Carnegie-Mellon University (1985).
6. N.J. I. Adams and H.G. Munro, A single test method for evaluation of the J integral as a fracture parameter. *Engng Fracture Mech.* 6, 119-132 (1974).
7. Y. Akita, Scale effects in notch brittleness. *Weld. Res. Suppl.* 32, 475s-480s (1953).
8. W.R. Andrews, V. Kumar and M.M. Little, Small-specimen brittle-fracture toughness testing. *Fracture Mechanics: Thirteenth Conference, ASTM STP 743*, 576-598 (1981).
9. G. Argy, P.C. Paris, and F. Shaw, Fatigue crack growth and fracture toughness of 5083-0 aluminum alloy. *Properties of Materials for Liquefied Natural Gas Tankage, ASTM STP 579*, 96-137 (1975).
10. S. Banerjee, Influence of specimen size and configuration on the plastic zone size, toughness and crack growth. *Engng Fracture Mech.* 15, 343-390 (1981).
11. M.N. Bassim and T.R. Hsu, Fracture behavior of coal. *Fracture Problems and Solutions in the Energy Industry, Proc. Fifth Canadian Fracture Conf., Winnipeg, Canada*, 239-247 (1982).
12. A.D. Batte, W.S. Blackburn, A. Elsander, T.K. Hellen and A.D. Jackson, A comparison of the J^* integral with other methods of post yield fracture mechanics. *Int. J. Fracture* 21, 49-66 (1983).
13. J.A. Begley and J.D. Landes, The J-integral as a fracture criterion. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 1-20 (1972).
14. J.A. Begley and P.R. Toolin, Fracture toughness and fatigue crack growth rate properties of Ni-Cr-Mo-V steel sensitive to temper embrittlement. *Int. J. Fracture* 9, 243-253 (1973).

15. R.M. Bonesteel, Fracture of thin sections containing surface cracks. *Engng Fracture Mech.* 5, 541-554 (1973).
16. A. Boodberg, H.E. Davis, E.R. Parker and G.E. Troxell, Causes of cleavage fracture in ship plate - tests of wide notched plates. *Weld. Res. Suppl.* 27, 186s-199s (1948).
17. F.J. Bradshaw and C. Wheeler, The crack resistance of some aluminum alloys and the prediction of thin section failure. Rep. 73191, R. Aircr. Establ, Farnborough (1974).
18. W.F. Brown, Jr., J.D. Lubahn and L.J. Ebert, Effects of section size on the static notch bar tensile properties of mild steel plate. *Weld. Res. Suppl.* 26, 554s-559s (1947).
19. W.F. Brown, Jr. and J.E. Srawley, Plane strain crack toughness testing of high strength metallic metals. *Plane Strain Crack Toughness Testing of High Strength Metallic Materials, ASTM STP 410*, 1-65 (1966).
20. F.E. Buresch, Fracture toughness testing of alumina. *Fracture Mechanics Applied to Brittle Materials, ASTM STP 678*, 151-165 (1979).
21. C.M. Carman, D.F. Armiento and H. Markus, Crack resistance properties of high strength aluminum alloys. *Proc. First Int. Conf. Fracture*, Sendai, Japan, 2, 995-1038 (1965).
22. G.G. Chell and A. Davidson, A post-yield fracture mechanics analysis of single edge notched tension specimens *Mater. Sci. Engng* 24, 45-52 (1976).
23. G.G. Chell and R.S. Gates, A study of failure in the post yield regime using single edge-notched tension specimens *Int. J. Fracture* 14, 233-247 (1978).
24. G.G. Chell and G.M. Spink, A post yield fracture mechanics analysis of three-point bend specimens and its implications to fracture toughness testing. *Engng Fracture Mech.* 9, 101-121 (1977).
25. J.L.Christian, W.E. Witzell and A. Hurlich, Evaluation of the effects of specimen configuration and testing variables on crack propagation properties. *Adv. cryogen. Engng* 10, 86-101 (1964).
26. H.P. Chu, The notch-bend strength of titanium, aluminum, and copper-base alloys in heavy sections. *J. bas. Engng, Trans. Am. Soc. mech. Engrs* 91, 830-840 (1969).
27. G.A. Clarke, W.R. Andrews, P.C. Paris, and D.W. Schmidt, Single specimen tests for J_{IC} determination. *Mechanics of Crack Growth, ASTM STP 590*, 27-42 (1976).
28. L.S. Costin, Static and dynamic fracture behavior of oil shale. *Fracture Mechanics Method for Ceramics, Rocks, and Concrete, ASTM STP 745*, 169-184 (1981).

29. W.J. Crichlow, *The Ultimate Strength of Damaged Structure, Analysis Methods with Correlating Test Data*. Full scale testing of Aircraft Structures, International Series of Monographs in Aeronautics and Astronautics, Pergamon Press (1961).
30. T.S. DeSisto, F.L. Carr, and F.R. Larson, Influence of section size on mechanical properties and fracture toughness of 7075-T6 aluminum, 6A1-6V-2Sn titanium, and AISI 4340 steel. *Proc. Am. Soc. Test. Mater.* 63, 768-779 (1963).
31. A. Elsander, A. Poynton and D. Batte, Private communication (1977).
32. J. Eschweiler and D. Munz, Comparison of fracture toughness of aluminum alloys from short bar and compact specimens. *Int. J. Fracture* 20, R131-R133 (1982).
33. W.G. Ferguson and M.N. Sargisson, Fracture toughness of Comsteel En25. *Engng Fracture Mech.* 5, 499-508 (1973).
34. R.G. Forman, Experimental program to determine effect of crack buckling and specimen dimensions on fracture toughness of thin sheet materials. Report AFFDL-TR-65-146, Air Force Flight Dynamics Laboratory, Dayton, Ohio (1966).
35. A. Frediani, An evaluation of the reliability of fracture mechanics methods. *Engng Fracture Mech.* 14, 289-322 (1981).
36. C.N. Freed, A.M. Sullivan and J. Stoop, Influence of dimensions of the center-cracked tension specimen on K_{IC} . *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 98-113 (1972).
37. W.W. Gerberich, P.L. Hemmings, V.F. Zackay, and E.R. Parker, Interactions between crack growth and strain-induced transformation. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 288-305 (1969).
38. H.D. Greenberg, E.T. Wessel and W.H. Pryle, Fracture toughness of turbine-generator rotor forgings. *Engng Fracture Mech.* 1, 653-674 (1970).
39. A. W. Gunderson, Size effects for compact specimens made of a beta-processed mill-annealed plate of Ti-6Al-4V. Air Force Mater. Lab. Rep. AFML-MXE 73-3, Wright-Patterson AFB (1973).
40. G.S. Hall, S.R. Seagle and H.B. Bomberger, Effect of specimen width on fracture toughness of Ti-6Al-4V plate. *Toughness and Fracture Behaviour of Titanium, ASTM STP 651*, 227-245 (1978).
41. A.M. Hasofer, A statistical theory of the brittle fracture of steel. *Int. J. Fracture Mech.* 4, 439-452 (1968).
42. J.R. Hawthorne and T.R. Mager, Relationship between Charpy V and fracture mechanics K_{IC} assessments of A533-B class 2 pressure vessel steel. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II, ASTM STP 514*, 151-163 (1972).

43. R.H. Heyer and D.E. McCabe, Plane-stress fracture toughness testing using a crack-line-loaded specimen. *Engng Fracture Mech.* 4, 393-412 (1972).
44. G.H. Hilton, Evaluation of Ti-6Al-4V for specification requirements. *Fracture Prevention and Control*, Am. Soc. Metals, 181-197 (1974).
45. F.H. Huang and D.S. Gelles, Influence of specimen size and microstructure on the fracture toughness of a martensitic stainless steel. *Engng Fracture Mech.* 19, 1-20 (1984).
46. C.M. Hudson and P.E. Lewis, NASA-Langley research center's participation in a round-robin comparison between some current crack-propagation prediction methods. *Part-Through Crack Fatigue Life Prediction*, ASTM STP 687, 113-128 (1979).
47. K. Ikeda, M. Aoki, H. Kikuchi, U. Schieferstein and C. Berger, Fracture toughness of turbine rotor shaft and validity criterion for K_{IC} . *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 687-697 (1977).
48. M.H. Jones and W.F. Brown, Jr., The influence of crack length and thickness in plane strain fracture toughness tests. *Review of Developments in Plane Strain Fracture Toughness Testing*, ASTM STP 463, 63-91 (1970).
49. M.H. Jones, R.T. Bubsey and W.F. Brown, Jr., Sharply notched cylindrical tension specimen for screening plane-strain fracture toughness. Part I: Influence of fundamental testing variables on notch strength. *Developments in Fracture Mechanics Test Methods Standardization*, ASTM STP 632, 115-134 (1977).
50. H.-J. Kaiser and K.E. Hagedorn, Prediction of maximum load values of different sized CT-specimens using the J-R-curve concept. *Fracture and the Role of Microstructure*, Proc. Fourth European Conf. Fracture, Leoben, Austria, 1, 76-83 (1982).
51. M.F. Kaplan, Crack propagation and the fracture of concrete. *J. Am. Concr. Inst.* 58, 591-610 (1961).
52. J.G. Kaufman, Fracture toughness testing, including screening and quality control testing, in the aluminum industry. *Fracture Prevention and Control*, Am. Soc. Metals, 121-142 (1974).
53. J.G. Kaufman, Sharp-notch tension testing of thick aluminum alloy plate with cylindrical specimens. *Fracture Toughness, Proceedings of the 1971 National Symposium on Fracture Mechanics, Part II*, ASTM STP 514, 82-97 (1972).
54. J.G. Kaufman and F.G. Nelson, More on specimen size effects in fracture toughness testing. *Fracture Toughness and Slow Stable Cracking*, ASTM STP 559, 74-85 (1974).
55. J.G. Kaufman, G.T. Sha, R.F. Kohm, and R.J. Bucci, Notch-yield ratio as a quality control index for plane-strain fracture toughness. *Cracks and Fracture*, ASTM STP 601, 169-190 (1976).

56. H.P. Keller and D. Munz, Effect of specimen size on J-integral and stress-intensity factor at the onset of crack extension. *Flaw Growth and Fracture, ASTM STP 631*, 217-231 (1977).
57. E.P. Klier and V. Weiss, The effect of section size on the notch strength and fracture development in selected structural metals. *Proc. Am. Soc. Test. Mater.* 61, 1307-1323 (1961).
58. H. Kobayashi, K. Hirano, H. Nakamura and H. Nakazawa, A fractographic study on evaluation of fracture toughness. *Proc. Fourth Int. Conf. Fracture, Waterloo, Canada*, 3, 583-592 (1977).
59. J.M. Krafft, A.M. Sullivan and R.W. Boyle, Effect of dimensions on fast fracture instability of notched sheets. *Proc. Crack Propagation Symposium, Cranfield, U.K.*, 8-28 (1961).
60. A.J. Krasowsky, Yu. A. Kashtalyan and V.N. Krasiko, Brittle-to-ductile transition in steels and the critical transition temperature. *Int. J. Fracture* 23, 297-315 (1983).
61. P. Kuhn, Residual tensile strength in the presence of through cracks or surface cracks. Natn. Aeronaut. Space Adm. Tech. Note NASA TN D-5432 (1970).
62. P. Kuhn, Strength calculations for sheet metal parts with cracks. *Mater. Res. Stands* 8, 9/21-26 (1968).
63. R.L. Lake, 'What R-curves can tell us about specimen size effects in the K_{IC} test. *Mechanics of Crack Growth, ASTM STP 590*, 208-218 (1976).
64. J.D. Landes and J.A. Begley, Test results from J-integral studies: an attempt to establish a J_{IC} testing procedure. *Fracture Analysis, ASTM STP 560*, 170-186 (1974).
65. M.H. Lewis and G. Smith, Fracture mechanisms in Si-Al-O-N ceramics. *Proc. Fourth Int. Conf. Fracture, Waterloo, Canada*, 3, 867-874 (1977).
66. W.A. Logsdon, An evaluation of crack growth and fracture properties of AISI 403 modified 12Cr stainless steel. *Engng Fracture Mech.* 7, 23-40 (1975).
67. W.A. Logsdon, Elastic plastic (J_{IC}) fracture toughness values: their experimental determination and comparison with conventional linear elastic (K_{IC}) fracture toughness values for five materials. *Mechanics of Crack Growth, ASTM STP 590*, 43-60 (1976).
68. W.A. Logsdon and J.A. Begley, Upper shelf temperature dependence of fracture toughness for four low to intermediate strength ferritic steels. *Engng Fracture Mech.* 9, 461-470 (1977).
69. J.D. Lubahn, Effect of section size on fracturing. *Proc. 1955 Sagamore Res. Conf., Syracuse, N.Y.*, 143-161 (1955).

70. J.D. Lubahn, Experimental determination of energy release rate for notch bending and notch tension. *Proc. Am. Soc. Test. Mater.* 59, 885-913 (1959).
71. J.D. Lubahn and S. Yukawa, Size effects in slow notch-bend tests of a nickel-molybdenum-vanadium steel. *Proc. Am. Soc. Test. Mater.* 58, 661-676 (1958).
72. B.D. Macdonald, Fracture resistance of a structural steel as characterized by the strength of the plastic stress singularity. *Int. J. Fracture* 20, 179-194 (1982).
73. K. Markstrom, Experimental determination of J_c data using different types of specimen. *Engng Fracture Mech.* 9, 637-646 (1977).
74. K. Markstrom, On fracture toughness and its size dependence for steels showing thickness delamination. *Engng Fracture Mech.* 4, 593-603 (1972).
75. A.J. McEvily, Jr., W. Illg and H.F. Hadrath, Static strength of aluminum alloy specimens containing fatigue cracks. Natn. Aeronaut. Space Adm. Tech. Note NASA TN 3816 (1956).
76. K.R. McKinney and R.W. Rice, Specimen size effects in fracture toughness testing of heterogeneous ceramics by the notch beam method. *Fracture Mechanics Methods for Ceramics, Rocks, and Concrete, ASTM STP 745*, 118-126 (1981).
77. I. Milne and P.J. Worthington, The fracture toughness of a low alloy pressure vessel steel in the post yield regime. *Mater. Sci. Engng* 26, 185-193 (1976).
78. E.M. Morozov, Some problems in experimental fracture mechanics. *Engng Fracture Mech.* 13, 541-561 (1980).
79. H.G. Munro and N.J.I. Adams, Fatigue and fracture of a 200 ksi grade maraging steel proposed for use in military bridging. *Engng Fracture Mech.* 4, 705-715 (1972).
80. D. Munz, Minimum specimen size for the application of linear-elastic fracture mechanics. *Elastic-Plastic Fracture, ASTM STP 668*, 406-425 (1979).
81. D. Munz, K.H. Galda, and F. Link, Effect of specimen size on fracture toughness of a titanium alloy. *Mechanics of Crack Growth, ASTM STP 590*, 219-234 (1976).
82. N. Murayama, A.W. Pense, and R.D. Stout, The fracture toughness of cryogenic steels. *Adv. cryogen. Engng* 22, 27-34 (1977).
83. B.K. Neale, An investigation into the effect of thickness on the fracture behaviour of compact tension specimens. *Int. J. Fracture* 14, 203-212 (1978).
84. F.G. Nelson and J.G. Kaufman, Fracture toughness of plain and welded 3-in-thick aluminum alloy plate. *Progress in Flaw Growth and Fracture Toughness Testing, ASTM STP 536*, 350-376 (1973).

85. F.G. Nelson, P.E. Schilling and J.G. Kaufman, The effect of specimen size on the results of plane-strain fracture-toughness tests. *Engng Fracture Mech.* 4, 33-50 (1972).
86. J.C. Newman, Jr., Fracture analysis of various cracked configurations in sheet and plate materials. *Properties Related to Fracture Toughness, ASTM STP 605*, 104-123 (1976).
87. T.W. Orange, Fracture toughness of wide 2014-T6 aluminum sheet at -320°F. Natn. Aeronaut. Space Adm. Tech. Note NASA TN D-4017 (1967).
88. E.R. Parker, The effect of section size on the fracture strength of mild steel. *Fracturing of Metals*, ASM, Cleveland, Ohio, 82-89 (1948).
89. J.S. Pascover, M. Hill, and S.J. Matas, The application of fracture toughness testing to the development of a family of alloy steels. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 310-325 (1965).
90. W.F. Payne, Incorporation of fracture information in specifications. *Fracture Toughness Testing and its Applications, ASTM STP 381*, 357-371 (1965).
91. P.K. Poulouse, D.L. Jones and H. Liebowitz, A comparison of the geometry dependence of several nonlinear fracture toughness parameters. *Engng Fracture Mech.* 17, 133-151 (1983).
92. P.K. Poulouse and H. Liebowitz, A study of the size-effect on plastic energy dissipation and toughness in 2024-T3 aluminum alloy sheets. *Engng Fracture Mech.* 20, 179-185 (1984).
93. S.K. Putatunda and S. Banerjee, Effect of size on plasticity and fracture toughness. *Engng Fracture Mech.* 19, 507-529 (1984).
94. A.J. Repko, M.H. Jones, and W.F. Brown, Jr., Influence of sheet thickness on sharp-edge-notch properties of a β titanium alloy at room and low temperatures. *Symp. on Evaluation of Metallic Materials in Design for Low-Temperature Service, ASTM STP 302*, 213-229 (1961).
95. S.T. Rolfe and S.R. Novak, Discussion: M.H. Jones and W.F. Brown, Jr., Closure. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 92-95, 97-101 (1970).
96. S.T. Rolfe and S.R. Novak, Slow-bend K_{IC} testing of medium-strength high-toughness steels. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 124-159 (1970).
97. J. Royer, J.M. Tissot, A. Pelissier-Tanon, P. LePoac, and D. Miannay, J-integral determinations and analyses for small test specimens and their usefulness for estimating fracture toughness. *Elastic-Plastic Fracture, ASTM STP 668*, 334-357 (1979).
98. G. Sachs, B.B. Muvdi, and E.P. Klier, Design properties of high strength

- steels in the presence of stress concentrations, Part I - Dependence of tension and notch tension properties of high strength steels on a number of factors. Tech. Rep. 56-395, I, Wright Air Development Center, Dayton Ohio (1956).
99. R.A. Schmidt, Fracture-toughness testing of limestone. *Expl Mech.* 16, 161-167 (1976).
 100. R.A. Schmidt and T.J. Lutz, K_{IC} and J_{IC} of westerly granite - effects of thickness and in-plane dimensions. *Fracture Mechanics Applied to Brittle Materials, ASTM STP 678*, 166-182 (1979).
 101. W.L. Server and R.A. Wullaert, The use of small specimen strength ratio for measuring fracture toughness. *Engng Fracture Mech.* 11, 477-486 (1979).
 102. W.L. Server, R.A. Wullaert, and J.W. Sheckherd, Evaluation of current procedures for dynamic fracture-toughness testing. *Flaw Growth and Fracture, ASTM STP 631*, 446-461 (1977).
 103. W.O. Shabbitts, W.H. Pryle and E.T. Wessel, Heavy section fracture toughness properties of A533, Grade-B, Class-1 steel plate and submerged arc weldment. HSST Tech. Rep. 6, WCAP-7414, Westinghouse Electric Corporation, Pittsburgh, Pennsylvania (1969).
 104. J.L. Shannon, Jr., J.K. Donald and W.F. Brown, Jr., Heavy-section fracture toughness screening specimen. *Developments in Fracture Mechanics Test Methods Standardization, ASTM STP 632*, 96-114 (1977).
 105. P.E. Shearin, A. E. Ruark and R.M. Trimble, Size effects in steels and other metals from slow notch bend tests. *Proc. Fracturing of Metals Seminar*, Chicago, Illinois, 167-188 (1948).
 106. T.T. Shih and G.A. Clarke, Effects of temperature and frequency on the fatigue crack growth rate properties of a 1950 vintage CrMOV rotor material. *Fracture Mechanics, ASTM STP 677*, 125-143 (1979).
 107. W. Soete, An experimental approach to fracture initiation in structural steels. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 1, 775-804 (1977).
 108. Special ASTM Committee, Fracture testing of high-strength sheet materials (Third Report). *Mater. Res. Stands* 1, 877-885 (1961).
 109. Special ASTM Committee, Screening tests for high-strength alloys using sharply notched cylindrical specimens (Fourth Report). *Mater. Res. Stands* 2, 196-203 (1962).
 110. Special ASTM Committee, Progress in measuring fracture toughness and using fracture mechanics (Fifth Report). *Mater. Res. Stands* 4, 107-119 (1964).
 111. E.A. Steigerwald, Crack toughness measurements of high-strength steels. *Review of Developments in Plane Strain Fracture Toughness Testing, ASTM STP 463*, 102-123 (1970).

AD-A161 285

ON THE ROLE OF DIMENSIONLESS ELASTIC FRACTURE MECHANICS 2/2

(U) CARNEGIE-MELLON UNIV PITTSBURGH PA DEPT OF

MECHANICAL ENGINEERING G B SINCLAIR 03 JUL 85 SM-85-14

UNCLASSIFIED

AFOSR-TR-85-0942 AFOSR-84-0047


F/G 20/11

NL

END

TABED

OTC



MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

112. A.M. Sullivan, C.N. Freed and J. Stoop, Comparison of R-curves determined from different specimen types. *Fracture Toughness Evaluation by R-Curve Methods, ASTM STP 527*, 85-104 (1973).
113. A.M. Sullivan and J. Stoop, Further aspects of fracture resistance measurement on thin sheet material: yield stress and crack length. *Fracture Toughness and Slow-Stable Cracking, ASTM STP 559*, 99-110 (1974).
114. J.D.G. Sumpter, Use of scale models to study ductile tearing. *Int. J. Fracture* 23, R121-R124 (1983).
115. D. Sunamoto, M. Satoh, T. Funada and M. Tomimatsu, Specimen size effect on J-integral fracture toughness. *Proc. Fourth Int. Conf. Fracture*, Waterloo, Canada, 3, 267-272 (1977).
116. H.R. Thomas and D.F. Windenburg, A study of slotted tensile specimens for evaluating the toughness of structural steel. *Weld. Res. Suppl.* 27, 209s-215s (1948).
117. D.Y. Wang, Plane-stress fracture toughness and fatigue-crack propagation of aluminum alloy wide panels. *Progress in Flaw Growth and Fracture Toughness Testing, ASTM STP 536*, 334-349 (1973).
118. D.Y. Wang and D.E. McCabe, Investigation of R-curve using comparative tests with center-cracked-tension and crack-line-wedge-loaded specimens. *Mechanics of Crack Growth, ASTM STP 590*, 169-193 (1976).
119. S. Wei, Z. Tingshi, G. Daxing, L. Dunkang, L. Poliang and Q. Xiaoyun, Fracture toughness measurement by a cylindrical specimen with ring-shaped crack. *Engng Fracture Mech.* 16, 69-82 (1982).
120. V. Weiss, G. Schaeffer and J. Fehling, Effect of section size on notch strength. *J. bas. Engng, Trans. Am. Soc. mech. Engrs Ser. D* 88, 675-681 (1966).
121. V. Weiss, J. Sessler, P. Packman and G. Sachs, The effect of several geometrical variables on the notch tensile strength of 4340 steel sheet heat treated to three strength levels. Wright Air Development Div. Tech. Rep. 60-310, Wright-Patterson AFB (1960).
122. A.A. Wells, The geometrical size effect in notch brittle fracture. *Trans. NE.Cst Instn Engrs Shipbltrs* 71, 277-290 (1955).
123. E.T. Wessel, State of the art of the WOL specimen for K_{IC} fracture toughness testing. *Engng Fracture Mech.* 1, 77-103 (1968).
124. E.T. Wessel, W.G. Clark, Jr. and W.H. Pryle, Fracture mechanics technology applied to heavy section steel structures. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 825-850 (1969).
125. J.G. Williams and P.D. Ewing, Crack propagation in plates and shells subjected to bending and direct loading. *Proc. Second Int. Conf. Fracture*, Brighton, U.K., 119-130 (1969).

126. W.M. Wilson, R.A. Hechtman and W.H. Bruckner, Cleavage fracture of ship plates as influenced by size effect. *Weld. Res. Suppl.* 27, 200s-207s (1948).
127. D.H. Winne and B.M. Wundt, Application of the Griffith-Irwin theory of crack propagation to the bursting behavior of disks, including analytical and experimental studies. *Trans. Am. Soc. mech. Engrs* 80, 1643-1655 (1958).
128. F.J. Witt, Fracture toughness parameters obtained from single small specimen tests. Rep-WCAP-9397, Westinghouse Electric Corporation, Pittsburgh, Pennsylvania (1978).
129. P.J. Worthington, Private communication.
130. S. Yukawa, Temperature and microstructure dependence of size effects in notched bend tests of some alloy steels. *Trans. Am. Soc. Metals* 53, 871-881 (1961).
131. S. Yukawa and J.G. McMullin, Effects of specimen size and notch acuity on the brittle fracture strength of a heat-treated steel. *J. bas. Engng., Trans. Am. Soc. mech. Engrs Ser. D*, 83, 541-544 (1961).
132. S. Yusuff, Effects of yielding and size upon fracture of plates and pressure cylinders. *Int. J. Fracture Mech.* 8, 129-138 (1972).
133. S. Yusuff, Fracture phenomena in metal plates. *Aircr. Engng* 34, 140-148 (1962).
134. C. Zhen-Yuan, Exploring the fracture toughness K_{IE} and K_{IC} of a medium-strength steel plate using the surface-flaw test. *Engng Fracture Mech.* 13, 775-789 (1980).
135. R.E. Zinkham, Anisotropy and thickness effects in fracture of 7075-T6 and -T651 aluminum alloy. *Engng Fracture Mech.* 1, 275-289 (1968).
136. R.E. Zinkham and R.J. Baughan, Screening for fracture toughness using the sharp notch tension test. *Engng Fracture Mech.* 9, 147-154 (1977).
137. 1982 *Annual Book of Standards, Part 10*. ASTM, Philadelphia, Pennsylvania (1982).

APPENDIX

Here we tabulate all sources used together with a brief description of the testing and the actual data taken as well as its classification. Within the tables, sources are arranged alphabetically by author surname. For the test description we employ the following abbreviations for specimen type: CCP...center-cracked plate, CTS...compact tension specimen, CVN...Charpy V-notch, RCT...round compact tension, SEN...single-edge notch, TNF...thumbnail flaw, VNC...V-notched cylinder, WOL...wedge opening loading, 3PB...three-point bend, and 4PB...four-point bend. After specimen type (s), there is a sequence of quantities in parenthesis which can have as many entries as (n, r/a, T, a/W). The first, n, is always provided and is the number of distinct tests involved in all of the data gleaned from a single source. Thus the total n is somewhat less than the combined number of tests recorded in Table 1, since there some tests are involved in more than one ratio and are therefore counted twice, whereas here each is counted but once. In instances where the precise number of tests could not be determined, n is a greatest lower bound. The second, r/a, is the maximum dimensionless notch radius if in fact notches are employed; no corresponding entry implies fatigue pre-cracks only. The third, T, indicates inclusion of data for temperatures other than room temperature (RT); no T means all data at RT. The fourth, a/W, shows that some of the mean stress ratios are for pairs of scaled specimens whose only distinguishing feature is distinct a/W; no a/W means there is no appreciable variation in relative crack length. Finally by way of explanation, the abbreviations used in the classification are: p σ ...plane stress, p ϵ ...plane strain, b...brittle, b-d...brittle-ductile, and d...ductile. The tables in order present information for steels, aluminum alloys, other metals and non metals.

Table 4. Sources and data for steels

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Akita [7].	2.10	1.07	pr, d
3PB (4, 1/10)	4.20	1.06	pr, d
Andrews <i>et al.</i> [8], RCT (3,T)	2.00	1.25	pr, b-d
Banerjee [10].	8.00	1.34	pr, d
CTS (4)	12.00	1.38	pr, d
Batte <i>et al.</i> [12].	1.50	1.06	pr, d
SEN (8)	2.00	1.13	pr, d
	3.00	1.11	pr, d
Begley and Landes [13].	2.00	1.06	pr, d
CTS and 3PB (8,T)		1.18	pr, d
Begley and Toolin [14], CTS (2,T)	1.50	1.02	pr, b
Boodberg <i>et al.</i> [16].	2.00	1.01	pr, d
CCP (56, 1/160, T)		1.05	pr, d
		1.06	pr, d
		1.06	pr, d
		1.08	pr, d
		1.09	pr, d
		1.10	pr, d
		1.11	pr, d
	4.00	1.08	pr, d
		1.15	pr, d
		1.15	pr, d
		1.15	pr, d
		1.16	pr, d
		1.17	pr, d
	6.00	1.08	pr, d
		1.13	pr, d
		1.15	pr, d
		1.15	pr, d
		1.17	pr, d
		1.17	pr, d
		1.18	pr, d
		1.18	pr, d
		1.22	pr, d
		1.23	pr, d
		1.25	pr, d
		1.27	pr, d
	9.00	1.04	pr, d
		1.31	pr, d
Brown <i>et al.</i> [18].	2.00	1.10	pr, d
VNC (12, 1/36)	4.00	1.15	pr, d
	8.00	1.18	pr, d
	16.00	1.25	pr, d
Brown and Srawley [19].	2.00	1.36	pr, b
4PB and SEN (57, a/w)		1.36	pr, b
		1.38	pr, b
		1.39	pr, b
		1.45	pr, b
		1.48	pr, b
		1.51	pr, b
		1.54	pr, b-d
		1.63	pr, b
	3.00	1.82	pr, b
		1.96	pr, b
Chell and Davidson [22].	1.67	1.28	pr, d
SEN (10, a/w)		1.45	pr, d
	1.88	1.21	pr, d
	3.13	1.34	pr, d
		1.73	pr, d
		1.91	pr, d
Chell and Gates [23].	1.88	1.25	pr, d
SEN (10, a/w)		1.34	pr, d
	3.13	1.17	pr, d
		1.54	pr, d
Chell and Spink [24], 3PB (3)	4.00	1.48	pr, d
Christian <i>et al.</i> [25].	2.00	1.18	pr, b-d
CCP (14, 1/500, T)		1.21	pr, d
		1.23	pr, d
		1.31	pr, d
	3.25	1.48	pr, d
		1.53	pr, b-d
	4.50	1.69	pr, d
		1.72	pr, b-d
	9.00	2.05	pr, d
		2.24	pr, d
Clark <i>et al.</i> [27].	2.00	1.34	pr, d
CTS (29, T)		1.36	pr, d
		1.37	pr, d
	4.00	1.43	pr, d

Table 4 continued

Source and test	Scale factor, λ	Mean stress ratio σ_1/σ_2	Classification
DeSisto <i>et al.</i> [30], VNC (9, 1/23)	1.41 2.23 3.16 4.46 10.00 14.06 22.31 31.56	0.95 1.01 1.09 1.05 1.16 1.11 1.28 1.30	<i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i>
Elsender <i>et al.</i> [31], as reported in Chell and Gates [23], SEN (10, <i>slw</i>)	1.50 2.00 3.00	1.02 1.11 1.20 1.43	<i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i>
Ferguson and Sargisson [33], VNC (8)	1.25 1.47 1.75 2.01 2.51 3.01 4.02	1.10 0.98 1.11 1.15 1.22 1.37 1.55	<i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i>
Greenburg <i>et al.</i> [38], WOL (42,T)	1.33 1.50 2.00	0.96 1.66 0.97 1.19 1.26 1.27 1.27 1.43 1.49 1.50 1.58 1.69 1.09 2.26	<i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i>
Hasofer [41], VNC (89)	1.50	1.06	<i>pe, b-d</i>
Hawthorne and Mager [42], CT (2,T)	4.00	1.13	<i>pe, b</i>
Meyer and McCabe [43], WOL (9)	2.00	0.94 1.00 1.07 1.25	<i>pe, b</i> <i>b-d</i> <i>b-d</i> <i>b</i>
Huang and Gelles [45], CTS (2,T)	2.00	1.03	<i>pe, d</i>
Ikeda <i>et al.</i> [47], CTS (3,T)	3.00 6.00	1.21 1.23 1.25 1.21 1.72 1.74	<i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i>
Jones and Brown [48], 3PB (17)	1.85 2.20 3.70 4.07	1.18 1.37 1.62 1.40	<i>pe, b-d</i> <i>pe, b</i> <i>pe, b-d</i> <i>pe, b-d</i>
Kaiser and Hagedorn [50], CTS (4)	2.00 6.00	1.21 1.47	<i>pe, d</i> <i>pe, d</i>
Keller and Munz [56], CTS (4)	1.79 3.57 7.14	1.29 1.21 1.22	<i>pe, b-d</i> <i>pe, b-d</i> <i>pe, b-d</i>
Klier and Weiss [57], VNC (35, 1/44)	1.67 3.67 5.00	1.06 1.09 1.24 1.13 1.18 1.52 1.64 1.04 1.25 1.61 1.79	<i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i> <i>pe, d</i>
Kobayashi <i>et al.</i> [58], CTS (4)	2.00	2.13	<i>pe, b-d</i>
Krasowsky <i>et al.</i> [60], 3PB (88, T)	2.00	1.00 1.11 1.18 1.39 1.40 1.45 1.51 1.29 1.57	<i>pe, d</i> <i>pe, d</i> <i>pe, b-d</i> <i>pe, b-d</i> <i>pe, b</i> <i>pe, b</i> <i>pe, b</i> <i>pe, d</i> <i>pe, d</i>

Table 4 continued

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Kuhn [62], CCP (5)	1.50	0.85	pr, d
	2.00	1.03	pr, d
Lendes and Begley [64], CTS (6,T)	1.50	1.13	pr, d
	2.00	1.13	pr, d
	4.00	1.59	pr, d
	6.00	1.88	pr, d
	8.00	1.82	pr, d
Logsdon [66], CTS (6,T)	1.33	1.20	pr, b
	1.50	0.99	pr, b
Logsdon [67], CTS (2)	1.33	1.51	pr, b
Logsdon and Begley [68], CTS (9,T)	1.50	1.03	pr, b
	2.00	1.18	pr, b
		1.65	pr, b-d
Lubahn [69], 3PB and VNC (46, 1/12)	1.67	1.07	pr, d
		1.09	pr, d
		1.27	pr, d
	2.00	1.01	pr, d
		1.12	pr, d
	2.09	1.15	pr, d
	2.20	1.11	pr, d
	3.67	1.18	pr, d
		1.24	pr, d
		1.26	pr, d
		1.61	pr, d
		1.62	pr, d
		1.76	pr, d
	4.00	1.20	pr, d
	4.38	1.29	pr, d
	5.00	1.13	pr, d
		1.14	pr, d
		1.38	pr, d
		1.57	pr, d
		1.68	pr, d
		1.79	pr, d
		2.17	pr, d
	8.58	1.14	pr, d
	8.88	1.94	pr, d
	22.32	3.37	pr, d
Lubahn [70], 3PB and VNC (24, 1/12)	1.60	1.07	pr, d
	2.00	1.14	pr, d
	2.40	1.12	pr, d
	3.60	1.20	pr, d
	4.00	1.29	pr, d
	5.20	1.51	pr, d
	5.33	1.74	pr, d
	8.00	1.94	pr, d
	9.00	2.04	pr, d
	10.67	1.97	pr, d
	21.33	3.36	pr, d
Lubahn and Yukawa [71], 3PB (18, 1/13)	2.00	1.13	pr, d
		1.14	pr, d
	3.27	1.22	pr, b-d
	4.00	1.25	pr, d
		1.29	pr, d
	8.00	1.93	pr, d
	9.00	1.77	pr, d
	20.00	3.27	pr, d
Macdonald [72], CCP and 3PB (14, a/w)	3.00	1.06	pr, d
		1.16	pr, d
		1.21	pr, d
	4.00	2.41	pr, d
Markstrom [73], CT (16)	5.00	1.46	pr, d
		1.74	pr, d
Markstrom [74], 3PB (14,T)	2.50	1.05	pr, b
		1.85	pr, b
	4.00	1.01	pr, b
		1.04	pr, b
		1.17	pr, b
	10.00	1.21	pr, b
Milne and Worthington [77], 3PB (19 T, a/w)	2.40	1.14	pr, d
		1.15	pr, d
		1.16	pr, d
		1.23	pr, d
		1.23	pr, d
	8.00	1.38	pr, d
		2.11	pr, d

Table 4 continued

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Munro and Adams [79], 3PB (56)	1.50	1.16	pe, d
	2.00	1.38	pe, d
	4.00	1.36	pe, d
	5.50	1.21	pe, d
Murayama <i>et al.</i> [82], 3PB and CTS (6,T)	1.49	1.44	pe, b-d
	1.52	1.44	pe, d
		1.59	pe, b-d
Neale [83], CTS (6)	2.00	1.29	pe, b-d
	4.00	1.97	pe, b-d
Parker [88], CCP (9)	2.00	1.06	pe, d
		1.10	pe, d
	4.00	1.09	pe, d
	6.00	1.10	pe, d
		1.30	pe, d
	9.00	1.03	pe, d
		1.34	pe, d
Pascover <i>et al.</i> [89], CCP (4, a/w)	1.50	0.96	pe, d
		1.57	pe, d
Putatunda and Banerjee [93], CTS (13)	2.00	1.20	pe, d
	4.00	1.43	pe, d
	8.00	1.73	pe, d
Rolfe and Novak [95], 3PB (8)	1.50	1.12	pe, b-d
		1.22	pe, b
Rolfe and Novak [96], 4PB (6)	1.33	1.16	pe, d
	1.50	0.97	pe, d
	1.67	1.24	pe, d
	2.00	1.11	pe, d
Royer <i>et al.</i> [97], 3PB and CTS (9)	2.00	1.41	pe, d
		1.49	pe, d
	4.00	1.36	pe, d
		1.76	pe, d
		1.89	pe, d
	8.00	1.81	pe, d
Server <i>et al.</i> [102], 3PB (7)	2.00	1.34	pe, b
	2.54	1.36	pe, b
	5.08	1.96	pe, b
Shabbits <i>et al.</i> [103], as reported in Server and Wullaert [101], CTS (5)	2.00	1.21	pe, b
	4.00	1.13	pe, b
	10.00	0.94	pe, b
	11.00	0.92	pe, b
Shannon <i>et al.</i> [104], DEN (36)	2.00	1.39	pe, b-d
		1.40	pe, d
		1.41	pe, b-d
		1.48	pe, b
		1.50	pe, b
		1.62	pe, d
Shearin <i>et al.</i> [105], 4PB (5, 1/10)	3.00	0.83	pe, d
	3.13	0.96	pe, d
	5.00	0.79	pe, d
Shih and Clarke [106], CTS (2)	1.50	1.06	pe, b
Soete [107], CCP (20, a/w)	3.00	0.98	pe, d
		0.98	pe, d
		1.07	pe, d
	9.00	1.13	pe, d
Special ASTM Committee, Third Report [108], CCP (105, 1/1000)	2.31	1.06	pe, d
		1.20	pe, d
		1.34	pe, d
		1.37	pe, b
		1.39	pe, b
		1.47	pe, b
		1.59	pe, b-d
	2.50	1.06	pe, d
		1.23	pe, d
		1.36	pe, b
		1.39	pe, b-d
		1.40	pe, b
	3.00	1.33	pe, d
		1.45	pe, d
		1.64	pe, d
		1.67	pe, d
		1.77	pe, b
		1.79	pe, b
		2.33	pe, d
		2.72	pe, b

Table 4 continued

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Special ASTM Committee, Fourth Report [109], VNC (21)	1.67	1.05	pe, d
		1.09	pe, d
		1.10	pe, d
	3.00	0.98	pe, d
		1.13	pe, d
		1.37	pe, d
		1.42	pe, d
		1.05	pe, d
	3.67	1.24	pe, d
		1.52	pe, d
		1.78	pe, d
		1.08	pe, d
		1.30	pe, d
	5.00	1.65	pe, d
		2.00	pe, d
Special ASTM Committee, Fifth Report [110], CCP (7)	1.50	1.08	pe, d
	2.00	1.16	pe, d
	3.00	1.70	pe, d
	4.00	1.93	pe, d
Steigerwald [111], 3PB and 4PB (21)	1.04	0.88	pe, b-d
	1.14	0.94	pe, b-d
	1.17	0.88	pe, b-d
	1.23	0.86	pe, b-d
	1.27	0.91	pe, b-d
	1.30	0.98	pe, b-d
	1.35	0.99	pe, b-d
	1.72	1.16	pe, d
	2.10	1.36	pe, d
	2.26	1.44	pe, d
	2.47	1.96	pe, d
	2.84	1.57	pe, d
	3.24	1.65	pe, d
	3.62	1.75	pe, d
	3.90	1.65	pe, d
	4.12	1.74	pe, d
Sumpter [114], Bulge test (2)	6.00	1.12	pe, d
Sunamoto <i>et al.</i> [115], CTS (2), T, a/w	2.00	0.98	pe, d
		1.08	pe, d
		1.35	pe, b
		1.44	pe, d
		1.55	pe, d
	4.00	1.65	pe, d
		1.41	pe, d
Thomas <i>et al.</i> [116], CCP (8, T, a/w)	2.00	1.14	pe, d
		1.18	pe, d
		1.21	pe, d
		1.33	pe, d
Wei <i>et al.</i> [119], VNC (18, a/w)	1.20	0.99	pe, d
	1.25	0.98	pe, d
	1.27	1.09	pe, d
	1.48	1.10	pe, d
	2.00	1.12	pe, d
Weiss <i>et al.</i> [120], VNC (16)	1.84	1.21	pe, d
	4.21	2.30	pe, d
Weiss <i>et al.</i> [121], DEN and VNC (18, 1/56)	1.33	1.01	pe, d
	1.67	1.16	pe, d
	3.20	1.02	pe, d
	3.75	1.59	pe, d
	4.00	1.01	pe, d
		1.05	pe, d
		1.09	pe, d
		1.12	pe, d
		1.85	pe, d
	5.00		
Wells [122], 3PB (8, 1/40)	1.42	1.33	pe, d
	2.01	1.00	pe, d
	2.84	0.97	pe, d
	4.00	1.10	pe, d
	5.68	1.10	pe, d
	8.03	1.16	pe, d
	11.2	1.16	pe, d

Table 4 continued

Source and text	Scale factor, λ	Mean stress ratio, $\frac{\sigma_1}{\sigma_2}$	Classification
Wessel [123], WOL (84,T)	2.00	1.03	pr, b
		1.11	pr, b
		1.12	pr, b
		1.20	pr, b-d
		1.23	pr, b
		1.30	pr, b
		1.30	pr, b
		1.35	pr, b
		1.36	pr, b
		1.40	pr, b
		1.41	pr, b
		1.41	pr, b-d
		1.48	pr, b
		1.50	pr, b-d
		1.52	pr, b
		1.56	pr, b
		1.59	pr, b
		1.62	pr, b-d
	3.00	2.06	pr, b
	4.00	1.75	pr, b
		1.83	pr, b
		1.85	pr, b
		2.14	pr, b
Wessel <i>et al.</i> [124], CTS (32, T)	1.20	1.02	pr, b
	1.33	1.35	pr, b
	1.50	1.27	pr, b
		1.51	pr, b
	1.67	1.11	pr, b
	2.00	1.26	pr, b
		1.58	pr, b
		1.71	pr, b
		1.76	pr, b
	2.50	1.02	pr, b
	4.00	1.62	pr, b
		0.99	pr, b-d
Wilson <i>et al.</i> CCP (36, T)	2.00	1.06	pr, d
		1.09	pr, d
		1.12	pr, d
		1.13	pr, d
		1.19	pr, d
		1.27	pr, d
	3.00	1.06	pr, d
	4.00	1.03	pr, d
		1.12	pr, d
		1.20	pr, d
		1.24	pr, d
		1.28	pr, d
		1.31	pr, d
		1.33	pr, d
		1.34	pr, d
		1.12	pr, d
		1.13	pr, d
		1.22	pr, d
		1.24	pr, d
		1.28	pr, d
		1.34	pr, d
		1.35	pr, d
		1.42	pr, d
Winne and Wundt [127], spinning disks (5)	3.00	1.47	pr, d
		1.96	pr, b-d
Witt [128], CTS (10,T)	3.00	0.95	pr, d
	6.00	1.11	pr, d
		0.95	pr, d
	9.00	1.02	pr, d
		1.00	pr, d
Worthington [129], 3PB (3,T)	2.11	1.15	pr, d
	4.72	1.80	pr, d

Table 4 continued

Source and test	Scale factor, λ	Mean stress ratio, $\frac{\sigma_1}{\sigma_2}$	Classification
Yukawa [130], 3PB (58, 1/15, T)	2.00	1.14	pr. d
	2.08	0.93	pr. d
	4.00	1.09	pr. b
		1.09	pr. b
		1.12	pr. d
		1.14	pr. b
		1.17	pr. b
		1.19	pr. b
		1.19	pr. b
		1.19	pr. d
		1.20	pr. b
		1.28	pr. b
		1.32	pr. d
		1.38	pr. b
		1.52	pr. b
		1.60	pr. b
		1.65	pr. b
		1.77	pr. b
	4.05	0.99	pr. d
	9.46	0.99	pr. d
	10.67	1.47	pr. b
Yukawa and McMullin [131], VNC (28, 1/16)	2.00	1.61	pr. d
	3.00	1.64	pr. d
		1.75	pr. d
	7.50	2.17	pr. d
		3.22	pr. d
Zhen-Yuan [134], TNF (3)	1.80	1.00	pr. d
	2.00	1.05	pr. d

Table 5. Sources and data for aluminum alloys

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Adams and Munro [6], CCP and CTS (51)	1.33	1.01	pr, d
	1.49	0.95	pr, d
	1.92	1.02	pr, d
	1.98	0.99	pr, d
	2.00	1.07	pr, d
	2.47	1.01	pr, d
	2.98	1.07	pr, d
	3.85	1.08	pr, d
	3.98	1.06	pr, d
	5.77	1.17	pr, d
Argy <i>et al.</i> [9], CCP and CTS (8,T)	1.39	1.04	pr, d
	1.66	0.97	pr, d
		1.18	pr, d
Bonesteel [15], TNF (2)	1.60	1.12	pr, d
Bradshaw and Wheeler [17], as reported in Newman [86], CCP (8)	2.00	1.20	pr, d
		1.24	pr, d
	4.00	1.27	pr, d
		1.48	pr, d
	8.00	1.44	pr, d
		1.96	pr, d
Carman <i>et al.</i> [21], CCP(30, 1/1000, a/w)	5.00	1.12	pr, d
		1.66	pr, d
		1.78	pr, d
		1.82	pr, d
		1.96	pr, d
		2.12	pr, d
		2.29	pr, d
		2.29	pr, d
		2.49	pr, d
Christian <i>et al.</i> [25], CCP (6, 1/500, T)	2.00	1.31	pr, d
		1.47	pr, d
	9.00	2.57	pr, d
		2.85	pr, d
Chu [26], 4PB (29)	1.88	1.08	pr, d
		1.26	pr, d
		1.30	pr, d
	2.00	1.29	pr, b-d
		1.44	pr, b-d
	2.22	1.08	pr, d
		1.09	pr, d
	2.50	1.21	pr, d
		1.29	pr, d
		1.56	pr, b-d
		1.59	pr, b-d
	2.89	1.40	pr, d
	3.00	1.63	pr, b-d
	3.33	1.10	pr, d
	3.75	1.31	pr, d
		1.83	pr, b-d
	5.00	1.87	pr, d
	7.50	1.90	pr, d
Desisto <i>et al.</i> [30], VNC(9, 1/23)	1.41	0.91	pr, d
	1.59	1.29	pr, b-d
	2.23	1.03	pr, b
	2.24	0.94	pr, b-d
	3.16	1.02	pr, b
	4.46	1.05	pr, d
	10.00	1.31	pr, d
Eschweiler and Munz [32], Short bar (7)	1.52	1.24	pr, d
		1.25	pr, d
Forman [34] as reported in Wang [99], CCP (8)	1.20	1.00	pr, d
	1.60	1.03	pr, d
	2.40	1.06	pr, d
Frediani [35], CCP (7, a/w)	1.52	1.03	pr, d
		1.17	pr, d
Heyer and McCabe [43],	2.00	1.11	pr, b
		1.13	pr, b
Hudson and Lewis [46], data supplied by Rockwell International, CTS (8)	1.33	1.19	pr, b
	1.67	1.37	pr, b

Table 5 continued

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Jones <i>et al.</i> [49], VNC (141, 1/100, a/w)	1.25	1.10	$p\epsilon, b$
		1.11	$p\epsilon, b-d$
	1.50	1.03	$p\epsilon, d$
		1.05	$p\epsilon, d$
		1.06	$p\epsilon, d$
		1.16	$p\epsilon, b-d$
		1.21	$p\epsilon, d$
	2.00	1.03	$p\epsilon, d$
		1.06	$p\epsilon, d$
		1.08	$p\epsilon, d$
		1.08	$p\epsilon, d$
		1.10	$p\epsilon, d$
		1.18	$p\epsilon, b-d$
		1.31	$p\epsilon, b-d$
		1.31	$p\epsilon, b-d$
	3.00	1.09	$p\epsilon, d$
		1.13	$p\epsilon, d$
		1.14	$p\epsilon, d$
		1.38	$p\epsilon, b-d$
		1.55	$p\epsilon, b-d$
	4.00	1.11	$p\epsilon, d$
		1.18	$p\epsilon, d$
		1.20	$p\epsilon, d$
		1.64	$p\epsilon, b-d$
	5.00	1.15	$p\epsilon, d$
		1.25	$p\epsilon, d$
		1.27	$p\epsilon, d$
		1.84	$p\epsilon, b-d$
Kaufman [52], CTS (6)	2.00	1.32	$p\epsilon, b$
	3.00	1.50	$p\epsilon, b$
Kaufman [53], VNC (18, 1/147)	2.13	1.17	$p\epsilon, d$
		1.48	$p\epsilon, b-d$
Kaufman and Nelson [54], CTS (20)	1.50	1.11	$p\epsilon, b$
	2.00	1.16	$p\sigma, b-d$
		1.17	$p\epsilon, b$
		1.23	$p\epsilon, b$
		1.24	$p\sigma, b-d$
	3.00	1.42	$p\sigma, b-d$
Kaufman <i>et al.</i> [55], VNC (63, 1/100)	2.13	1.25	$p\epsilon, d$
		1.38	$p\epsilon, d$
		1.38	$p\epsilon, d$
Keller and Munz [56], CTS(2)	2.00	1.11	$p\epsilon, b-d$
Klier and Weiss [57], VNC (13, 1/44)	1.67	1.00	$p\epsilon, d$
	3.00	0.99	$p\epsilon, d$
	4.67	1.21	$p\epsilon, d$
	5.67	1.07	$p\epsilon, d$
		1.56	$p\epsilon, d$
Krafft <i>et al.</i> , CCP(2)	2.00	1.31	$p\sigma, d$
Lake [63], CTS(4)	4.00	1.79	$p\epsilon, b$
Lubahn [69], VNC(6, 1/160)	1.30	1.29	$p\epsilon, d$
Morozov [78], 3PB (19)	1.67	1.34	$p\epsilon, b-d$
		1.36	$p\epsilon, b$
	1.85	1.36	$p\epsilon, b$
	2.00	1.21	$p\epsilon, b-d$
	2.07	1.34	$p\epsilon, b$
	2.22	1.28	$p\epsilon, b$
		1.55	$p\epsilon, b-d$
	2.52	1.43	$p\epsilon, b-d$
		1.44	$p\epsilon, b$
	3.03	1.46	$p\epsilon, b-d$
	4.00	1.67	$p\epsilon, b-d$
		1.81	$p\epsilon, b$
	4.11	1.76	$p\epsilon, b-d$
	6.56	1.80	$p\epsilon, b-d$
Munz [80], 3PB (6)	2.00	1.08	$p\epsilon, b-d$
	4.00	1.24	$p\epsilon, b-d$
	8.00	1.50	$p\epsilon, b-d$
Nelson and Kaufman [84], 3PB (32)	1.33	1.09	$p\epsilon, d$
		1.14	$p\epsilon, d$
		1.15	$p\epsilon, d$
		1.25	$p\epsilon, d$
		1.26	$p\epsilon, d$
		1.26	$p\epsilon, d$
		1.33	$p\epsilon, d$
		1.37	$p\epsilon, d$

Table 5 continued

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Nelson <i>et al.</i> [85], 3PB and CTS (74)	1.33	1.10	$p\epsilon, b$
		1.07	$p\epsilon, b-d$
	1.50	1.07	$p\sigma, b-d$
		1.12	$p\epsilon, b$
		1.14	$p\epsilon, b$
		1.19	$p\epsilon, b$
		1.20	$p\sigma, b-d$
		1.21	$p\sigma, b$
		1.26	$p\sigma, b$
		0.88	$p\epsilon, b-d$
	2.00	1.26	$p\epsilon, b$
		1.28	$p\epsilon, b$
		1.37	$p\epsilon, b-d$
		1.43	$p\epsilon, b$
		1.56	$p\epsilon, b$
		0.94	$p\epsilon, b-d$
	4.00	0.76	$p\sigma, d$
		1.01	$p\epsilon, b-d$
Orange [87], CCP (24, T, a/w)	2.00	1.09	$p\sigma, d$
		1.13	$p\sigma, d$
		1.14	$p\sigma, d$
		1.15	$p\sigma, d$
		1.18	$p\sigma, d$
		1.19	$p\sigma, d$
		1.21	$p\sigma, d$
		1.32	$p\sigma, d$
	4.00	1.31	$p\sigma, d$
		1.39	$p\sigma, d$
		1.46	$p\sigma, d$
		1.52	$p\sigma, d$
		1.58	$p\sigma, d$
		1.63	$p\sigma, d$
		1.80	$p\sigma, d$
Poulose <i>et al.</i> [91], CTS (8)	1.50	1.07	$p\epsilon, d$
	2.00	1.12	$p\sigma, d$
		1.22	$p\epsilon, d$
		1.65	$p\sigma, d$
Poulose and Liebowitz [92], CCP (8)	2.00	1.03	$p\sigma, d$
	3.00	0.98	$p\sigma, d$
	6.00	1.08	$p\sigma, d$
	8.00	1.32	$p\sigma, d$
	10.00	1.32	$p\sigma, d$
	12.00	1.59	$p\sigma, d$
	14.00	1.75	$p\sigma, d$
Shannon <i>et al.</i> [104], DEN (22)	2.00	1.27	$p\epsilon, b-d$
		1.28	$p\epsilon, b-d$
		1.37	$p\sigma, d$
		1.89	$p\sigma, d$
Special ASTM Committee, Third Report [108], CCP and VNC (16)	1.50	1.03	$p\epsilon, d$
	2.00	1.03	$p\epsilon, d$
		1.06	$p\epsilon, d$
		1.07	$p\sigma, d$
		1.07	$p\sigma, d$
		1.20	$p\sigma, d$
		1.20	$p\sigma, d$
		1.24	$p\sigma, d$
		1.27	$p\sigma, d$
		1.13	$p\epsilon, d$
		1.30	$p\epsilon, d$
	2.50	1.13	$p\epsilon, d$
	3.00	1.30	$p\epsilon, d$
	3.20	1.38	$p\epsilon, d$
	4.00	1.29	$p\epsilon, d$
		1.46	$p\sigma, d$
		1.49	$p\epsilon, d$
		1.34	$p\sigma, d$
	5.14	1.34	$p\sigma, d$
	8.00	1.87	$p\epsilon, d$
	13.71	2.04	$p\epsilon, d$
		1.85	$p\sigma, d$
Steigerwald [111], 4PB and 3PB (16)	1.43	1.18	$p\epsilon, b-d$
	1.64	1.28	$p\epsilon, b-d$
	1.83	1.65	$p\epsilon, b-d$
	2.71	1.57	$p\epsilon, b-d$
	2.93	1.66	$p\epsilon, b-d$
	3.86	1.91	$p\epsilon, b-d$
	4.89	2.06	$p\epsilon, b-d$
Sullivan <i>et al.</i> [112], CTS (2)	1.67	2.14	$p\epsilon, b-d$
Sullivan and Stoop [113], CTS (13, a/w)	1.67	1.07	$p\sigma, d$
		1.18	$p\sigma, d$
		1.22	$p\sigma, d$

Table 5 continued

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Yusuff [132], from data in Crichtlow [29], McEvily <i>et al.</i> [75] and Yusuff [133], CCP (21)	1.50	1.19	ps, b-d
		1.36	ps, b-d
	2.00	1.31	ps, b-d
		1.36	ps, d
	4.44	1.47	ps, d
		1.47	ps, d
		1.69	ps, d
		2.01	ps, d
		2.12	ps, d
		2.37	ps, d
		2.93	ps, d
	8.89		
Wang [117], CCP (8, s/w)	1.33	1.09	ps, d
	2.50	1.67	ps, d
	3.33	1.82	ps, d
Wang and McCabe [118], CTS (5)	1.33	1.12	ps, d
	1.50	1.06	ps, d
	3.33	1.85	ps, d
Weiss <i>et al.</i> [120], VNC (33)	1.81	1.12	pe, d
	1.90	1.03	pe, d
	4.00	1.37	pe, d
		1.60	pe, d
Zinkham [135], CCP (18)	3.00	1.41	ps, b
		1.50	ps, b
Zinkham and Baughan [136], CTS (16)	1.67	1.14	pe, b
		1.18	pe, b

Table 6. Sources and data for other metals

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Chu [26], 4PB and 3PB (56)	1.33	0.98	pe, d
	1.67	1.07	pe, d
		1.18	pe, d
	2.00	1.30	pe, d
	2.50	1.08	pe, d
		1.15	pe, d
		1.16	pe, d
		1.18	pe, d
		1.23	pe, d
		1.31	pe, d
		1.40	pe, d
	2.67	1.22	pe, d
		1.28	pe, d
		1.32	pe, d
		1.41	pe, d
	4.00	1.58	pe, d
	5.00	1.32	pe, d
		1.33	pe, d
		1.34	pe, d
		1.39	pe, d
		1.65	pe, d
		1.68	pe, d
	5.33	1.64	pe, d
	10.00	1.50	pe, d
		1.52	pe, d
		1.56	pe, d
		1.68	pe, d
		1.71	pe, d
		1.86	pe, d
		2.29	pe, d
DeSisto <i>et al.</i> [30], VNC (8 1/23)	1.41	1.03	pe, d
	2.23	1.08	pe, d
	2.24	1.19	pe, b-d
	3.15	1.45	pe, b-d
	3.16	1.19	pe, d
	5.00	1.76	pe, b-d
Gunderson [39], as reported in Newman [86], CTS (2)	1.33	1.03	pe, b-d
Hall <i>et al.</i> [40], CTS (3)	2.67	1.55	pe, b-d
Hilton [44], CTS (15)	2.50	1.38	pe, b
		1.40	pe, b-d
		1.48	pe, b-d
Klier and Weiss [57], VNC (10, 1/44)	1.67	0.99	pe, d
		1.05	pe, d
	3.00	0.95	pe, d
		1.09	pe, d
	4.67	1.00	pe, d
		2.31	pe, d
	5.67	1.02	pe, d
Munz <i>et al.</i> [81], 3PB (102)		2.40	pe, d
	1.90	1.18	pe, b-d
		1.12	pe, b
	2.00	1.29	pe, b-d
		1.31	pe, b
	3.17	1.73	pe, b-d
	3.84	1.54	pe, b
	4.20	1.60	pe, b
Payne [90], CCP (8)	7.80	2.09	pe, b
	3.00	1.66	pe, d
Repko <i>et al.</i> [94], DEN (24)		1.83	pe, d
	3.00	1.10	pe, d
		1.46	pe, d
		1.54	pe, d
Shannon <i>et al.</i> [104], DEN (15)		1.63	pe, b-d
	2.00	1.34	pe, d
		1.44	pe, b-d
Special ASTM Committee, Third Report [108], CCP (30, 1/1000)		1.48	pe, b-d
	2.31	1.43	pe, b
		1.52	pe, b-d
	3.00	1.71	pe, b-d
Weiss <i>et al.</i> [121], DEN (3, 1/45)		1.81	pe, d
	2.00	1.36	pe, d
	4.00	1.90	pe, d

Table 7. Sources and data for nonmetals

Source and test	Scale factor, λ	Mean stress ratio, σ_1/σ_2	Classification
Bassim and Hsu [11], 3PB (5)	2.54	1.08	pr, b
Buresch [20], 4PB (40, 1/11)	2.33	1.32	pr, b
Costin [28], 3PB (12)	2.00 4.00	1.40 1.78	pr, d pr, d
Kaplan [51], 3PB and 4PB (27, a/w)	2.00	1.83 1.90 1.95 1.96 2.07 2.08 2.08 2.10 2.18	pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b
Lewis and Smith [65], 4PB (6)	2.00	2.10	pr, b
McKinney and Rice [76], 3PB (57, 1/12)	1.17 1.18 1.33 1.38 1.60 1.63 1.65 1.67 1.74 2.33 2.67 3.13 3.20 3.33 3.73 4.67 4.80	1.47 1.08 1.09 1.44 1.21 1.08 1.50 1.16 1.48 0.99 1.49 1.17 1.28 1.52 1.35 1.09 1.07 1.98 1.77	pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b
Schmidt [99], 3PB (16, a/w)	2.04 4.08	1.19 1.28 1.70	pr, d pr, d pr, d
Schmidt and Lutz [100], CTS and 3PB (22)	2.00 4.00 8.00	1.28 1.30 1.69 1.81 2.46	pr, d pr, d pr, d pr, d pr, d
Weiss <i>et al.</i> [120], 4PB and VNC (46, 1/21)	1.41 1.44 1.80 2.18 2.69 2.84 3.42 3.98 5.95 6.26 11.31	0.99 1.17 1.49 1.43 1.37 1.75 1.61 2.08 1.70 2.63 2.25	pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b pr, b
Williams and Ewing [125], Pressure vessels (6)	1.33 1.50	0.94 1.94	pr, b-d pr, b

SOME COMMENTS ON THE GRIFFITH-IRWIN
APPROACH TO FRACTURE MECHANICS

G.B. Sinclair

Department of Mechanical Engineering, Carnegie-Mellon University
Pittsburgh, Pennsylvania 15213

For brittle fracture, present day linear elastic fracture mechanics (LEFM) selects the stress intensity factor, K , as the parameter controlling damage. In essence this choice owes its origin to the classical thermodynamic or energy argument of Griffith, and the recognition of the equivalence of energy release rates and stress intensity factors by Irwin. While there now exist competing explanations for justifying K as the fracture controlling quantity, the underlying energy argument cannot be dismissed since the use of K to predict fracture implies the thermodynamic statement of Griffith, i.e. the connection is reversible. Accordingly an assessment of the validity of the energy balance approach is pertinent to an appraisal of LEFM even today.

A number of commentaries on the Griffith energy argument for brittle fracture are available in the literature and address various aspects of its consequences, e.g. Goodier in *Fracture*, Vol. II. The aspect of concern here is the size dependence implied by the approach. By virtue of having an energy source term which is one spatial dimension higher than the assumed sink, the balance always leads to a reduction in the predicted stress at fracture for scaled specimens as the inverse of the square root of some length. More precisely, for the uniaxial tension test Griffith's argument can be shown to result in

$$\sigma_u \propto \frac{1}{\sqrt{L}},$$

where σ_u is the ultimate stress, L is the length of the specimen: while for a cracked specimen with all its in-plane dimensions held in constant ratios to one another it gives

$$\sigma_* \propto \frac{1}{\sqrt{W}},$$

where σ_* is the applied stress at fracture, W is the width of the specimen. The question then arises as to how good such predictions are in practice. The answer is not too satisfactory. Specifically, the first, though representing a trend found to a limited extent in small specimens, is generally in complete disagreement with the physical evidence of size independence for the ultimate stress in sufficiently large specimens. And the second, on examination of over

300 experimental data for brittle and quasi brittle materials drawn from some forty odd references, is found to be complied with to within $\pm 10\%$ by less than 7% of the results. In all it would appear that the assumption of a surface-energy-like term as the sole energy sink in fracture processes in solids implicit in LEFM leads to an altogether too simple prediction of size effects - one that cannot really capture the variations in size dependence itself with size, or the sensitivity of size effects to different materials, or the way in which altering size by changing different dimensions enters into the effects. One explanation which has the potential of overcoming these shortcomings is to view size dependence as being governed by a highly stressed volume and admit Weibull-like dependencies. When these ideas are applied to various test geometries, including cracked test pieces, a consistent picture of strength size effects emerges.

SOME COMMENTS ON THE GRIFFITH-IRWIN
APPROACH TO FRACTURE MECHANICS

G.B. Sinclair

Department of Mechanical Engineering, Carnegie-Mellon University
Pittsburgh, Pennsylvania 15213

For brittle fracture, present day linear elastic fracture mechanics (LEFM) selects the stress intensity factor, K , as the parameter controlling damage. In essence this choice owes its origin to the classical thermodynamic or energy argument of Griffith, and the recognition of the equivalence of energy release rates and stress intensity factors by Irwin. While there now exist competing explanations for justifying K as the fracture controlling quantity, the underlying energy argument cannot be dismissed since the use of K to predict fracture implies the thermodynamic statement of Griffith, i.e. the connection is reversible. Accordingly an assessment of the validity of the energy balance approach is pertinent to an appraisal of LEFM even today.

A number of commentaries on the Griffith energy argument for brittle fracture are available in the literature and address various aspects of its consequences, e.g. Goodier in *Fracture*, Vol. II. The aspect of concern here is the size dependence implied by the approach. By virtue of having an energy source term which is one spatial dimension higher than the assumed sink, the balance always leads to a reduction in the predicted stress at fracture for scaled specimens as the inverse of the square root of some length. More precisely, for the uniaxial tension test Griffith's argument can be shown to result in

$$\sigma_u \propto \frac{1}{\sqrt{L}},$$

where σ_u is the ultimate stress, L is the length of the specimen: while for a cracked specimen with all its in-plane dimensions held in constant ratios to one another it gives

$$\sigma_* \propto \frac{1}{\sqrt{W}},$$

where σ_* is the applied stress at fracture, W is the width of the specimen. The question then arises as to how good such predictions are in practice. The answer is not too satisfactory. Specifically, the first, though representing a trend found to a limited extent in small specimens, is generally in complete disagreement with the physical evidence of size independence for the ultimate stress in sufficiently large specimens. And the second, on examination of over

300 experimental data for brittle and quasi brittle materials drawn from some forty odd references, is found to be complied with to within $\pm 10\%$ by less than 7% of the results. In all it would appear that the assumption of a surface-energy-like term as the sole energy sink in fracture processes in solids implicit in LEFM leads to an altogether too simple prediction of size effects - one that cannot really capture the variations in size dependence itself with size, or the sensitivity of size effects to different materials, or the way in which altering size by changing different dimensions enters into the effects. One explanation which has the potential of overcoming these shortcomings is to view size dependence as being governed by a highly stressed volume and admit Weibull-like dependencies. When these ideas are applied to various test geometries, including cracked test pieces, a consistent picture of strength size effects emerges.

On Size Effects In Fracture

G.B. Sinclair
Department of Mechanical Engineering
Carnegie-Mellon University
Pittsburgh, PA 15213, U.S.A.

Griffith's classical energy arguments [1], which form the basis of modern day fracture mechanics, imply a dependence of fracture stress on size. Specifically, for an in-plane scaled specimen pair (Fig.1), in theory we have

$$\sigma_1^*/\sigma_2^* = \sqrt{\lambda} \quad (1)$$

where σ_1^* , σ_2^* are the applied stresses at fracture in Specimen 1, 2 and λ is the scale factor. That is, the larger the specimen the smaller the fracture stress. In contrast for out-of-plane dependence, the same theory gives

$$\sigma_c^*/\sigma_T^* = \sqrt{1-\nu^2}, \quad (2)$$

where σ_c^* , σ_T^* correspond to plane stress, strain fracture stresses and ν is Poisson's ratio.

The objective here is to examine how well these predictions are actually complied with.




Fig.1. Scaled crack specimens

To this end Fig.2 presents in-plane size effects on the strength of cracked specimens from twenty references (see [2] for details).

While some of the data lie close to equation (1)

PROCEEDINGS OF THE TENTH CANADIAN CONGRESS OF APPLIED MECHANICS • COMPTES RENDUS DU DIXIEME CONGRES CANADIEN DE MECHANIQUE APPLIQUEE • THE UNIVERSITY OF WESTERN ONTARIO, LONDON JUNE 2 • JUNE 7 • 2 JUN - 7 JUIN 1985.

most do not, regardless of whether the data is for brittle or semi-brittle material, for plane stress or plane strain. Moreover scatter alone cannot account for the deviations from the theory (the bars in Fig.2 being 95% confidence limits for the associated data sets). Concerning thickness effects, there appears to be a lack of data for perfectly brittle solids to check if (2) holds. However, as is well known, nonbrittle data exhibit the opposite behavior to (2). While explanations of this trend exist none are generally recognized as being complete. In all, size predictions in fracture mechanics are in some conflict with the physical data.




Fig.2. In-plane size dependence data

By reviewing the basic arguments of fracture mechanics one can establish that the assumption of a surface term being the dominant energy sink in the thermodynamic condition for fracture is inappropriate. The question then arises is what is really happening in fracture size effects. One explanation follows on assuming cracks are not physically too different from other stress raisers. This enables their physical size dependence to be made compatible with size effects in general.

The general picture (Fig.3) of size effects has size independent and size dependent regimes. In the size independent regime fracture stress takes on the material handbook value, the ultimate stress σ_u . This value applies when V^* , the highly-stressed volume, is big enough. Consequently it is normally found via uniaxial tension tests wherein the entire volume can be highly stressed. If, though, this volume is sufficiently reduced ($V^* < V_u$), the size dependent regime is entered even using tensile tests (see e.g. Fig.3). In this regime models, such as those due to Weibull [3], provide reasonable data reduction schemes for predicting the increases in strength due to reductions in size.

Turning to other specimen types, if we make the nonunique but sensible definition that V^* be the volume seeing 95% or more of the maximum stress, we can obtain the estimates below for V^* in terms of the gross volume V :

$$\begin{aligned} V^* &\sim V(\text{tension}), V^* \sim .05 V(\text{bending}), \\ V^* &\sim .05^2 V(\text{notches}), V^* \sim .05^n V(\text{cracks}). \end{aligned} \quad (3)$$

Here n is an index whose range is approximately $2 < n < 3$. As a result, bend, smooth notch, and crack specimens, in that order, can be expected




Fig.3. General fracture size effects

to more frequently fall in the size dependent regime; nonetheless given sufficiently large specimens all three eventually enter the size independent regime (see Figs.2,3). To date we have been able to get all data gathered to comply with this explanation. Further, this interpretation offers the potential of increased understanding of thickness effects.

In sum, size effects predicted in current fracture mechanics can disagree with the physical evidence and hence are capable of causing errors in practice, even nonconservative ones: the explanation put forward here would seem to be consistent with physical results and could thus become a part of an improved technology.

REFERENCES

- [1]. A.A. Griffith, *Phil. Trans Roy. Soc. (Lond)* 221A, 163 (1920).
- [2]. G.B. Sinclair, Dept. Mech. Engng Rep. No. SM84-19, Carnegie-Mellon Univ. (1984).
- [3]. W. Weibull, *Proc. Roy. Swedish Inst. Engng Res.* 151, 5 (1939).

END

FILMED

1-86

DTIC