

AD-A168 813

THE ELASTIC CONSTANTS OF N13AL TO 14 GPA(U) CLOSE
COMBAT ARMAMENTS CENTER WATERVLIET NY J FRANKEL ET AL.
MAY 86 ARCCB-TR-86018

1/1

UNCLASSIFIED

F/G 11/6

NL



14

AD

TECHNICAL REPORT ARCCB-TR-86018

THE ELASTIC CONSTANTS OF Ni_3Al TO 1.4 GPa

AD-A166 813

J. FRANKEL

J. C. JAMIESON

J. VASSILIOU

D. P. DANDEKAR

W. SCHOLZ

MAY 1986



US ARMY ARMAMENT RESEARCH AND DEVELOPMENT CENTER

CLOSE COMBAT ARMAMENTS CENTER

BENET WEAPONS LABORATORY

WATERVILLE, N.Y. 12189-4050

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

DTIC FILE COPY

DTIC
ELECTE
JUN 20 1986
S D

CLAIMS

The findings in this report are not to be construed as an official statement of the Army position unless so designated by other authorized documents.

This is not to be taken as a manifestation of the Army's official endorsement or approval.

DISPOSITION NO. 11-1

Classified documents, follow the procedures in DoD 5200.22-M, Security Manual, Section 11-19 or DoD 7000.1-R, Information Management Regulation, Chapter IX.

Unclassified limited documents, destroy by any method that will prevent disclosure of contents or reconstruction of the document.

Unclassified unlimited documents, destroy when the report is no longer needed, do not return it to the originator.

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARCCB-TR-86018	2. GOVT ACCESSION NO.	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) THE ELASTIC CONSTANTS OF Ni ₃ Al to 1.4 GPa		5. TYPE OF REPORT & PERIOD COVERED Final
		6. PERFORMING ORG. REPORT NUMBER
7. AUTHOR(s) J. Frankel, J. Vassiliou, J. C. Jamieson, D. P. Dandekar, and W. Scholz (see reverse)		8. CONTRACT OR GRANT NUMBER(s)
9. PERFORMING ORGANIZATION NAME AND ADDRESS US Army Armament Research, Develop, & Engr Center Benet Weapons Laboratory, SMCAR-CCB-TL Watervliet, NY 12189-4050		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 6111.01.91A0.011 PRON No. 1A52F59W1A1A
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research, Develop, & Engr Center Close Combat Armaments Center Dover, NJ 07801-5001		12. REPORT DATE May 1986
		13. NUMBER OF PAGES 11
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Presented at the Xth AIRAPT International High Pressure Conference, Amsterdam, The Netherlands, 8-11 July 1985. Published in Proceedings of the Conference.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) High Pressure Elastic Constants Ultrasonics Single Crystals		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) The pressure derivatives of the elastic constants of single-crystal Ni ₃ Al have been determined to 1.4 GPa by both pulse superposition and pulse-echo overlap techniques. Measurements were made on single-crystal specimens of orientation <100> and <110>, thus providing at least one cross-check. The values of c ₁₁ , c ₁₂ , and c ₄₄ at one atmosphere are found to be 223.5, 149.0, and 122.9 GPa, respectively. The pressure derivatives of the elastic constants have been determined.		

4. AUTHORS (CONT'D)

J. Vassiliou and J. C. Jamieson
Department of Physics
University of Chicago
Chicago, IL

D. P. Dandekar
U.S. Army LABCOM, Materials Technology Laboratory
Watertown, MA

W. Scholz
Department of Physics
State University of New York at Albany
Albany, NY

UNCLASSIFIED

TABLE OF CONTENTS

	<u>Page</u>
INTRODUCTION	1
EXPERIMENTAL DETAILS	1
DATA ANALYSIS	3
RESULTS AND DISCUSSION	4
REFERENCES	8

TABLES

I.	DENSITY ρ (IN Mg/m^3), ELASTIC CONSTANTS c_{ij} AND ADIABATIC BULK MODULUS B_s (IN $10^{11} \text{ N}/\text{m}^2$) OF Ni_3Al	9
II.	SLOPES OF CHANGE IN FREQUENCY WITH PRESSURE (IN Hz/GPa) FOR VARIOUS VELOCITY MODES IN Ni_3Al	9
III.	PRESSURE DERIVATIVE OF THE ELASTIC CONSTANTS OF Ni_3Al	10



Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTRODUCTION

Ni_3Al , having the L1_2 ordered structure, belongs to a class of inter-metallic compounds which shows unusual mechanical behavior, namely, a peak in mechanical strength with an increase in temperature. The peak temperature for Ni_3Al is 922 K, where the yield stress value is four times its value at room temperature. A large number of investigations determining the dependence of different physical properties as a function of temperature have been done, but the pressure dependence of the properties of Ni_3Al remains to be investigated in depth. The present report fills this gap in our information by determining the pressure dependence of the three elastic constants c_{11} , c_{12} , and c_{44} of single-crystal Ni_3Al to 1.4 GPa at room temperature. The results of the present investigation are compared with previous elastic constant measurements at ambient conditions reported by Dickson et al. (ref 1) and Ono and Stern (ref 2). Our results are also compared with diffraction data to 12.0 GPa developed by Mauer et al (ref 3).

EXPERIMENTAL DETAILS

A single-crystal ingot of Ni_3Al was generously provided by Dr. B. H. Kear of United Technologies Research Center, Connecticut. Two nearly cubical specimens of Ni_3Al , one having [100] type faces and the other having two pairs of [110] and one pair of [100] type faces, were prepared from the crystal

¹R. W. Dickson, J. B. Wachtman, Jr., and S. M. Copley, J. Appl. Phys., Vol. 40, 1969, p. 2276.

²K. Ono and R. Stern, Trans. Met. Soc. AIME, Vol. 245, 1971, p. 171.

³F. A. Mauer, R. G. Munro, G. J. Piermarini, S. B. Block, and D. P. Dandekar, J. Appl. Phys. (to be published).

ingot. The faces on these specimens were oriented normal to ± 0.5 degree of their respective crystallographic directions by the back-reflection Laue technique. The parallel faces were hand-lapped, etched, and polished by the usual metallographic procedure. The specimen having only [100] type of faces had a thickness of 0.9525 ± 0.0005 cm. The thicknesses of the [110] type faces on the second specimen were 0.970 and 0.951 cm, respectively. The density was determined to be 7.478 ± 0.007 Mg/m³.

The values of the three elastic constants c_{11} , c_{12} , and c_{44} were obtained from measurements of travel times of longitudinal and shear waves in the $\langle 100 \rangle$ and $\langle 110 \rangle$ directions. Two independent sets of these measurements were performed on the two specimens. One set of measurements was done at the University of Chicago. The second set of measurements was made at Benet Weapons Laboratory.

At the University of Chicago, the acoustic velocities were measured using the pulse superposition method developed by McSkimmin (ref 4). X and AC cut quartz transducers with a fundamental frequency of 30 MHz were used to generate longitudinal and shear modes, respectively. They were bonded to the crystals by using DOW 276-V9 resin. The pulse repetition frequencies were recorded. A Bridgman pressure vessel was used, and pressure was determined using a calibrated Manganin coil. Measurements were performed to 0.6 GPa. The error in the absolute value of a velocity is estimated to be less than 0.5 percent. Relative accuracy is much greater.

⁴H. J. McSkimmin, J. Acoust. Soc. Am., Vol. 33, 1961, p. 12.

At Benet Weapons Laboratory, the acoustic velocities were measured to 1.4 GPa with the pulse-echo overlap method of Papadakis (ref 5) using a two frequency approach. Simply put, the experiment is done twice--once with a 10 MHz (for example) and once with a 15 MHz transducer. The result of the cycle-for-cycle comparison should be the same at the two transducer frequencies, but only if the correct cycle is chosen.

DATA ANALYSIS

The values of the elastic constants were estimated by the method of least squares from the pulse repetition or pulse-echo overlap frequencies measured for four acoustic modes. They are longitudinal in $\langle 100 \rangle$ and $\langle 110 \rangle$ directions, shear in $\langle 100 \rangle$ and shear in $\langle 110 \rangle$ polarized along $\bar{\langle 110 \rangle}$. For these modes in a cubic crystal we have

$$\rho V_L^2 \langle 100 \rangle = c_{11} \equiv K_1 \quad (1)$$

$$\rho V_S^2 \langle 100 \rangle = c_{44} \equiv K_2 \quad (2)$$

$$\rho V_L^2 \langle 110 \rangle = (c_{11} + c_{12} + 2c_{44})/2 \equiv K_3 \quad (3)$$

$$\rho V_S^2 \langle 110 \rangle p \bar{\langle 110 \rangle} = (c_{11} - c_{12})/2 \equiv c_s \equiv K_4 \quad (4)$$

We can construct a function F

$$F \equiv (K_1 - c_{11})^2 + (K_2 - c_{44})^2 + (K_3 - 0.5c_{11} - 0.5c_{12} - c_{44})^2 + (K_4 - 0.5c_{11} + 0.5c_{12})^2 \quad (5)$$

This function yields the least squares estimates of the three elastic constants

$$c_{11} = (3K_1 - K_2 + K_3 + K_4)/4 \quad (6)$$

⁵E. P. Papadakis, J. Acoust. Soc. Am., Vol. 42, 1967, p. 1045.

$$c_{12} = (K_1 - 3K_2 + 3K_3 - 5K_4)/4 \quad (7)$$

$$c_{44} = (-K_1 + 3K_2 + K_3 + K_4)/4 \quad (8)$$

Equations (6) through (8) are used to calculate the best values of the three elastic constants of Ni₃Al.

The pulse repetition and pulse-echo overlap frequencies for all four modes were found to vary linearly with pressure. Therefore, the frequency estimates for each of the modes at a given pressure were obtained from the least squares fit of a straight line for each mode. These estimates were utilized in conjunction with the estimating procedure of the elastic constants of a cubic crystal at high pressure developed by Dandekar (ref 6).

RESULTS AND DISCUSSION

The values of the elastic constants of Ni₃Al as obtained in the present investigation are given together with the previous measurements in Table I. This table shows that the values of the elastic constants of Ni₃Al obtained from the present two sets of independent measurements are in excellent agreement. On the other hand, the values of the elastic constants obtained by Dickson et al. (ref 1) and Ono and Stern (ref 2) are consistently lower than the values obtained in the present work. These differences are too large to be attributed to measurement errors in the acoustic velocities. The likely reasons for the differences in the values of the elastic constants determined by the previous workers and in the present work may be as follows. Dickson et

¹R. W. Dickson, J. B. Wachtman, Jr., and S. M. Copley, J. Appl. Phys., Vol. 40, 1969, p. 2276.

²K. Ono and R. Stern, Trans. Met. Soc. AIME, Vol. 245, 1971, p. 171.

⁶D. P. Dandekar, J. Appl. Phys., Vol. 41, 1970, p. 667.

al. (ref 1) obtained the values of the elastic constants by measuring resonance frequencies of seven rods of single-crystal Ni_3Al , with different orientations and different densities. The densities of these rods varied between 7.552 and 7.582 Mg/m^3 . These rods were of lengths between 10.7 and 13.8 cm and their diameter varied between 0.47 and 0.57 cm. The orientations of these rods were determined by using the Laue back-reflection technique. Even though both the ultrasonic method and the resonance technique should yield identical or very nearly identical values for the elastic constants of a solid, it is possible that different values of the elastic constants of Ni_3Al were obtained from the two techniques because the entire length of the rods used by Dickson et al. (ref 1) may not have been oriented uniformly with respect to the measurement orientation at a given point. The differences between the values of the elastic constants as obtained by Ono and Stern (ref 2) and in the present work are more difficult to explain because both sets of measurements were done on small oriented specimens by ultrasonic techniques. However, whereas the results of Ono and Stern (ref 2) cannot be checked for their internal consistency because they measured only three acoustic modes in $\langle 110 \rangle$ orientation of Ni_3Al , the results of the present work can be checked for their internal consistency because four independent wave velocities were measured at each of the two laboratories mentioned earlier by two different methods and different research personnel. Thus, we believe that the values of the elastic constants of Ni_3Al obtained in the present work are the valid ones.

¹R. W. Dickson, J. B. Wachtman, Jr., and S. M. Copley, J. Appl. Phys., Vol. 40, 1969, p. 2276.

²K. Ono and R. Stern, Trans. Met. Soc. AIME, Vol. 245, 1971, p. 171.

The pulse repetition frequencies and pulse-echo overlap frequencies for the four acoustic modes in Ni₃Al were found to vary linearly with pressure. The worst correlation coefficient between the frequencies and pressure was for the shear wave propagating along $\langle 110 \rangle$ and polarized along $\langle \bar{1}10 \rangle$ which has a value of 0.989. The slopes of change in frequencies with pressure for the four acoustic modes measured in this work are given in Table II. The consistency between the two sets of measurements taken on the same specimens is self-evident. The pressure derivatives of the adiabatic elastic constants of Ni₃Al are given in Table III.

Compression data of Ni₃Al obtained by the in situ high pressure x-ray diffraction technique to 12.0 GPa by Mauer et al. (ref 3), showed excessive scatter. As a result they were unable to obtain an estimate for the pressure derivative of the isothermal bulk modulus of Ni₃Al. Their estimate of the isothermal bulk modulus was 185 GPa, as compared to a value of 169 GPa obtained here. The present work allows us to compute the pressure derivative of the isothermal bulk modulus B_T of Ni₃Al as 4.88. Here we have used $B_T = B_S/(1+\Delta)$ with $\Delta = \alpha\gamma T$, where $\gamma = 2.12$ is the Gruneisen constant at ambient pressure and temperature and $\alpha = 4.24 \times 10^{-5}/K$ is the temperature coefficient of linear expansion. $B_S = (c_{11}+2c_{12})/3$ is the adiabatic bulk modulus. If the compression curve of Ni₃Al is expressed by Bridgman's equation $\partial V/V = aP + bP^2$, we obtain

$$-\partial V/V = 5.915 \times 10^{-3} P - 1.0286 \times 10^{-4} P^2 \quad (9)$$

³F. A. Mauer, R. G. Munro, G. J. Piermarini, S. B. Block, and D. P. Dandekar, J. Appl. Phys. (to be published).

where $\partial V/V_0$ is the change in volume with respect to the ambient volume and P is pressure in GPa.

REFERENCES

1. R. W. Dickson, J. B. Wachtman, Jr., and S. M. Copley, J. Appl. Phys., Vol. 40, 1969, p. 2276.
2. K. Ono and R. Stern, Trans. Met. Soc. AIME, Vol. 245, 1971, p. 171.
3. F. A. Mauer, R. G. Munro, G. J. Piermarini, S. B. Block, and D. P. Dandekar, J. Appl. Phys. (to be published).
4. H. J. McSkimmin, J. Acoust. Soc. Am., Vol. 33, 1961, p. 12.
5. E. P. Papadakis, J. Acoust. Soc. Am., Vol. 42, 1967, p. 1045.
6. D. P. Dandekar, J. Appl. Phys., Vol. 41, 1970, p. 667.

TABLE I. DENSITY ρ (IN Mg/m^3), ELASTIC CONSTANTS c_{ij} AND ADIABATIC BULK MODULUS B_s (IN 10^{11} N/m^2) OF Ni_3Al

Source	c_{11}	c_{12}	c_{44}	B_s	ρ
Ref (2)	1.978	1.265	1.178	1.503	7.491
Ref (1)	1.688	0.886	1.212	1.153	7.563
U. of Chicago	2.232	1.495	1.228	1.740	7.478
Benet Labs.	2.238	1.485	1.230	1.736	7.478

TABLE II. SLOPES OF CHANGE IN FREQUENCY WITH PRESSURE (IN Hz/GPa) FOR VARIOUS VELOCITY MODES IN Ni_3Al

Propagation Direction	Particle Motion	Univ. of Chicago	Benet Laboratory
$\langle 100 \rangle$	$\langle 100 \rangle$	0.3364×10^4	0.3308×10^4
$\langle 100 \rangle$	$\perp$ to $\langle 100 \rangle$	0.1869×10^4	0.1813×10^4
$\langle 110 \rangle$	$\langle 110 \rangle$	0.3938×10^4	0.3825×10^4
$\langle 110 \rangle$	$\bar{\langle 110 \rangle}$	0.7112×10^3	0.5917×10^3

TABLE III. PRESSURE DERIVATIVE OF THE ELASTIC CONSTANTS OF Ni_3Al

Elastic Constant	Pressure Derivative
c_{11}	5.58
c_{12}	4.72
c_{44}	2.34
c_s	0.43
B_s	5.01
B_T	4.88

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>
CHIEF, DEVELOPMENT ENGINEERING BRANCH	
ATTN: SMCAR-CCB-D	1
-DA	1
-DP	1
-DR	1
-DS (SYSTEMS)	1
-DC	1
-DM	1
CHIEF, ENGINEERING SUPPORT BRANCH	
ATTN: SMCAR-CCB-S	1
-SE	1
CHIEF, RESEARCH BRANCH	
ATTN: SMCAR-CCB-R	2
-R (ELLEN FOGARTY)	1
-RA	1
-RM	1
-RP	1
-RT	1
TECHNICAL LIBRARY	5
ATTN: SMCAR-CCB-TL	
TECHNICAL PUBLICATIONS & EDITING UNIT	2
ATTN: SMCAR-CCB-TL	
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN: SMCAR-CCB-TL,
OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY AMCCOM ATTN: SMCAR-ESP-L ROCK ISLAND, IL 61299	1
COMMANDER DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-DDA CAMERON STATION ALEXANDRIA, VA 22314	12	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61299	1
COMMANDER US ARMY MAT DEV & READ COMD ATTN: ORCDE-SG 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	DIRECTOR US ARMY INDUSTRIAL BASE ENG ACTV ATTN: DRXIB-M ROCK ISLAND, IL 61299	1
COMMANDER ARMAMENT RES & DEV CTR US ARMY AMCCOM ATTN: SMCAR-FS	1	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRSTA-TSL WARREN, MI 48090	1
SMCAR-FSA	1	COMMANDER US ARMY TANK-AUTMV COMD ATTN: DRSTA-RC WARREN, MI 48090	1
SMCAR-FSM	1		
SMCAR-FSS	1		
SMCAR-AEE	1	COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996	1
SMCAR-AES	1		
SMCAR-AET-O (PLASTECH)	1		
SMCAR-MSI (STINFO)	2		
DOVER, NJ 07801		US ARMY MISSILE COMD REDSTONE SCIENTIFIC INFO CTR ATTN: DOCUMENTS SECT, BLDG. 4484 REDSTONE ARSENAL, AL 35898	2
DIRECTOR BALLISTICS RESEARCH LABORATORY ATTN: AMXBR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY FGN SCIENCE & TECH CTR ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1
MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND, MD 21005	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY LABCOM MATERIALS TECHNOLOGY LAB ATTN: SLCMT-IML WATERTOWN, MA 01272	2	DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27, (DOC LIB) WASHINGTON, D.C. 20375	1 1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/DLJ AFATL/DLJG EGLIN AFB, FL 32542	1 1
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CTR BATTELLE COLUMBUS LAB 505 KING AVENUE COLUMBUS, OH 43201	1
COMMANDER NAVAL SURFACE WEAPONS CTR ATTN: TECHNICAL LIBRARY CODE X212 DAHLGREN, VA 22448	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

END

Dtic

7-86