

AD-A177 828

GROOVE ADHESION TEST FOR ELECTRODEPOSITED CHROMIUM(III)

1/1

ARMY ARMAMENT RESEARCH DEVELOPMENT AND ENGINEERING


CENTER WATERVLIET NY BENET WEAPONS LAB S K PAN ET AL


UNCLASSIFIED

JAN 87 ARCCB-TR-87802

F/G 11/6

NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

AD-A177 828

AD

TECHNICAL REPORT ARCCB-TR-87002

GROOVE ADHESION TEST FOR ELECTRODEPOSITED CHROMIUM

S. K. PAN

E. S. CHEN

JANUARY 1987

DTIC
MAR 11 1987
E



**US ARMY ARMAMENT RESEARCH, DEVELOPMENT
AND ENGINEERING CENTER**

**CLOSE COMBAT ARMAMENTS CENTER
BENÉT WEAPONS LABORATORY
WATERVLIET, N.Y. 12189-4050**

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

DTIC FILE COPY

DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) does not constitute an official indorsement or approval.

DESTRUCTION NOTICE

For classified documents, follow the procedures in DoD 5200.22-M, Industrial Security Manual, Section II-19 or DoD 5200.1-R, Information Security Program Regulation, Chapter IX.

For unclassified, limited documents, destroy by any method that will prevent disclosure of contents or reconstruction of the document.

For unclassified, unlimited documents, destroy when the report is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE		READ INSTRUCTIONS BEFORE COMPLETING FORM
1. REPORT NUMBER ARCCB-TR-87002	2. GOVT ACCESSION NO. ADA177828	3. RECIPIENT'S CATALOG NUMBER
4. TITLE (and Subtitle) GROOVE ADHESION TEST FOR ELECTRODEPOSITED CHROMIUM		5. TYPE OF REPORT & PERIOD COVERED Final
7. AUTHOR(s) S. K. Pan and E. S. Chen		6. PERFORMING ORG. REPORT NUMBER
9. PERFORMING ORGANIZATION NAME AND ADDRESS US Army Armament Research, Develop, & Engr Center Benet Weapons Laboratory, SMCAR-CCB-TL Watervliet, NY 12189-4050		8. CONTRACT OR GRANT NUMBER(s)
11. CONTROLLING OFFICE NAME AND ADDRESS US Army Armament Research, Develop, & Engr Center Close Combat Armaments Center Dover, NJ 07801-5001		10. PROGRAM ELEMENT, PROJECT, TASK AREA & WORK UNIT NUMBERS AMCMS No. 6111.02.H600.0 PRON No. 1A6DZ602NMSC
14. MONITORING AGENCY NAME & ADDRESS (if different from Controlling Office)		12. REPORT DATE January 1987
		13. NUMBER OF PAGES 16
		15. SECURITY CLASS. (of this report) UNCLASSIFIED
		15a. DECLASSIFICATION/DOWNGRADING SCHEDULE
16. DISTRIBUTION STATEMENT (of this Report) Approved for public release; distribution unlimited.		
17. DISTRIBUTION STATEMENT (of the abstract entered in Block 20, if different from Report)		
18. SUPPLEMENTARY NOTES Presented at the International Conference on Metallurgical Coatings, San Diego, California, 7-11 April 1986. Published in Proceedings of the Conference.		
19. KEY WORDS (Continue on reverse side if necessary and identify by block number) Adhesion Test Electrodeposit Chromium		
20. ABSTRACT (Continue on reverse side if necessary and identify by block number) A quantitative test has been devised to evaluate the adhesion of electro-deposited chromium on steel substrates. The test involves the cutting of parallel grooves across a plated surface using a small metal shaper equipped with a carbide tool. The grooves are cut at a depth just below the interface and shearing stresses are generated which can produce failure of the coating. In general, varying amounts of residual chromium are left on the surface of the (CONT'D ON REVERSE)		

20. ABSTRACT (CONT'D)

lands depending on the relative cohesive and adhesive bond strengths of the electrodeposited chromium. Energy dispersive x-ray analysis is used to map the distribution of residual chromium and obtain an intensity count. The ratio of intensity count normalized against a reference of 100 percent chromium coverage provides a quantitative measurement of adhesion. The groove adhesion test was found to be equally applicable for the evaluation of both hard chromium and soft chromium deposits.

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution	
Availability	
Dist	
A-1	



UNCLASSIFIED

TABLE OF CONTENTS

	<u>Page</u>
ACKNOWLEDGEMENT	ii
INTRODUCTION	1
EXPERIMENTAL PROCEDURES	2
Grooving	2
Evaluation of Fracture Surface	3
RESULTS AND DISCUSSION	4
CONCLUSIONS	7
REFERENCES	8

TABLES

I. GROOVE ADHESION TEST DATA ON VARIOUS BONDING OF ELECTRODEPOSITED CHROMIUM ON STEEL	5
II. EVALUATION OF ADHESION OF CHROMIUM COATING AND COMPARISON OF EROSION DATA	6

LIST OF ILLUSTRATIONS

1. Schematic diagram of the groove adhesion test apparatus.	9
2. Geometry of grooving tool.	10
3. Energy dispersive x-ray analysis set up for the evaluation of groove adhesion test.	11
4. Photograph and chromium x-ray mapping of electrodeposited chromium showing good adhesion.	12
5. Photograph and chromium x-ray mapping of electrodeposited chromium showing poor adhesion.	13
6. Photograph and chromium x-ray mapping of reference specimen.	14

ACKNOWLEDGEMENT

The authors wish to express their appreciation to their colleague Leo McNamara for SEM analysis.

INTRODUCTION

Electrodeposited coatings are commonly used to improve the decorative appeal of metal surfaces and to protect them against corrosion and wear. In all such applications, adhesion is a parameter of primary consideration because it determines whether or not a coating will become detached during service. The need to evaluate coating adhesion is apparent; however, the difficulty is that very often, individual adhesion tests must be developed to meet a specific need.

A large number of methods, both qualitative and quantitative, are used to measure adhesion. Descriptive accounts of these methods are available in ASTM standards (ref 1), journal articles, and critical reviews (refs 2-6). In general, the selection of a suitable adhesion test method depends to a large extent on whether thin films or thick coatings are to be tested and whether the coatings are hard and brittle or soft and ductile. For hard, thin films, the scratch test has been found to be capable of providing a quantitative measure of adhesive strength. The basic model was derived on the assumption that the interface is subjected to a shear force produced by the motion of a loaded stylus. Adhesion strength is identified with the critical load at which the coating spalls.

Generally, thick, brittle deposits are not amenable to the scratch test unless a chisel or other sharp instrument is used in conjunction to expose the coating/substrate interface (ref 1). The groove test (ref 7) was developed using features associated with the hybrid scratch test. In this case, coating failure is produced by the grooving action of a shaper cutting tool. As a

References are listed at the end of this report.

qualitative tool, optical microscopy is used to examine the exposed interfacial area of a failed region; however, quantified adhesion strength can also be obtained when analytical instrumentation is applied to determine the degree of exposed interfacial area. This report describes the use of energy dispersive x-ray analysis (EDAX) with the groove test. Quantitative adhesion measurements of thick chromium deposition on steel are presented.

EXPERIMENTAL PROCEDURES

The groove test was developed specifically to evaluate the adhesion of chromium electrodeposits on steel substrates. The test procedure involves (a) cutting parallel grooves across the plated surface to induce coating failure, and (b) analyzing the fractured surface with EDAX to determine the relative concentrations of residual chromium and exposed steel. The ratio of intensities of residual chromium to a reference of 100 percent chromium provides a quantitative measure of adhesion strength.

Grooving

The procedures for conducting the groove test have been reported in earlier publications (refs 7-8). For this test, specimen geometry is not crucial provided the specimen can be held securely for a cutting tool to traverse evenly across the plated surface. In this study, a small metal shaper equipped with a carbide tool is used to cut parallel grooves on the surface of chromium plated steel samples as illustrated in Figure 1. Since shear stresses necessary to fracture the coating are generated by the grooving tool, the correct geometry of the tool tip is critical to achieve optimum stresses consistently. From tests with different tool configurations, the best design was found to be a tip machined with a top rake angle of 15 degrees and an

included angle of 90 degrees, Figure 2. Other test parameters remain unchanged, i.e., deposit thickness > 75 μm , grooving depth at 0.3 mm below the coating/substrate interface, and a groove separation of 1.0 mm.

Evaluation of Fracture Surface

When the chromium coating is delaminated by the grooving process, fracture takes place either at the chromium/steel interface or within one of the metals depending on the relative cohesive and adhesive bond strengths. Because chromium deposits contain microcracks and are highly stressed, it is reasonable to assume that delamination will occur in the chromium deposit and/or chromium/steel interface. Therefore, the amount of chromium remaining on the land surfaces (area between grooves) provides a measure of adhesion of chromium to steel.

Energy dispersive x-ray mapping is employed to reveal the chromium distribution on the fractured surface, Figure 3. The chromium x-ray intensity is proportional to the amount of residual chromium on the surface. The total intensity is counted for a given period of time, e.g. 100 seconds, and normalized against a reference intensity of a 100 percent chromium coverage. The degree of chromium adhesion to the steel substrate is calculated in terms of percent of coverage.

An ETEC Autoscan-U1 scanning electron microscope furnished with an energy dispersive analyzer, KEVE-7000, was used in the analysis. The grooved specimen was cleaned to remove the loose fragments and particles of the fractured chromium in preparation for scanning electron microscopy. Test specimens were tilted 30 degrees from a horizontal position toward the electron detector to

obtain the overall surface image. The specimens were subsequently tilted to 40 degrees and the condenser lens current in the microscope set at 1.5 Amp for the chromium x-ray mapping and intensity counting over a period of 100 seconds. The electron beam was generated at 20,000 volts.

An identical specimen grooved by precision grinding to insure perfect chromium coverage on the lands was used as a reference of 100 percent chromium adhesion. The reference specimen was tested under the same conditions as the fractured specimens to obtain intensity counting for normalization.

RESULTS AND DISCUSSION

The groove adhesion test was used to sample a large group of chromium plated steel specimens. The tests were divided into two categories. Specimens in the first category were plated using pretreatment processes known to produce different degrees of adhesion. Four degrees of adhesion were produced and classified as excellent, good, fair, and poor. Table I shows a comparison of the groove adhesion test data with the known values. Figures 4 and 5 show typical chromium x-ray mapping of specimens with good adhesion and poor adhesion. Figure 6 illustrates the distribution of perfect chromium coverage on the reference specimen.

From these results, it is clear that the groove adhesion test has the sensitivity to differentiate the degree of chromium coating adhesion to the steel substrate with respect to both the strength and the uniformity of interfacial bonding. Because the chromium x-ray can be produced by both the incident electron beam and the iron x-ray, these measurements can theoretically include some error contributed from the fluorescent x-ray induced by the excitation of iron x-ray in the steel substrate. Since the chromium x-ray

intensity counting and mapping are based on the chromium x-ray produced only by the incident electron beam striking the residual chromium on the fractured surface, it is necessary to assure that the iron x-ray bordering chromium does not contribute to an enhancement of x-ray intensity. Tests were conducted showing that this was indeed the case. The effect on the counting of chromium intensity was negligible and no effect was observed on the chromium x-ray mapping.

TABLE I. GROOVE ADHESION TEST DATA ON VARIOUS BONDING OF ELECTRODEPOSITED CHROMIUM ON STEEL

Specimen No.	Substate Surface Preparation	Coating Thickness (μ)	Groove Adhesion Test	
			Chromium (%)	Chromium Distribution
CR1ML	Reference	25	100	Completely Covered (Fig. 6)
HC4P1	Excellent	168	73	Uniform (Fig. 4)
HC4P3	Good	177	66	Spotty
HC4P7	Fair	147	42	Spotty
HC4P5	Poor	147	37	Area (Fig. 5)

The fracturing of coatings by grooving is a complicated process. The mechanism of coating delamination is beyond the scope of this study. However, the parameters of importance to the grooving process, such as tool geometry, groove speed, groove depth, and groove separation, which determine the sensitivity and reproducibility of the method, have been optimized experimentally and reported previously (refs 7-8). A double-tip tool has been designed for future testing. The design is based on the depth of cut and the separation of

the groove for producing a land of constant width and acted on by a uniform shear stress. It is expected that this refinement will improve the consistency of test conditions.

In order to compare the results of the groove adhesion test to the proof firing test, the second category of test specimens was prepared from the chromium plated extension rings of the 120 mm M256 gun tubes. Chromium coatings were rated by firing tests and grouped into good, medium, and poor. Table II lists both test data, the proof firing test (after 13 rounds) showing chromium loss area in (mm^2), and the groove adhesion test showing residual chromium on land area in (%). There is good agreement between the two tests for the specimens rated in the groups of good and medium. However, in the group of poor the chromium coatings have much better adhesion. It is quite reasonable to assume that the high chromium loss from those good adhesion coatings is of cohesive fracture, i.e., instead of chromium breaking off from the interface of the coating and steel, it flaked off the coating partially.

**TABLE II. EVALUATION OF ADHESION OF CHROMIUM COATING
AND COMPARISON OF EROSION DATA**

Specimen Ring No.	Proof Firing Test		Cr-Thickness (μ)	Groove Adhesion Test	
	Rating	Cr Loss (mm^2)		Cr (%)	Cr Distribution
212	Good	10	146	81.8	Uniform
215		0	146	57.2	Uniform
223		20	113	87.8	Uniform
239	Medium	400	130	64.4	Spotty
241		500	135	68.4	Spotty
248		200	136	62.8	Spotty
270	Poor	3835	147	95.4	Uniform
309		4187	163	85.8	Uniform
291		5827	178	95.8	Uniform

CONCLUSIONS

The above results show that the chromium loss data include both the adhesive and cohesive fracture of chromium coating. SEM/EDAX data in the groove adhesive test reveals only the adhesive fracture of the chromium coating. Therefore, evaluation of the grooving chips to determine the combination of cohesive and adhesive fracture should be continued in groove adhesion tests. The complete groove test will provide the method of chromium plating quality evaluation, including coating adhesion as well as the combination of the cohesive and adhesive bonding strength of chromium coating on gun steel.

REFERENCES

1. "ASTM Standard Methods of Test for Adhesion of Metallic Coatings," B571-2, November 1972.
2. L. Serota, "Science for Electroplaters, Part 61," Metal Finishing, Vol. 58 November 1960, pp. 65-69 and Vol. 58, December 1960, pp. 65-67.
3. J. W. Dini, J. R. Helms, and H. R. Johnson, Electroplating and Metal Finishing, Vol. 25, 1972, p. 5.
4. K. L. Mittal, in Properties of Electrodeposits, Their Measurements and Significance, R. Sard, Ed., Electrochemical Society, 1975.
5. Adhesion Measurements of Thin Films, Thick Films, and Bulk Coatings, ASTM STP 640, K. L. Mittal, Ed., ASTM, Philadelphia, PA, 1978.
6. A. J. Perry, P. Laeng, and H. E. Huitermann, in Proceedings of the VIII International Conference on CVD, The Electrochemical Society, Pennington, NJ, 1981, pp. 475-88.
7. E. S. Chen and W. Baldauf, "Improved LC Chromium for Gun Tube Applications," ARRADCOM Technical Report ARLCB-TR-80008, Benet Weapons Laboratory, Watervliet, NY, March 1980.
8. E. S. Chen and W. Baldauf, "Activation of Superalloys and Stainless Steels for Chromium Plating," ARRADCOM Technical Report ARLCB-TR-81035, Benet Weapons Laboratory, Watervliet, NY, August 1981.




Figure 1. Schematic diagram of the groove adhesion test apparatus.




Figure 2. Geometry of grooving tool.




Figure 3. Energy dispersive x-ray analysis set up for the evaluation of groove adhesion test.





Figure 4. Photograph and chromium x-ray mapping of electrodeposited chromium showing good adhesion.



Figure 5. Photograph and chromium x-ray mapping of electrodeposited chromium showing poor adhesion.




Figure 6. Photograph and chromium x-ray mapping of reference specimen.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	NO. OF COPIES
CHIEF, DEVELOPMENT ENGINEERING BRANCH	
ATTN: SMCAR-CCB-D	1
-DA	1
-DP	1
-DR	1
-DS (SYSTEMS)	1
-DC	1
-DM	1
CHIEF, ENGINEERING SUPPORT BRANCH	
ATTN: SMCAR-CCB-S	1
-SE	1
CHIEF, RESEARCH BRANCH	
ATTN: SMCAR-CCB-R	2
-R (ELLEN FOGARTY)	1
-RA	1
-RM	1
-RP	1
-RT	1
TECHNICAL LIBRARY	
ATTN: SMCAR-CCB-TL	5
TECHNICAL PUBLICATIONS & EDITING UNIT	
ATTN: SMCAR-CCB-TL	2
DIRECTOR, OPERATIONS DIRECTORATE	1
DIRECTOR, PROCUREMENT DIRECTORATE	1
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1

NOTE: PLEASE NOTIFY DIRECTOR, BENET WEAPONS LABORATORY, ATTN: SMCAR-CCB-TL,
OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH & DEVELOPMENT ATTN: DEP FOR SCI & TECH THE PENTAGON WASHINGTON, D.C. 20315	1	COMMANDER US ARMY AMCCOM ATTN: SMCAR-ESP-L ROCK ISLAND, IL 61299	1
COMMANDER DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-ODA CAMERON STATION ALEXANDRIA, VA 22314	12	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM (MAT SCI DIV) ROCK ISLAND, IL 61299	1
COMMANDER US ARMY MAT DEV & READ COMD ATTN: DRCDE-SG 5001 EISENHOWER AVE ALEXANDRIA, VA 22333	1	DIRECTOR US ARMY INDUSTRIAL BASE ENG ACTV ATTN: DRXIB-M ROCK ISLAND, IL 61299	1
COMMANDER ARMAMENT RES & DEV CTR US ARMY AMCCOM ATTN: SMCAR-FS SMCAR-FSA SMCAR-FSM SMCAR-FSS SMCAR-AEE SMCAR-AES SMCAR-AET-O (PLASTECH) SMCAR-MSI (STINFO) DOVER, NJ 07801	1 1 1 1 1 1 1 2	COMMANDER US ARMY TANK-AUTMV R&D COMD ATTN: TECH LIB - DRSTA-TSL WARREN, MI 48090	1
DIRECTOR BALLISTICS RESEARCH LABORATORY ATTN: AMXBR-TSB-S (STINFO) ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US ARMY TANK-AUTMV COMD ATTN: DRSTA-RC WARREN, MI 48090	1
MATERIEL SYSTEMS ANALYSIS ACTV ATTN: DRXSY-MP ABERDEEN PROVING GROUND, MD 21005	1	COMMANDER US MILITARY ACADEMY ATTN: CHMN, MECH ENGR DEPT WEST POINT, NY 10996	1
		US ARMY MISSILE COMD REDSTONE SCIENTIFIC INFO CTR ATTN: DOCUMENTS SECT, BLDG. 4484 REDSTONE ARSENAL, AL 35898	2
		COMMANDER US ARMY FGN SCIENCE & TECH CTR ATTN: DRXST-SD 220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	1

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
COMMANDER US ARMY LABCOM MATERIALS TECHNOLOGY LAB ATTN: SLCMT-IML WATERTOWN, MA 01272	2	DIRECTOR US NAVAL RESEARCH LAB ATTN: DIR, MECH DIV CODE 26-27, (DOC LIB) WASHINGTON, D.C. 20370	1 1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/MN AFATL/MNG EGLIN AFB, FL 32542-5000	1 1
COMMANDER US ARMY HARRY DIAMOND LAB ATTN: TECH LIB 2800 POWDER MILL ROAD ADELPHIA, MD 20783	1	METALS & CERAMICS INFO CTR BATTELLE COLUMBUS LAB 505 KING AVENUE COLUMBUS, OH 43201	1
COMMANDER NAVAL SURFACE WEAPONS CTR ATTN: TECHNICAL LIBRARY CODE X212 DAHLGREN, VA 22448	1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET WEAPONS LABORATORY, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

END

4-~~2~~-87

DTIC