

AD-A178 504

AD

MEMORANDUM REPORT BRL-MR-3547

HIGH-PROGRESSIVITY/DENSITY (HPD)
PROPELLING CHARGE CONCEPTS; PROGRESS
OF PROGRAMMED-SPLITTING
STICK PROPELLANT

Frederick W. Robbins
Albert W. Horst

September 1986

DTIC
ELECTE
MAR 24 1987
S D

APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.

US ARMY BALLISTIC RESEARCH LABORATORY
ABERDEEN PROVING GROUND, MARYLAND

87 3 23 012


Destroy this report when it is no longer needed.
Do not return it to the originator.

Additional copies of this report may be obtained
from the National Technical Information Service,
U. S. Department of Commerce, Springfield, Virginia
22161.

The findings in this report are not to be construed as an official
Department of the Army position, unless so designated by other
authorized documents.

The use of trade names or manufacturers' names in this report
does not constitute indorsement of any commercial product.

DISCLAIMER NOTICE



THIS DOCUMENT IS BEST QUALITY AVAILABLE. THE COPY FURNISHED TO DTIC CONTAINED A SIGNIFICANT NUMBER OF PAGES WHICH DO NOT REPRODUCE LEGIBLY.

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

AD-A178504

REPORT DOCUMENTATION PAGE				Form Approved OMB No 0704-0188 Exp. Date Jun 30, 1986	
1a. REPORT SECURITY CLASSIFICATION Unclassified			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION / AVAILABILITY OF REPORT Approved for Public Release; Distribution Unlimited.		
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE			5. MONITORING ORGANIZATION REPORT NUMBER(S)		
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Memorandum Report BRL-MR-3547			7a. NAME OF MONITORING ORGANIZATION		
6a. NAME OF PERFORMING ORGANIZATION Ballistic Research Laboratory		6b. OFFICE SYMBOL (If applicable) SLCBL-IE	7b. ADDRESS (City, State, and ZIP Code)		
6c. ADDRESS (City, State, and ZIP Code) Aberdeen Proving Ground Maryland 21005-5066		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER			
8a. NAME OF FUNDING / SPONSORING ORGANIZATION		8b. OFFICE SYMBOL (If applicable)	10. SOURCE OF FUNDING NUMBERS		
8c. ADDRESS (City, State, and ZIP Code)		PROGRAM ELEMENT NO.	PROJECT NO. 1L162618A80	TASK NO. NG	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) High-Progressivity/Density (HPD) Propelling Charge Concepts; Programmed-Splitting Stick Propellant					
12. PERSONAL AUTHOR(S) Robbins, Frederick W., Horst, Albert W.					
13a. TYPE OF REPORT Memorandum Report		13b. TIME COVERED FROM 10/1/83 TO 30/84	14. DATE OF REPORT (Year, Month, Day) September 1986		15. PAGE COUNT 29
16. SUPPLEMENTARY NOTATION					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	Gun Propellant, High Progressivity, High Density,		
20	12		Piezometric Efficiency, Stick Propellant, Programmed-		
21	02		Splitting Propellant; Interior Ballistics, Guns		
19. ABSTRACT (Continue on reverse if necessary and identify by block number) This report summarizes progress to date on the manufacture and closed bomb evaluation of a new high-progressivity gun propellant configuration. The concept is known as programmed-splitting stick propellant and involves the use of embedded slits which are not initially exposed to hot ignition gases. Normal surface regression during burning, however, exposes the slits, typically after peak pressure has been reached in the gun, leading to a large increase in surface area and a corresponding increase in the mass generation rate. Accompanying increases in downbore pressures can lead to significant gains in muzzle velocity without any increase in maximum chamber pressure. At the time of this review, small lots of programmed-splitting stick propellant have been manufactured and subjected to closed bomb evaluation. The results of these tests indicate a high progressivity but not to the degree theoretically predicted. The disparity is postulated to be linked to a finite voidage associated with the slits in the actual grains and its possible influence on successful closure of the ends to ignition gases and mechanical behavior of the grains during the burning process.					
20. DISTRIBUTION AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED UNLIMITED ☒ SAME AS RPT ☐ DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a. NAME OF RESPONSIBLE INDIVIDUAL Frederick W. Robbins			22b. TELEPHONE (Include Area Code) (301) 278-6201		22c. OFFICE SYMBOL SLCBL-IB-A

DD FORM 1473, 84 MAR

83 APR edition may be used until exhausted

All other editions are obsolete

SECURITY CLASSIFICATION OF THIS PAGE

UNCLASSIFIED

TABLE OF CONTENTS

	Page
LIST OF ILLUSTRATIONS.....	5
I. INTRODUCTION.....	7
II. THEORETICAL.....	8
III. MANUFACTURING EXPERIENCE.....	8
IV. EXPERIMENTAL RESULTS.....	11
V. DISCUSSION.....	18
VI. CONCLUSIONS.....	21
ACKNOWLEDGMENTS.....	21
DISTRIBUTION LIST	23

Distribution Statement A is correct for this report.
Per Mr. Lee Hadden, BRL/SLCBB-DD-T



Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

LIST OF ILLUSTRATIONS

Figure		Page
1	Programmed-Splitting Stick Propellant.....	9
2	Calculated Pressure-Time Profile for Programmed-Splitting Stick Propellant.....	9
3	Die Design for Programmed-Splitting Stick Propellant.....	10
4	Theoretical Apparent Burning Rate Profile for Programmed-Splitting Stick Propellant.....	12
5	Theoretical Surface Profile for Programmed-Splitting Stick Propellant.....	13
6	Burning Rates for Solid Strands of NOSOL 363 Propellant.....	14
7	Apparent Burning Rates for Programmed-Splitting Stick Propellant with Open Ends.....	15
8	Burning Surface Profiles for Programmed-Splitting Stick Propellant with Open Ends.....	15
9	Apparent Burning Rates for Programmed-Splitting Stick Propellant with Asphalt-Covered Ends.....	16
10	Apparent Burning Rates for Programmed-Splitting Stick Propellant with Acetone-Solvated Ends.....	16
11	Burning Surface Profiles for Programmed-Splitting Stick Propellant with Acetone-Solvated Ends.....	17
12	Averaged Apparent Burning Rates.....	17
13	Apparent Burning Rates Reduced from a Synthetic Pressure-Time Profile.....	20
14	Burning Surface Profile Reduced from a Synthetic Pressure-Time Profile.....	20

I. INTRODUCTION

The objective of the High-Progressivity/Density (HPD) Propelling Charge Concepts Program is to investigate the feasibility of achieving significant increases in muzzle velocity, for a given maximum pressure, over that achieved by conventional systems now being used. Moreover, this performance increase is to be obtained using existing propellant formulations and without invoking nonconventional ballistic concepts such as traveling charge or light gas guns.

The velocity achieved by a particular projectile as it exits the muzzle of a gun is principally the result of the pressure history acting on its base while it travels down the bore of the tube. The maximum pressure value allowable is usually dictated by gun tube design, but the actual pressure profile, apart from this maximum value, exerted on the projectile base is a result of the competition between the quantity of gas produced by the burning propellant and the amount of free volume available. At the beginning of the event, the projectile is not moving or is moving only very slowly, so the pressure rises rapidly as the propellant burns. However, as the projectile speeds up, it eventually creates additional volume much faster than gases are created to fill it. As a result, in virtually all cases, the pressure falls off much more rapidly than desired.

Past attempts to counter this problem have most often involved the use of propellant configurations exhibiting a continuous increase in burning surface as a function of distance burned (e.g., 7-, 19-, or even 37-perforated grains). Less conventional approaches have included consolidated propellant charges (i.e., one or more compacted aggregates of individual propellant grains), offering an increase in total available energy and the potential for an additional increase in burning surface during the ballistic event as the aggregate deconsolidates. However, programmability and reproducibility of the deconsolidation event have presented serious challenges to the charge designer.

Concepts being considered under the HPD Program include programmed-splitting, perforation-augmented burning, erosive-augmented burning, pressure-supported perforation-augmented burning, monolithic charges, programmed ignition, multiple granulations, and multi-layered propellants.

The approach to be presented in this report is based on a concept by which the increase in surface area can be programmed to commence at any particular point in the burning process, rather than being operative as soon as the propellant is ignited. Thus, a very high loading density charge can be employed without excessive burning surface and overpressurization of the gun early in the ballistic cycle. Second, this increase in surface area is, conceptually at least, unlimited. Thus, despite a desirably low initial burning surface, the programmed increase in burning surface after peak pressure can assure total burning of the charge before the projectile exits the gun, meeting the second major requirement for the use of very high loading density charges. This concept, applicable to a number of propellant configurations, has been exploited first as programmed-splitting stick propellant, and progress to date will be reported.

II. THEORETICAL

Many gun systems utilize 7-perforated granular propellant as the main propellant charge. If the same charge weight as used in the 7-perforated charge is assumed to burn such that the maximum velocity is obtained (a constant pressure calculation), a velocity increase of only about 5% over that of an optimized 7-perforated charge is predicted. Therefore, not only a near-optimum burning surface profile (i.e., extremely progressive) but also more total energy (i.e., greater charge weight) is required in order to achieve greater increases in velocity.

Particularly attractive in respect to both of these requirements is the programmed-splitting propellant concept, which effectively decouples the burning surface after peak pressure from that preceding it. This concept provides for a discontinuous increase in burning surface at any desired regression distance, at which point the burning surface reaches an embedded array of slits and the flame envelopes the additional surface area. A programmed-splitting stick (see Figure 1) was selected for initial study because it seemed to be manufacturable with current extrusion technology, to offer a very high loading density, and to provide the fault-tolerant, ignition benefits of a stick propellant configuration. The same concept can be applied to slab or scroll propellant configurations, but manufacturing problems were felt to be greater. Any of these configurations, of course, requires that the ends or edges where the slits are initially exposed be adequately inhibited to prevent the flame from prematurely reaching the slits. NOSOL 363 propellant (Lot RAD-1-2-73) was chosen for this initial effort because it is extruded without solvents and potential problems with drying would be reduced; in addition, the sheet stock was readily available.

The programmed-splitting stick propellant configuration was modeled as a cord until the slits were reached and then as long pie-shaped wedges. The slits were assumed initially to occupy no volume. The optimization process involved first determining the proper cord geometry to achieve the desired maximum pressure and then defining the slit parameters (number and dimension) to raise the pressure to this same value once again, as shown in Figure 2. Clearly, a multiplicity of such grain configurations could be employed to achieve an even greater number of peaks, approaching the optimal flat pressure-time curve. However, even the single, basic configuration with three or four slits of the same dimension (yielding six or eight pie-shaped wedges) was calculated to provide the desired increase in performance for the 155-mm howitzer.

III. MANUFACTURING EXPERIENCE

A die and stake, shown in Figure 3, were designed and fabricated for manufacturing programmed-splitting stick propellant of the calculated, nominal dimensions for the 155-mm howitzer. The stake was made by soldering four half-vanes to one whole vane, all 0.254 mm thick, making a three-vane stake. The vanes were then soldered into a base which fit into the die. Both cord propellant and programmed-splitting stick propellant were extruded for closed bomb firings. The cord propellant was made by




Figure 1. Programmed-Splitting Stick Propellant




Figure 2. Calculated Pressure-Time Profile for Programmed-Splitting Stick Propellant




Figure 3. Die Design for Programmed-Splitting Stick Propellant

removing the stake and extruding through the same die. Both configurations expanded after extrusion, with the programmed-splitting stick expanding by 3% and the solid cord expanding 5.6% on the outside diameter.

Initial extrusions were successful in that the slits remained blind, never breaking through to the outer lateral surfaces, despite the small webs. The overall average web was 0.686 mm, but, as the vanes, once assembled to the base, were not all of the same dimension, a smaller-web region resulted where the average was 0.546 mm and the minimum was 0.483 mm. The discrepancies between the diameters associated with the die vanes and those with the resulting propellant slits varied, with the largest deviations associated with the largest vanes. Moreover, the slits in the propellant, rather than having no volume, exhibited approximately the same width as the vanes. This resulted in an internal void volume of approximately 10%. It was also noted that the edges near the center of the grains had small irregularities similar to the edge of a saw blade. Table 1 summarizes all pertinent dimensions.

After the first two-pound extrusion of NOSOL 363, the vanes were found to be loose and were resoldered. Subsequently, while attempting to extrude a sample of JA2 propellant sheet stock, the stake separated from the base. New stakes have been machined from one piece of metal but, as of the time of this writing, have yet to be tried. The procedure for defining the new stake and die dimensions was to assume that the slit diameter would remain the same as the vane diameter and that an expansion of 3% would occur in the propellant web. Further, the tips and the edges of the vanes were filed to a sharp edge in an attempt to reduce slit width.

TABLE I. SUMMARY OF DIE AND PROPELLANT DIMENSIONS

	DIE AND STAKE (FROM DRAWING) mm	DIE AND STAKE (MEASURED) mm	PROGRAMMED -SPLITTING GRAIN (MEASURED) mm (MIN) (MAX)	SOLID CORD GRAIN (MEASURED) mm (MIN) (MAX)
DIAM (X)	5.89	5.83	6.07 (5.99) (6.17)	6.22 (6.20) (6.24)
SLOT DIAM (Y1)	4.70	4.55	4.57 (4.34) (4.83)	
(Y2)	4.70	4.78	4.70 (4.47) (4.98)	
(Y3)	4.70	4.83	5.06 (4.90) (5.21)	
AVERAGE	4.70	4.72	4.78	
SLOT WIDTH (Z)	0.254	0.254	0.254	
WEB (W)	0.594 *	0.585 *	0.686 (0.483) (0.914)	

* CALCULATED

IV. EXPERIMENTAL RESULTS

Closed bomb firings were conducted in an attempt to determine whether the programmed-splitting propellant burns as mathematically modeled and to test the effectiveness of different methods of sealing the ends of the grains. Also, tests were performed statically in a high pressure oil bath to evaluate the end seals.

A closed bomb is a closed vessel with no moving boundaries in which propellant is burned. The pressure-time curve is measured, and with certain assumptions (e.g., instantaneous ignition, normal regression on all propellant surfaces, and a given mass fraction as a function of distance burned) one can deduce the rate of surface regression (i.e., the burning rate) as a function of pressure.

A 210-cc closed bomb was chosen for these studies because of the limited amount of propellant available. All samples were cut to 9.6 cm in length, the longest the bomb would accommodate. Configurations tested were both cord and programmed-splitting, the latter with a variety of end conditions, including open-ended, asphalt-covered, acetone-solvated, acetone-solvated covered with collodion, covered with a small aluminum cap, and capped with NOSOL 363 discs bonded with an isocyanate crosslinking agent. In addition, a previously extruded, single-perforated grain of the same composition but a different length was tested to allow comparison with past results.

Since the closed bomb data reduction program does not include a form function to describe programmed-splitting configurations, the analysis was performed assuming the grain to be a solid cord, yielding an apparent burning rate. However, by assuming the burning rates obtained for the sample of actual cord propellant to be applicable to the programmed-splitting grains as well, we were able to deduce burning surface profiles from the mass-generation rate data, revealing more directly the behavior of the programmed-splitting event. Theoretically, the apparent burning rate curves should have resembled Figure 4 and the surface area profiles should have looked like Figure 5.

A problem was encountered in the reduction of closed bomb data because of the internal voidage associated with the blind slits. There were 21 grains used in each firing, but the computer program calculated (from the density, mass of propellant, and grain dimensions) that there were approximately 19 grains. This led to apparent burning rates and surface areas which were higher at all points than theoretically expected; however, it should not have changed the shape of the curves.




Figure 4. Theoretical Apparent Burning Rate Profile for Programmed-Splitting Stick Propellant




Figure 5. Theoretical Surface Profile for Programmed-Splitting Stick Propellant

Another problem with the reduction technique which could have changed the shape of the curves was the smoothing technique applied to the pressure-time output from the closed bomb firings. Such procedures tend to smooth out any abrupt changes, such as that expected with a discontinuous increase in surface area. To probe this concern, a computer-generated pressure-time curve (generated using a true, programmed-splitting form function) was smoothed in the same manner as the real output from a closed bomb firing. Indeed, the expected, abrupt changes in the reduced data were rounded but not to a degree that would prevent recognition of the splitting event.

The burning rates for the cord, shown in Figure 6, and for the single-perforated granulations were consistent and also agreed well with previous NOSOL 363 closed bomb data. These burning rates were therefore used as the baseline and for the reduction of all burning surface profiles.




Figure 6. Burning Rates for Solid Strands of NOSOL 363 Propellant

The apparent burning rates for the open-ended, programmed-splitting configuration (reduced as a cord) showed considerable variability in the 7-35 MPa pressure range and, as expected, manifested about a 3-fold increase over the burning rates of the cord for the entire pressure range (see Figure 7). The accompanying burning surface profiles are provided in Figure 8. Figure 9 displays the apparent burning rates for the sample with asphalt-covered ends. Figure 10 presents the apparent burning rates for the sample whose ends had been solvated in acetone to close the slits, and Figure 11 shows the corresponding surface profiles. A comparison of the averaged values of the burning rates for the cord and the apparent burning rates for the three programmed-splitting samples is shown in Figure 12.

Other attempts at closing off the ends of the blind slits in the programmed-splitting propellant samples, such as the use of aluminum end caps and NOSOL 363 discs as mentioned earlier, were no more effective than just solvating the ends with acetone. The discussion will therefore be centered around the configuration with acetone-solvated ends.

Grains with acetone-solvated ends similar to those used in the closed bomb studies were also pressurized slowly in an oil bath, in 70-MPa increments, to over 500 MPa. The samples were inspected after each increment of pressurization. One out of the ten pressurized had oil in the voidage after the first 70 MPa; the rest all remained intact with no oil in the voidage over the entire pressure range.




Figure 7. Apparent Burning Rates for Programmed-Splitting Stick Propellant with Open Ends




Figure 8. Burning Surface Profiles for Programmed-Splitting Stick Propellant with Open Ends




Figure 9. Apparent Burning Rates for Programmed-Splitting Stick Propellant with Asphalt-Covered Ends




Figure 10. Apparent Burning Rates for Programmed-Splitting Stick Propellant with Acetone-Solvated Ends




Figure 11. Burning Surface Profiles for Programmed-Splitting Stick Propellant with Acetone-Solvated Ends




Figure 12. Averaged Apparent Burning Rates

V. DISCUSSION

Successful application of the programmed-splitting stick propellant concept in the gun environment requires that the discontinuous increase in surface area must occur only after maximum pressure has occurred. This, in turn, requires that the flame not reach the blind slits prematurely (i.e., by any means except the planned burn-through of the web). The flame must be prevented from entering the ends of the grains and the grain must not break, opening a path to the blind slits. Therefore, most of the discussion will address this aspect of the problem.

From Figure 12, it would appear that the asphalt covering did not prevent the flame from getting to the slits since the apparent burning rates for that sample are higher in the low pressure region than for the cords or the sample with acetone-solvated ends. The asphalt seems, however, to have acted as an inhibitor on the ends themselves, since the apparent burning rates are not as high as for the open-ended grains. Further, no progressivity is revealed, as the curves for the samples with asphalt-covered and open ends are nearly parallel to that for the cord propellant.

Figure 12 shows a small increase in the apparent burning rates at low pressures for the samples with acetone-solvated ends. This is not, however, totally unexpected since the reduction procedure will, because it ignores the presence of voidage in the slit region, underestimate the total number of grains (and accompanying initial surface) and therefore overestimate the apparent burning rates by about 10%. We further expect to see the apparent burning rates increasing faster than for the cord propellant and the curve then becoming parallel to that for the open-ended grains. What is surprising is that the burning rate curve should start to rise at such a low pressure (50 MPa) and continue to exhibit progressivity long after expected web burn-through at about 125 MPa!

We next call attention to the burning surface profile for this same sample with acetone-solvated ends, shown in Figure 11 along with a theoretical profile for the programmed-splitting grain. The surface profile seems to be a much better discriminator for the processes of interest to us here. Again we see an early increase around 50 MPa, followed by incremental increases until the curve approaches the theoretical curve at a point long after web burn-through should have occurred.

There are three effects which could have been responsible for the unexpected, early rise in the apparent burning rates and the burning surface profile. They are data-smoothing during the reduction procedure (mentioned earlier), variations in the web, and early exposure of some portion of the blind slits. In order to study each of these possibilities, calculations were made with a computer code to simulate the programmed-splitting configuration burning in a closed bomb. The form function was programmed to assume burning on lateral and end surfaces until web burn-through and then on the remaining long, pie-shaped wedges. It was also assumed that the slits occupied no volume. The resultant pressure-time curve served as input to the existing closed bomb data reduction program,

and apparent burning rates and surface areas were calculated using minimal smoothing (no smoothing on the pressure-time curve and a 5-point smoothing bridge to obtain dp/dt) and then with the normal smoothing procedure (a 25-point smoothing bridge on the pressure-time curve and a 15-point bridge to obtain dp/dt). The apparent burning rate curves are shown in Figure 13, and the surface area ratio curves are displayed in Figure 14. It is apparent that smoothing was not responsible for the unexpected closed bomb results.

Other synthetic runs were performed to investigate the possibility of the web variation being large enough to account for this effect. A run was made with 1/3 of the charge weight having a web equal to the smallest measured web (0.483 mm) and the rest of the charge having the average of the smallest web (0.546 mm). An increase in surface area was then indicated at approximately twice the mass fraction burned (which translates also into twice the closed bomb pressure) as that where the observed, apparent burning rate curve started to rise. Even in combination with smoothing effects, this did not provide an explanation for observed behavior.

A third series of synthetic runs was made with 1/3 of the charge configured such that burn-through of the web occurred at 50 MPa and the remaining portion having a web of 0.546 mm (the average of the smallest web). These conditions, of course, reproduced the observed, early increase in the burning surface, but they also delayed burn-through of the 0.546-mm web until a pressure which was some 35 MPa higher than the value where burn-through for a 0.545-mm web would have taken place. This result approximated what we saw in the surface profiles for the samples with acetone-solvated ends, and, along with the static test results indicating grain survivability at high pressures, is consistent with an explanation for the observed closed bomb results based on early flame penetration into a significant portion but not a majority of the blind slits.

Many other problem areas remain to be investigated, including the effects of aging on any successful end-closure techniques, sensitivity of performance to web variations, the influence of propellant mechanical properties, and temperature effects. At the same time, alternative HPD concepts warrant consideration in the near future.




Figure 13. Apparent Burning Rates Reduced From a Synthetic Pressure-Time Profile




Figure 14. Burning Surface Profile Reduced from a Synthetic Pressure-Time Profile

CONCLUSIONS

Substantial performance gains are theoretically possible from rather straight-forward HPD propulsion concepts using existing propellant technology.

The feasibility of manufacturing a programmed-splitting stick propellant has been demonstrated using existing extrusion technology.

Techniques for sealing the ends of programmed-splitting stick propellant have been partially demonstrated, offering significant hope for demonstrating this HPD concept in the gun environment within the coming year.

ACKNOWLEDGMENTS

The authors are indebted to Mr. John Moniz and the Pilot Plant personnel at the Naval Ordnance Station, Indian Head, MD, for extruding these first samples of programmed-splitting propellant. We also wish to thank Dr. A. Juhasz, Mr. W. Aungst and Mr. W. Bowman of the Ballistic Research Laboratory for performing the closed bomb firings as well as Mr. A. Koszoru for sample measurements and preparation. Appreciation is also expressed to Mr. D. Bullock for performing the high-pressure oil bath compression tests and to Mr. F. Lynn for implementing the programmed-splitting stick form function into an interior ballistic code.

DISTRIBUTION LIST

<u>No. Of</u> <u>Copies</u>	<u>Organization</u>	<u>No. Of</u> <u>Copies</u>	<u>Organization</u>
12	Administrator Defense Technical Info Center ATTN: DTIC-DDA Cameron Station Alexandria, VA 22304-6145	1	Commander US Army Materiel Command ATTN: AMCDRA-ST 5001 Eisenhower Avenue Alexandria, VA 22333-5001
1	Commander USA Concepts Analysis Agency ATTN: D. Hardison 8120 Woodmont Avenue Bethesda, MD 20014-2797	1	Commander US Army Materiel Command ATTN: AMCDE-DW 5001 Eisenhower Avenue Alexandria, VA 22333-5001
1	HQDA/DAMA-ZA Washington, DC 20310-2500	5	Project Manager Cannon Artillery Weapons System, ARDC, AMCCOM ATTN: AMCPM-CW, F. Menke AMCPM-CWW AMCPM-CWS M. Fisette AMCPM-CWA R. DeKleine H. Hassmann Dover, NJ 07801-5001
1	HQDA, DAMA-CSM, E. Lippi Washington, DC 20310-2500		
1	HQDA/SARDA Washington, DC 20310-2500		
1	Commander US Army War College ATTN: Library-FF229 Carlisle Barracks, PA 17013		
1	US Army Ballistic Missile Defense Systems Command Advanced Technology Center P. O. Box 1500 Huntsville, AL 35807-3801	2	Project Manager Munitions Production Base Modernization and Expansion ATTN: AMCPM-PBM, A. Siklosi AMCPM-PBM-E, L. Laibson Dover, NJ 07801-5001
1	Chairman DOD Explosives Safety Board Room 856-C Hoffman Bldg. 1 2461 Eisenhower Avenue Alexandria, VA 22331-9999	3	Project Manager Tank Main Armament System ATTN: AMCPM-TMA, K. Russell AMCPM-TMA-105 AMCPM-TMA-120 Dover, NJ 07801-5001
1	Commander US Army Materiel Command ATTN: AMCPM-GCM-WF 5001 Eisenhower Avenue Alexandria, VA 22353-5001	1	Commander US Army Watervliet Arsenal ATTN: SARWV-RD, R. Thierry Watervliet, NY 12189-5001

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
20	Commander US Army ARDC, AMCCOM ATTN: SMCAR-TSS SMCAR-TDC SMCAR-LC LTC N. Barron SMCAR-LCA A. Beardell D. Downs S. Einstein S. Westley S. Bernstein C. Roller J. Rutkowski SMCAR-LCB-I D. Spring SMCAR-LCE SMCAR-LCM-E S. Kaplowitz SMCAR-LCS SMCAR-LCU-CT E. Barrieres R. Davitt SMCAR-LCU-CV C. Mandala SMCAR-LCW-A M. Salsbury SMCAR-SCA L. Stiefel B. Brodman Dover, NJ 07801-5001	1	HQDA DAMA-ART-M Washington, DC 20310-2500
		1	Director Benet Weapons Laboratory Armament R&D Center US Army AMCCOM ATTN: SMCAR-LCB-TL Watervliet, NY 12189-5001
		1	Commander US Army Aviation Research and Development Command ATTN: AMSAV-E 4300 Goodfellow Blvd. St. Louis, MO 63120-1702
		1	Commander US Army TSARCOM 4300 Goodfellow Blvd. St. Louis, MO 63120-1702
		1	Director US Army Air Mobility Research And Development Laboratory Ames Research Center Moffett Field, CA 94035-1099
		1	Commander US Army Communications - Electronics Command ATTN: AMSEL-ED Fort Monmouth, NJ 07703-5301
1	Commander Armament R&D Center U.S. Army AMCCOM ATTN: SMCAR-TSS Dover, NJ 07801-5001	1	Commander ERADCOM Technical Library ATTN: DELSD-L (Report Section) Fort Monmouth, NJ 07703-5301
1	Commander Armament R&D Center U.S. Army AMCCOM ATTN: SMCAR-TDC Dover, NJ 07801	1	Commander US Army Harry Diamond Lab. ATTN: DELHD-TA-L 2800 Powder Mill Road Adelphi, MD 20783-1145
4	Commander US Army Armament Munitions and Chemical Command ATTN: SMCAR-ESP-L Rock Island, IL 61299-7300		

DISTRIBUTION LIST

<u>No. Of</u> <u>Copies</u>	<u>Organization</u>	<u>No. Of</u> <u>Copies</u>	<u>Organization</u>
1	Commander US Army Missile Command ATTN: AMSMI-CM Redstone Arsenal, AL 35898-5249	2	Program Manager M1 Abrams Tank System ATTN: AMCPM-GMC-SA, T. Dean Warren, MI 48092-2498
1	Commander US Army Missile and Space Intelligence Center ATTN: AIAMS-YDL Redstone Arsenal, AL 35898-5500	1	Project Manager Fighting Vehicle Systems ATTN: AMCPM-FVS Warren, MI 48092-2498
1	Commander US Army Missile Command Research, Development, and Engineering Center ATTN: AMSMI-RD Redstone Arsenal, AL 35898-5500	1	President US Army Armor & Engineer Board ATTN: ATZK-AD-S Fort Knox, KY 40121-5200
1	Commandant US Army Aviation School ATTN: Aviation Agency Fort Rucker, AL 36360	1	Project Manager M-60 Tank Development ATTN: AMCPM-M60TD Warren, MI 48092-2498
1	Commander US Army Tank Automotive Command ATTN: AMSTA-TSL Warren, MI 48397-5000	1	Director US Army TRADOC Systems Analysis Activity ATTN: ATAA-SL White Sands Missile Range, NM 88002
1	Commander US Army Tank Automotive Command ATTN: AMSTA-CG Warren, MI 48397-5000	1	Commander US Army Training & Doctrine Command ATTN: ATCD-MA/ MAJ Williams Fort Monroe, VA 23651
1	Project Manager Improved TOW Vehicle ATTN: AMCPM-ITV US Army Tank Automotive Command Warren, MI 48397-5000	2	Commander US Army Materials and Mechanics Research Center ATTN: AMXMR-ATL Tech Library Watertown, MA 02172
		1	Commander US Army Research Office ATTN: Tech Library P. O. Box 12211 Research Triangle Park, NC 27709-2211

DISTRIBUTION LIST

<u>No. Of</u> <u>Copies</u>	<u>Organization</u>	<u>No. Of</u> <u>Copies</u>	<u>Organization</u>
1	Commander US Army Belvoir Research & Development Center ATTN: STRBE-WC Fort Belvoir, VA 22060-5606	1	Commander US Army Development and Employment Agency ATTN: MODE-TED-SAB Fort Lewis, WA 98433-5099
1	Commander US Army Logistics Mgmt Ctr Defense Logistics Studies Fort Lee, VA 23801	1	Chief of Naval Material Department of the Navy ATTN: J. Amlie Arlington, VA 20360
1	Commandant US Army Infantry School ATTN: ATSH-CD-CSO-OR Fort Benning, GA 31905	1	Office of Naval Research ATTN: Code 473, R. S. Miller 800 N. Quincy Street Arlington, VA 22217-9999
1	President US Army Artillery Board Ft. Sill, OK 73503-5600	3	Commandant US Army Armor School ATTN: ATZK-CD-MS M. Falkovitch Armor Agency Fort Knox, KY 40121-5215
1	Commandant US Army Command and General Staff College Fort Leavenworth, KS 66027	2	Commander Naval Sea Systems Command ATTN: SEA 62R SEA 64 Washington, DC 20362-5101
1	Commandant US Army Special Warfare School ATTN: Rev & Tng Lit Div Fort Bragg, NC 28307	1	Commander Naval Air Systems Command ATTN: AIR-954-Tech Lib Washington, DC 20360
3	Commander Radford Army Ammunition Plant ATTN: SMCRA-QA/HI LIB Radford, VA 24141-0298	1	Assistant Secretary of the Navy (R, E, and S) ATTN: R. Reichenbach Room 5E787 Pentagon Bldg. Washington, DC 20350
1	Commander US Army Foreign Science & Technology Center ATTN: AMXST-MC-3 220 Seventh Street, NE Charlottesville, VA 22901-5396	1	Naval Research Lab Tech Library Washington, DC 20375
2	Commandant US Army Field Artillery Center & School ATTN: ATSF-CO-MW, B. Willis Ft. Sill, OK 73503-5600		

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
5	Commander Naval Surface Weapons Center ATTN: Code G33, J. L. East W. Burrell J. Johndrow Code G23, D. McClure Code DX-21 Tech Lib Dahlgren, VA 22448-5000	1	Program Manager AFOSR Directorate of Aerospace Sciences ATTN: L. H. Caveny Bolling AFB, DC 20332-0001
2	Comander US Naval Surface Weapons Center ATTN: J. P. Consaga C. Gotzmer Indian Head, MD 20640-5000	6	Commander Naval Ordnance Station ATTN: P. L. Stang J. Birkett L Torreyson T. C. Smith D. Brooks Tech Library Indian Head, MD 20640-5000
4	Commander Naval Surface Weapons Center ATTN: S. Jacobs/Code 240 Code 730 K. Kim/Code R-13 R. Bernecker Silver Spring, MD 20903-5000	1	AFSC/SDOA Andrews AFB, MD 20334
2	Commanding Officer Naval Underwater Systems Center Energy Conversion Dept. ATTN: CODE 5B331, R. S. Lazar Tech Lib Newport, RI 02840	3	AFRPL/DY, Stop 24 ATTN: J. Levine/DYCR R. Corley/DYC D. Williams/DYCC Edwards AFB, CA 93523-5000
4	Commander Naval Weapons Center ATTN: Code 388, R. L. Derr C. F. Price T. Boggs Info. Sci. Div. China Lake, CA 93555-6001	1	AFRPL/TSTL (Tech Library) Stop 24 Edwards AFB, CA 93523-5000
2	Superintendent Naval Postgraduate School Dept. of Mechanical Engineering Monterey, CA 95043-5100	1	AFATL/DLYV Eglin AFB, FL 32542-5000
		1	AFATL/DLXP Eglin AFB, FL 32542-5000
		1	AFATL/DLJE Eglin AFB, FL 32542-5000
		1	AFATL/DLODL ATTN: Tech Lib Eglin AFB, FL 32542-5000
		1	AFWL/SUL Kirtland AFB, NM 87117

DISTRIBUTION LISTS

<u>No. of Copies</u>	<u>Organization</u>	<u>No. of Copies</u>	<u>Organization</u>
1	NASA/Lyndon B. Johnson Space Center ATTN: NHS-22, Library Section Houston, TX 77054	10	Central Intelligence Agency Office of Central Reference Dissemination Branch Room GE-47 HQS Washington, DC 20505
1	AFELM, the Rand Corporation ATTN: Library D (Required or 1700 Main Street Classified Santa Monica CA Only) 90401-3297	1	General Electric Company Armament Systems Dept. ATTN: M. J. Bulman, Room 1311 128 Lakeside Avenue Burlington, VT 05401-4985
1	General Applied Sciences Lab ATTN: J. Erdos Merrick & Stewart Avenues Westbury Long Isld, NY 11590	1	IITRI ATTN: M. J. Klein 10 W. 35th Street Chicago, IL 60616-3799
2	AAI Corporation ATTN: J. Hebert J. Frankle P. O. Box 6767 Baltimore, MD 21204	1	Hercules Inc. Allegheny Ballistics Laboratory ATTN: R. B. Miller P. O. Box 210 Cumberland, MD 21501-0210
1	Aerojet Ordnance Company ATTN: D. Thatcher 2521 Michelle Drive Tustin, CA 92680-7014	1	Hercules, Inc. Bacchus Works ATTN: K. P. McCarty P. O. Box 98 Magna, UT 84044-0098
1	Aerojet Solid Propulsion Co. ATTN: P. Micheli Sacramento, CA 95813	1	Hercules, Inc. Radford Army Ammunition Plant ATTN: J. Pierce Radford, VA 24141-0299
1	Atlantic Research Corporation ATTN: M. K. King 5390 Chesapeake Avenue Alexandria, VA 22312-2302	1	Honeywell, Inc. - MN64 2200 Defense Systems Division ATTN: C. Hargreaves 6110 Blue Circle Drive Minnetonka MN 55436
1	AVCO Everett Rsch Lab ATTN: D. Stickler 2385 Revere Beach Parkway Everett, MA 02149-5936	1	Lawrence Livermore National Laboratory ATTN: L-355, A. Buckingham M. Finger P. O. Box 808 Livermore, CA 94550-0622
2	Calspan Corporation ATTN: C. Morphy P. O. Box 400 Buffalo, NY 14225-0400		

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	Lawrence Livermore National Laboratory ATTN: L-324 M. Constantino P. O. Box 808 Livermore, CA 94550-0622	3	Thiokol Corporation Huntsville Division ATTN: D. Flanigan R. Glick Tech Library Huntsville, AL 35807
1	Olin Corporation Badger Army Ammunition Plant ATTN: R. J. Thiede Baraboo, WI 53913	1	Scientific Research Assoc., Inc. ATTN: H. McDonald P.O. Box 498 Glastonbury, CT 06033-0498
1	Olin Corporation Smokeless Powder Operations ATTN: D. C. Mann P.O. Box 222 St. Marks, FL 32355-0222	1	Thiokol Corporation Wasatch Division ATTN: J. A. Peterson P. O. Box 524 Brigham City, UT 84302-0524
1	Paul Gough Associates, Inc. ATTN: P. S. Gough P. O. Box 1614, 1048 South St. Portsmouth, NH 03801-1614	2	Thiokol Corporation Elkton Division ATTN: R. Biddle Tech Lib. P. O. Box 241 Elkton, MD 21921-0241
1	Physics International Company ATTN: Library H. Wayne Wampler 2700 Merced Street San Leandro, CA 94577-5602	2	United Technologies Chemical Systems Division ATTN: R. Brown Tech Library P. O. Box 358 Sunnyvale, CA 94086-9998
1	Princeton Combustion Research Lab., Inc. ATTN: M. Summerfield 475 US Highway One Monmouth Junction, NJ 08852-9650	1	Veritay Technology, Inc. ATTN: E. Fisher 4845 Millersport Hwy. P. O. Box 305 East Amherst, NY 14051-0305
2	Rockwell International Rocketdyne Division ATTN: BA08 J. E. Flanagan J. Gray 6633 Canoga Avenue Canoga Park, CA 91303-2703	1	Universal Propulsion Company ATTN: H. J. McSpadden Black Canyon Stage 1 Box 1140 Phoenix, AZ 85029
1	Science Applications, Inc. ATTN: R. B. Edelman 23146 Cumorah Crest Drive Woodland Hills, CA 91364-3710		

DISTRIBUTION LIST

<u>No. Of</u> <u>Copies</u>	<u>Organization</u>	<u>No. Of</u> <u>Copies</u>	<u>Organization</u>
1	Battelle Memorial Institute ATTN: Tech Library 505 King Avenue Columbus, OH 43201-2693	3	Georgia Institute of Tech School of Aerospace Eng. ATTN: B. T. Zinn E. Price W. C. Strahle Atlanta, GA 30332
1	Brigham Young University Dept. of Chemical Engineering ATTN: M. Beckstead Provo, UT 84601	1	Institute of Gas Technology ATTN: D. Gidaspow 3424 S. State Street Chicago, IL 60616-3896
1	California Institute of Tech 204 Karman Lab Main Stop 301-46 ATTN: F. E. C. Culick 1201 E. California Street Pasadena, CA 91109	1	Johns Hopkins University Applied Physics Laboratory Chemical Propulsion Information Agency ATTN: T. Christian Johns Hopkins Road Laurel, MD 20707-0690
1	California Institute of Tech Jet Propulsion Laboratory ATTN: L. D. Strand 4800 Oak Grove Drive Pasadena, CA 91109-8099	1	Massachusetts Institute of Technology Dept of Mechanical Engineering ATTN: T. Toong 77 Massachusetts Avenue Cambridge, MA 02139-4307
1	University of Illinois Dept of Mech/Indust Engr ATTN: H. Krier 144 MEB; 1206 N. Green St. Urbana, IL 61801-2978	1	G. M. Faeth Pennsylvania State University Applied Research Laboratory University Park, PA 16802-7501
1	University of Massachusetts Dept. of Mechanical Engineering ATTN: K. Jakus Amherst, MA 01002-0014	1	Pennsylvania State University Dept. Of Mech. . ineering ATTN: K. Kuo University Park, PA 16802-7501
1	University of Minnesota Dept. of Mechanical Engineering ATTN: E. Fletcher Minneapolis, MN 55414-3368	1	Purdue University School of Mechanical Engineering ATTN: J. R. Osborn TSPC Chaffee Hall West Lafayette, IN 47907-1199
1	Case Western Reserve University Division of Aerospace Sciences ATTN: J. Tien Cleveland, OH 44135		

DISTRIBUTION LIST

<u>No. Of Copies</u>	<u>Organization</u>	<u>No. Of Copies</u>	<u>Organization</u>
1	SRI International Propulsion Sciences Division ATTN: Tech Library 333 Ravenswood Avenue Menlo Park, CA 94025-3493		<u>Aberdeen Proving Ground</u> Dir, USAMSAA ATTN: AMXSY-D AMXSY-MP, H. Cohen Cdr, USATECOM ATTN: AMSTE-TO-F AMSTE-CM-F, L. Nealley Cdr, CSTA ATTN: STECS-AS-H, R. Hendricksen Cdr, CRDC, AMCCOM ATTN: SMCCR-RSP-A SMCCR-MU SMCCR-SPS-IL
1	Rensselaer Polytechnic Inst. Department of Mathematics Troy, NY 12181		
2	Director Los Alamos Scientific Lab ATTN: T3, D. Butler M. Division, B. Craig P. O. Box 1663 Los Alamos, NM 87544		
1	Stevens Institute of Technology Davidson Laboratory ATTN: R. McAlevy, III Castle Point Station Hoboken, NJ 07030-5907		
1	Rutgers University Dept. of Mechanical and Aerospace Engineering ATTN: S. Temkin University Heights Campus New Brunswick, NJ 08903		
1	University of Southern California Mechanical Engineering Dept. ATTN: OHE200, M. Gerstein Los Angeles, CA 90089-5199		
2	University of Utah Dept. of Chemical Engineering ATTN: A. Baer G. Flandro Salt Lake City, UT 84112-1194		
1	Washington State University Dept. of Mechanical Engineering ATTN: C. T. Crowe Pullman, WA 99163-5201		

USER EVALUATION SHEET/CHANGE OF ADDRESS

This Laboratory undertakes a continuing effort to improve the quality of the reports it publishes. Your comments/answers to the items/questions below will aid us in our efforts.

1. BRL Report Number _____ Date of Report _____

2. Date Report Received _____

3. Does this report satisfy a need? (Comment on purpose, related project, or other area of interest for which the report will be used.) _____

4. How specifically, is the report being used? (Information source, design data, procedure, source of ideas, etc.) _____

5. Has the information in this report led to any quantitative savings as far as man-hours or dollars saved, operating costs avoided or efficiencies achieved, etc? If so, please elaborate. _____

6. General Comments. What do you think should be changed to improve future reports? (Indicate changes to organization, technical content, format, etc.) _____

CURRENT ADDRESS	_____
	Name

	Organization

	Address

	City, State, Zip

7. If indicating a Change of Address or Address Correction, please provide the New or Correct Address in Block 6 above and the Old or Incorrect address below.

OLD ADDRESS	_____
	Name

	Organization

	Address

	City, State, Zip

(Remove this sheet along the perforation, fold as indicated, staple or tape closed, and mail.)

----- FOLD HERE -----

Director
U.S. Army Ballistic Research Laboratory
ATTN: SLCBR-DD-T
Aberdeen Proving Ground, MD 21005-5066




NO POSTAGE
NECESSARY
IF MAILED
IN THE
UNITED STATES

OFFICIAL BUSINESS
PENALTY FOR PRIVATE USE, \$300

BUSINESS REPLY MAIL
FIRST CLASS PERMIT NO 12062 WASHINGTON, DC
POSTAGE WILL BE PAID BY DEPARTMENT OF THE ARMY

Director
U.S. Army Ballistic Research Laboratory
ATTN: SLCBR-DD-T
Aberdeen Proving Ground, MD 21005-9989



----- FOLD HERE -----