

AD-A188 222

NOISE IN LEAD BETA ALUMINA(U) UTAH UNIV SALT LAKE CITY
DEPT OF PHYSICS J J BROPHY ET AL MAY 87 TR-11
N88014-82-K-0603


1/1

UNCLASSIFIED

F/G 28/5

NL





MICROCOPY RESOLUTION TEST CHART
NATIONAL BUREAU OF STANDARDS-1963-A

AD-A180 222

REPORT DOCUMENTATION PAGE

12

UNCLASSIFIED			1b RESTRICTIVE MARKINGS			
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release and sale. Distribution unlimited.			
2b DECLASSIFICATION/DOWNGRADING SCHEDULE						
4 PERFORMING ORGANIZATION REPORT NUMBER(S) ONR TECHNICAL REPORT #11			5. MONITORING ORGANIZATION REPORT NUMBER(S)			
6a NAME OF PERFORMING ORGANIZATION PHYSICS DEPARTMENT		6b OFFICE SYMBOL (if applicable)	7a NAME OF MONITORING ORGANIZATION OFFICE OF NAVAL RES. RESIDENT REPRESENTATIVE			
6c ADDRESS (City, State, and ZIP Code) UNIVERSITY OF UTAH SALT LAKE CITY, UTAH 84112			7b. ADDRESS (City, State, and ZIP Code) UNIVERSITY OF NEW MEXICO Bandelier Hall West Albuquerque, NM 07131			
8a NAME OF FUNDING / SPONSORING ORGANIZATION OFFICE OF NAVAL RES.		8b OFFICE SYMBOL (if applicable) ONR	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-82-K-0603			
8c. ADDRESS (City, State, and ZIP Code) Leader, Chemistry Div., Assoc. Dir. of Mathematics & Physical Sciences 800 N. Quincy St., Arlington VA 22217			10. SOURCE OF FUNDING NUMBERS			
			PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.	WORK UNIT ACCESSION NO.
11 TITLE (Include Security Classification) Noise in Lead Beta" Alumina						
12 PERSONAL AUTHOR(S) James J. Brophy and J. Jeff Carroll						
13a TYPE OF REPORT Technical		13b TIME COVERED FROM 2/1/87 TO 5/1/87		14. DATE OF REPORT (Year, Month, Day) May 1987		15 PAGE COUNT 4 (four)
16 SUPPLEMENTARY NOTATION						
17 COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)			
FIELD	GROUP	SUB-GROUP				
19 ABSTRACT (Continue on reverse if necessary and identify by block number) Conductivity fluctuations ascribed to diffusion noise of the mobile ions have been observed in single crystal and polycrystalline ceramic Pb Beta"alumina. The observed noise levels are much greater and the temperature dependence stronger than predicted by the standard expression for diffusion noise. The calculated effective ion density, 10^{20} ions/cm ³ , is two orders of magnitude larger than that of Na Beta"alumina and Ag Beta"alumina. This can be attributed to smaller correlation effects between the mobile ions because of the lesser actual mobile ion density in Pb Beta"alumina. ten to the tenth power						
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input checked="" type="checkbox"/> SAME AS RPT <input type="checkbox"/> DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED			
22a NAME OF RESPONSIBLE INDIVIDUAL			22b TELEPHONE (Include Area Code)		22c OFFICE SYMBOL	

DTIC ELECTE
MAY 13 1987

(12)

OFFICE OF NAVAL RESEARCH
Contract No. N00014-82-K-0603
TECHNICAL REPORT NO. 11

NOISE IN LEAD β ALUMINA

by

James J. Brophy and J. Jeff Carroll

Prepared for Presentation
at the

9th International Conference on Noise in Physical Systems
Universite de Montreal
Montreal (Quebec) Canada
May 25-29, 1987

Department of Physics
University of Utah
Salt Lake City, Utah 84112

May 1987

Reproduction in whole or in part is permitted for
any purpose of the United States Government

This document has been approved for public release
and sale; its distribution is unlimited



Accession	
By	
Distribution/	
Availability Codes	
Class	Special
A1	

NOISE IN LEAD β ALUMINA

by

James J. Brophy and J. Jeff Carroll
Physics Department
University of Utah

Salt Lake City, Utah 84112

I. INTRODUCTION

Conductivity fluctuations ascribed to diffusion noise of the mobile ions have been reported in both sodium¹ and silver² β alumina. The observed noise levels are much greater and the temperature dependence stronger than predicted by the standard expression for diffusion noise.³ It is supposed that the discrepancies arise from correlation effects between the mobile ions. This work reports on experimental measurements of conductivity fluctuations in single crystal and ceramic Pb β alumina in which the mobile ion density is one-half of that in sodium and silver conductors because the mobile ions are doubly charged. Correlation effects might be expected to be different in this case because of the smaller ion density.

II. EXPERIMENTAL TECHNIQUE

Single crystals⁴ and ceramic samples⁵ of Na β alumina⁵, $5 \times 5 \times 0.5$ mm³, are converted⁶ to Pb β alumina by immersion in molten PbCl₂ at 550°C for 24 hours under a partial pressure of oxygen. The converted crystals are clear and the measured weight change indicates essentially complete exchange of one lead ion for two sodium ions. As in previous studies,^{1,2} the corners of the square samples are sealed into plastic test tubes containing saturated aqueous Pb(NO₃)₂ to provide longitudinal current contacts and transverse noise contacts. Noise levels at the transverse contacts are measured with a PAR 113 preamplifier and a digital FFT analyzer.

III. EXPERIMENTAL RESULTS

Aqueous lead nitrate yields very low noise contacts after aging for several hours. Typical noise spectra are shown in Figure 1. At zero current, Nyquist noise is observed above amplifier noise for frequencies greater than about 30 Hz. Room temperature conductivity determined from the sample resistance calculated using the observed Nyquist noise level is $8.3 \times 10^{-3} \text{ (ohm-cm)}^{-1}$, in good agreement with literature values.⁶ Current noise spectra vary as $f^{-3/2}$, characteristic of diffusion noise,³ and increase with the square of the current. As shown in Figure 1, both transverse and longitudinal noise levels are




Figure 1. Transverse and Longitudinal Noise Spectra of a Pb β Alumina Single Crystal at Room Temperature

the same, indicating the absence of contact current noise and confirming that the observed noise is due to bulk conductivity fluctuations. This has previously been observed in the case of Ag β alumina but not for Na β alumina.

Essentially identical results are seen for polycrystalline ceramic specimens. The noise levels are similar, indicating that the polycrystalline grain structure does not markedly influence the observed noise. This agrees with results previously reported for both sodium¹ and silver² β -alumina. All current noise spectra vary as $f^{-3/2}$, characteristic of diffusion noise.

IV. DIFFUSION NOISE

The voltage noise spectral density, $S(V,f,T)$, arising from diffusion can be written³

$$\frac{S(V,f,T)}{V^2} = \frac{4}{N} \left(\frac{D}{2L^2} \right)^{1/2} \omega^{-3/2} \quad (1)$$

where N is the number of diffusing entities, D is the diffusion constant, L is the sample length, and V is the average voltage across the sample. This expression is valid above a characteristic frequency given by $\omega_0 = 2D/L^2$. Below ω_0 the spectrum flattens, becoming a constant in the case of three-dimensional diffusion.

The observed noise signals are thermally activated, Figure 2. The activation energy in the case of Nyquist noise ($0\mu A, 5kHz$) agrees with conductivity values⁶ for both single crystal and ceramic samples. The temperature dependence for diffusion noise ($I > 0, 10Hz$) is greater than can be accounted for by Equation (1). This is consistent with previous results for sodium and silver β -alumina.

As in the case of sodium and silver β -alumina, the noise level predicted by Equation (1) is many orders of magnitude less than that observed in the Pb β -alumina samples. This is attributed to correlation effects between the diffusing ions which may lead to an effectively smaller ion concentration for diffusion noise. Equation (1) can be used to calculate an effective ion density as a means of comparing experimental results between the different ion species.

The calculated effective ion density for the lead conductors is 10^{10} ions/cm³, larger than that of the other two, which may result from the smaller actual ion density in these specimens because the lead ions are doubly charged. The known mobile ion density in

β'' alumina is approximately 10^{21} ions/cm³, so that the larger value in the case of lead may suggest smaller correlation effects.




Figure 2. Temperature Dependence of Nyquist Noise (5kHz) and Diffusion Noise (10Hz) of Single Crystal and Ceramic Pb β'' Alumina.

The authors are deeply grateful to J. A. Catalano of Airtron, Inc., for supplying the single crystals. This research is supported in part by the Office of Naval Research.

References

- 1) Brophy, J. J. and Smith, S. W., J. Appl. Phys., 58, 354 (1985).
- 2) Brophy, J. J., J. Appl. Phys., 61, 500 (1987).
- 3) VanVliet, K. M. and Fassett, J. R., "Fluctuation Phenomena in Solids," R. E. Burgess (ed), Academic Press, Inc., New York, (1965) p. 268.
- 4) Obtained from Airtron Inc., Morris Plains, N.J., Run No. β'' -26.
- 5) Obtained from Ceramatec Inc., Salt Lake City, Utah.
- 6) SeEVERS, R., DeNuzzio, J. and Farrington, G. C., J. Solid State Chem., 50, 256 (1983).

END

6-87

DTIC