

ND-A182 927


ANALYSIS OF THE SPECTRA OF TRIPLY IONIZED IRON IN
RARE-EARTH ALUMINUM GARNETS(U) HARRY DIAMOND LABS
ADELPHI MD C A MORRISON ET AL. JUL 87 HDL-TR-2113


1/1

UNCLASSIFIED

F/G 7/2

NL





12

DTIC FILE COPY

HDL-TR-2113

July 1987

**Analysis of the Spectra of Triply Ionized Iron
in Rare-Earth Aluminum Garnets**

by Clyde A. Morrison
John D. Bruno
Gregory A. Turner

DTIC
ELECTE
JUL 3 1 1987
S D
C E

AD-A182 927



**U.S. Army Laboratory Command
Harry Diamond Laboratories
Adelphi, MD 20783-1197**

Approved for public release; distribution unlimited.

37 7 29 028

A152 927

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY			3. DISTRIBUTION / AVAILABILITY OF REPORT		
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE			Approved for public release; distribution unlimited.		
4. PERFORMING ORGANIZATION REPORT NUMBER(S) HDL-TR-2113			5. MONITORING ORGANIZATION REPORT NUMBER(S)		
6a. NAME OF PERFORMING ORGANIZATION Harry Diamond Laboratories		6b. OFFICE SYMBOL (If applicable) SLCHD-RT-RA	7a. NAME OF MONITORING ORGANIZATION		
6c. ADDRESS (City, State, and ZIP Code) 2800 Powder Mill Road Adelphi, MD 20783-1197			7b. ADDRESS (City, State, and ZIP Code)		
8a. NAME OF FUNDING / SPONSORING ORGANIZATION Center for Night Vision and Electro-Optics		8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8c. ADDRESS (City, State, and ZIP Code) Ft Belvoir, VA 22060			10. SOURCE OF FUNDING NUMBERS		
		PROGRAM ELEMENT NO. 61102A	PROJECT NO.	TASK NO.	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Analysis of the Spectra of Triply Ionized Iron in Rare-Earth Aluminum Garnets					
12. PERSONAL AUTHOR(S) Clyde A. Morrison, John D. Bruno, and Gregory A. Turner					
13a. TYPE OF REPORT Interim		13b. TIME COVERED FROM Jun 86 TO Sep 86		14. DATE OF REPORT (Year, Month, Day) July 1987	
15. PAGE COUNT 56					
16. SUPPLEMENTARY NOTATION AMS code: 611102.31B0011; HDL project: 590751; PRON: CJ727269-01-CJ-CT					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	Rare-earth aluminum garnets, optical spectra of Fe ³⁺ , transition metal ion spectra, crystal-field splittings in garnets, crystal field theory		
20	02				
20	05				
19. ABSTRACT (Continue on reverse if necessary and identify by block number)					
Experimental data on the spectra of Fe³⁺ in seven rare-earth aluminum garnets are analyzed. The first analysis consists of the conventional cubic approximations to obtain the Slater parameters F⁽²⁾, F⁽⁴⁾ and the crystal field parameters, B₄₀. The concept of rotational invariance of the crystal fields, along with the point charge lattice sums, was used to predict the crystal field parameters for the Al₂ site with C_{3i} symmetry. The best fit Slater parameters, along with the spin-orbit parameter, were used to predict the optical spectra of Fe³⁺ in R₃Al₅O₁₂ for R = Gd, Tb, Dy Ho, Er, Tm, Yb, and Lu.					
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED		
22a. NAME OF RESPONSIBLE INDIVIDUAL Clyde A. Morrison			22b. TELEPHONE (Include Area Code) (202) 394-2042		22c. OFFICE SYMBOL SLCHD-RT-RA

DTIC
JUL 31 1987

CONTENTS

	Page
1. INTRODUCTION	5
2. THEORY	5
3. WAVE FUNCTIONS AND FITTING THE EXPERIMENTAL DATA	7
3.1 Cubic Approximation	8
3.2 Theoretical Crystal Field Parameters	16
3.3 Final Parameters and Predicted Splittings, Including Spin-Orbit Interaction	17
4. DISCUSSION, CONCLUSION, AND PLANS	50
ACKNOWLEDGEMENT	50
LITERATURE CITED	50
DISTRIBUTION	53

TABLES

1. Slater Parameters $F^{(k)}$ and Crystal Field Parameters (Cubic) B_{40} , B_{43} for Fe^{3+} Ion in $R_3Al_5O_{12}$	8
2. Energy Levels of Fe^{3+} in $Gd_3Al_5O_{12}$	9
3. Energy Levels of Fe^{3+} in $Tb_3Al_5O_{12}$	10
4. Energy Levels of Fe^{3+} in $Dy_3Al_5O_{12}$	11
5. Energy Levels of Fe^{3+} in $Ho_3Al_5O_{12}$	12
6. Energy Levels of Fe^{3+} in $Er_3Al_5O_{12}$	13
7. Energy Levels of Fe^{3+} in $Tm_3Al_5O_{12}$	14
8. Energy Levels of Fe^{3+} in $Yb_3Al_5O_{12}$	15
9. Crystallographic Data for $R_3Al_5O_{12}$ Cubic $Ia\bar{3}d$, 230, $Z = 8$	18
10. Best Least-Squares Fit to Lattice Sums A_{nm} for Al_1 Ion in 16a [C_{31}] Site in $R_3Al_5O_{12}$	18
11. Least-Squares Fit to Lattice Sums A_{nm} for Al_2 Ion In 24d [S_4] Site in $R_3Al_5O_{12}$	19

TABLES (cont'd)

	Page
12. Crystal Field Parameters B_{nm} , Dq , v , and v'	20
13. Linear Fit Values of $S^{(0)}$, $S^{(2)}$, $S^{(4)}$ for Al_1 and Al_2 sites	20
14. Final Linear Fit Free-Ion and Crystal Field Parameters for Fe^{3+} in $R_3Al_5O_{12}$	21
15. Energy Levels of Fe^{3+} in $Gd_3Al_5O_{12}$	22
16. Energy Levels of Fe^{3+} in $Tb_3Al_5O_{12}$	25
17. Energy Levels of Fe^{3+} in $Dy_3Al_5O_{12}$	29
18. Energy Levels of Fe^{3+} in $Ho_3Al_5O_{12}$	32
19. Energy Levels of Fe^{3+} in $Er_3Al_5O_{12}$	36
20. Energy Levels of Fe^{3+} in $Tm_3Al_5O_{12}$	39
21. Energy Levels of Fe^{3+} in $Yb_3Al_5O_{12}$	43
22. Energy Levels of Fe^{3+} in $Lu_3Al_5O_{12}$	46

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



INTRODUCTION

Recent successes in transferring energy from excited chromium ions to neodymium ions in gadolinium scandium gallium garnets have increased interest in the spectra of transition-metal ions in potential laser host materials [1-4]. In particular, the garnet materials, which can be doped with both rare-earth and transition-metal ions, are possible candidates for such a laser.

In the work reported here, we analyze the spectra of Fe^{3+} in the rare-earth aluminum garnets, $\text{R}_3\text{Al}_5\text{O}_{12}$ (RAG), for $\text{R} = \text{Gd, Tb, Dy, Ho, Er, Tm, and Yb}$ [5]. The Fe^{3+} ion is assumed to occupy the 6(a) site with S_6 symmetry [6]. The reported analysis of the experimental data [5] assumes cubic symmetry and gives the usual parameters (B, C, and Dq) for the free ion and the crystal field. Using the known crystallographic data [7] on RAG, we then compute the crystal field components, A_{nm} . The concept of rotational invariance is used [8] to obtain an estimate of the radial integrals needed to convert the crystal field components to the crystal field parameters, B_{nm} . The resulting crystal field parameters are used to calculate the energy levels of Fe^{3+} in the entire RAG series, including lutetium. This latter calculation is performed with the spin-orbit constant, ζ , equal to 370 cm^{-1} , which we assume is approximately 80 percent of the free ion value [9].

2. THEORY

The interactions of the free ion considered here for the d^N electronic configuration are the coulomb interaction, the spin-orbit interaction, and the configuration interaction. Although these interactions are tabulated in numerous places, we include a brief discussion here for completeness.

The coulomb interaction for the configuration d^N is given by

$$H_1 = \sum_{\substack{k=0 \\ k \text{ even}}}^4 F^{(k)} \sum_{\substack{i>j \\ m}}^N C_{km}^*(i) C_{km}(j), \quad (1)$$

where the $F^{(k)}$ are the Slater parameters. The $C_{km}(i)$ in equation (1) are related to the ordinary spherical harmonics by

$$C_{km}(i) = [4\pi/2k + 1]^{1/2} Y_{km}(\theta_i, \phi_i). \quad (2)$$

The Slater integrals are related to the Racah parameters B and C [10] by

$$\begin{aligned} F^{(2)} &= 7(7B + C) \\ F^{(4)} &= 63C/5. \end{aligned} \quad (3)$$

*References appear at the end of the report (p 50).

The Slater parameter $F^{(0)}$ and the Racah parameter A are ignored in our analysis. The spin-orbit interaction for the d^N configuration is taken as

$$H_2 = \zeta \sum_{i=1}^N \vec{s}_i \cdot \vec{l}_i, \quad (4)$$

where $\vec{s}_i$ and $\vec{l}_i$ are the spin and orbital angular momentum operators. Values of $F^{(k)}$ and ζ calculated with the use of nonrelativistic Hartree-Fock wave functions for a large number of ions with the nd^N configurations are given by Fraga et al [11]. For Fe^{3+} their values (in cm^{-1}) are

$$F_{HF}^{(2)} = 99,367, \quad F_{HF}^{(4)} = 62,291, \quad \text{and} \quad \zeta_{HF} = 499.53.$$

For the free ion, Uylings et al [9] give (in cm^{-1}) $F^{(2)} = 83,302$, $F^{(4)} = 53,070$, and $\zeta = 463$ (other parameters used by Uylings et al are (in cm^{-1}) $\alpha = 35.40$, $\beta = -486.7$, and $T = -6.2$).

For the interconfiguration interaction we take the form suggested by the work of Rajnak and Wybourne [12] as

$$H_3 = \alpha L(L + 1) + \gamma G(R_5), \quad (5)$$

which is a form previously suggested by Trees [13]. However, in the form suggested by Trees, the second term in equation (5) involves the seniority operator Q with the parameter β instead of the Casimir operator $G(R_5)$. Unfortunately, the inclusion of either form (βQ or $\gamma G(R_5)$) in a fitting of the experimental data generally gives erratic values for β or γ . That is, small changes in the experimental data give large changes in the values of γ or β so that this interaction is frequently ignored. On the other hand, the inclusion of the term involving α in equation (5) frequently improves the fit to the experimental data, and the value found by fitting generally is positive and less than 100 cm^{-1} . The crystal field interaction for the d^N electronic configuration in the C_{3i} site in $R_3Al_5O_{12}$ is taken as

$$H_4 = B_{20} \sum_{i=1}^w C_{20}^{(i)} + B_{40} \sum_{i=1}^n C_{40}^{(i)} + B_{43} \sum_{i=1}^n [C_{43}^{(i)} - C_{4-3}^{(i)}], \quad (6)$$

where the B_{nm} are the crystal field parameters and the $C_{nm}^{(i)}$ are given in equation (2). In equation (6) the crystal field parameter B_{43} has been chosen real and can be further chosen positive or negative with no loss in generality. In the cubic approximation we have

$$\begin{aligned} B_{20} &= 0, \\ B_{40} &= -14Dq, \\ \text{and} \quad B_{43} &= \sqrt{10/7} B_{40}, \end{aligned} \quad (7)$$

where Dq is the more familiar crystal field parameter used in the analysis of the spectra of ions with the d^N electronic configuration. The relation of the crystal field parameters of equation (6) to the parameters given by Macfarlane [14] are

$$\begin{aligned} B_{20} &= (7v - 2w)/3, \\ B_{40} &= -7Dq/5 + 2w/3, \end{aligned} \quad (8)$$

and

$$B_{43} = -\sqrt{7/10} (2Dq + w/3),$$

where $w = 2v + 3\sqrt{2} v'$, and it should be noted that this relation gives $B_{43} < 0$ since the value of Dq is usually chosen positive. In obtaining the result given in equation (8), we have used the relations

$$\begin{aligned} \sum_{i=1}^N C_{2m}(i) &= \sqrt{2/7} U_m^{(2)} \\ \sum_{i=1}^N C_{4m}(i) &= \sqrt{2/7} U_m^{(4)}, \end{aligned} \quad (9)$$

where the $U_m^{(n)}$ are the unit tensors introduced by Racah [10] and are identical to those used by Nielson and Koster [15]. The relation of other conventions used for the crystal field parameters for the electronic configuration d^N are given by Konig and Kremer [16]. The complete Hamiltonian we consider is

$$H = \sum_{i=1}^4 H_i. \quad (10)$$

3. WAVE FUNCTIONS AND FITTING THE EXPERIMENTAL DATA

Because of the large variation in the relative strength of the various interactions occurring in H_1 through H_5 , we decided to use total angular momentum wave functions, J , as a basis for calculating the energy levels of Fe^{3+} in RAG. That is, the wave functions are $|J M \alpha LS\rangle$, with $\underline{J} = \underline{L} + \underline{S}$, and α represents the additional quantum numbers needed to uniquely specify the states. In C_3 or C_{3i} symmetry, the states given by $M = 1/2 + 3q$ ($q = 0, \pm 1, \dots$) and $M = -1/2 + 3q$ ($q = 0, \pm 1, \dots$) are degenerate and correspond to the Γ_4 and Γ_5 irreducible representations of the C_{3i} group, respectively. The states with $M = 3/2 + 3q$ ($q = 0, \pm 1$), which correspond to the Γ_6 irreducible representation, are chosen as

$$\begin{aligned} \psi_6^+ &= (|J M \alpha LS\rangle + (-1)^{J-M} |J - M \alpha LS\rangle) / \sqrt{2} \\ \psi_6^- &= (|J M \alpha LS\rangle - (-1)^{J-M} |J - M \alpha LS\rangle) / \sqrt{2}, \end{aligned} \quad (11)$$

and the energy levels obtained by using ψ_6^+ or ψ_6^- are degenerate. The matrix for H in the states $|JM\pm L\rangle$ for $M = 1/2 + 3q$ is 84×84 , and for the ψ_6^+ is 42×42 .

3.1 Cubic Approximation

The experimental data on Fe^{3+} in RAG with $R = \text{Gd, Tb, Dy, Ho, Er, Tm, and Yb}$ have been reported by Arsenev et al [5]. In their analysis, they assumed cubic symmetry and reported the crystal field parameter Dq and the Racah parameters B and C , as well as the experimental and theoretical energy levels. These parameters were converted to $F^{(k)}$ and B_{nm} with the use of equations (3) and (7) and are given in table 1 in the row labeled 1. As can be seen, the rms deviation of the theoretical from the experimental levels is quite large, and it was assumed that there was a misprint or that one or more levels were mislabeled. To try to resolve this possible discrepancy, we used the reported theoretical energy levels as data and varied the parameters to obtain a best fit, with the results given in table 1, row 2. Despite a number of different reasonable selections of level changes and other possible changes, we were unable to obtain what we considered a satisfactory result. It was then decided to best fit the experimental data starting with the parameters given in row 1 of table 1. The results are given in row 3 of table 1, and, as is shown, the resulting fits to Gd through Yb are very good. With the use of the parameters given in row 3 of table 1, tables 2 through 8 give the energy levels of Fe^{3+} for all the compounds. In these tables the familiar Mulligen notation is used for the irreducible representation. It was decided to proceed with the analysis and prediction using the results of row 3, table 1.

TABLE 1. SLATER PARAMETERS $F^{(k)}$ AND CRYSTAL FIELD PARAMETERS (CUBIC) B_{40} , B_{43} FOR Fe^{3+} ION IN $R_3\text{Al}_5\text{O}_{12}$

R	$F^{(2)}$ (cm^{-1})	$F^{(4)}$ (cm^{-1})	B_{40} (cm^{-1})	B_{43} (cm^{-1})	rms (cm^{-1})	Row No.
Gd	53305	41706	-19110	22840.82	725.0	1
Gd	51732	37897	-19198	22945.94	464.0	2
Gd	52406	42491	-21441	25627.23	78.7	3
Tb	53501	41618	-19320	23091.82	686.0	1
Tb	52538	37825	-19312	23082.19	409.0	2
Tb	52553	42403	-21521	25722.10	84.1	3
Dy	53872	41403	-20160	24095.81	600.0	1
Dy	53355	38773	-20134	24064.53	278.0	2
Dy	52934	42164	-21668	25898.31	86.7	3
Ho	53963	41391	-20370	24346.81	436.0	1
Ho	53464	38954	-20332	24301.39	272.0	2
Ho	53126	42039	-21757	26004.29	81.1	3
Er	54362	41139	-21000	25099.80	463.0	1
Er	53535	42184	-20903	24983.66	318.0	2
Er	53522	41738	-21882	26153.99	89.9	3
Tm	54488	41101	-21574	25785.86	476.0	1
Tm	53477	42968	-21447	25633.62	314.0	2
Tm	53672	41654	-21963	26250.80	91.5	3
Yb	54663	41063	-21840	26103.79	146.0	1
Yb	54929	40773	-21829	26090.30	116.0	2
Yb	53876	41567	-22065	26372.72	97.3	3

1--Parameters reported by Arsenev et al [5].

2--Best-fit parameters obtained by fitting the theoretical levels of Arsenev et al [5].

3--Best-fit parameters obtained by fitting the experimental data of Arsenev et al [5].

TABLE 2. ENERGY LEVELS OF Fe^{3+} IN $\text{Gd}_2\text{Al}_5\text{O}_{12}$
 [Theoretical levels were calculated with $F^{(2)} = 52406$,
 $F^{(4)} = 42491$, and $B_{40} = -21441$ ($Dq = 1531.5$, $B = 587.75$,
 and $C = 3372.3$). All quantities are in cm^{-1} .]

No.	IR ^a	[†] E _{obs}	E _{th}	Free ion state composition			
1	${}^6A_1$	0	-3	1.00	6S		
2	${}^2T_2$	0	9511	0.31	2I + 0.27	2H + 0.18	2F1
3	${}^4T_1$	10295	10225	0.59	4G + 0.36	4P + 0.04	4F
4	${}^4T_2$	14155	14188	0.43	4G + 0.31	4F + 0.26	4D
5	${}^2A_2$	0	21550	0.54	2I + 0.41	2F1 + 0.04	2F2
6	${}^2T_1$	0	21710	0.59	2I + 0.25	2H + 0.13	2F1
7	${}^4(A_1, E)$	22700	22736	1.00	4G		
8	${}^2T_2$	0	23089	0.47	2I + 0.24	2F1 + 0.12	2H
9	${}^2E$	0	24669	0.34	2I + 0.30	2H + 0.14	2D3
10	${}^4T_2$	24645	24712	0.52	4D + 0.46	4G + 0.02	4F
11	${}^4E$	27005	25850	1.00	4D		
12	${}^2T_1$	0	28326	0.33	2G2 + 0.21	2F2 + 0.19	2F1
13	${}^2T_2$	0	30169	0.27	2F2 + 0.27	2G2 + 0.15	2D2
14	${}^2A_1$	0	30975	0.41	2I + 0.29	2G2 + 0.20	2G1
15	${}^2E$	0	33734	0.45	2I + 0.24	2D3 + 0.14	2D1
16	${}^4T_1$	0	34006	0.56	4F + 0.36	4P + 0.08	4G
17	${}^2A_1$	0	34646	0.58	2I + 0.29	2G2 + 0.07	2G1
18	${}^2T_2$	0	35424	0.54	2I + 0.34	2D3 + 0.07	2D1
19	${}^4A_2$	0	36533	1.00	4F		
20	${}^2E$	0	38045	0.72	2G2 + 0.12	2I + 0.06	2D2
21	${}^2T_2$	0	39565	0.42	2F2 + 0.29	2G2 + 0.15	2I
22	${}^2A_2$	0	40447	0.75	2F2 + 0.20	2I + 0.05	2F1
23	${}^2T_1$	0	40524	0.49	2F2 + 0.39	2G2 + 0.08	2I
24	${}^2T_1$	0	40856	0.69	2H + 0.30	2F1 + 0.00	2F2
25	${}^4T_1$	0	42754	0.40	4F + 0.33	4G + 0.27	4P
26	${}^2A_1$	0	43462	0.66	2S + 0.30	2G2 + 0.03	2G1
27	${}^2E$	0	44887	0.39	2D3 + 0.33	2H + 0.25	2D2
28	${}^2T_1$	0	46855	0.39	2H + 0.19	2F1 + 0.17	2G1
29	${}^4T_2$	0	47219	0.67	4F + 0.22	4D + 0.11	4G
30	${}^2T_2$	0	48465	0.30	2F1 + 0.18	2H + 0.17	2D2
31	${}^2T_1$	0	53012	0.40	2H + 0.29	2I + 0.18	2F1
32	${}^2E$	0	53292	0.76	2G1 + 0.10	2H + 0.07	2D1
33	${}^2A_2$	0	53296	0.54	2F1 + 0.26	2I + 0.21	2F2
34	${}^2T_2$	0	57362	0.43	2D2 + 0.16	2I + 0.13	2G1
35	${}^2E$	0	58789	0.51	2D2 + 0.15	2H + 0.13	2G2
36	${}^2T_1$	0	59336	0.72	2G1 + 0.13	2P + 0.07	2F2
37	${}^2T_2$	0	61059	0.28	2D3 + 0.20	2H + 0.16	2F1
38	${}^2T_2$	0	63298	0.42	2G1 + 0.16	2D1 + 0.14	2G2
39	${}^2A_1$	0	66100	0.69	2G1 + 0.18	2S + 0.12	2G2
40	${}^2T_1$	0	69400	0.80	2P + 0.07	2F2 + 0.07	2G2
41	${}^2E$	0	81083	0.68	2D1 + 0.13	2G1 + 0.11	2D3
42	${}^2T_2$	0	81851	0.62	2D1 + 0.10	2H + 0.07	2G1

^aIrreducible representations of the cubic group.
[†]Arsenev et al [5].

TABLE 3. ENERGY LEVELS OF Fe^{3+} IN $\text{Tb}_2\text{Al}_5\text{O}_{12}$
 [Theoretical levels were calculated with $F^{(2)} = 52553$,
 $F^{(4)} = 42403$, and $B_{40} = -21521$ ($Dq = 1537.2$, $B = 591.75$,
 and $C = 3365.3$). All quantities are in cm^{-1} .]

No.	IR*	$\dagger E_{\text{obs}}$	E_{th}	Free ion state composition			
1	$6A_1$	0	-4	1.00	6S		
2	$2T_2$	0	9385	0.31	2I + 0.27	4P + 0.04	4F
3	$4T_1$	10238	10167	0.59	4G + 0.37	4P + 0.04	4F
4	$4T_2$	14085	14159	0.43	4G + 0.31	4F + 0.26	4D
5	$2A_2$	0	21478	0.54	2I + 0.41	2F1 + 0.04	2F2
6	$2T_1$	0	21641	0.59	2I + 0.25	2H + 0.13	2F1
7	$4(A_1, E)$	22709	22740	1.00	4G		
8	$2T_2$	0	23027	0.47	2I + 0.24	2F1 + 0.12	2H
9	$2E$	0	24612	0.34	2I + 0.30	2H + 0.14	2D3
10	$4T_2$	24651	24730	0.52	4D + 0.46	4G + 0.02	4F
11	$4E$	27050	26883	1.00	4D		
12	$2T_1$	0	28295	0.33	2G2 + 0.21	2F2 + 0.19	2F1
13	$2T_2$	0	30159	0.27	2F2 + 0.27	2G2 + 0.15	2D2
14	$2A_1$	0	30966	0.41	2I + 0.29	2G2 + 0.20	2G1
15	$2E$	0	33703	0.45	2I + 0.24	2D3 + 0.14	2D1
16	$4T_1$	0	34027	0.56	4F + 0.36	4P + 0.08	4G
17	$2A_1$	0	34647	0.58	2I + 0.29	2G2 + 0.07	2G1
18	$2T_2$	0	35413	0.54	2I + 0.34	2D3 + 0.07	2D1
19	$4A_2$	0	36572	1.00	4F		
20	$2E$	0	38060	0.72	2G2 + 0.12	2I + 0.06	2D2
21	$2T_2$	0	39589	0.42	2F2 + 0.29	2G2 + 0.15	2I
22	$2A_2$	0	40479	0.75	2F2 + 0.20	2I + 0.05	2F1
23	$2T_1$	0	40558	0.49	2F2 + 0.39	2G2 + 0.08	2I
24	$2T_1$	0	40835	0.69	2H + 0.30	2F1 + 0.00	2F2
25	$4T_1$	0	42815	0.40	4F + 0.33	4G + 0.27	4P
26	$2A_1$	0	43518	0.66	2S + 0.30	2G2 + 0.03	2G1
27	$2E$	0	44922	0.39	2D3 + 0.33	2H + 0.25	2D2
28	$2T_1$	0	46880	0.38	2H + 0.19	2F1 + 0.17	2G1
29	$4T_2$	0	47306	0.67	4F + 0.22	4D + 0.11	4G
30	$2T_2$	0	48493	0.30	2F1 + 0.18	2H + 0.17	2D2
31	$2T_1$	0	53054	0.40	2H + 0.29	2I + 0.18	2F1
32	$2A_2$	0	53342	0.54	2F1 + 0.26	2I + 0.21	2F2
33	$2E$	0	53357	0.76	2G1 + 0.10	2H + 0.07	2D1
34	$2T_2$	0	57435	0.43	2D2 + 0.16	2I + 0.13	2G1
35	$2E$	0	58863	0.51	2D2 + 0.15	2H + 0.13	2G2
36	$2T_1$	0	59434	0.72	2G1 + 0.13	2P + 0.07	2F2
37	$2T_2$	0	61148	0.28	2D3 + 0.20	2H + 0.16	2F1
38	$2T_2$	0	63407	0.42	2G1 + 0.16	2D1 + 0.14	2G2
39	$2A_1$	0	66226	0.69	2G1 + 0.18	2S + 0.12	2G2
40	$2T_1$	0	69557	0.80	2P + 0.07	2F2 + 0.07	2G2
41	$2E$	0	81224	0.68	2D1 + 0.13	2G1 + 0.11	2G1
42	$2T_2$	0	81983	0.62	2D1 + 0.10	2H + 0.08	2G1

* Irreducible representations of the cubic group.
 $\dagger$ Arsenov et al [5].

TABLE 4. ENERGY LEVELS OF Fe^{3+} IN $\text{Dy}_{15}\text{O}_{12}$
 [Theoretical levels were calculated with $F(2) = 52934$,
 $F(4) = 42264$, and $B_{40} = -21668$ ($Dq = 1547.50$, $B = 602.24$, and $C = 3346.35$). All quantities are in cm^{-1} .]

No.	IR ^a	E_{obs}	E_{th}	Free ion state composition			
1	$6A_1$	0	-4	1.00	6S		
2	$2T_2$	0	9137	0.31	2I + 0.37	4P + 0.04	4F
3	$4T_1$	10120	10054	0.59	4G + 0.37	4P + 0.04	4F
4	$4T_2$	14051	14121	0.43	4G + 0.31	4F + 0.26	4D
5	$2A_2$	0	21329	0.54	2I + 0.41	2F1 + 0.04	2F2
6	$2T_1$	0	21498	0.58	2I + 0.25	2H + 0.13	2F1
7	$4(A_1, E)$	22730	22750	1.00	4G		
8	$2T_2$	0	22900	0.47	2I + 0.24	2F1 + 0.12	2H
9	$2E$	0	24496	0.34	2I + 0.30	2H + 0.14	2D3
10	$4T_2$	24683	24777	0.52	4D + 0.46	4G + 0.02	4F
11	$4E$	27140	26966	1.00	4D		
12	$2T_1$	0	28247	0.33	2G2 + 0.20	2F2 + 0.19	2F1
13	$2T_2$	0	30167	0.27	2F2 + 0.27	2G2 + 0.15	2D2
14	$2A_1$	0	30965	0.42	2I + 0.29	2G2 + 0.20	2G1
15	$2E$	0	33628	0.45	2I + 0.24	2D3 + 0.14	2D1
16	$4T_1$	0	34072	0.56	4F + 0.36	4P + 0.08	4G
17	$2A_1$	0	34654	0.57	2I + 0.30	2G2 + 0.07	2G1
18	$2T_2$	0	35381	0.54	2I + 0.34	2D3 + 0.07	2D1
19	$4A_2$	0	36670	1.00	4F		
20	$2E$	0	38099	0.72	2G2 + 0.12	2I + 0.06	2D2
21	$2T_2$	0	39648	0.42	2F2 + 0.29	2G2 + 0.15	2I
22	$2A_2$	0	40558	0.74	2F2 + 0.20	2I + 0.05	2F1
23	$2T_1$	0	40642	0.48	2F2 + 0.39	2G2 + 0.08	2I
24	$2T_1$	0	40773	0.69	2H + 0.30	2F1 + 0.01	2F2
25	$4T_1$	0	42929	0.40	4F + 0.33	4G + 0.27	4P
26	$2A_1$	0	43664	0.66	2S + 0.30	2G2 + 0.03	2G1
27	$2E$	0	45009	0.39	2D3 + 0.33	2H + 0.25	2D2
28	$2T_1$	0	46933	0.38	2H + 0.18	2F1 + 0.17	2G1
29	$4T_2$	0	47486	0.67	4F + 0.22	4D + 0.11	4G
30	$2T_2$	0	48549	0.30	2F1 + 0.18	2H + 0.17	2D2
31	$2T_1$	0	53114	0.40	2H + 0.30	2I + 0.18	2F1
32	$2A_2$	0	53411	0.53	2F1 + 0.25	2I + 0.21	2F2
33	$2E$	0	53526	0.76	2G1 + 0.10	2H + 0.07	2D1
34	$2T_2$	0	57593	0.44	2D2 + 0.16	2I + 0.13	2G1
35	$2E$	0	59015	0.51	2D2 + 0.15	2H + 0.13	2G2
36	$2T_1$	0	59669	0.72	2G1 + 0.12	2P + 0.07	2F2
37	$2T_2$	0	61321	0.27	2D3 + 0.20	2H + 0.16	2F1
38	$2T_2$	0	63662	0.42	2G1 + 0.16	2D1 + 0.14	2G2
39	$2A_1$	0	66506	0.69	2G1 + 0.18	2S + 0.12	2G2
40	$2T_1$	0	69940	0.80	2P + 0.07	2F2 + 0.07	2G2
41	$2E$	0	81551	0.67	2D1 + 0.13	2G1 + 0.11	2D3
42	$2T_2$	0	82264	0.62	2D1 + 0.10	2H + 0.08	2I

^aIrreducible representations of the cubic group.
^bArsenev et al [5].

TABLE 5. ENERGY LEVELS OF Fe^{3+} IN $\text{Ho}_2\text{Al}_5\text{O}_{12}$
 [Theoretical levels were calculated with $F^{(2)} = 53126$,
 $F^{(4)} = 42039$, and $B_{40} = -21757$ ($Dq = 1554.06$, $B = 607.57$, and $C = 3336.43$). All quantities are in cm^{-1} .]

No.	IR*	E_{obs}	E_{th}	Free ion state composition			
1	$6A_1$	0	-2	1.00	6S		
2	$2T_2$	0	8986	0.31	2I + 0.27	2H + 0.18	2F1
3	$4T_1$	10040	9984	0.59	4G + 0.37	4P + 0.04	4F
4	$4T_2$	14034	14090	0.43	4G + 0.31	4F + 0.26	4D
5	$2A_2$	0	21240	0.54	2I + 0.41	2F1 + 0.04	2F2
6	$2T_1$	0	21412	0.58	2I + 0.25	2H + 0.13	2F1
7	$4(A_1, E)$	22748	22755	1.00	4G		
8	$2T_2$	0	22823	0.47	2I + 0.24	2F1 + 0.12	2H
9	$2E$	0	24424	0.33	2I + 0.31	2H + 0.14	2D3
10	$4T_2$	24700	24801	0.52	4D + 0.46	4G + 0.02	4F
11	$4E$	27170	27008	1.00	4D		
12	$2T_1$	0	28210	0.33	2G2 + 0.20	2F2 + 0.19	2F1
13	$2T_2$	0	30159	0.27	2F2 + 0.27	2G2 + 0.15	2D2
14	$2A_1$	0	30955	0.42	2I + 0.28	2G2 + 0.20	2G1
15	$2E$	0	33585	0.45	2I + 0.24	2D3 + 0.14	2D1
16	$4T_1$	0	34097	0.56	4F + 0.36	4P + 0.08	4G
17	$2A_1$	0	34655	0.56	2I + 0.30	2G2 + 0.07	2G1
18	$2T_2$	0	35363	0.54	2I + 0.34	2D3 + 0.07	2D1
19	$4A_2$	0	36719	1.00	4F		
20	$2E$	0	38117	0.72	2G2 + 0.12	2I + 0.06	2D2
21	$2T_2$	0	39676	0.42	2F2 + 0.29	2G2 + 0.15	2I
22	$2A_2$	0	40598	0.74	2F2 + 0.20	2I + 0.05	2F1
23	$2T_1$	0	40682	0.45	2F2 + 0.39	2G2 + 0.08	2I
24	$2T_1$	0	40743	0.67	2H + 0.28	2F1 + 0.04	2F2
25	$4T_1$	0	42999	0.40	4F + 0.33	4G + 0.27	4P
26	$2A_1$	0	43737	0.66	2S + 0.30	2G2 + 0.03	2G1
27	$2E$	0	45052	0.39	2D3 + 0.33	2H + 0.25	2D2
28	$2T_1$	0	46962	0.38	2H + 0.18	2F1 + 0.17	2G1
29	$4T_2$	0	47591	0.67	4F + 0.22	4D + 0.11	4G
30	$2T_2$	0	48580	0.30	2F1 + 0.18	2H + 0.16	2D2
31	$2T_1$	0	53156	0.40	2H + 0.30	2I + 0.18	2F1
32	$2A_2$	0	53458	0.53	2F1 + 0.25	2I + 0.21	2F2
33	$2E$	0	53609	0.75	2G1 + 0.10	2H + 0.07	2G1
34	$2T_2$	0	57680	0.44	2D2 + 0.16	2I + 0.13	2G1
35	$2E$	0	59102	0.51	2D2 + 0.15	2H + 0.13	2G2
36	$2T_1$	0	59792	0.72	2G1 + 0.12	2P + 0.07	2F2
37	$2T_2$	0	61423	0.27	2D3 + 0.20	2H + 0.16	2F1
38	$2T_2$	0	63798	0.42	2G1 + 0.16	2D1 + 0.14	2G2
39	$2A_1$	0	66661	0.69	2G1 + 0.18	2S + 0.12	2G2
40	$2T_1$	0	70141	0.80	2P + 0.07	2F2 + 0.07	2G2
41	$2E$	0	81726	0.67	2D1 + 0.13	2G1 + 0.11	2D3
42	$2T_2$	0	82423	0.62	2D1 + 0.10	2H + 0.08	2G1

* Irreducible representation of the cubic group.
 † Arsenov et al [5].

TABLE 6. ENERGY LEVELS OF Fe^{3+} IN $\text{Er}_3\text{Al}_5\text{O}_{12}$
 [Theoretical levels were calculated with $F^{(2)} = 53522$,
 $F^{(4)} = 41738$, and $B_{40} = -21882$ ($Dq = 1563.00$, $B = 619.07$, and $C = 3312.54$). All quantities are in cm^{-1} .]

No.	IR*	E_{obs}	E_{th}	Free ion state composition					
1	$6A_1$	0	-2	1.00	6S				
2	$2T_2$	0	8731	0.31	2I	+ 0.27	2H	+ 0.18	2F1
3	$4T_1$	9920	9866	0.59	4G	+ 0.37	4P	+ 0.04	4F
4	$4T_2$	14000	14054	0.43	4G	+ 0.31	4F	+ 0.26	4D
5	$2A_2$	0	21071	0.54	2I	+ 0.41	2F1	+ 0.04	2F2
6	$2T_1$	0	21251	0.58	2I	+ 0.25	2H	+ 0.13	2F1
7	$2T_2$	0	22680	0.47	2I	+ 0.24	2F1	+ 0.12	2H
8	$4(A_1, E)$	22755	22751	1.00	4G				
9	$2E$	0	24290	0.33	2I	+ 0.31	2H	+ 0.14	2D3
10	$4T_2$	24715	24838	0.52	4D	+ 0.46	4G	+ 0.02	4F
11	$4E$	27261	27084	1.00	4D				
12	$2T_1$	0	28151	0.33	2G2	+ 0.20	2F2	+ 0.19	2F1
13	$2T_2$	0	30163	0.27	2G2	+ 0.27	2F2	+ 0.15	2D2
14	$2A_1$	0	30943	0.44	2I	+ 0.28	2G2	+ 0.19	2G1
15	$2E$	0	33482	0.45	2I	+ 0.24	2D3	+ 0.14	2D1
16	$4T_1$	0	34123	0.55	4F	+ 0.37	4P	+ 0.08	4G
17	$2A_1$	0	34645	0.55	2I	+ 0.31	2G2	+ 0.08	2G1
18	$2T_2$	0	35301	0.53	2I	+ 0.34	2D3	+ 0.07	2D1
19	$4A_2$	0	36805	1.00	4F				
20	$2E$	0	38139	0.72	2G2	+ 0.13	2I	+ 0.06	2D2
21	$2T_2$	0	39716	0.42	2F2	+ 0.28	2G2	+ 0.15	2I
22	$2T_1$	0	40640	0.68	2H	+ 0.30	2F1	+ 0.02	2G2
23	$2A_2$	0	40658	0.74	2F2	+ 0.20	2I	+ 0.06	2F1
24	$2T_1$	0	40755	0.49	2F2	+ 0.38	2G2	+ 0.09	2I
25	$4T_1$	0	43085	0.41	4F	+ 0.33	4G	+ 0.26	4P
26	$2A_1$	0	43875	0.66	2S	+ 0.30	2G2	+ 0.04	2G1
27	$2E$	0	45120	0.39	2D3	+ 0.33	2H	+ 0.25	2D2
28	$2T_1$	0	46990	0.38	2H	+ 0.18	2F1	+ 0.17	2G1
29	$4T_2$	0	47749	0.67	4F	+ 0.22	4D	+ 0.11	4G
30	$2T_2$	0	48604	0.30	2F1	+ 0.18	2H	+ 0.16	2D2
31	$2T_1$	0	53174	0.40	2H	+ 0.30	2I	+ 0.18	2F1
32	$2A_2$	0	53485	0.53	2F1	+ 0.25	2I	+ 0.22	2F2
33	$2E$	0	53767	0.75	2G1	+ 0.10	2H	+ 0.07	2D1
34	$2T_2$	0	57810	0.44	2D2	+ 0.16	2I	+ 0.13	2G1
35	$2E$	0	59221	0.51	2D2	+ 0.14	2H	+ 0.13	2G2
36	$2T_1$	0	60014	0.72	2G1	+ 0.12	2P	+ 0.07	2F2
37	$2T_2$	0	61555	0.27	2D3	+ 0.21	2H	+ 0.15	2F1
38	$2T_2$	0	64036	0.41	2G1	+ 0.16	2D1	+ 0.14	2G2
39	$2A_1$	0	66918	0.69	2G1	+ 0.18	2S	+ 0.12	2G2
40	$2T_1$	0	70521	0.81	2P	+ 0.07	2F2	+ 0.06	2G2
41	$2E$	0	82031	0.67	2D1	+ 0.13	2G1	+ 0.11	2D3
42	$2T_2$	0	82668	0.62	2D1	+ 0.10	2H	+ 0.08	2G1

* Irreducible representation of the cubic group.

† Arsenov et al [5].

TABLE 7. ENERGY LEVELS OF Fe^{3+} IN $\text{Im}_3\text{Al}_5\text{O}_{12}$
 [Theoretical levels were calculated with $F^{(2)} = 53672$,
 $F^{(4)} = 41654$, and $B_{40} = -21963$ ($Dq = 1568.79$, $B = 623.08$, and $C = 3305.87$). All quantities are in cm^{-1} .]

No.	IR*	E_{obs}	E_{th}	Free ion state composition							
1	$6A_1$	0	-2	1.00	6S						
2	$2T_2$	0	8607	0.30	2I	+	0.27	2H	+	0.18	2F1
3	$4T_1$	9857	9809	0.59	4G	+	0.37	4P	+	0.04	4F
4	$4T_2$	13980	14027	0.43	4G	+	0.31	4F	+	0.26	4D
5	$2A_2$	0	21002	0.54	2I	+	0.42	2F1	+	0.04	2F2
6	$2T_1$	0	21184	0.58	2I	+	0.25	2H	+	0.13	2F1
7	$2T_1$	0	22620	0.47	2I	+	0.24	2F1	+	0.12	2H
8	$4(A_1, E)$	22773	22758	1.00	4G						
9	$2E$	0	24234	0.33	2I	+	0.31	2H	+	0.14	2D3
10	$4T_2$	24725	24859	0.52	4D	+	0.46	4G	+	0.02	4F
11	$4E$	27296	27120	1.00	4D						
12	$2T_1$	0	28121	0.33	2G2	+	0.20	2F2	+	0.19	2F1
13	$2T_2$	0	30156	0.27	2G2	+	0.27	2F2	+	0.15	2D2
14	$2A_1$	0	30935	0.44	2I	+	0.27	2G2	+	0.19	2G1
15	$2E$	0	33453	0.45	2I	+	0.24	2D3	+	0.14	2D1
16	$4T_1$	0	34148	0.55	4F	+	0.36	4P	+	0.08	4G
17	$2A_1$	0	34650	0.55	2I	+	0.31	2G2	+	0.08	2G1
18	$2T_2$	0	35293	0.53	2I	+	0.34	2D3	+	0.07	2D1
19	$4A_2$	0	36847	1.00	4F						
20	$2E$	0	38157	0.72	2G2	+	0.13	2I	+	0.06	2D2
21	$2T_2$	0	39743	0.42	2F2	+	0.28	2G2	+	0.15	2I
22	$2T_1$	0	40623	0.69	2H	+	0.30	2F1	+	0.01	2G2
23	$2A_2$	0	40694	0.74	2F2	+	0.21	2I	+	0.06	2F1
24	$2T_1$	0	40792	0.49	2F2	+	0.38	2G2	+	0.09	2I
25	$4T_1$	0	43150	0.41	4F	+	0.33	4G	+	0.26	4P
26	$2A_1$	0	43935	0.66	2S	+	0.30	2G2	+	0.04	2G1
27	$2E$	0	45157	0.39	2D3	+	0.33	2H	+	0.25	2D2
28	$2T_1$	0	47020	0.38	2H	+	0.18	2F1	+	0.17	2G1
29	$4T_2$	0	47840	0.67	4F	+	0.22	4D	+	0.11	4G
30	$2T_2$	0	48637	0.30	2F1	+	0.18	2H	+	0.16	2D2
31	$2T_1$	0	53220	0.40	2H	+	0.30	2I	+	0.18	2F1
32	$2A_2$	0	53536	0.53	2F1	+	0.25	2I	+	0.22	2F2
33	$2E$	0	53836	0.75	2G1	+	0.10	2H	+	0.07	2D1
34	$2T_2$	0	57888	0.44	2D2	+	0.16	2I	+	0.13	2G1
35	$2E$	0	59301	0.51	2D2	+	0.14	2H	+	0.13	2G2
36	$2T_1$	0	60115	0.72	2G1	+	0.12	2P	+	0.07	2F2
37	$2T_2$	0	61648	0.27	2D3	+	0.21	2H	+	0.15	2F1
38	$2T_2$	0	64150	0.41	2G1	+	0.16	2D1	+	0.14	2G2
39	$2A_1$	0	67049	0.69	2G1	+	0.18	2S	+	0.12	2G2
40	$2T_1$	0	70683	0.81	2P	+	0.07	2F2	+	0.06	2G2
41	$2E$	0	82179	0.67	2D1	+	0.13	2G1	+	0.11	2D3
42	$2T_2$	0	82808	0.62	2D1	+	0.10	2H	+	0.08	2G1

* Irreducible representation of the cubic group.

† Arsenov et al [5].

TABLE 8. ENERGY LEVELS OF Fe^{3+} IN $\text{Yb}_2\text{Al}_5\text{O}_{12}$
 [Theoretical levels were calculated with $F(2) = 53876$,
 $F(4) = 41567$, and $B_{40} = -22065$ ($Dq = 1576.07$, $B =$
 628.23 , and $C = 3298.97$). All quantities are in cm^{-1} .]

No.	IR ^a	E_{obs}	E_{th}	Free ion state composition							
1	$6A_1$	0	-2	1.00	6S						
2	$2T_2$	0	8465	0.30	2I	+	0.27	2H	+	0.18	2F1
3	$4T_1$	9790	9746	0.59	4G	+	0.37	4P	+	0.04	4F
4	$4T_2$	13960	14002	0.43	4G	+	0.31	4F	+	0.26	4D
5	$2A_2$	0	20929	0.54	2I	+	0.42	2F1	+	0.04	2F2
6	$2T_1$	0	21114	0.58	2I	+	0.25	2H	+	0.13	2F1
7	$2T_2$	0	22558	0.47	2I	+	0.24	2F1	+	0.12	2H
8	$4(A_1, E)$	22798	22776	1.00	4G						
9	$2E$	0	24178	0.33	2I	+	0.31	2H	+	0.14	2D3
10	$4T_2$	24751	24894	0.52	4D	+	0.46	4G	+	0.02	4F
11	$4E$	27350	27173	1.00	4D						
12	$2T_1$	0	28099	0.33	2G2	+	0.20	2F2	+	0.20	2F1
13	$2T_2$	0	30161	0.27	2G2	+	0.27	2F2	+	0.15	2D2
14	$2A_1$	0	30940	0.45	2I	+	0.27	2G2	+	0.19	2G1
15	$2E$	0	33432	0.45	2I	+	0.23	2D3	+	0.14	2D1
16	$4T_1$	0	34189	0.55	4F	+	0.37	4P	+	0.08	4G
17	$2A_1$	0	34670	0.54	2I	+	0.31	2G2	+	0.08	2G1
18	$2T_2$	0	35297	0.53	2I	+	0.34	2D3	+	0.07	2D1
19	$4A_2$	0	36912	1.00	4F						
20	$2E$	0	38194	0.72	2G2	+	0.13	2I	+	0.06	2D2
21	$2T_2$	0	39791	0.42	2F2	+	0.28	2G2	+	0.15	2I
22	$2T_1$	0	40617	0.69	2H	+	0.30	2F1	+	0.01	2G2
23	$2A_2$	0	40752	0.74	2F2	+	0.21	2I	+	0.06	2F1
24	$2T_1$	0	40852	0.49	2F2	+	0.39	2G2	+	0.09	2I
25	$4T_1$	0	43241	0.41	4F	+	0.33	4G	+	0.26	4P
26	$2A_1$	0	44025	0.66	2S	+	0.30	2G2	+	0.04	2G1
27	$2E$	0	45220	0.39	2D3	+	0.33	2H	+	0.25	2D2
28	$2T_1$	0	47074	0.37	2H	+	0.18	2F1	+	0.17	2G1
29	$4T_2$	0	47965	0.67	4F	+	0.22	4D	+	0.11	4G
30	$2T_2$	0	48695	0.30	2F1	+	0.18	2H	+	0.16	2D2
31	$2T_1$	0	53293	0.40	2H	+	0.30	2I	+	0.18	2F1
32	$2A_2$	0	53615	0.53	2F1	+	0.25	2I	+	0.22	2F2
33	$2E$	0	53941	0.75	2G1	+	0.10	2H	+	0.07	2D1
34	$2T_2$	0	58003	0.44	2D2	+	0.16	2I	+	0.13	2G1
35	$2E$	0	59417	0.51	2D2	+	0.14	2H	+	0.13	2G2
36	$2T_1$	0	60262	0.72	2G1	+	0.12	2P	+	0.07	2F2
37	$2T_2$	0	61780	0.27	2D3	+	0.21	2H	+	0.15	2F1
38	$2T_2$	0	64313	0.41	2G1	+	0.16	2D1	+	0.14	2G2
39	$2A_1$	0	67230	0.69	2G1	+	0.18	2S	+	0.12	2G2
40	$2T_1$	0	70907	0.81	2P	+	0.07	2F2	+	0.06	2G2
41	$2E$	0	82389	0.67	2D1	+	0.13	2G1	+	0.12	2D3
42	$2T_2$	0	83005	0.61	2D1	+	0.10	2H	+	0.08	2G1

^a Irreducible representation of the cubic group.

[†] Arsenov et al [5].

3.2 Theoretical Crystal Field Parameters

The crystallographic data [7] on the RAG compounds are presented in table 9. It is assumed that the Fe^{3+} ion enters the compound substitutionally at the Al_1 site, but in a few cases the Fe^{3+} has been reported to occupy the Al_2 site. To obtain theoretical crystal field parameters for these two sites (Al_1 and Al_2), we used existing computer programs that calculate the crystal field components A_{nm} . In these programs the charge on the ions, q , in table 9 is in units of the electronic charge, and the polarizability, α , is in units of cubic angstroms. The specific x-ray data used in these programs are given in table 9. With the use of the data of table 9, the A_{nm} for the Al_1 site were computed for both the point charge and the total. The total includes the point charge, point dipole, and self-induced contribution [16,17]. Since the x-ray data are missing for some of the compounds, the crystal field components were least-squares fit to a straight line, and the resulting A_{nm} for all compounds are given in table 10. If the site occupied by the Al_1 site were cubic, then A_{20} would be zero and $A_{43} = |A_{40}|(10/17)^{1/2}$. However, A_{20} is considerable and A_{43} differs significantly from the cubic relation. Table 11 gives the crystal field components, A_{nm} , for the Al_2 site (S_4 symmetry), which has been linear least-squares fit as in table 11. For the Al_2 site, the presence of odd n terms (A_{32} , A_{52}) indicates the possibility of electric dipole transitions. Also, if the site were cubic then A_{20} would be zero and $A_{44} = (5/14)^{1/2} |A_{40}|$, which is certainly not the case.

In the theory of the crystal fields developed for the rare-earth ions [7], the theoretical crystal field parameters are given by

$$B_{nm} = \rho_n A_{nm} , \quad (12)$$

where A_{nm} are the crystal field components obtained from the lattice sums and ρ_n contain parameters such as shielding, wave function expansion, etc (see Morrison and Leavitt [7]). To proceed further, we use the crystal field invariants [8] which we define as

$$S_n(B) = \left[\sum_m B_{nm}^* B_{nm} \right]^{1/2} , \quad (13)$$

which for $n = 4$ and C_{3i} symmetry reduces to

$$S_4(A) = \rho_4 [A_{40} + 2A_{43}^2]^{1/2} , \quad (14)$$

and for cubic symmetry the $S_4(B)$ is

$$S_4(B) = |B_{40}^e| \sqrt{27/7} , \quad (15)$$

where the experimental crystal field parameter, B_{40}^e , is given in row 3 for each compound in table 1. Using equations (14) and (15), we determined a value of ρ_4 for each compound given in table 1, row 3, and from the resulting set of ρ_4 , we calculated the simple arithmetic average. That is, we assumed that the radial factors ρ_4 and ρ_2 were independent of the host material.

In the crystal field theory developed for the rare-earth ions, ρ_n is proportional to $\langle r^n \rangle$ evaluated by use of Hartree-Fock radial wave functions and an expansion parameter, τ , or

$$\rho_n = \frac{\langle r^n \rangle}{\tau^n} \text{HF}(1 - \sigma_n) , \quad (16)$$

where σ_n is a screening factor [7]. We shall ignore the screening factor ($\sigma_n = 0$) and assume that

$$\rho_4 = \langle r^4 \rangle_{\text{HF}} / \tau^4 , \quad (17)$$

and from equation (16) we have

$$\rho_2 = \langle r^2 \rangle_{\text{HF}} [\rho_4 / \langle r^4 \rangle_{\text{HF}}]^{1/2} . \quad (18)$$

For Fe^{3+} the Hartree-Fock values [11] are $\langle r^2 \rangle = 0.3196 \text{ \AA}^2$ and $\langle r^4 \rangle = 0.2168 \text{ \AA}^4$, and we obtain $\rho_2 = 0.7344 \text{ \AA}^2$ and $\rho_4 = 1.1483 \text{ \AA}^4$.

The theoretical values of B_{20} , B_{40} , and B_{43} were computed from

$$\begin{aligned} B_{20} &= \rho_2 A_{20} , \\ B_{40} &= \rho_4 A_{40} , \text{ and} \\ B_{43} &= \rho_4 A_{43} . \end{aligned} \quad (19)$$

Table 12 gives the B_{20} , B_{40} , and B_{43} for all compounds using point charge A_{nm} from table 10. Also included in table 12 are the crystal field parameters given by equation (8). The sums $S^{(0)}$, $S^{(2)}$, and $S^{(4)}$ for Al_1 and Al_2 were calculated with the x-ray data of table 2. The linear least-squares fit for these parameters is given in table 13. The role of $S^{(0)}$, $S^{(2)}$, and $S^{(4)}$ is discussed by Morrison et al [17].

3.3 Final Parameters and Predicted Splittings, Including Spin-Orbit Interaction

The theoretical crystal field parameters B_{20} , B_{40} , and B_{43} given in table 12 were used in a least-squares-fit program along with experimental levels reported by Arsenev et al [5], and the best fit $F^{(2)}$ and $F^{(4)}$ were obtained for each ion. Again, a linear least-squares fit to $F^{(2)}$ and $F^{(4)}$ was obtained, and the result is given in table 7.

The final set of parameters resulting from the above analysis is given in table 14. That is, table 14 gives the linear least-squares fit for the parameters $F^{(2)}$, $F^{(4)}$, B_{20} , B_{40} , and B_{43} . The set of parameters given in table 14 is used along with the spin-orbit interaction included ($\zeta = 370 \text{ cm}^{-1}$ - 80 percent of the free ion value) to calculate the energy levels of Fe^{3+} , and the results are given in tables 15 through 22.

TABLE 9. CRYSTALLOGRAPHIC DATA FOR $R_3Al_5O_{12}$
CUBIC $Ia\bar{3}d$, 230, $Z = 8$

Ion	Site	Symm	x	y	z	q	* α ($\text{\AA}^3$)
Al ₁	16a	C _{3i}	0	0	0	3	0.053
Al ₂	24d	S ₄	0	1/4	3/8	3	0.053
R	24c	D ₂	0	1/4	1/8	3	α_R^b
O	96h	C ₁	x	y	z	-2	1.349

X-ray data and polarizabilities for $R_3Al_5O_{12}$

R	a ($\text{\AA}$)	x	y	z	$\dagger\alpha_R$ ($\text{\AA}^3$)
Gd	12.110	-0.0311	0.0509	0.1490	1.0100
Tb	12.000	-0.0314	0.0502	0.1480	0.9700
Dy	12.040	-0.0320	0.0560	0.1510	0.9400
Ho	12.000	-0.0311	0.0513	0.1503	0.9000
Er	11.964	---	---	---	---
Tm	11.957	---	---	---	---
Yb	11.930	-0.0296	0.0529	0.1504	0.8000
Lu	11.910	-0.0294	0.0537	0.1509	0.7700

*P. C. Schmidt, A. Weiss, and T. P. Das, *Effect of Crystal Fields and Self Consistency of Dipole and Quadrupole Polarizabilities of Closed-Shell Ions*, *Phys. Rev. B19* (1979), 5525.

$\dagger$ S. Fraga et al [11].

TABLE 10. BEST LEAST-SQUARES FIT TO LATTICE SUMS
 A_{nm} ($\text{cm}^{-1}/\text{\AA}^n$) FOR Al₁ ION IN 16a [C_{3i}] SITE IN $R_3Al_5O_{12}$
[Rotated so that z axis is parallel to (111) axis.]

Ion	Point charge			Total		
	A ₂₀	A ₄₀	A ₄₃	A ₂₀	A ₄₀	A ₄₃
Gd	4001.8	-19678	22438	-8012.9	-8396.6	14386
Tb	5497.8	-19744	22380	-7741.3	-8516.9	13576
Dy	6993.8	-19811	22322	-7469.8	-8637.1	13665
Ho	8489.7	-19878	22265	-7198.2	-8757.4	13755
Er	9985.7	-19944	22207	-6926.6	-8877.7	13845
Tm	11481.6	-20011	22150	-6655.0	-8998.0	13934
Yb	12977.6	-20078	22092	-6383.4	-9118.3	14024
Lu	14473.5	-20144	22035	-6111.9	-9238.6	14114

TABLE 11. LEAST SQUARES FIT TO LATTICE SUMS
 χ_{nm} ($\text{cm}^{-1}/\text{\AA}^n$) FOR Al_2 ION IN $24d$ [S_4] SITE IN $\text{R}_3\text{Al}_5\text{O}_{12}$
 [Rotated so that A_{44} is real and positive]

a. Monopole sums

Ion	A_{20}	$\text{Re}A_{32}$	$\text{Im}A_{32}$	A_{40}	A_{44}	$\text{Re}A_{52}$	$\text{Im}A_{52}$
Gd	3489.0	45761	1950.6	-24188	9886.2	4402.7	-0.0360
Tb	4114.5	45935	1910.9	-24364	9882.9	4567.1	7.8475
Dy	4740.0	46109	1871.1	-24539	9879.6	4731.5	15.731
Ho	5365.5	46283	1831.3	-24715	9876.4	4895.9	23.614
Er	5991.0	46456	1791.6	-24890	9873.1	5060.4	31.498
Tm	6616.5	46630	1751.8	-25065	9869.9	5224.8	39.381
Yb	7242.1	46804	1712.0	-25241	9866.6	5389.2	47.265
Lu	7867.6	46977	1672.3	-25416	9863.4	5553.6	55.148

b. Total

Ion	A_{20}	$\text{Re}A_{32}$	$\text{Im}A_{32}$	A_{40}	A_{44}	$\text{Re}A_{52}$	$\text{Im}A_{52}$
Gd	14838	13445	-76.047	-21229	7215.7	1691.7	-94.485
Tb	15408	18608	-146.09	-21372	7251.7	2460.2	-134.66
Dy	15978	13770	-216.14	-21515	7287.7	3228.7	-174.84
Ho	16549	28931	-286.18	-21658	3723.7	3997.2	-215.01
Er	17119	34094	-356.23	-21801	7359.7	4765.6	-255.19
Tm	17690	39255	-426.27	-21944	7395.7	5534.1	-295.37
Yb	18260	44418	-496.31	-22088	7431.7	6302.6	-335.54
Lu	18830	49580	-566.36	-22231	7467.7	7071.1	-375.72

TABLE 12. CRYSTAL FIELD PARAMETERS

 B_{nm} , Dq , v , and v' (all in cm^{-1})

Ion	B_{20}	B_{40}	B_{43}	Dq	v	v'
Gd	2943.2	-22592	25761	1558.9	931.7	-711.3
Tb	4043.5	-22668	25694	1557.4	1361.4	-948.4
Dy	5143.7	-22745	25628	1555.9	1790.8	-1185.5
Ho	6243.9	-22822	25562	1554.5	2220.6	-1422.6
Er	7344.2	-22898	25496	1552.9	2650.4	-1659.7
Tm	8444.4	-22975	25430	1551.4	3080.0	-1896.7
Yb	9544.6	-23052	25364	1549.9	3509.8	-2133.7
Lu	10644.8	-23127	25297	1548.4	3939.6	-2370.8

TABLE 13. LINEAR FIT VALUES OF $S^{(0)}$, $S^{(2)}$, $S^{(4)}$
FOR Al_1 AND Al_2 SITES

Ion	Al_1 site			Al_2 site		
	$S^{(0)}$	$S^{(2)}$	$S^{(4)}$	$S^{(0)}$	$S^{(2)}$	$S^{(4)}$
	($\text{cm}^{-1}/\text{\AA}^2$)	($\text{cm}^{-1}/\text{\AA}^4$)	($\text{cm}^{-1}/\text{\AA}^8$)	($\text{cm}^{-1}/\text{\AA}^2$)	($\text{cm}^{-1}/\text{\AA}^4$)	($\text{cm}^{-1}/\text{\AA}^8$)
Gd	18889	14244	1647.2	22079	19742	3269.7
Tb	18907	14259	1649.0	22273	19952	319.3
Dy	18907	14274	1650.7	22468	20163	3368.9
Ho	18944	14289	1652.4	22663	20374	3418.5
Er	18962	14304	1654.1	22858	20585	3468.1
Tm	18981	14319	1655.9	23053	20795	35178
Yb	18999	14334	1657.6	23248	21006	3567.4
Lu	19017	14349	1659.3	23443	21217	3617.0

TABLE 14. FINAL LINEAR FIT FREE-ION AND CRYSTAL
FIELD PARAMETERS FOR Fe^{3+} IN $\text{R}_3\text{Al}_5\text{O}_{12}$
(all in cm^{-1})

Table 14a. Slater and Crystal Field Parameters (B_{nm})

R	F^2	F^4	B_{20}	B_{40}	B_{43}
Gd	52204	43368	2943.2	-22592	25761
Tb	52465	43188	4043.5	-22668	25694
Dy	52728	43009	5143.7	-22745	25628
Ho	52991	42830	6243.9	-22822	25562
Er	53254	42651	7344.2	-22898	25496
Tm	53517	42471	8444.4	-22975	25430
Yb	53780	42292	9544.6	-23052	25364
Lu	54043	42113	10644.8	-23127	25297

Table 14b. Racah and Macfarlane Parameters

R	Dq	B	C	v	v'
Gd	1558.75	573.69	3441.90	-1591.15	478.02
Tb	1557.19	581.05	3427.62	-2104.63	685.49
Dy	1555.70	588.45	3413.41	-2618.12	892.93
Ho	1554.20	595.85	3399.21	-3131.61	1100.36
Er	1552.69	603.24	3385.00	-3644.82	1307.93
Tm	1551.19	610.65	3370.71	-4158.31	1515.36
Yb	1549.70	618.05	3356.51	-4671.80	1722.80
Lu	1548.12	625.45	3342.30	-5184.92	1930.36

TABLE 15. ENERGY LEVELS OF Fe^{3+} IN $\text{Gd}_3\text{Al}_5\text{O}_{12}$
 [Energy levels were calculated with $F^{(2)} = 52204$,
 $F^{(4)} = 43368$, $\zeta = 370$, $B_{20} = 2943.2$, and $B_{40} = -22592$
 ($Dq = 1559.09$, $B = 573.69$, and $C = 3442.90$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
1	4,5	0.000	1.00	6S	+	0.00	4P	+	0.00	4G
2	6	0.103	1.00	6S	+	0.00	4P	+	0.00	4G
3	4,5	0.174	1.00	6S	+	0.00	4P	+	0.00	4G
4	4,5	8718	0.25	2I	+	0.22	2H	+	0.16	2F1
5	4,5	9330	0.24	2I	+	0.22	2H	+	0.14	2F1
6	6	9486	0.22	2I	+	0.20	2H	+	0.17	4G
7	6	10101	0.56	4G	+	0.33	4P	+	0.05	4F
8	4,5	10186	0.54	4G	+	0.32	4P	+	0.05	4F
9	4,5	10284	0.58	4G	+	0.36	4P	+	0.04	4F
10	6	10417	0.45	4G	+	0.28	4P	+	0.07	2I
11	4,5	10433	0.53	4G	+	0.33	4P	+	0.03	4F
12	4,5	10447	0.50	4G	+	0.31	4P	+	0.05	2I
13	4,5	13686	0.44	4G	+	0.32	4F	+	0.24	4D
14	6	13703	0.44	4G	+	0.32	4F	+	0.24	4D
15	4,5	14304	0.40	4G	+	0.31	4F	+	0.28	4D
16	6	14323	0.41	4G	+	0.31	4F	+	0.27	4D
17	4,5	14335	0.42	4G	+	0.31	4F	+	0.26	4D
18	4,5	14347	0.42	4G	+	0.31	4F	+	0.26	4D
19	4,5	21528	0.53	2I	+	0.23	2H	+	0.13	2F1
20	6	21669	0.53	2I	+	0.23	2H	+	0.12	2F1
21	4,5	21690	0.53	2I	+	0.40	2F1	+	0.05	2F2
22	4,5	22004	0.53	2I	+	0.22	2H	+	0.13	2F1
23	4,5	22635	0.63	4G	+	0.16	2I	+	0.09	2F1
24	4,5	22798	0.75	4G	+	0.12	2I	+	0.06	2F1
25	6	22812	0.73	4G	+	0.12	2I	+	0.06	2F1
26	4,5	23029	0.91	4G	+	0.05	2I	+	0.02	2H
27	4,5	23052	0.91	4G	+	0.05	2I	+	0.02	2H
28	6	23068	0.90	4G	+	0.06	2I	+	0.02	2H
29	6	23389	0.33	2I	+	0.28	4G	+	0.16	2F1
30	4,5	23422	0.32	2I	+	0.31	4G	+	0.16	2F1
31	4,5	23482	0.32	2I	+	0.32	4G	+	0.15	2F1
32	4,5	24518	0.33	4G	+	0.32	4D	+	0.12	2I
33	6	24546	0.31	4D	+	0.31	4G	+	0.13	2I
34	4,5	24729	0.48	4D	+	0.48	4G	+	0.02	4F
35	4,5	24841	0.51	4D	+	0.46	4G	+	0.02	4F
36	6	24929	0.38	4D	+	0.34	4G	+	0.09	2I
37	4,5	25068	0.32	4D	+	0.28	4G	+	0.14	2I

^aIrreducible representation of the C_{3i} group.

TABLE 15. ENERGY LEVELS OF Fe^{3+} IN $\text{Gd}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52204$,
 $F^{(4)} = 43368$, $\zeta = 370$, $B_{20} = 2943.2$, and $B_{40} = -22592$
 ($Dq = 1559.09$, $B = 573.69$, and $C = 3442.90$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
38	4,5	25152	0.40	4D	+	0.32	4G	+	0.09	2I
39	6	25169	0.34	4D	+	0.28	4G	+	0.13	2I
40	4,5	26928	0.98	4D	+	0.00	4F	+	0.00	2G2
41	6	26936	0.98	4D	+	0.00	4G	+	0.00	4F
42	4,5	26938	0.99	4D	+	0.00	4F	+	0.00	4G
43	4,5	26947	0.99	4D	+	0.00	4G	+	0.00	4F
44	6	28224	0.34	2G2	+	0.20	2F2	+	0.18	2F1
45	4,5	28252	0.32	2G2	+	0.21	2F2	+	0.18	2H
46	4,5	28758	0.34	2G2	+	0.21	2F2	+	0.17	2F1
47	4,5	29610	0.25	2G2	+	0.24	2F2	+	0.14	2D2
48	6	30359	0.30	2F2	+	0.26	2G2	+	0.15	2D2
49	4,5	30490	0.28	2F2	+	0.27	2G2	+	0.15	2D2
50	4,5	31108	0.32	2G2	+	0.32	2I	+	0.22	2G1
51	6	33658	0.36	4F	+	0.27	4P	+	0.14	2I
52	4,5	33722	0.40	4F	+	0.30	4P	+	0.12	2I
53	4,5	34057	0.26	4F	+	0.24	2I	+	0.17	4P
54	6	34226	0.28	4F	+	0.22	2I	+	0.19	4P
55	4,5	34572	0.51	4F	+	0.29	4P	+	0.08	2I
56	4,5	34671	0.43	4F	+	0.23	4P	+	0.19	2I
57	6	34749	0.46	4F	+	0.26	4P	+	0.10	2I
58	4,5	34830	0.48	4F	+	0.27	4P	+	0.08	2I
59	4,5	35080	0.42	2I	+	0.19	2G2	+	0.18	4F
60	4,5	35830	0.52	2I	+	0.32	2D3	+	0.06	2D1
61	6	35832	0.52	2I	+	0.31	2D3	+	0.06	2D1
62	4,5	35880	0.51	2I	+	0.34	2D3	+	0.07	2D1
63	4,5	36791	0.97	4F	+	0.01	2D3	+	0.01	2I
64	6	36796	0.97	4F	+	0.01	2D3	+	0.01	2I
65	6	38198	0.69	2G2	+	0.12	2I	+	0.06	2D2
66	4,5	38248	0.69	2G2	+	0.13	2I	+	0.06	2D2
67	6	39589	0.36	2F2	+	0.30	2G2	+	0.15	2I
68	4,5	39677	0.38	2F2	+	0.28	2G2	+	0.14	2I
69	4,5	40136	0.45	2F2	+	0.30	2G2	+	0.13	2I
70	4,5	40312	0.52	2F2	+	0.26	2G2	+	0.16	2I
71	4,5	40378	0.46	2F2	+	0.22	2H	+	0.13	2F1
72	6	40804	0.46	2F2	+	0.32	2G2	+	0.12	2H
73	4,5	40862	0.50	2F2	+	0.38	2G2	+	0.07	2I
74	4,5	41483	0.61	2H	+	0.29	2F1	+	0.03	2G2
75	6	41598	0.54	2H	+	0.25	2F1	+	0.09	2G2

TABLE 15. ENERGY LEVELS OF Fe^{3+} IN $\text{Cd}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52204$,
 $F^{(4)} = 43368$, $\zeta = 370$, $B_{20} = 2943.2$, and $B_{40} = -22592$
 ($Dq = 1559.09$, $B = 573.69$, and $C = 3442.90$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
76	4,5	41856	0.42	2H	+	0.24	2F2	+	0.19	2F1
77	4,5	42729	0.30	4F	+	0.28	4G	+	0.24	4P
78	4,5	42938	0.34	4F	+	0.31	4G	+	0.28	4P
79	6	43012	0.36	4F	+	0.32	4G	+	0.28	4P
80	4,5	43123	0.37	4F	+	0.32	4G	+	0.28	4P
81	4,5	43636	0.50	2S	+	0.24	2G2	+	0.08	4F
82	6	44001	0.40	4F	+	0.32	4G	+	0.24	4P
83	4,5	44084	0.38	4F	+	0.30	4G	+	0.23	4P
84	6	45050	0.37	2D3	+	0.31	2H	+	0.22	2D2
85	4,5	45076	0.38	2D3	+	0.31	2H	+	0.23	2D2
86	4,5	46791	0.37	2H	+	0.21	2F1	+	0.17	2G1
87	4,5	47485	0.63	4F	+	0.20	4D	+	0.11	4G
88	4,5	47536	0.49	4F	+	0.16	4D	+	0.10	2H
89	4,5	47586	0.33	4F	+	0.20	2H	+	0.11	4D
90	6	47589	0.48	4F	+	0.16	4D	+	0.10	2H
91	6	47817	0.29	2H	+	0.16	4F	+	0.13	2F1
92	4,5	47965	0.48	4F	+	0.16	4D	+	0.11	2H
93	6	48003	0.61	4F	+	0.20	4D	+	0.11	4G
94	4,5	48043	0.64	4F	+	0.20	4D	+	0.12	4G
95	4,5	48866	0.28	2F1	+	0.17	2D2	+	0.17	2H
96	6	48996	0.27	2F1	+	0.16	2D2	+	0.16	2H
97	4,5	49364	0.28	2F1	+	0.17	2H	+	0.16	2G1
98	4,5	53118	0.37	2G1	+	0.24	2H	+	0.16	2I
99	6	53193	0.41	2G1	+	0.22	2H	+	0.14	2I
100	4,5	53792	0.39	2G1	+	0.25	2H	+	0.16	2I
101	6	53938	0.36	2G1	+	0.26	2H	+	0.17	2I
102	4,5	53993	0.47	2F1	+	0.28	2I	+	0.16	2F2
103	4,5	54433	0.34	2H	+	0.26	2I	+	0.22	2F1
104	4,5	57502	0.46	2D2	+	0.15	2I	+	0.12	2G1
105	6	57807	0.38	2D2	+	0.17	2G1	+	0.16	2I
106	4,5	57865	0.39	2D2	+	0.17	2G1	+	0.16	2I
107	4,5	59233	0.35	2G1	+	0.24	2D2	+	0.10	2H
108	6	59259	0.45	2G1	+	0.16	2D2	+	0.09	2H
109	6	59789	0.34	2D2	+	0.23	2G1	+	0.12	2H
110	4,5	59830	0.31	2G1	+	0.29	2D2	+	0.09	2H
111	4,5	60059	0.68	2G1	+	0.15	2P	+	0.08	2F2
112	4,5	61542	0.26	2D3	+	0.24	2H	+	0.15	2I
113	6	61942	0.29	2D3	+	0.17	2H	+	0.16	2F1

TABLE 15. ENERGY LEVELS OF Fe^{3+} IN $\text{Gd}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 52204$,
 $F^{(4)} = 43368$, $\zeta = 370$, $B_{20} = 2943.2$, and $B_{40} = -22592$
 $(Dq = 1559.09, B = 573.69, \text{ and } C = 3442.90)$. All
quantities are in cm^{-1} .]

No.	IR^a	Energy	Free ion state composition							
114	4,5	62080	0.27	2D3	+	0.17	2H	+	0.15	2F1
115	4,5	63256	0.34	2G1	+	0.21	2D1	+	0.15	2G2
116	6	63889	0.46	2G1	+	0.14	2F2	+	0.14	2G2
117	4,5	63988	0.44	2G1	+	0.15	2G2	+	0.14	2D1
118	4,5	66617	0.69	2G1	+	0.18	2S	+	0.12	2G2
119	4,5	69291	0.78	2P	+	0.07	2G2	+	0.07	2G1
120	6	69606	0.77	2P	+	0.07	2F2	+	0.07	2G2
121	4,5	69610	0.76	2P	+	0.08	2F2	+	0.07	2G2
122	6	81740	0.67	2D1	+	0.13	2G1	+	0.10	2D3
123	4,5	81820	0.67	2D1	+	0.13	2G1	+	0.10	2D3
124	6	82148	0.63	2D1	+	0.10	2H	+	0.07	2G1
125	4,5	82215	0.63	2D1	+	0.11	2H	+	0.06	2G1
126	4,5	83895	0.58	2D1	+	0.10	2G1	+	0.10	2H

^aIrreducible representation of the C_{3i} group.

TABLE 16. ENERGY LEVELS OF Fe^{3+} IN $\text{Tb}_3\text{Al}_5\text{O}_{12}$

[Energy levels were calculated with $F^{(2)} = 52465$,
 $F^{(4)} = 43188$, $\zeta = 370$, $B_{20} = 4043.5$, and $B_{40} = -22668$
 $(Dq = 1557.62, B = 581.05, \text{ and } C = 3427.62)$. All
quantities are in cm^{-1} .]

No.	IR^a	Energy	Free ion state composition							
1	4,5	0.000	1.00	6S	+	0.00	4P	+	0.00	4G
2	6	0.122	1.00	6S	+	0.00	4P	+	0.00	4G
3	4,5	0.218	1.00	6S	+	0.00	4P	+	0.00	4G
4	4,5	8603	0.25	2I	+	0.22	2H	+	0.16	2F1
5	4,5	9253	0.25	2I	+	0.22	2H	+	0.14	2F1
6	6	9473	0.21	2I	+	0.20	4G	+	0.18	2H
7	6	10000	0.54	4G	+	0.31	4P	+	0.05	4F
8	4,5	10054	0.54	4G	+	0.31	4P	+	0.05	4F
9	4,5	10265	0.57	4G	+	0.36	4P	+	0.04	4F
10	6	10391	0.44	4G	+	0.27	4P	+	0.08	2I
11	4,5	10414	0.49	4G	+	0.31	4P	+	0.05	2I
12	4,5	10424	0.54	4G	+	0.34	4P	+	0.04	4F

^aIrreducible representation of the C_{3i} group.

TABLE 16. ENERGY LEVELS OF Fe^{3+} IN $\text{Tb}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52465$,
 $F^{(4)} = 43188$, $\zeta = 370$, $B_{20} = 4043.5$, and $B_{40} = -22668$
 ($Dq = 1557.62$, $B = 581.05$, and $C = 3427.62$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
13	4,5	13521	0.45	4G	+	0.32	4F	+	0.23	4D
14	6	13540	0.45	4G	+	0.32	4F	+	0.23	4D
15	4,5	14451	0.41	4G	+	0.31	4F	+	0.28	4D
16	6	14464	0.41	4G	+	0.30	4F	+	0.27	4D
17	4,5	14470	0.42	4G	+	0.31	4F	+	0.26	4D
18	4,5	14478	0.42	4G	+	0.31	4F	+	0.26	4D
19	4,5	21401	0.53	2I	+	0.24	2H	+	0.13	2F1
20	6	21624	0.53	2I	+	0.23	2H	+	0.12	2F1
21	4,5	21625	0.53	2I	+	0.40	2F1	+	0.05	2F2
22	4,5	21957	0.53	2I	+	0.22	2H	+	0.13	2F1
23	4,5	22575	0.58	4G	+	0.18	2I	+	0.10	2F1
24	4,5	22756	0.73	4G	+	0.12	2I	+	0.06	2F1
25	6	22758	0.64	4G	+	0.16	2I	+	0.08	2F1
26	4,5	22991	0.91	4G	+	0.05	2I	+	0.02	2H
27	4,5	23041	0.93	4G	+	0.04	2I	+	0.02	2H
28	6	23058	0.91	4G	+	0.06	2I	+	0.02	2H
29	6	23290	0.36	4G	+	0.28	2I	+	0.14	2F1
30	4,5	23349	0.41	4G	+	0.27	2I	+	0.13	2F1
31	4,5	23450	0.35	2I	+	0.28	4G	+	0.16	2F1
32	4,5	24517	0.35	4G	+	0.33	4D	+	0.11	2I
33	6	24551	0.33	4G	+	0.33	4D	+	0.11	2I
34	4,5	24709	0.48	4G	+	0.47	4D	+	0.02	4F
35	4,5	24813	0.50	4D	+	0.47	4G	+	0.02	4F
36	6	24946	0.31	4D	+	0.28	4G	+	0.14	2I
37	4,5	25073	0.24	4D	+	0.22	4G	+	0.19	2I
38	4,5	25211	0.48	4D	+	0.35	4G	+	0.06	2I
39	6	25225	0.40	4D	+	0.30	4G	+	0.10	2I
40	4,5	26932	0.97	4D	+	0.01	4F	+	0.00	4G
41	6	26943	0.97	4D	+	0.01	4F	+	0.01	4G
42	4,5	26945	0.98	4D	+	0.01	4F	+	0.00	4G
43	4,5	26955	0.98	4D	+	0.01	4G	+	0.01	4F
44	6	28169	0.33	2G2	+	0.20	2F2	+	0.18	2F
45	4,5	28201	0.31	2G2	+	0.21	2F2	+	0.19	2H
46	4,5	28922	0.33	2G2	+	0.20	2F2	+	0.17	2F1
47	4,5	29425	0.24	2G2	+	0.21	2F2	+	0.15	2I
48	6	30528	0.30	2F2	+	0.26	2G2	+	0.15	2D2
49	4,5	30642	0.28	2F2	+	0.27	2G2	+	0.15	2D2
50	4,5	31183	0.32	2G2	+	0.32	2I	+	0.21	2G1
51	6	33547	0.39	4F	+	0.31	4P	+	0.11	2I

TABLE 16. ENERGY LEVELS OF Fe^{3+} IN $\text{Tb}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F(2) = 52465$,
 $F(4) = 43188$, $\zeta = 370$, $B_{20} = 4043.5$, and $B_{40} = -22668$
 ($Dq = 1557.62$, $B = 581.05$, and $C = 3427.62$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
52	4,5	33604	0.43	4F	+	0.35	4P	+	0.08	2I
53	4,5	34034	0.32	2I	+	0.16	2D3	+	0.16	4F
54	6	34182	0.29	2I	+	0.19	4F	+	0.15	2D3
55	4,5	34718	0.41	4F	+	0.23	4P	+	0.20	2I
56	4,5	34792	0.37	4F	+	0.23	2I	+	0.21	4P
57	6	34889	0.50	4F	+	0.28	4P	+	0.06	4G
58	4,5	34990	0.53	4F	+	0.29	4P	+	0.07	4G
59	4,5	35161	0.31	4F	+	0.26	2I	+	0.18	4P
60	6	35781	0.52	2I	+	0.31	2D3	+	0.06	2D1
61	4,5	35783	0.51	2I	+	0.31	2D3	+	0.06	2D1
62	4,5	35851	0.51	2I	+	0.35	2D3	+	0.07	2D1
63	4,5	36850	0.97	4F	+	0.01	2D3	+	0.01	2I
64	6	36857	0.97	4F	+	0.01	2D3	+	0.01	2I
65	6	38123	0.67	2G2	+	0.12	2I	+	0.06	2D2
66	4,5	38200	0.68	2G2	+	0.13	2I	+	0.06	2D2
67	6	395001	0.35	2F2	+	0.28	2G2	+	0.15	2I
68	4,5	39583	0.37	2F2	+	0.27	2G2	+	0.14	2I
69	4,5	40111	0.36	2F2	+	0.27	2H	+	0.14	2G2
70	4,5	40180	0.55	2F2	+	0.19	2I	+	0.18	2G2
71	4,5	40296	0.47	2F2	+	0.30	2G2	+	0.13	2I
72	6	40827	0.43	2F2	+	0.31	2G2	+	0.13	2H
73	4,5	40912	0.49	2F2	+	0.38	2G2	+	0.06	2I
74	4,5	41544	0.56	2H	+	0.28	2F1	+	0.06	2G2
75	6	41693	0.48	2H	+	0.24	2F1	+	0.13	2G2
76	4,5	42131	0.33	2H	+	0.28	2F2	+	0.15	2F1
77	4,5	42629	0.31	4F	+	0.28	4G	+	0.24	4P
78	4,5	42811	0.33	4F	+	0.30	4G	+	0.26	4P
79	6	42864	0.36	4F	+	0.32	4G	+	0.28	4P
80	4,5	42970	0.38	4F	+	0.32	4G	+	0.28	4P
81	4,5	43631	0.54	2S	+	0.26	2G2	+	0.05	4F
82	6	44285	0.41	4F	+	0.31	4G	+	0.22	4P
83	4,5	44353	0.41	4F	+	0.31	4G	+	0.22	4P
84	6	45003	0.35	2D3	+	0.31	2H	+	0.21	2D2
85	4,5	45038	0.36	2D3	+	0.31	2H	+	0.22	2D2
86	4,5	46634	0.36	2H	+	0.22	2F1	+	0.17	2G1
87	4,5	47556	0.64	4F	+	0.21	4D	+	0.11	4G
88	4,5	47634	0.61	4F	+	0.20	4D	+	0.10	4G
89	6	47704	0.54	4F	+	0.18	4D	+	0.09	4G

TABLE 16. ENERGY LEVELS OF Fe^{3+} IN $\text{Tb}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F(2) = 52465$,
 $F(4) = 43188$, $\zeta = 370$, $B_{20} = 4043.5$, and $B_{40} = -22668$
 ($Dq = 1557.62$, $B = 581.05$, and $C = 3427.62$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
90	4,5	47741	0.30	4F	+	0.22	2H	+	0.11	4D
91	6	48035	0.32	2H	+	0.13	2F1	+	0.13	2G1
92	4,5	48122	0.36	4F	+	0.17	2H	+	0.13	4D
93	6	48157	0.57	4F	+	0.18	4D	+	0.10	4G
94	4,5	48208	0.63	4F	+	0.20	4D	+	0.12	4G
95	4,5	48839	0.26	2F1	+	0.17	2H	+	0.16	2D2
96	6	48995	0.25	2F1	+	0.16	2H	+	0.15	2D2
97	4,5	49504	0.28	2F1	+	0.17	2H	+	0.16	2G1
98	4,5	52981	0.27	2G1	+	0.27	2H	+	0.19	2I
99	6	53066	0.30	2G1	+	0.26	2H	+	0.18	2I
100	4,5	53877	0.36	2G1	+	0.18	2H	+	0.16	2I
101	4,5	53920	0.39	2F1	+	0.24	2I	+	0.13	2F2
102	6	54041	0.46	2G1	+	0.22	2H	+	0.14	2I
103	4,5	54662	0.35	2H	+	0.25	2I	+	0.21	2F1
104	4,5	57430	0.48	2D2	+	0.14	2I	+	0.12	2G1
105	6	57742	0.38	2D2	+	0.20	2G1	+	0.15	2I
106	4,5	57790	0.38	2D2	+	0.20	2G1	+	0.15	2I
107	4,5	59189	0.35	2G1	+	0.23	2D2	+	0.11	2H
108	6	59230	0.41	2G1	+	0.17	2D2	+	0.10	2H
109	6	60087	0.32	2D2	+	0.24	2G1	+	0.11	2H
110	4,5	60129	0.31	2D2	+	0.27	2G1	+	0.09	2H
111	4,5	60362	0.67	2G1	+	0.15	2P	+	0.09	2F2
112	4,5	61560	0.25	2H	+	0.24	2D3	+	0.15	2I
113	6	62103	0.27	2D3	+	0.16	2H	+	0.15	2F1
114	4,5	62229	0.26	2D3	+	0.16	2H	+	0.14	2F1
115	4,5	63252	0.31	2G1	+	0.22	2D1	+	0.15	2G2
116	6	64116	0.47	2G1	+	0.14	2G2	+	0.13	2F2
117	4,5	64227	0.45	2G1	+	0.15	2G2	+	0.13	2D1
118	4,5	66778	0.69	2G1	+	0.17	2S	+	0.12	2G2
119	4,5	69424	0.78	2P	+	0.07	2G2	+	0.07	2G1
120	4,5	69747	0.75	2P	+	0.07	2F2	+	0.06	2G2
121	6	69762	0.76	2P	+	0.07	2F2	+	0.06	2G2
122	6	82044	0.64	2D1	+	0.08	2G1	+	0.08	2H
123	4,5	82154	0.65	2D1	+	0.11	2G1	+	0.08	2D3
124	6	82156	0.65	2D1	+	0.11	2G1	+	0.08	2D3
125	4,5	82231	0.64	2D1	+	0.08	2G1	+	0.08	2H
126	4,5	84509	0.56	2D1	+	0.11	2G1	+	0.09	2H

^aIrreducible representation of the C_{2v} group.

TABLE 17. ENERGY LEVELS OF Fe^{3+} IN $\text{Dy}_3\text{Al}_5\text{O}_{12}$
 [Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22745$
 $(Dq = 1556.23, B = 588.45, \text{ and } C = 3413.41)$. All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition						
1	4,5	0.000	1.00	6S	+	0.00	4P	+	0.00 4G
2	6	0.140	1.00	6S	+	0.00	4P	+	0.00 4G
3	4,5	0.255	1.00	6S	+	0.00	4P	+	0.00 4G
4	4,5	8449	0.25	2I	+	0.22	2H	+	0.16 2F1
5	4,5	9185	0.24	2I	+	0.22	2H	+	0.14 2F1
6	6	9435	0.24	4G	+	0.18	2I	+	0.16 2H
7	6	9896	0.50	4G	+	0.29	4P	+	0.05 4F
8	4,5	9910	0.55	4G	+	0.31	4P	+	0.06 4F
9	4,5	10225	0.56	4G	+	0.35	4P	+	0.04 4F
10	6	10348	0.43	4G	+	0.27	4P	+	0.08 2I
11	4,5	10367	0.47	4G	+	0.30	4P	+	0.06 2I
12	4,5	10389	0.56	4G	+	0.35	4P	+	0.04 4F
13	4,5	13344	0.45	4G	+	0.32	4F	+	0.23 4D
14	6	13364	0.45	4G	+	0.32	4F	+	0.22 4D
15	4,5	14602	0.42	4G	+	0.30	4F	+	0.27 4D
16	4,5	14610	0.43	4G	+	0.30	4F	+	0.26 4D
17	6	14611	0.42	4G	+	0.30	4F	+	0.27 4D
18	4,5	14620	0.42	4G	+	0.30	4F	+	0.27 4D
19	4,5	21258	0.52	2I	+	0.25	2H	+	0.13 2F1
20	4,5	21550	0.52	2I	+	0.40	2F1	+	0.05 2F2
21	6	21559	0.53	2I	+	0.23	2H	+	0.12 2F1
22	4,5	218901	0.53	2I	+	0.22	2H	+	0.12 2F1
23	4,5	22488	0.50	4G	+	0.20	2I	+	0.11 2F1
24	6	22672	0.51	4G	+	0.21	2I	+	0.11 2F1
25	4,5	22699	0.72	4G	+	0.12	2I	+	0.07 2F1
26	4,5	22938	0.91	4G	+	0.05	2I	+	0.02 2H
27	4,5	23030	0.93	4G	+	0.04	2I	+	0.01 2H
28	6	23037	0.89	4G	+	0.06	2I	+	0.02 2H
29	6	23188	0.51	4G	+	0.21	2I	+	0.10 2F1
30	4,5	23263	0.50	4G	+	0.22	2I	+	0.10 2F1
31	4,5	23407	0.36	2I	+	0.26	4G	+	0.17 2F1
32	4,5	24508	0.38	4G	+	0.35	4D	+	0.09 2I
33	6	24548	0.37	4G	+	0.36	4D	+	0.09 2I
34	4,5	24677	0.48	4G	+	0.46	4D	+	0.02 4F
35	4,5	24772	0.49	4D	+	0.47	4G	+	0.03 4F
36	6	24966	0.24	4D	+	0.22	4G	+	0.19 2I
37	4,5	25081	0.23	2I	+	0.18	4D	+	0.18 2H
38	4,5	25283	0.52	4D	+	0.36	4G	+	0.04 2I

^aIrreducible representation of the C_{3i} group.

TABLE 17. ENERGY LEVELS OF Fe^{3+} IN $\text{Dy}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22745$
 $(Dq = 1556.23, B = 588.45, \text{ and } C = 3413.41)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
39	6	25294	0.45	4D	+	0.32	4G	+	0.08	2I
40	4,5	26921	0.96	4D	+	0.01	4F	+	0.01	4G
41	6	26935	0.96	4D	+	0.01	4F	+	0.01	4G
42	4,5	26937	0.97	4D	+	0.01	4F	+	0.01	4G
43	4,5	26949	0.97	4D	+	0.01	4F	+	0.01	4G
44	6	28111	0.33	2G2	+	0.19	2F2	+	0.18	2F1
45	4,5	28147	0.31	2G2	+	0.20	2F2	+	0.19	2H
46	4,5	29047	0.31	2G2	+	0.20	2F2	+	0.12	2H
47	4,5	29263	0.27	2G2	+	0.19	2F2	+	0.13	2I
48	6	30697	0.30	2F2	+	0.26	2G2	+	0.15	2D2
49	4,5	30793	0.27	2F2	+	0.27	2G2	+	0.14	2D2
50	4,5	31260	0.32	2I	+	0.32	2G2	+	0.21	2G1
51	6	33422	0.40	4F	+	0.35	4P	+	0.09	2I
52	4,5	33469	0.44	4F	+	0.39	4P	+	0.06	4G
53	4,5	34009	0.37	2I	+	0.19	2D3	+	0.11	2D1
54	6	34133	0.34	2I	+	0.18	2D3	+	0.13	4F
55	4,5	34809	0.49	2I	+	0.17	2G2	+	0.15	4F
56	4,5	34948	0.48	4F	+	0.28	4P	+	0.08	2I
57	6	35072	0.50	4F	+	0.29	4P	+	0.07	4G
58	4,5	35194	0.53	4F	+	0.30	4P	+	0.08	4G
59	4,5	35319	0.44	4F	+	0.25	4P	+	0.11	2I
60	6	35725	0.50	2I	+	0.30	2D3	+	0.06	2D1
61	4,5	35735	0.48	2I	+	0.29	2D3	+	0.06	4F
62	4,5	35819	0.50	2I	+	0.35	2D3	+	0.07	2D1
63	4,5	36911	0.98	4F	+	0.01	2D3	+	0.01	2I
64	6	36919	0.98	4F	+	0.01	2D3	+	0.01	2I
65	6	38021	0.65	2G2	+	0.11	2I	+	0.06	2H
66	4,5	38125	0.67	2G2	+	0.12	2I	+	0.06	2D2
67	6	39391	0.34	2F2	+	0.27	2G2	+	0.15	2I
68	4,5	39462	0.36	2F2	+	0.25	2G2	+	0.14	2I
69	4,5	39822	0.36	2F2	+	0.30	2H	+	0.16	2F1
70	4,5	40070	0.52	2F2	+	0.21	2G2	+	0.21	2I
71	4,5	40420	0.48	2F2	+	0.31	2G2	+	0.12	2I
72	6	40858	0.42	2F2	+	0.31	2G2	+	0.14	2H
73	4,5	40961	0.47	2F2	+	0.38	2G2	+	0.06	2I
74	4,5	41635	0.50	2H	+	0.27	2F1	+	0.09	2G2
75	6	41803	0.44	2H	+	0.23	2F1	+	0.15	2G2
76	4,5	42338	0.19	4F	+	0.19	2F2	+	0.16	4G

TABLE 17. ENERGY LEVELS OF Fe^{3+} IN $\text{Dy}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22745$
 ($Dq = 1556.23$, $B = 588.45$, and $C = 3413.41$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
77	4,5	42543	0.30	4F	+	0.25	4G	+	0.22	4P
78	6	42711	0.37	4F	+	0.31	4G	+	0.27	4P
79	4,5	42739	0.23	4F	+	0.21	2H	+	0.20	4G
80	4,5	42814	0.38	4F	+	0.31	4G	+	0.27	4P
81	4,5	43599	0.56	2S	+	0.27	2G2	+	0.04	4F
82	6	44568	0.39	4F	+	0.29	4G	+	0.19	4P
83	4,5	44638	0.41	4F	+	0.30	4G	+	0.21	4P
84	6	44949	0.30	2D3	+	0.30	2H	+	0.17	2D2
85	4,5	44982	0.33	2D3	+	0.31	2H	+	0.19	2D2
86	4,5	46476	0.36	2H	+	0.23	2F1	+	0.17	2G1
87	4,5	47655	0.64	4F	+	0.21	4D	+	0.11	4G
88	4,5	47746	0.61	4F	+	0.20	4D	+	0.10	4G
89	6	47833	0.55	4F	+	0.19	4D	+	0.09	4G
90	4,5	47913	0.39	4F	+	0.17	2H	+	0.14	4D
91	6	48236	0.26	4F	+	0.21	2H	+	0.11	2F1
92	4,5	48303	0.31	4F	+	0.20	2H	+	0.11	4D
93	6	48357	0.35	4F	+	0.17	2H	+	0.11	4D
94	4,5	48394	0.54	4F	+	0.17	4D	+	0.11	4G
95	4,5	48845	0.23	2F1	+	0.17	2H	+	0.14	2D2
96	6	49022	0.22	2F1	+	0.15	2H	+	0.15	4F
97	4,5	49659	0.28	2F1	+	0.17	2H	+	0.15	2G1
98	4,5	52840	0.28	2H	+	0.22	2G1	+	0.21	2I
99	6	52927	0.27	2H	+	0.23	2G1	+	0.20	2I
100	4,5	53818	0.47	2F1	+	0.27	2I	+	0.17	2F2
101	4,5	53986	0.50	2G1	+	0.20	2H	+	0.12	2I
102	6	54156	0.51	2G1	+	0.20	2H	+	0.12	2I
103	4,5	54910	0.36	2H	+	0.25	2I	+	0.20	2F1
104	4,5	57376	0.50	2D2	+	0.13	2I	+	0.13	2G1
105	6	57665	0.39	2D2	+	0.22	2G1	+	0.14	2I
106	4,5	57700	0.39	2D2	+	0.23	2G1	+	0.14	2I
107	4,5	59133	0.35	2G1	+	0.20	2D2	+	0.11	2H
108	6	59188	0.39	2G1	+	0.17	2D2	+	0.11	2H
109	6	60423	0.32	2D2	+	0.23	2G1	+	0.11	2H
110	4,5	60463	0.33	2D2	+	0.24	2G1	+	0.09	2H
111	4,5	60686	0.67	2G1	+	0.15	2P	+	0.09	2F2
112	4,5	61587	0.26	2H	+	0.22	2D3	+	0.16	2G1
113	6	62295	0.25	2D3	+	0.16	2D2	+	0.16	2H
114	4,5	62410	0.24	2D3	+	0.16	2H	+	0.15	2G1
115	4,5	63258	0.27	2G1	+	0.23	2D1	+	0.15	2G2

TABLE 17. ENERGY LEVELS OF Fe^{3+} IN $\text{Dy}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22745$
 ($Dq = 1556.23$, $B = 588.45$, and $C = 3413.41$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition
116	6	64354	0.48 2G1 + 0.14 2G2 + 0.13 2F2
117	4,5	64482	0.45 2G1 + 0.15 2G2 + 0.11 2D1
118	4,5	66958	0.69 2G1 + 0.17 2S + 0.12 2G2
119	4,5	69574	0.78 2P + 0.07 2G2 + 0.07 2G1
120	4,5	69846	0.73 2P + 0.07 2F2 + 0.06 2G2
121	6	69876	0.74 2P + 0.07 2F2 + 0.06 2G2
122	6	82094	0.63 2D1 + 0.11 2H + 0.05 2G1
123	4,5	82196	0.64 2D1 + 0.10 2H + 0.06 2G1
124	6	82532	0.64 2D1 + 0.13 2G1 + 0.11 2D3
125	4,5	82651	0.64 2D1 + 0.12 2G1 + 0.10 2D3
126	4,5	85155	0.55 2D1 + 0.12 2G1 + 0.09 2H

^aIrreducible representation of the C_{3i} group.

TABLE 18. ENERGY LEVELS OF Fe^{3+} IN $\text{Ho}_3\text{Al}_5\text{O}_{12}$
 [Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22822$
 ($Dq = 1554.85$, $B = 595.85$, and $C = 3399.21$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition
1	4,5	0.000	1.00 6S + 0.00 4P + 0.00 4G
2	6	0.145	1.00 6S + 0.00 4P + 0.00 4G
3	4,5	0.264	1.00 6S + 0.00 4P + 0.00 4G
4	4,5	8262	0.25 2I + 0.23 2H + 0.15 2F1
5	4,5	9118	0.24 2I + 0.22 2H + 0.14 2F1
6	6	9371	0.31 4G + 0.17 4P + 0.15 2I
7	4,5	9758	0.55 4G + 0.31 4P + 0.06 4F
8	6	9793	0.45 4G + 0.26 4P + 0.08 2I
9	4,5	10164	0.54 4G + 0.35 4P + 0.05 4F
10	6	10288	0.41 4G + 0.26 4P + 0.09 2I
11	4,5	10301	0.46 4G + 0.29 4P + 0.06 2I
12	4,5	10337	0.55 4G + 0.35 4P + 0.04 4F
13	4,5	13153	0.46 4G + 0.32 4F + 0.22 4D
14	6	13175	0.46 4G + 0.32 4F + 0.22 4D
15	4,5	14748	0.43 4G + 0.30 4F + 0.26 4D

^aIrreducible representation of the C_{3i} group.

TABLE 18. ENERGY LEVELS OF Fe^{3+} IN $\text{Ho}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F(2) = 52728$,
 $F(4) = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22822$
 $(Dq = 1554.85, B = 595.85, \text{ and } C = 3399.21)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
16	4,5	14755	0.43	4G	+	0.29	4F	+	0.26	4D
17	6	14763	0.42	4G	+	0.29	4F	+	0.26	4D
18	4,5	14774	0.42	4G	+	0.29	4F	+	0.27	4D
19	4,5	21102	0.52	2I	+	0.25	2H	+	0.13	2F1
20	4,5	21464	0.52	2I	+	0.40	2F1	+	0.05	2F2
21	6	21473	0.53	2I	+	0.23	2H	+	0.12	2F1
22	4,5	21798	0.53	2I	+	0.22	2H	+	0.12	2F1
23	4,5	22374	0.42	4G	+	0.23	2I	+	0.13	2F1
24	6	22546	0.37	4G	+	0.26	2I	+	0.13	2F1
25	4,5	22628	0.72	4G	+	0.12	2I	+	0.06	2F1
26	4,5	22867	0.90	4G	+	0.04	2I	+	0.02	2H
27	6	22981	0.81	4G	+	0.08	2I	+	0.03	2F1
28	4,5	23011	0.91	4G	+	0.04	2I	+	0.02	2H
29	6	23117	0.73	4G	+	0.12	2I	+	0.05	2F1
30	4,5	23178	0.61	4G	+	0.17	2I	+	0.07	2F1
31	4,5	23349	0.37	2I	+	0.25	4G	+	0.17	2F1
32	4,5	24489	0.41	4G	+	0.37	4D	+	0.07	2I
33	6	24530	0.41	4G	+	0.38	4D	+	0.07	2I
34	4,5	24634	0.48	4G	+	0.46	4D	+	0.03	4F
35	4,5	24721	0.48	4D	+	0.48	4G	+	0.03	4F
36	6	24992	0.24	2I	+	0.19	4D	+	0.17	2H
37	4,5	25093	0.26	2I	+	0.19	2H	+	0.14	4D
38	4,5	25361	0.54	4D	+	0.36	4G	+	0.03	2I
39	6	25370	0.48	4D	+	0.32	4G	+	0.07	2I
40	4,5	26897	0.95	4D	+	0.02	4F	+	0.01	4G
41	6	26914	0.95	4D	+	0.02	4F	+	0.01	4G
42	4,5	26915	0.96	4D	+	0.02	4F	+	0.01	4G
43	4,5	26929	0.96	4D	+	0.01	4F	+	0.01	4G
44	6	28050	0.32	2G2	+	0.19	2F2	+	0.18	2H
45	4,5	28090	0.30	2G2	+	0.20	2F2	+	0.19	2H
46	4,5	28937	0.24	2G2	+	0.19	2F2	+	0.15	2I
47	4,5	29320	0.33	2G2	+	0.19	2F2	+	0.16	2F1
48	6	30864	0.30	2F2	+	0.27	2G2	+	0.15	2D2
49	4,5	30939	0.27	2G2	+	0.27	2F2	+	0.14	2D2
50	4,5	31338	0.33	2I	+	0.32	2G2	+	0.20	2G1
51	6	33288	0.41	4F	+	0.38	4P	+	0.07	2I
52	4,5	33325	0.44	4F	+	0.42	4P	+	0.07	4G
53	4,5	33978	0.40	2I	+	0.20	2D3	+	0.11	2D1

TABLE 18. ENERGY LEVELS OF Fe^{3+} IN $\text{Ho}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22822$
 ($Dq = 1554.85$, $B = 595.85$, and $C = 3399.21$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
54	6	34079	0.37	2I	+	0.19	2D3	+	0.11	2D1
55	4,5	34831	0.56	2I	+	0.21	2G2	+	0.06	4F
56	4,5	35145	0.44	4F	+	0.26	4P	+	0.10	2I
57	6	35274	0.44	4F	+	0.26	4P	+	0.10	2I
58	4,5	35423	0.50	4F	+	0.29	4P	+	0.08	4G
59	4,5	35543	0.48	4F	+	0.28	4P	+	0.09	4G
60	6	35676	0.44	2I	+	0.26	2D3	+	0.11	4F
61	4,5	35701	0.41	2I	+	0.25	2D3	+	0.14	4F
62	4,5	35787	0.49	2I	+	0.34	2D3	+	0.07	2D1
63	4,5	36972	0.98	4F	+	0.01	2D3	+	0.01	2I
64	6	36981	0.98	4F	+	0.01	2D3	+	0.01	2I
65	6	37892	0.63	2G2	+	0.10	2I	+	0.08	2H
66	4,5	38023	0.65	2G2	+	0.11	2I	+	0.06	2D2
67	6	39266	0.33	2F2	+	0.26	2G2	+	0.16	2I
68	4,5	39323	0.35	2F2	+	0.23	2G2	+	0.15	2I
69	4,5	39515	0.35	2F2	+	0.31	2H	+	0.17	2F1
70	4,5	39945	0.51	2F2	+	0.23	2I	+	0.21	2G2
71	4,5	40554	0.48	2F2	+	0.31	2G2	+	0.11	2I
72	6	40897	0.41	2F2	+	0.31	2G2	+	0.13	2H
73	4,5	41010	0.46	2F2	+	0.38	2G2	+	0.06	2H
74	4,5	41740	0.45	2H	+	0.27	2F1	+	0.11	2G2
75	6	41914	0.40	2H	+	0.22	2F1	+	0.17	2G2
76	4,5	42313	0.34	4F	+	0.28	4G	+	0.24	4P
77	4,5	42451	0.35	4F	+	0.28	4G	+	0.25	4P
78	6	42558	0.38	4F	+	0.30	4G	+	0.26	4P
79	4,5	42648	0.39	4F	+	0.31	4G	+	0.27	4P
80	4,5	42907	0.38	2H	+	0.27	2F2	+	0.13	2F1
81	4,5	43541	0.56	2S	+	0.27	2G2	+	0.04	2G1
82	6	44736	0.25	2D3	+	0.23	2H	+	0.15	2D2
83	4,5	44835	0.26	2D3	+	0.24	2H	+	0.15	2D2
84	6	45005	0.32	4F	+	0.24	4G	+	0.16	4P
85	4,5	45011	0.33	4F	+	0.25	4G	+	0.16	4P
86	4,5	46319	0.35	2H	+	0.24	2F1	+	0.17	2G1
87	4,5	47780	0.63	4F	+	0.22	4D	+	0.11	4G
88	4,5	47878	0.59	4F	+	0.20	4D	+	0.10	4G
89	6	47975	0.53	4F	+	0.18	4D	+	0.09	4G
90	4,5	48086	0.42	4F	+	0.16	4D	+	0.15	2H
91	6	48365	0.31	4F	+	0.15	2H	+	0.11	2F1

TABLE 18. ENERGY LEVELS OF Fe^{3+} IN $\text{Ho}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 52728$,
 $F^{(4)} = 43009$, $\zeta = 370$, $B_{20} = 5143.7$, and $B_{40} = -22822$
 ($Dq = 1554.85$, $B = 595.85$, and $C = 3399.21$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
92	4,5	48428	0.31	4F	+	0.15	2H	+	0.11	2F1
93	6	48616	0.25	4F	+	0.25	2H	+	0.09	2F2
94	4,5	48623	0.44	4F	+	0.14	4D	+	0.13	2H
95	4,5	48925	0.18	4F	+	0.18	2F1	+	0.17	2H
96	6	49099	0.21	4F	+	0.18	2F1	+	0.15	2H
97	4,5	49821	0.29	2F1	+	0.18	2H	+	0.14	2G1
98	4,5	52704	0.28	2H	+	0.22	2I	+	0.19	2F1
99	6	52788	0.28	2H	+	0.22	2I	+	0.19	2G1
100	4,5	53723	0.47	2F1	+	0.27	2I	+	0.17	2F2
101	4,5	54077	0.52	2G1	+	0.19	2H	+	0.11	2I
102	6	54269	0.53	2G1	+	0.19	2H	+	0.12	2I
103	4,5	55174	0.36	2H	+	0.24	2I	+	0.19	2F1
104	4,5	57343	0.52	2D2	+	0.14	2G1	+	0.12	2I
105	6	57587	0.40	2D2	+	0.24	2G1	+	0.13	2I
106	4,5	57606	0.40	2D2	+	0.25	2G1	+	0.13	2I
107	4,5	59073	0.36	2G1	+	0.18	2D2	+	0.11	2H
108	6	59140	0.38	2G1	+	0.16	2D2	+	0.11	2H
109	6	60784	0.32	2D2	+	0.22	2G1	+	0.10	2H
110	4,5	60819	0.35	2D2	+	0.21	2G1	+	0.09	2I
111	4,5	61024	0.66	2G1	+	0.15	2P	+	0.10	2F2
112	4,5	61617	0.27	2H	+	0.19	2D3	+	0.19	2G1
113	6	62513	0.24	2D3	+	0.17	2D2	+	0.15	2H
114	4,5	62616	0.22	2D3	+	0.18	2G1	+	0.16	2H
115	4,5	63276	0.23	2D1	+	0.23	2G1	+	0.16	2D3
116	6	64597	0.48	2G1	+	0.14	2G2	+	0.12	2F2
117	4,5	64744	0.46	2G1	+	0.15	2G2	+	0.10	2D1
118	4,5	67154	0.68	2G1	+	0.17	2S	+	0.12	2G2
119	4,5	69729	0.77	2P	+	0.07	2G2	+	0.07	2G1
120	4,5	69919	0.73	2P	+	0.07	2F2	+	0.06	2G2
121	6	69952	0.73	2P	+	0.07	2F2	+	0.06	2D1
122	6	82122	0.64	2D1	+	0.10	2H	+	0.05	2G1
123	4,5	82235	0.64	2D1	+	0.10	2H	+	0.06	2G1
124	6	83035	0.63	2D1	+	0.13	2G1	+	0.11	2D3
125	4,5	83177	0.62	2D1	+	0.12	2G1	+	0.11	2D3
126	4,5	858278	0.54	2D1	+	0.13	2G1	+	0.08	2H

^aIrreducible representation of the C_{3i} group.

TABLE 19. ENERGY LEVELS OF Fe^{3+} IN $\text{Er}_3\text{Al}_5\text{O}_{12}$
 [Energy levels were calculated with $F(2) = 53254$,
 $F(4) = 42651$, $\zeta = 370$, $B_{20} = 7344.2$, and $B_{40} = -22898$
 ($Dq = 1553.46$, $B = 603.24$, and $C = 3385.00$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
1	4,5	0.000	1.00	6S	+	0.00	4P	+	0.00	4G
2	6	0.174	1.00	6S	+	0.00	4P	+	0.00	4G
3	4,5	0.313	1.00	6S	+	0.00	4P	+	0.00	4G
4	4,5	8050	0.25	2I	+	0.23	2H	+	0.15	2F1
5	4,5	9047	0.24	2I	+	0.21	2H	+	0.14	2F1
6	6	9278	0.37	4G	+	0.21	4P	+	0.11	2I
7	4,5	9598	0.56	4G	+	0.31	4P	+	0.07	4F
8	6	9693	0.39	4G	+	0.23	4P	+	0.10	2I
9	4,5	10085	0.53	4G	+	0.34	4P	+	0.05	4F
10	6	10214	0.38	4G	+	0.24	4P	+	0.10	2I
11	4,5	10217	0.45	4G	+	0.29	4P	+	0.06	2I
12	4,5	10266	0.55	4G	+	0.35	4P	+	0.04	4F
13	4,5	12951	0.47	4G	+	0.32	4F	+	0.21	4D
14	6	12975	0.47	4G	+	0.32	4F	+	0.21	4D
15	4,5	14895	0.44	4G	+	0.29	4F	+	0.25	4D
16	4,5	14906	0.43	4G	+	0.29	4F	+	0.26	4D
17	6	14920	0.43	4G	+	0.29	4F	+	0.26	4D
18	4,5	14936	0.42	4G	+	0.29	4F	+	0.26	4D
19	4,5	20933	0.52	2I	+	0.26	2H	+	0.13	2F1
20	6	21365	0.53	2I	+	0.23	2H	+	0.11	2F1
21	4,5	21367	0.52	2I	+	0.40	2F1	+	0.06	2F2
22	4,5	21674	0.52	2I	+	0.22	2H	+	0.12	2F1
23	4,5	22238	0.35	4G	+	0.26	2I	+	0.14	2F1
24	6	22383	0.30	2I	+	0.25	4G	+	0.15	2F1
25	4,5	22540	0.72	4G	+	0.12	2I	+	0.06	2F1
26	4,5	22777	0.90	4G	+	0.04	2I	+	0.02	4F
27	6	22884	0.79	4G	+	0.08	2I	+	0.03	2F1
28	4,5	22970	0.84	4G	+	0.06	2I	+	0.03	2F1
29	6	23088	0.86	4G	+	0.07	2I	+	0.03	2H
30	4,5	23109	0.76	4G	+	0.11	2I	+	0.04	2F1
31	4,5	23274	0.38	2I	+	0.23	4G	+	0.18	2F1
32	4,5	24458	0.44	4G	+	0.38	4D	+	0.06	2I
33	6	24498	0.44	4G	+	0.40	4D	+	0.05	2I
34	4,5	24583	0.49	4G	+	0.45	4D	+	0.03	4F
35	4,5	24663	0.48	4G	+	0.47	4D	+	0.03	4F
36	6	25024	0.27	2I	+	0.18	2H	+	0.15	4D
37	4,5	25108	0.28	2I	+	0.20	2H	+	0.11	4G
38	4,5	25443	0.56	4D	+	0.35	4G	+	0.03	2I

^aIrreducible representation of the cubic group.

TABLE 19. ENERGY LEVELS OF Fe^{3+} IN $\text{Er}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F(2) = 53254$,
 $F(4) = 42651$, $\zeta = 370$, $B_{20} = 7344.2$, and $B_{40} = -22898$
 ($Dq = 1553.46$, $B = 603.24$, and $C = 3385.00$). All
 quantities are in cm^{-1} .]

No.	IR ^d	Energy	Free ion state composition							
39	6	25451	0.51	4D	+	0.32	4G	+	0.06	2I
40	4,5	26862	0.94	4D	+	0.02	4F	+	0.02	4G
41	6	26881	0.94	4D	+	0.02	4G	+	0.02	4F
42	4,5	26883	0.95	4D	+	0.02	4F	+	0.02	4G
43	4,5	26896	0.94	4D	+	0.02	4G	+	0.02	4F
44	6	27988	0.32	2G2	+	0.19	2F2	+	0.19	2H
45	4,5	28031	0.30	2G2	+	0.19	2F2	+	0.19	2H
46	4,5	28714	0.23	2G2	+	0.17	2I	+	0.17	2F2
47	4,5	29477	0.34	2G2	+	0.19	2F2	+	0.17	2F1
48	6	31028	0.29	2F2	+	0.27	2G2	+	0.14	2D2
49	4,5	31081	0.27	2G2	+	0.26	2F2	+	0.14	2I
50	4,5	31416	0.33	2I	+	0.32	2G2	+	0.19	2G1
51	6	33147	0.41	4P	+	0.41	4F	+	0.06	4G
52	4,5	33176	0.44	4P	+	0.43	4F	+	0.07	4G
53	4,5	33942	0.42	2I	+	0.20	2D3	+	0.11	2D1
54	6	34021	0.39	2I	+	0.20	2D3	+	0.11	2D1
55	4,5	34823	0.58	2I	+	0.23	2G2	+	0.05	2G1
56	4,5	35304	0.26	2I	+	0.25	4F	+	0.16	4P
57	6	35404	0.34	2I	+	0.19	2D3	+	0.19	4F
58	4,5	35630	0.40	4F	+	0.23	4P	+	0.14	2I
59	6	35719	0.35	4F	+	0.19	2I	+	0.19	4P
60	4,5	35724	0.43	2I	+	0.29	2D3	+	0.07	4F
61	4,5	35779	0.40	4F	+	0.23	4P	+	0.13	2I
62	4,5	35844	0.44	4F	+	0.26	4P	+	0.09	2I
63	4,5	37033	0.98	4F	+	0.01	2D3	+	0.01	2I
64	6	37044	0.98	4F	+	0.01	2D3	+	0.00	2I
65	6	37739	0.61	2G2	+	0.10	2H	+	0.09	2I
66	4,5	37895	0.64	2G2	+	0.10	2I	+	0.08	2H
67	6	39134	0.33	2F2	+	0.25	2G2	+	0.17	2I
68	4,5	39155	0.35	2F2	+	0.21	2H	+	0.16	2G2
69	4,5	39217	0.34	2F2	+	0.23	2H	+	0.15	2G2
70	4,5	39813	0.49	2F2	+	0.25	2I	+	0.20	2G2
71	4,5	40688	0.49	2F2	+	0.31	2G2	+	0.11	2I
72	6	40942	0.40	2F2	+	0.32	2G2	+	0.12	2H
73	4,5	41059	0.45	2F2	+	0.38	2G2	+	0.06	2H
74	4,5	41843	0.40	2H	+	0.25	2F1	+	0.13	2G2
75	6	42015	0.34	2H	+	0.22	2F1	+	0.17	2G2
76	4,5	42203	0.37	4F	+	0.28	4G	+	0.25	4P

TABLE 19. ENERGY LEVELS OF Fe^{3+} IN $\text{Er}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 53254$,
 $F^{(4)} = 42651$, $\zeta = 370$, $B_{20} = 7344.2$, and $B_{40} = -22898$
 ($Dq = 1553.46$, $B = 603.24$, and $C = 3385.00$). All
 quantities are in cm^{-1} .]

No.	IR ^d	Energy	Free ion state composition							
77	4,5	42326	0.37	4F	+	0.28	4G	+	0.24	4P
78	6	42410	0.37	4F	+	0.28	4G	+	0.24	4P
79	4,5	42489	0.41	4F	+	0.30	4G	+	0.26	4P
80	4,5	43190	0.39	2H	+	0.32	2F2	+	0.14	2F1
81	4,5	43461	0.55	2S	+	0.27	2G2	+	0.04	2G1
82	6	44680	0.32	2H	+	0.31	2D3	+	0.18	2D2
83	4,5	44772	0.33	2H	+	0.33	2D3	+	0.18	2D2
84	6	45285	0.44	4F	+	0.31	4G	+	0.20	4P
85	4,5	45302	0.45	4F	+	0.32	4G	+	0.20	4P
86	4,5	46163	0.33	2H	+	0.25	2F1	+	0.17	2G1
87	4,5	47929	0.63	4F	+	0.22	4D	+	0.10	4G
88	4,5	48022	0.53	4F	+	0.18	4D	+	0.09	4G
89	6	48120	0.46	4F	+	0.16	4D	+	0.08	4G
90	4,5	48246	0.38	4F	+	0.16	2H	+	0.14	4D
91	6	48449	0.31	4F	+	0.14	2H	+	0.12	2F1
92	4,5	48498	0.36	4F	+	0.13	4D	+	0.11	2F1
93	4,5	48872	0.48	4F	+	0.14	4D	+	0.12	2H
94	6	48885	0.29	4F	+	0.23	2H	+	0.09	4D
95	4,5	49106	0.22	2H	+	0.19	4F	+	0.13	2F1
96	6	49247	0.23	4F	+	0.17	2H	+	0.14	2F1
97	4,5	49980	0.29	2F1	+	0.18	2H	+	0.13	2I
98	4,5	52577	0.28	2H	+	0.22	2I	+	0.20	2F1
99	6	52656	0.28	2H	+	0.23	2I	+	0.20	2F1
100	4,5	53620	0.47	2F1	+	0.27	2I	+	0.17	2F2
101	4,5	54161	0.53	2G1	+	0.18	2H	+	0.11	2I
102	6	54373	0.54	2G1	+	0.19	2H	+	0.11	2I
103	4,5	55451	0.36	2H	+	0.23	2I	+	0.19	2F1
104	4,5	57339	0.53	2D2	+	0.15	2G1	+	0.11	2I
105	6	57513	0.43	2D2	+	0.25	2G1	+	0.12	2I
106	4,5	57515	0.42	2D2	+	0.26	2G1	+	0.12	2I
107	4,5	59017	0.37	2G1	+	0.16	2D2	+	0.11	2H
108	6	59094	0.39	2G1	+	0.14	2D2	+	0.12	2H
109	6	61161	0.32	2D2	+	0.21	2G1	+	0.10	2H
110	4,5	61189	0.37	2D2	+	0.19	2G1	+	0.09	2F2
111	4,5	61372	0.64	2G1	+	0.15	2P	+	0.10	2F2
112	4,5	61649	0.27	2H	+	0.23	2G1	+	0.16	2D3
113	6	62752	0.22	2D3	+	0.17	2D2	+	0.15	2H
114	4,5	62842	0.21	2D3	+	0.21	2G1	+	0.15	2H

TABLE 19. ENERGY LEVELS OF Fe^{3+} IN $\text{Er}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F(2) = 53254$,
 $F(4) = 42651$, $\zeta = 370$, $B_{20} = 7344.2$, and $B_{40} = -22898$
 ($Dq = 1553.46$, $B = 603.24$, and $C = 3385.00$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition
115	4,5	63312	0.23 2D1 + 0.19 2G1 + 0.18 2D3
116	6	64840	0.49 2G1 + 0.14 2G2 + 0.11 2F2
117	4,5	65007	0.46 2G1 + 0.15 2G2 + 0.09 2F2
118	4,5	67365	0.68 2G1 + 0.16 2S + 0.12 2G2
119	4,5	69846	0.73 2P + 0.06 2F2 + 0.06 2G1
120	6	69997	0.71 2P + 0.08 2D1 + 0.07 2F2
121	4,5	70015	0.76 2P + 0.06 2G1 + 0.06 2G2
122	6	82172	0.64 2D1 + 0.10 2H + 0.05 2G1
123	4,5	82297	0.65 2D1 + 0.10 2H + 0.05 2F1
124	6	83613	0.61 2D1 + 0.13 2G1 + 0.11 2D3
125	4,5	83774	0.60 2D1 + 0.12 2G1 + 0.11 2D3
126	4,5	86522	0.53 2D1 + 0.14 2G1 + 0.08 2H

^aIrreducible representation of the C_{3i} group.

TABLE 20. ENERGY LEVELS OF Fe^{3+} IN $\text{Tm}_3\text{Al}_5\text{O}_{12}$
 [Energy levels were calculated with $F(2) = 53517$,
 $F(4) = 42471$, $\zeta = 370$, $B_{20} = 8444.4$ and $B_{40} = -22975$
 ($Dq = 1552.10$, $B = 610.65$, and $C = 3370.71$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition
1	4,5	0.000	1.00 6S + 0.00 4P + 0.00 4G
2	6	0.191	1.00 6S + 0.00 4P + 0.00 4G
3	4,5	0.333	1.00 6S + 0.00 4P + 0.00 4G
4	4,5	7815	0.25 2I + 0.23 2H + 0.15 2F1
5	4,5	8967	0.23 2I + 0.21 2H + 0.14 2F1
6	6	9159	0.43 4G + 0.23 4P + 0.08 2I
7	4,5	9429	0.56 4G + 0.30 4P + 0.08 4F
8	6	9594	0.35 4G + 0.21 4P + 0.12 2I
9	4,5	9987	0.51 4G + 0.33 4P + 0.05 4F
10	4,5	10116	0.44 4G + 0.28 4P + 0.06 2I
11	6	10125	0.36 4G + 0.23 4P + 0.11 2I
12	4,5	10178	0.54 4G + 0.35 4P + 0.05 4F
13	4,5	12738	0.48 4G + 0.32 4F + 0.20 4D
14	6	12763	0.47 4G + 0.32 4F + 0.20 4D

^aIrreducible representation of the C_{3i} group.

TABLE 20. ENERGY LEVELS OF Fe^{3+} IN $\text{Tm}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 53517$,
 $F^{(4)} = 42471$, $\zeta = 370$, $B_{20} = 8444.4$, and $B_{40} = -22975$
 $(Dq = 1552.10, B = 610.65, \text{ and } C = 3370.71)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
15	4,5	15044	0.44	4G	+	0.28	4F	+	0.25	4D
16	4,5	15059	0.44	4G	+	0.28	4F	+	0.25	4D
17	6	15078	0.43	4G	+	0.28	4F	+	0.25	4D
18	4,5	15101	0.43	4G	+	0.28	4F	+	0.26	4D
19	4,5	20753	0.51	2I	+	0.26	2H	+	0.13	2F1
20	6	21232	0.53	2I	+	0.23	2H	+	0.11	2F1
21	4,5	21260	0.51	2I	+	0.40	2F1	+	0.06	2F2
22	4,5	21511	0.51	2I	+	0.21	2H	+	0.12	2F1
23	4,5	22090	0.29	4G	+	0.29	2I	+	0.14	2F1
24	6	22189	0.32	2I	+	0.17	4G	+	0.16	2F1
25	4,5	22434	0.72	4G	+	0.11	2I	+	0.06	2F1
26	4,5	22667	0.89	4G	+	0.03	2I	+	0.03	4F
27	6	22766	0.82	4G	+	0.06	2I	+	0.02	2H
28	4,5	22889	0.77	4G	+	0.09	2I	+	0.04	2F1
29	4,5	23073	0.88	4G	+	0.06	2I	+	0.02	2H
30	6	23075	0.91	4G	+	0.05	2I	+	0.02	2H
31	4,5	23182	0.38	2I	+	0.21	4G	+	0.18	2F1
32	4,5	24417	0.47	4G	+	0.39	4D	+	0.05	2I
33	6	24455	0.47	4G	+	0.40	4D	+	0.04	2I
34	4,5	24526	0.50	4G	+	0.44	4D	+	0.03	4F
35	4,5	24601	0.49	4G	+	0.46	4D	+	0.03	4F
36	6	25057	0.30	2I	+	0.19	2H	+	0.12	4D
37	4,5	25124	0.30	2I	+	0.21	2H	+	0.11	2D3
38	4,5	25528	0.58	4D	+	0.35	4G	+	0.02	2I
39	6	25534	0.53	4D	+	0.32	4G	+	0.06	2I
40	4,5	26818	0.92	4D	+	0.03	4G	+	0.03	4F
41	6	26839	0.92	4D	+	0.03	4G	+	0.03	4F
42	4,5	26843	0.93	4D	+	0.03	4G	+	0.03	4F
43	4,5	26854	0.93	4D	+	0.03	4G	+	0.02	4F
44	6	27926	0.31	2G2	+	0.19	2H	+	0.18	2F2
45	4,5	27969	0.29	2G2	+	0.19	2H	+	0.18	2F2
46	4,5	28473	0.22	2G2	+	0.18	2I	+	0.15	2F2
47	4,5	29641	0.34	2G2	+	0.19	2F2	+	0.18	2F1
48	6	31187	0.29	2F2	+	0.27	2G2	+	0.14	2D2
49	4,5	31216	0.27	2G2	+	0.26	2F2	+	0.15	2I
50	4,5	31493	0.34	2I	+	0.32	2G2	+	0.19	2G1
51	6	33001	0.43	4P	+	0.40	4F	+	0.07	4G
52	4,5	33024	0.46	4P	+	0.42	4F	+	0.07	4G

TABLE 20. ENERGY LEVELS OF Fe^{3+} IN $\text{Tm}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 53517$,
 $F^{(4)} = 42471$, $\zeta = 370$, $B_{20} = 8444.4$, and $B_{40} = -22975$
 $(Dq = 1552.10, B = 610.65, \text{ and } C = 3370.71)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
53	4,5	33900	0.44	2I	+	0.20	2D3	+	0.11	2D1
54	6	33958	0.41	2I	+	0.20	2D3	+	0.11	2D1
55	4,5	34795	0.58	2I	+	0.23	2G2	+	0.06	2G1
56	4,5	35320	0.43	2I	+	0.26	2D3	+	0.07	4F
57	6	35366	0.48	2I	+	0.27	2D3	+	0.06	2D1
58	4,5	35699	0.49	2I	+	0.33	2D3	+	0.06	2D1
59	4,5	35839	0.46	4F	+	0.28	4P	+	0.09	4G
60	6	35939	0.47	4F	+	0.28	4P	+	0.09	4G
61	4,5	36035	0.48	4F	+	0.29	4P	+	0.10	4G
62	4,5	36130	0.49	4F	+	0.31	4P	+	0.11	4G
63	4,5	37095	0.98	4F	+	0.01	2D3	+	0.00	2I
64	6	37106	0.98	4F	+	0.01	2D3	+	0.00	2G2
65	6	37565	0.59	2G2	+	0.12	2H	+	0.08	2I
66	4,5	37744	0.62	2G2	+	0.10	2H	+	0.09	2I
67	4,5	38853	0.34	2F2	+	0.33	2H	+	0.18	2F1
68	6	38998	0.32	2F2	+	0.24	2G2	+	0.18	2I
69	4,5	39040	0.34	2F2	+	0.22	2G2	+	0.16	2I
70	4,5	39675	0.48	2F2	+	0.27	2I	+	0.19	2G2
71	4,5	40819	0.49	2F2	+	0.32	2G2	+	0.10	2I
72	6	40990	0.39	2F2	+	0.32	2G2	+	0.11	2H
73	4,5	41108	0.44	2F2	+	0.38	2G2	+	0.05	2H
74	4,5	41923	0.29	2H	+	0.21	2F1	+	0.12	2G2
75	6	42082	0.22	2H	+	0.16	2F1	+	0.14	2G2
76	4,5	42084	0.38	4F	+	0.27	4G	+	0.23	4P
77	4,5	42209	0.34	4F	+	0.25	4G	+	0.21	4P
78	6	42294	0.29	4F	+	0.21	4G	+	0.17	4P
79	4,5	42338	0.41	4F	+	0.28	4G	+	0.24	4P
80	4,5	43356	0.53	2S	+	0.26	2G2	+	0.04	2G1
81	4,5	43495	0.39	2H	+	0.32	2F2	+	0.13	2F1
82	6	44578	0.34	2H	+	0.31	2D3	+	0.17	2D2
83	4,5	44674	0.34	2H	+	0.32	2D3	+	0.17	2D2
84	6	45612	0.46	4F	+	0.32	4G	+	0.19	4P
85	4,5	45631	0.46	4F	+	0.32	4G	+	0.19	4P
86	4,5	46010	0.32	2H	+	0.27	2F1	+	0.17	2G1
87	4,5	48099	0.61	4F	+	0.22	4D	+	0.10	4G
88	4,5	48145	0.34	4F	+	0.13	2H	+	0.12	4D
89	6	48232	0.29	4F	+	0.15	2H	+	0.14	2F1
90	4,5	48363	0.39	4F	+	0.15	4D	+	0.13	2H

TABLE 20. ENERGY LEVELS OF Fe^{3+} IN $\text{Im}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F(2) = 53517$,
 $F(4) = 42471$, $\zeta = 370$, $B_{20} = 8444.4$, and $B_{40} = -22975$
 $(B_4 = 1552.10, B = 610.65, \text{ and } C = 3370.71)$. All
quantities are in cm^{-1} .]

No.	IR^a	Energy	Free ion state composition							
91	6	48535	0.42	4F	+	0.16	4D	+	0.09	2H
92	4,5	48615	0.50	4F	+	0.19	4D	+	0.08	4G
93	4,5	49121	0.54	4F	+	0.16	4D	+	0.12	4G
94	6	49142	0.39	4F	+	0.18	2H	+	0.11	4D
95	4,5	49354	0.28	2H	+	0.14	4F	+	0.13	2F2
96	6	49463	0.22	2H	+	0.20	4F	+	0.12	2F1
97	4,5	50130	0.30	2F1	+	0.18	2H	+	0.14	2I
98	4,5	52463	0.27	2H	+	0.23	2I	+	0.22	2F1
99	6	52536	0.27	2H	+	0.23	2I	+	0.22	2F1
100	4,5	53512	0.46	2F1	+	0.27	2I	+	0.17	2F2
101	4,5	54237	0.53	2G1	+	0.18	2H	+	0.11	2I
102	6	54469	0.54	2G1	+	0.18	2H	+	0.11	2I
103	4,5	55741	0.36	2H	+	0.22	2I	+	0.18	2F1
104	4,5	57364	0.55	2D2	+	0.16	2G1	+	0.10	2I
105	4,5	57428	0.45	2D2	+	0.26	2G1	+	0.11	2I
106	6	57444	0.45	2D2	+	0.25	2G1	+	0.11	2I
107	4,5	58972	0.39	2G1	+	0.13	2D2	+	0.11	2H
108	6	59060	0.39	2G1	+	0.12	2D2	+	0.12	2H
109	6	61550	0.32	2D2	+	0.21	2G1	+	0.10	2I
110	4,5	61566	0.38	2D2	+	0.16	2G1	+	0.10	2F2
111	4,5	61645	0.30	2G1	+	0.24	2H	+	0.13	2D3
112	4,5	61765	0.59	2G1	+	0.13	2P	+	0.09	2F2
113	6	63008	0.20	2D3	+	0.17	2D2	+	0.16	2G1
114	4,5	63082	0.24	2G1	+	0.19	2D3	+	0.15	2H
115	4,5	63373	0.22	2D1	+	0.20	2D3	+	0.16	2G1
116	6	65077	0.48	2G1	+	0.14	2G2	+	0.10	2F2
117	4,5	65266	0.46	2G1	+	0.16	2G2	+	0.09	2D3
118	4,5	67590	0.68	2G1	+	0.16	2S	+	0.11	2G2
119	4,5	69886	0.68	2P	+	0.10	2D1	+	0.07	2F2
120	6	70024	0.68	2P	+	0.10	2D1	+	0.07	2F2
121	4,5	70186	0.78	2P	+	0.07	2G1	+	0.07	2G2
122	6	82245	0.65	2D1	+	0.10	2H	+	0.05	2G1
123	4,5	82382	0.65	2D1	+	0.10	2H	+	0.05	2F1
124	6	84260	0.59	2D1	+	0.12	2G1	+	0.11	2D3
125	4,5	84437	0.58	2D1	+	0.12	2G1	+	0.11	2D3
126	4,5	87239	0.52	2D1	+	0.14	2G1	+	0.08	2D2

^aIrreducible representation of the C_{3i} group.

TABLE 21. ENERGY LEVELS OF Fe^{3+} IN $\text{Yb}_3\text{Al}_5\text{O}_{12}$
 [Energy levels were calculated with $F(2) = 53780$,
 $F(4) = 42292$, $\zeta = 370$, $B_{20} = 9544.6$, and $B_{40} = -23052$
 ($Dq = 1550.75$, $B = 618.05$, and $C = 3356.51$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
1	4,5	0.000	1.00	6S	+	0.00	4P	+	0.00	4G
2	6	0.208	1.00	6S	+	0.00	4P	+	0.00	4G
3	4,5	0.347	1.00	6S	+	0.00	4P	+	0.00	4G
4	4,5	7562	0.25	2I	+	0.23	2H	+	0.15	2F1
5	4,5	8878	0.22	2I	+	0.20	2H	+	0.14	4G
6	6	9018	0.48	4G	+	0.25	4P	+	0.07	4F
7	4,5	9254	0.56	4G	+	0.30	4P	+	0.08	4F
8	6	9491	0.33	4G	+	0.20	4P	+	0.13	2I
9	4,5	9874	0.49	4G	+	0.33	4P	+	0.06	4F
10	4,5	10001	0.42	4G	+	0.27	4P	+	0.07	2I
11	6	10024	0.32	4G	+	0.21	4P	+	0.13	2I
12	4,5	10072	0.53	4G	+	0.35	4P	+	0.05	4F
13	4,5	12513	0.48	4G	+	0.32	4F	+	0.19	4D
14	6	12540	0.48	4G	+	0.32	4F	+	0.19	4D
15	4,5	15195	0.45	4G	+	0.28	4F	+	0.24	4D
16	4,5	15214	0.44	4G	+	0.28	4F	+	0.25	4D
17	6	15239	0.44	4G	+	0.27	4F	+	0.25	4D
18	4,5	15269	0.44	4G	+	0.27	4F	+	0.25	4D
19	4,5	20564	0.51	2I	+	0.27	2H	+	0.13	2F1
20	6	21071	0.52	2I	+	0.22	2H	+	0.11	2F1
21	4,5	21142	0.51	2I	+	0.40	2F1	+	0.06	2F2
22	4,5	21309	0.48	2I	+	0.20	2H	+	0.12	2F1
23	4,5	21937	0.31	2I	+	0.25	4G	+	0.14	2F1
24	6	21977	0.33	2I	+	0.17	2F1	+	0.15	2H
25	4,5	22308	0.72	4G	+	0.10	2I	+	0.05	2F1
26	4,5	22535	0.88	4G	+	0.04	4F	+	0.03	2I
27	6	22633	0.83	4G	+	0.04	2I	+	0.03	4F
28	4,5	22775	0.74	4G	+	0.09	2I	+	0.04	2H
29	4,5	23056	0.86	4G	+	0.07	2I	+	0.03	2F1
30	6	23068	0.93	4G	+	0.03	2I	+	0.01	2H
31	4,5	23075	0.35	2I	+	0.27	4G	+	0.17	2F1
32	4,5	24371	0.49	4G	+	0.39	4D	+	0.04	2I
33	6	24406	0.49	4G	+	0.40	4D	+	0.03	4F
34	4,5	24467	0.51	4G	+	0.43	4D	+	0.03	4F
35	4,5	24537	0.51	4G	+	0.44	4D	+	0.04	4F
36	6	25089	0.31	2I	+	0.19	2H	+	0.10	2D3
37	4,5	25138	0.31	2I	+	0.21	2H	+	0.12	2D3
38	4,5	25615	0.60	4D	+	0.34	4G	+	0.02	2I

^aIrreducible representation of the C_{3i} group.

TABLE 21. ENERGY LEVELS OF Fe^{3+} IN $\text{Yb}_3\text{Al}_5\text{O}_{12}$ (cont'd)
 [Energy levels were calculated with $F^{(2)} = 53780$,
 $F^{(4)} = 42292$, $\zeta = 370$, $B_{20} = 9544.6$, and $B_{40} = -23052$
 ($Dq = 1550.75$, $B = 618.05$, and $C = 3356.51$). All
 quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition						
39	6	25619	0.55	4D	+	0.32	4G	+	0.05 2I
40	4,5	26769	0.90	4D	+	0.04	4G	+	0.03 4F
41	6	26792	0.90	4D	+	0.04	4G	+	0.03 4F
42	4,5	26798	0.91	4D	+	0.04	4G	+	0.03 4F
43	4,5	26806	0.91	4D	+	0.04	4G	+	0.03 4F
44	6	27866	0.30	2G2	+	0.19	2H	+	0.18 2F2
45	4,5	27896	0.27	2G2	+	0.18	2H	+	0.17 2F2
46	4,5	28232	0.22	2G2	+	0.18	2I	+	0.15 2F2
47	4,5	29808	0.34	2G2	+	0.18	2F2	+	0.18 2F1
48	6	31341	0.28	2F2	+	0.27	2G2	+	0.14 2D2
49	4,5	31342	0.27	2G2	+	0.25	2F2	+	0.16 2I
50	4,5	31570	0.34	2I	+	0.31	2G2	+	0.18 2G1
51	6	32855	0.45	4P	+	0.40	4F	+	0.07 4G
52	4,5	32870	0.48	4P	+	0.41	4F	+	0.07 4G
53	4,5	33855	0.45	2I	+	0.20	2D3	+	0.11 2D1
54	6	33892	0.43	2I	+	0.20	2D3	+	0.11 2D1
55	4,5	34753	0.57	2I	+	0.23	2G2	+	0.06 2G1
56	4,5	35244	0.47	2I	+	0.29	2D3	+	0.07 2D1
57	6	35263	0.49	2I	+	0.29	2D3	+	0.07 2D1
58	4,5	35665	0.49	2I	+	0.33	2D3	+	0.06 2D1
59	4,5	36114	0.48	4F	+	0.30	4P	+	0.10 4G
60	6	36228	0.47	4F	+	0.30	4P	+	0.11 4G
61	4,5	36339	0.47	4F	+	0.31	4P	+	0.12 4G
62	4,5	36445	0.46	4F	+	0.32	4P	+	0.13 4G
63	4,5	37157	0.98	4F	+	0.01	2D3	+	0.00 2I
64	6	37166	0.97	4F	+	0.01	2G2	+	0.01 2D3
65	6	37380	0.56	2G2	+	0.14	2H	+	0.08 2I
66	4,5	37574	0.59	2G2	+	0.12	2H	+	0.08 2I
67	4,5	38520	0.34	2F2	+	0.33	2H	+	0.19 2F1
68	6	38861	0.31	2F2	+	0.24	2G2	+	0.19 2I
69	4,5	38890	0.34	2F2	+	0.21	2G2	+	0.18 2I
70	4,5	39533	0.47	2F2	+	0.29	2I	+	0.19 2G2
71	4,5	40948	0.49	2F2	+	0.32	2G2	+	0.10 2I
72	6	41041	0.39	2F2	+	0.33	2G2	+	0.10 2H
73	4,5	41156	0.44	2F2	+	0.37	2G2	+	0.05 2I
74	4,5	41926	0.31	4F	+	0.20	4G	+	0.17 4P
75	4,5	41980	0.39	4F	+	0.26	4G	+	0.21 4P
76	6	42040	0.37	4F	+	0.23	4G	+	0.20 4P

TABLE 21. ENERGY LEVELS OF Fe^{3+} IN $\text{Yb}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 53780$,
 $F^{(4)} = 42292$, $\zeta = 370$, $B_{20} = 9544.6$, and $B_{40} = -23052$
 $(Dq = 1550.75, B = 618.05, \text{ and } C = 3356.51)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
77	4,5	42134	0.29	4F	+	0.20	4G	+	0.16	4P
78	4,5	42222	0.29	4F	+	0.19	4G	+	0.15	4P
79	6	42284	0.31	2H	+	0.21	2F1	+	0.15	2G2
80	4,5	43241	0.53	2S	+	0.27	2G2	+	0.04	2D2
81	4,5	43792	0.41	2H	+	0.33	2F2	+	0.12	2F1
82	6	44466	0.35	2H	+	0.30	2D3	+	0.16	2D2
83	4,5	44570	0.35	2H	+	0.31	2D3	+	0.16	2D2
84	4,5	45861	0.30	2H	+	0.29	2F1	+	0.17	2G1
85	6	45956	0.47	4F	+	0.33	4G	+	0.18	4P
86	4,5	45975	0.47	4F	+	0.33	4G	+	0.18	4P
87	4,5	48175	0.24	2H	+	0.19	2F1	+	0.15	2G1
88	6	48264	0.23	2H	+	0.19	2F1	+	0.15	2G1
89	4,5	48292	0.61	4F	+	0.23	4D	+	0.10	4G
90	4,5	48506	0.55	4F	+	0.21	4D	+	0.09	4G
91	6	48686	0.54	4F	+	0.21	4D	+	0.09	4G
92	4,5	48809	0.55	4F	+	0.22	4D	+	0.09	4G
93	4,5	49371	0.58	4F	+	0.16	4D	+	0.13	4G
94	6	49392	0.46	4F	+	0.14	2H	+	0.13	4D
95	4,5	49625	0.31	2H	+	0.15	2F2	+	0.11	4F
96	6	49716	0.27	2H	+	0.16	4F	+	0.12	2F2
97	4,5	50265	0.30	2F1	+	0.18	2H	+	0.16	2I
98	4,5	52366	0.26	2H	+	0.24	2F1	+	0.23	2I
99	6	52433	0.26	2H	+	0.23	2F1	+	0.23	2I
100	4,5	53401	0.45	2F1	+	0.27	2I	+	0.17	2F2
101	4,5	54310	0.53	2G1	+	0.18	2H	+	0.12	2I
102	6	54558	0.53	2G1	+	0.18	2H	+	0.12	2I
103	4,5	56042	0.36	2H	+	0.22	2I	+	0.18	2F1
104	4,5	57340	0.49	2D2	+	0.24	2G1	+	0.11	2I
105	6	57380	0.48	2D2	+	0.25	2G1	+	0.11	2I
106	4,5	57433	0.55	2D2	+	0.18	2G1	+	0.09	2I
107	4,5	58948	0.41	2G1	+	0.11	2H	+	0.10	2D2
108	6	59047	0.41	2G1	+	0.12	2H	+	0.09	2D2
109	4,5	61672	0.27	2H	+	0.26	2G1	+	0.12	2D3
110	6	61950	0.33	2D2	+	0.20	2G1	+	0.10	2I
111	4,5	61956	0.40	2D2	+	0.15	2G1	+	0.11	2F2
112	4,5	62125	0.64	2G1	+	0.15	2P	+	0.11	2F2
113	6	63277	0.19	2D3	+	0.18	2G1	+	0.17	2D2
114	4,5	63320	0.24	2G1	+	0.18	2D3	+	0.12	2H

TABLE 21. ENERGY LEVELS OF Fe^{3+} IN $\text{Yb}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 53780$,
 $F^{(4)} = 42292$, $\zeta = 370$, $B_{20} = 9544.6$, and $B_{40} = -23052$
 $(Dq = 1550.75, B = 618.05, \text{ and } C = 3356.51)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
115	4,5	63477	0.22	2D3	+	0.17	2D1	+	0.16	2G1
116	6	65300	0.48	2G1	+	0.14	2G2	+	0.09	2F2
117	4,5	65512	0.45	2G1	+	0.16	2G2	+	0.10	2D3
118	4,5	67829	0.67	2G1	+	0.15	2S	+	0.11	2G2
119	4,5	69898	0.65	2P	+	0.12	2D1	+	0.07	2G1
120	6	70045	0.66	2P	+	0.12	2D1	+	0.07	2F2
121	4,5	70397	0.79	2P	+	0.07	2G1	+	0.07	2G2
122	6	82339	0.65	2D1	+	0.09	2H	+	0.05	2D3
123	4,5	82490	0.65	2D1	+	0.10	2H	+	0.05	2F1
124	6	84968	0.57	2D1	+	0.12	2G1	+	0.12	2D3
125	4,5	85159	0.56	2D1	+	0.12	2G1	+	0.12	2P
126	4,5	87977	0.51	2D1	+	0.15	2G1	+	0.08	2D2

^aIrreducible representation of the C_{3i} group.

TABLE 22. ENERGY LEVELS OF Fe^{3+} IN $\text{Lu}_3\text{Al}_5\text{O}_{12}$

[Energy levels were calculated with $F^{(2)} = 54043$,
 $F^{(4)} = 42113$, $\zeta = 370$, $B_{20} = 10645$, and $B_{40} = -23127$
 $(Dq = 1549.34, B = 625.45, \text{ and } C = 3342.30)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
1	4,5	0.000	1.00	6S	+	0.00	4P	+	0.00	4G
2	6	0.225	1.00	6S	+	0.00	4P	+	0.00	4G
3	4,5	0.356	1.00	6S	+	0.00	4P	+	0.00	4G
4	4,5	7293	0.25	2I	+	0.23	2H	+	0.15	2F1
5	4,5	8776	0.21	2I	+	0.19	2H	+	0.16	4G
6	6	8861	0.51	4G	+	0.26	4P	+	0.08	4F
7	4,5	9074	0.56	4G	+	0.29	4P	+	0.08	4F
8	6	9381	0.32	4G	+	0.20	4P	+	0.13	2I
9	4,5	9747	0.48	4G	+	0.32	4P	+	0.06	4D
10	4,5	9874	0.40	4G	+	0.26	4P	+	0.07	2I
11	6	9916	0.29	4G	+	0.18	4P	+	0.14	2I
12	4,5	9952	0.52	4G	+	0.35	4P	+	0.06	4F
13	4,5	12280	0.49	4G	+	0.32	4F	+	0.19	4D
14	6	12309	0.49	4G	+	0.32	4F	+	0.18	4D

^aIrreducible representation of the C_{3i} group.

TABLE 22. ENERGY LEVELS OF Fe^{3+} IN $\text{Lu}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 54043$,
 $F^{(4)} = 42113$, $\zeta = 370$, $B_{20} = 10645$, and $B_{40} = -23127$
 (Dq = 1549.34, B = 625.45, and C = 3342.30). All
 quantities are in cm^{-1}]

No.	IR ^a	Energy	Free ion state composition							
15	4,5	15349	0.45	4G	+	0.27	4F	+	0.24	4D
16	4,5	15373	0.45	4G	+	0.27	4F	+	0.24	4D
17	6	15403	0.45	4G	+	0.27	4F	+	0.24	4D
18	4,5	15439	0.44	4G	+	0.26	4F	+	0.25	4D
19	4,5	20364	0.50	2I	+	0.27	2H	+	0.13	2F1
20	6	20880	0.51	2I	+	0.22	2H	+	0.11	2F1
21	4,5	21010	0.49	2I	+	0.36	2F1	+	0.06	2F2
22	4,5	21074	0.47	2I	+	0.17	2H	+	0.16	2F1
23	6	21755	0.35	2I	+	0.17	2H	+	0.16	2F1
24	4,5	21782	0.34	2I	+	0.23	4G	+	0.15	2H
25	4,5	22161	0.72	4G	+	0.10	2I	+	0.05	2F1
26	4,5	22380	0.86	4G	+	0.05	4F	+	0.04	4D
27	6	22482	0.83	4G	+	0.04	4F	+	0.04	2I
28	4,5	22638	0.73	4G	+	0.09	2I	+	0.04	2H
29	4,5	22947	0.40	2I	+	0.19	2F1	+	0.17	4G
30	4,5	23051	0.95	4G	+	0.03	2I	+	0.01	2H
31	6	23062	0.95	4G	+	0.03	2I	+	0.01	2H
32	4,5	24321	0.51	4G	+	0.38	4D	+	0.03	4F
33	6	24353	0.52	4G	+	0.39	4D	+	0.03	4F
34	4,5	24408	0.53	4G	+	0.41	4D	+	0.03	4F
35	4,5	24474	0.52	4G	+	0.42	4D	+	0.04	4F
36	6	25114	0.32	2I	+	0.19	2H	+	0.11	2D3
37	4,5	25146	0.31	2I	+	0.21	2H	+	0.12	2D3
38	4,5	25704	0.62	4D	+	0.33	4G	+	0.02	2I
39	6	25706	0.57	4D	+	0.31	4G	+	0.04	2I
40	4,5	26715	0.87	4D	+	0.05	4G	+	0.03	4F
41	6	26742	0.89	4D	+	0.05	4G	+	0.03	4F
42	4,5	26750	0.90	4D	+	0.06	4G	+	0.03	4F
43	4,5	26754	0.90	4D	+	0.05	4G	+	0.03	4F
44	4,5	27779	0.23	2G2	+	0.16	2I	+	0.14	2F2
45	6	27811	0.30	2G2	+	0.20	2H	+	0.17	2F2
46	4,5	28033	0.24	2G2	+	0.16	2F2	+	0.15	2I
47	4,5	29974	0.34	2G2	+	0.18	2F2	+	0.18	2F1
48	4,5	31458	0.27	2G2	+	0.23	2F2	+	0.17	2I
49	6	31487	0.27	2G2	+	0.27	2F2	+	0.13	2D2
50	4,5	31646	0.35	2I	+	0.31	2G2	+	0.17	2G1
51	6	32708	0.47	4P	+	0.39	4F	+	0.07	4G
52	4,5	32716	0.49	4P	+	0.40	4F	+	0.07	4G

TABLE 22. ENERGY LEVELS OF Fe^{3+} IN $\text{Lu}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F(2) = 54043$,
 $F(4) = 42113$, $\zeta = 370$, $B_{20} = 10645$, and $B_{40} = -23127$
 $(Dq = 1549.34, B = 625.45, \text{ and } C = 3342.30)$. All
quantities are in cm^{-1} .]

No.	IR ^d	Energy	Free ion state composition							
53	4,5	33808	0.46	2I	+	0.19	2D3	+	0.10	2D1
54	6	33821	0.44	2I	+	0.20	2D3	+	0.10	2D1
55	4,5	34696	0.56	2I	+	0.22	2G2	+	0.06	2G1
56	4,5	35132	0.46	2I	+	0.29	2D3	+	0.07	2D1
57	6	35132	0.48	2I	+	0.29	2D3	+	0.07	2D1
58	4,5	35633	0.49	2I	+	0.32	2D3	+	0.06	2D1
59	4,5	36417	0.45	4F	+	0.31	4P	+	0.12	4G
60	6	36538	0.44	4F	+	0.31	4P	+	0.12	4G
61	4,5	36658	0.44	4F	+	0.32	4P	+	0.13	4G
62	4,5	36768	0.43	4F	+	0.33	4P	+	0.14	4G
63	6	37162	0.44	2G2	+	0.20	4F	+	0.13	2H
64	4,5	37218	0.97	4F	+	0.01	2G2	+	0.01	2D3
65	6	37259	0.80	4F	+	0.10	2G2	+	0.03	2H
66	4,5	37392	0.56	2G2	+	0.14	2H	+	0.07	2I
67	4,5	38181	0.34	2F2	+	0.33	2H	+	0.19	2F1
68	6	38725	0.31	2F2	+	0.23	2G2	+	0.20	2I
69	4,5	38743	0.33	2F2	+	0.21	2G2	+	0.19	2I
70	4,5	39388	0.45	2F2	+	0.31	2I	+	0.18	2G2
71	4,5	41070	0.48	2F2	+	0.31	2G2	+	0.09	2I
72	6	41092	0.38	2F2	+	0.33	2G2	+	0.09	2H
73	4,5	41201	0.42	2F2	+	0.37	2G2	+	0.05	2I
74	4,5	41844	0.41	4F	+	0.24	4G	+	0.19	4P
75	4,5	41883	0.44	4F	+	0.26	4G	+	0.21	4P
76	6	41930	0.44	4F	+	0.26	4G	+	0.21	4P
77	4,5	42034	0.42	4F	+	0.25	4G	+	0.20	4P
78	4,5	42233	0.34	2H	+	0.26	2F1	+	0.11	2G2
79	6	42342	0.32	2H	+	0.24	2F1	+	0.18	2G2
80	4,5	43112	0.52	2S	+	0.26	2G2	+	0.05	2D2
81	4,5	44081	0.44	2H	+	0.31	2F2	+	0.10	2F1
82	6	44350	0.35	2H	+	0.29	2D3	+	0.15	2D2
83	4,5	44463	0.36	2H	+	0.29	2D3	+	0.15	2D2
84	4,5	45722	0.31	2F1	+	0.26	2H	+	0.18	2F2
85	6	46309	0.48	4F	+	0.33	4G	+	0.17	4P
86	4,5	46328	0.48	4F	+	0.33	4G	+	0.18	4P
87	4,5	48135	0.29	2H	+	0.21	2F1	+	0.17	2G1
88	6	48240	0.27	2H	+	0.20	2F1	+	0.17	2G1
89	4,5	48501	0.60	4F	+	0.23	4D	+	0.10	4G
90	4,5	48705	0.59	4F	+	0.23	4D	+	0.10	4G

TABLE 22. ENERGY LEVELS OF Fe^{3+} IN $\text{Lu}_3\text{Al}_5\text{O}_{12}$ (cont'd)

[Energy levels were calculated with $F^{(2)} = 54043$,
 $F^{(4)} = 42113$, $\zeta = 370$, $B_{20} = 10645$, and $B_{40} = -23127$
 $(Dq = 1549.34$, $B = 625.45$, and $C = 3342.30)$. All
quantities are in cm^{-1} .]

No.	IR ^a	Energy	Free ion state composition							
91	6	48892	0.58	4F	+	0.23	4D	+	0.10	4G
92	4,5	49038	0.56	4F	+	0.23	4D	+	0.09	4G
93	4,5	49625	0.59	4F	+	0.16	4D	+	0.14	4G
94	6	49639	0.49	4F	+	0.13	4D	+	0.12	2H
95	4,5	49890	0.34	2H	+	0.15	2F2	+	0.11	4F
96	6	49974	0.29	2H	+	0.15	4F	+	0.13	2F2
97	4,5	50379	0.31	2F1	+	0.18	2H	+	0.17	2I
98	4,5	52290	0.25	2H	+	0.25	2F1	+	0.23	2I
99	6	52350	0.25	2F1	+	0.25	2H	+	0.23	2I
100	4,5	53286	0.45	2F1	+	0.27	2I	+	0.17	2F2
101	4,5	54381	0.52	2G1	+	0.17	2H	+	0.12	2I
102	6	54643	0.53	2G1	+	0.18	2H	+	0.12	2I
103	4,5	56353	0.36	2H	+	0.21	2I	+	0.17	2F1
104	4,5	57258	0.51	2D2	+	0.23	2G1	+	0.10	2I
105	6	57317	0.51	2D2	+	0.23	2G1	+	0.10	2I
106	4,5	57534	0.55	2D2	+	0.19	2G1	+	0.08	2I
107	4,5	58959	0.44	2G1	+	0.11	2H	+	0.08	2G2
108	6	59062	0.44	2G1	+	0.12	2H	+	0.09	2G2
109	4,5	61680	0.28	2G1	+	0.26	2H	+	0.10	2I
110	4,5	62346	0.41	2D2	+	0.13	2G1	+	0.12	2F2
111	6	62358	0.33	2D2	+	0.19	2G1	+	0.10	2I
112	4,5	62507	0.63	2G1	+	0.15	2P	+	0.12	2F2
113	4,5	63502	0.21	2D3	+	0.17	2D1	+	0.15	2G1
114	6	63555	0.21	2G1	+	0.17	2D3	+	0.17	2D2
115	4,5	63677	0.26	2G1	+	0.19	2D3	+	0.13	2H
116	6	65501	0.47	2G1	+	0.14	2G2	+	0.08	2F2
117	4,5	65737	0.44	2G1	+	0.16	2G2	+	0.10	2D3
118	4,5	68080	0.67	2G1	+	0.15	2S	+	0.11	2G2
119	4,5	69915	0.62	2P	+	0.14	2D1	+	0.08	2G1
120	6	70075	0.63	2P	+	0.14	2D1	+	0.07	2G1
121	4,5	70628	0.79	2P	+	0.07	2G1	+	0.07	2G2
122	6	82452	0.65	2D1	+	0.09	2H	+	0.05	2D3
123	4,5	82616	0.66	2D1	+	0.09	2H	+	0.05	2F1
124	6	85730	0.55	2D1	+	0.13	2P	+	0.12	2G1
125	4,5	85932	0.54	2D1	+	0.14	2P	+	0.12	2G1
126	4,5	88734	0.50	2D1	+	0.16	2G1	+	0.09	2D2

^aIrreducible representation of the C_{3i} group.

4. DISCUSSION, CONCLUSION, AND PLANS

The final Slater parameters $F^{(2)}$ given in table 14 shows a slight increase in going from Gd to Lu. However, the Slater parameters $F^{(4)}$ shows a decrease over the same range. Since the shift in the Slater integrals is given [17] by $\Delta F^{(2)} = -\rho_2^2 S^{(2)}$ and $\Delta F^{(4)} = -\rho_4^2 S^{(4)}$ and table 13 shows that $S^{(2)}$ and $S^{(4)}$ increase slightly in going from Gd through Lu in the series, this would predict that $F^{(2)}$ and $F^{(4)}$ decrease through the series. This contradiction would indicate that either improvement in the theory or more extensive experimental data are necessary to ascertain the trend of the $F^{(k)}$ through the series of compounds. The only crystal field parameter to change significantly is B_{20} (table 14). Since this parameter has been determined by the lattice sum parameters, A_{20} , and not by the optical spectra, this trend cannot be taken too seriously.

The purpose of tables 15 through 22 is to present realistic estimates to the spectra of Fe^{3+} in the RAG host materials for $R = Gd$ through Lu . Hopefully, these results will aid in any further experimental efforts to measure the Fe^{3+} spectra more accurately. Further improvements in the theory will have to await better experimental results.

During the course of our work we did a preliminary investigation of Co^{3+} [18], Mn^{3+} [19], and Ni^{3+} [20], but were unable to obtain agreement of our calculation with the reported results. We cannot explain this disagreement; possibly the authors' severe round off (in the hundreds of cm^{-1}) of their reported calculations and of their experimental data made a fitting impossible.

ACKNOWLEDGEMENT

The authors wish to thank summer students Ron Lee, Ken Wong, and Glen Lee for performing most of the computations. We also wish to thank Richard P. Leavitt for writing the programs used in the calculation of the energy levels.

LITERATURE CITED

1. V. V. Osiko, A. M. Prokhorov, and I. A. Shcherbakov, Active Media of Solid-State Lasers, *Izv. Akad. Nauk SSSR Ser. Fiz.* 44 (1980), 1698.
2. E. V. Zharikov, N. N. Il'ichev, V. V. Laptev, A. A. Malyutin, V. G. Ostroumov, P. P. Pashinin, A. S. Pimenov, V. A. Smirnov, and I. A. Shcherbakov, Spectral, Luminescence, and Lasing Properties of Gadolinium Scandium Gallium Garnet Crystals Activated with Neodymium and Chromium Ions, *Sov. J. Quantum Electron.* 13 (1983), 82.
3. A. L. Denisov, V. G. Ostroumov, Z. S. Saidov, V. A. Smirnov, and I. A. Shcherbakov, Spectral and Luminescence Properties of Cr^{3+} and Nd^{3+} Ions in Gallium Garnet Crystals, *J. Opt. Soc. Am.* B3 (1986), 95. Also, V. G. Ostroumov, Yu. S. Privis, V. A. Smirnov, and I. A. Shcherbakov, Sensitizing of Nd^{3+} Luminescence by Cr^{3+} in Gallium Garnets, *J. Opt. Soc. Am.* B3 (1986), 81.

LITERATURE CITED (cont'd)

4. P. F. Moulton, Recent Advances in Solid State Lasers, in Digest of Conferences on Lasers and Electro-Optics '84, Optical Society of America, Washington, D.C. (1984), 76.
5. P. A. Arsenev, D. T. Sviridov, and R. K. Sviridova, Spectra of Rare Earth Metal Garnets Containing Iron Ions, Sov. Phys. Crystallogr. 17 (1972), 352.
6. International Tables for X-Ray Crystallography, Vol. I. Symmetry Groups, Kynoch, Birmingham, England, U.K. (1969).
7. C. A. Morrison and R. P. Leavitt, Handbook on the Physics and Chemistry of Rare Earths, Vol. 5, eds K. A. Gschneider and L. Eyring, North Holland, New York (1982).
8. R. P. Leavitt, On the Role of Certain Rotation Invariants in Crystal-Field Theory, J. Chem. Phys. 77 (1982), 1661.
9. P.H.M. Uylings, A.J.J. Raassen, and J. F. Wyart, Energies of N Equivalent Electrons Expressed in Terms of Two-Electron Energies and Independent Three-Electron Parameters: A New Complete Set of Orthogonal Operators: II. Application of $3d^N$ Configurations, J. Phys. B17 (1984), 4103.
10. G. Racah, Theory of Complex Spectra IV, Phys. Rev. 76 (1949), 1352.
11. S. Fraga, L.M.S. Saxena, and J. Karwowski, Physical Science Data: 5. Handbook of Atomic Data, Elsevier, New York (1976). Also see C. A. Morrison and R. G. Schmalbach, Approximate Values of $\langle r^k \rangle$ for the Divalent, Trivalent, and Quadrivalent Ions with the $3d^N$ Electronic Configuration, Harry Diamond Laboratories, HDL-TL-85-3 (July 1985).
12. K. Rajnak and B. G. Wybourne, Configuration Interaction Effects in l^N Configurations, Phys. Rev. 132 (1963), 280.
13. R. E. Trees, $4f^3$ and $4f^2d$ Configurations of Doubly Ionized Praseodymium (PrIII), J. Opt. Soc. Am. 54 (1964), 651.
14. R. M. Macfarlane, Analysis of the Spectrum of d^3 Ions in Trigonal Crystal Fields, J. Chem. Phys. 39 (1963), 3118.
15. C. W. Nielson and G. F. Koster, Spectroscopic Coefficients for p^n , d^n and f^n Configurations, Massachusetts Institute of Technology, Cambridge, MA (1963).
16. E. Konig and S. Kremer, Ligand Field Energy Diagrams, Plenum Press, New York (1977).
17. C. A. Morrison, R. P. Leavitt, and A. F. Hansen, Host Materials for Transition-Metal Ions with the nd^N Electronic Configuration, Harry Diamond Laboratories, HDL-DS-85-1 (October 1985).

LITERATURE CITED (cont'd)

18. P. A. Arsenev and N. L. Perlova, Properties of Cobalt Ions in the Lattice of Rare Earth Aluminum Garnets, Phys. Stat. Sol. 42 (1970), K89.
19. P. A. Arsenev and V. K. Medvedeva, Mn³⁺ Ion Properties in the Lattice of Rare Earth Aluminum Garnets, Krist. and Tech. 5 (1970), K25.
20. P. A. Arsenev, N. L. Perlova, and D. T. Sviridov, Absorption Spectra of Nickel Ions in the Crystals of Some Rare Earth Aluminum Garnets, Sov. Phys. Crystallogr. 16 (1971), 196.

DISTRIBUTION

ADMINISTRATOR
DEFENSE TECHNICAL INFORMATION
CENTER
ATTN DTIC-DDA (12 COPIES)
CAMERON STATION, BUILDING 5
ALEXANDRIA, VA 22314

DIRECTOR
NIGHT VISION & ELECTRO-OPTICS
LABORATORY
ATTN TECHNICAL LIBRARY
ATTN R. BUSER
ATTN A. PINTO
ATTN J. HABERSAT
FT BELVOIR, VA 22060

DIRECTOR
DEFENSE ADVANCED RESEARCH
PROJECTS AGENCY
ATTN J. FRIEBELE
1400 WILSON BLVD
ARLINGTON, VA 22209

DIRECTOR
DEFENSE NUCLEAR AGENCY
ATTN TECH LIBRARY
WASHINGTON, DC 20305

UNDER SECRETARY OF DEFENSE RES
& ENGINEERING
ATTN TECHNICAL LIBRARY, 3C128
WASHINGTON, DC 20301

OFFICE OF THE DEPUTY CHIEF OF STAFF,
FOR RESEARCH, DEVELOPMENT,
& ACQUISITION
DEPARTMENT OF THE ARMY
ATTN DAMA-ARZ-A, CHIEF SCIENTIST,
L. CAMERON
ATTN DAMA-ARZ-B, I. R. HERSHNER
WASHINGTON, DC 20310

COMMANDER
US ARMY ARMAMENT MUNITIONS &
CHEMICAL COMMAND (AMCCOM)
US ARMY ARMAMENT RESEARCH &
DEVELOPMENT CENTER
ATTN DRDAR-TSS, STINFO DIV
DOVER, NJ 07801

COMMANDER
ATMOSPHERIC SCIENCES LABORATORY
ATTN TECHNICAL LIBRARY
WHITE SANDS MISSILE RANGE, NM
88002

DIRECTOR
US ARMY BALLISTIC RESEARCH
LABORATORY
ATTN DRDAR-TSB-S (STINFO)
ABERDEEN PROVING GROUND, MD
21005

DIRECTOR
US ARMY ELECTRONICS WARFARE
LABORATORY
ATTN J. CHARLTON
ATTN DELET-DD
FT MONMOUTH, NJ 07703

COMMANDING OFFICER
USA FOREIGN SCIENCE &
TECHNOLOGY CENTER
FEDERAL OFFICE BUILDING
ATTN DRXST-BS, BASIC SCIENCE
DIV
CHARLOTTESVILLE, VA 22901

COMMANDER
US ARMY MATERIALS & MECHANICS
RESEARCH CENTER
ATTN DRXMR-TL, TECH LIBRARY
WATERTOWN, MA 02172

US ARMY MATERIEL COMMAND
5001 EISENHOWER AVE
ALEXANDRIA, VA 22333-0001

US ARMY MATERIEL SYSTEMS
ANALYSIS ACTIVITY
ATTN DRXSY-MP (LIBRARY)
ABERDEEN PROVING GROUND, MD
21005

COMMANDER
US ARMY MISSILE & MUNITIONS
CENTER & SCHOOL
ATTN ATSK-CTD-F
ATTN DRDMI-TB, REDSTONE SCI
INFO CENTER
REDSTONE ARSENAL, AL 35809

COMMANDER
US ARMY RESEARCH OFFICE
(DURHAM)
PO BOX 12211
ATTN ROBERT J. LONTZ
ATTN M. STROSIO
ATTN M. CIFTAN
ATTN B. D. GUENTHER

DISTRIBUTION (cont'd)

COMMANDER
US ARMY RESEARCH OFFICE
(DURHAM) (cont'd)
ATTN CHARLES BOGOSIAN
RESEARCH TRIANGLE PARK, NC
27709

COMMANDER
US ARMY RSCH & STD GRP (EUROPE)
FPO NEW YORK 09510

COMMANDER
US ARMY TEST & EVALUATION COMMAND
ATTN D. H. SLINNEY
ATTN TECH LIBRARY
ABERDEEN PROVING GROUND, MD
21005

COMMANDER
US ARMY TROOP SUPPORT COMMAND
ATTN DRXRES-RTL, TECH LIBRARY
NATICK, MA 01762

COMMANDER
ATTN DRSEL-WL-MS, ROBERT NELSON
WHITE SANDS MISSILE RANGE, NM
88002

OFFICE OF NAVAL RESEARCH
ATTN J. MURDAY
ARLINGTON, VA 22217

DIRECTOR
NAVAL RESEARCH LABORATORY
ATTN CODE 2620, TECH LIBRARY BR
ATTN CODE 5554, F. BARTOLI
ATTN CODE 5554, L. ESTEROWITZ
ATTN CODE 5554, R. E. ALLEN
WASHINGTON, DC 20375

COMMANDER
NAVAL WEAPONS CENTER
ATTN CODE 3854, R. SCHWARTZ
ATTN CODE 3854, M. HILLS
ATTN CODE 3844, M. NADLER
ATTN CODE 385, R. L. ATKINS
ATTN CODE 343, TECHNICAL
INFORMATION DEPARTMENT
CHINA LAKE, CA 93555

AIR FORCE OFFICE OF SCIENTIFIC
RESEARCH
ATTN MAJOR H. V. WINSOR, USAF
BOLLING AFB
WASHINGTON, DC 20332

HQ, USAF/SAMI
WASHINGTON, DC 20330

DEPARTMENT OF COMMERCE
NATIONAL BUREAU OF STANDARDS
ATTN LIBRARY
WASHINGTON, DC 20234

DIRECTOR
ADVISORY GROUP ON ELECTRON DEVICES
ATTN SECTRY, WORKING GROUP D
201 VARICK STREET
NEW YORK, NY 10013

AEROSPACE CORPORATION
PO BOX 92957
ATTN M. BIRNBAUM
ATTN N. C. CHANG
LOS ANGELES, CA 90009

COLORADO STATE UNIVERSITY
PHYSICS DEPARTMENT
ATTN S. KERN
FORT COLLINS, CO 80523

ALLIED
ADVANCED APPLICATION DEPT
ATTN A. BUDGOR
31717 LA TIEMDA DRIVE
WESTLAKE VILLAGE, CA 91362

AMES LABORATORY DOE
IOWA STATE UNIVERSITY
ATTN K. A. GSCHNEIDNER, JR. (2 COPIES)
AMES, IA 50011

ARGONNE NATIONAL LABORATORY
ATTN W. T. CARNALL
ATTN H. M. CROSSWHITE
9700 SOUTH CASS AVENUE
ARGONNE, IL 60439

ARIZONA STATE UNIVERSITY
DEPT OF CHEMISTRY
ATTN L. EYRING
TEMPE, AZ 85281

BRIMROSE CORP OF AMERICA
ATTN R. G. ROSEMEIER
7527 BELAIR ROAD
BALTIMORE, MD 21236

CARNEGIE MELLON UNIVERSITY
SCHENLEY PARK
ATTN PHYSICS & EE, J. O. ARTMAN
PITTSBURGH, PA 15213

ENGINEERING SOCIETIES LIBRARY
ATTN ACQUISITIONS DEPT
345 EAST 47TH STREET
NEW YORK, NY 10017

DISTRIBUTION (cont'd)

IBM RESEARCH DIVISION
ALMADEN RESEARCH CENTER
ATTN R. M. MACFARLANE
MAIL STOP K32 802(D)
650 HARRY ROAD
SAN JOSE, CA 95120

JOHNS HOPKINS UNIVERSITY
DEPT OF PHYSICS
ATTN B. R. JUDD
BALTIMORE, MD 21218

KALAMAZOO COLLEGE
DEPT OF PHYSICS
ATTN K. RAJNAK
KALAMAZOO, MI 49007

DIRECTOR
LAWRENCE RADIATION LABORATORY
ATTN MARVIN J. WEBER
ATTN HELMUT A. KOEHLER
ATTN W. KRUPKE
LIVERMORE, CA 94550

MARTIN MARIETTA
ATTN F. CROWNE
ATTN R. LEAVITT
ATTN J. LITTLE
ATTN T. WORCHESKY
ATTN D. WORTMAN
1450 SOUTH ROLLING ROAD
BALTIMORE, MD 21227

MASSACHUSETTS INSTITUTE OF
TECHNOLOGY
CRYSTAL PHYSICS LABORATORY
ATTN H. P. JENSSEN
ATTN A. LINZ
CAMBRIDGE, MA 02139

MASSACHUSETTS INSTITUTE OF
TECHNOLOGY
77 MASS AVE
ROOM 26-251
ATTN V. BAGNATO
CAMBRIDGE, MA 02139

MIT LINCOLN LAB
PO BOX 73
ATTN PETER MOULTON,
ATTN B. AULL
LEXINGTON, MA 02173

DEPARTMENT OF MECHANICAL, INDUSTRIAL,
& AEROSPACE ENGINEERING
PO BOX 909
ATTN S. TEMKIN
PISCATAWAY, NJ 08854

UNIVERSITY OF MICHIGAN
COLLEGE OF ENGINEERING NORTH CAMPUS
DEPARTMENT OF NUCLEAR ENGINEERING
ATTN CHIHIRO KIKUCHI
ANN ARBOR, MI 48104

NATIONAL OCEANIC & ATMOSPHERIC ADM
ENVIRONMENTAL RESEARCH LABS
ATTN LIBRARY, R-51, TECH RPTS
BOULDER, CO 80302

OAK RIDGE NATIONAL LABORATORY
ATTN R. G. HAIRE
OAK RIDGE, TN 37830

OKLAHOMA STATE UNIVERSITY
DEPT OF PHYSICS
ATTN R. C. POWELL
STILLWATER, OK 74078

PENNSYLVANIA STATE UNIVERSITY
MATERIALS RESEARCH LABORATORY
ATTN W. B. WHITE
ATTN B. K. CHANDRASEKHAR
UNIVERSITY PARK, PA 16802

SAN JOSE STATE UNIVERSITY
DEPARTMENT OF PHYSICS
ATTN J. B. GRUBER
SAN JOSE, CA 95192

SCIENCE APPLICATIONS, INC
ATTN T. ALLIK
1710 GOODRIDGE DRIVE
MCLEAN, VA 22102

SETON HALL UNIVERSITY
CHEMISTRY DEPARTMENT
ATTN H. BRITTAIN
SOUTH ORANGE, NJ 07099

PRINCETON UNIVERSITY
DEPARTMENT OF CHEMISTRY
ATTN D. S. McCLURE
PRINCETON, NJ 08544

UNIVERSITY OF MINNESOTA, DULUTH
DEPARTMENT OF CHEMISTRY
ATTN L. C. THOMPSON
DULUTH, MN 55812

UNIVERSITY OF VIRGINIA
DEPT OF CHEMISTRY
ATTN DR. F. S. RICHARDSON (2 COPIES)
ATTN DR. M. REID
CHARLOTTESVILLE, VA 22901

DISTRIBUTION (cont'd)

UNION CARBIDE CORP
ATTN M. R. KOKTA
ATTN J. H. W. LIAW
750 SOUTH 32ND STREET
WASHOUGAL, WA 98671

US ARMY LABORATORIES COMMAND
ATTN TECHNICAL DIRECTOR, AMSLC-CT

INSTALLATION SUPPORT ACTIVITY
ATTN HDL LIBRARY, SLCIS-IM-TL (3 COPIES)
ATTN HDL LIBRARY, SLCIS-IM-TL (WOODBIDGE)
ATTN LEGAL OFFICE, SLCIS-CC
ATTN S. ELBAUM, SLCIS-CC

USAISC
ATTN RECORD COPY, ASNC-ADL-TS
ATTN TECHNICAL REPORTS BRANCH,
ASNC-ADL-TR

HARRY DIAMOND LABORATORIES
ATTN D/DIVISION DIRECTORS
ATTN CHIEF, SLCHD-NW-E
ATTN CHIEF, SLCHD-NW-EC
ATTN CHIEF, SLCHD-NW-ED
ATTN CHIEF, SLCHD-NW-EE
ATTN CHIEF, SLCHD-NW-R
ATTN CHIEF, SLCHD-NW-RA
ATTN CHIEF, SLCHD-NW-RC
ATTN CHIEF, SLCHD-NW-RE
ATTN CHIEF, SLCHD-NW-RH
ATTN CHIEF, SLCHD-NW-RI
ATTN CHIEF, SLCHD-NW-P
ATTN CHIEF, SLCHD-PO
ATTN CHIEF, SLCHD-RT-C
ATTN CHIEF, SLCHD-RT-RS
ATTN CHIEF, SLCHD-RT-RA
ATTN CHIEF, SLCHD-TT
ATTN WALTER, SANDRA, SLCIS-CP-TD

HARRY DIAMOND LABORATORIES
(cont'd)
ATTN WILLIS, B., SLCHD-IT-EB
ATTN ZABLUDOWSKI, B., SLCHD-IT-EB
ATTN HERSHALL, P., SLCHD-MI-S
ATTN KENYON, C. S., SLCHD-NW-EC
ATTN MILETTA J. R., SLCHD-NW-EC
ATTN McLEAN, F. B., SLCHD-NW-RC
ATTN SATTTLER, J., SLCHD-PO-P
ATTN LIBELO, L., SLCHD-RT-AB
ATTN BENCIVENGA, A. A., SLCHD-RT-RC
ATTN KULPA, S., SLCHD-RT-CB
ATTN NEMARICH, J., SLCHD-RT-CB
ATTN WEBER, B., SLCHD-RT-CB
ATTN BAHDER, T., SLCHD-RT-RA
ATTN BENCIVENGA, B. SLCHD-RT-RD
ATTN BRODY, P., SLCHD-RT-RA
ATTN BRUNO, J., SLCHD-RT-RA (10 COPIES)
ATTN DROPKIN, H., SLCHD-RT-RA
ATTN EDWARDS, SLCHD-RT-RA
ATTN HALL, K., SLCHD-RT-RA
ATTN HANSEN, A., SLCHD-RT-RA
ATTN HAY, G., SLCHD-RT-RA
ATTN KATZEN, E., SLCHD-RT-RA
ATTN NEIFELD, R., SLCHD-RT-RA
ATTN PENNISE, C., SLCHD-RT-RA
ATTN SCHMALBACH, R., SLCHD-RT-RA
ATTN SEMENDY, F., SLCHD-RT-RA
ATTN SIMONIS, G., SLCHD-RT-RA
ATTN SIMPSON, T., SLCHD-RT-RA
ATTN STEAD, M., SLCHD-RT-RA
ATTN STELLATO, J., SLCHD-RT-RA
ATTN TOBIN, M., SLCHD-RT-RA
ATTN TURNER, G., SLCHD-RT-RA (10 COPIES)
ATTN WONG, B., SLCHD-RT-RA
ATTN WORTMAN, D., SLCHD-RT-RA
ATTN GARVIN, C., SLCHD-RT-RB
ATTN GOFF, J., SLCHD-RT-RB
ATTN MORRISON, C., SLCHD-RT-RA (10 COPIES)

END

9-87

Dtic