

AD-A184 886

STRUCTURE OF THERMOTROPIC POLYESTERS WITH LARGE
SUBSTITUENTS(U) CONNECTICUT UNIV STORRS INST OF
MATERIALS SCIENCE H H CHIN ET AL. 27 AUG 87
N00014-86-K-0772


1/1

UNCLASSIFIED

F/G 7/6

NL





DTIC FILE COPY

OFFICE OF NAVAL RESEARCH
CONTRACT NO. N00014-86-K-0772
TECHNICAL REPORT NO. 4

Structure of Thermotropic Polyesters with
Large Substituents

by

H. H. Chin, L. V. Azaroff,
A. Furukawa*, and R. W. Lenz*



Prepared for Publication

in

Molecular Crystals and Liquid Crystals

Liquid Crystalline Polymer Research Center
Institute of Materials Science, U-136
The University of Connecticut
Storrs, CT 06268

*Department of Chemical Engineering
University of Massachusetts, Amherst, MA

August 27, 1987

REPRODUCTION IN WHOLE OR IN PART IS PERMITTED FOR ANY
PURPOSE OF THE UNITED STATES GOVERNMENT.

THIS DOCUMENT HAS BEEN APPROVED FOR PUBLIC RELEASE
AND SALE; ITS DISTRIBUTION IS UNLIMITED.

Unclassified

SECURITY CLASSIFICATION OF THIS PAGE

ADA184086

REPORT DOCUMENTATION PAGE

1a REPORT SECURITY CLASSIFICATION Unclassified		1b RESTRICTIVE MARKINGS None	
2a SECURITY CLASSIFICATION AUTHORITY		3 DISTRIBUTION/AVAILABILITY OF REPORT Approved for Public Release, Distribution Unlimited	
2b DECLASSIFICATION/DOWNGRADING SCHEDULE			
4 PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report No. 4		5 MONITORING ORGANIZATION REPORT NUMBER(S)	
6a NAME OF PERFORMING ORGANIZATION University of Connecticut	6b OFFICE SYMBOL (if applicable)	7a NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c ADDRESS (City, State, and ZIP Code) Institute of Materials Science, U-136 97 N. Eagleville Road Storrs, CT 06268		7b ADDRESS (City, State, and ZIP Code) 800 North Quincy Avenue Arlington, VA 22217	
8a NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research	8b OFFICE SYMBOL (if applicable) ONR	9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-86-K-0772	
8c ADDRESS (City, State, and ZIP Code) 800 North Quincy Avenue Arlington, VA 22217		10 SOURCE OF FUNDING NUMBERS	
		PROGRAM ELEMENT NO	PROJECT NO
		TASK NO	WORK UNIT ACCESSION NO
11 TITLE (Include Security Classification) Structure of Thermotropic Polyesters with Large Substituents			
12 PERSONAL AUTHOR(S) H. H. Chin, L. V. Azaroff, A. Furukawa and R. W. Lenz			
13a TYPE OF REPORT Interim	13b TIME COVERED FROM 08/01/87 TO 08/27/87	14 DATE OF REPORT (Year, Month, Day) 1987-08-27	15 PAGE COUNT 12
16 SUPPLEMENTARY NOTATION Prepared for publication in Molecular Crystals and Liquid Crystals Presented in the International Conference on Liquid Crystal Polymers, Bordeaux, 07/20-24/87			
17 COSATI CODES		18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB GROUP	
		Thermotropic Polyesters	
		X-ray Diffraction	
19 ABSTRACT (Continue on reverse if necessary and identify by block number)			
Thermotropic aromatic polyesters were aligned by drawing from nematic melts and by quenching in a magnetic field of 15 tesla and subsequently examined by x-ray diffraction. The degree of alignment obtained depended slightly on the substituent (H, F, Cl, Br, CH₃, NO₂) present with the highest degree of alignment observed when the arylsulfonyl substituted group contained in the para-position H or F and the lowest when it contained Br or CH₃.			
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT ☐ DTIC USERS		21 ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a NAME OF RESPONSIBLE INDIVIDUAL Dr. Kenneth J. Wynne		22b TELEPHONE (Include Area Code) (202) 696-4410	22c OFFICE SYMBOL ONR

STRUCTURE OF THERMOTROPIC POLYESTERS WITH LARGE SUBSTITUENTS

H. H. CHIN and L. V. AZAROFF
Institute of Materials Science, University of
Connecticut, Storrs, 06268 USA
A. FURUKAWA and R. W. LENZ
Chemical Engineering Dept., University of
Massachusetts, Amherst, 01003 USA

Abstract. Thermotropic aromatic polyesters were aligned by drawing from nematic melts and by quenching in a magnetic field of 15 tesla and subsequently examined by x-ray diffraction. The degree of alignment obtained depended slightly on the substituent (H, F, Cl, Br, CH₃, NO₂) present with the highest degree of alignment³ observed when the arylsulfonyl substituted group contained in the para-position H or F and the lowest when it contained Br or CH₃.

INTRODUCTION



Substituent groups in extended linear polymers serve to reduce their melting points as do flexible spacer groups and other modifications introduced along the main chain. Lenz¹ has suggested that lateral substituents may have steric and polar effects: they may decrease the molecular anisotropy common to all liquid crystalline compounds and polymers,² destabilizing the mesophase thereby, or they may stabilize the mesophase through dipolar intermolecular interactions.³ In some cases, however, it has been suggested that steric effects may increase the thermal stability of a mesophase by interlocking effects.⁴

* Publication No. LCPRC 8701 of the LCP Research Center supported, in part, by ONR Grant N00014-86-K-0772.



ADDITIONAL	
NTIS (GPO)	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Date	
Approved for	
Signature	
DTIC	
COPY	
INSPECTED	
A-1	

The present study was undertaken to determine the effect of different lateral substituents on the molecular packing in the nematic mesophase of thermotropic polyesters based on a triad ester mesogenic unit containing an arylsulfonyl substituted hydroquinone group and a decamethylene spacer group of the following structure:



The arylsulfonyl groups were expected to show large steric and polar effects.

EXPERIMENTAL PROCEDURE

All six polymers in this study were first examined by DSC to determine their thermal transition points (Table I) which agreed, within experimental error, with those reported previously.³ The molecular weight averages of these polymers were determined next. All GPC curves, Fig. 1, except that for the NO₂ substituent, which did not dissolve fully in dichloromethane, contained a large peak corresponding to the polymer present and subsidiary peaks for the oligomers present. The latter were calibrated using a polystyrene standard and the molecular weight average of the polymer was determined by subsequent extrapolation from these values, Table II.

The polymers were packed inside glass and quartz capillaries having circular and square cross sections (1mm diam.) to detect surface-induced alignments, if present.

STRUCTURE OF THERMOTROPIC POLYESTERS




FIGURE 1. Gel-permeation chromatogram for Cl substituent.

X-ray diffraction showed that the final samples were amorphous as were the original polymers. Several capillaries containing the same polymer were placed inside a special furnace and heated to about 10-20°C above the melting point (T_m in Table I) in a superconducting magnet (field strength 15 tesla) at the Francis Bitter National Magnet Laboratory at M.I.T. and, following several hours at that temperature, quenched by cooling in air. In addition,

TABLE I. Thermal transition points (°C).

Substituent at X	T_g	T_m	T_i
H	87	100	170
CH ₃	83	102	142
F	79	95	161
Cl	85	101	154
Br	85	93	147
NO ₂	80	91	153

TABLE II. Molecular weight average.

Substituent at X	Weight average
H	10,800
CH ₃	11,500
F	9,000
Cl	8,400
Br	8,300

fibers were drawn directly from the nematic melts. All of these samples were examined in a Buerger precession camera equipped with a bent-crystal monochromator using Co or Fe K α radiations, before and after further annealing for several hours at temperatures slightly below their respective melting points.

RESULTS AND DISCUSSION

Well aligned monodomain samples were obtained both by quenching the nematic mesophase in the magnet and by forming a nematic glass by drawing a fiber directly from the nematic melt, Figs. 2 and 3. The stronger x-ray exposure in Fig. 3 shows the meridional reflections more clearly but, as can be seen in Table III, several orders were recorded for most the polymers examined with only minor variations relatable to the different substituents. Annealing the samples below their melting points did not enhance significantly the alignments of magnetically ordered samples. On the other hand, annealing the nematic-glass fibers did increase the alignment in all polymers except those containing NO₂ and Br substituents which remained unaltered. These differences cannot be considered



FIGURE 2. Normal-beam photograph of quenched F-substituted polymer (Fe K α).

to be very significant, however, because the 'absence' of a reflection may be caused by the relative length of the effective x-ray exposures which were affected by the exposure time and the relative thickness (absorption) of the nematic glass fibers.

On the whole, no significant alignment effect can be attributed to the wall effect of the capillaries although,




FIGURE 3. Normal-beam photograph of nematic glass fiber of F-substituted polymer (filtered Co K α).

qualitatively, magnetically aligned samples tended to give sharper photographs than corresponding unannealed fibers. This may be due to the synergistic effect of the capillary walls and the magnetic field.⁵ A definite wall effect was observed, however, in the case of a fluorine-substituted polymer which was cooled from the nematic melt inside a

round glass capillary without an external magnetic field. When it was cooled rapidly from the nematic temperature range, the normal-beam photograph showed two diffuse halos typical of an unaligned nematic. When the same sample was cooled slowly to room temperature, an aligned monodomain developed yielding a diffraction photograph only somewhat less "sharp" than that shown in Fig. 2. Whether similar alignments can be induced in the other polymer samples, by the wall effect of a capillary in the absence of an external magnetic field, was not investigated at this time.

The x-ray diffraction results reported above indicate a high degree of alignment for all polymers examined. The only variations attributable to the different substituents (Table III) are the much higher degree of alignment for H, F, Cl than for Br and CH_3 . This may be a consequence of the decreasing polarizability of the Br and CH_3 substituents. The effective length of the repeat unit parallel to the polymer main chain is 2.91 nm as deduced from the sharp 003 spacing. This compares to 2.96 nm for the extended molecule calculated from known bond distances. The relative constancy of this x-ray spacing and the small amount of arcing of the equatorial reflection for all samples except that containing CH_3 strongly suggests that the polymers align parallel to each other in the monodomain samples with a relative splay of less than 19° . Somewhat more surprisingly, the equatorial arcs yield d values in the range 0.426 to 0.431 nm, without any apparent correlation to the particular substituent in the *para*-position of the arylsulfonyl group. Thus if there is any effect of the substituents on the liquid-crystal polymers, it is primarily steric.

TABLE III. d values of meridional reflections (10^{-9} m)

Magnetically aligned and quenched						
l	H	F	Cl	Br	NO ₂	CH ₃
003	9.71	9.71	9.71		9.71	9.71
005	5.68	5.68	5.88	5.88	5.68	
006	4.72	4.85	4.72	4.85	4.85	
007	4.12				4.12	
Magnetically aligned and annealed						
003	9.71	9.71	9.71		9.71	9.71
005	5.88	5.88		5.88		
006	4.85	4.85	4.85	4.72	4.85	
007	4.22				4.22	
Nematic-glass fibers						
003	9.71	9.43	9.43		9.43	9.43
005	5.88	5.78		5.92		
006	4.85	4.83	4.83	4.81		
007	4.12	4.17	4.26			
Annealed nematic-glass fibers						
003	9.43	9.90	9.43		9.43	9.43
005	5.78	5.95	5.78	5.92		5.78
006	4.83	4.83	4.83	4.81		4.83
007	4.17	4.17	4.26			4.17

It should be noted that the reheating of a magnetically aligned polymer with a hydrogen substituent to a temperature 10° below the isotropization temperature (T_i in Table I) yielded an x-ray diffraction photograph containing several sharp arcs along the equator superimposed on the broad arc in Fig. 2 as well as an increased 'arcing' of the relatively sharp meridional and off-meridian reflections suggestive of the formation of multiple crystalline regions in the polymer. This effect and the role of the oligomers present in all samples examined is currently under investigation and will be reported separately.

ACKNOWLEDGEMENTS

We want to express our appreciation to the Francis Bitter National Magnet Laboratory at M.I.T. for providing access to their superconducting magnet for this study and to the Defense Advanced Research Projects Agency for a University Research Initiatives grant establishing the LCP Research Center at the University of Connecticut.

REFERENCES

1. R. W. Lenz, Pure J. Appl. Chem., **57**, 977 (1985).
2. P. J. Flory, in Polymer Liquid Crystals, edited by A. Ciferri (Academic Press, New York, 1982) Chap. 4.
3. A. Furukawa and R. L. Lenz, Macromol. Chem. Macromol. Symp. **2**, 3 (1986).
4. M. J. S. Dewar and A. C. Griffin, J. Am. Chem. Soc. **97**, 6662 (1975).
5. P. G. Martin, J. S. Moore, and S. I. Strupp, Macromol. **19**, 2461 (1986).

TECHNICAL REPORT DISTRIBUTION LIST, GEN

	<u>No. Copies</u>		<u>No. Copies</u>
Office of Naval Research Attn: Code 1113 800 N. Quincy Street Arlington, Virginia 22217-5000	2	Dr. David Young Code 334 NORDA NSTL, Mississippi 39529	1
Dr. Bernard Duda Naval Weapons Support Center Code 50C Crane, Indiana 47522-5050	1	Naval Weapons Center Attn: Dr. Ron Atkins Chemistry Division China Lake, California 93555	1
Naval Civil Engineering Laboratory Attn: Dr. R. W. Drisko, Code L52 Port Hueneme, California 93401	1	Scientific Advisor Commandant of the Marine Corps Code RD-1 Washington, D.C. 20380	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	12 high quality	U.S. Army Research Office Attn: CRD-AA-IP P.O. Box 12211 Research Triangle Park, NC 27709	1
DTNSRDC Attn: Dr. H. Singerman Applied Chemistry Division Annapolis, Maryland 21401	1	Mr. John Boyle Materials Branch Naval Ship Engineering Center Philadelphia, Pennsylvania 19112	1
Dr. William Tolles Superintendent Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5000	1	Naval Ocean Systems Center Attn: Dr. S. Yamamoto Marine Sciences Division San Diego, California 91232	1

END

10-87

DTIC