

AD-A185 963	DEVELOPING AN ACCELERATED ENDURANCE TEST FOR GREASES - A STATUS REPORT(U) ARMY BELVOIR RESEARCH DEVELOPMENT AND ENGINEERING CENTER FORT BELVOIR VA 1 RHEE AUG 87 DROC-2453	1/1
UNCLASSIFIED	F/Q 11/8	NL

DEVELOPING AN ACCELERATED ENDURANCE TEST FOR GREASES -
A STATUS REPORT(U) ARMY BELVOIR RESEARCH DEVELOPMENT
AND ENGINEERING CENTER FORT BELVOIR VA 1 RHEE AUG 87
BRDEC-2453 F/G 11/8

1/1

UNCLASSIFIED

F/G 11/8

ML

KETNER

AD-A185 963

DTIC FILE COPY

AD

2

technical Report



United States Army
Belvoir Research, Development & Engineering Center
Fort Belvoir, Virginia 22060-5606

Report 2453

Developing an Accelerated Endurance Test for Greases—A Status Report

Authored By:

In-Sik Rhee

Report Date:

August 1987

Approved for public release; distribution unlimited.

DTIC
ELECTE
OCT 15 1987
E

87 10 2 065

UNCLASSIFIED
SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE				Form Approved OMB No. 0704-0188 Exp. Date: Jun 30, 1986	
1a REPORT SECURITY CLASSIFICATION UNCLASSIFIED			1b RESTRICTIVE MARKINGS		
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION AVAILABILITY OF REPORT Approved for Public Release; distribution Unlimited		
2b DECLASSIFICATION/DOWNGRADING SCHEDULE					
4 PERFORMING ORGANIZATION REPORT NUMBER(S) 2453			5 MONITORING ORGANIZATION REPORT NUMBER(S)		
6a NAME OF PERFORMING ORGANIZATION Fuels & Lubricants Div., Matis, Fuels, Lubes Laboratory		6b OFFICE SYMBOL (if applicable) STRBE-VF		7a NAME OF MONITORING ORGANIZATION	
6c ADDRESS (City, State, and ZIP Code) Ft. Belvoir, VA 22060-5606			7b ADDRESS (City, State, and ZIP Code)		
8a NAME OF FUNDING SPONSORING ORGANIZATION		8b OFFICE SYMBOL (if applicable)		9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8c ADDRESS (City, State, and ZIP Code)			10 SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO		PROJECT NO
			TASK NO		WORK UNIT ACCESSION NO
11 TITLE (Include Security Classification) DEVELOPING AN ACCELERATED ENDURANCE TEST FOR GREASES--A STATUS REPORT					
12 PERSONAL AUTHOR(S) In-Sik Rhee					
13a TYPE OF REPORT Interim Report		13b TIME COVERED FROM _____ TO _____		14 DATE OF REPORT (Year, Month, Day) Aug 1987	
15 PAGE COUNT					
16 SUPPLEMENTARY NOTATION					
17 COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP			
19 ABSTRACT (Continue on reverse if necessary and identify by block number) The objective of this study was to develop a grease endurance test method which can be utilized in the comprehensive test methodologies being developed for predicting the performance life of military grease under laboratory environment. In an initial study, the ASTM D3527 test method, "Life Performance of Automotive Wheel Bearing Grease" has been evaluated because it is supposedly simulating an operating environment and has widespread applications. The results show that this method has poor precision, long-endurance test time and poor simulation of field conditions. In particular, the termination criteria used in this method tend to extend grease life. To solve the problem, tentative termination criteria were developed based on the softening of grease, which reduced the test time and distinguished between a good and a poor grease as well as the current method is able to do. To define the L10 life of MIL-G-10924 grease, baseline tests were conducted using the ASTM D3527 method. The L10 life of this grease is less than 20 h. Such a grease is not satisfactory in military vehicles with wheel bearings that are equipped with disc brakes.					
20 DISTRIBUTION AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED UNLIMITED ☐ SAME AS RPT ☐ DOWNGRADING			21 ABSTRACT SECURITY CLASSIFICATION UNCLASSIFIED		
22 NAME OF RESPONSIBLE INDIVIDUAL In-Sik Rhee			23 TELEPHONE (Include Area Code) _____ FAX _____		

DD FORM 1473, 84 MAR

33 APR edition may be used until exhausted
All other editions are obsolete

1. This form is to be filled out by the author of the report.
2. This form is to be filled out by the sponsor of the report.

CONTENTS

Section	Page
I INTRODUCTION	1
II OVERALL REVIEW OF ASTM D3527 METHOD.....	2
III THE LOADING REQUIREMENT ON THE ASTM D3527 METHOD.....	5
IV NEW TERMINATION CRITERIA FOR THE ASTM D3527 METHOD.....	11
V THE REQUIREMENT OF L10 LIFE OF GAA IN THE ASTM D3527 METHOD.....	16
VI DISCUSSION AND CONCLUSIONS.....	19
BIBLIOGRAPHY	20

Figure

1 Termination Profile of the ASTM D3527 Method.....	4
2 Life of MIL-G-10924C Grease at Two Different Loading Systems.....	6
3 Life of MIL-G-10924C Grease in the Modified ASTM D3527 Method.....	7-8
4 Life of MIL-G-10924C Grease in the SKF Method.....	9-10
5 Oxidation Stability Test Results of the Candidate Grease for MIL-G-10924E in the PDSC Method.....	15-16
6 Life of High Dropping Point Grease, MIL-G-10924D.....	17-18

Table

1 Grease Endurance Test Conditions in the Modified ASTM D3527 Method and the SKF Method.....	5
2 The Physical and Chemical Properties of Tested Greases.....	12
3 Grease Life in Both Termination Criteria.....	12
4 Consistency Test Results.....	13

Section I. INTRODUCTION

The US Army is presently using a multi-purpose National Lubricating Grease Institute (NLGI) Number 2 consistency grease covered by Military Specification MIL-G-10924D, "Grease Automotive and Artillery (G.A.A)," as the standard grease for all Army vehicles, artillery, and ground equipment operated worldwide.[1] With rapid advances in automobile technology, the operational and system requirements of military vehicles and equipment have imposed demands for increased capabilities of the lubricating greases. To meet these additional requirements, research is being conducted to develop new performance criteria that will be required for the "E" revision to MIL-G-10924. One of the major thrusts in executing this research effort is the development of comprehensive test methodologies which can be utilized to predict performance life of these military greases.

A project was initiated to develop a methodology for predicting the L10 life of grease products under a laboratory testing environment. The L10 life value is a means of defining the minimum life and is an expression meaning the 90 percent reliable grease life in bearings. A research plan was subsequently established for the following three phases:

Phase I: Develop the mathematical modeling system to evaluate functional performance of grease products.

Phase II: Select or develop accelerated endurance testing method(s).

Phase III: Correlate laboratory test methodology with field performance.

In one of our previous research efforts, the maximum likelihood (ML) computer program for the two-parameter Weibull probability distribution was developed to meet the primary objective of Phase I.[2] To provide meaningful input data, the current research effort is directed toward developing the grease endurance testing procedure which is planned in Phase II.

For the last three decades, numerous ball-bearing and roller-bearing grease endurance tests have been devised for laboratory evaluation of grease. Some of them were used to standardize specific test procedures in the grease industry, while others were used in individual laboratories for grease development. Among these standard methods, the American Society for Testing and Materials (ASTM) D3527 test method, "Life Performance of Automotive Wheel Bearing Grease," is widely used in the grease manufacturing and automotive industries. Because of its application and simulation of an operating environment, a study was conducted to evaluate the ASTM D3527 method prior to being incorporated into MIL-G-10924D. This report describes the advantages and disadvantages of this method, our findings, and the results of a feasibility study conducted to develop an accelerated endurance test using this method.

Section II. OVERALL REVIEW OF ASTM D3527 METHOD

The method covers a laboratory procedure for evaluating the high-temperature (160 °C) ASTM D3527 under specified conditions. The significance of this method is that it differentiates among wheel bearing greases having distinctly different high-temperature characteristics only. The current precision is as follows:

Repeatability = 0.8 X

Reproducibility = 1.2 X

Where X = average of the two test results

The basic configuration of the test apparatus consists of a simulated front wheel hub-spindle-bearings assembly, a heater, a dc-motor, a tachometer, an elapsed time meter, a torque meter, and a temperature monitor. Two tapered roller bearings were used as the test specimens in this procedure: LM67048-LM67010 for the inboard bearing, and LM11949-LM11910 for the outboard bearing. Both bearings are currently utilized in small vehicles. For the test, three main parameters (temperature, load, and speed) were applied to this method. Initially, a test temperature of 150 °C was selected at the outboard bearing because wheel bearing temperatures associated with front disc brake systems higher than 150 °C were encountered.[3] In 1985, the test temperature was raised from 150 to 160 °C at the outboard bearing to provide a more severe test condition. The test speed selected was 1,000 rpm. The thrust load of only 25 lbf (representing the vehicle curb and axial cornering weight) was applied to the test bearings because the test apparatus developed was based on modifications of the ASTM D1263, "Leakage Tendencies of Automotive Wheel Bearing Grease," method.[4] This preload was adapted from a wheel bearing adjusting nut torque value used in light trucks. With these test parameters, grease life was determined when the drive motor torque exceeded a preset torque limit for 30 seconds in 20 hours on, 4 hours off cycle operation.

The advantage of this method was to comprehensively evaluate all individual physical properties of greases directly related to high temperature and shear, using a simulated front wheel bearing system and a dynamic laboratory bench-type test apparatus. The disadvantage of this method was its poor precision. For this reason, this method did not have the capability to distinguish between the greases having similar high-temperature properties. Finally, the test results provided limited correlation to field performance.

Since this method was issued, it had not been extensively utilized in grease research and development and specifications because of its poor precision, long endurance test time, and questionable correlation with field vehicle operation conditions. The ASTM Committee D2 Subsection B0.04 on Automotive Greases is currently developing a Chassis Grease and Wheel Bearing Grease specification to cover lubricating grease suitable for the periodic relubrication of commercial vehicles.[5] In this wheel bearing specification, the ASTM D3527 method is listed with its minimum requirement (80 hours). Due to the method's poor precision, the following paragraph is included to justify this requirement:


"The test requirements (limits) given in this specification are, as the case may be, minimum or maximum acceptable values for valid duplicate test results. No additional corrections for test precision, such as described in the ASTM D3244, "Utilization of Test Data to Determine Conformance with Specifications," are to be applied inasmuch as the precision of the test methods were taken into account in the determination of the requirements."

However, the US Army currently uses a modified version of ASTM D3527 in the MIL-G-10924 specification without the above reservation. The currently identified problem areas are the termination criteria and the test temperature measurement technique.[6,7] According to the ASTM D3527, the test temperature is measured from the spindle hole in which the thermocouple is inserted, resulting in a temperature gap of 20 to 30 °C between the chamber and spindle. It appears that the test temperature is closer to the chamber temperature instead of the spindle temperature because the test specimen (wheel bearing hub system) is fully open in the chamber and the heat transfer is facilitated by hot air in the chamber. Therefore, the actual test temperature is assumed to be higher than 160 °C.

The problems associated with the ASTM termination criteria used in this method are:

- As a consequence of the cyclic operation, the resulting grease life is probably longer than the actual life of the grease.
- Test results are unrepeatable.
- Since the torque rarely reaches the preset torque limit, there is a termination problem.
- The test is terminated at room temperature rather than the test temperature.

The termination profile of the ASTM D3527 method is shown in Figure 1. These problems directly affect precision. To solve these problems, the ASTM G0.05 Subcommittee is studying possible modification to this test machine. Ever since this method has been issued, there have been informal reports of frequent equipment problems.






Figure 1. Termination Profile of the ASTM D3527 Method

Section III. THE LOADING REQUIREMENT ON THE ASTM D3527 METHOD

The primary objective of this study was to establish a comparative baseline for loading requirements (i.e., test severity) of the three major test parameters (temperature, loads, and speed) to be used in the laboratory grease endurance test procedure. The equipment targeted for use in developing this wear-life projection was the ASTM D3527 test apparatus. Because of questions concerning test parameters, the major focus on this apparatus was the radial load (vehicle weight) which had been used as a test parameter in previously conducted grease investigations using the SKF grease test procedure.[8,9,10]

For this reason, a study was conducted to determine whether the radial load should be considered as a test parameter in the grease endurance test procedure. This task was performed using the differences of two test methods (ASTM, SKF). The major differences of these methods were the load treatment on the test bearing, termination criteria, and test operation (continuous vs. cycle operation). To make a comparison, the grease endurance tests were performed according to the Modified ASTM D3527 test method. The grease used in these tests was a qualified MIL-G-10924C grease evaluated previously using the SKF grease test method. Table 1 presents test conditions.

Thirteen data points were generated using the four ASTM D3527 test devices. Due to the poor precision, the MIL-G-10924C "grease life" was determined using the ML computer program. The L10 life of the MIL-G-10924C grease was projected to be 238 hours. This L10 life value was approximately eight times longer than that previously obtained from the SKF method which gave an L10 life of 32 hours. This implied that the grease life also depends on the load as well as the temperature. Therefore, the results indicated that the radial load (vehicle weight) should be used as a test parameter in the grease performance test. These test results are plotted to make a comparison in Figure 2, and their test results are provided in Figures 3 and 4.

Table 1. Grease Endurance Test Conditions in the Modified ASTM 3527 Method and the SKF Method

	Modified ASTM	SKF
Test temperature	121 °C	121 °C
Speed	800 rpm	800 rpm
Thrust load	25 lbf (fixed)	560 lbf (applied each 5 minutes for 90 seconds duration)
Radial load	none	1,875 lbf (fixed)
Test bearings	Tapered roller bearing	same as ASTM
Operation	Cycle (20 hours on, 4 hours off)	continuous
Termination criteria	Torque	Vibration, Time-up, Noise, Temperature

MIL-G-10924C




Figure 2. Life of MIL-G-10924C Grease at Two Different Loading Systems

MIL-G-10924C (ASTM)




Figure 3. Life of MIL-G-10924C Grease in the Modified ASTM D3527 Method

ESTIMATES FOR THE CUMULATIVE WEIBULL DISTRIBUTION

$$F(X) = 1 - \exp(-(X/A)^B)$$

ESTIMATE AND TWO-SIDED 90% CONFIDENCE INTERVALS FOR DISTRIBUTION PARAMETERS

SHAPE (BETA) PARAMETER = 3.5328
LOWER LIMIT = 2.5310
UPPER LIMIT = 4.9310

SCALE PARAMETER = 449.9063
LOWER LIMIT = 392
UPPER LIMIT = 516.0136

ESTIMATED COVARIANCE MATRIX OF PARAMETER ESTIMATES

	SCALE	SHAPE
SCALE	1405.8787	9.0111
SHAPE	9.0111	.5128


ESTIMATE AND TWO-SIDED 90% CONFIDENCE INTERVALS FOR DISTRIBUTION PERCENTILES

PERCENTAGE	PERCENTILE ESTIMATE	LOWER LIMIT	UPPER LIMIT
1.0	122	74	201
5.0	194	137	276
10.0	238	178	318
20.0	294	234	370
50.0	406	348	472
70.0	474	415	541
90.0	570	499	651
95.0	614	533	707
99.0	693	589	815
99.9	778	644	938

1.10				1.50			
UCL	MED	UCL		UCL	MED	UCL	
178	238	318		348	406	472	

Figure 3. Continued

MIL-G-10924C (SKF)



CUMULATIVE PROBABILITY IN PERCENT

Figure 4. Life of MIL-G-10924C Grease in the SKF Method

ESTIMATES FOR THE CUMULATIVE WEIBULL DISTRIBUTION

$$F(X) = 1 - \exp(-(X/A)^B)$$

ESTIMATE AND TWO-SIDED 90% CONFIDENCE INTERVALS FOR DISTRIBUTION PARAMETERS

SHAPE (BETA) PARAMETER = 1.5500
 LOWER LIMIT = 1.1471
 UPPER LIMIT = 2.0943

SCALE PARAMETER = 134.7947
 LOWER LIMIT = 105
 UPPER LIMIT = 172.7830

ESTIMATED COVARIANCE MATRIX OF PARAMETER ESTIMATES

	SCALE	SHAPE
SCALE	413.9144	1.7054
SHAPE	1.7054	.0804

ESTIMATE AND TWO-SIDED 90% CONFIDENCE INTERVALS FOR DISTRIBUTION PERCENTILES

PERCENTAGE	PERCENTILE ESTIMATE	LOWER LIMIT	UPPER LIMIT
1.0	7	3	19
5.0	20	10	40
10.0	32	18	55
20.0	51	33	79
50.0	106	81	140
70.0	152	120	193
90.0	231	179	297
95.0	274	208	360
99.0	361	261	500
99.9	469	319	689

L10					L50			
	LCL	MED	UCL			LCL	MED	UCL
	18	32	55			81	106	140

Figure 4. Continued

Section IV. NEW TERMINATION CRITERIA FOR THE ASTM D3527 METHOD

The current grease failure criteria used in the ASTM D3527 method originally were developed based on a hardening of grease which, in turn, produced lubricant starvation. However, it now appears that these criteria can only be utilized when the running torque value has a higher value than a steady-state torque value which developed at the first 2 hours of operation. In practice, the running torque value does not always produce a higher value than its initial value measured at 2 hours of operation. In our previous tests, evidently, it was observed that the MIL-G-10924C grease sample underwent changes at 121 °C in two distinct stages. In the first stage, the grease appeared to soften or become semifluid at the given test temperature and speed. The running torque observed at this stage was about a quarter of the steady-state torque obtained at the first 2 hours of operation; then, hardening of the grease occurred in the later stage. To provide more evidence, a lubrication comparison test was conducted using the modified ASTM D3527 method used in the MIL-G-10924C grease endurance tests. The lubrication used in this comparison test was the VV-L-800, "General Purpose Preservative Oil," having similar property as the base stock used in the MIL-G-10924C grease.[11] The results showed that the lubrication life marked 9.3 hours, and the running torque value was almost identical to that obtained with the MIL-G-10924C grease. It would appear that the grease in question changed its consistency during the test due to the temperature and shear forces incurred in the first stage. These physical property changes may affect grease endurance life and lead to subsequent bearing failure. Generally, the deterioration of grease results from oxidation reactions, a breakdown of grease structure, excess bleeding or separation of oil from the thickener, and contamination.[12] These physical property changes can all be considered as grease failure criteria.

To develop new termination criteria for the ASTM D3527 method, a feasibility study was conducted using a candidate grease for the "E" revision of MIL-G-10924 Specification and the MIL-G-10924C grease used in the SKF tests. The former is a high dropping point grease, whereas the latter is a low dropping point grease. The physical and chemical properties of these greases are shown in Table 2. For the feasibility study, the following tentative termination criteria were developed based on the softening of grease indicated in the previous test results:

$$TC = M(ST - N) - N, \text{ where}$$

$$M = 2$$

ST = steady-state torque value obtained at 2 hours operation

N = torque of unloaded motor

Holding time for TC = 30 seconds

To make a comparison, grease endurance tests were performed using both current ASTM termination criteria (high set point) and the tentative new termination criteria (low set point) at 121 °C and 160 °C. The test results are shown in Table 3.

Table 2. The Physical and Chemical Properties of Tested Greases

Test	ASTM Method	Grease	
		MIL-G-10924C	Candidate Grease for MIL-G-10924E
NLGI Consistency Number:			
Worked 60X	D217	2	1½
Unworked	D217	—	3½
Thickener Type:		Calcium	Lithium Complex
Base oil		Petroleum	Polyalphaolefin
Base oil viscosity at 40°C, cSt		13.3	220
Cone Penetration (worked 60X):	D217	281	305
Dropping Point, °C:	D2265	143	260 +
Oil Separation, %:	D1747	5.2	0.62
Evaporation, %:	D972	5.3	1.72
Oxidation:			
Stability, 100 hours	D942	2	2
4 Ball EP, LWI	D2596	35.8	50

Table 3. Grease Life in Both Termination Criteria

Test Temperature	MIL-G-10924C		Candidate Grease for MIL-G-10924E	
	LSP*	HSP**	LSP	HSP
120 °C	80 hours	150 hours	—	>1,000 hours
160 °C	—	> 20 hours	57.9 hours	123.8 hours

* LSP: Low set point

** HSP: High set point (current ASTM D3527 termination criteria)

ASTM termination criteria:

TC = 8 (initial torque - unloaded torque) + unloaded torque

Holding time for TC: 30 seconds

The candidate grease for MIL-G-10924E Specification did not follow either termination criteria at 121 °C. It appeared that the test temperature (121 °C) may be too low to fully stress or deteriorate the high dropping point grease. This grease was terminated by both set points when tested at 160 °C. The grease terminated by the low set point criteria appeared to be moderately oxidized and dried with free oil. On the other hand, the failed grease detected by the high set point criteria appeared to be completely oxidized and only residue grease remained in the bearings. The life obtained using the low set point criteria was approximately one half of that obtained when using the high set point criteria. In the other test, the MIL-G-10924C grease (low dropping point grease) also followed both set points at 121 °C. The condition of this grease in both tests was similar to the condition of the high dropping point grease. At 160 °C, this grease only operated for 20 hours. However, the actual "life" of this grease was less than 20 hours because most grease failures were observed at the initial cycle operation after a 4-hour rest. Therefore, the minimum life of this method can be considered to be 20 hours. This grease was not suitable to conduct the grease endurance test according to the ASTM D3527 method because of its low dropping point (143 °C). Evidently, the grease completely melted at the test temperature and the tested bearings looked like unlubricated new bearings. Both test results indicated that the tentative termination criteria can reduce the test time to as much as one half of that obtained from the ASTM termination criteria.

To address whether the grease becomes soft or not at the tentative termination criteria, a consistency test was conducted on exposed samples according to the ASTM D1403, "Cone Penetration of Lubricating Grease using One-Quarter and One-Half Cone Scale Equipment." Due to the insufficient amount of grease, only the unworked penetration number of the candidate grease for MIL-G-10924E was determined. The test results showed that the unworked penetration number measured from the used grease (54.4 hours) was softened by a half NLGI number in comparison to that obtained from the new grease. It would appear that the decrease in the running torque at this stage resulted from the combination of softening of the grease and adsorption of certain additives on bearing surfaces. The test results are summarized in Table 4.

Table 4. Consistency Test Results

Grease	Unworked Penetration	
	New	Used (54.4 hours)
Candidate grease for MIL-G-10924	215	238
NLGI Number	3-2	3

To define an additional failure criteria for tested greases, experimental oxidation stability tests were conducted using the Pressure Differential Scanning Calorimetry (PDSC) method which is being developed within the ASTM Committee D2 Subsection 09.0E on oxidation.[13] The test results are provided in Figure 5.

The test results showed that the MIL-G-10924C grease used in the modified ASTM D3527 test for 80 hours gave 1.4 minutes in induction time which indicates the relative degree of oxidation in this method. This value was lower than that obtained from the new grease (16.2 minutes) and equivalent to that determined from the heavy oxidized residue grease. The new candidate grease for MIL-G-10924E showed a good oxidation stability at the given test conditions, and the grease used in outboard and inboard bearings for 57.9 hours marked 15.3 minutes and 31.9 minutes respectively. Both values were higher than those obtained from new MIL-G-10924C grease. Although the grease was not oxidized at this stage, the result indicated that the grease was being degraded by the temperature and shear force. Evidently, the induction time obtained from the used grease (57.9 hours) was significantly lower than new grease and higher than the residue grease collected at 123.8 hours.

In summary, the grease lubricated in the outboard bearing gave lower induction time than that obtained from the inboard bearing under the same hub system. This implied that the grease used in the outboard bearing (small bearing) failed earlier than grease obtained from the inboard bearing (large bearing). As the ASTM D3527 method was designed to determine the grease failure life when grease packed in both bearings completely deteriorates, the grease failure occurring in the outboard bearing actually does not signal failure life. Therefore, this developed preliminary termination criteria, based on the oxidation and hardening of grease, intends to extend grease life and sometimes give a termination problem. Based on data developed to date, this method needs new termination criteria which can determine the true grease life. The tentative termination criteria reduced the test time and distinguished a good and poor grease as well as the current method is able to do.

DSC




Figure 5. Oxidation Stability Test Results of the Candidate Grease for MIL-G-10924E in the PDSC Method

MIL-G-10924C**Candidate Grease
for MIL-G-10924E**

Grease:	New grease		TTC		ASTM		New grease		TTC		ASTM	
			IB	OB	IB	OB			IB	OB	IB	OB
Bearing:												
Induction Time (min):	16.2		1.4	—	—	—	120		31.9	15.3	6.3	4

TTC: Tentative termination criteria

ASTM: ASTM termination criteria

IB: Inboard bearing


OB: Outboard bearing

Figure 5. Continued

**Section V. THE REQUIREMENT OF L10 LIFE OF GAA
IN THE ASTM D3527 METHOD**

To establish the requirement of L10 life of current GAA grease and the future long life Army grease, baseline tests were conducted using the ASTM D3527 method. Of the nine qualified products under the MIL-G-10924D Amendment 1 Specification, only one high dropping point grease was qualified to perform according to the ASTM D3527 method.[14] The other greases were not included in this evaluation due to their lower dropping points (143 °C). Eight data points were generated on the one qualified product and its L10 life was determined using the MIL computer program. The baseline grease life, with 90 percent confidence intervals, and its numerical percentile life are shown in Figure 6. The L10 life obtained from this baseline test was 52 hours, and the L50 life (representing the average life) was 116 hours. This L50 life was longer than the requirement of the draft ASTM wheel bearing specification. The average life of conventional wheel bearing greases is between 80 to 150 hours. The current low dropping point greases supplied under the MIL-G-10924D Specification are generally satisfactory for artillery and ground equipment, but not necessarily in disc brake wheel bearing applications because the testing at 160 °C provided a life less than 20 hours.

MIL-G-10924D (H)



CUMULATIVE PROBABILITY IN PERCENT

Figure 6. Life of High Dropping Point Grease, MIL-G-10924D

ESTIMATES FOR THE CUMULATIVE WEIBULL DISTRIBUTION

$$F(X) = 1 - \exp(-(X/A)^B)$$

ESTIMATE AND TWO-SIDED 90% CONFIDENCE INTERVALS FOR DISTRIBUTION PARAMETERS

SHAPE (BETA) PARAMETER = 2.3637
LOWER LIMIT = 1.5017
UPPER LIMIT = 3.7203

SCALE PARAMETER = 135.8103
LOWER LIMIT = 105
UPPER LIMIT = 176.2104

ESTIMATED COVARIANCE MATRIX OF PARAMETER ESTIMATES

	SCALE	SHAPE
SCALE	462.2547	4.5875
SHAPE	4.5875	.4248

ESTIMATE AND TWO-SIDED 90% CONFIDENCE INTERVALS FOR DISTRIBUTION PERCENTILES

		PERCENTILE ESTIMATE		LOWER LIMIT		UPPER LIMIT	
		1.0	19	7	53		
		5.0	39	19	78		
		10.0	52	30	93		
		20.0	72	46	113		
		50.0	116	87	156		
		70.0	147	114	189		
		90.0	193	149	250		
		95.0	216	164	285		
		99.0	259	188	358		
		99.9	308	211	448		
L10				L50			
LCL		MED	UCL	LCL		MED	UCL
30		52	93	87		116	156

Figure 6. Continued

Section VI. DISCUSSION AND CONCLUSIONS

Although the ASTM D3527 method was studied with limited data, it can be concluded that this method may be as good as the screening test, but not applicable to use in the Army grease specification without any modification. The reasons are that this method has poor precision and definition of the meaning of the test. Based on test results, grease life also depends on the load as well as the temperature. Therefore, the radial load should be used as a test parameter with the thrust load.

The current ASTM termination criteria developed based on a hardening of grease gave a termination problem and tended to extend grease life. The new developed tentative termination criteria, based on the softening of grease, reduced the test time as much as one half of that obtained from the current ASTM termination criteria. It also differentiated between a good and a poor grease as well as the current ASTM D3527 does. Results clearly show that this approach resolved the problem associated with the current method. Further study of this termination would be beneficial for developing an accelerated grease endurance method.

The L10 life of high dropping point grease supplied under MIL-G-10924D Specification obtained 52 hours, and L50 life (representing the average life) was 116 hours, which is a longer life than the requirement of the draft ASTM wheel bearing specification (80 hours). The traditional low dropping point MIL-G-10924D grease provided less life than 20 hours. It appears that this grease is not satisfactory in disc brake wheel bearing applications.

BIBLIOGRAPHY

1. Military Specification MIL-G-10924D, "Grease Automotive and Artillery (GAA)," 13 June 1983.
2. In-Sik Rhee, "Evaluation of the L10 Life of Military Greases in Wheel Bearings by Computer Analysis," ASME Failure Prevention and Reliability Conference, 1985.
3. R. McClintock, General Motors Research Laboratories, "A Laboratory Study of Wheel Bearing Grease High-Temperature Life," NLGI 45th Annual Meeting, 1979.
4. D. J. Sargent, E/M Lubricants, Inc., "A Historical View of ASTM Method D3527," NLGI 45th Annual Meeting, October 1977.
5. Minutes of ASTM Subsection BO.04, 6 August 1986.
6. In-Sik Rhee, Trip Report ASTM Committee D2 Meeting, Louisville, KY, 8 July 1986.
7. In-Sik Rhee, Trip Report ASTM Committee D2 Meeting, Savannah, GA, 13 January 1987.
8. Contract No. DAAK 70-77-C-0034, "Performance Evaluation of Automotive Wheel Bearing Greases," Final Report, SKF Inc.
9. Contract No. DAAK 70-79-C-0213, "Performance Evaluation of Automotive Wheel Bearing Greases," Final Report, SKF Inc.
10. Contract No. DAAK 70-83-C-0063, "Performance Evaluation of Automotive Wheel Bearing Greases," Final Report, SKF Inc.
11. Military Specification VV-L-800, "General Purpose Preservative Oil," 15 September 1986.
12. O'Connor & Boyd, *Standard Handbook of Lubrication Engineering*, Ch 17, p.10.
13. ASTM Draft Method, "Oxidation Resistance of Lubricating Greases by Pressure Differential Scanning Calorimetry," 4 October 1984.
14. Military Qualified Products List of Products Qualified under Military Specification MIL-G-10924D and Amendment 1, 26 June 1986.

DEPARTMENT OF THE ARMY

- | | |
|---|--|
| <p>1 Commander
US Army Materiel Command
ATTN: AMCDE-SS
ATTN: AMCSM-WST
5001 Eisenhower Avenue
Alexandria, VA 22333-0001</p> | <p>1 Director
Propulsion Directorate
US Army Research & Technology
Activities (AVSCOM)
ATTN: SAVDL-PL-D (Mr. Acurio)
21000 Brookpark Road
Cleveland, OH 44135-3127</p> |
| <p>1 Commander
US Army Tank-Automotive Command
ATTN: AMSTA-RG (Mr. Wheelock)
ATTN: AMSTA-TSL (Mr. Burg)
ATTN: AMSTA-RGP (Mr. Raggio/
Mr. McCartney)
ATTN: AMSTA-MTC (Mr. Gaglio),
AMSTA-MC, AMSTA-MV
ATTN: AMSTA-MLF (Mr. Keller)
Warren, MI 48397-5000</p> | <p>1 Commander
US Army Armament Research
& Development Center
ATTN: AMSMC-LC
ATTN: AMSMC-SC
Dover, NJ 07801-5001</p> |
| <p>1 Commander
US Army Aviation Systems
Command
ATTN: AMSAV-EP (Mr. Edwards)
ATTN: AMSAV-NS
4300 Goodfellow Blvd
St. Louis, MO 63120-1798</p> | <p>1 Commander
US Army Research Office
ATTN: SLCRO-EG (Dr. Mann)
ATTN: SLCRO-CB
P.O. Box 12211
Research Triangle Park, NC 27709-2211</p> |
| <p>1 Director
US Army Aviation Research
& Technology Activities (AVSCOM)
ATTN: SAURT-R (Mr. Andre)
Ames Research Center (Mail Stop 207-5)
Moffet Field, CA 94035-1099</p> | <p>1 Commander
US Army Depot Systems Command
ATTN: AMSDS-RM-EFO
Chambersburg, PA 17201</p> |
| <p>1 Commander
US Army Laboratory Command
ATTN: AMSLC-TP-AL (LTC Schrader)
Adelphi, MD 20783-1145</p> | <p>1 Director
Director
AMC Packaging, Storage, and
Containerization Center
ATTN: SDSTO-TE-S
Tobyhanna, PA 18466-5097</p> |
| <p>1 Director
Applied Technology Directorate
US Army Research & Technology
Activities (AVSCOM)
ATTN: SAVDL-ATL-ATP (Mr. Morrow)
ATTN: SAVDL-ATL-ASV
Fort Eustis, VA 23604-5577</p> | <p>1 Director
US Army Materials Technology Laboratory
ATTN: SLCMT-M
ATTN: SLCMT-EM (Dr. Fopiano)
Watertown, MA 02172-2796</p> |
| | <p>1 Commander
US Army Watervliet Arsenal
ATTN: SARWY-RDD
Watervliet, NY 12189</p> |

- | | |
|--|--|
| <p>1 Commander
US Army Foreign Science & Technology
Center
ATTN: AIAST-RA-ST3 (Mr. Busi)
ATTN: AIAST-MT-1
Federal Building
Charlottesville, VA 22901</p> | <p>1 Commander
US Army General Materiel &
Petroleum Activity
US Army Troop Support Command
ATTN: STRGP-PW (Mr. Price)
BLDG 247, Defense Depot Tracy
Tracy, CA 95376-5051</p> |
| <p>1 Commander
AMC Materiel Readiness Support Activity
(MRSA)
ATTN: AMXMD-MO (Mr. Brown)
Lexington, KY 40511-5101</p> | <p>1 HQ
US Army Armament, Munitions &
Chemicals Command
ATTN: AMSAR-LEM
Rock Island Arsenal, IL 61299-6000</p> |
| <p>1 HQ, US Army Test & Evaluation Command
ATTN: AMSTE-TO-O
ATTN: AMSTE-CM-R-O
ATTN: AMSTE-TE-T (Mr. Ritondo)
Aberdeen Proving Ground, MD 21005-5006</p> | <p>1 Commander
US Army Research & Standardization
Group (Europe)
ATTN: AMXSN-UK-RA (Dr. Oertel)
ATTN: AMXSN-UK-SE
Box 65
FPO New York 09510</p> |
| <p>1 Project Manager, Petroleum &
Water Logistics
ATTN: AMCPM-PWL
4300 Goodfellow Blvd
St. Louis, MO 63120-1798</p> | <p>1 Commander
US Army Yuma Proving Ground
ATTN: STEYP-MT-TL-M (Mr. Doebbler)
Yuma, AZ 85364-9130</p> |
| <p>Commander
US Army Troop Support Command
ATTN: AMSTR-ME
ATTN: AMSTR-E
ATTN: AMSTR-S
4300 Goodfellow Blvd
St. Louis, MO 63120-1798</p> | <p>1 Commander
Construction Engineering Research
Laboratory
ATTN: CERL-EM
ATTN: CERL-ES (Mr. Case)
ATTN: CERL-EH
P.O. Box 4005
Champaign, IL 61820</p> |
| <p>1 Commander
US Army General Materiel &
Petroleum Activity
US Army Troop Support Command
ATTN: STRGP-F (Mr. Ashbrook)
ATTN: STRGP-FT (Mr. Foster)
ATTN: STRGP-FE, Bldg 85-3
(Mr. Gary Smith)
New Cumberland, PA 17070-5008</p> | <p>1 Program Manager, Tank Systems
ATTN: AMCFM-GCM-SM
ATTN: AMCPM-M60
Warren, MI 48397</p> |
| | <p>1 Program Manager,
Bradley Fighting Vehicle Systems
ATTN: AMCPM-FVS-M
Warren, MI 48397</p> |

1 Program Manager, Tactical Vehicle
ATTN: AMCPM-TV
Warren, MI 48397

1 Product Manager, M113 Family of Vehicles
ATTN: AMCPM-M113-T
Warren, MI 48397

1 Project Manager, Light Combat Vehicles
ATTN: AMCPM-LCV-TC
Warren, MI 48397

1 Project Manager, Light Armored Vehicles
ATTN: AMCPM-LA-E
Warren, MI 48397

1 Commander
US Army Quartermaster School
ATTN: ATSM-CD
ATTN: ATSM-TD
ATTN: ATSM-PFS (Mr. Elliott)
Fort Lee, VA 23801

1 Commander
US Army Armor of Engineer Board
ATTN: ATZK-AE-AR
ATTN: ATZK-AE-LT
Fort Knox, KY 40121

1 Commander
US Army Field Artillery School
ATTN: ATSF-CD
Fort Sill, OK 73503-5600

1 Commander
US Army Transportation School
ATTN: ATSP-CD-MS (Mr. Harnett)
Fort Eustis, VA 23604-5000

1 Commander
US Army Infantry School
ATTN: ATSH-CD-MS-M
Fort Benning, GA 31905-5400

1 Commander
US Army Aviation Center & Fort Rucker
ATTN: ATZQ-DI
Fort Rucker, AL 36362

1 Commander
US Army Engineer School
ATTN: ATZA-TSM-G
Fort Belvoir, VA 22060-5606

1 Commander
US Army Ordnance Center & School
ATTN: ATSL-CD-CS
Aberdeen Proving Ground, MD 21005

1 Director
Belvoir Fuels & Lubricants Research
Facility (SwRI)
ATTN: Mr. S. J. Lester
Post Office Drawer 28510
San Antonio, TX 78284

DEPARTMENT OF THE AIR FORCE

1 Commander
US Air Force Wright Aeronautical
Laboratories
ATTN: AFWAL POSL (Mr. Jones)
ATTN: AFWAL MLSE
ATTN: AFWAL MLBT (Mr. Snyder)
Wright-Patterson AFB, OH 45433-6563

1 Commander
San Antonio Air Logistics Center
ATTN: SAALC SFT (Mr. Makris)
ATTN: SAALC MMPRR
Kelly Air Force Base, TX 78241

1 Commander
Warner Robins Air Logistics Center
ATTN: WRALC MMTV (Mr. Graham)
Robins Air Force Base, GA 31098

DEPARTMENT OF THE NAVY

1 Commander
Naval Air Propulsion Center
ATTN: PE-33 (Mr. D'Orazio)
ATTN: PE-32 (Mr. Mangione)
P.O. Box 7176
Trenton, NJ 06828

1 Office of Chief of Naval Research
ATTN: OCNR-126
Arlington, VA 22217-5000

1 Commander
Naval Air Engineer Center
ATTN: Code 92727
Lakehurst, NJ 08733

1 Commander
Naval Sea Systems Command
ATTN: Code 05M4
Washington, DC 20362-5101

1 Commander
David Taylor Naval Ship Research
& Development Center
ATTN: 2830 (Mr. Singerman)
ATTN: Code 2831
ATTN: Code 2759 (Mr. Strucko)
Annapolis, MD 21402-5067

1 Commander
Navy Petroleum Office
ATTN: Code 43 (Mr. Long)
Cameron Station
Alexandria, VA 22304-6180

1 Commanding General
US Marine Corps Development &
Education Command
ATTN: D074
Quantico, VA 22134

1 Joint Oil Analysis Program - Technical
Support Center
Bldg 780
Naval Air Station
Pensacola, FL 32508

1 Commander
Naval Research Laboratory
ATTN: Code 6170
ATTN: 6180
ATTN: 6110
Washington, DC 20375-5000

1 Commander
Naval Air Systems Command
ATTN: Code 53645 (Mr. Mearns)
Washington, DC 20361

1 Commander
Naval Air Development
ATTN: Code 60612
Warminster, PA 18974

1 Project Manager, M60 Tank Development
ATTN: USMC-LNO
US Army Tank-Automotive Command
(TACOM)
Warren, MI 48397

1 Commander
Naval Ship Engineering Center
ATTN: Code 6764
Philadelphia, PA 19112

DEPARTMENT OF DEFENSE

1 Commander
Defense General Supply Center
ATTN: DGSC-SSM (Mr. Reynolds)
ATTN: DGSC-STC (Mr. Doyle)
Richmond, VA 23297-5000

1 Defense Advanced Research Projects Agency
Defense Sciences Office
1400 Wilson Boulevard
Arlington, VA 22209

1 Defense Standardization Office
ATTN: Dr. S. Miller
5203 Leesburg Pike, Suite 1403
Falls Church, VA 22041

OTHER FEDERAL AGENCIES

1 National Aeronautics and Space
Administration
Lewis Research Center
Cleveland, OH 44135

- | | |
|---|---|
| <p>1 National Institute for Petroleum
and Energy Research
P.O. Box 2128
Bartlesville, OK 74005</p> <p>1 Department of Energy
CE-151, ATTN: Mr. Ecklund
1000 Independence Ave., SW.
Washington, DC 20585</p> <p>1 Southwest Research Institute
Fuels & Lubricants Research Division
6220 Culebra Road
San Antonio, TX 78284</p> <p>1 Mobil Research & Development Corp.
Mr. John A. Keller
Paulsboro, NJ 08066</p> <p>1 Witco Corporation
Mr. Jon C. Root
1400 South Harrison
P.O. Box 1974
Olathe, KS 66061</p> <p>1 Battenfeld Grease & Oil Corporation
of New York
Mr. Thomas G. Musilli
1174 Erie Avenue
Box 728
North Tonawanda, NY 14120</p> <p>1 BELVOIR RD&E CENTER</p> <p>Commander STRBE-Z
Deputy Commander STRBE-ZD
Technical Director STRBE-ZT
Assoc Tech Dir (E&A) STRBE-ZTE
Assoc Tech Dir (R&D) STRBE-ZTR
Executive Officer STRBE-ZX
Sergeant Major STRBE-ZM
Advanced Systems Concepts Dir STRBE-H
Program Planning Div STRBE-HP
Foreign Intelligence Div STRBE-HF
Systems and Concepts Div STRBE-HC</p> | <p>3 Materials, Fuels, &
Lubricants Lab STRBE-V</p> <p>25 Fuels & Lubricants Div STRBE-VF</p> <p>10 Mr. Rhee STRBE-VFH</p> <p>3 Security Office (for liaison
officers) STRBE-S</p> <p>2 Tech Library STRBE-BT</p> <p>1 Public Affairs Office STRBE-I</p> <p>1 Office of Chief Counsel STRBE-L</p> |
|---|---|

END
DATE
FILMED
JAN
1988