

NO-A106 723

GROWTH OF HAZNTE LAYERS BY LPE TECHNIQUE(U) ISRAEL  
ATOMIC ENERGY COMMISSION YAVNE SOREQ NUCLEAR RESEARCH  
CENTRE A SHER 01 AUG 87 SSP-PR-40-253-87

1/1


UNCLASSIFIED

DAJA45-85-C-0049

F/G 20/2

NL





ISRAEL ATOMIC ENERGY COMMISSION  
SOREQ NUCLEAR RESEARCH CENTER



הועדה לאנרגיה אטומית  
מרכז המחקר גרעיני סורק

AD-A186 723

DTIC FILE COPY

SSP-PR-40-253-87

Growth of HgZnTe Layers by LPE Technique

Ariel Sher

Soreq Nuclear Research Center

Contract # DAJA45-85-C0049

4th Period Report

February 1st, 1987 - August 1st, 1987

DISTRIBUTION STATEMENT A

Approved for public release;  
Distribution Unlimited

DTIC  
ELECTE  
OCT 19 1987  
S D  
H

The research in this document has been made possible through the support and sponsorship of the U.S. government through its European Research Office of the U.S. Army. This report is intended only for the internal management of the contractor and the U.S. government.

87

TELEX 341975 • TELEFAX 06-437363 • TEL 06 484211 • 11272 • 70416 • 11272

87 9 23 076

- 2 -

✓ The goal of this project is to evaluate the LPE growth technique as a tool for preparing  $\text{Hg}_{1-x}\text{Zn}_x\text{Te}$  suitable for photodetectors.

In the first year of this project optimization of the growth conditions was done.

The objective for the second year is to study the parameters which determine the transport electrical properties of the  $\text{Hg}_{1-x}\text{Zn}_x\text{Te}$  epilayers.

In this interim report we report the first results of annealing experiments on the epilayers and compare the characteristics of the annealed epilayers with those of the "as grown".

The "as grown" epilayers of  $\text{Hg}_{1-x}\text{Zn}_x\text{Te}$ , 0.15 ~~to~~ 0.24, exhibit p type conductivity with carrier concentration of the order  $1 \times 10^{15} \text{ cm}^{-3}$ . <sup>2 or =</sup> <sup>2 or =</sup> <sup>10 to the 15th</sup>  
In order to decrease the carrier concentration down to the level of  $1 \times 10^{14}$ , <sup>10 to the 14th</sup> the optimum carrier concentration for photodetectors, the epilayers were annealed in Hg atmosphere. The conditions of the annealing were similar to those which are generally used for the annealing of  $\text{Hg}_{1-x}\text{Cd}_x\text{Te}$ , namely, temperature of the sample around  $400^\circ\text{C}$  for several hours. About ten annealing experiments were done so far. Of the ten annealing experiments only three had successful results, decreasing the carrier concentration down to  $1 \times 10^{14} \text{ cm}^{-3}$ . In all the other samples the carrier concentration remained as high as in the non-annealed samples. So far, no dependence was found between minor changes in the annealing conditions and the annealing results.

The characteristics of sample HZ85AN which are presented in table 1, represent results on the epilayers successfully annealed. <sup>20A175786</sup>

20A175786  
70.2

Codes


Avail and/or  
Special

DTIC

COPY  
INSPECTED

A-1

Keywords:  
Mercury Compounds,  
Cadmium Tellurides



- 3 -

Table 1:

| <u>Characteristic</u>        | <u>"as grown"</u>                     | <u>Annealed</u>                       |
|------------------------------|---------------------------------------|---------------------------------------|
| Thickness                    | 18 $\mu$ m                            | 18 $\mu$ m                            |
| Max. Transmittance at 300K   | 20%                                   | 40%                                   |
| Measured cut off at 300k     | 6.1 $\mu$ m                           | 6.1 $\mu$ m                           |
| Estimated cut off at 80k     | 9.5 $\mu$ m                           | 9.5 $\mu$ m                           |
| Carrier concentration at 80k | 1 x 10 <sup>17</sup> /cm <sup>3</sup> | 1 x 10 <sup>16</sup> /cm <sup>3</sup> |
| Hall mobility at 80k         | 150cm <sup>2</sup> /V.sec             | 300cm <sup>2</sup> /V.sec             |
| FWHM                         | 100 arcsec                            | 100 arcsec                            |

It can be seen in table 1 that the carrier concentration decreased by an order of magnitude due to the annealing process. The other characteristics which should depend on the carrier concentration, namely the maximum transmittance in the IR and the Hall mobility were also changed. The crystalline quality of the epilayer was found by measuring the full width at the half maximum (FWHM of the X Ray rocking curve). This parameter and the cut off were not influenced by the annealing process.

Further characterization of the annealed samples is underway.

END

FEB.

1988

DTic