

AD-A187 067

13C AND 14N SOLID STATE NMR CHARACTERIZATION OF
ARAMID-CONTAINING NYLON-6 (U) UNIVERSITY OF SOUTHERN
MISSISSIPPI HATTIESBURG DEPT OF POLYME
D G POWELL ET AL 81 DEC 87 TR-7


1/1

UNCLASSIFIED

F/G 7/6

NL





AD-A187 067

OFFICE OF NAVAL RESEARCH

Contract N00014-86-K-0659

Technical Report No. 7

**¹³C AND ¹⁵N SOLID STATE NMR CHARACTERIZATION OF ARAMID-
CONTAINING NYLON-6 POLYMERS SYNTHESIZED BY IN SITU POLYMERIZATION
OF CAPROLACTAM WITH BENZOYL CAPROLACTAM DERIVATIVES**

by

Douglas G. Powell, Allison M. Sikes and Lon J. Mathias

Prepared for Publication in

Polymer Preprints, in press

Department of Polymer Science
University of Southern Mississippi
Southern Station Box 10076
Hattiesburg, MS 39406-0076

DTIC
ELECTE
DEC 14 1987
S D
H

Reproduction in whole or in part is permitted for any purpose of
the United States Government.

This document has been approved for public release and sale; its
distribution is unlimited.

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION NONE		1b. RESTRICTIVE MARKINGS NONE	
2a. SECURITY CLASSIFICATION AUTHORITY NONE		3. DISTRIBUTION/AVAILABILITY OF REPORT UNLIMITED	
2b. DECLASSIFICATION/DOWNGRADING SCHEDULE NONE			
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report # 7		5. MONITORING ORGANIZATION REPORT NUMBER(S) ONR N00014-86-K-0659	
6a. NAME OF PERFORMING ORGANIZATION University of Southern Mississippi	6b. OFFICE SYMBOL (if applicable)	7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c. ADDRESS (City, State, and ZIP Code) University of Southern Mississippi Polymer Science Department Southern Station Box 10076 Hattiesburg, MS 39406-0076		7b. ADDRESS (City, State, and ZIP Code) 800 North Quincy Avenue Arlington, VA 22217	
8a. NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research	8b. OFFICE SYMBOL (if applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8c. ADDRESS (City, State, and ZIP Code) 800 N. Quincy Avenue Arlington, VA 22217		10. SOURCE OF FUNDING NUMBERS PROGRAM ELEMENT NO. PROJECT NO. TASK NO. WORK UNIT ACCESSION	
11. TITLE (Include Security Classification) 13C and 15N Solid State NMR Characterization of Aramid-Containing Nylon-6 Polymers Synthesized by <u>in situ</u> Polymerization of Caprolactam with Benzoyl Caprolactam Derivatives			
12. PERSONAL AUTHOR(S) Douglas G. Powell, Allison M. Sikes and Lon J. Mathias			
13a. TYPE OF REPORT Technical	13b. TIME COVERED FROM TO	14. DATE OF REPORT (Year, Month, Day) 12/1/87	15. PAGE COUNT
16. SUPPLEMENTARY NOTATION Polymer Preprints, in press.			
17. COSATI CODES FIELD GROUP SUB-GROUP		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
19. ABSTRACT (Continue on reverse if necessary and identify by block number) Copolyamides were prepared by <u>in situ</u> polymerization from p-Aminobenzoylcaprolactam and caprolactam systems initiated with sodium hydride. The microstructure of the copolymers as determined by 13C solution NMR varied from alternating to blocks of aliphatic and/or aromatic units depending on the reaction conditions and the ratio of the comonomers. The solid-state CP/MAS 13C NMR were consistent with solution studies. Detailed interpretation was difficult due to large linewidth and number of resonances. Natural abundance CP/MAS 15N spectra were found to be less complicated. Based on these results and 15N studies with model amides, 15N CP/MAS was shown to be a useful technique for probing copolymer composition and microstructure.		20. DISTRIBUTION/AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS	
21. ABSTRACT SECURITY CLASSIFICATION		22a. NAME OF RESPONSIBLE INDIVIDUAL Lon J. Mathias	
22b. TELEPHONE (Include Area Code) (601)266-4868		22c. OFFICE SYMBOL	

**¹³C AND ¹⁵N SOLID STATE NMR CHARACTERIZATION OF
ARAMID-CONTAINING NYLON-6 BY IN SITU POLYMERIZATION
WITH BENZOYL CAPROLACTAM DERIVATIVES**

Douglas G. Powell, Allison M. Sikes, and Lon J. Mathias*
Department of Polymer Science
University of Southern Mississippi
Hattiesburg, Mississippi 39406 0076

INTRODUCTION

Polyamides and aramids are two important structural materials noted for their toughness, high modulus, and tensile strength.¹ They are currently used in a wide variety of applications as structural plastics and as reinforcing fibers in high performance composites.

Natural abundance ¹⁵N NMR spectroscopy has been used to characterize polyamides in solution.^{2,3,4,5} ¹⁵N NMR spectroscopy has several advantages over ¹³C NMR including larger spectral width and simpler spectra. Characterization of polyamides by solution ¹⁵N NMR is, however, hampered by the limited solubility of many polyamides, especially homo- and copolymers containing aromatic moieties. Polyamide nitrogens are subject to large chemical shift changes in the solvents needed to dissolve them.^{6,7} Moreover, solution studies cannot duplicate the crystalline structure or hydrogen bonding in solid polyamides.

Recently, polyamic acid precursors to polyimides have been characterized by solid state ¹⁵N CP-MAS NMR.⁸ We had previously prepared and characterized several aliphatic/aromatic copolyamides based on caprolactam and several N-benzoyl caprolactam initiators.⁹ (Figure 1) We have compared these results with ¹⁵N CP-MAS NMR data to evaluate the usefulness of the latter technique for polyamide microstructure characterization. In this paper we present the ¹⁵N CP-MAS NMR results for several copolyamides along with model amides used for chemical shift assignments.

EXPERIMENTAL

Caprolactam homo- and copolymers were prepared as previously described.^{9,10} Model amides were purchased from Aldrich Chemical Company and used as received. ¹⁵N solid state CP-MAS measurements were made on a Bruker MSL-200 NMR spectrometer equipped with a Bruker MAS solids accessory. Measurements were made in a 4.7T field corresponding to ¹H and ¹⁵N frequencies of 200.13 and 20.267 MHz, respectively. Cross-polarization was performed using a 5 μ s ¹H pulse and a contact pulse of 1 to 5 ms to meet the Hartmann-Hahn condition. MAS rotor speeds were 3.0 to 3.2 KHz. Sample temperature was maintained at 300K. Spectral widths were 25 KHz. Between 20,000 and 50,000 scans were acquired for each sample with a delay of 3 s between scans. Chemical shifts are reported relative to ¹⁵NH₄NO₃ (NO₃ = 0 ppm; ¹⁵NH₄ = -353.5 ppm) as an external standard. Solution ¹⁵N measurements were made using an inverse-gated decoupling technique with a

pulse width of 25 μ s. All solution spectra were obtained in concentrated sulfuric acid solvent. $^{15}\text{NH}_4\text{NO}_3$ dissolved in D_2O was used as the reference ($\text{NH}_4^+ = -353.5$ ppm), by inserting a tube containing the solution coaxially into the sample.

RESULTS AND DISCUSSION

^{15}N chemical shifts of model amides and polyamides are listed in Table I. As expected, the chemical shifts of the solid samples are approximately 30 ppm upfield of the solution resonances. Protonation of the amide carbonyl causes unpredictable shifts in ^{15}N resonances depending on the pK_a of the amide and solvent acidity.⁹ Typical linewidths at half height were 8-10 ppm.

The solid-state chemical shifts of di-functional initiated and star initiated nylon-6 are similar to wholly linear nylon 6 although the star polymer is insoluble in concentrated H_2SO_4 . We were disappointed to find that nitrogens on the initiator species were not visible in the spectrum. The low concentration of initiator (<1%) makes this technique inadequate without ^{15}N enrichment in the initiator. With atom enrichment, determination of the number of imide sites consumed would give the efficiency of initiation as well as confirm the synthesis of a star polymer.¹⁰

Figure 2 shows the ^{15}N CP-MAS spectra of a previously prepared copolymer of p-aminobenzoic acid and caprolactam with alternating aliphatic and aromatic units. This copolymer consists of only two types of amide nitrogens in equal proportions. The resonances at -240.6 and -261.3 show equivalent areas consistent with the alternating copolymer structure. Comparison with the model acetanilide (-241.9) indicates the downfield resonance is due to the aromatic substituent on the nitrogen. N-methyl benzamide, however, lies well upfield of any other resonances in the Table. It is apparently a poor model for an aliphatic substituted amide in the copolymer. A possible explanation is that the methyl group of these models cannot duplicate the effects of an aliphatic chain on the nitrogen resonance. These "neighboring residue effects" have also been recognized in solution ^{15}N experiments as well.²⁻⁶ The solution ^{15}N spectrum of the copolymer in sulfuric acid is also shown and is consistent with the solid state spectrum with the exception of large chemical shift changes.

Figure 3 shows a series of copolymers synthesized under conditions slightly different than those for the alternating copolymer. By altering conditions it was found that blocks of aromatic units could be generated *in situ* and incorporated into novel copolymers. Figure 3a shows a copolymer containing blocks of p-benzamide with few caprolactam units. The downfield shift of the ^{15}N resonance is consistent with nitrogen in a deshielding environment between an aromatic ring and carbonyl group. This shift also compared favorably with the ^{15}N spectrum of fully aromatic

poly(p-benzamide) (-248.5 ppm). Figures 3b and 3c show copolymers containing 3% and 20% aramid units, respectively, with the remainder being caprolactam units. The upfield shift is consistent with the of nylon-6 spectrum shown in 3d. The copolymer peak, however, is 5-6 ppm downfield of the homopolymer. It is surprising that the presence of the aramid species causes such a shift even though the concentration is too low for the aramid ^{15}N resonances to be seen. Solution ^{15}N NMR of these samples gave a chemical shift identical to that of the nylon-6 homopolymer.

The presence of two crystal forms of nylon-6 is well known and both have been previously characterized by IR and x-ray.^{11,12} Figures 4a and 4c show the ^{15}N NMR of α and γ crystal forms of nylon-6, respectively, while 4b shows a mixture that is predominately α . Although ^{13}C and ^{15}N chemical shifts have been reported to be conformationally dependent,¹³ the ^{13}C CP-MAS chemical shifts were identical for both crystal forms. It is clear that ^{15}N solid state NMR is a better tool for differentiating the two crystal forms. Moreover, the the chemical shifts correlate well with observed nylon-6 resonances seen in the copolymers in Figure 3. The ^{15}N solid state NMR clearly shows that the nylon-6 blocks in the copolymers are mostly of the γ form.

SUMMARY AND CONCLUSION

Natural abundance ^{15}N NMR of solids has been demonstrated as a useful characterization tool for polyamides. Anisotropies and crystal forms can be examined in the solid phase which are not present in solution. ^{15}N CP MAS NMR provides a new method for determining the crystal structure of nylon-6. The greater sensitivity of nitrogen to its environment in solid state NMR compared to carbon opens up a broad area for study of crystalline polyamides. Potential also exists for characterization of peptides and other nitrogen containing crystalline materials using ^{15}N CP-MAS NMR to complement traditional X-ray analysis.

ACKNOWLEDGEMENT

We gratefully acknowledge the Department of Defense grant for purchasing the solid state NMR, and the Office of Naval Research and ICI Americas for support of our work on composites.

1. G. Odian, "Principles of Polymerization," 2nd ed., Chap. 1, John Wiley and Sons, Inc., New York, 1981.
2. Kricheldorf, H.R.; Hull, W.E. Makromol. Chem. 1981, **182**, 1177; Macromolecules, 1980, **13**, 87.
3. Kricheldorf, H.R. Makromol. Chem., 1978, **179**, 2687.

4. Kricheldorf, H.R.; Joshi, S.V. J. Poly. Sci.: Poly. Chem. Ed., **1982**, 20, 2791.
5. Kricheldorf, H.R.; Schilling, G. Makromol. Chem., **1978**, 179, 2667.
6. Kricheldorf, H.R. Makromol. Chem., **1978**, 179, 2675.
7. Martin, G.J.; Martin, N.L.; Gouennard, J.-P. "¹⁵N NMR Spectroscopy," Chap. 5. Springer-Verlag, Berlin, 1981, p. 57-58.
8. Weber, W.D.; Murphy, P.D. Preprints of the PMSE Division of ACS, **Fall 1987**, 57, 341.
9. Mathias, L.J.; Moore, D.R.; Smith, C.A. J. Polym. Sci.: Part A: Polym. Chem., **1987**, 25, 2699.
10. Mathias, L. J.; Sikes, A. M. "Chemistry, Properties, and Applications of Crosslinking Systems," A. C. S. Symposium Series, in press.
11. Holmes, D.R.; Bunn, C.W.; Smith, D.J. J. Poly. Sci., **1955**, 17, 159.
12. Arimoto, H. J. Poly. Sci. Part A, **1964**, 2, 2283.
13. Shoji, A.; Ozaki, T.; Fujito, T.; Deguchi, K.; Ando, I. Macromolecules, **1987**, 20, 2441.

TABLE I

	<u>CP-MAS</u>	<u>Solution</u>
N-methyl benzamide	-273.3	-226.3
Acetanilide	-241.9	-221.0
poly(p-benzamide)	-248.5	-----
Alternating copolymer	-240.6, -261.3	-224.1, -229.2
Nylon-6 (annealed)	-261.7	} 228.4
3-Arm star nylon-6	-258.4	
Nylon-6 (quenched)	-256.7, -261.1	

LIST OF FIGURES


Figure 1: a) Synthesis of aliphatic/aromatic block and alternating copolymers;
b) Synthesis of nylon-6 star polymers using tri functional initiator.

Figure 2: ^{15}N CP-MAS spectrum (upper trace) and ^{15}N solution spectrum (LLSOL) of poly(p-benzamide-alt-caproamide) alternating copolymer


Figure 3: ^{15}N CP-MAS NMR spectra of block copolymers of caprolactam and p-aminobenzoic acid: a) 80-90 mole% aromatic comonomer; b) 10 mole % aromatic comonomer; c) 20 mole % aromatic comonomer; d) nylon-6 homopolymer



Figure 4: ^{15}N CP-MAS NMR OF Nylon-6 homopolymer crystal forms: a) mainly gamma nylon-6; b) predominately alpha nylon-6; c) alpha nylon-6


a)




b)









END

DATE

FILMED

JAN

1988