

AD-A191 998

A REVIEW OF MULTIAXIAL FATIGUE AND FRACTURE OF
FIBRE-REINFORCED COMPOSITES (U) AERONAUTICAL RESEARCH

171

UNCLASSIFIED

LAOS DEL MONTE (AUSTRALIA) P M BEAVER JAN 87
ARL-STRUC-TH-464 DOD-AR-884-545

F/G 11/4

NL

END

DATE
FILMED
13



DTIC FILE COPY

AD-A191 990



DEPARTMENT OF DEFENCE
DEFENCE SCIENCE AND TECHNOLOGY ORGANISATION
AERONAUTICAL RESEARCH LABORATORIES

MELBOURNE, VICTORIA

Structures Technical Memorandum 464

A REVIEW OF MULTIAXIAL FATIGUE AND FRACTURE
OF FIBRE-REINFORCED COMPOSITES (U)

by

P.W. BEAVER

DTIC
ELECTE
MAR 09 1988
S H D

Approved for public release.

This work is copyright. Apart from any fair dealing for the purpose of study, research, criticism or review, as permitted under the Copyright Act, no part may be reproduced by any process without written permission. Copyright is the responsibility of the Director Publishing and Marketing, AGPS. Inquiries should be directed to the Manager, AGPS Press, Australian Government Publishing Service, GPO Box 24, Canberra, ACT 2600.

JANUARY 1937

DISTRIBUTION STATEMENT A

Approved for public release
Distribution Unlimited

88 3 01 106

DEPARTMENT OF DEFENCE
DOCUMENT CONTROL DATA

PAGE CLASSIFICATION
UNCLASSIFIED

PRIVACY MARKING

1a. AR NUMBER AR-004-545	1b. ESTABLISHMENT NUMBER ARL-STRUC-TM-464	2. DOCUMENT DATE JANUARY 1987	3. TASK NUMBER DST 86/009
4. TITLE A REVIEW OF MULTIAXIAL FATIGUE AND FRACTURE OF FIBRE-REINFORCED COMPOSITES		5. SECURITY CLASSIFICATION (PLACE APPROPRIATE CLASSIFICATION IN BOX (S) IE. SECRET (S), CONFIDENTIAL (C), RESTRICTED (R), UNCLASSIFIED (U).) ☐ U ☐ U ☐ U DOCUMENT TITLE ABSTRACT	6. No. PAGES 39
		7. No. REFS. 35	
8. AUTHOR (S) P.W. BEAVER		9. DOWNGRADING/DELIMITING INSTRUCTIONS NOT APPLICABLE	
10. CORPORATE AUTHOR AND ADDRESS AERONAUTICAL RESEARCH LABORATORIES P.O. BOX 4331, MELBOURNE VIC. 3001		11. OFFICE/POSITION RESPONSIBLE FOR SPONSOR _____ SECURITY _____ DOWNGRADING _____ APPROVAL _____	
12. SECONDARY DISTRIBUTION (OF THIS DOCUMENT) Approved for public release. OVERSEAS ENQUIRIES OUTSIDE STATED LIMITATIONS SHOULD BE REFERRED THROUGH ASDIS, DEFENCE INFORMATION SERVICES BRANCH, DEPARTMENT OF DEFENCE, CAMPBELL PARK, CANBERRA, ACT 2801			
13a. THIS DOCUMENT MAY BE ANNOUNCED IN CATALOGUES AND AWARENESS SERVICES AVAILABLE TO..... No limitations			
13b. CITATION FOR OTHER PURPOSES (IE. CASUAL ANNOUNCEMENT) MAY BE ☒ UNRESTRICTED OR ☐ AS FOR 13a.			
14. DESCRIPTORS Multiaxial stress, Fibre reinforced composites, Fracture strength, AUSTRALIA Fatigue life, Fatigue limit,		15. DDOA SUBJECT CATEGORIES 0071F	
16. ABSTRACT A review of the limited number of papers in the literature on multiaxial fatigue and fracture of fibre-reinforced composites has shown that biaxial stress states can have a significant effect on both the fatigue and fracture properties of these materials. In addition, none of the presently available failure theories for composites agrees with the observed experimental results with sufficient accuracy to be confidently used for design purposes. K. J. G. 1/2			

PAGE CLASSIFICATION

UNCLASSIFIED

PRIVACY MARKING

THIS PAGE IS TO BE USED TO RECORD INFORMATION WHICH IS REQUIRED BY THE ESTABLISHMENT FOR ITS OWN USE BUT WHICH WILL NOT BE ADDED TO THE DISTIS DATA UNLESS SPECIFICALLY REQUESTED.

16. ABSTRACT (CONT.)

17. IMPRINT

AERONAUTICAL RESEARCH LABORATORIES, MELBOURNE

18. DOCUMENT SERIES AND NUMBER

STRUCTURES TECHNICAL
MEMORANDUM 464

19. COST CODE

25 1070

20. TYPE OF REPORT AND PERIOD COVERED

21. COMPUTER PROGRAMS USED

22. ESTABLISHMENT FILE REF. (S)

23. ADDITIONAL INFORMATION (AS REQUIRED)

CONTENTS

	Page No.
1. INTRODUCTION	1
2. MULTIAXIAL TESTING TECHNIQUES	2
3. MULTIAXIAL FAILURE CRITERIA FOR BOTH STATIC AND CYCLIC LOADING	6
4. EFFECTS OF BIAXIAL LOADING ON STATIC STRENGTH	11
5. EFFECTS OF BIAXIAL LOADING ON FATIGUE PROPERTIES	18
6. CONCLUSIONS	27
ACKNOWLEDGEMENT	27
REFERENCES	29
APPENDIX - ADDITIONAL REFERENCES NOT CITED IN TEXT	34



Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

NOTATION

$\sigma_1, \sigma_2, \sigma_6$	normal and shear stresses in the direction of principal material axes
$X, Y, S,$	tensile strengths in the principal material directions and the $0^\circ - 90^\circ$ principal shear strength
X', Y'	compressive strengths in the principal material directions
K_1, K_2	constants evaluated under combined stress tests
F_{12}	normal stress interaction component of a strength tensor
$\lambda = \sigma_1/\sigma_2$	biaxial stress ratio
X_0	yield strength for an unnotched uniaxial specimen
$\Delta\sigma$	axial tensile stress range
$\Delta\tau$	shear stress range
N_f	number of cycles to failure
da/dN	crack growth rate
ΔK	stress intensity factor range

1. INTRODUCTION

The use of fibre-reinforced composites in high performance structures and components, such as found in the aircraft and power generation industries, has increased rapidly in recent years. Their high specific strength and specific modulus, excellent corrosion properties and design flexibility make them ideally suited for many applications, especially when there is a need to save weight and conserve energy. However, the ability to predict the strength and safe fatigue life of composite structures and components has not kept pace with the increase in the number of new applications, i.e. design in composites has been hampered by the lack of proven design procedures.

Most design data for composite materials are obtained by testing laboratory specimens of simple geometry with the principal fibre direction usually parallel to the loading direction. In addition the specimens are treated as if they were homogeneous and that the failure condition is defined by separation into two pieces. In comparison, most engineering structures and components operate under multiaxial loading conditions and the general stress states may be further complicated by the presence of geometric discontinuities, such as notches, holes or joints. Furthermore, it is difficult to fabricate a homogeneous and defect-free composite component. Such components can fail in several different modes prior to complete separation.

At present, the amount of multiaxial fatigue and fracture research on engineering materials has been limited compared with that undertaken for uniaxial loading conditions. This situation has arisen for the following reasons:

- i) There has been a lack of reliable multiaxial or biaxial testing machines as the design, development and experimental work associated with building such equipment tends to be complicated, time consuming and expensive compared with that for uniaxial testing systems [1,2].
- ii) Intricate specimen designs are required, hence the specimens also are expensive [3].

- iii) There is no substantial theoretical framework for analysing the data [4].
- iv) The experimental work is time consuming.
- v) A large number of test results are required to develop and prove or disprove empirical criteria [3].

The influence of multiaxial stresses on material properties is starting to receive considerable attention [5] as some isotropic materials have shown significant biaxial loading effects. For example, a recent review of the literature [6, 7] has shown that for metals the more damaging biaxial stress states can (compared with uniaxial tension) decrease the low-cycle fatigue life by factors of up to 20, accelerate fatigue crack growth rates by factors of 3 to 4, and decrease critical stress intensity factors and stress intensity notch correction factors by up to 50%. The effects of multiaxial stressing on the fatigue and fracture properties of fibre-reinforced composites are recognized as being even more complex than for metals because (1) biaxial stresses may enhance the damage during loading as a result of the anisotropy of strength and stiffness, and (2) several additional problems are encountered during multiaxial testing of composites, such as premature failure of a specimen near the end attachments as a result of poor load transfer.

The objective of this report is to review the limited literature on the effects of multiaxial stress on the fatigue and fracture properties of fibre-reinforced composites. To the best of the author's knowledge no such review has been published.

2. MULTIAXIAL TESTING TECHNIQUES

A wide variety of techniques has been used to test laboratory specimens under multiaxial stress states [8,9]. Of these only three appear useful for studying the complex behaviour of composite materials

under such stresses: these are the off-axis [10,11], the thin-walled tubular [11-14] and the cruciform [11, 15-17] specimen methods.

The off-axis (Fig. 1(a)) method is the simplest, cheapest and most widely used method of measuring the biaxial stress-strain behaviour relative to the fibre direction. However, this method has several limitations, the most significant being (1) the lack of independent control of the biaxial stress components, so that only a limited range of stress states is possible, and (2) that the application of the applied stress produces a shear in the material at the grips, which may cause premature failure in that region.

A greater range of biaxial stress states can be achieved by subjecting thin-walled tubular specimens to a combination of axial loading, torsion and internal and/or external pressure, Fig. 1(b). This specimen geometry is more versatile than the off-axis geometry as it is possible to apply any desired biaxial stress state (with or without proportional loading) together with triaxial stress states, although these are seldom used. Tubular specimens are very useful for the yield and fracture testing of unnotched composites. However, several of the problems with this technique are:

- i) It is difficult to fabricate high quality tubes with no overlaps or discontinuities in the reinforcement and yet with a uniform wall thickness.
- ii) The specimens are expensive.
- iii) Specialised testing equipment is required.
- iv) The use of oil to pressurise tubes can lead to environmental effects on crack initiation and propagation. [This can be minimised by the use of a rubber sleeve to prevent contact between the oil and the specimen surface].




FIG. 1 Schematic representation of (a) the off-axis, (b) thin-walled tubular and (c) cruciform methods for producing biaxial stress states.

- v) The hydrowedge effect may be encountered, that is, high pressure oil may enter a crack and wedge it open thereby providing an additional mode I opening stress. [This effect can also be minimised by using a rubber sleeve].
- vi) It is difficult to design specimen end attachments to give good load transfers without failures in these regions.
- vii) Fatigue crack propagation tests with through-thickness cracks are impossible.

A full range of biaxial stress states can also be achieved in flat cruciform-shaped specimens by simultaneously applying two principal stresses σ_1 and σ_2 along mutually perpendicular loading arms, Fig. 1(c). This technique is the most suitable means for biaxial testing of notched composites and for biaxial fatigue crack propagation studies, and has been used with some success for yield and fracture testing of a few composite materials. Compared with tubular specimens, this type of specimen is easier and cheaper to fabricate, fibre overlaps and discontinuities are avoided, and there are no environmental or hydrowedge effects from a pressurising fluid. However, biaxial testing of cruciform-shaped specimens still requires specialised testing equipment and the specimens are still expensive. Other disadvantages of this technique are:

- a) Stress determinations and strain measurements in the test area are difficult.
- b) Differences between the stiffnesses of the loading arms and the test area exist. These differences, which depend on stress state, make it difficult to test in equibiaxial tension.
- c) Problems can be encountered in testing unnotched specimens, as premature failure may occur at areas of stress concentration such as corner fillets.

3. MULTIAXIAL FAILURE CRITERIA FOR BOTH STATIC AND CYCLIC LOADING

At present more than 40 multiaxial failure theories for composites have been proposed [18] which can be used for both static and cyclic loading. Most of these are based on only a limited amount of experimental data since multiaxial testing is both expensive and difficult. Moreover, these theories all use complete separation as the failure criterion and do not consider the various deformation mechanisms such as debonding, resin cracking, delamination or fibre fracture which can produce local failure before complete separation occurs. Owen and Rice [19] found that the mechanisms which cause a composite to fail depend on the matrix/fibre combination, specimen design, type of loading and stress state.

There are two main groups of failure theories for anisotropic materials under biaxial loading conditions. Group 1 theories require only the normal stresses and shear stresses in the direction of the principal material axes whereas the theories in the second group require both biaxial strength values and shear strength values. Some of the better known failure theories in each group for composite materials under plane stress conditions are listed in Table 1. These failure theories are generally represented graphically as a surface in 3-dimensional Cartesian space using σ_1 , σ_2 and σ_6 as the co-ordinate axes, where σ_1 and σ_2 are the in-plane normal stresses, and σ_6 is the in-plane shear stress in the directions of the principal material axes. In practice it is easier to represent a failure surface by a series of planar sections through the surface, examples of which are shown in Fig. 2 for glass-polyester composites.

Thorough investigation of any failure theory requires a comparison of experimental data from biaxial tests over a wide range of values of σ_1 , σ_2 and σ_6 . Most of the failure theories have been supported by data obtained from static off-axis tests to rupture [10]. Unfortunately, it is difficult to discriminate between the various theories by these tests because they cover only a small part of the failure surface [10]. For better discrimination, Owen, Found, Rice and Griffith [10,11,12,14,18-

TABLE 1: Some of the better known static failure theories for anisotropic materials under plane stress conditions [14].

1. *Goldenblat and Kopnov*

$$\frac{1}{2} \left(\frac{1}{X} - \frac{1}{X'} \right) \sigma_1 + \frac{1}{2} \left(\frac{1}{Y} - \frac{1}{Y'} \right) \sigma_2 + \left[\frac{1}{4} \left(\frac{1}{X} + \frac{1}{X'} \right)^2 \sigma_1^2 + \frac{1}{4} \left(\frac{1}{Y} + \frac{1}{Y'} \right)^2 \sigma_2^2 + 2 F_{12} \sigma_1 \sigma_2 + \frac{\sigma_6^2}{S} \right]^{\frac{1}{2}} = 1$$
2. *Tsai and Wu*

$$\left(\frac{1}{X} - \frac{1}{X'} \right) \sigma_1 + \left(\frac{1}{Y} - \frac{1}{Y'} \right) \sigma_2 + \frac{\sigma_1^2}{XX'} + \frac{\sigma_2^2}{YY'} + 2 F_{12} \sigma_1 \sigma_2 + \frac{\sigma_6^2}{S} = 1$$
3. *Modified Fischer*

$$\frac{\sigma_1^2}{X^2} - \frac{K_1 \sigma_1 \sigma_2}{XY} + \frac{\sigma_2^2}{Y} + \frac{\sigma_6^2}{S} = 1$$
4. *Modified Marin*

$$\frac{\sigma_1^2 - K_2 \sigma_1 \sigma_2}{XX'} + \frac{\sigma_2^2}{YY'} + \left(\frac{X' - X}{XX'} \right) \sigma_1 + \left(\frac{Y' - Y}{YY'} \right) \sigma_2 + \frac{\sigma_6^2}{S} = 1$$
5. *Marin*


$$\left(\frac{X' - X}{XX'} \right) \sigma_1 + \left(\frac{1}{Y} - \frac{Y}{XX'} \right) \sigma_2 + \left(\frac{2}{XX'} - \frac{X'X - S(X' - X - X' \left[\frac{X}{Y} \right] + Y)}{XX'S^2} \right) \sigma_1 \sigma_2 + \frac{\sigma_1^2}{XX'} + \frac{\sigma_2^2}{XX'} = 1$$
6. *Norris and McKinnon*

$$\frac{\sigma_1^2}{X} + \frac{\sigma_2^2}{Y} + \frac{\sigma_6^2}{S} = 1$$
7. *Norris distortional energy*

$$\frac{\sigma_1^2}{X} - \frac{\sigma_1 \sigma_2}{XY} + \frac{\sigma_2^2}{Y} + \frac{\sigma_6^2}{S} = 1$$


NOTATION

$\sigma_1, \sigma_2, \sigma_6$	normal and shear stresses in the direction of the principal material axes	K_1, K_2	constants evaluated under combined stress tests
X, Y, S	tensile strengths in the principal material directions and the 0° - 90° principal shear strength	F_{12}	normal stress interaction component of a strength tensor
X', Y'	compressive strengths in the principal material directions		



(a)

FIG. 2 Comparison of theoretical failure curves with experimental results for two glass-polyester composites (a) Y449/T500 and (b) Y449/T500P [14] (σ_1 and σ_2 are the stresses in the directions of the principal material axes).



(b)

FIG. 2 (cont)

21] evaluated the various failure theories for several glass-polyester composites for both static and cyclic loading using thin-walled tubes under combined axial loading and internal/external pressure. This method offers the most comprehensive way of evaluating the complete failure surface. They tested over 1200 thin-walled tubular specimens under various biaxial loading conditions during a ten year period, and the main conclusions from their work are as follows:

- i) None of the Group 1 theories was entirely adequate as a different failure theory is required for each stress octant.
- ii) The fit of a failure theory varies from one material to another and is worse for fatigue loading than for static loading.
- iii) A reasonable fit between the Group 2 theories and experimental results can only be achieved by a subjective choice of the biaxial data, because the shape of the failure surface is dependent on (a) the stress ratio chosen to evaluate the interaction coefficients F_{12} and K_2 , and (b) the value of the in-plane shear strength σ_6 (determined from a torsion test) which is a function of the length of the tubular specimens used.
- iv) The shapes of the Group 2 failure surfaces are also very sensitive to experimental scatter (which is significant and should be treated statistically) and to changing failure modes.
- v) Existing failure theories do not take into account the various deformation mechanisms and failure modes which are dependent on lay-up, specimen design and stress state.
- vi) For most commercial applications of fibre-reinforced composites the expense and effort in using thin-walled tubular specimens to evaluate the various failure theories cannot be justified.

The overall conclusion from this comprehensive research program was that any failure theory should be used with extreme caution. Similarly, Rowlands [22,23] concluded that none of the failure theories agreed with his experimental results with sufficient accuracy to be confidently used in design. Found [11] later suggested that a conservative estimate of failure for design purposes, for both biaxial static and fatigue loading conditions, could be obtained for tension/tension stress states by using the Norris interaction (Norris and McKinnon) theory [14] i.e.

$$\left(\frac{\sigma_1}{X} \right)^2 + \left(\frac{\sigma_2}{Y} \right)^2 = 1 \quad (1)$$

and for tension/compression stress states by using the maximum shear stress theory i.e.

$$\frac{\sigma_1}{X} - \frac{\sigma_2}{Y'} = 1 \quad (2)$$

However, he suggested that further work was needed to verify these simple criteria.

4. EFFECTS OF BIAXIAL LOADING ON STATIC STRENGTH

The effects of biaxial loading on the static strength of composite materials have been determined by only a few workers and for different specimen geometries. Bert, Mayberry and Ray [15] tested glass-epoxy (181-style E-glass cloth/Epon 828 E-epoxy) unnotched cruciform-shaped specimens in biaxial tension. They found that the values of the limit strength (0.01 percent strain offset) generally increased as the stress state changed from uniaxial tension to biaxial stress ratios of $\lambda = 0.5, 1.0$ and 2.0 as shown in Figs 3(a) and (b) [$\lambda = \sigma_2/\sigma_1$, where σ_1 and σ_2 are the maximum and minimum stresses in the directions of the principal material axes]. The ultimate strength values were also dependent on stress state. However these differences, when expressed as a percentage of the uniaxial value, were smaller than those for the limit strength values.

The effects of biaxial stress ratio on the static failure strengths of plain weave fabric, woven roving fabric and chopped strand mat glass-polyester composites were determined by Owen and coworkers [14,20,21] when evaluating the various failure theories described in the previous Section. They found that the maximum hoop stress at failure in the thin-walled tubular specimens (with the principal material axis parallel to the principal loading direction) increased as the biaxial stress ratio λ changed from -1.0 through to 0.5, and then decreased slightly for $\lambda = 1.0$ as shown for example in Fig. 4(a) and Table 2. The effects of biaxial loading on the failure strength were even more pronounced when the principal material axis was at 45° to the principal loading direction, Fig. 4(b) and Table 2. These results suggest that the layup of the composite is important in determining the magnitude of the biaxial load effect on the static strength of composites.

Guess and Gerstle [24] using unnotched, thin-walled, filament-wound tubular specimens also found that the static failure strengths of two graphite - and one Kevlar - epoxy composites were, in general, significantly greater for biaxial tension than for either axial or circumferential uniaxial tension, Table 3. They suggested that in the composite layups which they tested, the reinforcing effect of the fibres is greater with biaxial stress states. Similarly, Hotter, Schelling and Krauss [25] found that the failure strengths of unnotched thin-walled tubular specimens made from a glass-epoxy composite were greater in biaxial tension than uniaxial tension.

More recently, Jones, Poulou and Liebowitz [26] tested graphite-epoxy cruciform-shaped specimens containing central holes in biaxial tension. They found that the biaxial stress ratio λ had a significant effect on both the fracture plane and the static failure strength. For quasi-isotropic $[0/\pm 45/90]_s$ laminates the static strength values increased by a factor of 1.44 as λ increased from 0 to 1, Table 4, and the fracture plane rotated from being one at 90° to the principal loading direction to one at approximately 45° . Daniel [27] also found that the static strengths of quasi-isotropic graphite-epoxy specimens of similar geometry






FIG. 3 Biaxial-tension strength envelopes for two different lay ups of a glass-epoxy composite (a) four parallel-ply lay up and (b) four-ply symmetrically cross lay up [15].

TABLE 2: Effects of biaxial stress ratio on the failure stresses of a glass fabric (TYGLASS Y449) - polyester resin (BEETLE L2615 BIP Chemicals Ltd) composite [21].

Orientation of fibres with respect to the principal loading direction (α)	Applied biaxial stress ratio ($\lambda = \sigma_{\text{HOOP}}/\sigma_{\text{AXIAL}}$)	Stress at failure (MPa)	
		σ_{HOOP}	σ_{RADIAL}
0°	-∞ (axial compression)	0	-266
	-1.0	167	-149
	-0.5	237	-62
	0	266	0
	+0.5	266	132
	+1.0	242	233
	+∞ (axial tension)	0	266
45°	-∞ (axial compression)	0	-200
	-1.0	103	-91
	-0.5	156	-64
	0	204	0
	+0.5	270	134
	+1.0	233	241
	+∞ (axial tension)	0	200


TABLE 3: The effect of biaxial stress ratio on the failure strength values (normalized with respect to the uniaxial values) for two graphite - and one Kevlar-epoxy composites [24] [Z and θ represent the axial and circumferential directions of tubular specimens respectively].

Filament/resin	Stress ratios $\sigma_{\theta}:\sigma_Z$	Normalized strengths	
		$\frac{\sigma_{\theta}}{F_{\theta}}$	$\frac{\sigma_Z}{F_Z}$
T75/332 - T403	0:1	0.0	1.10
	1:0	1.02	0.00
	1:0	0.98	0.00
	1:1	1.071	1.10
T400/332-T403	1:0	1.064	0.00
	1:0	1.013	0.00
	1:0	0.922	0.00
	1:1	1.146	1.18
	2:1	1.429	0.74
Kevlar 49/332-T403	0:1	0.000	1.00
	1:0	1.04	0.00
	1:0	0.956	0.00
	1.6:1	1.435	0.77
	2:1	1.23	0.60



(a)

FIG. 4 Static and constant fatigue-life curves for rupture of glass-polyester thin-walled tubes with two different orientations between the principal material axes and the principal loading directions (a) $\alpha = 0^\circ$ and (b) $\alpha = 45^\circ$ [21].



(b)

FIG. 4 (cont)

were greater in equibiaxial tension ($\lambda = 1$) than uniaxial tension by approximately 30% for the same hole radius, Fig. 5.

Biaxial strength data exist for cruciform-shaped specimens containing sharp cracks and slots. Daniel [28] tested quasi-isotropic $[0/\pm 45/90]_s$ graphite-epoxy cruciform specimens containing sharp cracks inclined at 30° to the principal loading direction and parallel to a principal material axis. The static failure strengths in biaxial tension were approximately 20% below the uniaxial value indicating an appreciable contribution to failure by the shear stress, Fig. 6. Pascoe and Tutton [17] tested cruciform specimens containing two transverse edge slots oriented at 45° to both the principal material axis and the principal loading axis. These specimens were also fabricated using a quasi-isotropic graphite-epoxy composite. The static failure strength for this type of geometric discontinuity was not significantly affected by the biaxiality of loading. It is difficult to draw any conclusions from the results of Daniel and Pascoe and Tutton other than to suggest that the effects of biaxial loading on static strength depend on the nature of the geometric discontinuity, and its orientation with respect to both the principal material axis and principal loading direction.

5. EFFECTS OF BIAxIAL LOADING ON FATIGUE PROPERTIES

The assessment of multiaxial fatigue behaviour of composites is very important not only for the safe and reliable operation of composite structures and components but also for a more complete understanding of the fundamental nature of the cyclic damage and failure mechanisms. The few papers published on this subject have shown that multiaxial loading can have a considerable effect on the fatigue lives of composite materials [13,21,29-33]. For example, Owen, Found and Griffith [13,21] observed that the fatigue lives of glass-polyester thin-walled tubes, with the principal material axes parallel to the principal loading directions ($\alpha = 0$), decreased by a factor of approximately 100 when the biaxial stress ratio λ changed from +0.5 to -1.0. This decrease in fatigue life was much greater when the principal material axes were inclined at 45° to the principal loading directions, as shown for example in Figs 4 and 7.

TABLE 4: Effect of biaxial stress ratio on the tensile static strength parallel to the principal material axis of $[0/\pm 45/90]_3$ graphite-epoxy cruciform-specimens containing 25 mm diameter holes [26].

Biaxial stress ratio (λ)	Breaking load (kN)	Static failure strength (MPa)
0	55.2	349
0	56.9	356
0.5	64.9	405
1.0	81.0	507




FIG. 5 Strength reduction as a function of hole radius for a $[0/\pm 45/90]$ graphite-epoxy plate under uniaxial and biaxial tension [X_0 is the yield strength for an unnotched uniaxial specimen] [27].




FIG. 6 The effect of biaxial loading including a shear component on the strength of a $[0/\pm 45/90]$ graphite-epoxy plate containing a crack. The shear component was produced by inclining both the fibre axes and the crack at 30° to the side of the specimen. [X_0 is the yield strength of an unnotched uniaxial specimen] [29].

Francis and coworkers [29,30] observed similar changes in the fatigue lives of graphite-epoxy thin-walled tubes containing a small hole and having a $[\pm 45]$ layup, Fig. 8. A power law was fitted to the data using regression analyses i.e.

$$\sigma_{\max} = AN^B \quad (3)$$

where A and B are the co-efficient and exponent respectively, $\sigma_{\max}$ is the maximum stress of the cycle and N is the number of cycles to failure. The results of this analysis (given in Fig. 8) showed that the coefficient decreased with increasing tension to torsion ratio. Figure 8 also shows that when the tension to torsion ratio is 1:1 the fatigue life is reduced by a factor of about 100 compared with tension alone, and that when the ratio is 1:2 the life reduction is much greater.

In order to compare the results on a more scientific basis the octahedral shear stresses were calculated for each of the conditions. Figure 9 shows the transformed data. On this basis the multiaxial effects are reversed but again large differences in life are apparent.

Wang, Chim and Socie [31] studied the biaxial fatigue behaviour of glass-epoxy (G-10 grade) tubular specimens subjected to in-phase cyclic tension and torsion loading at cryogenic temperatures. They found strong biaxial effects and their conclusions can be summarised as follows:

- i) At any given cyclic axial stress range the fatigue life was considerably reduced by increasing the cyclic shear stress range, Fig. 10.
- ii) Similarly, at any given shear stress range the fatigue life decreased by increasing the cyclic axial stress range, Fig. 11.




FIG. 7 Stress-life curves for biaxial fatigue loading of a glass-polyester composite for two orientations of the principal material axes to the principal loading axes: $\alpha = 0$ and $\alpha = 45^\circ$ [21].




FIG. 8 Maximum axial stress-life curves for biaxial fatigue loading of $[\pm 45]_s$ graphite-epoxy tubes with a 4.8 mm diameter hole [29].




FIG. 9 Octahedral shear stress-life curves for biaxial fatigue loading of $[\pm 45]_s$ graphite-epoxy tubes with a 4.8 mm diameter hole [29].




FIG. 10 Axial tensile stress range $\Delta\sigma$ versus cycles to failure curves for several values of shear range versus $\Delta\tau$ in cryogenic biaxial fatigue of a glass-epoxy composite [31].




FIG. 11 Shear Stress range $\Delta\tau$ versus cycles to failure curves for several values of axial tensile stress range $\Delta\sigma$ in cryogenic biaxial fatigue of a glass-epoxy composite [31]

- iii) The damage mechanisms were generally very complex. Extensive matrix cracking, fibre/matrix debonding, tensile fracture of load bearing fibres, microbuckling of fibre bundles and interlayer delamination all occurred during the fatigue loading. The severity of the individual mechanisms was closely related to the magnitudes of the different stress components and the biaxial stress ratio.

With reference to damage mechanisms, Smith and Pascoe [32,33] also observed several types of damage in a woven roving glass-polyester composite under various biaxial fatigue conditions at room temperature. These mechanisms depended on stress state, cyclic frequency and orientation of the principal material axis with respect to the principal loading direction.

Smith and Pascoe [32,33] also examined the effects of biaxial loading on the cyclic stress-strain behaviour of woven roving glass-polyester cruciform-shaped specimens. They found that the hysteresis behaviour was dependent on stress state, as shown for example in Fig. 12. When the stress state was equibiaxial ($\lambda = 1$), a distinct knee occurred in the first tensile half cycle but it disappeared on subsequent tensile half-cycles, whereas a linear stress-strain relationship was observed during the first compressive half cycle, Fig. 12(a). It was suggested that this behaviour indicated irrecoverable damage during the first tensile half cycle, such as breakdown of the fibre/matrix bond and matrix cracking. During subsequent cycles the amount of hysteresis was small and approximately constant, whereas the tensile and compressive moduli began to change with the difference increasing with the number of cycles. In comparison, for shear loading ($\lambda = -1$), the stress-strain curve for the first cycle did not exhibit a distinct knee and there was a marked build up in hysteresis energy with increasing number of cycles, Fig. 12(b). Also the stress-strain behaviour for shear loading was markedly dependent on cyclic frequency whereas for equibiaxial loading the behaviour was not affected by frequency.




FIG.12 Progressive stress-strain loops for a woven roving glass-polyester composite subject to biaxial loading (a) equibiaxial stress ($\lambda = +1$) and (b) shear stress along the fibres ($\lambda = -1$) [33].

The effects of biaxial loading on fatigue crack growth rates in composite materials have been reported by Radon and Wachnicki [34,35]. They tested chopped strand mat glass-polyester centre-notched cruciform specimens. Results from this work showed that biaxial loading did not produce a significant change in the fatigue crack growth rate ($\frac{da}{dN}$) as shown in Fig. 13. However, this result is surprising given the large effect of biaxial stress states on the fatigue life curves of fibre-reinforced composite materials. Therefore, more experimental data, including that for other fibre/matrix and layup combinations, are required to confirm these results.

6. CONCLUSIONS

A review of the limited number of papers in the literature on multiaxial fatigue and fracture of composites has suggested that biaxial stress states may increase static limit strengths by up to approximately 50%, increase ultimate strengths by approximately 30%, decrease fatigue lives by factors of up to several orders of magnitude and change both the cyclic stress-strain behaviour and the failure modes in a complex manner. However, more multiaxial fatigue data covering a greater range of fibre/matrix and layup combinations are required to assess the general validity of these trends. There is also a need for more biaxial fatigue crack propagation data for composites. In addition, none of the presently available multiaxial failure theories for composites agree with the observed experimental results with sufficient accuracy to be confidently used for design purposes.

ACKNOWLEDGEMENT

The author would like to thank Dr J.M. Finney for his constructive comments on the manuscript of this report.




FIG. 13 Relationship between fatigue crack growth rate (da/dN) and stress intensity factor range perpendicular to the crack line (ΔK) for chopped strand mat glass-polyester centre-notched specimens [34].

REFERENCES

1. Lohr, R.D. Biaxial high strain fatigue of 1 Cr-Mo-V steel, Ph. D. Thesis, Bristol: University of Bristol, 1977.
2. Lohr, R.D. and Ellison, E.G. Biaxial high strain fatigue testing of 1 Cr-Mo-V steel. Fatigue Engng Mater. Struct., 3, 1980, 19-37.
3. Brown, M.W. and Miller, K.J. Two decades of progress in the assessment of multiaxial low-cycle fatigue. Low-Cycle Fatigue and Life Prediction. [Editors: C. Amzallag, B.N. Leis and P. Rabbe]. Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 770, 1982, 482-499.
4. Leever, P.S., Radon, J.C. and Culver, L.E. Crack growth in plastic panels under biaxial stress. Polymer, 17, 1976, 627-632.
5. Miller, K.J. and Brown, M.W. [Editors:] Multiaxial Fatigue. Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 853, 1985.
6. Beaver, P.W. Multiaxial fatigue and fracture - a literature review. Aust. Aeronaut. Res. Lab. Struct. Rep. 410, 1984.
7. Beaver, P.W. Biaxial fatigue and fracture of metals: a review, Metals Forum, 8 (1), 1985, 14-29.
8. Evans, W.J. Deformation and failure under multiaxial stresses - a survey of laboratory techniques and experimental data. London: Her Majesty's Stationary Office, C.P. No. 1306, 1972.
9. Krempl, E. The Influence of State of Stress on Low-Cycle Fatigue of Structural Materials: A Literature Survey and Interpretive Report. Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 549, 1974.

10. Owen, M.J. and Found, M.S. The fatigue behaviour of glass fabric reinforced polyester resin under off-axis loading. J. Phys. (D.) Appl. Phys., 8, 1975, 480-497.
11. Found, M.S. A review of the multiaxial fatigue testing of fibre reinforced plastics. Multiaxial Fatigue. [Editors: K.J. Miller and M.W. Brown], Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 853, 1985, 381-395.
12. Coles, B.W. and Pipes, R.B. Filamentary composite laminates subjected to biaxial stress fields. U.S. Air Force, Air Force Flight Dynamics Lab. Tech. Rep. TR-73-115, 1974.
13. Owen, M.J. and Found, M.S. Static and fatigue failure of glass reinforced polyester resin under complex stress conditions, Faraday Special Discussions of the Chemical Society, no. 2, 1972, 77-89.
14. Owen, M.J. and Rice, D.J. Biaxial strength behaviour of glass fabric-reinforced polyester resins. Composites, 12 (1), 1981, 13-25.
15. Bert, C.W., Mayberry, B.L. and Ray, J.D. Behaviour of fibre-reinforced laminates under biaxial loading. Composite Materials : Testing and Design. Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 460, 1969, 362-380.
16. Smith, E.W., and Pascoe, K.J. The role of shear deformation in the fatigue failure of a glass fiber-reinforced composite. Composites, 8, 1977, 237-243.
17. Pascoe, K.J. and Tutton, P.A., Biaxial testing of multi-laminate fibre composites. Fatigue and Creep of Composite Materials, [Editors: H. Lilholt and R. Talreja]. Riso, Denmark: Riso National

University, 1982, 265-270.

18. Owen, M.J. Biaxial failure of GRP-Mechanisms, Modes and theories. Composite Materials-2. [Editor: I.H. Marshall]. London: Applied Science Publishers, 1983, 21-39.
19. Owen, M.J. and Rice, J.D. Biaxial strength behaviour of glass-reinforced polyester resins Composite Materials : Testing and Design (Sixth Conference). [Editor: I.M. Daniel], Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 787, 1982, 124-144.
20. Owen, M.J., Griffiths, J.R., and Found, M.S. Biaxial stress fatigue testing of thin-walled GRP cylinders. ICCM-2, Proceedings of the 1975 International Conference on Composite Materials. [Editors: E. Scala, E. Anderson, I. Toch and B.R. Norton]. New York: The Metallurgical Society of AIME, 1975, 917-941.
21. Owen, M.J. and Griffiths, J.R. Evaluation of biaxial stress failure surfaces for a glass fabric reinforced polyester resin under static and fatigue loading. J. Mater. Sci., **13**, 1978, 1521-1537.
22. Rowlands, R.E. Flow and failure of biaxially loaded composites. Inelastic behaviour of composite materials. ASME-AMD-13, 1975, 97-125.
23. Rowlands, R.E. Analytical-experimental correlations of polyaxial states of stress in thronel-epoxy laminates. Exp. Mech., **18**, 1978, 253-260.
24. Guess, T.R. and Gerstle Jr, F.P. Deformation and fracture of resin matrix composites in combined stress states. J. Composite Materials, **11**, 1977, 146-163.

25. Hotter, U., Schelling, H. and Krauss, H. An experimental study to determine failure envelope of composite materials with tubular specimens under combined loads and comparison between several classical criteria. AGARD Conf. Proc. No. 163, 1975, 3.1 - 3.11.
26. Jones, D.L., Poulouse, P.K. and Liebowitz, H. Effect of biaxial loads on the static and fatigue properties of composite materials. Multiaxial Fatigue. [Editors: K.J. Miller and M.W. Brown]. Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 853, 1985, 413-427.
27. Daniel, I.M. Behavior of graphite/epoxy plates with holes under biaxial loading. Exp. Mech., 20, 1980, 1-8.
28. Daniel, I.M. Biaxial testing of graphite/epoxy laminates with cracks. Test Methods and Design Allowables for Fibrous Composites. [Editor: C.C. Chamis]. Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 734, 1981, 109-128.
29. Francis, P.H., Walrath, D.E., Sims, D.F. and Weed, D.N. Biaxial fatigue loading of notched composites. NASA CR-145198, 1977.
30. Francis, P.H., Walrath, D.E., Sims, D.F., and Weed, D.M. Biaxial fatigue loading of notched composites. J. Composite Materials, 11, 1977, 488-501.
31. Wang, S.S., Chim, E.S.-M. and Socie, D.F. Biaxial fatigue of fibre reinforced composites at cryogenic temperatures part 1. Fatigue fracture life mechanisms. Engng Mater. Technol. (Trans ASME), 104, 1982, 128-136.
32. Smith, E.W. and Pascoe, K.J. Assessment of fatigue damage in the cyclic loading of a glass-fibre reinforced polyester composite. Mechanical Behaviour of Materials, ICM vol. 3. [Editors: K.J. Miller and R.F. Smith]. Oxford: Pergamon Press, 1979, 217-226.

33. Smith, E.W. and Pascoe, K.J. Practical strain extensometry for biaxial cruciform specimens. Part 1 and Part 2, Strain 21 (3), 1985, 103-126 and 21 (4), 1985, 175-181.
34. Radon, J.C. and Wachnicki, C.R. Fatigue damage in glass reinforced plastics. Fracture Mechanics Technology Applied to Material Evaluation and Structure Design. [Editors: G.C. Sih, N.E. Ryan and R. Jones]. The Hague: Martinus Nijhoff Publishers, 1983, 623-634.
35. Radon, J.C. and Wachnicki, C.R. Biaxial fatigue of glass fiber reinforced polyester resin. Multiaxial Fatigue. [Editors: K.J. Miller and M.W. Brown], Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 853, 1985, 396-412.

APPENDIX - ADDITIONAL REFERENCES NOT CITED IN TEXT.

MULTIAXIAL TESTING TECHNIQUES

. Daniel, I.M., Liber T., Vanderby, R. and Koller, G.M. Analysis of tubular specimen for biaxial testing of composite laminates. Advances in Composite Materials, vol. 1. [Editors: A.R. Bunsell, C. Bathias, A. Martrencher, D. Menkes and G. Verchery]. Oxford: Pergamon Press, 1980, 841-855.

. Duggan, M.F. and Bailie, J.A. A new test specimen geometry for achieving uniform biaxial stress distributions in laminated composite cylinders, Advances in Composite Materials, vol. 1. [Editors: A.R. Bunsell, C. Bathias, A. Martrencher, D. Menkes and G. Verchery]. Oxford: Pergamon Press, 901-913.

. Marloff, R.H. and Gabrielse, S.E. Further evaluation of proposed biaxial stress test specimen for composite materials. Advances in Composite Materials, vol. 1. [Editors: A.R. Bunsell, C. Bathias, A. Martrencher, D. Menkes and G. Verchery]. Oxford: Pergamon Press, 885-899.

. Thor, S.-E. Biaxial Strength of Graphite/epoxy laminates using flat test specimens. Advances in Composite Materials, vol. 1. [Editors: A.R. Bunsell, C. Bathias, A. Martrencher, D. Menkes and G. Verchery]. Oxford: Pergamon Press, 866-874.

. Marloff, R.H. Finite element analysis of biaxial stress test specimen for graphite/epoxy and glass fabric/epoxy composites. Composite Materials Testing and Design (Sixth Conference) [Editor: I.M. Daniel] Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 787, 1982, 34-49.

. Toombes, G.R., Swanson, S.R. and Cairns, D.S. Biaxial testing of composite tubes. Exp. Mech., 25, 1985, 186-192.

MULTIAXIAL FAILURE CRITERIA

. Francis, P.H., Walrath, D.E. and Weed, D.N. First ply failure of g/e laminates under biaxial loadings. Fibre Sci. Technol., 12, 1979. 97-110.

. Jones, R.M. and Hennemann, J.C. Biaxial strength characteristics of fibre-reinforced laminate. Proc. 2nd Int. Conf. on Composite Materials ICCM/2, Toronto, Canada, 1978, 689-708.

. Sendekyj, G.P. A brief survey of empirical multiaxial strength criteria for composites. Composite Materials : Testing and Design. (Second Conference). Philadelphia: American Society for Testing and Materials, Spec. Tech. Publ. 497, 1972, 41-51.

. Smith, E.W. and Pascoe, K.J. Behaviour of a glass-reinforced composite subject to biaxial monotonic and fatigue loading. Proc. 2nd Int. Conf. on Mechanical Behavior of Materials. Boston: American Society for Metals, 1976, 941-945.

. Tennyson, R.C. and Elliott, W.G. Failure analysis of composite laminates including biaxial compression, NASA-CR-172192, 1983.

. Tennyson, R.C., Macdonald D. and Nanyaro, A.P. Evaluation of the tensor polynomial failure criterion for composite materials. J. Composite Materials, 12, 1978, 63-75.

. Tennyson, R.C., Nanyaro, A.P. and Wharram, G.E. Application of the cubic strength criterion to the failure analysis of composite materials. J. Composite Materials Supplement, 14, 1980, 28-41.

. Wetherhold, R.C. and Woonbong Hwang. An inconsistency in the maximum strain theory for failure of biaxially stressed composite materials. J. Mater. Sci. Engng, 66, 1984, L7-L8.

. Wu, E.M. Optimal experimental measurements of anisotropic failure tensors. J. Composite Materials, 6, 1972, 472-489.

. Zweben, C. Failure analysis of unidirectional fiber composites under combined axial tension and shear. J. Mech. Phy. Solids, 22, 1974, 193-215.

MULTIAXIAL FATIGUE

. Owen, M.J. Biaxial fatigue of composites with short and long fibres. Fatigue and Creep of Composite Materials [Editors: H. Lilholt and R. Talreja]. Riso, Denmark: Riso National University, 1982, 101-112.

. Prentice, P., Wachnicki, C.R. and Radon, J.C. Environmental influences of fatigue damage in glass fibre reinforced polyester. Plastics and Rubber Processing and Applications, 3, 1983, 273-279.

. Wachnicki, C.R., and Radon, J.C. Fatigue crack growth measurement in a CSM composite using compliance and Moire techniques. Composites, 15, 1984, 211-216.

DISTRIBUTION

AUSTRALIA

Department of Defence

Defence Central

Chief Defence Scientist
Deputy Chief Defence Scientist (shared copy)
Superintendent, Science and Program Administration (shared copy)
Controller, External Relations, Projects and
Analytical Studies (shared copy)
Director, Departmental Publications
Counsellor, Defence Science (London) (Doc Data Sheet Only)
Counsellor, Defence Science (Washington) (Doc Data Sheet Only)
S.A. to Thailand MRD (Doc Data Sheet Only)
S.A. to the DRC (Kuala Lumpur) Doc Data Sheet Only)
OIC TRS, Defence Central Library
Document Exchange Centre, DISB (18 copies)
Joint Intelligence Organisation
Librarian H Block, Victoria Barracks, Melbourne
Director General - Army Development (NSO) (4 copies)

Aeronautical Research Laboratories

Director
Library
Divisional File - Structures
Superintendent - Aero Propulsion
Superintendent - Aircraft Materials
Author: P.W. Beaver
A.A. Baker
G. Clark
J.M. Finney
F.G. Harris
B.C. Hoskin
R. Jones
G.W. Revill
D.S. Saunders

Materials Research Laboratories

Director/Library

Defence Research Centre

Library

Navy Office

Navy Scientific Adviser (Doc Data sheet only)
Aircraft Maintenance and Flight Trials Unit
Director of Naval Aircraft Engineering
Director of Naval Air Warfare
Superintendent, Aircraft Maintenance and Repair
Director of Naval Ship Design

Army Office

Scientific Adviser - Army (Doc Data sheet only)
Engineering Development Establishment, Library
Royal Military College Library
US Army Research, Development and Standardisation Group

Air Force Office

Air Force Scientific Adviser (Doc Data sheet only)
Aircraft Research and Development Unit
Library
Technical Division Library
Director General Aircraft Engineering - Air Force
HQ Support Command (SLENGO)
RAAF College, Point Cook

Central Studies Establishment

Information Centre

Aerospace Technologies Australia

Manager
Library

Department of Aviation

Library
Mr C. Torkington

Statutory and State Authorities and Industry

CSIRO, Division of Materials Science, Library
Australian Airlines, Library
Gas & Fuel Corporation of Vic., Manager Scientific Services
SEC of Vic., Herman Research Laboratory, Library
Ansett Airlines of Australia, Library
BHP, Melbourne Research Laboratories
Hawker de Havilland Aust. Pty Ltd., Victoria, Library
Hawker de Havilland Aust. Pty Ltd., Bankstown, Library

Universities and Colleges

Adelaide

Barr Smith Library
Professor of Mechanical Engineering

Flinders

Library

La Trobe

Library

Melbourne

Engineering Library

Monash
Hargrave Library
Prof I.J. Polmear, Materials Engineering

Newcastle
Library

New England
Library

Sydney
Engineering Library
Head, School of Civil Engineering

NSW
Physical Sciences Library
Library, Australian Defence Force Academy

Queensland
Library

Tasmania
Engineering Library

Western Australia
Library

RMIT
Library

SPARES (10 copies)
TOTAL (97 copies)

DATE
FILMED
8