

2

REPORT DOCUMENTATION PAGE

AD-A197 491

1b. RESTRICTIVE MARKINGS

3. DISTRIBUTION / AVAILABILITY OF REPORT

Approved for public release;
distribution unlimited.

4. PERFORMING ORGANIZATION REPORT NUMBER(S)

5. MONITORING ORGANIZATION REPORT NUMBER(S)

ARO 21380.1-MS

6a. NAME OF PERFORMING ORGANIZATION
Department of Physics
Kansas State University

6b. OFFICE SYMBOL
(if applicable)

7a. NAME OF MONITORING ORGANIZATION
U. S. Army Research Office

6c. ADDRESS (City, State, and ZIP Code)
Cardwell Hall, Manhattan, KS 66506

7b. ADDRESS (City, State, and ZIP Code)
P. O. Box 12211
Research Triangle Park, NC 27709-2211

8a. NAME OF FUNDING / SPONSORING ORGANIZATION
U. S. Army Research Office

8b. OFFICE SYMBOL
(if applicable)

9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER
MIPR 126-84 MIPR 112-85 MIPR 113-86

8c. ADDRESS (City, State, and ZIP Code)
P. O. Box 12211
Research Triangle Park, NC 27709-2211

10. SOURCE OF FUNDING NUMBERS

PROGRAM ELEMENT NO.	PROJECT NO.	TASK NO.	WORK UNIT ACCESSION NO.

11. TITLE (Include Security Classification)
Investigation of As-Cast Iron-Light Rare-Earth-Boron Alloys for Permanent Magnets

12. PERSONAL AUTHOR(S)
G.C Hadjipanayis

13a. TYPE OF REPORT
Final report

13b. TIME COVERED
FROM 2/1/84 TO 1/31/87

14. DATE OF REPORT (Year, Month, Day)
7/1/88

15. PAGE COUNT
17

16. SUPPLEMENTARY NOTATION
The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

COSATI CODES		
FIELD	GROUP	SUB-GROUP

18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
Permanent magnet materials,
Magnetic hardening

19. ABSTRACT (Continue on reverse if necessary and identify by block number)
The magnetic and structural properties of Fe-R-B magnets were studied in the melt-spun and sintered state. The formation of Fe₁₄R₂B phase including its magnetic properties (Curie temperature, magnetic moment and coercivity) and the effects of partial substitutions of iron, rare-earth and metalloid were studied in melt-spun samples. The magnetic properties of as-cast Fe-R-B powders were examined as a function of particle size. The fine powders were sintered into dense magnets and the properties of the magnets were examined over a range of temperatures. The magnetic properties of all samples (melt-spun, powders and sintered magnets) were correlated with the microstructure and magnetic domain structure in an attempt to elucidate the origin of magnetic hardening in these materials. The results of these studies indicate that the high coercivities are due to domain wall pinning at grain boundaries in ribbons and sintered magnets and at the surface of the particles in powders.

20. DISTRIBUTION / AVAILABILITY OF ABSTRACT
 UNCLASSIFIED/UNLIMITED SAME AS RPT DTIC USERS

21. ABSTRACT SECURITY CLASSIFICATION
Unclassified

22a. NAME OF RESPONSIBLE INDIVIDUAL

22b. TELEPHONE (Include Area Code)

22c. OFFICE SYMBOL

DTIC FILE COPY

DTIC
LECTE
JUL 2 0 1988

TABLE OF CONTENTS

I. ACCOMPLISHMENTS 1

 A. Magnetic Properties of R-Fe-B Based Magnets 2

 B. Microstructure Studies - Lorentz Microscopy 3

 C. Magnetic Hardening Studies 4

II. PAPERS PUBLISHED IN REFEREED JOURNALS 7

III. PRESENTATIONS AT MEETINGS AND CONFERENCES 10

IV. PERSONNEL 14

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



I. ACCOMPLISHMENTS

A. MAGNETIC PROPERTIES OF R-Fe-B-BASED MAGNETS

(i) Melt-Spun Ribbons

The magnetic properties of melt-spun Fe-R-B alloys have been examined in the whole rare-earth series. The tetragonal $\text{Fe}_{14}\text{R}_2\text{B}$ phase occurs in all alloys studied except in Eu and Yb containing alloys. The Curie temperature of this phase increases from about 170°C in $\text{Fe}_{14}\text{Ce}_2\text{B}$ to 375°C for $\text{Fe}_{14}\text{Gd}_2\text{B}$ and then decreases for the heavier rare-earths and is only 320°C in $\text{Fe}_{14}\text{Ho}_2\text{B}$. The magnetic hysteresis properties of melt-spun rare-earth boron alloys were examined and maximum coercivities (greater than 10 kOe) were obtained in Pr and Nd-containing samples. The coercivities were found to scale with the anisotropy fields which are estimated to be 40, 80 and 40 kOe for $\text{Fe}_{14}\text{Y}_2\text{B}$, $\text{Fe}_{14}\text{Nd}_2\text{B}$ and $\text{Fe}_{14}\text{Gd}_2\text{B}$, respectively.

1. Transition Metal Substitution

The effects of partial Fe substitution with Co, Mn and Ni have been examined. It is found that the Curie temperature increases steadily with Co substitution while it decreases drastically with the substitution of Mn which couples antiferromagnetically with Fe. In the case of Ni, an initial increase of T_C is observed and this is followed by a large decrease for higher Ni concentrations. Similar observations were made by Narasimhan and the results can be explained with the energy band theory. The increase in T_C for Co substituted alloys leads to smaller temperature coefficients of remanence. It is interesting to note that for higher Co substitutions the Curie temperature is increased above the crystallization temperature so that magnetic annealing is possible for these alloys. The Co, Mn, Ni substituted alloys when crystallized showed again large H_C indicating that the anisotropy of the substituted alloys is still high. In the case of Co-rich

Co-Nd-B alloys large coercive fields could also be obtained consistent with the fact that the anisotropy field of the $\text{Co}_{14}\text{Nd}_2\text{B}$ phase is comparable to that of $\text{Fe}_{14}\text{R}_2\text{B}$ phase.

2. Rare-Earth Metal Substitutions

Partial substitution of neodymium with non-magnetic (Y), isotropic (Gd) and anisotropic (Tb) rare-earths was made to understand better the effects of exchange and anisotropy on the magnetic properties of the mixed alloys. The Curie temperatures of the mixed rare-earth 14:2:1 phase are found to be an average of the Curie temperatures of the individual rare-earth 14:2:1 phases. The increase in anisotropy by heavy rare-earth substitutions is reflected in an increase of H_c . Substitutions of Y and Gd on the other hand, lead to a reduction in coercivity.

3. Metalloid Substitutions

The $\text{Fe}_{14}\text{R}_2\text{M}$ phase is found to be formed only with boron as the metalloid with the exception of $\text{Fe}_{14}\text{Gd}_2\text{C}$ which is found to form only with Gd. The Curie temperature of this phase is found to be about 260°C with a coercivity of about 2 kOe and an anisotropy field of 14 kOe. However, the 14:2:1 phase is still formed after partial substitution of boron with other metalloids. In some cases the phase is formed even with 75% substitution of boron. This is not possible in the as-cast alloys where a mixture of 2 or 3 phases is usually observed. This again shows the high power of rapid solidification techniques in producing metastable phases that cannot be produced otherwise. The magnetic properties, T_c , M_s and H_c of the substituted alloys are found to deteriorate drastically. The larger size of other metalloids is probably sufficient to increase Fe-Fe and Fe-R inter-atomic distances leading to a decrease in J_{ex} and therefore T_c .

(ii) Powders - Sintered Magnets

The magnetic properties of powders have been examined as a function of particle size. It is found that the coercivity increases as the particle size is decreased. Optimum results were found for sizes in the range of 5-10 μ . The maximum coercivity in Fe-Nd-B is found to be 4-5 kOe and it increases with Tb(Dy) substitutions.

The fine Fe-R-B powders were aligned and pressed in a magnetic field of 8 kOe. The "green bodies" were sintered at a temperature in the range of 1000-1100°C. Coercivities around 10 kOe and $(BH)_m$ around 30 MGOe have been obtained in Fe-Nd-B. The coercivity was increased with Tb(Dy) substitutions. The effects of particle size, compaction pressure, aligning field, sintering temperature and time on the final product were studied in Fe-Nd-B permanent magnets.

B. MICROSTRUCTURE STUDIES - LORENTZ MICROSCOPY

Transmission electron microscope studies on heat-treated Fe-Nd-B ribbons showed the same phases as in sintered Fe-Nd-B magnets; the tetragonal $Fe_{14}Nd_2B$ phase, a tetragonal $Fe_4Nd_{1+\epsilon}B_4$ phase, a high Nd content phase and some α -Fe. The secondary phases are not distributed around the 14:2:1 grains but rather they are found at intersections of several $Fe_{14}R_2B$ grains. The only difference observed in the ribbons is the much finer size of the grains. The grain size in melt-spun ribbons ranges from 250-2000 \AA whereas that in sintered magnets is much greater than 1 μ (10-50 μ). In melt-spun Fe-Tb-B alloys the $Fe_{14}Tb_2B$ grains are even finer with a size approximately 100 \AA . This fine microstructure is again characteristic of rapid solidification processes and leads to coercivities much higher than those observed in sintered magnets.

Lorentz microscope studies show the presence of domain walls. In the sintered magnets each grain contains several magnetic domains. In ribbons, however, the smaller grains are basically single domain while the larger ones contain several domains. The size of the domains in Fe-Nd-B is around 0.3μ and is approximately equal to that reported by Livingston for Nd-Fe-B single domain particles (SDP). In both cases domain walls end at grain boundaries and it is believed that they are pinned there. In some ribbons with very fine grain size, "multigrain" domains were also observed. These are large domains containing many grains and are explained by the interactions among the magnetic moments of neighboring grains.

C. MAGNETIC HARDENING STUDIES

In an attempt to understand the origin of the large coercive fields in these alloys, the microstructure and magnetic domain structure were correlated with the magnetic properties.

(i) Summary of results

1. The high coercivities in Fe-R-B magnets are attributed to the highly anisotropic tetragonal phase $Fe_{14}R_2B$. However, the coercivities of ribbons are much higher than those in sintered magnets.

Sample	H_c		
	Ribbon	Sintered	
$Fe_{77}Nd_{15}B_8$	>16 kOe	10-12 kOe	
$Fe_{67}Co_7Al_4Nd_{15}B_7$	>16 kOe	8-10 kOe	(Fig. 1)
$Fe_{77}Mm_{15}B_8$	8 kOe	1-2 kOe	
$Fe_{77}Tb_{15}B_8$	>145 kOe	20-30 kOe	

Co additions increase T_c but decrease H_c . Additions of Tb (or Dy) lead to an increase in H_c because of a substantial increase of the anisotropy field. The high H_c are much lower than the anisotropy field $H = 2K/M_s$ indicating a non-coherent magnetization reversal.

In ribbons the high coercivities are also obtained in samples with

composition around the stoichiometric composition (presence of other phases is minimum).

2. The higher coercivities in ribbons are due to the much finer size of $\text{Fe}_{14}\text{R}_2\text{B}$ grains as compared to that of sintered magnets (a few microns, 10-50 μ). In the fine microstructure samples (a few hundred Angstroms) large interaction magnetic domains are observed including many fine $\text{Fe}_{14}\text{R}_2\text{B}$ grains. In ribbons with larger grains, 2-3 magnetic domains were observed inside the grain with the domain walls ending at grain boundaries indicating domain wall pinning there. These observations roughly suggest a domain wall pinning process responsible for the magnetization reversal mechanism.
3. The initial magnetization increases slowly but gradually with magnetic field as compared to the steep increase observed in sintered magnets. This, however, is due to the random orientation of the $\text{Fe}_{14}\text{R}_2\text{B}$ crystallites (SDP) which need higher fields to align the magnetic domains. It is interesting to know that after ac or dc demagnetization the new "initial magnetization curve" lies below the one corresponding to thermally demagnetized samples. This indicates that the domain wall distribution is changed to a new state that is more difficult to magnetize showing stronger domain wall pinning.
4. The field dependence of H_c is also characteristic of domain wall pinning with a small increase at low fields, a steeper increase at medium fields and a saturation at higher fields. The smaller increase of H_c with H_a disappears in ac(dc) demagnetized samples showing again a more effective domain wall pinning in such samples.
5. The remanence curves of the ribbon samples show a similar behavior. The remanence relationship $M_D(H) = M_R(\infty) - 2M_R(H)$ is not obeyed in thermally demagnetized samples; $M_D(H)$ is the demagnetization remanence, $M_R(H)$ the initial remanence and $M_R(\infty)$ the saturation remanence.

This result indicates a non uniform domain wall pinning where the domain walls encounter different pins in the initial magnetization state than in the demagnetization state. Such behavior was expected in sintered magnets but not in ribbons with such fine microstructure. It appears, however, that after ad(dc) demagnetization the relationship is closer to being obeyed than before.

6. Based on these observation the domain wall pinning model of Gaunt was used to check the temperature dependence of H_C . According to the model for a strong domain wall pinning

$$\left(\frac{H_C}{H_O}\right)^{1/2} = 1 - \left(\frac{75kT}{4b\gamma}\right)^{2/3}$$

and for a weak domain wall pinning

$$\frac{H_C}{H_O} = 1 - \frac{25kT}{2\pi N\gamma b^2} .$$

The experimental results indicate a strong domain wall pinning.

(ii) Conclusion

All of these measurements indicate that the coercivities in Fe-R-B magnets are due to domain wall pinning at the grain boundaries. The H_C are higher in ribbons because of more effective domain wall pinning due to the many more grain boundaries of ribbons. The nature of the inhomogeneities at the grain boundaries is not yet well understood.

II. PAPERS PUBLISHED IN REFEREED JOURNALS

1. "Thermomagnetic Data in Iron-Rare-Earth-Boron Alloys," G.C. Hadjipanayis, Y.F. Tao, K.R. Lawless and D.J. Sellmyer, *Mater. Lett.* 3, 270 (1985).
2. "Magnetic Properties of Melt-Spun Iron-Rare-Earth Boron Alloys," G.C. Hadjipanayis, C.P. Wong and Y.F. Tao, *Rapidly Quenched Metals*, S. Steeb, H. Warlimont, eds., Elsevier Science Publishers B.V., 1985.
3. "Magnetic and Structural Studies of Rapidly Quenched Iron-Rare-Earth-Metalloid Alloys," Y.F. Tao and G.C. Hadjipanayis, *J. Appl. Phys.* 57, 4103 (1985).
4. "Magnetic Hardening in Iron-Neodymium-Boron Permanent Magnets," G.C. Hadjipanayis and K.R. Lawless, *J. Appl. Phys.* 57, 4097 (1985).
5. "Microstructure and Magnetic Properties of Iron-Rare-Earth Magnets," G.C. Hadjipanayis, Y.F. Tao and K.R. Lawless, 8th International Workshop on Rare-Earth Magnets and Their Applications, Dayton, Ohio (May 1985) p. 657.
6. "Magnetic Properties of Melt-Spun and Sintered Fe-Nd-B Magnets at Elevated Temperatures," G.C. Hadjipanayis and Y.F. Tao, *J. de Physique* C6, 237 (1985).
7. "Low-Field Magnetic Properties of Fe-Nd Based Permanent Magnets," K.V. Rao, R. Malmhall and G.C. Hadjipanayis, *J. de Physique* C6, 229.
8. "Formation of $Fe_{14}La_2B$ Phase in As-Cast and Melt-Spun Samples," G.C. Hadjipanayis, Y.F. Tao and G. Gudimetta, *Appl. Phys. Lett.* 47, 757 (1985).
9. "Rapidly Solidified Alloys for Permanent Magnets," G.C. Hadjipanayis, *Mater. Res. Soc. Symp. Proc.* 58, 187 (1986).
10. "An Analytical Electron Microscopy Characterization of Melt-Spun Iron-Rare-Earth Boron Magnetic Materials," R.C. Dickenson, K.R. Lawless and G.C. Hadjipanayis, *Mater. Res. Soc. Symp. Proc.* 58, 199 (1986).

11. "Crystallization and Magnetic Studies in Melt-Spun $\text{Fe}_{77}\text{Nd}_{15-x}\text{R}_x\text{B}_8$ Ribbons, K.V. Rao, R. Malmhall, K. Gudimetta and G.C. Hadjipanayis, Mater. Res. Soc. Symp. Proc. 58, 203 (1986).
12. "Magnetic Properties of Amorphous Iron-Rare-Earth-Boron Alloys," S.H. Aly, G.N. Nicolaidis, Y.F. Tao and G.C. Hadjipanayis, J. Phys. F: Met. Phys. 16, L21 (1986).
13. "Magnetic Properties of Fe-R-B Powders," K. Gudimetta, C.N. Christodoulou and G.C. Hadjipanayis, Appl. Phys. Lett. 48, 670 (1986).
14. "The Microstructure and Magnetic Properties of Melt-Spun $\text{Fe}_{76}\text{Nd}_{16}\text{B}_8$ Magnetic Materials," G.C. Hadjipanayis, R.C. Dickenson and K.R. Lawless, J. Magn. Magn. Mater. 54-57, 557 (1986).
15. "Magnetic and Structural Properties of Melt-Spun Iron-Rare-Earth Based Magnets," G.C. Hadjipanayis, Proc. First Int. Workshop on Non Cryst. Solids, San Feliu de Guixols, Spain (1986).
16. "Magnetic Hardening Studies in Sintered and Melt-Spun Rare-Earth Transition Metal Based Magnets," G.C. Hadjipanayis, Soft and Hard Mgn. Mat. Symp. Proc., Orlando (1986).
17. "Magnetic Hardening in Melt-Spun $\text{F}_2\text{Fe}_{14}\text{B}$ and RFe_4B Alloys," G.C. Hadjipanayis and S. Aly, Proc. 3rd Int. Conf. Phys. Magn. Mat., Poland (1986).
18. "Lorentz Microscopy in Melt-Spun R-Fe-B Alloys," G.C. Hadjipanayis and G. Wei, J. Magn. Man. Mat. 66, 390 (1987).
19. "The Use of Rapid Solidification Techniques for the Search of New Hard Magnetic Materlias," G.C. Hadjipanyis, Can. J. Phys. 65, 1200 (1987).
20. "Magnetic Hysteresis of Amorphous and Crystalline RTM_4B Alloys, S.H. Aly and G.C. Hadjipanayis, J. Appl. Phys. 61, 3757 (1987).
21. "Microstructure and Magnetic Properties of Iron-Based Rare-Earth Magnets," G.C. Hadjipanayis, Y.F. Tao and K.R. Lawless, IEEE Trans. Magn. MAG-22, 1849 (1986).

22. "Magnetic Hysteresis in Fe-R-B Powders," G.C. Hadjipanayis and C.N. Christodoulou, J. Magn. Magn. Mater. 71 (1987).
23. "Formation of RFe₅ Phase by Rapid Solidification," G.C. Hadjipanayis, A. Nazareth, S.M. Kanetkar and S.G. Cheng, Proc. Int. Symp. Phys. Magn. Mater., Sendai, Japan (1987).

III. PRESENTATIONS AT MEETINGS AND CONFERENCES

1. "Thermomagnetic and Crystallization Data in Iron-Rare-Earth Metalloid Alloys," Y.F. Tao and G.C. Hadjipanayis, 32nd Annual Midwest Solid State Conf., Lincoln (1984).
2. "Magnetic Properties of Iron-Rare-Earth-Boron Powders," K.M. Gudimetta and G.C. Hadjipanayis, 32nd Annual Midwest Solid State Conference, Lincoln (1984).
3. "Magnetic Hardening in Iron-Neodymium-Boron Permanent Magnets," G.C. Hadjipanayis, K.R. Lawless, 30th Conference Magn. Mater., San Diego (1984).
4. "Mossbauer Studies in Rapidly Quenched Rare-Earth-Iron-Boron Alloys," D.G. Niarchos, B.D. Dunlap, G.C. Hadjipanayis and D.R. Jones, 30th Conf. Magn. Mater., San Diego (1984).
5. "Magnetic and Structural Studies of Rapidly Quenched Iron-Rare-Earth-Metalloid Alloys," Y.F. Tao and G.C. Hadjipanayis, 30th Conf. Magn. Mater., San Diego (1984).
6. "Magnetic and Crystallization Studies in Iron-Nickel Chromium-Metalloid Glasses," G.C. Hadjipanayis and A. Nazareth, American Physical Society Meeting, Baltimore (1985).
7. "Microstructure and Magnetic Properties of Iron-Based Rare-Earth Magnets," G.C. Hadjipanayis, Y.F. Tao and K.R. Lawless and R.C. Dickenson, Intermag, St. Paul (1985). INVITED
8. "Low-Field Thermomagnetic Studies on Nd-Fe-B Permanent Magnetic Material" K.V. Rao, R. Malmhall and G.C. Hadjipanayis, Intermag, St. Paul (1985).

9. "Microstructure and Magnetic Properties of Fe-Based Rare-Earth Magnets," G.C. Hadjipanayis, Y.F. Tao and K.R. Lawless, 8th International Workshop on Rare-Earth Magnets and Their Applications, Dayton (1985).
10. "Microstructure of Iron-Neodymium-Boron Magnets," G.C. Hadjipanayis, Y.F. Tao and K.R. Lawless, 4th Annual Conf. on Properties and Applications of Magnetic Materials, Illinois Institute of Tehcnology, Chicago (1985). INVITED
11. "Magnetic Properties of Melt-Spun and Sintered Fe-Nd-B Magnets at Elevated Temperatures," G.C. Hadjipanayis and Y.F. Tao, Magnetic Materials for Applications Conference, Grenoble, France (1985).
12. "Low-Field Magnetic Properties of Fe-Nd-Based Permanent Magnets," K.V. Rao, R. Malmhall and G.C. Hadjipanayis, Magnetic Materials for Appication, Grenoble, France (1985).
13. "Magnetic Properties of Amorphous Iron-Rare-Earth-Boron Alloys," S.H. Aly, G.K. Nicolaidis, Y.F. Tao and G.C. Hadjipanayis, International Conference on Magnetism, San Francisco (1985).
14. "The Microstructure and Magnetic Properties of Melt-Spun $Fe_{76}Nd_{16}B_8$ Magnetic Materials, G.C. Hadjipanayis, R.C. Dickenson and K.R. Lawless, International Conference on Magnetism, San Francisco (1985).
15. "The Effect of Metalloid Substuitutions on the magnetic Properties of Fe-P-B Alloys," Y.F. Tao and G.C. Hadjipanayis, 31st Midwest Solid State Conference, Kansas City (1985).
16. "Formation of the RFe_5 Phase by Rapid Solidification," S.M. Kanetkar, G.C. Hadjipanayis, Y.F. Tao and S.F. Cheng, 31st Midwest Solid State Conference, Kansas City (1985).

17. "Magnetic Properties of Rare-Earth Bodies with Composition $R(Fe,Co)_4B$, S.H. Aly and G.C. Hadjipanayis, 31st Midwest Solid State Conference, Kansas City (1985).
18. "Rapid Solidified Alloys for Permanent Magnets," G.C. Hadjipanayis, Materials Society Meeting, Boston (1985). INVITED
19. "An Analytical Electron Microscopy Characterization of Melt-Spun Iron-Rare-Earth-Boron Magnetic Materials," R.C. Dickenson, K.R. Lawless and G.C. Hadjipanayis, Materials Society Meeting, Boston (1985).
20. "Crystallization and Magnetic Studies in Melt-Spun $Fe_{77}Nd_{15-x}R_xB_8$ Ribbons," K.V. Rao, R. Malmhall, K. Gudimetta and G.C. Hadjipanayis, Materials Society Meeting, Boston (1985).
21. "The Effect of Metalloid Substitutions on the Magnetic Properties of Fe-R-B Alloys," G.C. Hadjipanayis, Y.F. Tao, American Physical Society Meeting, Las Vegas (1986).
22. "Magnetic Hysteresis in Melt-Spun and Powdered Fe-Y-B and Fe-Tb-B Samples," G.C. Hadjipanayis, Y.F. Tao, G. Wei and C. Christodoulou, Intermag. Phoenix (1986). INVITED
23. "Effects of Y, Gd and Dy Substitution on the Thermal and Magnetic Properties of Melt-Spun $Fe_{77}Nd_{15-x}R_xB_8$," R. Malmhall, J.S. Munoz, A. Roig, K.V. Rao, Y.F. Tao and G.C. Hadjipanayis, 6th Gen. Conf. Cond. Mett. Div. of EPS, Stockholm (1986).
24. "Auger Spectroscopic Analyses of Compositional Inhomogeneities in Technical Fe-Nd-Based High Energy Product Permanent Magnet Materials," R. Malmhall, A. Oberg, K.V. Rao and G.C. Hadjipanayis, 6th Gen. Conf. Mett. Div. of EPS, Stockholm (1986).

25. "Magnetic and Structural Properties of Melt-Spun Iron-Rare-Earth Based Magnets," G.C. Hadjipanayis, 1st Int Workshop on Non. Cryst. Solids, San Feliu de Guixols, Spain (1986). INVITED
26. "New R-Fe-M Pseudoternaries: A Search for Derivatives of the NaZn_{13} and BaGd_{11} Structure as Candidates for Hard Magnetics," D. Niarchos, A. Roig, K.V. Rao and G.C. Hadjipanayis, 1st Int. Workshop on Non. Cryst. Solids, San Feliu de Guixols, Spain (1986).
27. "Magnetic Hardening Studies in Melt-Spun $\text{R}_2\text{Fe}_{14}\text{B}$ and RFe_4B Alloys," G.C. Hadjipanayis, S. Aly, 3rd Int. Conf. Phys. Magn. Mater., Szczyrk-Bila, Poland (1986). INVITED
28. "Magnetic Hardening Studies in Sintered and Melt-Spun Rare-Earth-Transition Metal Based Magnets," ASM's Materials Week 86, Orlando (1986). INVITED
29. "Magnetic Hysteresis of Amorphous and Crystalline RTM_4B Alloys," G.C. Hadjipanayis and S.H. Aly, Conf. Magn. Mater., Baltimore (1986).
30. "Formation of RFe_5 Phase by Rapid Solidification," G.C. Hadjipanayis, A. Nazareth, S.M. Kanetkar and S.G. Cheng, Int. Symp. on Phys. Magn. Mater. Sendai, Japan (1987).
31. "Temperature Dependence of Magnetic Hysteresis in Melt-Spun and Sintered Fe-Nd-B Magnets," G.C. Hadjipanayis and A. Kim, Intermag, Tokyo (1987).

IV. SCIENTIFIC PERSONNEL SUPPORTED BY THIS PROJECT AND DEGREES AWARDED

1. G.C. Hadjipanayis, Associate Professor, Kansas State University
2. K.R. Lawless, Professor, University of Virginia
3. S. Aly, Postdoctor, Kansas State University
4. J. Strzeszewski, Research Associate, Kansas State University
5. Y.F. Tao, Graduate Student, Ph.D. (1986), Kansas State University
6. K. Gudimetta, Graduate Student, (1985), Kansas State University
7. C. Christodoulou, Graduate Student, M. Sc (1987), Kansas State University
8. W. Gong, Graduate Student, M. Sc (1988), Kansas State University
9. R.C. Dickenson, Graduate Student, M. Sc (1985), Kansas State University
10. E. Singleton, Graduate Student, Kansas State University
11. 2 part-time undergraduate students, Kansas State University