

DTIC FILE COPY

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

AD-A205 946

JAN 27 1989

SER(S)

D_{CS}1b. RESTRICTIVE MARKINGS
None3. DISTRIBUTION / AVAILABILITY OF REPORT
Approved for public release;
distribution unlimited

(2)

5. MONITORING ORGANIZATION REPORT NUMBER(S)

AFOSR-TR- 89-0325

6a. NAME OF PERFORMING ORGANIZATION

Coordinated Science Lab
University of Illinois6b. OFFICE SYMBOL
(if applicable)

N/A

7a. NAME OF MONITORING ORGANIZATION

AFOSR/NE Building 410

6c. ADDRESS (City, State, and ZIP Code)

1101 W. Springfield Ave.
Urbana, IL 61801

7b. ADDRESS (City, State, and ZIP Code)

Bolling AFB. D.C 20332-6448

8a. NAME OF FUNDING / SPONSORING
ORGANIZATION

AFOSR /PRD

8b. OFFICE SYMBOL
(if applicable)

NE

9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER

AFOSR 86-0111

8c. ADDRESS (City, State, and ZIP Code)

Building 410
Bolling AFB D.C. 20332-6448

10. SOURCE OF FUNDING NUMBERS

PROGRAM
ELEMENT NO.

11112F

PROJECT
NO.

2365

TASK
NO.

C1

WORK UNIT
ACCESSION NO.

11. TITLE (Include Security Classification)

III-V Heterojunction Structures and High Speed Devices

12. PERSONAL AUTHOR(S)

Morkoc, Hadis

13a. TYPE OF REPORT

FINAL Progress

13b. TIME COVERED

FROM 1/1/88 TO 12/31/88

14. DATE OF REPORT (Year, Month, Day)

Feb. 17, 1989

15. PAGE COUNT

16. SUPPLEMENTARY NOTATION

17. COSATI CODES

FIELD	GROUP	SUB-GROUP

18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

→ This effort explored the new phenomena in high speed semiconductor devices and structures intended for optoelectronics, while the details of progress made in each subject matter can be found in the publications, a list of which is provided, a few will be highlighted here.

→ A detailed investigation of the collector breakdown properties in GaAs/AlGaAs HBT's has revealed light emission at junctions edges for the first time. The spectral features when analyzed led to the determination of electron and hole threshold energies for ionization for the first time. Additional features observed may shed light into the processing mechanisms not otherwise conveniently accessible.

Other areas, e. g., modulation doped FET's, extremely low resistance nonalloyed ohmic contacts, HBT's on InP, quantum wells, optical properties of bulk AlGaAs and InGaAs were among many projects that were explored.

20. DISTRIBUTION / AVAILABILITY OF ABSTRACT

☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS

21. ABSTRACT SECURITY CLASSIFICATION

Unclassified

22a. NAME OF RESPONSIBLE INDIVIDUAL

G. WERT

22b. TELEPHONE (Include Area Code)

(302) 717-4431

22c. OFFICE SYMBOL

NE

AFOSR-TR- 89 - 0325

Annual Progress Report

III-V HETEROJUNCTION STRUCTURES
AND HIGH SPEED DEVICES

U.S. Air Force AFOSR 86-0111

February 17, 1989

Principal Investigator

H. Morkoc

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 W. Springfield Avenue

Urbana, Illinois 61801

Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

89 0325 001

TABLE OF CONTENTS

I. Summary	1
II. Progress Made.....	2
III. Representative Papers.....	13
IV. List of Latest Publications.....	47

I. SUMMARY

This effort explored the new phenomena in high speed semiconductor devices and structures intended for optoelectronics while the details of progress made in each subject matter can be found in the publications, a list of which is provided, a few will be highlighted here.

A detailed investigation of the collector breakdown properties in GaAs/AlGaAs HBT's has revealed light emission at junctions edges for the first time. The spectral features when analyzed led to the determination of electron and hole threshold energies for ionization for the first time. Additional features observed may shed light into the processing related mechanisms not otherwise conveniently accessible.

Other areas, e. g. , modulation doped FET's, extremely low resistance nonalloyed ohmic contacts, HBT's on InP, quantum wells, optical properties of bulk AlGaAs and InGaAs were among many projects that were explored.

II. PROGRESS MADE

Field-effect Transistors

A. MODFET Heterojunction Quantum Well

The modulation-doped field-effect transistor (MODFET) offers great promise for low-noise microwave amplification and high-speed switching. We have developed a new analytical model for eigenfunctions, eigen-energies, and related properties of the quasi-triangular quantum well in the MODFET. The model makes use of a new approximation for the potential energy function to simultaneously solve the Schrodinger equation and the Poisson equation. The potential energy function is general enough to represent the potential energy of quantum wells of MODFETs fabricated from all possible different semiconductors, having all possible doping conditions and mole fractions. In order to determine the applicability of the present model we have attempted to compare our results with those from five other models : (1) Classical model in which the subband structure is neglected, and the Maxwell-Boltzmann statistics is used to describe the electron distribution. (2) Classical model in which the subband structure is neglected, and the Fermi-Dirac statistics is used to describe the electron distribution. (3) Self-consistent field quantum mechanical model accounting for many body exchange and correlation effects in the framework of local density-function approximation. (4) Approximate quantum mechanical model using the triangular approximation for the quantum well. (5) Numerical method for exact calculations. It is noted that our results for Fermi energy level, sheet electron concentration, average electron distance from the heterointerface, and fractional subband occupancy agree almost quantitatively with the exact results from numerical calculations. These results appeared to be better than those from classical and semi-classical calculations, and from the quantum mechanical calculations with triangular potential approximation.

We have applied our model for the quantum well to calculate transconductance of Al-GaAs/GaAs MODFETs. For this calculation use is made of a two-piece model for the saturation drift velocity. When compared with experimental results reported earlier by our laboratory, the

calculated results show reasonably good agreements with them. Although not applied to various other systems, from the trend of the results obtained from the calculations, it is apparent that our model is general enough to be applicable to all systems of technological importance.

B. I-V Characteristics of JFETs

An analytical model has been developed to investigate the I-V characteristics of JFETs from various semiconductor materials, and with various doping conditions in the channel. The short-channel effect has also been studied. In order to study this short-channel effect, the field-dependence of the electron velocity in the channel of short-channel JFETs has been taken into consideration. A new approximation for the electron velocity has been used to develop analytical formulas for the drain saturation current, and intrinsic transconductance. This is given by

$$v = \left(\frac{N_d}{N_o} \right)^\alpha \frac{\mu(N_d)E}{1 + \mu(N_o)E/v_s} \quad (1)$$

where N_d is the doping density in the channel, $\mu(N_d)$ is the doping dependent mobility of electrons, N_o and α are adjustable parameters, chosen to be $N_o = 10^{19} \text{ cm}^{-3}$ and $\alpha = 0.333333$, E is the electric field, and v_s is the saturation velocity of electrons.

Results from eq. (1) have been compared with available experiments for GaAs and Ge. The comparison is encouraging.

In order to test the applicability of the present model we have performed calculations for JFETs from five different semiconductors : GaAs, Ge, Si, InP, and InGaAs. For these calculations we have considered the effects of both bandgap narrowing and Fermi-Dirac statistics. The bandgap narrowing has been modelled as

$$\Delta E_g = C_n N_d^{1/3} \quad (2)$$

where C_n is an empirical parameter; $C_n = 1.6 \times 10^{-8}$, 3.0×10^{-8} , 2.25×10^{-8} , 1.5×10^{-8} , and $1.6 \times 10^{-8} \text{ eV/cm}$ for GaAs, Si, InP, Ge, and $\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ respectively. Our results for drain saturation current and transconductance are found to be more sensitive to channel doping in the region $2 \times 10^{18} \leq N_d \leq 5 \times 10^{18} \text{ cm}^{-3}$ than in the region $10^{17} \leq N_d \leq 2 \times 10^{18} \text{ cm}^{-3}$. Both

of these parameters are higher for shorter channel length than for longer channel length. The investigation suggests that, provided the leakage current is not high, a semiconductor alloy with composition suitable for the highest possible electron drift velocity should be most effective for high-speed JFETs. A submicron gate length would be the most effective for high-speed JFETs. A submicron gate length would, however, accompany short-channel effects. To circumvent these short-channel effects a channel doping higher than the 'Nulled Degeneracy Level' would be quite useful. The study indicates that the doping in the p-region gate of high-speed JFETs should not exceed a doping level of about 10^{20} cm^{-3} . This is because, in an attempt to satisfy charge neutrality condition such an exceedingly high gate would not allow drain electron velocity to saturate at a lower distance from the source end of the channel.

C. I-V Characteristics of MESFETs

High-speed low-cost monolithically integrated optoelectronic circuits using MESFETs (metal semiconductor field-effect transistors) are highly promising for low-wavelength optical communications. We have theoretically studied the I-V characteristics of both long-channel and short-channel MESFETs, the structure being grown by ion-implantation. For the modeling of this I-V characteristics of short-channel MESFETs we have taken the velocity saturation of electrons due to high electric field into account. Also, we have considered the effect of nonuniformity of band structure, and the effect of bandgap narrowing and Fermi-Dirac statistics for the heavily doped channel region. For the drift velocity of electrons use has been made of eq. (1). For the doping dependent mobility a new approximation has been made. It is given by

$$\mu(y) = \mu_L \left[\frac{A_1}{N_d^{\nu_1}} + \frac{A_2}{N_d^{\nu_2}} \right] \quad (3)$$

where A_1 , A_2 , ν_1 , and ν_2 are empirical parameters given by $A_1 = 0.232676 \times 10^6 \text{ cm}^{-1}$, $A_2 = -3.0 \times 10^{15}$, cm^{-3} , $\nu_1 = 0.333333$, and $\nu_2 = 1.0$ respectively. $\mu_L = 10^4 \text{ cm}^2/\text{V} - \text{s}$ for GaAs and $1.4 \times 10^3 \text{ cm}^2/\text{V} - \text{s}$ for Si. To circumvent various difficulties arising from the integration of Gaussian profile for the drain region doping, we have made use of a fitting :

$$y^{-1} = \sum_{j=0}^6 D_j \exp(-\epsilon_j y^2) \quad (4)$$

where D_j and ϵ_j are appropriate fitting parameters.

In order to study the applicability of the present model we carried out calculations of drain saturation current I_{ds} and transconductance g_m for GaAs and Si. For the sake of calculation the drain saturation velocity for both GaAs and Si was chosen to be 10^7 cm/sec. Both I_{ds} and g_m are found to be very sensitive to the choice of channel doping as well as channel length. Both I_{ds} and g_m increase with increase in the channel doping and with decrease in the channel length. As higher value of the gate-source voltage V_{gs} causes higher modulation of electron conduction through the channel region, a higher value of V_{gs} leads to a higher drain saturation current and transconductance. The calculated variation of I_{ds} with V_{gs} agrees very well with available experiments.

Earlier device simulations by the relaxation time approximation method, and by the Monte Carlo method, which take the nonequilibrium electron transport in the channel into account, predicted that the electron velocity in submicrometer gate length MESFETs is higher than that in the micrometer gate-length MESFETs. Yamasaki and Hirayama measured the dependence of effective saturation velocity and threshold voltage on the gate length of GaAs MESFETs. We tried to study the implication of these results to the present method. It was noted that while we carried out calculations using increased saturation velocity and decreased threshold voltage for decreased gate length, our results agreed better with available experiments. Thus the present investigation strongly suggested that there occurs velocity overshoot in submicron gate length MESFETs.

D. Ion-implanted FET's

We have proposed a model for ion-implanted FETs that takes into account velocity-saturation effect. This model is expected to be more accurate than the previous models because it uses the exact doping profile instead of assuming an equivalent constant doping density. We have demonstrated that the results predicted by this model are in reasonable agreement with experimental data. Then we used this model to predict the dc characteristics of FET's with laterally graded

doping profile, in particular, FET's with two different implants under the gate, the heavier doping being near the source. We studied the device performance as a function of the position of the implant-step and showed that it is in qualitative agreement with experimental data.

E. Backgating effect

We designed and fabricated a MODFET with a p-n junction back gate and demonstrated that the device current can be controlled by the normal front gate as well as the back gate quite efficiently. Also, we studied experimentally the variation of the transconductance as a function of the gate biases. This idea can be used in realizing novel structures that have been proposed in the past including the velocity modulation transistor. We also studied backgating effect in MODFET's that causes cross-talk in integrated circuits. To reduce this effect, we used p-n junction isolation and demonstrated that if the mesas etched deeper than the junction, excellent device isolation can be achieved.

F. GaAs-based FET's on InP

Metal-insulator-semiconductor-type AlGaAs/GaAs FET's have been successfully fabricated on InP substrates by incorporating an InGaAs/GaAs strained-layer superlattice in the buffer structure to reduce dislocation propagation into the active device region. A typical device shows an intrinsic transconductance of 180 mS/mm. It exhibits excellent pinch-off and large gate-to-source breakdown voltage. These devices will be useful for monolithic integration of GaAs-based electronic devices with InP-based optical devices for applications in low cost, high performance long wavelength optoelectronic integrated circuits (OEIC's)

Heterojunction Bipolar Transistors

A. InGaAs/InAlAs HBTs

We have undertaken a thorough investigation of InAlAs/InGaAs HBT's. This was to take advantage of the many distinct properties such as high electron mobility, low surface recombination velocity, and high valence band discontinuity afforded by this material system. In addition,

these devices are compatible with 1.3-1.55 μm optical fiber communication systems. In some devices, we utilized an n^+ -InAs emitter cap layer for nonalloyed contacts and obtained specific contact resistances of about 1.8×10^{-7} and 6.0×10^{-6} for emitter and base contacts, respectively. Since no high-temperature annealing is necessary, excellent contact surface morphology on thinner devices can easily be obtained. In devices with $50 \times 50 \mu\text{m}^2$ emitter area, common emitter current gain as high as 1500 were achieved at a collector current density of $2.7 \times 10^3 \text{ A/cm}^2$. The p-n-p devices exhibited a common emitter current gain of up to 70 at a collector current density of $1.2 \times 10^3 \text{ A/cm}^2$. To our knowledge, these values are the best reported to date.

We also succeeded in the first realization of InAlAs/InGaAs HBT's on GaAs substrates. Among the advantages of integrating InGaAs/InAlAs HBT's on GaAs are lower cost and less fragility of GaAs substrates, integration of InP-based optoelectronic systems with well developed GaAs technology, and elimination of ion diffusion from InP substrates during growth. Recently HBT structure with a compositionally graded emitter-base junction employing a linearly graded $\text{In}_{0.53}\text{Ga}_{0.47-x}\text{Al}_x\text{As}$ between two ternary layers, and with a pseudo- quaternary InAlAs/InGaAs short period superlattice were investigated. Typical quaternary graded devices with an emitter dimension of $50 \times 50 \mu\text{m}^2$ exhibited a current gain as high as 1260 at a collector current density of $2.8 \times 10^3 \text{ A/cm}^2$.

B. $\text{Ge}_{1-x}\text{Si}_x$ HBTs

Another area we investigated in heterojunction bipolar transistor was $\text{Ge}_{1-x}\text{Si}_x$ on Si substrate. Epitaxial growth of $\text{Ge}_{1-x}\text{Si}_x$ on Si has recently received much attention because of both fundamental interest in overlayer ordering as well as potential device application using tunable bandgap. Pursuing the realization of such a novel device, a study was undertaken to examine the potential performance of a n-Si emitter, p- $\text{Si}_x\text{Ge}_{1-x}$ base on a n-Si collector heterojunction bipolar transistor. Such a device combines the advantage of heterojunction with the advanced processing technology of Si. Using a compact transistor model, calculations of the high-speed capability of the transistor were performed revealing performance values superior to those for state-of-the-art Si bipolar transistors. Specifically, for an emitter area of $1 \times 5 \mu\text{m}^2$, an f_t of over 70 GHz and

f_{max} of over 30 GHz were computed at a collector current density of 1×10^5 A/cm² and V_{CB} of 5 V. As these simulations made use of fairly conservative dimension and device parameters, the simulated results are encouraging and suggest further investigation of this device.

C. GaAs/AlGaAs HBTs

We have continued our efforts to enhance the performance of GaAs/AlGaAs HBT's on Si substrates. Using optimized growth conditions, a series of HBT structure with varying parameters were grown on (100) Si substrate tilted 4° toward (110) by MBE. Devices exhibited current gains of about 45 at a collector current density of 2×10^3 A/cm², the highest current gain reported for GaAs/AlGaAs HBT's on Si to date. The diode characteristics exhibited remarkably high breakdown voltages of 10 and 15 V for emitter-base and base-collector junctions, respectively. The output characteristics of the n-p-n and p-n-p devices did not show any negative differential resistance (NDR), presumably due to the better thermal conductivity of Si substrates.

We have studied the avalanche breakdown behavior at the collector junction of the AlGaAs/GaAs HBT. The dependence of collector-base breakdown voltage upon the collector doping concentration and thickness was reported, with the results showing expected functional behavior. Associated breakdown voltage calculations using simple punch-through considerations were found to be in close agreement with the maximum breakdown voltages – measured from devices displaying the most uniform junction breakdown.

Junction breakdown characteristics including both localized microplasma effects as well as uniform microplasma-free behavior were observed. At avalanche breakdown in the GaAs *p-n* junction, we reported the first known observation of light emission from the collector-base junction of a GaAs/AlGaAs HBT. Collector-emitter breakdown characteristics showing expected negative resistance breakdown were also studied. Associated current gain measurements were performed in connection with the analysis of the collector-emitter/collector-base breakdown voltages.

AlGaAs/GaAs HBT's have also been successfully fabricated on InP substrates. These devices, because of their superior high current handling capability, will be used for laser drivers for long

wavelength optoelectronic monolithic integrated circuits on a single InP chip. Small-signal current gains of these HBT's were 30 on InP as compared to 150 for those on GaAs. The ideality factors of the emitter-base junctions were 1.3 and 1.2 for devices on InP and GaAs, respectively. Since the minority-carrier lifetime is quite sensitive to defects in the base region, these measurements demonstrate the high quality of GaAs on InP.

For the next research period, we plan to study and optimize HBT's performance to push their performance to the limit. As a one step further, the technology of HBT's will be applied to other novel devices such as resonant tunneling transistors. Most recently, a theoretical thermoelectro-feedback model has been developed for thermal designs of high power GaAs/AlGaAs HBT's. The power handling capability, thermal instability, junction temperature, and current distribution of HBT's with multiple emitter fingers will be investigated.

Non-alloyed ohmic contacts

We have developed extremely low resistance non-alloyed ohmic contacts to *n*- and *p*- type GaAs using superlattice contact layers consisting of small bandgap materials. The non-alloyed contacts on *n*- GaAs consist of InAs/InGaAs and InAs/GaAs superlattices and an InAs cap layer. Extremely low contact resistances of less than $8.5 \times 10^{-8} \Omega \text{ cm}^2$ have been reported. The non-alloyed contacts on *p*- GaAs consist of a GaAs/GaSb superlattice layer and a GaSb cap layer. A specific contact resistivity of $3.16 \times 10^{-7} \Omega \text{ cm}^2$ was obtained.

We incorporated the non-alloyed ohmic contact on *n*- GaAs described above on a conventional GaAs MESFET. Extremely low non-alloyed contact resistances of less than $5.0 \times 10^{-8} \Omega \text{ cm}^2$ have been achieved in this case, which is to our knowledge the lowest contact resistance obtained to date on GaAs. MESFETs with $1 \mu\text{m}$ gate lengths had transconductances of about 210 mS/mm.

We plan to take further steps in implementing these novel non-alloyed contacts in various other devices, especially those that InGaAs based, since the smaller bandgap of InGaAs coupled with the generally higher performance of these devices would make the availability of extremely low resistance non-alloyed contacts even more desirable.

We are conducting several studies relating to the growth of these superlattice contacts, primarily by transmission electron microscopy. We are also studying the effect of heat treatment on the resistance and uniformity of these non-alloyed contacts, as well as their sensitivity to the choice of contact metal.

Direct and resonant tunneling diodes

We have calculated the I-V characteristics of single barrier direct tunneling diode. The $k \cdot p$ model was used to calculate the transmission probability and two coupled Poisson's equations were used to calculate the band-bending. Quantitative agreement with experiment on an $\text{In}_{0.53}\text{Ga}_{0.47}\text{As}/\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ diode was obtained. This method of calculation for the single barrier diode was directly extended to the double barrier resonant tunneling diode. And we are actively doing calculations on the latter.

We are currently doing research on three terminal resonant tunneling transistors. We will also simulate the I-V characteristics of this kind of devices using the same technique as with the two terminal devices.

Optical studies

A. Multiple Quantum Well Optical Modulators

Multiple quantum well (MQW) p-i-n modulators, based on the quantum-confined stark effect, have been demonstrated extensively for AlGaAs/GaAs and InGaAs/GaAs systems grown on GaAs substrates. As previously reported, we have demonstrated a InGaAs/GaAs strained layer MQW optical modulator based on the electro-absorption effect. A change of 27% in the transmission with 6 volt reverse bias voltage and at $0.971 \mu\text{m}$ wavelength was measured. As an extension, we investigated the reflection properties and demonstrated a p-i-n reflection modulator consisting of a 50 period strained layer $\text{In}_{0.15}\text{Ga}_{0.85}\text{As}/\text{GaAs}$ MQW and a 5 period AlAs/GaAs quarter wave stack dielectric mirror, grown on GaAs substrate. A relative change in the reflectivity of the modulator of 12% was observed with 4.5 V reverse bias voltage and at $0.996 \mu\text{m}$

wavelength. The reflection modulators are of interest for bidirectional communication systems, in parallel arrays of optical switching and processing devices, and for optical interconnects. With the progress of the GaAs on Si technique, we have also investigated the optical properties of AlGaAs/GaAs MQW grown on Si substrates for the potential applications in optical integration. Using photocurrent measurement, we observed the large excitonic absorption at room temperature for that material system. For the first time we demonstrated an optical reflection modulator and observed a 7.7% change in the reflectivity at wavelength of $0.86\text{ }\mu\text{m}$ for the device with 6 V reverse bias voltage across the AlGaAs/GaAs MQW p-i-n structure, grown on Si substrate.

B. Characterization of III-V materials grown by MBE

GaAsSb/GaAs strained layer MQW have been grown and characterized by photoreflectance (PR), photoluminescence (PL), and transmission measurements. For the first time we observed the PR features corresponding to the various subband transitions in GaAsSb/GaAs MQW at room temperature, indicating the greatly improved material quality. By the comparison between the theoretical calculated transition energies and the experimental observed ones, we determined the band offset for the $\text{GaAs}_{0.9}\text{Sb}_{0.1}/\text{GaAs}$ interface of $Q\sim 1.7$ for heavy holes, establishing a type II structure with electrons in GaAs layers and heavy and light holes in $\text{GaAs}_{0.9}\text{Sb}_{0.1}$ layer, respectively.

In our on-going research of InGaAs/GaAs strained layer MQW, we extended our studies from the confined to unconfined states. Optical transitions with energies higher than that of GaAs band gap in InGaAs/GaAs MQW have been observed. The theoretical calculations based on transfer matrix method were used to locate the positions of unconfined subband energies. Reasonable agreement between the calculation and the observation were obtained. We found that the intensity of the transition involving unconfined subbands decreases with increasing well width, but is weakly dependent of the mole fraction, x .

In collaboration with T. A. Tombrello of CALTECH, we investigated and characterized the most important alloy system, AlGaAs, through optical absorption, PR, PL, as well as nuclear

resonant reaction analysis. By using the energy gap E_g derived from the PR and absorption spectra and the AlAs mole fraction x determined from nuclear resonant reaction analysis, we obtained $E_g \sim x$ relation as $E_g = 1.424 + 1.427x + 0.041x^2$ (eV). The above relation shows larger slope and smaller bowing factor than those accepted earlier, and consistent with the most recently results reported by other groups.

The study of GaAs grown on InP substrate is of interest due to its potential applications in opto-electronic devices. We characterized the GaAs film grown on InP substrate through low temperature PL, transmission, and reflection measurements. Several important PL peaks were identified which include the excitonic and impurity associated transitions. From the fact that the excitonic peaks were observed in PL spectra, and that the reasonably good device characteristics were obtained, we have demonstrated that high quality GaAs film can be grown on InP substrate in spite of 4% lattice mismatch between two materials.

III. REPRESENTATIVE PAPERS

Analytical Model for I-V Characteristics of Ion-Implanted MESFETs with Heavily Doped Channel

S. Noor Mohammad, Mahesh B. Patil, James J. Chen, J.-I. Chyi,
M. Selim Ünlü, G.B. Gao, and Hadis Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 West Springfield Avenue

Urbana, Illinois 61801, U.S.A.

Abstract

A theoretical model for the I-V characteristics of ion-implanted MESFETs has been developed. A new formula for effective drift saturation velocity for electrons, and a Gaussian approximation for the inverse of reduced distances in the channel have eased the process of formulation. Theoretical formulas for early saturation of drain current and transconductance obtained in the framework of Lehocvec-Zuleeg procedure, are quite simple and accurate. When calculated results from the present model are compared with available experiments, an encouraging correspondence between the two is observed. When used to study the appropriateness of the velocity overshoot and the softening of pinch-off voltage, it suggests that both of these phenomena are real in short-channel MESFETs, and these need to be carefully accounted for in a realistic model. The model is equally applicable also to ion-implanted JFETs.

**Heavy doping for improved short-channel operation of
GaAs MESFET**

S. NOOR MOHAMMAD, MAHESH B. PATIL, AND HADIS MORKOÇ

University of Illinois at Urbana-Champaign, Coordinated Science Laboratory

1101 West Springfield Ave., Urbana, IL 61801, U.S.A.

Abstract

A theoretical calculation is performed to investigate the I-V characteristics of GaAs MESFETs. The calculation is based on a simple model that takes into account the dependence of electron mobility on electric field and doping. It is shown that velocity overshoot may be treated by an effective velocity higher than the bulk value.

Reference #493

Analytical treatment of MODFET heterojunction quantum well in GaAs/AlGaAs system

S. NOOR MOHAMMAD, M. SELİM ÜNLÜ and HADIS MORKOÇ, FELLOW, IEEE

Abstract

A new theoretical model has been developed to characterize the energy levels, eigenfunctions, and related properties of two-dimensional electron gas (2-DEG) formed in the quasi-triangular quantum well of a modulation doped field-effect transistor (MODFET). Rather than using a triangular form of potential, which is valid only for low electron densities in the inversion layer, the present model makes use of a realistic form of potential for the quantum well. This potential is versatile enough to fit almost every quantum well that may result from varying doping, mole fractions, and other parameters of the semiconductors forming the heterojunction. Numerical results, for example, for Fermi energy, fractional subband occupancy, etc. of the quantum well, and the transconductance of the MODFET containing this quantum well, are in very good correspondence with the exact and/or experimental results for the similar quantities of $\text{Al}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ system.

The authors are with the University of Illinois at Urbana-Champaign, Coordinated Science Laboratory, 1101 West Springfield Ave., Urbana, IL 61801-3082.



Analytical Model for I-V Characteristics of JFETs with Heavily Doped Channel

S. Noor Mohammad, Mahesh B. Patil, James J. Chen, M. Selim Ünlü, and Hadis Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 West Springfield Avenue

Urbana, IL 61801, U.S.A.

Abstract

A theoretical analysis of the I-V characteristics of junction field-effect transistors (JFETs), which are useful for electronic and optoelectronic integrations, has been carried out in some details. Attempts have been made to study the effects of various device parameters, including carrier degeneracy and heavy doping of the channel and shortening of gate length, on the I-V characteristics of JFETs. A new theoretical model for drift velocity v in semiconductors has been proposed for this purpose. A comparison of results from this model with those from the existing model of Trofimenkoff and with available experimental data for v attests to the accuracy of the proposed model. Unlike almost all other models, the simple functional form of the proposed model provides it with additional advantages for application to the analytical I-V study of FETs with both uniformly and nonuniformly doped channels. Use of this model in the framework of Lehovec-Zuleeg procedure for short-channel FETs appears to provide reasonably good results. Whereever experimental data are available, they agree well with those from the present model. The latter demonstrates that a very heavy doping in the p-type gate does not yield higher transconductance. A submicron gate and a heavy doping (higher than the nulled degeneracy level) in the channel are, on the other hand, necessary for higher drain saturation current and transconductance. A semiconductor alloy with the highest possible electron saturation velocity is the most suitable for high-speed JFETs.

Modeling of Ion-Implanted Field-Effect Transistors

M. B. Patil, S. N. Mohammad, and H. Morkoç

University of Illinois

Coordinated Science Laboratory

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

Interest in ion-implanted Field-Effect Transistors (FET's) has led to a study of device parameters as a function of implant parameters. In this paper, ion-implanted FET's are analyzed by considering the effect of electric field as well as doping density on the electron mobility. An effective mobility is defined such that the total current remains unchanged. This definition enables the calculation of device parameters for different implant conditions, gate lengths and material parameters. This computation is more efficient than two-dimensional numerical analysis. It is more involved than that employing an effective uniform doping profile. However, it is expected to be more accurate and allows direct theoretical comparison between different implant conditions. Such comparative analysis shows that a doping profile with a peak closer to the gate leads to improved transconductance and increased saturation current. The effect of source and drain resistance is taken into account by an iterative method. The degradation of device parameters due to these parasitic resistances is made clear. The model developed is compared with experimental data and is shown to produce reasonable agreement. Finally, the limitations of the model are pointed out.

Modeling of Field-Effect Transistors

with Laterally Graded Doping

M. B. Patil, S. N. Mohammad, and H. Morkoç

University of Illinois

Coordinated Science Laboratory

1101 W. Springfield Ave.

Urbana, IL 61801

and Material Research Laboratory

Abstract

Field-effect transistors with a laterally graded doping profile are analyzed. In particular, two different doping profiles are assumed under the gate with lower doping near the drain. The dependence of mobility on doping density is taken into account. The effect of velocity saturation is considered through a simple approximation. Source and drain series resistances are taken into account by solving a nonlinear system of equations. Device parameters are computed as a function of the position of implant-step from the source. The results are found to be in reasonable qualitative agreement with experimental data. Finally, the limitations on the validity of this model are discussed.

Reference #492

**Back-gated Field-Effect in a Double Heterostructure
Modulation Doped Field-Effect Transistor**

M. B. Patil, S. Agarwala, and H. Morkoç,

University of Illinois

Coordinated Science Laboratory

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

An $\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}/\text{GaAs}/\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}$ double heterojunction field-effect transistor has been fabricated, the novel feature being a p-n junction back gate. A device with $2\mu\text{m}$ channel length has yielded a change in transconductance by a factor of 2 for a change in back gate voltage of 1V. The performance of this device shows that this approach could be used in realizing novel devices such as velocity modulation transistor. Also, the change in threshold voltage with back gate bias could be useful in implementing digital circuits.

Reference #457

**Reduced Backgating Effect in
Modulation Doped Field-Effect Transistors
by p-n Junction Isolation**

M. B. Patil, S. Kalem, and H. Morkoç

University of Illinois
Coordinated Science Laboratory
1101 W. Springfield Ave.
Urbana, IL 61801

Abstract

Reduced backgating in modulation doped field-effect transistors (MODFET's) is achieved by p-n junction isolation. Before growing buffer layer for transistors, an AlGaAs p-n junction is included for isolating devices. Backgating characteristics are measured as a function of mesa depth and a dramatic reduction in backgating is observed when the mesas reach beyond the p-n junction. The dc performance of the MODFET is found to be comparable to previous results without such a p-n junction. Following this approach, great reduction in cross-talk between devices could be obtained in digital circuits.

Reference #465

**$\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}/\text{GaAs}$ MIS-TYPE FIELD-EFFECT TRANSISTOR
FABRICATED ON InP SUBSTRATE**

S. Agarwala, M. B. Patil, C. K. Peng, and H. Morkoç

University of Illinois

Coordinated Science Laboratory

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

An MIS-type $\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}/\text{GaAs}$ field-effect transistor with $1\text{-}\mu\text{m}$ -long by $145\text{-}\mu\text{m}$ -wide gates and intrinsic transconductance of 180 mS/mm has been demonstrated on InP substrate. The dislocation propagation is minimized by incorporating a superlattice on InP and a $1.5\text{-}\mu\text{m}$ undoped GaAs buffer layer is grown prior to the actual channel to ensure good quality of the $250\text{ \AA}$ active layer. A channel mobility of $1920\text{ cm}^2/\text{Vs}$ and a carrier concentration of $1.28 \times 10^{18}\text{ cm}^{-3}$ have been measured at 300 K . The device exhibits excellent pinch-off and the gate-to-source reverse breakdown voltage is greater than 5 V . The low output conductance of 2.5 mS/mm indicated small parallel conduction in the undoped GaAs buffer layer. Also, very little hysteresis was found in the i - v characteristics implying few traps in the epilayer.

A High Performance InGaAs/InAlAs Double Heterojunction Bipolar
Transistor with Non-alloyed n^+ -InAs Cap Layer on InP(n) by
Molecular Beam Epitaxy

C. K. Peng, T. Won, C. W. Litton, and H. Morkoç

ABSTRACT

We have demonstrated an InGaAs/InAlAs double heterojunction bipolar transistor (DHBT) on InP(n) grown by molecular beam epitaxy (MBE) with high dc performance. An n^+ -InAs emitter cap layer was used for non-alloyed contacts in the structure and specific contact resistances of 1.8×10^{-7} and $6.0 \times 10^{-6} \Omega \cdot \text{cm}^2$ were measured for the non-alloyed emitter and base contacts, respectively. Since no high temperature annealing is necessary, excellent contact surface morphology on thinner base devices can easily be obtained. In devices with $50 \times 50 \mu\text{m}^2$ emitter area, common-emitter current gains as high as 1,500 were achieved at a collector current density of $2.7 \times 10^3 \text{ A/cm}^2$. To our knowledge this is the highest current gain ever obtained in In based structures grown by MBE.

C. K. Peng, T. Won, and H. Morkoç are with the Coordinated Science Laboratory, University of Illinois, Urbana, IL 61801

C. W. Litton is with the Avionics Laboratory, Wright Patterson Air Force Base, OH 45433

Reference #428

In_{0.52}Al_{0.48}As/In_{0.53}Ga_{0.47}As Double Heterojunction
PnP Bipolar Transistors by Molecular Beam Epitaxy

by

T. Won, C.K. Peng, J. Chyi, and H. Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave

Urbana, IL 61801

Abstract

PnP In_{0.52}Al_{0.48}As/In_{0.53}Ga_{0.47}As double heterojunction bipolar transistors with a p⁺-InAs emitter cap layer grown by molecular beam epitaxy have been realized and tested for the first time. A 15 Å-thick In_{0.53}Ga_{0.47}As/InAs five period superlattice was incorporated between In_{0.53}Ga_{0.47}As and InAs emitter cap layer to smooth out the valence band discontinuity. Specific contact resistances of 1×10^{-5} and $2 \times 10^{-6} \Omega\text{cm}^2$ were measured for non-alloyed emitter and base contacts, respectively. The maximum common emitter current gain of 70 have been measured for 1500 Å-thick base transistors at a collector current density of $1.2 \times 10^3 \text{ A/cm}^2$. The current gains of the typical devices with an emitter area of $50 \times 50 \mu\text{m}^2$ were around 50 with an ideality factor of 1.4.

An $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ heterojunction bipolar
transistor on GaAs by molecular beam epitaxy

by

T. Won, S. Agarwala, and H. Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

We report on the first $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ heterojunction bipolar transistors grown on a GaAs substrate. In order to suppress the propagation of threading dislocations to the surface, a ten period $\text{AlAs}/\text{In}_{0.52}\text{Al}_{0.48}\text{As}$ ($20\text{\AA}/20\text{\AA}$) strained layer superlattice were repeated twice with intervening undoped $\text{In}_{0.52}\text{Al}_{0.48}\text{As}$ layers. The typical common emitter current gain in $50 \times 50 \mu\text{m}^2$ emitter area devices was 50, with a maximum of 63, at a collector current density of $2 \times 10^3 \text{ A/cm}^2$.

High Speed Performance of InP/In_{0.53}Ga_{0.47}As/InP
Double Heterojunction Bipolar Transistors

by

T. Won and H. Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

A theoretical comparison of In_{0.53}Ga_{0.47}As/InP and Al_{0.3}Ga_{0.7}As/GaAs heterojunction bipolar transistors has been undertaken in an effort to determine the relative merits of these material system. The analysis uses a compact transistor model and considers devices with self-aligned geometries including both extrinsic and intrinsic parameters. The high electron mobility in the In_{0.53}Ga_{0.47}As base layer and high peak velocity of electrons in the collector depletion layer result in a current gain cutoff frequency in excess of 150 GHz for an InP/In_{0.53}Ga_{0.47}As transistor with base thickness of 0.1 μm . Calculation revealed, however, that maximum oscillation frequency is strongly dependent on the contact resistance of the p-type base layer even for self-aligned base transistor. A maximum oscillation frequency of 138 GHz is theoretically predicted for an InP/In_{0.53}Ga_{0.47}As transistor with base thickness of 0.06 μm , base doping of $1 \times 10^{20} \text{cm}^{-3}$, a p-type contact resistance of $1.0 \times 10^{-7} \Omega \text{cm}^2$, a current density of $5 \times 10^4 \text{A/cm}^2$, and a V_{CB} of 5 volt.

Reference #420

Heterojunction Bipolar Transistors (HBTs)
for Millimeter-wave and Optoelectronic Applications

by

T.Won and H.Morkoç

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

This paper reviews the theory, governing parameters, and current status of heterojunction bipolar transistors fabricated using GaAs/AlGaAs and other III-V compounds. Because of many distinctive advantages over FETs such as higher current handling capability, elimination of stringent submicron lithography for high speed, and low $1/f$ noise, HBTs are of promise for future millimeter-wave and microwave integrated circuits. Fueled by the advancements of epitaxial growth and fabrication technologies, the devices with an f_{max} of 175 GHz and an f_t of 105 GHz have already been obtained. Epitaxial growth has reached a level where a whole host of new materials can be exploited for enhanced performance.

High-speed Performance of Si/Si_{1-x}Ge_x
Heterojunction Bipolar Transistors

by

T. Won and H. Morkoç

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

A theoretical investigation of Si/Si_{1-x}Ge_x heterojunction bipolar transistors has been undertaken in an attempt to determine their speed potential. The analysis is based on a compact transistor model and devices with self-aligned geometry, including both extrinsic and intrinsic parameters, are considered. For an emitter area of $1 \times 5 \mu\text{m}^2$, an f_t of over 70 GHz and f_{max} of over 30 GHz were computed at a collector current density of $1 \times 10^5 \text{ A/cm}^2$ and V_{CB} of 5V.

A High Gain GaAs/AlGaAs NpN Heterojunction Bipolar Transistor
on (100) Si Grown by Molecular Beam Epitaxy

by

T. Won, C.W. Litton¹, and H. Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

A. Yariv

California Institute of Technology

Pasadena, CA 91125

Abstract

High gain GaAs/AlGaAs NpN heterojunction bipolar transistors on Si substrates grown by molecular beam epitaxy have been fabricated and tested. In this structure, a n^+ -InAs emitter cap layer was grown in order to achieve a better ohmic contact. Typical devices with an emitter dimension of $50 \times 50 \mu\text{m}^2$ exhibited a current gain as high as 45 at a collector current density of $2 \times 10^3 \text{ A/cm}^2$ with an ideality factor of 1.4. To our knowledge, this is the highest current gain reported for HBTs grown on Si substrates. Breakdown voltages as high as 10 and 15 V were observed for the emitter-base and collector-base junctions, respectively. The investigation on devices with varying emitter dimensions demonstrates that much higher current gains can be expected by reducing the surface recombination at the periphery of the emitter junction.

¹Permanent address, Avionics Laboratory, Wright Patterson Air Force Base, OH 45433.

GaAs/AlGaAs Heterojunction Pnp Bipolar Transistors

Grown on (100) Si by Molecular Beam Epitaxy

by

T. Won, C.W. Litton¹, and H. Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

A. Yariv

California Institute of Technology

Pasadena, CA 91125

Abstract

GaAs/AlGaAs Pnp heterojunction bipolar transistors (HBTs) were fabricated and tested on (100) Si substrates for the first time. A common emitter current gain of $\beta = 8$ was measured for the typical devices with an emitter area of $50 \times 50 \mu\text{m}^2$ at a collector current density of $1 \times 10^4 \text{cm}^{-2}$ with no output negative differential resistance up to 280 mA, highest current used. A very high base-collector breakdown voltage of 10 V was obtained. Comparing the similar structures grown on GaAs substrates, the measured characteristics clearly demonstrate that device grade hole injection can be obtained in GaAs on Si epitaxial layers despite the presence of dislocations.

¹Permanent address, Avionics Laboratory, Wright Patterson Air Force Base, OH 45433

**AlGaAs/GaAs Single Heterojunction Bipolar
Transistors Grown on InP
by Molecular Beam Epitaxy**

by

S. Agarwala, T. Won, and H. Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

and

Materials Research Laboratory

1101 W. Springfield Avenue

Urbana, IL 61801

ABSTRACT

AlGaAs/GaAs single heterojunction bipolar transistors grown on InP substrates by molecular beam epitaxy have been fabricated and tested. An eight period $25 \text{ \AA} / 25 \text{ \AA}$ $\text{In}_{0.53}\text{Ga}_{0.47}\text{As}/\text{GaAs}$ strained layer superlattice is incorporated in the buffer structure to reduce dislocation propagation to the active region. Small-signal common emitter current gains of about 20 and 30 at a collector current density of $2 \times 10^3 \text{ A/cm}^2$ have been obtained for devices on InP as compared to about 60 and 150 for those on GaAs in structures with base thickness of $0.12 \text{ }\mu\text{m}$ doped with Be to 1×10^{19} and $1 \times 10^{18} \text{ cm}^{-3}$, respectively. Current densities as high as $1 \times 10^4 \text{ A/cm}^2$ have been achieved in these devices with emitter area of $50 \times 50 \text{ }\mu\text{m}^2$ without degradation demonstrating the excellent stability of this material. From the collector current dependence of the current gain, ideality factors of 1.3 and 1.2 for the emitter junctions have been obtained for devices on InP and GaAs, respectively.

Breakdown Behavior of GaAs/AlGaAs HBTs

by

J. Chen, Student Member, IEEE, G. B. Gao*, Senior Member, IEEE, J. Chyi and H. Morkoç, Fellow, IEEE

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 W. Springfield Avenue

Urbana, IL 61801

Abstract

Avalanche breakdown behavior at the collector junction of the GaAs/AlGaAs HBT has been studied. The dependence of collector-base breakdown voltage upon the collector doping concentration and thickness was investigated, showing expected functional behavior. Associated breakdown voltage calculations using simple punch-through considerations were found to be in close agreement with the maximum breakdown voltages - measured from devices displaying the most uniform junction breakdown.

Junction breakdown characteristics including both localized microplasma effects as well as uniform microplasma-free behavior were observed. At avalanche breakdown in the GaAs p - n junction, we report the first known observation of light emission from the collector-base junction of a GaAs/AlGaAs HBT. Collector-emitter breakdown characteristics showing expected negative resistance breakdown were also investigated. Associated current gain measurements were performed in connection with the analysis of the collector-emitter/collector-base breakdown voltages.

* On leave from the Beijing Polytechnic University, Reliability Physics Laboratory, Beijing, China.

An $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ heterojunction bipolar transistor
on GaAs substrate by molecular beam epitaxy

by

T.Won, S.Agarwala, and H.Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

The $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ heterojunction bipolar transistors were grown and fabricated on a GaAs substrate by molecular beam epitaxy. In order to suppress the propagation of threading dislocations to the surface, a ten period $\text{AlAs}/\text{In}_{0.52}\text{Al}_{0.48}\text{As}$ ($20\text{\AA}/20\text{\AA}$) strained layer superlattice was incorporated twice with intervening undoped $\text{In}_{0.52}\text{Al}_{0.48}\text{As}$ layers. The devices with an emitter area of $50 \times 50 \mu\text{m}^2$ exhibited a typical common emitter current gain of 50, with a maximum of 63, at a collector current density of $2 \times 10^3 \text{ A/cm}^2$.

Collector Offset Voltage of Heterojunction Bipolar Transistors

Grown By Molecular Beam Epitaxy

by

T.Won, S.Iyer, S.Agarwala, and H.Morkoc

Coordinated Science Laboratory

University of Illinois

1101 W. Springfield Ave.

Urbana, IL 61801

Abstract

The collector-emitter offset voltages of AlGaAs/GaAs and InAlAs/InGaAs heterojunction bipolar transistors grown by molecular beam epitaxy have been investigated. Both geometrical and electrical asymmetry between emitter and collector junctions in these mesa isolated transistors account for the offset voltages observed. Devices exhibited offset voltages in the range of 50 to 300 mV depending on the structures and geometrical parameters. Several electrical and geometrical factors affecting the offset voltage are discussed in detail.

**EXTREMELY LOW RESISTANCE NON-ALLOYED OHMIC CONTACTS ON GaAs USING
InAs/InGaAs AND InAs/GaAs STRAINED LAYER SUPERLATTICES**

C. K. Peng, G. Ji, N. S. Kumar, and H. Morkoc
University of Illinois
Coordinated Science Laboratory
1101 W. Springfield Ave.
Urbana, IL 61801

Abstract

Employing a structure consisting of n^+ InAs/InGaAs and InAs/GaAs strained layer superlattices (SLS) grown by molecular beam epitaxy on GaAs films, non-alloyed contact resistances less than $8.5 \times 10^{-8} \Omega \text{cm}^2$ have been obtained. Self-consistent simulations show that these extremely small non-alloyed contact resistances are due to the suppression of the depletion depth in the GaAs channel and tunneling through the SLS layer. Similar structures on InGaAs channels have led to non-alloyed specific contact resistances of about $1.5 \times 10^{-8} \Omega \text{cm}^2$. These results represent the smallest figures reported for these important material systems.

Reference #450

**A GaAs METAL SEMICONDUCTOR FIELD EFFECT TRANSISTOR
WITH EXTREMELY LOW RESISTANCE NON-ALLOYED OHMIC CONTACTS
USING AN InAs/GaAs SUPERLATTICE**

by

N. S. Kumar, J.-I. Chyi, C. K. Peng and H. Morkoç

University of Illinois

Coordinated Science Laboratory

1101 W. Springfield Avenue

Urbana, IL 61801

ABSTRACT

GaAs MESFETs with extremely low resistance non-alloyed ohmic contacts have been demonstrated. The contact structure consists of an n^+ -InAs/GaAs strained layer superlattice (SLS) and an InAs cap layer. Contact resistances of 0.036 Ω -mm and specific contact resistivities of $4.9 \times 10^{-8} \Omega \text{ cm}^2$ have been measured. These results represent the smallest figures reported to date for FETs on any material system. Non-alloyed MESFETs with 1- μm gate lengths had transconductances of about 210 mS/mm.

Reference #499

**Low resistance nonalloyed ohmic contacts on p-type GaAs
using GaSb/GaAs strained-layer superlattices**

J.-I. Chyi, J. Chen, N. S. Kumar, C. Kiely, C. K. Peng*, and H. Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory and Materials Research Laboratory

1101 W. Springfield Avenue

Urbana, IL 61801

ABSTRACT

The formation of ohmic contacts is of considerable importance in semiconductor devices, particularly, for high power, low noise microwave transistors and laser diodes. To obtain high performance and good reliability, a low-resistance ohmic contact is necessary. Conventional ohmic contacts to GaAs involve alloying at high temperatures, which cause diffusion of contact metals into the semiconductor. As device dimensions shrink, nonalloyed ohmic contacts become an almost inevitable part of the fabrication process, avoiding the lateral and vertical diffusion associated with high temperature processing. Using a GaSb/GaAs strained-layer superlattice (SLS) and a GaSb cap layer, we have obtained p-type nonalloyed ohmic contacts with specific contact resistivities as low as $3.16 \times 10^{-7} \Omega \cdot \text{cm}^2$, which is, to our knowledge, the lowest value reported to date for nonalloyed contacts on p-type GaAs. The samples investigated in this study were grown on semi-insulating (100)GaAs substrates by molecular beam epitaxy (MBE). The structure consists of a $0.2 \mu\text{m}$ undoped GaAs buffer, a $0.1 \mu\text{m}$ Be-doped ($5 \times 10^{18} \text{ cm}^{-3}$) GaAs channel, ten periods of $10 \text{ \AA}/10 \text{ \AA}$ Be-doped ($1 \times 10^{19} \text{ cm}^{-3}$) GaSb/GaAs SLS, and finally a $50 \text{ \AA}$ Be-doped ($1 \times 10^{19} \text{ cm}^{-3}$) GaSb cap layer. Detailed discussion of growth conditions, sample preparation and resistance measurements will be presented. Thermal stability, contact metal selectivity and the results of TEM studies will also be discussed.

* Current address: University of Florida, Department of Electrical Engineering, Gainesville, FL 32608.

Calculation of the I-V Characteristics of Direct Tunneling Diodes

D. Mui, M. Patil, J. Chen, S. Agarwala, N. S. Kumar, and H. Morkoç

University of Illinois at Urbana-Champaign,

Coordinated Science Laboratory,

1101 West Springfield Avenue, Illinois 61801

We present a calculation of the I-V characteristics of direct tunneling diodes with an undoped tunneling barrier. The effect of band-bending is included in the calculation by solving two coupled one-dimensional Poisson's equations. The transfer matrix method is used for the calculation of the transmission probability of the tunneling electron whose complex k -vector is obtained from a $k \cdot p$ band structure calculation. An energy dependent density of states effective mass which is also calculated from the $k \cdot p$ band structure is used. Predictions for an $\text{In}_{0.53}\text{Ga}_{0.47}\text{As}/\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ diode which is lattice matched to InP agree quantitatively with experiment. Results obtained from models based on the effective-mass approximation is approximately a factor of four smaller than that of the present model.

Reference #476

**AlGaAs/GaAs MULTIPLE QUANTUM WELL REFLECTION MODULATORS
GROWN ON Si SUBSTRATES.**

W. Dobbelaere, D. Huang, M.S. Ünlü and H. Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 W. Springfield Ave.

Urbana, Illinois 61801

ABSTRACT

We report for the first time large excitonic absorption at room temperature in AlGaAs/GaAs Multiple Quantum Well structures grown on Si substrates in a p-i-n configuration, using photocurrent measurements. We demonstrate an optical reflection modulator which is based on the quantum-confined Stark Effect and exciton broadening with a reverse bias voltage applied across the p-i-n structure. A 7.7% change in the reflectivity of the device with 6V reverse bias voltage was observed. These results demonstrate clearly that optical device quality GaAs/AlGaAs is obtainable directly on Si substrates which has great implications with regard to the monolithic integration of optical III-V and electronical Si-technology.

Reference #437

InGaAs/GaAs multiple quantum well reflection modulators

by

W. Dobbelaere, D. Huang, S. Kalem and H. Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 W. Springfield Avenue

Urbana, IL 61801

U.S.A.

ABSTRACT

We demonstrate a p-i-n reflection modulator consisting of a 50 period strained layer $\text{In}_{0.15}\text{Ga}_{0.85}\text{As}$ / GaAs multiple quantum well and a 5 period AlAs/GaAs quarter wave stack dielectric mirror, grown on a GaAs substrate by Molecular Beam Epitaxy. We observed a relative change in the reflectivity of the modulator of 12 % with 4.5V reverse bias voltage and at 0.996 μm wavelength.

Reference #464

InGaAs/GaAs STRAINED LAYER MQW ELECTROABSORPTION

OPTICAL MODULATOR AND SELF-ELECTROOPTIC EFFECT

DEVICE

Abstract. We observed a clear excitonic absorption effect at room temperature in MBE-grown $\text{In}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ strained layer Multiple Quantum Well structures and fabricated optical p-i-n modulators on the same structures. A change of 27% in the transmission, corresponding to a change in the absorption coefficient of 2260 cm^{-1} , with 6 volt reverse bias voltage and at $9710\text{ \AA}$ wavelength was measured. We also operated the modulator as a Self-Electrooptic Effect Device, resulting in a non-linear optical input-output characteristic.

Multiple Quantum Well (MQW) p-i-n modulators, based on the quantum confined Stark effect have been demonstrated extensively in the $\text{AlGaAs}/\text{GaAs}$ material system^{1,2}. The ternary material InGaAs is however becoming increasingly interesting for optical modulator and laser applications in integrated optics because it allows operation in the infrared region. High frequency MQW electroabsorption optical modulators have been reported in the InGaAs/InP material system, grown by MOCVD³, and in the $\text{InGaAs}/\text{InAlAs}$ material system grown by MBE⁴. In this letter we report an MBE-grown p-i-n electroabsorption light modulator in the strained layer $\text{InGaAs}/\text{GaAs}$ ⁵ material system. We first describe the modulator structure and the device fabrication. Then we discuss the electroabsorption effect which is the basis for the modulator operation along with the device performance. Finally we describe the performance as a Self-Electrooptic Effect Device (SEED)⁶.

Band Lineup in $\text{GaAs}_{1-x}\text{Sb}_x/\text{GaAs}$ Strained-Layer Multiple Quantum
Wells Grown by Molecular Beam Epitaxy

G. Ji, S. Agarwala, D. Huang and H. Morkoc

Coordinated Science Laboratory
University of Illinois at Urbana-Champaign
1101 West Springfield Avenue
Urbana, IL 61801

Abstract

$\text{GaAs}_{1-x}\text{Sb}_x/\text{GaAs}$ strained-layer multiple quantum wells (MQWs) have been grown by molecular beam epitaxy and characterized by room temperature photoreflectance (PR). The PR spectra denote that high quality layers can be grown in the $\text{GaAs}_{1-x}\text{Sb}_x/\text{GaAs}$ system. The method for determining the band offset Q_{vh} is discussed in this strained-layer system. Based on this treatment and the band gap formula of bulk $\text{GaAs}_{1-x}\text{Sb}_x$ a value of the heavy hole band offset, $Q_{vh} \sim 1.7$ has been obtained for $\text{GaAs}_{1-x}\text{Sb}_x/\text{GaAs}$ with $x = 0.1$ establishing a type II structure with electrons in GaAs layers and heavy and light holes in $\text{GaAs}_{1-x}\text{Sb}_x$ layers, respectively.

Reference #433

PACS numbers 78.65 -S 78.65 Fa.

**Optical Transitions Involving Unconfined Energy States
in InGaAs/GaAs Multiple Quantum Wells**

G. Ji, W. Dobbelaere, D. Huang and H. Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 W. Springfield Ave.

Urbana, IL 61801

Optical transitions with energies higher than that of GaAs bandgap in highly strained $\text{In}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ multiple quantum well structures have been observed in photoreflectance spectra. In some samples as many as seven such structures were present. We identify them as transitions between the unconfined electron states and the confined heavy hole states. For energies below GaAs signal, intense transitions corresponding to such unconfined subbands were also observed. The intensity of the transitions involving unconfined subbands decreases with increasing well width, but is weakly dependent of the mole fraction, x . The transmission coefficients are calculated in order to locate the positions of the unconfined subband energies. Good agreement is obtained between the experimental data and the theoretical calculation.

PACS numbers 78.65-5, 78.65-Fa

Reference #430

Photoreflectance, Absorption and Nuclear Resonance Reaction Studies of
 $\text{Al}_x\text{Ga}_{1-x}\text{As}$ Grown by Molecular Beam Epitaxy

D. Huang, G. Ji, U.K. Reddy, and H. Morkoc

Coordinated Science Laboratory
University of Illinois at Urbana-Champaign
1101 W. Springfield Ave.
Urbana, IL 61801

F. Xiong and T.A. Tombrello

Division of Physics and Astronomy
California Institute of Technology
Pasadena, CA 91125

Abstract

The photoreflectance (PR) spectra of bulk $\text{Al}_x\text{Ga}_{1-x}\text{As}$ alloys with $x \leq 0.45$ were studied. The observed lineshapes from different samples suggest that PR technique is very sensitive to the material quality, surface condition and the background impurities. The energy gap derived from the PR spectra compared well to that obtained from the absorption spectra. The relationship between the energy gap and the Al mole fraction value, x , was established through the nuclear resonance reaction analysis (NRRA). The electric field near the surface was calculated from the periodicity of Franz-Keldysh oscillations observed in many of the samples. From our analysis, we believe that the number of oscillations shown in PR spectra corresponds to sample quality, in general. We also believe that the low-field-like lineshape is mainly caused by the fluctuation of Al distribution along the growth direction. An additional feature related to the impurity transition was also observed in the spectra.

Reference #

PACS No. 78.20.WC

Excitonic absorption in modulation-doped
GaAs/Al_xGa_{1-x}As quantum wells

D. Huang, H.Y. Chu,* Y.C. Chang,* R. Houdre and H. Morkoc

Coordinated Science Laboratory
University of Illinois at Urbana-Champaign
1101 West Springfield Avenue
Urbana, Illinois 61801-3082

We have performed transmission measurements in a range of undoped through heavily modulation doped GaAs/Al_xGa_{1-x}As multiple-quantum-well structures (MQW). The observed absorption spectra demonstrate quenching of the excitonic oscillations with increasing quasi-two-dimensional electron gas. The electron density corresponding to the total bleaching of the lowest excitonic oscillation is greater than or equal to $3 \times 10^{11} \text{ cm}^{-2}$ for a quantum well size of 200 Å. Theoretical calculations of the absorption spectra which include the effect of carrier screening have been made. The results show that both long-range and short range many-body effects should be included to explain the experimentally observed spectra. In the modulation doped case, we conclude that the phase-space filling and exchange of the electron gas are the dominant effects on excitonic absorption. From the observation that the linewidth increases with the electron density, we demonstrate that the exciton lifetime reduces due to the interaction between the electrons and the excitons.

* also at Materials Research Laboratory, University of Illinois at Urbana-Champaign, 104 South Goodwin Avenue, Urbana, Illinois, 61801

pacs # 71.35.+Z, 78.65.Fa

Band Structure Determination of Modulation Doped Multiquantum Well Heterostructures

G. Ji, T. Henderson, C.K. Peng, D. Huang and H. Morkoc
University of Illinois at Urbana-Champaign
Coordinated Science Laboratory
1101 W. Springfield Avenue, Urbana IL 61801

Abstract

We present a precise and effective numerical procedure to model the band diagram of modulation doped multiquantum well heterostructures. This method is based on a self-consistent iterative solution of the Schrödinger equation and the Poisson equation. It can be used rather easily in any arbitrary modulation-doped structure. In addition to confined energy subbands, the unconfined states can be calculated as well. Examples on realistic device structures are given to demonstrate capabilities of this procedure. The numerical results are in good agreement with experiments. With the aid of this method we have identified the transitions involving both the confined and unconfined conduction subbands in a modulation doped AlGaAs/GaAs superlattice, and in a strained layer InGaAs/GaAs superlattice. These results represent the first observation of unconfined transitions in modulation doped multiquantum well structures.

Reference #440

PACS numbers 73.20.DX 78.65.Fa

PHOTOLUMINESCENCE STUDIES OF GaAs GROWN ON InP SUBSTRATES
BY MOLECULAR BEAM EPITAXY

D.Huang, S.Agarwala, and H.Morkoç

University of Illinois at Urbana-Champaign

Coordinated Science Laboratory

1101 W. Springfield Avenue

Urbana, IL 61801

Abstract

GaAs based field effect transistor structures have been grown on InP substrates with the InGaAs/GaAs strained layer superlattices and 1.5 μm GaAs layer as the buffer. The low temperature (4K) photoluminescence (PL) from this GaAs buffer has been studied for the first time. Among five observable peaks, the excitonic transition at energy 1.513 eV and the impurity associated recombination at energy 1.483 eV have been identified with the aid of reflection, absorption, and temperature and excitation-intensity dependent PL measurements. The peak at 1.504 eV, most probably due to an exciton bound to a defect, is greatly enhanced compared with that of homoepitaxially grown GaAs. The optical results show that GaAs films of good quality can be grown on InP substrate, which is consistent with device results.

PUBLICATIONS

Books

1. H. Morkoc, H. Ünlü and G. Ji, "Fundamentals and Technology of MODFETs", in process. Wiley and Sons.
2. R.L. Gunshor and H. Morkoc, Eds., "Growth of Compound Semiconductors, *Proc. of SPIE*, Bay Point, FL, Meeting, 1987.
3. F. Leonberger, H.C. Lee, F. Capasso and H. Morkoc, Eds., *Proc. of 1987 OSA Picosecond Electronics and Optoelectronics Meeting*, Springer Verlag, Springer-Series in Electronics and Photonics, 24, Berlin Heidelberg, 1987.

Book Chapters & Special Issues

1. H. Morkoc, "Modulation Doped $\text{Al}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ Field Effect Transistors (MODFETs)," *Analysis, Fabrication and Performance, MBE and Heterostructures*, Ed. L.L. Chang and K. Ploog, Martinus Nijhoff Publishers, The Netherlands, Series E, Vol. 87, Ch. 7, pp. 625-676, 1985. (Based on a lecture given at NATO Advanced Series E, Study Institute on MBE and Heterostructures, March 7-19, 1983).
2. H. Morkoc, Editor, Proceedings of the 4th MBE Workshop, *J. Vac. Sci. Technol. B*, Vol. 1, pp. 119-205, 1983.
3. H. Morkoc, "Modulation Doped $\text{Al}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ Heterostructures," in *The Technology and Physics of Molecular Beam Epitaxy*, Ed. E.H.C. Parker, Plenum, NY 1985 (pp. 185-231).
4. H. Morkoc and H. Ünlü, "A Critical Discussion of Factors Affecting the Performance of MODFETs, Microwave and Digital Applications," in *Device and Circuit Applications of III-V Semiconductor Superlattices and Modulation Doping*, Editor, R. Dingle, Semiconductors and Semimetals, Academic Press, 1987.
5. H. Morkoc and M. Abe, Editors, "Heterojunction Field Effect Transistors," *IEEE Trans. Electron. Dev.*, Vol. ED-33, No. 5, pp. 541-792, May 1986.
6. R. Houdré and H. Morkoc, "Properties of MBE Grown GaAs on Si," *CRC Critical Rev.*
7. H. Ünlü and H. Morkoc, "Growth and Properties of GaAs-Based Devices on Si," in *GaAs Technology*, Vol. II, Ed. D.K. Ferry, Howard Sons and Co., Indianapolis, 1988

Popular Articles

1. H. Morkoc and P.M. Solomon, "The HEMT: A Superfast Transistor," *IEEE Spectrum*, Vol. 21, No. 2, pp. 28-35, February 1984. (invited)

2. T.J. Drummond, W.T. Masselink, and H. Morkoc, "Modulation Doped GaAs/(Al,Ga)As Heterojunction Field-Effect Transistors: MODFETs," *Proceedings of IEEE*, Vol. 74, No. 6, pp. 773-822, June 1986. Translated into Russian as well.
3. H. Morkoc and P.M. Solomon, "MODFET - Superschennelle Transistoren". *Technische Rundschau*, TR10, 77 Jahrgang, pp. 74-79, March 1985. (invited)
4. H. Morkoc, "Developments in the GaAs on Si Technology," American Inst. of Physics News Release.
5. G. Munns and H. Morkoc, "GaAs on Si: Progress and Opportunities," *Physics Today*, Physics News in 1986, January 1987, (invited).
6. H.Z. Chen, A. Ghaffari, H. Wang, H. Morkoc, and A. Yariv, "Continuous Wave operation of GaAs Lasers on Si Substrates," *Optics News*, Vol. 13, pp. 13, Dec 1987.
7. H.Z. Chen, J. Paslaski, A. Yariv and H. Morkoc, "GaAs/AlGaAs Lasers on Si Substrates and Their High Frequency Characteristics," *Industrial Research and Development*, Vol. , pp. Jan 1988.
8. H. Ünlü and H. Morkoc, "Strained Layer InGaAs/GaAs Quantum Wells and Their Applications to Ultra-high Frequency MODFETs", *Solid State Technology*, Vol. 31, pp. 83-87, March, 1988.
9. H. Morkoc, H. Ünlü, H. Zabel and N. Otsuka, "GaAs on Si: A Review", *Solid State Technology*, Vol. 31, pp. 71-76, March 1988.
10. S. Iyer, H. Morkoc, N. Otsuka, and H. Zabel, "New Structures Formed by Molecular Beam Epitaxy: The Case of GaAs on Si," *Comments on Condensed Matter Physics*, in process.
11. S. Iyer, H. Morkoc, N. Otsuka, and H. Zabel, "Gallium Arsenide on Silicon: Epitaxial Growth and Characterization," *J. Appl. Phys. Rev.*, pending.
12. H.Z. Chen, J. Paslaski, H. Morkoc and A. Yariv, "High Speed GaAs Lasers and Detectors on Silicon for Optical Interconnects," *Optics News*, Vol. 14, pp. 24-25, (1988).

396. D. Levi, S.L. Zhang, M.V. Klein, J. Klem, and H. Morkoc, "Raman Study of the Effects of Annealing on Folded LA and Confined LO Phonons in GaAs-AlAs Superlattices." *Phys. Review B*, Vol. 36, pp. 8032-8037 (1987).
397. S.L. Zhang, D. Levi, T.A. Grant, M.V. Klein, J. Klem, and H. Morkoc, "Investigation of Confined Optic Phonons and Their Annealing Effects in GaAs/AlAs Superlattices," *Proc. of 10th Int. Conf. on Raman Spect.*, Chemical Physics Institute, University of Oregon, 1986.
398. A. Schenstrom, M. Levy, B.K. Sharma, and H. Morkoc, "Frequency Dependent Break-down of the Dissipation Less State in the Quantum Hall Effect," *Phy. Rev. Lett.*, pending.
399. K. Shum, M.R. Junnarkar, H.S. Chao, R.R. Alfano, and H. Morkoc, "Observation of Ultrafast Lateral Diffusion of Photogenerated Carriers in An Assymetric GaAs Quantum Well," *Phy. Rev. Lett.*, pending.
400. K. Shum, M.R. Junnarkar, H.S. Chao, R.R. Alfano, and H. Morkoc, "Effects of Non-equilibrium Phonon on the Energy Relaxation and Recombination Lifetime of Photogenerated Carriers in Undoped GaAs Quantum Wells," *Phys. Rev. B*, Vol. 37, pp. 8923-8931. (1988).
401. D.Y. Oberli, D.R. Wake, M.V. Klein, T. Henderson, and H. Morkoc, "Picosecond Raman and Luminescence Studies of Carrier Relaxation in Quantum Wells," *Proc. of 3rd USA-USSR Symposium on Laser Optics of Condensed Matter*, Leningrad, June 1-6, 1987.
402. M.V. Klein, T.A. Gant, D. Levi, S.L. Zhang, T. Henderson, J. Klem, and H. Morkoc, "Raman Studies of Phonons in GaAs/AlGaAs Superlattices," *Proc. of 3rd USA/USSR Symposium on User Optics of Condensed Matter*, Leningrad, June 1-6, 1987.
403. D.A. Neumann, H. Zabel, and H. Morkoc, "Terracing in Strained Layer Superlattices," *J. Appl. Phys.*, in print.
404. Y.E. Ihm, N. Otsuka, J. Klem, and H. Morkoc, "Ordering in $\text{GaAs}_{1-x}\text{Sb}_x$ Grown by Molecular Beam Epitaxy," *Appl. Phys. Lett.*, Vol. 51, pp. 2013-2015 (1987).
405. D. Huang, H.Y. Cho, Y.C. Chang, R. Houdré and H. Morkoc, "Excitonic Absorption in Modulation Doped GaAs/AlGaAs Quantum Wells," *Phys. Rev. B*, Vol. 38, pp. 1246-1250.
406. H.Z. Chen, A. Ghaffari, H. Morkoc, and A. Yariv, "Very Low Threshold (under 100 A/cm²) GaAs/AlGaAs Graded Index Separate Confinement Lasers Grown by Molecular Beam Epitaxy," *Electronics Letts.*, Vol. 23, pp. 1334-1335 (1987).
407. H.Z. Chen, A. Ghaffari, H. Morkoc, and A. Yariv, "Effect of Substrate Tilting on Molecular Beam Epitaxial Grown AlGaAs/GaAs Lasers Having Very Low Threshold Current Densities," *Appl. Phys. Letts.*, Vol. 51, pp. 2094-2096 (1987).
408. R. Vincent, D. Cherns, S.J. Bailey, and H. Morkoc, "Structure of AlGaAs/GaAs Multilayers Imaged in Superlattice Reflections," *Phil. Mag. Lett.*, Vol. 56, (1), pp. 1-6, (1987).

409. D.C. Reynolds, K.K. Bajaj, G. Peters, C. Leak, W.M. Theis, P.W. Yu and H. Morkoc, "Correlation Between the Light and Heavy Hole Free Exciton Fine Structure in $\text{Al}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ Multi-Quantum Well Using Photoluminescence Excitation Spectroscopy," *Phys. Rev. B*, Vol. 37, pp. 7133-7136, (1988).
410. W.M. Theis, G.D. Sanders, C.E. Leak, K.K. Bajaj and H. Morkoc, "Excitonic Transitions in GaAs , GaAlAs Quantum Wells Observed by Photoreflectance Spectroscopy: Comparison with a First Principle," *Phys. Rev. B*, Vol. B37, pp. 3042, (1988).
411. P.L. Derry, H.Z. Chen, H. Morkoc, A. Yariv, K.Y. Lau, N. Bar-Chaim, K. Leonard, J. Rosenberg, "Ultra Low Threshold Graded Index Separate Confinement Heterostructure Single Quantum Well (Al,Ga)As Lasers," Presented at the 8th MBE Workshop Sept. 9-11, 1987, UCLA, J. Vac. Sci. & Technol., Vol. B6, pp. (1988).
412. F. Xiong, T.A. Tombrello, H.Z. Chen, H. Morkoc, and A. Yariv, "Direct Determination of Al Depth Fluctuation in MBE Grown $\text{Al}_x\text{Ga}_{1-x}\text{As}$," Presented at the 8th MBE Workshop Sept. 9-11, 1987, UCLA, J. Vac. Sci. & Technol., Vol. B6, pp. 758-762, (1988).
413. Y.E. Ihm, N. Otsuka, J. Klem and H. Morkoc, "Ordering in $\text{GaAs}_x\text{Sb}_{1-x}\text{As}$ Grown by Molecular Beam Epitaxy," Presented at the 8th MBE Workshop Sept. 9-11, 1987, UCLA, Appl. Phys. Lett., Vol. 51(20), pp. 2013-2015, (1987).
414. K.T. Tsen and H. Morkoc, "Picosecond Raman Studies of the Optical Phonons in the $\text{Al}_x\text{Ga}_{1-x}\text{As}$ Layers of $\text{GaAs}/\text{AlGaAs}$ Multiple Quantum Well Structures," *Phys. Rev. B Rapid Comm.*, April, 1988.
415. T. Henderson, U.K. Reddy, G. Ji, H. Morkoc, and N. Otsuka, "Characterization of Pseudomorphic $\text{InGaAs}/\text{AlGaAs}$ MODFET Structures Grown by Molecular Beam Epitaxy," *Tech. Digest of 1987 Int. Elect. Dev. Meeting*, Dec. 7-9, 1987, Washington, D.C., pp. 418-421.
416. J. Chen, M.S. Ünlü, T. Won, G. Munns, and H. Morkoc, "Electrical Properties of Thermally Annealed $\text{p-GaAs}/\text{Sn-Si}$ Heterojunctions and the Implications for GaAs/Si Heterojunction Bipolar Transistors," *Tech. Digest of 1987 Int. Elec. Dev. Meeting*, Dec. 7-9, 1987, Washington, D.C., pp. 82-85.
417. H.Z. Chen, J. Paslaski, A. Ghaffari, H. Wang, H. Morkoc, and A. Yariv, "High Speed Modulation and CW Operation of $\text{AlGaAs}/\text{GaAs}$ Lasers on Si," *Tech. Digest of 1987 Int. Elect. Dev. Meeting*, Dec. 7-9, 1987, Washington, D.C., pp. 238-241.
418. Y.E. Ihm, N. Otsuka, J. Klem and H. Morkoc, "Ordering in $\text{GaAs}_{1-x}\text{Sb}_x$ Grown by Molecular Beam Epitaxy," *Proc. of MRS Fall Meeting (Epitaxy of Semiconductor Layered Structures)*, Eds. R.T. Tung, L.R. Dawson and R.L. Gunshor.
419. J. Chen, T. Won, M.S. Ünlü, H. Morkoc, and D. Verret, "GaAs/Si Heterojunction Bipolar Transistors," *Appl. Phys. Lett.*, Vol. 52, pp. 822-824, (1988).
420. T. Won and H. Morkoc, "High Speed Performance of $\text{InP}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}/\text{InP}$ Double Heterojunction Bipolar Transistors," *Appl. Phys. Lett.*, Vol. 52, pp. 552-554, (1987).

421. H.Z. Chen, J. Paslaski, A. Yariv and H. Morkoc, "High Frequency Modulation of AlGaAs/GaAs Lasers Grown on Si by Molecular Beam Epitaxy," *Appl. Phys. Lett.*, Vol. 52, pp. 605-606 (1987).
422. D. Huang, J. Chyi, J. Klem and H. Morkoc, "Optical Properties of Molecular Bean Epitaxially Grown $\text{GaAs}_{1-x}\text{Sb}_x$ ($0 \leq x \leq 0.5$) on GaAs and InP Substrates," *J. Appl. Phys.*, Vol. 63, pp. 5859-5862, (1988).
423. C.K. Peng, J. Chen, J. Chyi, and H. Morkoc, "Extremely Low Non- alloyed and Alloyed Contact Resistances Using InAs Cap Layers on InGaAs by Molecular Beam Epitaxy," *J. Appl. Phys.*, Vol. 64, pp. 429-431, 1988.
424. T. Henderson and H. Morkoc, "Performance of AlGaAs/InGaAs Pseudomorphic MOD-FETs at Cryogenic Temperatures," *Proc. of Electronic Chem. Soc., Low Temperature Elec-tronics*, Oct. 19-24, 1987, Hawaii (Invited).
425. H.Z. Chen, H. Morkoc, and A. Yariv, "Very Low Threshold AlGaAs/GaAs Lasers Grown on Tilted (100) Substrates by Molecular Beam Epitaxy," *Tech. Digest of 1987 IEDM*, Dec 7-9, 1987, pp. 887-888.
426. A.S. Bommannavar, A. Wobenschuss, G.E. Ice, C.J. Sparks, H. Morkoc, and H. Zabel, "X-ray diffraction study of a Thin GaAs Film on Si (100)," *Proc. of Materials Res. Soc.*, Fall meeting, 1987.
427. J. Paslaski, H.Z. Chen, H. Morkoc, and A. Yariv, "High Speed GaAs pin Diodes Grown on Si Substrates by Molecular Beam Epitaxy," *Appl. Phys. Lett.*, Vol. 52, pp. 1410-1412, (1988).
428. C.K. Peng, T. Won, C.W. Litton and H. Morkoc, "A High performance InGaAs/InAlAs Double Heterojunction Bipolar Transistor with Non-alloyed n^+ InAs Cap Layer on InP(n) Grown by Molecular Beam Epitaxy," *IEEE Electron. Device Lett.*, Vol. 9, pp. 331-333, (1988).
429. W. Dobbelaere, S. Kalem, D. Huang, S. Ünlü and H. Morkoc, "InGaAs/GaAs Strained Layer Multiple Quantum Well Electro-absorption Optical Modulation," *Electronics Lett.*, Vol. 24, pp. 295-297, (1988).
430. G. Ji, W. Dobbelaere, D. Huang and H. Morkoc, "Optical Transitions Involving Unconfined Energy States in InGaAs/GaAs Multiple Quantum Wells," *Phys. Review B.*, in print.
431. P. Roblin, L. Rice, S. Bibyk ~~Wann~~, and H. Morkoc, "Non-Linear Parasitics in MODFETs and the MODFET I-V Characteristics," *IEEE Trans. on Elec. Devices.*, Vol. 35, pp. 1207-1213, (1988).
432. S.C. Kan, H. Morkoc, and A. Yariv, "GaAs/AlAs Double Barrier Resonant Tunneling Structure on Si with Large Peak to Valley Ratio at Room Temperature," *Appl. Phys. Lett.*, Vol. 52, pp. 2250-2251, (1988).

433. G. Ji, S. Agarwala, D. Huang, J. Chyi and H. Morkoc, "Band Lineup in $\text{GaAs}_{1-x}\text{Sb}_x/\text{GaAs}$ Strained Layer Multiple Quantum Wells Grown by Molecular Beam Epitaxy," *Phys. Rev. B.*, Vol. 38, pp. 1057-1061 (1988).
434. J.F. Klem, J.I. Chyi, H. Morkoc, Y.E. Ihm, and N. Otsuka, "Electrical Characterisitcs of MBE grown $\text{GaAs}_{1-x}\text{Sb}_x$ on InP and Correlation with Film Thickness," *Proc. of SPIE-O-E*, Los Angeles, Jan. 13, 1988.
435. J.F. Klem, D. Huang, Y.E. Ihm, H. Morkoc and N. Otsuka, "Opticial Characterization of $\text{GaAs}_{1-x}\text{Sb}_x$ and $\text{GaAs}_{1-x}\text{Sb}_x/\text{GaAs}$ Strained Layer Superlattice," *SPIE-O-E*, Los Angeles, Jan. 13, 1988.
436. T. Won, C.K. Peng, J. Chyi, and H. Morkoc, " $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ Double Heterojunction PnP Bipolar Transistors by Molecular Beam Epitaxy," *IEEE Electron Dev. Lett.*, Vol. 9, pp. 334-336, (1988).
437. W. Dobbelaere, D. Huang, M.S. Ünlü, and H. Morkoc, "AlGaAs/GaAs Multiple Quantum Well Reflection Modulators Grown on Si Substrates," *Appl. Phys. Lett.*, Vol. 53(2), pp. 94-96, (1988).
438. S.T. Fu, S.M. Liu, M.B. Das, P.C. Chao, D.M. Smith, K.C.G. Litor, W. Kopp, C.V. Peng, J. Klem, T. Henderson and H. Morkoc, "Design Characteristics and Millimeter Wave Performance of $0.25\mu\text{m}$ Gate Length MODFETs," *Proc. of Int. Symp. on Electron Devices, Circuits, and Systems*, Dec. 16-18, 1987, Karayhpur, India.
439. V. Iyenger, S.T. Fu, S.M. Liu, M.B. Das, C.K. Peng, J.F. Klem, T. Henderson, and H. Morkoc, "Low Temperature Current Drift and its origin in Heterostructure and Quantum Well MODFETs," *Proc. of GaAs and Related Compounds Symp.*, Sept. 29 - Oct. 1, 1987, Crete, Greece.
440. G. Ji, T. Henderson, C.K. Peng and H. Morkoc, "Band Structure Determination of Modulation Doped Multiquantum Well Heterostructures" *J. Appl. Phys.*, pending.
441. N. Lucas, H. Zabel, H. Morkoc, and H. Ünlü, "Anisotropy of Thermal Expansion of GaAs on Si(001)", *Appl. Phys. Lett.*, Vol. 52, pp. 2117-2119, (1988).
442. T. Won, C.W. Litton, H. Morkoc and A. Yariv, "A High Gain GaAs/AlGaAs NpN Heterojunction Bipolar Transistor on (100) Si Grown by Molecular Beam Epitaxy," *IEEE Electron Device Lett.*, Vol. EDL-9, pp.405-407, (1988).
443. T. Won, C.W. Litton, H. Morkoc and A. Yariv, "GaAs/AlGaAs Heteronjunction Pnp Bipolar Transistors Grown on (100) Si by Molecular Beam Epitaxy," *Electronic Letters*, Vol. 24(10), pp. 588-590, (1988).
444. S. Kalem, J. Chyi, C.W. Litton, H. Morkoc, S.C. Kan and A. Yariv, "Electrical Properties of InAs Epilayers grown by Molecular Beam Epitaxy on Si Substrates," *Appl. Phys. Lett.*, Vol. 53, pp. 562-564, 1988
445. V.V. Gridin, R. Beserman and H. Morkoc, "The Energy Dependence of the Electron Phonon Coupling in a Thin Layer GaAs/AlAs Superlattice", *Phys. Rev. B.*, May 15, 1988.

446. M.R. Junnarkar, K. Shum, H.S. Chao, K.S. Wong, R.R. Alfano, H. Ünlü and H. Morkoc, "Dynamics of HOT Carriers and Phonons in GaAs Quantum Well", Proc. of SPIE Ultrafast Laser Probe Phenomena in Bulk and Microstructure Semiconductors, March 14-15, 1988, Newport Beach, CA.
447. K.T. Tsen, S.C.Y. Tsen and H. Morkoc, "Time -resolved Raman studies in GaAs/ $\text{Al}_x\text{Ga}_{1-x}\text{As}$ Multiple quantum well structures", Proc. of SPIE Ultrafast Laser Probe Phenomena in Bulk and Microstructure Semiconductors, March 14-15, 1988, Newport Beach, CA.
448. Zhang Shu Lin, T.A. Gant, M. Delaney, M.V. Klein, J. Klem and H. Morkoc, "Resonant Behavior of GaAs LO Phonons in a GaAs-AlAs Superlattice", *Chinese Phys. Lett.*, Vol. 5, No. (3), pp. 113-116, (1988).
449. S. Agarwala, M.B. Patil, C.K. Peng and H. Morkoc, " $\text{Al}_{0.3}\text{Ga}_{0.7}\text{As}/\text{GaAs}$ MIS-type Field-effect Transistor Fabricated on InP Substrates", *Appl. Phys. Lett.*, Vol. 53, pp. 493-494, 1988.
450. C.K. Peng, G. Ji, N.S. Kumar and H. Morkoc, "Extremely Low Resistance Non alloyed Ohmic Contacts on GaAs Using InAs/InGaAs and InAs/GaAs Strained Layer Superlattices", *Appl. Phys. Lett.*, Vol. 53, pp. 900-901, 1988.
451. T. Won, S. Agarwala, and H. Morkoc, "An $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ Heterojunction Bipolar Transistor on GaAs by Molecular Beam Epitaxy", *Appl. Phys. Lett.*, in print.
452. S. Kalem, J. Chyi, H. Morkoc, R. Bean and K. Zanio, "Growth and Transport Properties of InAs Epilayers on GaAs", *Appl. Phys. Lett.*, Vol. 53, pp. 1647, (1988).
453. L.M. Smith, D.R. Wake, J.P. Wolfe, D. Levi, M.V. Klein, J. Klem, T. Henderson and H. Morkoc, "Picosecond Imaging of Photoexcited Carriers in Quantum Wells-Anomalous Lateral Confinement at High Densities", *Phys. Rev. Lett.*, Vol. 54, (8), pp. 5788-5791, 1985.
454. H.S. Chao, K.S. Wong, R.R. Alfano, H. Ünlü and H. Morkoc, "Spin Orientation and Relaxation of Carriers in GaAs/AlGaAs Quantum Wells", Proc. of SPIES, Newport Beach, CA, March 14-18 (1988).
455. K.S. Tsen and H. Morkoc, "Subpicosecond time-resolved Raman spectroscopy of LO phonons in GaAs/ $\text{Al}_x\text{Ga}_{1-x}\text{As}$ multiple quantum well structures", *Phys. Rev. B*, in print.
456. K.T. Tsen, R.P. Joshi, D.K. Ferry and H. Morkoc, "Time-resolved Raman scattering of non-equilibrium LO phonons in GaAs quantum wells", *Phys. Rev. B Rapid Communications*, Vol. 39(2), pp. 1446-1449, (1988).
457. M.B. Patil, S. Agarwala, and H. Morkoc, "Back-gated Field-Effect in a Double Heterostructure Modulation Doped Field-Effect Transistor", *Electronic Letters*, Vol. 24, pp. 925-926, (1988).
458. L.M. Smith, J.S. Preston, J.P. Wolfe, D.R. Wake, J. Klem, T. Henderson and H. Morkoc, "Phonon-wind-driven Transport of Photoexcited Carriers in a Semiconductor Quantum Well", *Phys. Rev. B*, Vol. 40, pp. 1155-1158, (1989).

459. T.A. Gant, M. Delaney, M.V. Klein, R. Houdré and H. Morkoc, "Resonant Raman Studies of Confined LO Modes and interface Modes in a Small Period GaAs/AlAs Superlattice", *Phys. Rev. B*, submitted.
460. C.K. Peng, J. Chen, and H. Morkoc, "Contact Regrowth (CORE) Technique for Low Resistance Non-alloyed Contacts to the Hot Electron Transistor", *Appl. Phys. Lett.*, Vol. 53, pp. 1738-1740, (1988).
461. J.I. Chyi, S. Kalem, N.S. Kumar, C.W. Litton and H. Morkoc, "Growth of InSb and InAs_{1-x}Sb_x on GaAs by Molecular Beam Epitaxy", *Appl. Phys. Lett.*, Vol. 53, pp. 1092-1094, 1988.
462. G. Radhakrishnan, J. Liu, F. Grunthaner, K. Katz, H. Morkoc and J. Mazur, "Growth of (111) GaAs on (111) Si Using Molecular Beam Epitaxy", *J. Appl. Phys.*, (1988).
463. S.J. Bailey, A.R. Preston, J.W. Steeds and H. Morkoc, "Analytical Electron Beam Microscopy study of Stacking Fault Pyramids in Multiple Quantum Wells", *Proc. of 7th Int. Conf. on* Sept., 1987.
464. W. Dobbelaere, D. Huang, S. Kalem and H. Morkoc, "InGaAs/GaAs Multiple Quantum Well Reflection Modulators", *Electron. Lett.*, Vol. 24, p. 1239, (1988).
465. M.B. Patil, S. Kalem and H. Morkoc, "Reduced Back Gating Effect in Modulation Doped Field Effect Transistors by p-n junction Isolation", *Appl. Phys. Lett.*, Vol. 53, pp. 2417, (1988).
466. T. Won, S. Agarwala, C.K. Peng and H. Morkoc, "Self Aligned In_{0.52}Al_{0.48}As/In_{0.53}Ga_{0.47}As Heterojunction Bipolar Transistors with Graded Interfaces on Semi Insulating InP Grown by Molecular Beam Epitaxy", *IEEE Electron. Dev. Lett.*, in print.
467. H. Morkoc, "Electronic and Optical Devices with Gallium Arsenide on Silicon Prepared by MBE", *Proc. 5th Int. MBE Symp.*, *J. Crystal Growth*, (1989)
468. R.D. Groeber, H.O. Drew, J.I. Chyi, S. Kalem and H. Morkoc, "Infrared Photoluminescence of InP Epilayers Grown on GaAs and Si Substrates", *J. Appl. Phys.*, in print.
469. T. Won and H. Morkoc, "Heterojunction Bipolar Transistors (HBTs) for Millimeter Wave and Optoelectronic Applications", *Proc. of IEEE Princeton Section*, Sept. 29, (1988).
470. T. Won and H. Morkoc, "High Speed Performance of Si/Si_{1-x}Ge_x Heterojunction Bipolar Transistors", *IEEE Electron. Dev. Lett.*, Vol. EDL-10, pp. 33-35, (1988), print.
471. D. Biswas, J.I. Chyi, H. Morkoc, S. DiVita and K. Kordas, "Growth and Characterization of GaAs on Sapphire by Molecular Beam Epitaxy", *SPIE*, San Diego, CA, Aug. 15-19 (1988).
472. K.T. Tsen, O.F. Jankey, G. Hallaway, S.C.Y. Tsen and H. Morkoc, "Transport of Photoexcited Electron Hole Plasma in GaAs Quantum Wells", *Phys. Rev. B*, *Rapid Comm.*, pending.

473. F. Xiong, T.A. Tombrello, H. Wang, T.R. Chen, H. Morkoc and A. Yariv, "High Efficiency Single Quantum Well RIN-SCH Lasers Fabricated with MeV Oxygen Implantation", *Appl. Phys. Lett.*, pending.
474. C. Kieley, J.I. Chyi, A. Rockett and H. Morkoc, "On the Microstructure and Interfacial Structure of InSb Layers Grown on GaAs (100) by Molecular Beam Epitaxy", *Philosophical Magazine*, in print.
475. N. Otsuka, Y. Ihm, Y. Hirotsu, R. Venkatasubramanian, J. Klem, and H. Morkoc, "Atomic Ordering in $\text{GaAs}_{0.5}\text{Sb}_{0.5}$ Grown by MBE", Proc. 5th Int MBE Symp., Aug. 28 - Sept. 1, 1988, *J. Crystal Growth*, (1989).
476. D. Mui, M. Patil, J. Chen, N.S. Kumar and H. Morkoc, "Calculation of the I-V Characteristics of Direct Tunneling Diodes", *J. Appl. Phys.*, pending.
477. M.W. Peterson, J.A. Turner, C.A. Parsons, A.J. Npzik, D.J. Arent, C. Van Hoof, G. Borghs, R. Houdré and H. Morkoc, "Strong Miniband Dispersion in GaAs/AlGaAs Superlattices with Very Thin Barrier Layers", *Appl. Phys. Lett.*, pending.
478. J.I. Chyi, D. Biswas, S.V. Iyer, N.S. Kumar, H. Morkoc, R. Bean, K. Zanio, R. Grober and D. Drew, "MBE Growth and Characterization of InSb on Si", Presented at 9th MBE Workshop, Purdue University, Sept. 21-23, 1988. *Jour. of Vac. Sci & Techn.*, in print.
479. T. Won, S. Agarwala and H. Morkoc, "An $\text{In}_{0.52}\text{Al}_{0.48}\text{As}/\text{In}_{0.53}\text{Ga}_{0.47}\text{As}$ heterojunction bipolar transistor on GaAs substrate by molecular beam epitaxy", Presented at 9th MBE Workshop, Purdue University, Sept. 21-23, 1988. *Jour. of Vac. Sci & Techn.*, in print.
480. C.J. Kiely, J.I. Chyi, A. Rockett and H. Morkoc, "High Resolution Electron Microscopy Studies of MBE Grown InSb Layers on GaAs (001)", Presented at 1988 Fall Meeting of Materials Research Society, Boston, MA, Nov. 28-Dec. 3, 1988. To be published in MRS Bulletin.
481. T.A. Tombrello, H. Wang, T.R. Chen, H. Morkoc and A. Yariv, "Fabrication of GaAs/AlGaAs Quantum Well Lasers with MeV Oxygen Ion Implantation", Presented at 1988 Fall Meeting of Materials Research Society, Boston, MA, Nov. 28-Dec. 3, 1988. To be published in MRS Bulletin.
482. K. Shum, M.R. Junnarkar, H.S. Chao, R.R. Alfano, and H. Morkoc, "Non-equilibrium Phonon Effects on the Time Dependent Relaxation of Hot Carriers in GaAs MQW," *Solid State Electronics*, Vol. 31, pp. 451-454, (1988).
483. B.H. Bairamov, R.A. Evarestov, I.P. Ipatova, Yu E. Kitaev, A.Yu. Maslov, M. Delaney, T.A. Gant, M.V. Klein, D. Levi, J. Klem, and H. Morkoc, "Inelastic Light Scattering in GaAs/AlAs Superlattices," 4th International Conference on Superlattices, Microstructures and Microdevices, Trieste, Italy, Aug. 8-12, 1988. To be published in *Superlattice and Microstructures*.
484. V.V. Gridin, R. Berserman, and H. Morkoc, "The Tunneling of Electron-Hole Pairs in a Raman Scattering Study of a Thin Layer GaAs/AlAs Superlattice," *Solid State Commun.*, Vol. 67, No. 3, pp. 317-319, 1988.

485. M.B. Patil, S.N. Mohammad, and H. Morkoc. "Modeling of Ion-Implanted Field-Effect Transistors." Submitted to *Transactions on Electron Devices*.
486. D. Huang, D. Mui and H. Morkoc, "Interference effects probed by photoreflectance spectroscopy." Submitted to *Appl. Phys. Lett.*
487. M.E. Hoenk, H.Z. Chen, A. Yariv, H. Morkoc and K.J. Vahala. "Cathodoluminescence measurement of an orientation dependent aluminum concentration in $\text{Al}_x\text{Ga}_{1-x}\text{As}$ epilayers grown by molecular beam epitaxy on a nonplanar substrate." submitted to *Appl. Phys. Lett.*
488. P.W. Yu, C.K. Peng and H. Morkoc. "Quasi-Donor-Acceptor Pair Photoluminescence Emission in $\text{Ga}_x\text{In}_{1-x}\text{As}/\text{InP}$," submitted to *Appl. Phys. Lett.*
489. V.V. Gridin, R. Beserman and H. Morkoc. "Correspondence Between the Dependence of Frequencies and Intensities of GaAs and AlAs Longitudinal Optical Modes on the Photon Energy in a Thin Layer GaAs/AlAs Superlattice", *Phys. Rev. B*, Vol. , pp. , (1989).
490. I. Sela, R. Beserman and H. Morkoc, Resonance Raman Scattering Induced Interface Roughness in a Short Period GaAs/AlGaAs Superlattice," *Phys. Rev. B*, Vol. , pp. , (1989).
491. S. Agarwala, T. Won and H. Morkoc. "AlGaAs/GaAs Single Heterojunction Bipolar Transistors Grown on InP by Molecular Beam Epitaxy", *Appl. Phys. Lett.*, in print.
492. M.B. Patil, S.N. Mohammad and H. Morkoc, "Modeling of Field Effect Transistors with Laterally Graded Doping," *Solid State Electronics*, pending.
493. S.N. Mohammad, M.B. Patil and H. Morkoc. "Heavy Doping for Improved Short Channel Operation of GaAs MESFETs," *Electronic Letts.*, pending.
494. S.N. Mohammad, M.B. Patil, J.J. Chen, J.I. Chyi, M.S. Ünlü, G.B. Gao and H. Morkoc. "Analytical Model for I-V Characteristics of Ion Implanted MESFETs," *IEEE Electron Dev.*, pending.
495. S.N. Mohammad, M.B. Patil, J.J. Chen, M.S. Ünlü and H. Morkoc. "Analytical Model for I-V Characteristics of JFETs with Heavily Doped Channels," *Solid State Electronics*, pending.
496. J.I. Chyi, D. Biswas, S.V. Iyer, N.S. Kumar, H. Morkoc, R. Bean, K. Zanio, H.Y. Lee and H. Chen, "Molecular Beam Epitaxial Growth and Characterization of InSb on Si," *Appl. Phys. Lett.*, in print.
497. S.J. Ou, S.C.Y. Tsen, K.T. Tsen, J.M. Cowley, J.I. Chyi, A. Salvador and H. Morkoc. "Determination of the Local Al Conceration in $\text{Al}_x\text{Ga}_{1-x}\text{As}/\text{GaAs}$ Quantum Well Structures using (200) Diffraction Insenity Obtained with a $10\text{\AA}$ Electron Beam," *Appl. Phys. Lett.*, pending.
498. H. Zabel, N. Lucas, H. Morkoc and C.J. Sparks. "X-Ray Characterization of Heteroeptaxial GaAs on Si (001)," Proc. of 174th J. Electrochemical Society, Oct. 9-14, 1988, Chicago, IL

499. S.N. Kumar, J.I. Chyi, C.K. Peng and H. Morkoc. "A GaAs Metal Semiconductor Field Effect Transistor with Extremely Low resistance Non-Alloyed Ohmic Contacts Using an InAs/GaAs Superlattice." *Appl. Phys. Lett.*, pending.
500. J. Chen, G.B. Gao, J.I. Chyi and H. Morkoc. "Breakdown Behavior of GaAs/AlGaAs HBTs." *IEEE Trans. on Electron Dev.*, pending.
501. S.N. Mohammad, M.S. Ünlü and H. Morkoc. "Analytical Treatment of MODFET Heterojunction in GaAs/AlGaAs System." *IEEE Electron Dev.*, pending.
502. Kai Shum, K.S. Wong, H.S. Chao, R.R. Alfano, S. Iyer and H. Morkoc. "Picosecond Dynamics of Exciton Dissociation by Ionized Carbon Acceptors in GaAs Quantum Wells." *Phys. Rev. B*, pending.

68. W.M. Thies, P.W. Yu, D.C. Reynolds, K.K. Bajaj, G. Peters, C. Leak, and H. Morkoc. "correlation Between the Light- and Heavy-Hole Free Exciton Fine Structure in $\text{Al}_x\text{Ga}_{1-x}\text{As-GaAs}$ Multi-Quantum Wells Using Photoluminescence Excitation Spectroscopy." *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
69. T.A. Gant, M. Delaney, S.L. Zhang, M.V. Klein, J. Klem, and H. Morkoc. "Bleaching" of Peaks in the LO phonon Resonance Raman Profile of GaAs-AlAs Superlattice". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
70. A.L. Kotz, T.N. Krabach, S. Kong, M.V. Klein, and H. Morkoc. "Brillouin Scattering from (AlGa)As Alloys and GaAs-(AlGa)As Superlattices". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
71. K.T. Tsen and H. Morkoc. "Determination of population time of the Lo phonons propagating along the layers of $\text{GaAs-al}_x\text{Ga}_{1-x}$ as multiple quantum well structures". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
72. N. Lucas, H. Zabel, and H. Morkoc. "Thermal Expansion of Epitaxial GaAs on Si (100)". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
73. Y.E. Ihm, N. Otsuka, Y. Hirotsu, J. Klem, and H. Morkoc. "Ordering in $\text{GaAs}_{1-x}\text{Sb}_x$ Grown by Molecular Beam Epitaxy". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
74. D. Levi, D.R. Wake, M.V. Klein, J. Klem, and H. Morkoc. "Time-resolved Raman-scattering investigation of upper-subband population relaxation rates in optically excited multiple quantum wells". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
75. D. Huang, J. Chyi, S. Kalem, and H. Morkoc. "Excitonic Absorption in P-type Modulation Doped GaAs Quantum Wells". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
76. Y.S. Yoon, P.S. Jung, J.J. Song, J.N. Schulman, C.W. Tu, and H. Morkoc. "Observation of Saddle-point Excitonic Effects in $\text{GaAs/Al}_x\text{Ga}_{1-x}\text{As}$ Superlattice". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
77. K.T. Tsen, G. Halama, and H. Morkoc. "Picosecond time-resolved Raman studies of plasma expansion in GaAs quantum wells". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
78. G. Ji, W. Dobbelaere, D. Huang, and H. Morkoc. "Optical Transitions Involving Unconfined Energy States in InGaAs/GaAs Multiple Quantum Wells". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA
79. L.M. Smith, D.R. Wake, H. Morkoc, D. Levi, M.V. Klein, and J.P. Wolfe. "Transport of Photoexcited Carriers in a Multiple Quantum Well: Anomalous Lateral Confinement at High Densities". *Meeting of the American Physical Society*, March 21-25, 1988, New Orleans, LA

80. J. Paslaski, H.Z. Chen, H. Morkoc and A. Yariv, "High Speed GaAs/Si "Pin Detectors"", *IEEE/OSA, CLEO Meeting*, April 28, 1988, Anaheim, CA
81. C.K. Peng, T. Won, J. Chen, C.W. Litton and H. Morkoc, "High Gain N-p-n and P-n-p InGaAs/InAlAs Double Heterojunction Bipolar Transistors with InAs Cap Layers by Molecular Beam Epitaxy," 46th Annual Device research Conf., June 20-22, 1988, Boulder, CO, and *IEEE Trans. on Electron Dev.*, Vol. ED-35, pp. 2445-2446, (1988).
82. J.I. Chyi, S. Kalem, C.W. Litton and H. Morkoc, "MBE Growth and Characterization of InSb and InAs_{1-x}Sb_x Grown on GaAs", Electronic Materials Conference, June 22-24, 1988, Boulder, CO
83. H. Zabel, N. Lucas and H. Morkoc, "X-Ray Characterization of Heteroepitaxial GaAs on Si(001)", *Electrochemical Society Meeting*, Oct. 9-14, 1988, Chicago, IL