

REPORT NO. NADC-88102-60



ANALYSIS OF THE NAVAIRDEVCON SELF-PRIMING TOPCOAT ON GRAPHITE/EPOXY COMPOSITES

Anthony T. Eng

Air Vehicle and Crew Systems Technology Directorate
Naval Air Development Center
Warminster, PA 18974-5000

15 AUGUST 1988

Final Report
PROJECT NO. R534A52
Work Unit ZM540

Approved for public release. Distribution is unlimited.

Prepared for
NAVY EXPLORATORY DEVELOPMENT PROGRAM
Airborne Materials
(NA2A)
Naval Air Development Center
Warminster, PA 18974-5000

DTIC
ELECTE
S 13 MAR 1989 **D**
α
E

AD-A205 961

NOTICES

REPORT NUMBERING SYSTEM - The numbering of technical project reports issued by the Naval Air Development Center is arranged for specific identification purposes. Each number consists of the Center acronym, the calendar year in which the number was assigned, the sequence number of the report within the specific calendar year, and the official 2-digit correspondence code of the Command Office or the Functional Department responsible for the report. For example: Report No. NADC-86015-70 indicates the fifteenth Center report for the year 1986 and prepared by the Systems and Software Technology Department. The numerical codes are as follows:

CODE	OFFICE OR DEPARTMENT
00	Commander, Naval Air Development Center
01	Technical Director, Naval Air Development Center
02	Comptroller
05	Computer Department
07	Planning Assessment Resources Department
10	Anti-Submarine Warfare Systems Department
20	Tactical Air Systems Department
30	Warfare Systems Analysis Department
40	Communication & Navigation Technology Department
50	Mission Avionics Technology Department
60	Air Vehicle & Crew Systems Technology Department
70	Systems & Software Technology Department
80	Engineering Support Group

PRODUCT ENDORSEMENT - The discussion or instructions concerning commercial products herein do not constitute an endorsement by the Government nor do they convey or imply the license or right to use such products.

APPROVED BY:

W. F. Moroney

DATE:

Oct 3, 1988

W. F. MORONEY
CAPT, MSC, U.S. NAVY

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE				Form Approved OMB No 0704-0188	
1a REPORT SECURITY CLASSIFICATION Unclassified			1b RESTRICTIVE MARKINGS		
2a SECURITY CLASSIFICATION AUTHORITY			3 DISTRIBUTION AVAILABILITY OF REPORT Approved for public release. Distribution is unlimited.		
2b DECLASSIFICATION/DOWNGRADING SCHEDULE					
4 PERFORMING ORGANIZATION REPORT NUMBER(S) NADC-88102-60			5 MONITORING ORGANIZATION REPORT NUMBER(S)		
6a NAME OF PERFORMING ORGANIZATION Naval Air Development Center		6b OFFICE SYMBOL (If applicable) 6062		7a NAME OF MONITORING ORGANIZATION	
6c ADDRESS (City, State, and ZIP Code) Warminster, PA 18974-5000		7b ADDRESS (City, State, and ZIP Code)			
8a NAME OF FUNDING/SPONSORING ORGANIZATION Navy Exploratory Development Program		8b OFFICE SYMBOL (If applicable) NA2A		9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8c ADDRESS (City, State, and ZIP Code) Naval Air Development Center Warminster, PA 18974-5000		10 SOURCE OF FUNDING NUMBERS			
		PROGRAM ELEMENT NO 62234N		PROJECT NO R534A52	TASK NO ZM540
11 TITLE (Include Security Classification). Analysis Of The NAVAIRDEVGEN Self-Priming Topcoat on Graphite/Epoxy Composites					
12 PERSONAL AUTHOR(S) Eng. Anthony T.					
13a TYPE OF REPORT Final		13b TIME COVERED FROM Oct 86 TO Sep 87		14 DATE OF REPORT (Year, Month, Day) 1988, August, 15	
15 PAGE COUNT					
16 SUPPLEMENTARY NOTATION					
17 COSAT CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP	Self-Priming Topcoat Graphite/Epoxy		
11	03				
19 ABSTRACT (Continue on reverse if necessary and identify by block number)					
The standard coating system for Navy aircraft consists of an epoxy-polymade primer (MIL-P-23377) under a polyurethane topcoat (MIL-C-83286). In September of 1986, the Naval Air Development Center developed a self-priming topcoat (single coating) to replace the standard Navy aircraft coating system. Equivalent or superior paint properties were achieved with potential material and labor savings. This self-priming topcoat was developed for use on aluminum-skinned aircraft. Since the amount of polymeric composite components used on naval aircraft is rapidly increasing, the current effort was undertaken to determine the compatibility of the self-priming topcoat with graphite/epoxy composite substrates.					
20 DISTRIBUTION AVAILABILITY OF ABSTRACT ☐ UNCLASSIFIED UNLIMITED ☐ SAME AS RPT ☐ DTIC USERS			21 ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a NAME OF RESPONSIBLE INDIVIDUAL Anthony T. Eng			22b TELEPHONE (Include Area Code) (215) 441-3269		22c OFFICE NAME

NADC-88102-60

TABLE OF CONTENTS

	Page #
LIST OF ILLUSTRATIONS	ii
INTRODUCTION	1
EXPERIMENTAL	
MATERIALS	1
PROCEDURES	1
RESULTS AND DISCUSSION	2
CONCLUSIONS AND RECOMMENDATIONS	3
REFERENCES	4

Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	



NADC-88102-60

LIST OF ILLUSTRATIONS

	Page #
Table I: Composition Of Lusterless White Self-Priming Topcoat	5
Table II: X-Cut (Method A) Adhesion Rating	6
Table III: Cross-Hatch (Method B) Adhesion Rating	7
Table IV: Summary Of Results On Gr/Ep	8
Figure1: X-Cut Adhesion Test On Coated Gr/Ep Substrates	9

INTRODUCTION

The standard paint system for naval aircraft consists of a polyurethane topcoat (MIL-C-83286 or MIL-C-85285) over a epoxy-polyamide primer (MIL-P-23377 or MIL-P-85582). Occasionally, a polysulfide sealant (MIL-S-8802 or MIL-S-81733) is applied between the primer and the topcoat to increase the flexibility of this coating system in highly stressed areas such as fastener patterns. The topcoat provides the weather, abrasion, and fluid resistance, and the optical properties such as color, opacity, and gloss. The primer, which currently contains carcinogenic pigments (chromates), acts as a corrosion inhibitor and an adhesion promoter.

In September of 1986, the Naval Air Development Center developed a single coating system to replace the standard two or three coating systems described above. In effect, a self-priming topcoat (SPTC) was produced (1). Equivalent or superior paint properties were achieved with potential weight, material, and labor savings. This SPTC was developed for use on aluminum-skinned aircraft. Since the amount of graphite fiber reinforced epoxy (Gr/Ep) composite components used on Navy aircraft is rapidly increasing, the current effort was undertaken to determine the compatibility of the SPTC with Gr/Ep composite substrates.

EXPERIMENTAL

MATERIALS

The materials analyzed in this effort were the SPTC and the control coating system (MIL-P-23377/MIL-C-83286) on Gr/Ep substrates. The SPTC consisted of a two component aliphatic polyurethane resin with a non-lead, non-chromate pigment system (Table I). Specifically, the resin components are a polyester diol reacted with a hexamethylene diisocyanate. The pigment system consisted of titanium dioxide vesticulated beads (2), titanium dioxide, a proprietary organo-zinc complex, zinc molybdate, and zinc phosphate. The titanium dioxide vesticulated beads and the titanium dioxide impart the opacity and color to the SPTC while the three other pigments mainly provide corrosion inhibition but also contribute to the opacity and color. The solvent system, excluding the solvents in the resin system, consisted solely of 1,1,1-trichloroethane which is currently classified as a volatile organic compound (VOC) exempt solvent.

The control coating system consisted of an epoxy-polyamide primer (MIL-P-23377 type I) under an aliphatic polyurethane topcoat (MIL-C-83286). The primer used in this analysis contained approximately 27% strontium chromate by weight in the dry film.

The substrate material consisted of the Hercules AS/3501-6 graphite fiber/epoxy matrix composite system.

PROCEDURES

Application

The surfaces of the Gr/Ep substrates were prepared by gently wiping using non-oil extractable wipes moistened with reagent grade methyl ethyl ketone. The coating were applied using conventional air spray equipment at the desired coating thicknesses: 0.6 mils (15.4 micron) to 0.9 mils (22.86 micron) for MIL-P-23377, and 1.7 mils (43.18 micron) to 2.3 mils (58.42 micron) for both MIL-C-83286 and the SPTC. The coatings were allowed to cure for one week at ambient laboratory conditions prior to testing.

NADC-88102-60

The two coating system were analyzed based on adhesion, fluid immersion, and accelerated environmental exposure properties. In the tests involving fluid and/or environmental acrylic lacquer to prevent moisture diffusion through the composite specimen to the coating/substrate interface. Also, the perimeter of the coated test panels were sealed with wax to prevent edge effects.

Adhesion

The X-cut tape and the cross-hatch tape tests (ASTM D3359, Methods A and B) were used to analyze the adhesion of the coatings to the Gr/Ep substrates (three trials per coating per test). Wet tape adhesion tests (Fed. Test Method Std. 141C, Method 6301.2) were also conducted in which the coated substrates were first subjected to 24 hours static immersion in distilled water at room temperature ($75 \pm 5^\circ\text{F}$) before using X-cut and cross-hatch test procedures. Accelerated wet tape adhesion tests were performed in which the temperature was $120 \pm 5^\circ\text{F}$ at 4 and 10 days. The dry and wet tape tests were evaluated using the classifications listed in ASTM D3359 (Tables II & III).

Fluid Immersion

The coated Gr/Ep specimens (two trials per coating per test) were exposed to a variety of fluids, at various temperatures and durations: hydraulic fluid (MIL-H-83282) at $150 \pm 5^\circ\text{F}$ for 1 day, lubricating oil (MIL-L-23699) at $250 \pm 5^\circ\text{F}$ for 1 day, jet fuel at $75 \pm 5^\circ\text{F}$ for 14 days, distilled water at $75 \pm 5^\circ\text{F}$ for 4 and 10 days. After the specimens were subjected to the appropriate test conditions, the coatings were examined for softening, blistering, uplifting or any other defects.

Accelerated Environmental Exposure

Accelerated weathering, 95% relative humidity, and 5% NaCl salt fog tests were used to determine coating/substrate resistance to these accelerated environmental conditions. In all three tests (2 trials per coating per test), to the coating were examined for blistering, uplifting, or any other coating delamination defect after being subjected to the designated test conditions. For 500 and 1000 hr xenon-arc accelerated weathering (ASTM G26), the test specimens were subjected to a constant 6000 watt light source with a water spray being introduced the last 18 minutes of every two hours. Other cabinet conditions include a black body temperature of $140 \pm 5^\circ\text{F}$, a relative humidity of $50 \pm 5\%$, and a Xe-arc intensity of 0.3 to 0.4 watt/sq. meter at 340 nm wavelength. For humidity resistance (ASTM B117), the specimens were subjected to 95% relative humidity at $120 \pm 2^\circ\text{F}$ for 30 days. For 2000 hr salt fog resistance (ASTM B117), the test specimens were subjected to a 5% NaCl salt fog at an orientation of 15 degrees from vertical and examined every 500 hours for coating defects and also for delamination by tape test.

RESULTS AND DISCUSSION

The objective of the current effort was to determine the compatibility of the SPTC with Gr/Ep composite substrates. The SPTC was analyzed and comparatively rated against the standard Navy coating system on Gr/Ep substrates based on three main properties: adhesion, fluid immersion resistance, and accelerated environmental resistance. Due to the inherent structural properties of Gr/Ep composites, several common physical tests were not conducted. For example, impact resistance (toughness), impact flexibility, and mandril bend flexibility tests could not be performed due to the rigidity of the Gr/Ep panels. The common corrosion resistance tests (5% NaCl salt fog, SO₂/NaCl salt fog, and filiform) do not yield substrate corrosion data since polymers degrade rather than corrode. However, the SPTC has been analyzed for flexibility and corrosion protection on aluminum (1). A summary of the test results for the coatings on Gr/Ep substrates is provided in Table IV.

NADC-88102-60

Adhesion can be defined (as in ASTM D907) as 'the state in which two surfaces are held together by interfacial forces which consist of valence forces or interlocking forces, or both.' The force of removal can be determined by using the X-cut and cross-hatch which combine two mechanisms of removal: scraping and peeling. These two tests showed that the control coating and SPTC both possess good substrate/coating adhesion to Gr/Ep. Both coatings passed the dry and wet tape adhesion tests at the standard and accelerated conditions. The values obtained were 4A by the X-cut method and 4B by the cross-hatch method. Small areas at the fringe of the incision were removed, causing the rating to be slightly less than perfect but still passing (Figure 1).

The solutions used in the fluid immersion tests are indicative of common Navy aircraft operational fluids that may come in contact with coated Gr/Ep substrates. In an earlier study, these solutions were determined to be non-deleterious (with respect to tensile strength) to bare Gr/Ep substrates immersed for over two months at approximately 212°F (3). Also, the SPTC on aluminum was found to be resistant to these fluids at conditions identical to the current study (1). Thus the current fluid immersion tests actually indicate the permeability (or the non-permeability) of the coating to these fluids. These exposures also further test adhesion since the permeability of these fluids in these coatings may affect the coating/substrate interface. Other than some discoloration, the control coating and the SPTC were not affected by the test fluids. They showed good barrier resistance (no softening) and good adhesion (no blistering or any other coating delamination).

The xenon-arc accelerated weathering, 95% humidity, and 5% NaCl salt fog resistance tests are designed to simulate environmental conditions but at highly accelerated rates. Since Gr/Ep substrates produce no corrosion products in these environments, these tests are actually being used to determine the resistance of the coating to degradation, permeability, and its related adhesion properties. The SPTC and the control coating system showed no signs of blistering, uplifting, or any other type of coating delamination after exposure to these test conditions. Tape adhesion testing, performed on the specimens exposed to salt fog, produced no removal of the coatings.

CONCLUSIONS AND RECOMMENDATIONS

The SPTC performed as well as the control coating (MIL-P-22337/MIL-C-83286) on Gr/Ep substrates in controlled laboratory tests. After the anticipated successful completion of fleet testing (currently on Gr/Ep panels on one F-14 and three H-3's), this coating can be effectively transitioned into the fleet for use on Gr/Ep components on Navy aircraft.

It is recommended that an optimized self-priming topcoat with primary and/or barrier pigments alone be developed for use on Gr/Ep or other non-metal substrates at a future date. Since, corrosion inhibitive pigments (in general) are heavier and more expensive than barrier pigments, a reduction in coating weight and raw materials expense can be achieved. Also, a study of the disbondment characteristics of organic coatings on polymeric substrates would be beneficial to future coatings development.

NADC-88102-60

REFERENCES

1. C.R. Hegedus, 'Development of a Primer/Topcoat and Flexible Primer For Aluminum,' NADC-87016-60, Warminster, PA, March 1987.
2. C.R. Hegedus and P.G. Prale, 'The Effect of Pigmented Polymer Beads on Contrast Ratio,' NADC-85036-60, Warminster, PA, April 1985.
3. K.G. Clark, 'Compatibility of Aircraft Operational Fluids With a Graphite/Epoxy Composite-Development of an Exterior Coating System and Remover,' NADC-80046-60, Warminster, PA, June 1980.

NADC-88102-60

Table I: Composition Of Lusterless White Self-Priming Topcoat

<u>Component A</u>	<u>Formulation Wt%</u>
X3009-A (Coatings For Industry)	37.6
Titanium Dioxide (DuPont)	1.1
Titanium Dioxide Vesticulated Beads (Enterprise)	0.4
Zinc Molybdate (Sherwin Williams)	29.9
Zinc Phosphate (Mineral Pigments)	17.0
Sicorin RZ, an organo-zinc complex (BASF)	1.7
Anti-Terra-204 (Byk Chemie)	<u>0.5</u>
Sub-Total	88.2
<u>Component B</u>	
X3009-B (Coatings For Industry)	<u>11.8</u>
Total	100.0

NADC-88102-60

Table II: X-Cut (Method A) Adhesion Rating

<u>Rating</u>	<u>Description</u>
5A	No peeling or removal
4A	Trace peeling or removal along incisions.
3A	Jagged removal along incisions up to 1/16 inch (1.6 mm) on either side.
2A	Jagged removal along most of incisions up to 1/8 inch (3.2 mm) on either side.
1A	Removal from most of the area of the X under the tape.
0A	Removal beyond the area of the X.

NADC-88102-60

Table III: Cross-Hatch (Method B) Adhesion Rating

<u>Rating</u>	<u>Description</u>
5B	The edge of the cuts are completely smooth; none of the squares of the lattice is detached.
4B	Small flakes of the coating are detached at intersections; less than 5% of the area is affected.
3B	Small flakes of the coating are detached along edges and at intersections of cuts. The area affected is 5 to 15% of the lattice.
2B	The coating has flaked along the edges and on parts of the squares. The area affected is 15 to 35% of the lattice.
1B	The coating has flaked along the edges of cuts in large ribbons and whole squares have detached. The area affected is 35 to 65% of the lattice.
0B	Flaking and detachment worse than Rating 1B.



NADC-88102-60

Table IV: Summary Of Results On Gr/Ep

	<u>Test Conditions</u>	<u>MIL-P-23377/ MIL-C-83286</u>	<u>Self-Priming Topcoat</u>
ADHESION			
X-Cut:	Dry, 75°F	4A	4A
	H ₂ O, 75°F, 1 day	4A	4A
	H ₂ O, 120°F, 4 day	4A	4A
	H ₂ O, 120°F, 10 day	4A	4A
Cross-Hatch:	Dry, 75°F	4B	4B
	H ₂ O, 75°F, 1 day	4B	4B
	H ₂ O, 120°F, 4 day	4B	4B
	H ₂ O, 120°F, 10 day	4B	4B
FLUID IMMERSION			
MIL-H-83282:	150°F, 1 day	ND	ND
MIL-L-23699:	250°F, 1 day	ND	ND
JP-5:	75°F, 1 day	ND	ND
H ₂ O:	75°F, 1 day	ND	ND
	120°F, 4 day	ND	ND
	120°F, 10 day	ND	ND
Break Free:	75°F, 14 day	ND	ND
ACCELERATED ENVIRONMENTAL EXPOSURE			
Weatherometer:	Xe-arc, H ₂ O spray, 500 hr	ND	ND
	Xe-arc, H ₂ O spray, 1000hr	ND	ND
Humidity:	95% RH, 120°F, 30 day	ND	ND
Salt Fog:	5% NaCl, 2000 hr, tape adhesion	ND	ND

ND - No coating defects

Figure 1: X-Cut Adhesion Test On Coated Gr/Ep Subs rates



NADC-88102-60

DISTIRBUTION LIST Continued

No of Copies

Wright Aeronautical Laboratories (MLSA)	1
Wright-Patterson AFB, OH 45433-6533	
NAVAIRDEVCEN (80 for 6062, 3 for 8131, 1 for 60C2)	84
Center for Naval Analyses	1
4401 Font Ave.	
P.O. Box 16268	
Alexandria, VA 22303-0268	

NADC-88102-60

DISTIRBUTION LIST Continued

No of Copies

Naval Sea Systems Command (SEA-05M1)	1
Washington, DC 20362	
Office Of Naval Research (431,12)	2
800 N. Quincy St.	
Arlington, VA 22217-5000	
Office Of Naval Technology (ont-255)	1
800 N. Quincy St.	
Arlington, VA 22217-5000	
Pfizer Inc.	1
Attn: D. Towhill	
640 N. 13th St.	
Easton, PA 18042	
Pratt & Lambert	1
Attn: S. Mack	
16116 E. 13th St.	
Wichita, KS 67201	
Rockwell International	1
Attn: L. Streett; Dept. 871	
4300 E. 5th Ave.	
Columbus, OH 43216	
Sherwin Williams	1
Attn: G. Bierwagen	
10909 S. Cottage Grove Ave.	
Chicago, IL 60628	
Sterling Lacquer	1
Attn: G. Halet	
3150 Brannon Ave.	
St. Louis, MO 63139	
Titanine Div.	1
Attn: C. Scatturo	
320 Paterson Plank Rd.	
Carlstadt, NJ 07072	
U.S. Paints	1
Attn: J. Lott	
831 S. 21st St.	
St. Louis, MO 63103	
Warner-Robbins Air Logistics Command (MMEMC, MMTRC)	2
Robbins AFB, GA 31098	

NADC-88102-60

DISTIRBUTION LIST Continued

No of Copies

National Bureau of Standards	1
Attn: M. McKnight	
Washington, DC 20234	
Naval Air Engineering Center (9231)	1
Lakehurst, NJ 08733-5100	
Naval Air Station (AIRLANT-528)	1
Norfolk, VA 23511-5188	
Naval Air Station, North Island (AIRPAC-7412)	1
San Diego, CA 92135-5100	
Naval Air System Command (AIR-4112E, AIR-530D)	2
Washington, DC 20361	
Naval Air Depot (342)	1
Naval Air Station	
Alameda, CA 94501	
Naval Aviation Depot (343)	1
Naval Air Station	
Jacksonville, FL 32212-0016	
Naval Aviation Depot (343)	1
Naval Air Station	
Norfolk, VA 23511-5188	
Naval Aviation Depot (342)	1
Naval Air Station	
Pensacola, FL 32508	
Naval Aviation Depot (34210)	1
Naval Air Station, North Island	
San Diego, CA 92135-5100	
Naval Civil Engineering Laboratory (L52)	1
Port Hueneme, CA 93043	
Naval Facilities Engineering Laboratory (032)	1
200 Stoval St.	
Alexandria, VA 22322-2300	
Naval Research Laboratory (6120, 6123, 6124)	3
4555 Overlook Ave.	
Washington, DC 20375	

NADC-88102-60

DISTIRBUTION LIST Continued

No of Copies

Hughson Chemicals	1
Attn: A. Patterson	
2000 W. Grandview Blvd.	
Erie, PA 16512	
Koppers Inc.	1
Attn: F. Winkleman	
480 Frelinghuysen Ave.	
Newark, NJ 07114	
Lehigh University	1
Attn: H. Leidheiser	
Bethlehem, PA 18015	
Lenmar Inc.	1
Attn: M. Sandler	
150 S. Calverton Rd.	
Baltimore, MD 21223	
Lockheed-GA	1
Attn: B. Bradley	
86 S. Cobb Dr., Dept 72-27	
Marietta, GA 30063	
Marine Corps Air Station (342)	1
Cherry Point, NC 28533-5030	
Martin Marietta Labs	1
Attn: J. Venables	
1450 S. Rolling Rd.	
Baltimore, MD 21227	
McCloskey Varnish Co.	1
Attn: R. Frusco	
7600 State Road	
Phila, PA 19136	
McDonnell Douglas	1
Attn: B. Williams	
St. Louis, MO	
Mobay Chemical	1
Attn: B. Sylvester	
Penn-Lincoln Parkway	
West Pittsburgh, PA 15205	

NADC-88102-60

DISTIRBUTION LIST Continued

No of Copies

David Taylor Naval Ship Research & Development Center	2
(2813, 2841)	
Annapolis, MD 21402-5067	
Defense Technical Information Center	12
Cameron Station	
Alexandria, VA 22314	
Deft Inc.	1
Attn: B. Levine	
17451 Von Karman Ave.	
Irvine, CA 92714	
Desoto Inc.	1
Attn: B. Byrd	
1700 S. Mount Prospect Rd.	
Des Plaines, IL 60018	
Dexter Corp.	1
Attn: B. Harlman	
31500 Hayman St.	
Haywood, CA 94544	
Enterprise Chemical	1
Attn: S. Kish	
1191 S. Wheeling Rd.	
Wheeling, IL 60090	
General Dynamics	1
Attn: J. Peoples	
P.O. Box 748	
Ft. Worth, TX 76101	
General Electric	1
Attn.: P. Lavin	
Silicone Rd.	
Waterford, NY 12188	
Grumman Aerospace Corp.	1
Attn: G. Kelley	
Bethpage, NY 11714	
Hercules Inc., Coatings	1
Attn: R. Wint	
910 Market St.	
Wilmington, DE 19899	

NADC-88102-60

DISTRIBUTION LIST

No of Copies

Advanced Coatings	1
Attn: T. Corboy	
4343 Temple City Blvd.	
Temple City, CA 91780	
 Alox Corp.	 1
Attn: D. Knowlton	
3943 Buffalo Ave.	
Niagara Falls, NY 14302	
 American Cyanamid	 1
Attn: J. Bennett	
Bound Brook, NJ 08805	
 Ameron-Prot. Coat.	 1
Attn: F. Farrell	
201 N. Berry St.	
Brea, CA 92621	
 Army Aviation Systems Command (DRDAV-DS)	 1
4300 Goodfellow Blvd.	
St. Louis, MO 63120-1798	
 Army Belvoir Research & Development Center (STRBE-VO)	 1
Fort Belvoir, VA 22060-5606	
 Army Materials Technology Laboratory (DRXMR-MM)	 1
Watertown, MA 02172	
 BASF-Wyandotte Corp.	 1
Attn: M. Nienhuis	
491 Columbia Ave.	
Holland, MI 49423	
 Boeing Aerospace	 1
Attn: W. Hamilton	
P.O. Box 3999	
Seattle, WA 98124	
 Bostik Div.	 1
Attn: K. Silberger	
20846 S. Normandie Ave.	
Torrance, CA 90502	
 Ciba-Geigy Corp.	 1
Attn: R. Varron	
Ardsley, NY 10502	