

SECURITY CLASSIFICATION OF THIS PAGE

PORT DOCUMENTATION PAGE

AD-A214 701

1b. RESTRICTIVE MARKINGS	
3. DISTRIBUTION/AVAILABILITY OF REPORT Approved for public release; distribution unlimited.	
4. PERFORMING ORGANIZATION REPORT NUMBER(S)	5. MONITORING ORGANIZATION REPORT NUMBER(S) ARO 23400.1-MS
6a. NAME OF PERFORMING ORGANIZATION Cornell University	6b. OFFICE SYMBOL (if applicable)
7a. NAME OF MONITORING ORGANIZATION U. S. Army Research Office	
6c. ADDRESS (City, State, and ZIP Code) Ithaca, NY 24853	7b. ADDRESS (City, State, and ZIP Code) P. O. Box 12211 Research Triangle Park, NC 27709-2211
8a. NAME OF FUNDING/SPONSORING ORGANIZATION U. S. Army Research Office	8b. OFFICE SYMBOL (if applicable)
9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER DAAL03-86-K-0063	
8c. ADDRESS (City, State, and ZIP Code) P. O. Box 12211 Research Triangle Park, NC 27709-2211	10. SOURCE OF FUNDING NUMBERS
	PROGRAM ELEMENT NO.
	PROJECT NO.
	TASK NO.
	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Ion Beam Modification of Metals: Mechanical Properties and Structure	
12. PERSONAL AUTHOR(S) James W. Mayer	
13a. TYPE OF REPORT Final	13b. TIME COVERED FROM 8/15/86 TO 8/14/89
14. DATE OF REPORT (Year, Month, Day) October 1, 1989	15. PAGE COUNT 6
16. SUPPLEMENTARY NOTATION The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.	
17. COSATI CODES	18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)
FIELD	GROUP
	SUB-GROUP
19. ABSTRACT The objective of this work was to study the phase transformations and property changes of metals brought about by ion beam induced materials modification and then to use this information to produce stable surface layers exhibiting optimal chemical and mechanical integrity. <i>Summary of Most Significant Results:</i> 1) Amorphous alloys can be formed by ion mixing a wide variety of metal systems within defined regions of atomic composition. 2) Two step processing such as implanting C and N into ion beam mixed layers improves the friction behavior. (OVER)	
20. DISTRIBUTION/AVAILABILITY OF ABSTRACT <input type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS	
21. ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a. NAME OF RESPONSIBLE INDIVIDUAL	22b. TELEPHONE (Include Area Code)
	22c. OFFICE SYMBOL

DTIC
ELECTE
NOV 28 1989
S E D

- 3) Fe-Ti mixed on stainless steel and implanted with N and C results in a wear resistant layer that deforms to depths greater than the thickness of the modified layer.
- 4) These novel structures on stainless steel were used to demonstrate a technique for distinguishing between deformation and material removal on worn surfaces.
- 5) Mixing substantial amounts of Au into Ti improves corrosion resistance of the Ti without appreciably degrading the wear and friction behavior.

**ION BEAM MODIFICATION OF METALS:
MECHANICAL PROPERTIES AND STRUCTURE**

Final Report to the U.S. Army Research Office

October 1, 1989

Contract Number: DAAL03-86-K-0063
N00014-87-K-0263 15 August 1986-14 August 1989

Submitted by: Cornell University
Ithaca, NY 14853

Principal Investigator: James W. Mayer *James W Mayer*

Final Report Written by: E. L. Fleischer *E. L. Fleischer*

Statement of the Problem Studied:

The objective of this work was to study the phase transformations and property changes of metals brought about by ion beam induced materials modification and then to use this information to produce stable surface layers exhibiting optimal chemical and mechanical integrity.

Summary of Most Significant Results:

- 1) Amorphous alloys can be formed by ion mixing a wide variety of metal systems within defined regions of atomic composition.
- 2) Two step processing such as implanting C and N into ion beam mixed layers improves the friction behavior.
- 3) Fe-Ti mixed on stainless steel and implanted with N and C results in a wear resistant layer that deforms to depths greater than the thickness of the modified layer.
- 4) These novel structures on stainless steel were used to demonstrate a technique for distinguishing between deformation and material removal on worn surfaces.
- 5) Mixing substantial amounts of Au into Ti improves corrosion resistance of the Ti without appreciably degrading the wear and friction behavior.

Ion For	
GRA&I	<input checked="" type="checkbox"/>
AB	<input type="checkbox"/>
anced	<input type="checkbox"/>
lection	

button/	
Availability Codes	
Dist	Avail and/or Special
A-1	



Discussion of Results:

Over the past several years we investigated hardness, friction, wear, and corrosion of ion beam mixed metal/metal systems and studied the resulting structural and compositional changes.

Our research (see list of publications acknowledging Army Research Office support) focused on the use of ion beams, both ion mixing and ion mixing plus ion implantation, to improve the wear and friction of stainless steels and titanium. The improvement in performance was dramatic in many cases.

Ion implantation has been used extensively to improve both mechanical and chemical properties of metals [1-3]. It has been shown that ion implantation in metals significantly reduces the friction coefficient and improves wear resistance. In applications, doses above 10^{17} ions/cm² are required to significantly alter surface compositions and to change mechanical properties. At these high doses sputtering sets the limit of composition achievable by ion implantation [4,5]. To overcome the composition limitation so as to reach the required high doses and to speed processing, ion beam mixing was used. By mixing deposited multilayer films into a metal substrate, one can obtain a homogeneous layer on stainless steel with good tribomechanical properties at doses as low as 10^{16} ions/cm². [6-8]

In our ARO supported work we have used four methods of ion beam modification to improve wear, friction, and corrosion of metals. The modes are: 1) direct ion implantation which is used to implant species such as carbon or nitrogen into the material at concentrations of a few atomic percent. 2) ion beam mixing which relies on the penetration of energetic ions through a deposited layer to cause intermixing between film and substrate. Single layer or multilayer deposited films are used to achieve the desired mixed composition. 3) ion-induced adhesion which is carried out by the penetration of energetic ion beams

past the film/substrate interface. The primary effect is to rearrange bonds at the interface to promote adhesion. Ion mixing between the film and substrate is minimal and the film must be deposited with the appropriate composition. 4) Two stage processing which uses ion mixing or ion-assisted adhesion to obtain an adherent film of the proper composition and a second implantation stage which introduces nitrogen or carbon into the modified layer to further improve mechanical properties. For stainless steel, two stage processing gave superior results compared to the one stage methods.

For example, nitrogen implantation was observed to significantly improve the dry sliding properties of an ion mixed FeTi surface alloy on stainless steel [9]. Two stage processing was also used in coevaporated films [10,11]. In this work, coevaporation of Pt and Ti on a stainless steel substrate produced a homogeneous film at the equiatomic composition. Adhesion of the evaporated film to the substrate was enhanced by a low dose ion implantation with light species, either Si or Ne. The tribomechanical properties were further improved by N implantation into the surface film.

We have shown that amorphous alloys can be formed by ion mixing in a wide variety of systems in defined regions of atomic compositions. Subsequent implantation even further improves the mechanical properties. The two stage process combined with layer-deposition allows the formation of layers with different composition and mechanical properties. That is, one can modify not only the surface layers, but also the intermediate layer between the surface region and the stainless steel substrate.

We found ion beam mixing substantial amounts of gold into titanium improves the corrosion resistance of the titanium without appreciably degrading the wear and friction properties [12]. The full range of compositions were measured by creating samples with linearly varying composition along the

length of the sample. This was accomplished by depositing alternating wedge shaped layers of Au and Ti and then ion mixing them. Reciprocal motion wear and friction tests across the composition gradient showed the variation of friction with composition. Likewise, the corrosion improvements for all compositions were compared on a single sample. Rutherford backscattering and transmission electron microscopy were used to correlate the property changes with composition and structure. A composition of 60%Ti-40%Au was chosen as optimal for improving corrosion resistance without appreciably degrading wear and friction properties. The microstructure consisted of a combination of crystalline and amorphous phases near the titanium end and of an fcc Au solid solution at the Au-rich end.

EDX line profiles (energy dispersive x-rays) combined with SEM (scanning electron microscopy) and Alpha Step surface profiles were used to distinguish between wear mechanisms such as deformation and material removal for surface layers with a different composition from the substrate. We used the ion beam modified steel samples as a model to demonstrate this simple, quick, and non-destructive method for distinguishing between the two processes. The samples were modified by mixing Fe and Ti on the surface and subsequently implanting C and N. The analysis technique is based on scanning an electron beam across the wear track while monitoring the characteristic X-ray emission from an element present only in the modified layer, Ti in our case [13]. This method correlates composition (indicating the amount of the modified layer remaining) to the physical contour of the wear track.

In the work at Cornell we used the facilities of the Materials Science Center for film deposition, scanning electron microscopy, and transmission electron microscopy. Ion implantation and Alpha Step profilometry was carried out at the National Nanofabrication Facility. Ion beam analysis was done using

the tandemron accelerator at Bard Hall. Wear and friction measurements were conducted on a Finnish designed (J.-P. Hirvonen) apparatus. Microindentation tests were carried out in collaboration with Prof. C.-Y. Li.

References

1. C. M. Preece and J. K. Hirvonen, *Ion Implantation Metallurgy*, (The Metallurgical Society of AIME, New York, 1980).
2. T. A. Smidt, *Ion Implantation for Materials Processing*, (Noyes Data Corp., Park Ridge, 1983).
3. I. L. Singer, *Mat. Res. Soc. Symp. Proc.* 27 (1984) 585.
4. R. Behrisch, *Sputtering by Particle Bombardment*, (Springer-Verlag, Berlin, 1981).
5. Z. L. Liao J. W. Mayer, *J. of Vac. Soc. Techn.* 15 (1978) 1629.
6. J.-P. Hirvonen, J. W. Mayer, M. Nastasi, D. Stone, Workshop on Surface Modification by Plasma-Surface Interactions, NIM B23 (1987) 487.
7. J.-P. Hirvonen, M. Nastasi, J. W. Mayer, *Appl. Phys. Lett.* 49 (1986) 1345.
8. J.-P. Hirvonen, M. Nastasi, J. W. Mayer, *Appl. Phys. Lett.* 51 (1987) 232.
9. J.-P. Hirvonen, M. Nastasi, J. W. Mayer, "Unlubricated friction and wear of an ion beam mixed nitrogen implanted Fe₅₀Ti₅₀ surface alloy on AISI 304 stainless steel", *Appl. Phys. Letter* 51 (1987) 232-234.
10. L. R. Zheng, L. S. Hung, J. W. Mayer, "Sliding properties of coevaporated and N implanted Pt₅₀Ti₅₀ films on AISI 304 stainless steel", *Mat. Sci. Lett.* 7 (1988) 1014-1017.
11. L. R. Zheng, L. S. Hung, J. W. Mayer, "Coevaporation and ion implantation of Pd₅₀Ti₅₀ and Pt₅₀Ti₅₀ on AISI stainless steels for reducing wear", *J. Appl. Phys.* 65 (1989) 300-304.
12. E. L. Fleischer, J. W. Mayer, J.-P. Hirvonen, "Ion beam mixing of Au-Ti", *Mat. Res. Soc. Symp. Proc.* 93 (1987) 227-232.
13. E. L. Fleischer, P. Børgesen, J.-P. Hirvonen, M. Nastasi, "A simple method for distinguishing between deformation and wear of modified surfaces", *Wear* 127(3) (1988) 221-228.

PAPERS ACKNOWLEDGING ARO SUPPORT

1. J.-P. Hirvonen, M. Nastasi, J. W. Mayer, "Unlubricated friction and wear of an ion beam mixed nitrogen-implanted Fe₅₀Ti₅₀ surface alloy on AISI 304 stainless steel", *Appl. Phys. Letter* 51 (1987) 232-234.
2. J.-P. Hirvonen, J. W. Mayer, M. Nastasi, D. Stone, "Modification of mechanical properties by ion beam mixing", *Nucl. Instr. Meth. B23* (1987) 487-497.
3. J.-P. Hirvonen, M. Nastasi, J. W. Mayer, "Effect of ion beam mixing on wear and friction of Fe-Ti multilayered structure on AISI 304 stainless steel", *Appl. Phys. Lett.* 49 (1986) 1345-1347.
4. J.-P. Hirvonen, J. W. Mayer, "Fretting wear of nitrogen implanted AISI 304 stainless steel", *Mat. Lett.* 4 (1986) 404-408.
5. J.-P. Hirvonen, M. Nastasi, J. W. Mayer, "Tribological properties of ion implanted amorphous Fe₅₀Ti₅₀ films", *Mat. Res. Soc. Symp. Proc.* (1987).
6. E. L. Fleischer, J. W. Mayer, J.-P. Hirvonen, "Ion beam mixing of Au-Ti", *Mat. Res. Soc. Symp. Proc.* 93 (1987) 227-232.
7. E. L. Fleischer, P. Børgesen, J.-P. Hirvonen, M. Nastasi, "A simple method for distinguishing between deformation and wear of modified surfaces", *Wear* 127(3) (1988) 221-228.
8. L. R. Zheng, L. S. Hung, J. W. Mayer, "Sliding properties of coevaporated and N implanted Pt₅₀Ti₅₀ films on AISI 304 stainless steel", *J. Mat. Sci. Lett.* 7 (1988) 1014-1017.
9. L. R. Zheng, L. S. Hung, J. W. Mayer, "Coevaporation and ion implantation of Pd₅₀Ti₅₀ and Pt₅₀Ti₅₀ on AISI stainless steels for reducing wear", *J. Appl. Phys.* 65 (1989) 300-304.

Scientific personnel supported under the U.S. Army Research Office Contract:
Bart Blanpain, Larry Doolittle, Elizabeth Fleischer, J.-P. Hirvonen, Jian Li, Steve Russell, Long Rue Zheng

Scientific personnel showing advanced degrees earned while employed by the U. S. Army Research Office Project:
E. L. Fleischer, M.S.