

SECURITY CLASSIFICATION OF THIS PAGE

PORT DOCUMENTATION PAGE

AD-A217 748

1b. RESTRICTIVE MARKINGS

3. DISTRIBUTION/AVAILABILITY OF REPORT

Approved for public release;
distribution unlimited.

4. PERFORMING ORGANIZATION REPORT NUMBER(S)

5. MONITORING ORGANIZATION REPORT NUMBER(S)

ARO 23791.2-MS-FC

6a. NAME OF PERFORMING ORGANIZATION

DUKE UNIVERSITY

6b. OFFICE SYMBOL
(If applicable)

7a. NAME OF MONITORING ORGANIZATION

U. S. Army Research Office

6c. ADDRESS (City, State, and ZIP Code)

Department of Mechanical Engineering
and Materials Science/Duke University
Durham, NC 27706

7b. ADDRESS (City, State, and ZIP Code)

P. O. Box 12211
Research Triangle Park, NC 27709-22118a. NAME OF FUNDING/SPONSORING
ORGANIZATION

U. S. Army Research Office

8b. OFFICE SYMBOL
(If applicable)

9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER

DAAL03-86-G-0046

8c. ADDRESS (City, State, and ZIP Code)

P. O. Box 12211
Research Triangle Park, NC 27709-2211

10. SOURCE OF FUNDING NUMBERS

PROGRAM
ELEMENT NO.PROJECT
NO.TASK
NO.WORK UNIT
ACCESSION NO.11. TITLE (Include Security Classification) Positron Annihilation Spectroscopy: A Nondestructive,
Submicroscopic Characterization Technique for Structural Polymers. (unclassified)

12. PERSONAL AUTHOR(S)

Phillip L. Jones

13a. TYPE OF REPORT

Final

13b. TIME COVERED

FROM 9-1-86 TO 8-31-89

14. DATE OF REPORT (Year, Month, Day)

1989, November 16

15. PAGE COUNT

16. SUPPLEMENTARY NOTATION

The view, opinions and/or findings contained in this report are those
of the author(s) and should not be construed as an official Department of the Army position,
policy, or decision, unless so designated by other documentation.

17. COSATI CODES

FIELD

GROUP

SUB-GROUP

18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)

Positron Annihilation Lifetime Spectroscopy,
Polycarbonate, Physical Aging, Structural Relaxation

19. ABSTRACT (Continue on reverse if necessary and identify by block number)

Positron annihilation lifetime spectroscopy (PALS) has been used to characterize as extruded and aged LEXAN polycarbonate. The long-lived component of the PALS analysis is attributed to orthoPositronium (oPs) pick off annihilations. The oPs pickoff component lifetime and intensity decrease as the result of the aging heat treatment, and this decrease is associated with a decrease in the free volume site size and concentration in glassy polycarbonate due to aging. Isothermal relaxation experiments performed over the range 12°C to 30°C performed on as-extruded and aged polycarbonate indicate that the relaxation kinetics are significantly different, and are consistent with a decrease in molecular mobility as the result of aging. An activation energy for structural relaxation of 8.2 kcal/mole for aged polycarbonate versus 3.0 kcal/mole for unaged polycarbonate was determined. The relaxation kinetics observed using PALS is related to the structural state and molecular mobility of the polymer.

20. DISTRIBUTION/AVAILABILITY OF ABSTRACT

☐ UNCLASSIFIED/UNLIMITED ☐ SAME AS RPT. ☐ DTIC USERS

21. ABSTRACT SECURITY CLASSIFICATION

Unclassified

22a. NAME OF RESPONSIBLE INDIVIDUAL

22b. TELEPHONE (Include Area Code)

22c. OFFICE SYMBOL

FINAL REPORT

Proposal Number: 23791-MS
Funding Document: DAAL-86-G-0046

Statement of the Problem Studied

Positron annihilation lifetime spectroscopy (PALS) has been used to study the mechanism of physical aging in polycarbonate. The PALS analysis was supplemented with tensile testing, differential scanning calorimetry, density measurements and x-ray diffraction.

Summary of Findings

The results of this investigation have led to the following conclusions:

1. Physical aging of polycarbonate increases the relaxation times of ortho-positronium (o-Ps) pickoff intensity I_3 during free volume recovery. This increase in relaxation time is a reflection of the increase in molecular response times due to physical aging, which is also evident in the changes in tensile and physical properties (increased yield strength, post yield stress drop, glass transition temperature and density).
2. The time rate of change observed in I_3 during contraction and expansion experiments in glassy polycarbonate is of the same form as volume and enthalpy recovery, and can be modeled similarly.
3. Any change in molecular conformation *during* physical aging is not evident in the o-Ps pickoff lifetime or intensity. Thus, the physical aging phenomena is not the result of a decrease in the amount of free volume or mean free volume cavity size.
4. The physical aging mechanism in polycarbonate is postulated to be associated with either an increase in entanglement density, an increase in the population of *trans* conformations, or a combination of both.
5. Over the temperature range 20°C to 120°C the o-Ps pickoff lifetimes and intensities are lower in aged polycarbonate than in as-

extruded polycarbonate, which is interpreted as a decrease in free volume concentration and cavity size as the *result* of physical aging.

6. The change in I_3 measured during isothermal relaxation experiments for both as-extruded and physically aged polycarbonate can be substituted for the fractional free volume in various theories used to model viscoelastic behavior of glassy polymers.

7. The nondestructive character and relative ease of data collection associated with positron annihilation lifetime spectroscopy could make this technique important in the prediction of physical property response in glassy polymers.

Publications

1. P.L. Jones, A.J. Hill, G.W. Pearsall and J.H. Lind, "A Positron Annihilation Lifetime Study of Poly(Bisphenol-A Carbonate)", Materials Research Society Symposium Proceedings, **82** (1987) 29-34.

2. A.J. Hill, P.L. Jones, J.H. Lind and G.W. Pearsall, "A Positron Annihilation Lifetime Study of Isothermal Structural Relaxation in Bisphenol-A Polycarbonate", Journal of Polymer Science, A, **26** (1988) 1541-1549.

3. A.J. Hill, K.J. Heater and C.M. Agrawal, "The Effects of Physical Aging in Polycarbonate", Journal of Polymer Science, (accepted June 1989).

Scientific Personnel

1. Phillip L. Jones, Associate Professor of Materials Science, Department of Mechanical Engineering and Materials Science, Duke University, Durham, North Carolina, 27706.

2. Anita J. Hill, graduate student (M.S., December 1986 and Ph.D., May 1989)