

2

DTIC FILE COPY

Office of Naval Research
Contract N00014-87-K-0438

R&T Code 413j009

Technical Report No. 4

Synthesis and Radical Polymerization
of 1,1,2,2-Tetracyanocyclopropylstyrene

by

Ju-Yeon Lee and H.K. Hall, Jr.

Polym. Bull.

in press

University of Arizona
Department of Chemistry
Tucson, AZ 85721

March, 1990

DTIC
UNCLASSIFIED
MAR 02 1990
E D

Reproduction in whole, or in part, is permitted for any purpose of the United States Government.

*This document has been approved for public release and sale: its distribution is unlimited.

REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION None			1b. RESTRICTIVE MARKINGS		
2a. SECURITY CLASSIFICATION AUTHORITY None			3. DISTRIBUTION / AVAILABILITY OF REPORT Unlimited		
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE None					
4. PERFORMING ORGANIZATION REPORT NUMBER(S) Technical Report #4			5. MONITORING ORGANIZATION REPORT NUMBER(S) ONR N00014-87-K-0437		
6a. NAME OF PERFORMING ORGANIZATION University of Arizona		6b. OFFICE SYMBOL (If applicable)		7a. NAME OF MONITORING ORGANIZATION Office of Naval Research	
6c. ADDRESS (City, State, and ZIP Code) Department of Chemistry University of Arizona Tucson, AZ 85721				7b. ADDRESS (City, State, and ZIP Code) 800 North Quincy Avenue Arlington, VA 22217	
8a. NAME OF FUNDING / SPONSORING ORGANIZATION		8b. OFFICE SYMBOL (If applicable)		9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER	
8c. ADDRESS (City, State, and ZIP Code) 800 N. Quincy Avenue Arlington, VA 22217				10. SOURCE OF FUNDING NUMBERS	
				PROGRAM ELEMENT NO.	PROJECT NO.
				TASK NO.	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) Synthesis and Radical Polymerization of 1,1,2,2-Tetracyanocyclopropylstyrene					
12. PERSONAL AUTHOR(S) Ju-Yeon Lee and H.K. Hall, Jr.					
13a. TYPE OF REPORT Technical		13b. TIME COVERED FROM _____ TO _____		14. DATE OF REPORT (Year, Month, Day)	
15. PAGE COUNT					
16. SUPPLEMENTARY NOTATION Polym. Bull.					
17. COSATI CODES			18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB-GROUP			
19. ABSTRACT (Continue on reverse if necessary and identify by block number) An isomeric mixture (m-p/: 70/30, mole/mole) of 1,1,2,2-tetracyanocyclopropylstyrene 2 was prepared by cyclopropane formation from bromonalonitrile and vinyl benzaldehyde. The substituted styrene compound 2 was polymerized with free radical initiator to obtain the polymers with multicyno functions in the pendant group. The resulting polymers were soluble in acetone and dimethyl sulfoxide (DMSO) and the inherent viscosities were in the range of 0.27-0.32 dL/g. Solution-cast films were clear and brittle, showing T _g value of 112°C. H. K. Hall, Jr. (PIU)					
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☒ SAME AS RPT. ☐ DTIC USERS			21. ABSTRACT SECURITY CLASSIFICATION		
22a. NAME OF RESPONSIBLE INDIVIDUAL H.K. Hall, Jr.			22b. TELEPHONE (Include Area Code) 602-621-6325		22c. OFFICE SYMBOL

by

C.S. Marvel Laboratories
Department of Chemistry
University of Arizona
Tucson, AZ 85721

February 7, 1990

[illegible]

Synopsis

An isomeric mixture (m-/p-: 70/30, mole/mole) of 1,1,2,2-tetracyanocyclopropylstyrene 2 was prepared by cyclopropane formation from bromomalononitrile and vinyl benzaldehyde. The substituted styrene compound 2 was polymerized with free radical initiator to obtain the polymers with multicyno functions in the pendant group. The resulting polymers were soluble in acetone and dimethyl sulfoxide (DMSO) and the inherent viscosities were in the range of 0.27-0.32 dL/g. Solution-cast films were clear and brittle, showing T_g value of 112°C.

Introduction

Amorphous polymers with a high concentration of dipole moments exhibit piezoelectric properties if the main chain has an all planar zigzag conformation. The copolymer of vinylidene cyanide and vinyl acetate is such a case (1). Poly(1-bicyclobutanecarbonitrile), because the rigid ring structure prevents a helical structure, also shows a piezoelectric effect (2).

We proposed recently that three- and four-membered rings with several cyano groups held rigidly would have large dipole moment (3-4). In this report, we describe the synthesis and radical polymerization of substituted styrene containing the 1,1,2,2-tetracyanocyclopropane unit.

Experimental

Materials

The reagent grade chemicals were purified by distillation or recrystallization before use. Vinylbenzyl chloride (m- and p-isomeric mixture) was purchased from Kodak Co. and distilled under vacuum before use. Dimethyl sulfoxide (DMSO) was dried over 4 Å molecular sieves for several days and distilled under vacuum. Acetonitrile was refluxed with calcium hydride and fractionally distilled. Benzene was purified by refluxing over sodium metal, distilled, and stored over 4 Å molecular sieves under nitrogen. γ -Butyrolactone was dried

with anhydrous calcium sulfate and fractionally distilled. Bromomalononitrile was prepared according to a literature procedure (5) and recrystallized twice from chloroform. 2,2'-Azo-bisisobutyronitrile was recrystallized from methanol and stored at 5°C.

Measurements

All melting point temperatures are uncorrected. IR spectra were taken on Perkin-Elmer 983 spectrometer. ^1H -NMR and ^{13}C -NMR spectra were obtained on a Bruker WM 250 nuclear magnetic resonance spectrometer at 250 MHz. Elemental analyses were performed by Desert Analytics, Tucson, AZ. Viscosity values were obtained by using a Cannon-Fenske viscometer. Melting points were measured in a Thomas-Hoover melting point apparatus. The glass transition temperatures (T_g) were measured on a Perkin-Elmer DSC-4 differential scanning calorimeter in a nitrogen atmosphere.

Preparation of Vinyl Benzaldehyde 1

A mixture of 12.2 g (0.08 mole) of vinylbenzyl chloride (m- and p-isomeric mixture) and 23.3 g (0.12 mole) of potassium chromate in 100 ml of dimethyl sulfoxide was refluxed with vigorous stirring at 120°C for 2 hr under nitrogen. The resulting black solution was filtered on Celite and rinsed with 20 ml of DMSO. Extraction was performed on the filtrate twice with 100 ml of diethyl ether. The organic layer was washed twice with 100 ml of water and dried over anhydrous magnesium sulfate. The resulting solution was concentrated by rotary evaporator, followed by fractional distillation, which yielded 7.6 g of 1 (72% yield; m-/p-: 67/33 mole/mole). Bp 63-64°C/0.5 mmHg. ^1H -NMR (CDCl_3) δ 5.36-5.48 (q, 1H), 5.83-5.97 (q, 1H), 6.73-6.83 (q, 1H), 7.45-7.94 (m, 4H), 9.97-10.03 (d, 1H); IR (neat) 1698 (C=O), 1627, 1600 (C=C) cm^{-1} . Anal. Calcd for $\text{C}_9\text{H}_8\text{O}$: C, 81.82; H, 6.06. Found: C, 81.76; H, 6.02.

Synthesis of 1,1,2,2-Tetracyanocyclopropylstyrene 2

A solution of 7 g (0.042 mole) of potassium iodide in 20 ml of water was added slowly to the solution of vinyl benzaldehyde (2.64 g, 0.02 mole) and bromomalononitrile (2.90 g, 0.02 mole) in 20 ml of ethanol at room temperature. After stirring for 1 hr. at room temperature, the product was filtered and rinsed with 20 ml of cold ethanol. The obtained white crystals were recrystallized from 95% ethanol to give 1.54 g (63% yield) of 2 (m-/p-: 70/30, mole/mole). Mp 157°-160° (dec.). ^1H -NMR (acetone- d_6) δ 4.98-5.02 (d, 1H), 5.32-5.40 (m, 1H), 5.88-6.01 (m, 1H), 6.77-6.89 (q, 1H), 7.50-8.08 (m, 4H); IR (KBr) 2259 (C=N), 1631, 1600 (C=C) cm^{-1} ; ^{13}C -NMR (acetone- d_6) δ 23.5 (s, $\text{C}=\text{C}$), 43.0 (s, $\text{C}=\text{C}$), 109.5 (s, cis-CN), 111.2 (s, trans-CN), 115.6-116.2 (d, CH_2 =), 127.3-130.4 (m, aromatic), 136.4 (s, $\text{CH}=\text{C}$), 139.5 (s, $\text{C}=\text{C}$). Anal. Calcd for $\text{C}_{11}\text{H}_6\text{N}_4$: C, 73.77; H, 3.28; N, 22.95. Found: C, 73.83; H, 3.21; N, 22.85.


Radical Polymerization of 1,1,2,2-Tetracyanocyclopropylstyrene 2

A representative free radical polymerization procedure was as follows: A γ -butyrolactone (2.0 ml) solution of 2 (0.61 g, 2.5 mmole) was placed in a polymerization tube and 4.1 mg (2.5×10^{-2} mmole) of AIBN was added under nitrogen. The mixture was degassed by a freeze-thaw process under vacuum. After warming to room temperature, it was placed in an oil bath kept at 65°C. After 13 hr, the polymerization tube was opened and the viscous product was poured into a 350 ml of diethyl ether. The precipitated polymer was collected and reprecipitated from acetone into diethyl ether. 3: 0.54 g (89% yield); $\eta_{inh}=0.30$ dL/g (0.5 g/dL in acetone at 25°C). $^1\text{H-NMR}$ (acetone- d_6) δ 1.10-1.95 (s, 3H), 4.35-4.80 (s, 1H), 6.25-7.65 (m, 4H); IR (KBr) 2256 (C $\equiv$ N), 1604 (aromatic C=C); $^{13}\text{C-NMR}$ (acetone- d_6) δ 23.0 (s, $\text{NC} > \text{C} < \text{NC}$), 40.5-41.0 (m, -CH $_2$ -), 41.1-42.0 (m, -CH-), 42.4-43.5 (m, $>\text{C} <_{\text{H}}$), 109.3 (s, cis-CN), 110.5 (s, trans-CN), 123.4-132.5 (m, aromatic). Anal. Calcd for $(\text{C}_{15}\text{H}_8\text{N}_4)_n$: C, 73.77; H, 3.28; N, 22.95. Found C, 73.68; H, 3.22; N, 22.86.

Results and Discussion

Synthesis of Monomer 2

1,1,2,2-Tetracyanocyclopropylstyrene 2 was prepared using the Wideqvist method for cyclopropane synthesis (6-8). Vinyl benzaldehyde was synthesized, according to a known method (9), by oxidation of vinylbenzyl chloride. The latter is purchased as a 70/30 mixture of the meta- and para-isomers. Reaction of vinylbenzaldehyde with bromomalononitrile in diluted aqueous ethanol solution led to tetracyanocyclopropylstyrene in good yield at room temperature. The chemical structure was confirmed by $^1\text{H-NMR}$, IR, $^{13}\text{C-NMR}$ spectra, and elemental analysis. $^1\text{H-NMR}$ spectrum showed that tetracyanocyclopropylstyrene 2 is a mixture of m-isomer (70 mole %) and p-isomer (30 mole %). Compound 2 was quite stable when heated to 100°C.



Radical Polymerization of Tetracyanocyclopropylstyrene 2

Tetracyanocyclopropylstyrene 2 was polymerized by free radical initiator such as AIBN to obtain the polytetracyanocyclopropylstyrene 3. Radical polymerizations were carried out in solution at 65°C. Monomer 2 was quite reactive toward radical initiator and polymerized readily. The free radical initiator did not attack the tetracyanocyclopropane ring during polymerization. The polymerization results are summarized in Table 1. In most cases, conversions were very high, but the molecular weights were rather low.

The chemical structure of polymer 3 was confirmed by IR, ¹H-NMR, ¹³C-NMR spectra, and elemental analyses. The polymer was soluble in acetone and DMSO, but was not soluble in diethyl ether and chloroform. The inherent viscosity measured in acetone at 25°C was in the range 0.27-0.32 dL/g. The thermal behavior of the polymer was investigated by DSC at scanning rate of 10°C/min to determine the glass




Table 1. Free Radical Polymerization of 2^a by AIBN at 65°C.

Solvent (vol/vol)	2/Solvent (g/mL)	Time (h)	Yield (%)	η_{inh}^b (dL/g)	Tg ^c (°C)
C ₆ H ₆ /CH ₃ CN, 0.5	0.20	14	90	0.27	--
C ₆ H ₆ /CH ₃ CN, 0.4	0.22	12	86	0.29	--
C ₆ H ₆ /CH ₃ CN, 0.5 ^d	0.20	20	88	0.31	--
γ -butyrolactone	0.31	13	89	0.30	112
γ -butyrolactone	0.41	16	90	0.32	--

^a2 = 1,1,2,2-tetracyanocyclopropylstyrene (m-/p-: 70/30, mole/mole), 1 mole % AIBN.

^bInherent viscosity of polymer: concentration of 0.5 g/dL in acetone at 25°C.

^cDetermined from DSC curves measured on a Perkin-Elmer DSC-4 differential scanning calorimeter with a heating rate of 10°C/min in a nitrogen atmosphere.

^dCatalytic amount of glacial acetic acid was added.

transition temperature (Tg). The Tg value was higher than that of polystyrene. Films cast from the polymer solution were brittle, which could be due to the rather low molecular weight and high dipole density. The piezoelectric activity has not been measured yet.

Conclusion

We synthesized a m- and p-isomeric mixture of tetracyanocyclopropylstyrene containing cyclopropane ring with tetracyano groups. The substituted styrene was polymerized by radical initiator (AIBN) to obtain the polymers with multiccyano functions. The resulting polymer was soluble in acetone and DMSO, but insoluble in chloroform. The Tg value of the polymer was higher than that of polystyrene. Films cast from the polymer solution were brittle, which could be due to the rather low molecular weight as indicated by the inherent viscosities, and/or to the presence of strong dipoles in the side chain. Attempts to obtain higher molecular weights failed. The tetracyanocyclopropane ring could act as weak inhibitors. Copolymerization with other monomers and measurements of piezoelectric activity are in progress and the full accounts of the results will be reported later.

Acknowledgements

We are deeply indebted to the Office of Naval Research for partial financial support of this work.

References

1. Jo, Y.S.; Inoue, Y.; Chujo, R.; Saito, K.; Miyata, S. Macromolecules, **1985**, *18*, 1850.
2. Hall, Jr., H.K.; Chan, R.J.H.; Oku, J.; Hughes, O.R.; Scheinbeim, J.; Newman, B. Polym. Bull., **1987**, *17*, 135.
3. Hall, Jr., H.K.; Padias, A.B.; Fuso, F.; Ni, Z.; Mitchell, M.A.; Leslie, T.M. (to be published).
4. Lee, J.Y.; Padias, A.B.; Hall, Jr., H.K. Macromolecules (submitted).
5. Hesse, B.C. J. Am. Chem. Soc., **1986**, *108*, 723.
6. Ramberg, L.; Wideqvist, S. Arkiv Kemi, **1937**, *12A* (22), 12.
7. Ramberg, L.; Wideqvist, S. ibid, **1945**, *20B* (4), 8.
8. Hart, H.; Freeman, F. J. Org. Chem., **1963**, *28*, 1220.
9. Thuy, V.M.; Mattice, P. Bull. Soc. Chim. Belg., **1989**, *98*, 221.

TECHNICAL REPORT DISTRIBUTION LIST, GENERAL

	<u>No.</u> <u>Copies</u>		<u>No.</u> <u>Copies</u>
Office of Naval Research Chemistry Division, Code 1113 800 North Quincy Street Arlington, VA 22217-5000	3	Dr. Ronald L. Atkins Chemistry Division (Code 385) Naval Weapons Center China Lake, CA 93555-6001	1
Commanding Officer Naval Weapons Support Center Attn: Dr. Bernard E. Douda Crane, IN 47522-5050	1	Chief of Naval Research Special Assistant for Marine Corps Matters Code 00MC 800 North Quincy Street Arlington, VA 22217-5000	1
Dr. Richard W. Drisko Naval Civil Engineering Laboratory Code L52 Port Hueneme, California 93043	1	Dr. Bernadette Eichinger Naval Ship Systems Engineering Station Code 053 Philadelphia Naval Base Philadelphia, PA 19112	1
Defense Technical Information Center Building 5, Cameron Station Alexandria, Virginia 22314	2 <u>high</u> <u>quality</u>	Dr. Sachio Yamamoto Naval Ocean Systems Center Code 52 San Diego, CA 92152-5000	1
David Taylor Research Center Dr. Eugene C. Fischer Annapolis, MD 21402-5067	1	David Taylor Research Center Dr. Harold H. Singerman Annapolis, MD 21402-5067 ATTN: Code 283	1
Dr. James S. Murday Chemistry Division, Code 6100 Naval Research Laboratory Washington, D.C. 20375-5000	1		