

(2)

AD-A225 381

DTIC FILE COPY

CONTRACT CRYSTAL GROWTH  
AND  
FABRICATION SERVICES

DTIC  
ELECTE  
AUG 15 1990  
S D  
Co D

Quarterly Technical Report # 5

Period: May 1990 through July 1990

Report Date: August 7, 1990

Contract Number: N00014-89-C-2222

Contributors: J. E. Creamer, R. C. Acklin, M. H. Randles

Prepared by: M. H. Randles  
Airtron Division of Litton Systems, Inc.  
PO Box 410168  
Charlotte, N. C. 28241-0168

APPROVED FOR PUBLICATION  
Approved for public release  
Distribution Unlimited

Submitted to: Dr. Charles Marquardt, COTR  
Naval Research Laboratory  
Code 6551  
4555 Overlook Ave., SW  
Washington, D. C. 20375-5000

00 08 13 100

SUMMARY

This program is intended to give the scientists at the Naval Research Laboratory the ability to evaluate new solid state laser crystals. During the fifth quarter of this contract only one growth run was performed, the tenth since project start.

CRYSTAL GROWTH

The crystal requested and grown was Er,Tm:YAG. The melt composition is listed in Table 1. It was assumed that the distribution coefficients are unity and that the crystal composition will be the same as the melt. (JFS)

TABLE 1: Composition

<u>Growth Run</u>	<u>Melt composition</u>	<u>Nominal Doping</u> at% (cm <sup>-3</sup> )
NRL-10	Y <sub>2.685</sub> Er <sub>0.3</sub> Tm <sub>0.015</sub> Al <sub>5</sub> O <sub>12</sub>	10 % Er (1.4x10 <sup>21</sup> ) 0.5 % Tm (6.9x10 <sup>19</sup> )

The growth conditions are listed in Table 2. The crystal grew well and only 6 widely separated scattering sites were observed. A green fluorescence was observed with a bright fiber optic inspection light.

TABLE 2: Growth Conditions

<u>Growth Run</u>	<u>Pull Rate</u> mm/Hr	<u>Rotation</u> RPM	<u>Oxygen</u> %	<u>Average Diameter</u> mm	<u>Length at Diam</u> mm	<u>Fraction Crystallized</u> %
NRL-10	1.5	10	0.3	31	67	27

PLANS FOR NEXT QUARTER

Fabricate diode pumpable rods from NRL-10. At this time no further runs have been scheduled.

AD-A22135  
Codes  
ref/or  
symbol

2

