



REPORT DOCUMENTATION PAGE

Form Approved

OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)

2. REPORT DATE
1990

3. REPORT TYPE AND DATES COVERED

Final 1 Jul 87 - 31 May 90

4. TITLE AND SUBTITLE

Rapid Isothermal Processing of Thin Epitaxial CaF_2
Dielectric Films for Advanced Si Radiation
Tolerant Integrated Circuits

5. AUTHOR(S)

Rajendra Singh

6. FUNDING NUMBERS

DAAL03-87-K-0081

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)

University of Oklahoma
Norman, OK 73019

8. PERFORMING ORGANIZATION
REPORT NUMBER

9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)

U. S. Army Research Office
P. O. Box 12211
Research Triangle Park, NC 27709-2211

10. SPONSORING/MONITORING
AGENCY REPORT NUMBER

ARO 25046.17-EL-SDI

11. SUPPLEMENTARY NOTES

The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

12a. DISTRIBUTION/AVAILABILITY STATEMENT

Approved for public release; distribution unlimited.

12b. DISTRIBUTION CODE

13. ABSTRACT (Maximum 200 words)

This report contains research results in the areas of in-situ rapid isothermal processing, in-situ cleaning of semiconductor surfaces, solid phase epitaxial growth of II-A fluorides, in-situ metallization, the role of thermal stress, use of II-A fluorides as buffer layers for the decomposition of high temperature superconducting thin films and the set up of RIP assisted MOCVD.

DTIC
ELECTE
S **D**
AUG 29 1990
B

14. SUBJECT TERMS

Dielectric Films, Integrated Circuits, Isothermal Processing,
Semiconductors, Fluorides, Metallization, Thermal Stress,
Superconducting Thin Films.

15. NUMBER OF PAGES

14

16. PRICE CODE

17. SECURITY CLASSIFICATION
OF REPORT

UNCLASSIFIED

18. SECURITY CLASSIFICATION
OF THIS PAGE

UNCLASSIFIED

19. SECURITY CLASSIFICATION
OF ABSTRACT

UNCLASSIFIED

20. LIMITATION OF ABSTRACT

UL

AD-A225 995

1. ARO PROPOSAL NUMBER: 25046-EL-SDI
2. PERIOD COVERED BY REPORT: FINAL REPORT 1 July 1987 - 31 May 1990
3. TITLE OF PROPOSAL: Rapid Isothermal Processing of Thin Epitaxial CaF_2 Dielectric Films for Advanced Si Radiation Tolerant Integrated Circuits

4. CONTRACT OR GRANT NUMBER: DAAL03-87-K-0081

5. NAME OF INSTITUTION: University of Oklahoma

6. AUTHOR OF REPORT:

Rajendra Singh
 School of Electrical Engineering and Computer Science
 202 W. Boyd, Rm. 219
 Norman, OK 73019
 (405) 325-4721
 FAX (405) 325-2894

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

7. LIST OF MANUSCRIPTS SUBMITTED OR PUBLISHED UNDER ARO SPONSORSHIP DURING THIS REPORTING PERIOD, INCLUDING JOURNAL REFERENCES:

1. R. Singh, R.P.S. Thakur, A. Katz, A.J. Nelson, S.C. Gebhard, and A.B. Swartzlander, "Relationship Between Thermal Stress and Structural Properties of SrF_2 Films of (100) InP," Appl. Phys. Lett (In Press).
2. R. Singh, R.P.S. Thakur, A.J. Nelson, S.C. Gebhard, and A.B. Swartzlander, "Low Thermal Budget Solid Phase Epitaxial Growth of CaF_2 on Si (111) Substrates," J. Electronic Materials (In Press).
3. R. Singh and R.P.S. Thakur, "Role of In-situ Rapid Isothermal Processing in the Advanced Metallizations," Journal of the Institution of Electronics and Telecommunications Engineering, (In Press).

4. R. Singh, R.P.S. Thakur, A. Kumar, J. Narayan, and A. Katz, "Role of In-situ Rapid Isothermal Processing in the Metallization and Passivation of Indium Phosphide Devices," Proc. Mat. Res. Soc., 1990 Spring Meeting, San Francisco, CA, (In Press).
5. R. Singh, R.P.S. Thakur, J. Narayan, A. Katz, and A.J. Nelson, "In-situ Rapid Isothermal Processing (RIP) of InP Based Devices," Proc. Second International Conference on InP and Related Materials, April 23-25, 1990, Denver, Colorado, published by IEEE, New York, 1990, p. 207.
6. R. Singh, A. Kumar, R.P.S. Thakur, P. Chou, J. Chaudhuri, V. Gondhalekar, and J. Narayan, "Planar Stress Relaxation in Solid Phase Epitaxial CaF_2 Films Grown on (111) Si by In-situ Rapid Isothermal Processing," Appl. Phys. Lett., 1990, Vol. 56, pp. 1567-1569.
7. R. Singh R.P.S. Thakur, A. Kumar, P. Chou, and J. Narayan, "Structural Properties of Solid Phase Epitaxial Films of BaF_2 on (100) InP Formed by In-situ Rapid Isothermal Processing," J. App. Phys. 1990, Vol. 67, pp. 6411-6414.
8. R. Singh, R.P.S. Thakur, A. Kumar, and J. Narayan, "In-situ Rapid Isothermal Processing with Applications to InP Devices," Annual Meeting of the Minerals, Metals, and Materials Society, Anaheim, CA, Feb. 18-22, 1990.
9. R. Singh, "Rapid Isothermal Processing of Advanced Electronic Materials," Proc. SPIE Symposium on Laser/Optical Processing of Electronic Materials, Santa Clara, Vol. 1190, pp. 1167-1187 (1990).
10. R. Singh, R.P.S. Thakur, A. Kumar, P. Chou, and J. Narayan, "Role of In-situ

- Rapid Isothermal Processing in the Solid Phase Epitaxial Growth of II-A Fluoride Films on InP," Appl. Phys. Lett., 1990, Vol. 56, pp. 247-249 and 1990, Vol. 56, p. 1808.
11. R. Singh, A. Kumar, R.P.S. Thakur, P. Chou, J. Narayan, A.R. Srivasta, A.J. Nelson, and h.S. Ullal, "Solid Phase Epitaxial Growth of II-A Fluorides on Semiconductors, by In-situ Rapid Isothermal Processing," Journal of Electronic Materials, Vol. 19, pp. 481-486, 1990.
 12. R. Singh, A. Kumar, R.P.S. Thakur, P. Chou, J. Narayan, A.R. Srivasta, A.J. Nelson, and H.S. Ullal, "Solid Phase Epitaxial Growth of II-A Fluorides on InP by In-situ Rapid Isothermal Processing," Proc. Materials Research Society, Fall 1989 meetings, Boston, MA, (In Press).
 13. A.R. Srivasta, J. Narayan, F. Radpour, and R. Singh, "Novel $\langle 110 \rangle$ Growth Processes in Vacuum Evaporated Calcium Fluoride Films on $\langle 011 \rangle$ Silicon," J. Vac. Sci. and Technol A, 1989, Vol. 7, pp. 3200-3204.
 14. A.R. Srivasta, J. Narayan, R. Singh, and F. Radpour, "Microstructure of Vacuum Evaporated Calcium Fluoride Films on Silicon," Mat. Res. Soc. Meeting, Dec. 1988.
 15. F. Radpour, R. Singh, W.L. Krisa, M. Rahmati, and J. Narayan, "Electrical and Structural Properties of Thin Epitaxial Dielectric Films formed by In-situ Rapid Isothermal Processing," J. Vac. Sci. and Technol.; A, 1988, Vol. 63, pp. 1363-1366.
 16. R. Singh, F. Radpour, and J. Narayan, "In-Situ Rapid Isothermal Processing of II-A Fluorides on Compound Semiconductors," Proc. Int. Soc. for Optical

Engineering, 1988, Vol. 944, pp. 146-150.

17. R. Singh, R. Radpour, and J. Narayan, "In-Situ Rapid Isothermal Processing of II-A Fluorides on Silicon," Proc. Int. Soc. for Optical Engineering, 1988, Vol. 975, pp. 111-117.
 18. R. Singh and F. Radpour, "Rapid Isothermal Processing of Dielectrics," Proc. Int. Soc. for Optical Engineering; 1988, Vol. 945, pp. 72-83.
 19. R. Singh, F. Radpour, J. Narayan, and S.K. Kahng, "Thin Epitaxial Dielectric Films on Silicon" Proc. Int. Soc. for Optical Engineering, 1988, Vol. 877, pp. 13-20.
 20. F. Radpour, R. Singh and J. Narayan, "In-situ Rapid Isothermal Processing of Epitaxial II-A Fluorides on III-IV Semiconductors," Materials Research Society 1988 Spring Meeting, p. 271.
 21. F. Radpour, R. Singh, W.L. Krisa and J. Narayan, "Role of Interface on the Structural and Electrical Characteristics of Epitaxial II-A Fluorides on Silicon Grown by In-situ Rapid isothermal Processing," Materials Research Society 1988 Spring Meeting, p. 13.
8. SCIENTIFIC PERSONNEL SUPPORTED BY THIS PROJECT AND DEGREES AWARDED DURING THIS REPORTING PERIOD:
1. R. Singh, University of Oklahoma.
 2. F. Radpour, University of Oklahoma.
 3. R.P.S. Thakur, University of Oklahoma.
 4. J. Narayan, North Carolina State University.
 5. A.R. Srivasta, North Carolina State University, PhD, 1989.

6. William Krisa, University of Oklahoma, M.S., 1988.

I. INTRODUCTION

The original purpose of this three year project was to develop a low temperature processing technique for the deposition of Si/CaF₂ structure on Si substrate that can be used to realize advanced Si CMOS and bipolar circuits. However, after the first year at the direction of ARO the emphasis was changed from Si to InP substrates. Also at the end of the second year, this project was reduced from three years to only two years (reduced budget in second year). Thus, the project was not funded for the proposed three years. However, the project has been extremely successful, as is evident from the research result described here.

II. SUMMARY

A. IN-SITU RAPID ISOTHERMAL PROCESSING

For the first time, we have assembled an ultra high vacuum in-situ rapid isothermal processor. The in-situ rapid isothermal processor consists of an ultra high vacuum system coupled to a rapid isothermal processor. The in-situ rapid isothermal processor has the capability of in-situ cleaning of semiconductor surface, thermal or electron beam deposition and in-situ annealing of materials. The concept and the system developed in our laboratory can be used in the single wafer reduced thermal budget integrated manufacturing of micro, opto and cryo electronic devices and circuits. The system cost is much lower compared to individual deposition and annealing systems. Details of the system are described in reference 1. B. IN-SITU CLEANING OF SEMICONDUCTOR SURFACE

Based on rapid isothermal processing, we have developed a new reduced thermal budget (product of processing time and temperature) processing technique for the cleaning

of semiconductor surface. The technique involves heating the substrate for short periods in the presence of 5% H₂ and 95% Ar mixture. Excellent quality of interface was obtained, as was observed by TEM and auger depth profile. Details of silicon and InP surface cleaning are described in reference 1 and 2 respectively.

C. SOLID PHASE EPITAXIAL GROWTH OF II-A FLUORIDES

For the first time, we have grown II-A fluorides (CaF₂, BaF₂, SrF₂ and their mixture) by solid phase epitaxial growth. The process involves in-situ cleaning, room temperature deposition of II-A fluoride followed by in-situ annealing. The II-A fluoride films obtained by solid phase epitaxial approach are of excellent quality. Details of the preparation and characterization of the films are described in reference 1 to 5.

D. IN-SITU METALLIZATION

Generally, metallization and annealing are done in separate systems. For the first time, we have shown that in-situ annealing after metallization can provide improved quality of ohmic contacts compared to their ex-situ annealed counter partners. These results are described in reference 6.

E. ROLE OF THERMAL STRESS

The thermal stress plays a critical role in determining the structural and electrical properties of the thin films. We have studied the correlation between thermal stress and the structural properties. II-A fluoride films deposited at room temperature followed by in-situ annealing provide less thermal stress compared to the ex-situ annealed films and also show lower thermal hysteresis for the same thermal budget. The ex-situ annealed films are full of defects and are polycrystalline in nature. Thus we have found a direct

correlation between the structural properties and the thermal stress [4, 7].

F. USE OF II-A FLUORIDES AS BUFFER LAYER FOR THE DEPOSITION OF HIGH TEMPERATURE SUPERCONDUCTING THIN FILMS

We have used buffer layer BaF_2 to deposit thin films of Y-Ba-Cu-O on Si and other substrates [8-10]. The capability of depositing high temperature superconducting thin films on Si substrates [8, 10], coupled with already demonstrated capability of semiconductor-II-A-fluoride-silicon heterostructure suggest the possibility of integration of diverse technology on the silicon or some other common substrate (Fig. 1 and 2).

G. SET UP OF RIP ASSISTED MOCVD


We have setup an RIP assisted MOCVD system for the deposition of InP on silicon substrate. The system has the capability of in-situ rapid isothermal cleaning of silicon, InP and other semiconductor surfaces. A buffer layer of II-A fluorides can be deposited by RIP MOCVD system [11]. For the deposition of InP, we plan to use tertiary butyl phosphine and tri methyl indium as the precursors. In-situ surface study can be carried out by RHEED. The system will be operational by the end of next month.

It is worth mentioning here that for the similar or lower substrate temperature and smaller thermal budget, than furnace processing, the use of ultraviolet and visible photons in the rapid isothermal processing provide improved quality of materials [12]. Thus, even at lower substrate temperatures and long-time heating, RIP has advantages over furnace processing.

Fig. 1


- SUPERCONDUCTING ELECTRONICS
AND/OR
- HYBRID SEMICONDUCTOR /
SUPERCONDUCTOR ELECTRONICS

- MICROELECTRONICS
- OPTOELECTRONICS
- INTEGRATED OPTICS
- ENERGY CONVERSION
AND DETECTION DEVICES



ROLE OF EPITAXIAL FLUORIDES IN THE DEVELOPMENT OF
VARIOUS ELECTRONIC AND OPTICAL DEVICES AND CIRCUITS.

Fig. 2



**EPITAXIAL MATERIALS BASED SUPERCHIP
INTEGRATING DIVERSIFIED TECHNOLOGIES**

III. FUTURE PLANS

We propose to deposit InP on II-A fluoride/Si structure by RIP assisted MOCVD. The InP on silicon technology is of great importance, both for micro and opto electronics. As a test structure, we plan to demonstrate the feasibility of ultra high performance three terminal devices by using reduced thermal budget InP on Si technology.

REFERENCES

1. R. Singh, R.P.S. Thakur, A. Kumar, P. Chou and J. Narayan, Appl. Phys. Lett. 56, 247 (1990) and 56, 1808 (1990).
2. R. Singh, A. Kumar, R.P.S. Thakur, P. Chou, J. Narayan, A.J. Nelson and H.S. Ullal, J. Electronic Materials, 19, 481 (1990).
3. R. Singh, R.P.S. Thakur, A.J. Nelson, S.C. Gebhard, and A.B. Swartzlander, "Low Thermal Budget Solid Phase Epitaxial Growth of CaF_2 on Si (111) substrates," J. Electronic Materials, (In Press).
4. R. Singh, A. Kumar, R.P.S. Thakur, P. Chou, J. Chaudhuri, V. Gondhalekar and J. Narayan, Appl. Phys. Lett. 56, 1567 (1990).
5. R. Singh, R.P.S. Thakur, A. Kumar, P. Chou and J. Narayan, J. App. Phys. 67, 6411 (1990).
6. R. Singh and R.P.S. Thakur, "Role of In-situ Rapid Isothermal Processing in the Advanced Metallizations," Journal of the Institution of Electronics and Telecommunications Engineering, (In Press).
7. R. Singh, R.P.S. Thakur, A. Katz, A.J. Nelson, S.C. Gebhard, and A.B. Swartzlander, "Relationship Between Thermal Stress and Structural Properties of SrF_2 Films on (100) InP," Appl. Phys. Lett., (In Press).
8. F. Radpour, R. Singh, S. Sinha, A.M. Tulpule, P. Chou, R.P.S. Thakur, M. Rahmati, N.J. Hsu and A. Kumar, Appl. Phys. Lett. 54, 2479 (1989).
9. R. Singh, S. Sinha, N.J. Hsu, P. Chou, R.K. Singh and J. Narayan, J. App. Phys. 67, 1562 (1990).

10. R. Singh, S. Sinha, N.J. Hsu and P. Chou, J. Appl. Phys. 67, 3764 (1990).
11. R. Singh, S. Sinha, P. Chou, N.J. Hsu, F. Radpour, H.S. Ullal and A.J. Nelson, J. Appl. Phys. 66, 6179 (1989).
12. R. singh, S. Sinha, R.P.S. Thakur, and P. Chou, "Role of Photoeffects in Rapid Isothermal Processing," Appl. Phys. Lett., (In Review).

APPENDIX - SELECTED PUBLICATIONS