

AD-A226 202

FILE COPY

ARO 23940.8-MS

2

A Final Report  
Contract No. DAAL03-86-K-0128

July 1, 1986 - March 31, 1990

THE EFFECT OF ALLOY COMPOSITION AND  
PROCESSING ON THE STRUCTURE AND  
PROPERTIES OF I/M Al-Li-X ALLOYS

Submitted to:

U. S. Army Research Office  
P. O. Box 12211  
4300 S. Miami Boulevard  
Research Triangle Park, NC 27709

Attention:

Dr. Andrew Crowson, Program Officer  
Materials Science Division

Submitted by:

E. A. Starke  
Earnest Oglesby Professor of Materials Science  
and Dean

G. J. Shiflet  
Professor of Materials Science

Report No. UVA/525140/MS91/101  
July 1990

DTIC  
ELECTE  
AUG 31 1990  
S B D

DEPARTMENT OF MATERIALS SCIENCE

SCHOOL OF  
ENGINEERING   
& APPLIED SCIENCE

University of Virginia  
Thornton Hall  
Charlottesville, VA 22903

DISTRIBUTION STATEMENT A  
Approved for public release;  
Distribution Unlimited

**UNIVERSITY OF VIRGINIA**  
**School of Engineering and Applied Science**

The University of Virginia's School of Engineering and Applied Science has an undergraduate enrollment of approximately 1,500 students with a graduate enrollment of approximately 600. There are 160 faculty members, a majority of whom conduct research in addition to teaching.

Research is a vital part of the educational program and interests parallel academic specialties. These range from the classical engineering disciplines of Chemical, Civil, Electrical, and Mechanical and Aerospace to newer, more specialized fields of Applied Mechanics, Biomedical Engineering, Systems Engineering, Materials Science, Nuclear Engineering and Engineering Physics, Applied Mathematics and Computer Science. Within these disciplines there are well equipped laboratories for conducting highly specialized research. All departments offer the doctorate; Biomedical and Materials Science grant only graduate degrees. In addition, courses in the humanities are offered within the School.

The University of Virginia (which includes approximately 2,000 faculty and a total of full-time student enrollment of about 17,000), also offers professional degrees under the schools of Architecture, Law, Medicine, Nursing, Commerce, Business Administration, and Education. In addition, the College of Arts and Sciences houses departments of Mathematics, Physics, Chemistry and others relevant to the engineering research program. The School of Engineering and Applied Science is an integral part of this University community which provides opportunities for interdisciplinary work in pursuit of the basic goals of education, research, and public service.

THE EFFECT OF ALLOY COMPOSITION AND PROCESSING ON THE  
STRUCTURE AND PROPERTIES OF I/M Al-Li-X ALLOYS

FINAL REPORT

Submitted by:

E.A. STARKE, JR.  
Earnest Oglesby Professor of Materials Science  
and Dean

G.J. SHIFLET  
Professor of Materials Science

July 1990

U.S. ARMY RESEARCH OFFICE  
Contract Number DAAL03-86-K-0128

Department of Materials Science  
SCHOOL OF ENGINEERING AND APPLIED SCIENCE  
UNIVERSITY OF VIRGINIA  
CHARLOTTESVILLE, VIRGINIA

APPROVED FOR PUBLIC RELEASE;  
DISTRIBUTION UNLIMITED.

Report No. UVA/525140/MS91/101  
July 1990

Copy No. 23

The view, opinions, and/or findings contained in this report are those of the authors and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

SECURITY CLASSIFICATION OF THIS PAGE

## REPORT DOCUMENTATION PAGE

1a. REPORT SECURITY CLASSIFICATION Unclassified		1b. RESTRICTIVE MARKINGS	
2a. SECURITY CLASSIFICATION AUTHORITY		3. DISTRIBUTION / AVAILABILITY OF REPORT Approved for public release; distribution unlimited.	
2b. DECLASSIFICATION / DOWNGRADING SCHEDULE		4. PERFORMING ORGANIZATION REPORT NUMBER(S) UVA/525140/MS91/101	
4. PERFORMING ORGANIZATION REPORT NUMBER(S) UVA/525140/MS91/101		5. MONITORING ORGANIZATION REPORT NUMBER(S) ARO 23940.8-MS	
6a. NAME OF PERFORMING ORGANIZATION Department of Materials Science University of Virginia	6b. OFFICE SYMBOL (If applicable)	7a. NAME OF MONITORING ORGANIZATION U. S. Army Research Office	
6c. ADDRESS (City, State, and ZIP Code) University of Virginia Thornton Hall Charlottesville, VA 22901		7b. ADDRESS (City, State, and ZIP Code) P. O. Box 12211 Research Triangle Park, NC 27709-2211	
8a. NAME OF FUNDING / SPONSORING ORGANIZATION U. S. Army Research Office	8b. OFFICE SYMBOL (If applicable)	9. PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER DAAO3-86-K-0128	
8c. ADDRESS (City, State, and ZIP Code) P. O. Box 12211 Research Triangle Park, NC 27709-2211		10. SOURCE OF FUNDING NUMBERS	
		PROGRAM ELEMENT NO.	PROJECT NO.
		TASK NO.	WORK UNIT ACCESSION NO.
11. TITLE (Include Security Classification) The Effect of Alloy Composition and Processing on the Structure and Properties of I/M Al-Li-X Alloys			
12. PERSONAL AUTHOR(S) E.A. Starke, Jr., and G.J. Shiflet			
13a. TYPE OF REPORT Final	13b. TIME COVERED FROM 7/1/86 TO 3/31/90	14. DATE OF REPORT (Year, Month, Day) 1990 July	15. PAGE COUNT 14
16. SUPPLEMENTARY NOTATION The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.			
17. COSATI CODES		18. SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP	
		Aluminum lithium alloys	
		Microstructure - property relationships, and materials processing.	
19. ABSTRACT (Continue on reverse if necessary and identify by block number) The major objectives of this program were to characterize the microstructure, deformation and fracture modes of Al-Li-X alloys with emphasis on determining the relationships between alloying elements, processing parameters, microstructure, and deformation and fracture behavior. We have found that the growth mechanism of T <sub>1</sub> precipitate plates occurs by the diffusional glide of Shockley partials on (111) matrix planes and that the growth ledges migrate by the ledge-kink mechanism. Plastic deformation prior to aging was shown to decrease the T <sub>1</sub> plate length and thickness, increase the number density by almost two orders of magnitude, increase the yield strength by 100 MPa while simultaneously reaching peak strength in 20% of the time required without plastic deformation. Plastic deformation prior to aging was shown to have a similar effect on S' precipitation in Al-Cu-Li alloys containing Mg; however, the deformation			
20. DISTRIBUTION / AVAILABILITY OF ABSTRACT <input checked="" type="checkbox"/> UNCLASSIFIED/UNLIMITED <input type="checkbox"/> SAME AS RPT. <input type="checkbox"/> DTIC USERS		21. ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a. NAME OF RESPONSIBLE INDIVIDUAL		22b. TELEPHONE (Include Area Code)	22c. OFFICE SYMBOL

Continuation of 19.

does not affect the size or fraction of grain boundary precipitates. Plastic deformation prior to aging primarily affects the aging kinetics of the strengthening phase, leading to an improved yield strength/ductility combination at peak strength when compared with material that is not given pre-age plastic deformation. The icosahedral  $T_2$  phase formed at aging temperatures above 170°C. Since this phase decreases the fracture resistance, aging temperatures below 170°C are preferred for Al-Li-Cu alloys.

<b>Accession For</b>	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist.	Avail and/or Special
A-1	



## TABLE OF CONTENTS

I.	Abstract	1
II.	Introduction	2
III.	Accomplishments	
	A. Heterogeneous Precipitation and Mechanical Properties in Al-Li-Cu Alloys	3
	B. Heterogeneous Precipitation and Mechanical Properties in Al-Li-Cu-Mg Alloys	7
	C. Role of Vacancies on the Precipitation Processes in Zr-Modified Aluminum Alloys	9
IV.	List of Personnel Supported Under U.S. Army Research Office Sponsorship	10
V.	List of Theses Completed Under U.S. Army Research Office Sponsorship	10
VI.	List of Publications Under U.S. Army Research Office Sponsorship	10
VII.	References	13

THE EFFECT OF ALLOY COMPOSITION AND PROCESSING ON THE  
STRUCTURE AND PROPERTIES OF I/M Al-Li-X ALLOYS

I. ABSTRACT

The major objectives of this program were to characterize the microstructure, deformation and fracture modes of Al-Li-X alloys with emphasis on determining the relationships between alloying elements, processing parameters, microstructure, and deformation and fracture behavior. We have found that the growth mechanism of  $T_1$  precipitate plates occurs by the diffusional glide of Shockley partials on (111) matrix planes and that the growth ledges migrate by the ledge-kink mechanism. Plastic deformation prior to aging was shown to decrease the  $T_1$  plate length and thickness, increase the number density by almost two orders of magnitude, increase the yield strength by 100 MPa while simultaneously reaching peak strength in 20% of the time required without plastic deformation. Plastic deformation prior to aging was shown to have a similar effect on  $S'$  precipitation in Al-Cu-Li alloys containing Mg; however, the deformation does not affect the size or fraction of grain boundary precipitates. Plastic deformation prior to aging primarily affects the aging kinetics of the strengthening phase, leading to an improved yield strength/ductility combination at peak strength when compared with material that is not given pre-age plastic deformation. The icosahedral  $T_2$  phase formed at aging temperatures above 170°C. Since this phase decreases the fracture resistance, aging temperatures below 170°C are preferred for Al-Li-Cu alloys.

## II. INTRODUCTION

High strength aluminum alloys are used for many types of Army air and ground transportation systems. A significant need exists to reduce weight in these systems in order to realize subsequent reduction in fuel use and cost. This need, combined with the constant demand for critical property improvement of materials used for these applications, are the basis for the active interest in Al-Li alloys (1-5). The addition of lithium to an aluminum alloy results in a six percent increase in the elastic modulus and a three percent decrease in density for each weight percent of lithium added to the alloy. The lower density aluminum-lithium alloys provide an alternative to the conventional 2XXX and 7XXX alloys currently being used in transportation structures. Furthermore, the successful history of aluminum alloys in transportation structures favors these low density alloys over polymeric and metal matrix composite structures. Like all alternatives, however, there are disadvantages as well as advantages and early Al-Li-Cu alloys had the disadvantage of low ductility and fracture toughness as well as production difficulties. Extensive research of Al-Li-X systems, that began in the early 1970's, has provided numerous breakthroughs in our understanding of these complex alloys and has led to the development of a number of commercially viable aluminum-lithium products.

This document is our Final Report on U.S. Army Contract Number DAAL03-86-K0128, "The Effect of Alloy Composition and

Processing on the Structure and Properties of I/M Al-Li-X Alloys". The major objectives of this program have been to characterize the microstructure, deformation, and fracture modes of Al-Li-X alloys with emphasis on determining the relationships between the alloying elements, processing parameters, microstructure, and deformation and fracture behavior. The research results obtained on this program should aid in the development of Al-Li alloys having density, strength, stiffness, and ductility combinations needed for high performance transportation systems. The results have already aided in the modification of processing of 8090 so that it could be used successfully in a system constructed by Lockheed Missiles and Space Company for the United States Government. Processing procedures developed under this research program have been adopted by the commercial producers of Al-Li alloys.

### III. ACCOMPLISHMENTS

A. **Heterogeneous Precipitation and Mechanical Properties in Al-Li-Cu Alloys:** From the experimental work performed during this study of heterogeneous precipitation in an Al-2.4Li-2.4Cu-0.18Zr alloy the following conclusions may be drawn:

1. A single plate shaped precipitate phase ( $T_1$ ) is observed in the microstructure on aging for various times at 190°C. The  $T_1'$  phase previously reported (6-8) does not exist. This finding is based on the fact that the anomalous diffraction behavior observed by these investigators can be explained in terms of the  $T_1$  structure.

2. Analysis of structure images shows that the  $T_1$  unit cell is hexagonal with the reported cell parameters (9). Comparison of images with computer simulations based on the recently proposed atom positions (10) reveals that the chemical compositions of the individual (0001) planes within this cell are essentially correct. However, the placement of atoms on sites within planes apparently require further adjustments.

3.  $T_1$  precipitate plates and material of stoichiometric  $T_1$  composition ( $Al_2CuLi$ ) both contain stacking defects on (0001) planes. The presence of compositional defects (i.e. stacking of wrong chemical layers) has been shown to occur in the precipitate plates. Evidence also exists for displacement (i.e.,  $1/6(112)$ ) faulting between (0001) layers. Both types of faulting could conceivably cause the anomalous diffraction behavior observed for thick  $T_1$  plate shaped precipitates.

4. Stretching the solutionized material prior to aging at  $190^\circ C$  can result in a 20-25% increase in observed yield stress at peak strength depending on the extent of the cold work.

5. Relative alloy strength is directly related to the  $T_1$  volume fraction. Material stretched 4-8% will reach its peak strength 4-5 times faster than unstretched material.

6. The  $\delta'$  formation kinetics are not significantly affected by enhanced  $T_1$  precipitation in stretched material.

7. Stretching greatly increases the number of dislocation nucleation sites available for  $T_1$  formation as evidenced by a large increase in  $T_1$  number density. Material

stretched 8% has approximately a two order of magnitude increase in  $T_1$  number density over unstretched material.

8. Shorter average plate lengths are observed in stretched material. This is a result of a more rapid decrease in matrix supersaturation caused by a greater number of growing plates. Also, the number of interacting plates on two or more variants increases with stretch level (i.e., plate intersections and impingement points).

9. Stretching tends to produce thinner plates on average than unstretched material. Again, this finding is related to the rate at which supersaturation is removed from the matrix. The nucleation of new growth ledges which thicken the plates depends on matrix supersaturation. Plate thickening continues after the matrix supersaturation is used up (coarsening), but at a slower rate.

10. Preaging material after stretching 6% for 24 hours at 50°C was found to produce a significant amount of  $T_1$  prior to aging. The material would subsequently reach peak strength on aging at 190°C more quickly than material stretched 6% but not preaged. However, preaging probably does not significantly influence the peak aged yield stress between the two conditions.

11. The nucleation and growth of  $T_1$  plates proceed by the proposed mechanism of dissociation of matrix dislocations into partials  $(1/6(112))$  which form the growth interface of the plate and plate ledges (11).

12. Analysis of structure images reveals that the

initial nucleation of  $T_1$  plates produces a five layer (0001) HCP plate, and subsequent plate thickening is accomplished by growth ledges which add four new layers of  $T_1$  material on their passage across the broad face of the plate. In the absence of compositional faulting, the plates are always observed to consist of an odd number of (0001) layers.

13. Of the three chemical layers observed in the  $T_1$  cell, the C layer (2:1, Al:Li) is always observed to be the interfacial layer. This suggests a lower interfacial energy for the C layer than that which would result from the A and B chemical layers.

14.  $T_1$  plate nucleation can be modeled on the dissociation of a dislocation on opposite sides of a jog (or cross-slipped screw segment) one or two 111 planes high. Such dissociation will explain all of the observed characteristics of the  $T_1$  plates. The transformation produces a five layer HCP plate by the coupling of partials on these layers, and the model can produce either perfect or imperfect stacking with displacement faults.

15. The influence of stretching will not only increase the number of dislocations, but also the number of dislocation jogs. The model of  $T_1$  nucleation at jogs is, therefore, consistent with experimental observations derived from the plate distributions.

16.  $T_2$  is the dominate grain boundary precipitate produced in 2090 type alloys in the temperature range 200-520°C.

The  $\delta$  phase reported to occur (12) is not observed at any aging temperature or time studied. The  $\delta'$  PFZs observed in material containing  $\delta'$  are a result of the precipitation of the more stable  $T_2$  phase at grain boundaries.

17. Mixed  $T_2$  and R phase precipitation is observed at grain boundaries in material aged for various times between 150-190°C. Again, the  $\delta$  phase is not observed.

18.  $T_2$  has been determined in this investigation to be an icosahedral quasicrystal and to form by nucleation and growth as a solid-solid phase transformation.

The practical applications of this study are many. From a fracture toughness point of view, we have found that the  $T_2$  phase is responsible for most of the undesirable fracture characteristics, and its formation should be discouraged. Similarly, the desirable strengthening component added by enhanced  $T_1$  precipitation should be encouraged. Consequently, the best recommended treatment for optimizing properties of 2090-type alloys is to solutionize the material, quench, stretch between 4 and 6 percent, and subsequently age between 120-150°C to obtain the desired strength. Preaging at temperatures of 40-60°C for approximately 24-48 hours prior to higher temperature aging has some advantages for particular property enhancement.

**B. Heterogeneous Precipitation and Mechanical Properties in Al-Li-Cu-Mg Alloys:** From the experimental work performed during this study of heterogeneous precipitation in an Al-2.58Li-1.36Cu-0.89Mg-0.12Zr alloy the following conclusions may

be drawn:

1. S' precipitates may nucleate on the  $\delta'$ /matrix interface. Because of the negligible misfit between the matrix and  $\delta'$ , this interface would not be expected to serve as a favorable site for S' nucleation. However, during the growth of  $\delta'$  ( $\text{Al}_3\text{Li}$ ) excess Cu and Mg concentrations occur at the growth front. This coupled with the excess vacancies released when Li adds to the  $\delta'$  particle result in favorable conditions for S' nucleation.

2. S' also nucleates on matrix dislocations which may be induced by stretching after quenching, or on subgrain boundaries which may be present in unrecrystallized structures. Growth of the precipitates occurs by a ledge mechanism.

3. The cluster nucleation mechanism, which has been observed for S' in Al-Cu-Mg alloys, does not occur. This might be due to the high binding energy of Li to vacancies (13) which prevents supersaturation and collapse of the vacancy clusters to loops and subsequent dislocation climb to helices (14) which favor cluster formation sites.

4. Detailed inspection of atomic resolution micrographs, from alloys with and without Li, did not reveal two types of S-type precipitates (i.e. S and S'). This result reinforces the statement by Gregson and Flower (15) that unless a difference is noted between S and S', the notation should be dropped.

5. Deformation prior to aging of 8090-type alloys has an effect on S' precipitation similar to that observed for  $T_1$  precipitation in 2090-type alloys; i.e. the number density of S'

precipitates is increased, the aging kinetics are enhanced, the size of  $S'$  at peak strength is reduced, and the obtainable peak strength is increased by deformation.

6. Deformation prior to aging does not appear to have a significant effect on the size or volume fraction of grain boundary precipitates as a function of aging time. However, since the stretch does have a significant effect on the aging kinetics of the matrix precipitates, peak strength is reached at earlier times in stretched material resulting in reduced size and volume fraction of grain boundary precipitates and thus an improved yield strength/ductility combination.

**C. Role of Vacancies on the Precipitation Processes in Zr-Modified Aluminum Alloys:** From the experimental results from this aspect of our program we may draw the following conclusions:

1. Trace additions of Zr to an Al-Zn-Mg alloy retards GP zones and  $\eta'$  formation, slows down  $\eta$  precipitation, and inhibits T phase nucleation.

2. An excess loss of vacancies to subgrain boundary sinks together with the modification in the distribution of free vacancies in solution are responsible for the effects mentioned in 1.

3. The distribution of free vacancies in solution are affected by the Zr-vacancy binding prior to quenching, and by the positive  $\beta'/\alpha$  misfit associated with the coherent  $\beta'$  precipitates during aging.

**IV. LIST OF PERSONNEL SUPPORTED UNDER U.S. ARMY RESEARCH OFFICE SPONSORSHIP**

1. T. Ahrens, Post Doctoral Fellow in Materials Science
2. W.A. Cassada, Ph.D. Student in Materials Science
3. A.K. Mukhopadhyay, Post Doctoral Fellow in Materials Science
4. G.S. Shiflet, Professor of Materials Science
5. R.J. Sinko, M.S. Student in Materials Science
6. E.A. Starke, Jr., Oglesby Professor of Materials Science

**V. LIST OF THESES COMPLETED UNDER U.S. ARMY RESEARCH OFFICE SPONSORSHIP**

1. William A. Cassada, "Heterogeneous Precipitation in Al-Li-Cu Alloys," PhD Thesis, University of Virginia, May, 1987.
2. Robert J. Sinko, "The Effect of Plastic Deformation on S' Nucleation and Growth in an Al-Li-X Alloy, M.S. Thesis, University of Virginia, May, 1989.

**VI. LIST OF PUBLICATIONS UNDER U.S. ARMY RESEARCH OFFICE SPONSORSHIP**

1. W.A. Cassada, G.J. Shiflet and E.A. Starke, Jr., "Grain Boundary Precipitates with Five-Fold Diffraction Symmetry in an Al-Li-Cu Alloy", Scripta Met. Vol. 20, 1986, pp. 751-756.
2. R.F. Ashton, D.S. Thompson, E.A. Starke, Jr., and F.S. Lin, "Processing Al-Li-Cu-(Mg) Alloys," Aluminum-Lithium Alloys III, eds. C. Baker, P.J. Gregson, S.J. Harris and C.J. Peel, The Institute of Metals, London, 66-77 (1986).
3. W.A. Cassada, G.J. Shiflet and S.J. Poon, "Formation of an Icosahedral Phase by Solid-State Reaction", Phys. Rev.

- Letters, Vol. 56, 1986, pp. 2276-2279.
4. W.A. Cassada, Y. Shen, S.J. Poon, and G.J. Shiflet, "Mg<sub>32</sub>(Zn,Al)<sub>49</sub>-type Icosahedral Quasicrystals Formed by Solid-State Reaction and Rapid Solidification", Phys. Rev. B, Vol. 34, 1986, pp. 7413-7416.
  5. W.A. Cassada, G.J. Shiflet, and E.A. Starke, Jr., "Characterization of Two Grain Boundary Precipitates in Al-Li-Cu Alloys with Electron Micro-Diffraction," in Aluminum Alloys: Their Physical and Mechanical Properties, eds. E.A. Starke, Jr., and T.H. Sanders, Jr., EMAS Ltd., West Midlands, England, 1986, pp. 695-710.
  6. W.A. Cassada, G.J. Shiflet and E.A. Starke, Jr., "Electron Diffraction Studies of Al<sub>2</sub>CuLi (T<sub>1</sub>) Plates in an Al-2.4Li-2.4Cu-0.18Zr Alloy", Scripta Met. Vol 21, 1987, pp. 387-392.
  7. Y. Shen, S.J. Shen, W. Dmowski, T. Egami and G.J. Shiflet, "Structure of Al-Li-Cu Icosahedral Crystals and Penrose Tiling", Phys. Rev. Letters, Vol. 58, 1987, p. 1440.
  8. W.A. Cassada, G.J. Shiflet and E.A. Starke, Jr., "The Effect of Plastic Deformation on T1 Precipitation", Aluminum-Lithium IV, eds. G. Champier, B. Dubost, D. Miannay, L. Sabetay, Les Additions de Physique, Les Ulis, France, 1987, p. C3-397.
  9. R.E. Lewis, E.A. Starke, Jr., W.C. Coons, G.J. Shiflet, E. Willner, J.G. Bjeletich, C.H. Mills, R.M. Harrington and D.N. Petrakis, "Microstructure and Properties of Al-Li-Cu-Mg-Zr (8090) Heavy Sections Forgings," Aluminum-Lithium IV, eds. G.

- Champier, B. Dubost, D. Miannay, L. Sabetay, Les Additions de Physique, Les Ulis, France, 1987, p. C3-643-652.
10. W.A. Cassada, G.J. Shiflet and S.J. Poon, " Quasicrystalline Grain Boundary Precipitates in Aluminum Alloys Through Solid-Solid Transformations", J. of Microscopy, Vol. 146, 1987, pp. 323-335.
  11. R.J. Sinko, T. Ahrens, G.J. Shiflet and E.A. Starke, Jr., "Effect of Stretch on Nucleation and Growth of S' in an 8090 Al-Li Alloy", in Aluminum-Lithium Alloys V, eds. T.H. Sanders, Jr., and E.A. Starke, Jr., MCEP Ltd., Birmingham, England, 1989, pp. 375-384.
  12. T. Ahrens and E.A. Starke, Jr., "Effect of Stretch on Grain Boundary Precipitation in 8090", in Aluminum-Lithium Alloys V, eds. T.H. Sanders, Jr. and E.A. Starke, Jr., MCEP Ltd., Birmingham, England, 1989, pp. 385-396.
  13. T.H. Sanders, Jr. and E.A. Starke, Jr., "The Physical Metallurgy of Aluminum-Lithium Alloys - A Review", in Aluminum- Lithium Alloys V, eds. T.H. Sanders, Jr. and E.A. Starke, Jr., MCEP Ltd., Birmingham, England, 1989, pp. 1-40.
  14. V. Radmilovic, G. Thomas, G.J. Shiflet, and E.A. Starke, Jr., "On the Nucleation and Growth of Al<sub>2</sub>CuMg (S') in Al-Li-Cu-Mg and Al-Cu-Mg Alloys", Scripta Met. Vol. 23, 1989, pp. 1141-1146.
  15. A.K. Mukhopadhyay, G.J. Shiflet and E.A. Starke, Jr., "Role of Vacancies on the Precipitation Processes in Zr Modified Aluminum Based Alloys", Scripta Met. Vol. 24, 1990, pp.

307-312.

16. W.A. Cassada, G.J. Shiflet and E.A. Starke, Jr., "Mechanism of  $T_1$  Nucleation and Growth", Metallurgical Transactions A, in press.
17. W.A. Cassada, G.J. Shiflet and E.A. Starke, Jr., "The Effect of Plastic Deformation on  $T_1$  Precipitation", Metallurgical Transactions A, in press.

#### VII. REFERENCES

1. T.H. Sanders, Jr. and E.A. Starke, Jr., eds., Aluminum-Lithium Alloys - Proceedings of the First International Aluminum-Lithium Conference, The Metallurgical Society of AIME, Warrendale, PA, 1981.
2. E.A. Starke, Jr. and T.H. Sanders, Jr., eds., Aluminum-Lithium Alloys II - Proceedings of the Second International Aluminum-Lithium Conference, The Metallurgical Society of AIME, Warrendale, PA, 1984.
3. C. Baker, P.J. Gregson, S.J. Harris and C.J. Peel, eds., Aluminum-Lithium Alloys III - Proceedings of the Third International Aluminum-Lithium Conference, The Institute of Metals, London, 1986.
4. G. Champier, B. Dubost, D. Miannay and L. Sabetay, eds., 4th International Aluminum Lithium Conference, Journal de Physique, Paris, 1987.
5. T.H. Sanders, Jr. and E.A. Starke, Jr., eds., Aluminum-Lithium Alloys V - Proceedings of the Fifth International

- Aluminum-Lithium Conference, MCEP Ltd., Birmingham, England, 1989.
6. H. Suzuki, M. Kanno and N. Hayashi, J. Japan Inst. Metals, Vol. 32, 1982, p. 88.
  7. R.J. Rioja and E.A. Ludwiczak, Aluminum-Lithium Alloys III, The Institute of Metals, London, 1986, p. 471.
  8. A.K. Eikum and G.H. Narayanan, Proceedings of the 44th Annual Meeting of the Electron Microscopy Society of America, San Francisco Press, Inc., 1986.
  9. H.K. Hardy and J.M. Silcock, J. Inst. Metals, Vol. 84, 1955-56, p. 423.
  10. J.C. Haung and A.J. Ardell, Aluminum-Lithium Alloys III, The Institute of Metals, London, 1986, p. 455.
  11. B. Noble and G.E. Thompson, Metal Sci. J., Vol. 6, 1972, p. 167.
  12. M.H. Tosten, A.K. Vasudevan and P.R. Howell, Aluminum-Lithium Alloys III, The Institute of Metals, London, 1986, p. 483.
  13. S. Ceresara, A. Giarda and A. Sanchez, Phil. Mag., Vol. 35, 1977, p. 97.
  14. G. Thomas and M.J. Whelan, Phil. Mag., Vol. 4, 1959, p. 511.
  15. P.J. Gregson and H.M. Flower, Acta Met., Vol. 33, 1985, p. 527.

DISTRIBUTION LIST

- 1 - 50 U. S. Army Research Office  
P. O. Box 12211  
4300 S. Miami Boulevard  
Research Triangle Park, NC 27709
- Attention: Dr. Andrew Crowson, Program Officer  
Materials Science Division
- 51 Dr. Andrew Crowson, Program Officer  
Materials Science Division  
U. S. Army Research Office  
P. O. Box 12211  
4300 S. Miami Boulevard  
Research Triangle Park, NC 27709
- \* Office of Naval Research Resident Representative  
2135 Wisconsin Avenue, N. W., Suite 102  
Washington, DC 20007
- Attention: Mr. Michael McCracken  
Administrative Contracting Officer
- 52 -53 E. A. Starke, Jr., MS
- 54 G. J. Shiflet, MS
- 55 T. H. Courtney, MS
- 56 - 57 E. H. Pancake, Clark Hall
- 58 SEAS Preaward Administration Files

\*Cover letter

JO#3318:ph