

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188



Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)	2. REPORT DATE 1990	3. REPORT TYPE AND DATES COVERED Final Report- 1 Mar 86 - 28 Feb 89
----------------------------------	------------------------	--

4. TITLE AND SUBTITLE Structure and Properties of Titanium Nitride Strengthened Microlaminate Metal Matrix Composites	5. FUNDING NUMBERS DAAL03-86-G-0062
--	--

6. AUTHOR(S) J. Michael Rigsbee	8. PERFORMING ORGANIZATION REPORT NUMBER ARO 23805.2-MS-F
------------------------------------	--

7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Univ. of Illinois at Urbana-Champaign Urbana, IL 61801	9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709-2211
---	---

SDTIC
ELECTE
OCT 24 1990
D

11. SUPPLEMENTARY NOTES The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.	12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.	12b. DISTRIBUTION CODE
---	--	------------------------

13. ABSTRACT (Maximum 200 words) Microlaminate composites with two-dimensional strengthening have been successfully fabricated using reactive ion plating and hot pressing. The composite materials have been mechanically tested and characterized structurally and chemically. It has been observed that these laminate composites can be carefully designed to exhibit strengthening much greater than that predicted by the simple rule-of-mixtures and still maintain reasonable ductility. However, composite strengthening is limited by reinforcement precracking, diffusion bond delamination, and matrix/reinforcement reaction.

Continued on reverse side

14. SUBJECT TERMS Titanium Nitride, Composites, Microlaminate Composites, Reactive Ion Plating, Ion Plating, Metal Matrix Composites	15. NUMBER OF PAGES 6		
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL

14. SUBJECT TERMS Titanium Nitride, Composites, Microlaminate Composites, Reactive Ion Plating, Ion Plating, Metal Matrix Composites	15. NUMBER OF PAGES 6	16. PRICE CODE
---	--------------------------	----------------

AD-A228 279

From the results of this research, a fundamental understanding of these engineered composite materials has been developed and specifically the relationships between: 1) ion plating and vacuum hot press processing parameters; 2) microstructure and microchemistry of the composite and interfaces; and 3) mechanical behavior and the micromechanics of deformation and fracture.

(47)

STRUCTURE AND PROPERTIES OF TITANIUM NITRIDE
STRENGTHENED MICROLAMINATE METAL MATRIX COMPOSITES

JOHN HOWARD GIVENS
B.S., University of Illinois, 1985
M.S., University of Illinois, 1989

THESIS

Submitted in partial fulfillment of the requirements
for the degree of Doctorate of Philosophy in Metallurgical Engineering
in the Graduate College of the
University of Illinois at Urbana-Champaign, 1990

PROGRAM SUMMARY

This investigation examined the structure and properties of titanium nitride strengthened microlaminate metal matrix composites. Reactive ion plated titanium nitride (TiN) was deposited onto titanium, nickel, and aluminum foils which were subsequently hot pressed to form microlaminate composites. The TiN volume percent was varied and its effect upon the structure and properties of the composites investigated. Scanning electron microscopy (SEM), cross-sectional transmission electron microscopy (TEM) and scanning Auger electron spectroscopy (AES) have been used to characterize the film morphology, the fracture behavior of the composites, and the nature of the metal/ceramic interfaces formed during reactive ion plating and hot pressing. The mechanical properties (ultimate tensile strength, strain-to-failure and elastic modulus) of the microlaminate composites were determined by tensile testing specimens machined from the hot pressed composites.

The TiN strengthened Al matrix microlaminate composites exhibited poor mechanical properties due to reinforcement precracking (due to thermal expansion mismatch and weak intercolumnar boundary

strength of TiN film) and poor diffusion bonding both of which promoted failure of the hot pressed metal/ceramic interface at low applied loads. TEM examination of the Al/TiN composite interfaces showed the ion plated interface to be fully dense and continuous while the hot pressed interface exhibited porosity and mechanical interlocking of the Al and TiN surfaces (poor bonding). Interfacial modification of the Al-TiN hot pressed bond by the addition of a Ti film overlayer ion plated on the TiN film improved the mechanical behavior of the TiN strengthened Al matrix composite, by increasing the interfacial adherence between the Al matrix and TiN film reinforcement.

The TiN strengthened Ni matrix microlaminate composites exhibited strengths predicted by rule-of-mixtures calculations (ROM) which indicated that sufficient bonding between the TiN reinforcement and Ni matrix was present to allow the transfer of the applied load from the matrix to the reinforcement. XTEM analysis of the Ni/TiN composite interfaces showed both the ion plated and hot pressed interfaces to be well adhered and continuous. The addition of a Ti film overlayer ion plated on the TiN film improved the strength of the composite by altering the nature of the interfaces present as a result of the formation of the Ni_3Ti intermetallic phase.

The TiN strengthened Ti matrix microlaminate composites exhibited strengths greater than that predicted by rule-of-mixtures calculations while maintaining some ductility. However, after the initial few volume percent of TiN, the mechanical response of the composites diminished due to the increased crack sensitivity of the Ti matrix and the delamination of the interface region both of which are the result of the dissolution of the TiN film by the Ti matrix during the hot pressing procedure. The delamination of the interface region is greatly assisted by the connectivity of voids present in the dissolved TiN zone. TEM examination of the Ti/TiN composite interfaces showed the dissolution of the TiN film by the Ti matrix, the reduction of TiN to Ti_2N and Ti, and the presence of voids in the transformed film region due to the diffusion of nitrogen from the film to the matrix.

RESEARCH CONCLUSIONS

Microlaminate composites with two-dimensional strengthening have been successfully fabricated using reactive ion plating and hot pressing. The composite materials have been mechanically tested and characterized structurally and chemically. It has been observed that these laminate composites can be carefully designed to exhibit strengthening much greater than that predicted by the simple rule-of-mixtures and still maintain reasonable ductility. However, composite strengthening is limited by reinforcement precracking, diffusion bond delamination, and matrix/reinforcement reaction.

From the results of this research, a fundamental understanding of these engineered composite materials has been developed and specifically the relationships between: 1) ion plating and vacuum hot press processing parameters; 2) microstructure and microchemistry of the composite and interfaces; and 3) mechanical behavior and the micromechanics of deformation and fracture. Based upon the work of this research program the following statements have been outlined:

1. Ion plating is an effective technique for producing novel metal/ceramic microlaminate composite materials by virtue of its ability to deposit controlled volume percents of film reinforcement and produce highly adherent interfaces.

The ion plating process can deposit a metal overlayer (Ti) on the ceramic film reinforcement (TiN) thereby changing the bonding characteristics of the various microlaminate composites.

2. The ion plated interfaces and hot pressed interfaces differ structurally and chemically as shown by XRD, AES, and XTEM analysis.

The ion plated interface was shown to be fully dense and continuous along the film/matrix (e.g. TiN/Al) and

film/film (Ti/TiN) interfaces. The hot pressed Al-TiN interface was shown by XTEM to be very irregular and contain internal flaws and voids.

3. The mechanical integrity of the hot pressed bonds of these composites is very sensitive to the interdiffusion characteristics of the materials to be joined and the resulting interfacial defects.

XTEM analysis of the Al/TiN-Al and Ni/TiN-Ni composites revealed that the Al-TiN hot pressed interface consisted of a mechanical bonding which resulted in the non-existent strengthening effect imparted by the TiN to the Al and that the Ni-TiN interface was well adhered and continuous which was reflected in the TiN strengthening of the Ni matrix.

4. The laminate structure provided favorable strengthening while maintaining reasonable ductility. When failure occurred, it was a complicated mixed-mode failure involving such fracture mechanisms as brittle fracture of the filler, necking of the matrix, delamination along the hot pressed and ion plated interfaces, cracking of the reinforcement, and secondary crack initiation and propagation.
5. The mechanical behavior of these microlaminate materials does not conform to a conventional theory such as "rule-of-mixtures" but this theory does give a lower bound approximation.

The fundamental knowledge gained from the examination of these specific composites leads to the following basic conclusions for composite materials.

- Processing techniques can be optimized for the desired material characteristics.

Careful choice of composite materials: Ni/TiN-Ti

- Modification of the nature of the composite interfaces is directly observed by the mechanical response of the composite material.

Addition of Ti film overlayer: Al/TiN/Ti-Al

- Interface reactions between the matrix and reinforcement can enhance or reduce the physical properties of the composite.

Extent of reaction layer: Ni/Ti-Ni and Ni/TiN/Ti-Ni

- Chemical compatibility between the matrix and reinforcement is critical for proper composite properties.

Dissolution of reinforcement: Ti/TiN-Ti

Accession For	
NTIS GRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By _____	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	0

PUBLICATIONS

J. H. Givens and J. M. Rigsbee, "Metal Matrix Composites: Titanium Nitride Films as Microlaminate Reinforcements," R. B. Bhagat, et al, eds., Metal & Ceramic Matrix Composites: Processing, Modeling and Mechanical Behavior (Warrendale, PA: The Minerals, Metals and Materials Society, 1990), 587-596.

J. H. Givens, W. J. Croisant, H. S. Savage, R. T. Carson, and J. M. Rigsbee, "Characterization of Titanium Nitride Films Deposited by Reactive Ion Plating," To be published in Proceedings of the Symposium on Ceramic Thin and Thick Films; Presented at the annual meeting of the American Ceramic Society, Indianapolis, IN, April 23-27, 1989.

J. H. Givens and J. M. Rigsbee, "Structure and Properties of Titanium Nitride Strengthened Microlaminate Composites," T. S. Sudarshan and D. G. Bhat, eds., Surface Modifications Technologies II, 1989 (Warrendale, PA: The Minerals, Metals and Materials Society, 1989), 203-214; Presented at Proceedings of Second International Conference on Surface Modification Technologies during TMS Fall meeting, Chicago, IL, September 26-28, 1988.

V. H. Hock, J. H. Givens, J. E. Suarez, and J. M. Rigsbee, "Structure, Chemistry and Properties of Mixed Metal Oxides," Corrosion 88, Paper Number 230.

V. F. Hock, J. H. Givens, J. E. Suarez and J. M. Rigsbee, "Developments in Electrically Conductive Oxide Coatings for Cathodic Protection Anodes," Published in Proceedings of Pacific Corrosion 87 Conference, Melbourne, Australia, 1987.

Y. W. Lee, M. C. Yoo, J. H. Givens, M. Metzger, J. M. Rigsbee, V. F. Hock, L. D. Stephenson, N. A. Sicilian, and W. J. Croisant, "Adhesion and Corrosion Properties of Ion Plated TiN," IPAT 87, 249-251.

V. F. Hock, L. D. Stephenson, J. H. Givens, and J. M. Rigsbee, "Fabrication of Electrically Conductive Metal Oxide Coatings by Reactive Ion Plating," J. Vac Sci Tehnol, 3(6)(1985), 2661-2664.