

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE

AD-A236 596

1a REPORT SECURITY CLASSIFICATION Unclassified		1b RESTRICTED	
2a SECURITY CLASSIFICATION SELECTED		3 DISTRIBUTION STATEMENT	
2b DECLASSIFICATION/DOWNGRADING DATE JUN 13 1991		4 PERFORMING ORGANIZATION REPORT NUMBER(S)	
6a NAME OF PERFORMING ORGANIZATION Dept. of Chemistry Cornell University		6b OFFICE SYMBOL (If applicable)	
7a NAME OF MONITORING ORGANIZATION Office of Naval Research		7b ADDRESS (City, State, and ZIP Code) Chemistry Program 800 N. Quincy Street Alexandria, VA 22217	
8a NAME OF FUNDING/SPONSORING ORGANIZATION Office of Naval Research		8b OFFICE SYMBOL (If applicable)	
9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER N00014-91-J-1269		10 SOURCE OF FUNDING NUMBERS	
8c ADDRESS (City, State, and ZIP Code) Chemistry Program 800 N. Quincy St. Alexandria, VA 22217		PROGRAM ELEMENT NO	PROJECT NO
		TASK NO	WORK UNIT ACCESSION NO
11 TITLE (Include Security Classification) Unclassified: The Structure of Ta_3N_5 at 16K by Time-of-Flight Neutron Diffraction			
12 PERSONAL AUTHOR(S) Nathaniel Brese, Michael O'Keeffe, Paul Rauch, and Francis DiSalvo			
13a TYPE OF REPORT Technical rpt #10	13b TIME COVERED FROM 1990 TO 1993	14 DATE OF REPORT (Year, Month, Day) May 30, 1991	15 PAGE COUNT
16 SUPPLEMENTARY NOTATION			
17 COSATI CODES		18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)	
FIELD	GROUP	SUB-GROUP	
		Nitrides	
		Structure Refinement	
19 ABSTRACT (Continue on reverse if necessary and identify by block number)			
Polycrystalline Ta_3N_5 has been prepared from the reaction of $TaCl_5$ with ammonia, and its structure has been refined from time-of-flight neutron diffraction data. $M_r = 612.88$, orthorhombic, $Cmcm$, $a = 3.8862(1) \text{ \AA}$, $b = 10.2118(2) \text{ \AA}$, $c = 10.2624(3) \text{ \AA}$, $v = 407.26(3) \text{ \AA}^3$, $D_x = 9.99 \text{ g cm}^{-3}$, neutron time-of-flight, Rietveld refinement, wR_p, R_p, reduced $\chi^2 = 0.061, 0.043, 4.21$ for data collected at 16 K. Ta_3N_5 crystallizes with the pseudobrookite (Fe_2TiO_5) structure. Irregular TaN_6 octahedra share edges and corners.			
20 DISTRIBUTION/AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☒ SAME AS RPT ☐ DTIC USERS		21 ABSTRACT SECURITY CLASSIFICATION Unclassified	
22a NAME OF RESPONSIBLE INDIVIDUAL Dr. Mark Rosb		22b TELEPHONE (Include Area Code) 202-696-4409	22c OFFICE SYMBOL

Previous editions are obsolete

SECURITY CLASSIFICATION OF THIS PAGE

S/N 0102-LF-014-6603

91-01802



91 0 11 081

The Structure of Ta_3N_5 at 16K
by Time-of-Flight Neutron Diffraction

Nathaniel Brese, Michael O'Keeffe,
Department of Chemistry
Arizona State University
Tempe, AZ 85287-1604 USA

Paul Rauch and Francis DiSalvo
Baker Laboratory
Department of Chemistry
Cornell University
Ithaca, NY 14853 USA

Abstract:

Polycrystalline Ta_3N_5 has been prepared from the reaction of TaCl_5 with ammonia, and its structure has been refined from time-of-flight neutron diffraction data. $M_r = 612.88$, orthorhombic, $Cmcm$, $a = 3.8862(1) \text{ \AA}$, $b = 10.2118(2) \text{ \AA}$, $c = 10.2624(3) \text{ \AA}$, $V = 407.26(3) \text{ \AA}^3$, $D_x = 9.99 \text{ g cm}^{-3}$, neutron time-of-flight, Rietveld refinement, wR_p , R_p , reduced $\chi^2 = 0.061$, 0.043 , 4.21 for data collected at 16 K. Ta_3N_5 crystallizes with the pseudobrookite (Fe_2TiO_5) structure. Irregular TaN_6 octahedra share edges and corners.

Acta Cryst. C ^{accepted} ~~in press~~ A few changes after
review.

Introduction:

Several authors have mapped out the phase diagram of the Ta-N system (Brauer & Zapp, 1954; Schönberg, 1954b). γ -Ta₂N crystallizes with close-packed metal atoms; the nitrogen atoms fill the octahedral sites. ϵ -TaN has the B35 structure-type which consists of very densely packed metal atoms; nitrogen atoms fill deformed octahedral holes (Brauer & Zapp, 1953; Christensen & Lebech, 1978). Ta₄N₅ and Ta₅N₆ can be prepared as thin films and have been analyzed by electron diffraction (Terao, 1971). At elevated temperatures, δ' -TaN_x forms with the rocksalt structure (Gatterer, Dufek, Ettmayer & Kieffer, 1975). Thin films of δ -TaN_{0.8-0.9} are reported with the hexagonal WC structure (Brauer & Mohr-Rosenbaum, 1971). Some of these interstitial nitrides are probably contaminated with traces of oxygen and carbon.

The nitrides of most interest to us are the fully-nitrided, stoichiometric ones. TaON forms with the baddelyite (ZrO₂) structure in which Ta atoms are irregularly 7-coordinated; oxygen and nitrogen are regularly 3- and 4-coordinated (Armstrong & Fender, 1974; Brauer, Weidlein & Strähle, 1966; Weishaupt & Strähle, 1977). The compounds MTaN₂ (M=K,Rb,Cs) form with Ta in 4-coordination in the filled β -cristobalite structure, while NaTa₂N₂ forms

with Ta in 6-coordination in the α -NaFeO₂ structure (Jacobs & Pinkowski, 1989).

The binary compound, the vermillion Ta₃N₅, has been known for many years (Moureu & Hamblet, 1937). It is reported to have the pseudobrookite (Fe₂TiO₅) structure. Although the unit cell was originally given as metrically tetragonal (Brauer & Weidlein, 1965), its structure has been refined as orthorhombic (Strähle, 1973) and monoclinic (Terao, 1977). If it were truly isomorphic with high-temperature Ti₃O₅ (Åsbrink & Magnéli, 1959), Ta₃N₅ would be monoclinic. The reported structure also contains an unusually short Ta...Ta distance for a compound in which Ta-Ta bonding is not expected so that, in view of the uncertainty about the space group, we felt that it warranted further investigation. We report here neutron diffraction studies which confirm and refine Strähle's orthorhombic structure.

Experimental:

TaCl₅ was heated under flowing ammonia gas; the gas had been purified as the liquid over sodium. The temperature was slowly increased to 750°C where a rapid conversion to Ta₃N₅ occurred. The air-stable, maroon-colored material was ground under acetone. X-ray diffraction indicated the presence of

Discussion:

Our structure determination confirms and refines that proposed by Strähle (1973). Terao suggested a similar structural model but proposed the spacegroup $C2/m$ (Terao, 1977) based on analogy with Ti_3O_5 at high temperature (Åsbrink & Magnéli, 1959). We transformed our orthorhombic model to the monoclinic setting and found that an unstable refinement in $C2/m$ was not statistically better than the refinement in $Cmcm$: the difference profile curve was identical, and the structural parameters did not move more than 1-2 standard deviations away from those of the starting model. We therefore conclude that if Ta_3N_5 is actually monoclinic it is too close to orthorhombic to discern.

The structure of Ta_3N_5 is composed of octahedra of nitrogen atoms centered by tantalum atoms. Since the nitrogen atoms are both 3- and 4-coordinated, the octahedra are irregular. The bond lengths are given in Table III. Both Ta atoms have six Ta...Ta contacts shorter than 3.8 Å (the next-nearest neighbor distance). Figure 2 displays the structure projected on [100].

Shortest Ta-Ta distances derived from oxide and oxynitride materials are typically 3.3 Å, although compounds in which metal-metal bonding might be expected contain

shorter distances (e.g. Ta_4SiTe_4 2.98 Å). Shortest Ta-Ta distances for some structures are tabulated in Table IV. The structure for Ta_3N_5 proposed by Strähle, which we confirm, contains a short Ta(2)-Ta(2) distance of 3.00 Å, although the other Ta-Ta distances are over 3.25 Å.

Bond valence parameters appropriate for metal-metal bonding have recently been derived (O'Keeffe & Brese, 1991). These predict the length of a Ta-Ta single bond to be $R = 2.78$ Å and using the expression (Brown & Altermatt, 1985) for the valence v of a bond of length d : $v = \exp[(R - d)/0.37\text{Å}]$, the short bond in Ta_3N_5 corresponds to a valence of 0.55. Note, however, that in a material such as MgO (where the Mg...Mg distance is shorter than in elemental Mg), each of the twelve closest "bonds" is calculated to have a valence of 0.3, although it is generally accepted that there is no metal-metal bonding in this case.

Electrostatic potentials (ϕ) reported in Table I are calculated assuming integral nonoverlapping spherical charges (Tosi, 1964). Since the potential at both Ta sites are similar, both metal atoms are equivalently surrounded by opposite charges. Therefore, based on bond-valence as well as Madelung potential calculations, we believe the close Ta...Ta distance is more a constraint of the pseudobrookite structure than a result of metal-metal bonding.

This material is based upon work supported under a US National Science Foundation Graduate Fellowship to NEB and is part of a continuing program in crystal chemistry supported by the NSF (DMR 8813524). We have benefitted from the use of facilities at the Manuel Lujan, Jr. Neutron Scattering Center, a national user facility, funded as such, by the DOE/Office of Basic Energy Sciences. The synthesis work at Cornell is supported by the Office of Naval Research.

Table I. Structure of Ta₃N₅ at 16K^a

Atom	Site	x	y	z	100U _{eqv}	φ(V)
Ta(1)	4c	0	0.1971(1) [0.19757(5)]	1/4	0.56 0.37]	-54.7
Ta(2)	8f	0	0.13455(7) [0.13429(4)]	0.55906(7) 0.56010(5)	0.60 0.37]	-54.0
N(3)	4c	0	0.76322(7) [0.763(1)]	1/4	0.85 0.5]	37.3
N(4)	8f	0	0.04701(6) [0.0470(8)]	0.11949(5) 0.119(1)	1.00 0.5]	35.5
N(5)	8f	0	0.30862(6) [0.3097(9)]	0.07378(5) 0.073(1)	0.83 0.4]	38.5

^aSpacegroup Cmcm, This study: $a = 3.88617(9)$, $b = 10.2118(2)$, $c = 10.2624(3)$; room-temperature study in brackets (Strähle, 1973): $a = 3.893$, $b = c = 10.264$. U_{eqv} is defined as 1/3 the trace of the anisotropic temperature coefficients.

Table II. Anisotropic Temperature Factors for Ta₃N₅ at 16K^a

Atom	100U ₁₁	100U ₂₂	100U ₃₃	100U ₂₃
Ta(1)	0.48(3)	0.83(3)	0.37(3)	0
Ta(2)	0.37(2)	0.75(2)	0.69(3)	0.01(2)
N(3)	0.80(3)	0.86(3)	0.88(3)	0
N(4)	1.36(2)	0.81(2)	0.83(2)	-0.08(2)
N(5)	0.70(2)	0.83(2)	0.95(2)	0.12(2)

$$^a U_{12} = U_{13} = 0$$

Table III. Bond Distances (Å) and Angles (°) for Ta₃N₅

Ta(1)-2Ta(2)	3.2353(8)	N(3)-Ta(1)-N(3)	141.67(7)
Ta(1)-4Ta(2)	3.2513(7)	N(3)-Ta(1)-N(4)	104.31(2)
Ta(1)-2N(3)	2.0571(5)	N(3)-Ta(1)-N(5)	79.93(3)
Ta(1)-2N(4)	2.035(1)	N(4)-Ta(1)-N(4)	82.30(5)
Ta(1)-2N(5)	2.1372(8)	N(4)-Ta(1)-N(5)	81.05(2)
		N(4)-Ta(1)-N(5)	163.35(5)
Ta(2)-Ta(1)	3.2353(8)	N(5)-Ta(1)-N(5)	115.60(6)
Ta(2)-2Ta(1)	3.2513(7)		
Ta(2)-Ta(2)	3.004(1)	N(3)-Ta(2)-N(4)	99.55(4)
Ta(2)-2Ta(2)	3.287(1)	N(3)-Ta(2)-N(4)	177.96(5)
Ta(2)-N(3)	2.2203(8)	N(3)-Ta(2)-N(5)	78.48(2)
Ta(2)-N(4)	1.9550(8)	N(3)-Ta(2)-N(5)	99.44(3)
Ta(2)-N(4)	2.0388(9)	N(4)-Ta(2)-N(4)	82.49(4)
Ta(2)-2N(5)	2.0335(3)	N(4)-Ta(2)-N(5)	78.52(3)
Ta(2)-N(5)	2.240(1)	N(4)-Ta(2)-N(5)	101.06(3)
		N(4)-Ta(2)-N(5)	104.31(3)
N(3)-2Ta(1)	2.0571(5)	N(4)-Ta(2)-N(5)	161.01(4)
N(3)-2Ta(2)	2.2203(8)	N(5)-Ta(2)-N(5)	79.56(3)
		N(5)-Ta(2)-N(5)	145.70(5)
N(4)-Ta(1)	2.035(1)		
N(4)-Ta(2)	1.9550(8)	Ta(1)-N(3)-Ta(1)	141.67(7)
N(4)-Ta(2)	2.0388(9)	Ta(1)-N(3)-Ta(2)	98.88(1)
		Ta(2)-N(3)-Ta(2)	123.91(5)
N(5)-Ta(1)	2.1372(8)		
N(5)-2Ta(2)	2.0335(3)	Ta(1)-N(4)-Ta(2)	105.14(4)
N(5)-Ta(2)	2.240(1)	Ta(1)-N(4)-Ta(2)	157.34(4)
		Ta(2)-N(4)-Ta(2)	97.51(4)
		Ta(1)-N(5)-Ta(2)	95.28(4)
		Ta(1)-N(5)-Ta(2)	102.41(2)
		Ta(2)-N(5)-Ta(2)	100.44(3)
		Ta(2)-N(5)-Ta(2)	145.70(5)

Table IV. Shortest Ta...Ta Distances in Assorted Materials

Compound	Number	Distance (Å)	Reference
Ta	8	2.86	(Mueller, 1977)
ϵ -TaN	2	2.91	(Christensen & Lebech, 1978)
Ta ₄ SiTe ₄	8	2.97	(Badding & DiSalvo, 1990)
Ta ₂ CoN ₃	6	2.98	(Schönberg, 1954a)
Ta ₅ N ₆	6	2.99	(Fontbonne & Gilles, 1969)
Ta ₃ MnN ₄	6	3.02	(Schönberg, 1954a)
β -Ta ₂ N	6	3.03	(Conroy & Christensen, 1977)
Ta ₄ N ₅	6	3.04	(Fontbonne & Gilles, 1969)
δ -TaN	12	3.07	(Gatterer, Dufek, Ettmayer & Kieffer, 1975)
TaTa ₂ N ₂	6	3.13	(Jacobs & Pinkowski, 1989)
TaON	2	3.23	(Armytage & Fender, 1974)
RbTaO ₃	3	3.24	(Serafin & Hoppe, 1980)
TaI ₅	2	3.31	(Müller, 1979)
TaTe ₂	4	3.32	(Brown, 1966)
α -TaS ₂	6	3.35	(Jellinek, 1962)
TaBO ₄	4	3.40	(Zaslavskij & Zvincuk, 1953)
Ta ₃ N ₅	1	3.00	This study

Figure legends:

1. Neutron diffraction profile fit for Ta_3N_5 at 16 K ($2\theta = +148^\circ$ detector bank). The data points are shown as '+' marks, and the solid line is the calculated profile. The difference curve at the bottom is on the same scale. The background has been subtracted.
2. Projection of the Ta_3N_5 structure on (100). The b axis is horizontal, and the c axis is vertical. The dark-shaded octahedra are displaced by $a/2$ from the lighter ones. Dark circles represent the 4-coordinated N atoms, while the lighter circles represent the 3-coordinated ones. Larger circles represent Ta atoms within the octahedra.
3. Projection of the Ta_3N_5 structure on (100) emphasizing anion coordination. Larger circles again represent Ta atoms. The edge-sharing tetrahedra are centered by N atoms. The shading of the circles indicates displacement by $a/2$.

References:

- Armytage, D. & Fender, B. E. F. (1974). *Acta Cryst. B* **30**, 809-812.
- Åsbrink, S. & Magnéli, A. (1959). *Acta Cryst.* **12**, 575-581.
- Badding, M. E. & DiSalvo, F. J. (1990). *Inorg. Chem.* **29**,
- Brauer, G. & Mohr-Rosenbaum, E. (1971). *Monat. Chem.* **102**, 1311-1316.
- Brauer, G., Weidlein, J. & Strähle, J. (1966). *Z. Anorg. Allg. Chem.* **348**, 298-308.
- Brauer, G. & Weidlein, J. R. (1965). *Angew. Chem. Int. Ed.* **4**, 241-242.
- Brauer, G. & Zapp, K. H. (1953). *Naturwiss.* **40**, 604.
- Brauer, G. & Zapp, K. H. (1954). *Z. Anorg. Allg. Chem.* **277**, 129-139.
- Brown, B. E. (1966). *Acta Cryst.* **20**, 264-267.
- Brown, I. D. & Altermatt, D. (1985). *Acta Cryst. B* **41**, 244-247.
- Christensen, A. N. & Lebech, B. (1978). *Acta Cryst. B* **34**, 261-263.
- Conroy, L. E. & Christensen, A. N. (1977). *J. Solid State Chem.* **20**, 205-207.
- Fontbonne, A. & Gilles, J. (1969). *Rev. Int. Hautes Tempér. Réfract.* **6**, 181-192.
- Gatterer, J., Dufek, G., Ettmayer, P. & Kieffer, R. (1975). *Monat. Chem.* **106**, 1137-1147.

- Hewat, A. W. (1979). *Acta Cryst. A* **35**, 248.
- Jacobs, H. & Pinkowski, E. V. (1989). *J. Less-Common Met.* **146**, 147-160.
- Jellinek, F. (1962). *J. Less-Common Met.* **4**, 9-15.
- Larson, A. C. & Von Dreele, R. B. (1990). *Generalized Structure Analysis System (GSAS)*. LANSCE, MS-H805, Manuel Lujan Jr., Neutron Scattering Center, Los Alamos, NM 87545.
- Moureu, H. & Hamblet, C. H. (1937). *J. Amer. Chem. Soc.* **59**, 33-40.
- Mueller, M. H. (1977). *Scripta Metall.* **11**, 693.
- Müller, U. (1979). *Acta Cryst. B* **35**, 2502-2509.
- O'Keefe, M. & Brese, N. E. (1991). *J. Amer. Chem. Soc.* accepted for publication.
- Rauch, P. & DiSalvo, F. (1991). *Inorg. Synthesis* to be published.
- Rouse, K. D., Cooper, M. J. & Chakera, A. (1970). *Acta Cryst. A* **26**, 682-691.
- Schönberg, N. (1954a). *Acta Chem. Scand.* **8**, 213-222.
- Schönberg, N. (1954b). *Acta Chem. Scand.* **8**, 199-203.
- Serafin, M. & Hoppe, R. (1980). *Z. Anorg. Allg. Chem.* **464**, 240-254.
- Strähle, J. (1973). *Z. Anorg. Allg. Chem.* **402**, 47-57.
- Terao, N. (1971). *Jap. J. Appl. Phys.* **10**, 248-259.
- Terao, N. (1977). *C. R. Acad. Sci. Paris* **C285**, 17-20.
- Tosi, M. P. (1964). *Solid State Phys.* **16**, 1-120.

Von Dreele, R. B., Jorgensen, J. D. & Windsor, C. G. (1982).


J. Appl. Cryst. **15**, 581-589.

Weishaupt, M. & Strähle, J. (1977). *Z. Anorg. Allg. Chem.*


429, 261-269.


Zaslavskij, A. I. & Zvincuk, R. A. (1953). *Dokl. Akad. Nauk*

SSSR **90**, 781-783.



Brese, O'Kelle, Runtz, D.Slow Fig 1





TECHNICAL REPORT DISTRIBUTION LIST - GENERAL

Office of Naval Research (2)
Chemistry Division, Code 1113
800 North Quincy Street
Arlington, Virginia 22217-5000

Dr. Richard W. Drisko (1)
Naval Civil Engineering
Laboratory
Code L52
Port Hueneme, CA 93043

Dr. James S. Murday (1)
Chemistry Division, Code 6100
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. Harold H. Singerman (1)
David Taylor Research Center
Code 283
Annapolis, MD 21402-5067

Dr. Robert Green, Director (1)
Chemistry Division, Code 385
Naval Weapons Center
China Lake, CA 93555-6001

Chief of Naval Research (1)
Special Assistant for Marine
Corps Matters
Code 00MC
800 North Quincy Street
Arlington, VA 22217-5000

Dr. Eugene C. Fischer (1)
Code 2840
David Taylor Research Center
Annapolis, MD 21402-5067

Defense Technical Information
Center (2)
Building 5, Cameron Station
Alexandria, VA 22314

Dr. Elek Lindner (1)
Naval Ocean Systems Center
Code 52
San Diego, CA 92152-5000

Commanding Officer (1)
Naval Weapons Support Center
Dr. Bernard E. Doua
Crane, Indiana 47522-5050

* Number of copies to forward