

AD-A264 883

ENTATION PAGE

Form Approved
OMB No. 0704-0188

Estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering the necessary data, reviewing the collection of information, Send comments regarding this burden estimate or any other aspect of this burden to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. REPORT DATE May 18, 1993		3. REPORT TYPE AND DATES COVERED Technical report	
4. TITLE AND SUBTITLE Water-Soluble Polyphosphazenes and their Hydrogels		5. FUNDING NUMBERS N00014-91-J-1194	
6. AUTHOR(S) Harry R. Allcock		8. PERFORMING ORGANIZATION REPORT NUMBER #11	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Chemistry The Pennsylvania State University 152 Davey Laboratory University Park, Pennsylvania 16802		10. SPONSORING / MONITORING AGENCY REPORT NUMBER 4132007	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Office of Naval Research 800 North Quincy Street Arlington, Virginia 22217-5000		11. SUPPLEMENTARY NOTES Prepared for publication in PMSE preprints (ACS Chicago) 1993	
12a. DISTRIBUTION AVAILABILITY STATEMENT Reproduction in whole or in part is permitted for any purpose of the United State government. This document has been approved for public release and sale; its distribution is unlimited.		12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Description of polyphosphazenes and their relationship to: bioerodible systems; radiation-crosslinking to give hydrogels; surface hydrogel grafting; membranes, blends, and IPN's; gel-immobilized enzymes; and ion-crosslinked hydrogels;			
14. SUBJECT TERMS Polymers, polyphosphazenes, water-solubility, hydrogels, crosslinking, radiation		15. NUMBER OF PAGES 5	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT unclassified	20. LIMITATION OF ABSTRACT unlimited

NSN 7540-01-280-5500

Standard Form 298 (Rev. 2-89)
Prescribed by ANSI Std. Z39-18
298-102

DTIC
SELECTED
MAY 26 1993
S & D

400 343

93-11555



93 5 23 13

OFFICE OF NAVAL RESEARCH

Grant: N00014-91-J-1194

R&T Code: 4132007

Technical Report No. 11

Water-Soluble Polyphosphazenes and their Hydrogels

by

Harry R. Allcock

Prepared for Publication in PMSE Preprints

Department of Chemistry
The Pennsylvania State University
University Park, Pennsylvania 16802

May 18, 1993

Reproduction in whole, or in part, is permitted for any purpose of the United States government.

This document has been approved for public release and sale; its distribution is unlimited.

WATER-SOLUBLE POLYPHOSPHAZENES AND THEIR HYDROGELS

Harry R. Allcock

Department of Chemistry, The Pennsylvania State University, University Park, Pennsylvania 16802.

Much has been written about the special characteristics of different polymer backbone systems. Nevertheless, in spite of these differences, the side groups have a greater influence on the ambient temperature properties than does the backbone, irrespective of the type of backbone that is present. Thus, the development of methods for the incorporation of different side groups into polymers is a key step in the generation of specific combinations of properties. Two general methods exist for bringing about variations in polymer side groups: (1) The polymerization of different monomers that bear different side groups, and (2) macromolecular substitution reactions in which side groups already attached to a polymer are replaced by other units. The first method is more widely used than the second, mainly because organic macromolecular side group reactions are often relatively inefficient.

Polyphosphazenes are unusual polymers in many ways.¹⁻³ But their most significant advantage is the ease with which specific side groups can be linked to the phosphorus-nitrogen backbone by highly efficient substitutive techniques. Thus, by using the synthesis manifold shown in Scheme I, it is possible to vary the side group structure over a wide range. Note also that sequential or simultaneous cosubstitution can yield polymers with two or more different types of side groups per chain. This approach also allows the incorporation of side groups that generate water-solubility, hydrogel formation, or hydrophilic surface character. This talk will illustrate these principles at work.

Chart 1 gives the structures of six polyphosphazenes that are soluble in water. Species 2 is

Accession For	
NTIS CPA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail codes
A-1	Special

mainly soluble in alkaline aqueous media, provided the cations are monovalent.

Bioerodible Systems

Two of the polymers shown in Chart 1 are hydrolytically-sensitive. These are polymers 3 and 4.⁴⁻⁶ Hydrolysis leads to the formation of phosphate, ammonia, and glucose or glycerol--all bio-acceptable products. Thus, the glucosyl and glyceryl side groups are potentially important substituents or cosubstituents in bioerodible and bio-acceptable polyphosphazenes for use in controlled drug delivery, and bioabsorbable structural polymers. The glyceryl derivatives hydrolyze faster than their glucosyl counterparts.

Radiation-Crosslinking to Give Hydrogels

Polymer 1 and especially polymer 5 possess side groups that contain aliphatic carbon hydrogen bonds that are sensitive to gamma-ray induced homolytic C-H bond cleavage and free radical cross-combination to generate cross-links.⁷⁻¹² The materials formed absorb water to form hydrogels, with the cross-link density and degree of water imbibition being controllable by the radiation dose. Ultraviolet irradiation also induces the crosslinking of 5.

Surface Hydrogel Grafting

The high sensitivity of polymer 5 to gamma-ray or ultraviolet cross-linking allows films of this polymer to be radiation-grafted to the surface of polymers that themselves bear C-H or C-Cl bonds.¹³ Subsequent exposure to water creates a hydrogel layer covalently bonded to the surface of the substrate polymer. Systems based on this structure show anti-microbial activity, a property that may be useful for the surface preparation of a wide variety of polymers to be used in cardiovascular and other implantable devices.¹⁴

Membranes, Blends, and IPN's

Cross-linked **1** or **5** can serve as effective semi-permeable membranes. However, fine-tuning of membrane permeability can be achieved in three ways: (1) By the use of cosubstituent polymers that contain either -NHCH_3 or $\text{OCH}_2\text{CH}_2\text{OCH}_2\text{CH}_2\text{OCH}_3$ side groups, plus a second hydrophobic group such as $\text{-OCH}_2\text{CF}_3$ or OC_6H_5 . The amount of the hydrophobic cosubstituent allows control over the degree of swelling in aqueous media and the permeability of the membrane to different small molecules. (2) By the formation of polymer alloys (blends) between **1** or **5** and classical organic polymers such as polyvinyl, ester, or amide macromolecules. Membrane transport properties can be controlled by the ratios of the macromolecular components.¹⁵ (3) By the formation of partial or complete cross-linked interpenetrating polymer networks. In principle, this method allows a broader range of compositions to be generated than does method 2.¹⁶

Gel-Immobilized Enzymes

The radiation-cross-linking of **5** in the presence of enzymes brings about the entrapment of enzyme molecules within a hydrogel matrix.¹⁷ For example, urease has been immobilized in this way. The enzyme retains at least 80% of its activity during multiple, sequential exposures to urea. Uses for this methodology in sensors and bioreactors are being investigated.

Ion-Cross-linked Hydrogels

Finally, in one of the most striking uses of water-soluble polyphosphazenes, it has recently been shown that polymer **2**, which is soluble in aqueous potassium or sodium hydroxide solutions, can be cross-linked to hydrogels by exposure to solutions of di- or trivalent cations, such as Ca^{++} or Al^{++} .¹⁸⁻²⁰ Technology based on this process has been used to prepare microencapsulated living mammalian cells (such as hybridoma liver cells), proteins, and microorganisms. The hydrogel coating is

permeable to small-molecule nutrients and products of metabolism but is impermeable to antibodies. Several uses for this technology that appear to be promising are under development for artificial organ, biotechnology, and immunological research.

Acknowledgments

Parts of this work were supported originally by the National Institutes of Health. It has been sustained by generous support from the Virus Research Institute, Cambridge, Mass., the Focussed Giving program of Johnson & Johnson, the U.S. Army Research Office, and the Office of Naval Research. It is also a pleasure to acknowledge the contributions of the coworkers listed in the following references.

References

1. *Inorganic Polymers*, Mark, J. E.; Allcock, H. R.; West, R. eds., Prentice Hall: Englewood Cliffs, N. J. , 1992.
2. Allcock, H. R. *Science* **1992**, 255, 1106.
3. Allcock, H. R. In *Biodegradable Polymers as Drug Delivery Systems* (Langer, R.; Chasin, M., eds.), Marcel Dekker: New York, 1990.
4. Allcock, H. R.; Scopelianos, A. G. *Macromolecules* **1983**, 16, 715.
5. Allcock, H. R.; Pucher, S. R. *Macromolecules*, **1991**, 24, 23.
6. Allcock, H. R.; Kwon, S. *Macromolecules* **1988**, 21, 1980.
7. Allcock, H. R.; Gebura, M.; Kwon, S.; Neenan, T. X. *Biomaterials* **1988**, 19, 500.
8. Allcock, H. R.; Kwon, S.; Riding, G. H.; Fitzpatrick, R. J.; Bennett, J. L. *J. Am. Chem. Soc.* **1988**, 110, 980.
9. Bennett, J. L.; Dembek, A. A.; Allcock, H. R.; Heyen, B. J.; Shriver, D. F. *Chem. Mater.* **1989**, 1, 14.
10. Bennett, J. L.; Dembek, A. A.; Allcock, H. R.; Heyen, B. J.; Shriver, D. F. *Polym. Prepr. (ACS Polym.Div.)* **1989**, 30, 437.
11. Nelson, C. J.; Coggio, W. D.; Allcock, H. R. *Chem. Mater.* **1991**, 3, 786.

12. Allcock, H. R.; Pucher, S. R.; Turner, M. L.; Fitzpatrick, R. J. **1992**, 25, 5573.
13. Allcock, H. R.; Fitzpatrick, R. J.; Visscher, K. B. *Chem. Mater.* **1992**, 4, 775.
14. Allcock, H. R.; Pucher, S. R.; Fitzpatrick, R. J. *Biomaterials* **1992**, 13, 857.
15. Allcock, H. R.; Visscher, K. B. *Chem. Mater.* **1992**, 4, 1182.
16. Allcock, H. R.; Visscher, K. B.; Manners, I. *Chem. Mater.* **1992**, 4, 1188.
17. Pucher, S. R.; Allcock, H. R. unpublished work.
18. Allcock, H. R.; Kwon, S. *Macromolecules*, **1989**, 22, 75.
19. Cohen, S.; Bano, M. C.; Visscher, K. B.; Chow, M.; Allcock, H. R.; Langer, R. *J. Am. Chem. Soc.* **1990**, 112, 7832.
20. Bano, M. C.; Cohen, S.; Visscher, K. B.; Allcock, H. R.; Langer, R. *Biotechnology* **1991**, 9, 468.

TECHNICAL REPORT DISTRIBUTION LIST - GENERAL

Office of Naval Research (2)*
Chemistry Division, Code 1113
800 North Quincy Street
Arlington, Virginia 22217-5000

Dr. James S. Murday (1)
Chemistry Division, Code 6100
Naval Research Laboratory
Washington, D.C. 20375-5000

Dr. Robert Green, Director (1)
Chemistry Division, Code 385
Naval Air Weapons Center
Weapons Division
China Lake, CA 93555-6001

Dr. Elek Lindner (1)
Naval Command, Control and Ocean
Surveillance Center
RDT&E Division
San Diego, CA 92152-5000

Dr. Bernard E. Douda (1)
Crane Division
Naval Surface Warfare Center
Crane, Indiana 47522-5000

Dr. Richard W. Drisko (1)
Naval Civil Engineering
Laboratory
Code L52
Port Hueneme, CA 93043

Dr. Harold H. Singerman (1)
Naval Surface Warfare Center
Carderock Division Detachment
Annapolis, MD 21402-1198

Dr. Eugene C. Fischer (1)
Code 2840
Naval Surface Warfare Center
Carderock Division Detachment
Annapolis, MD 21402-1198

Defense Technical Information
Center (2)
Building 5, Cameron Station
Alexandria, VA 22314

* Number of copies to forward

ABSTRACT DISTRIBUTION LIST

Dr. Harry R. Allcock
Department of Chemistry
Pennsylvania State Univ.
University Park, PA 16802

Dr. Chris W. Allen
Department of Chemistry
University of Vermont
Burlington, VT 05405-0125

Dr. Andrew R. Barron
Department of Chemistry
Harvard University
Cambridge, MA 02138

Dr. Kurt Baum
Fluorochem, Inc.
680 South Ayon Avenue
Azusa, CA 91702

Dr. Alexander S. Blumstein
Department of Chemistry
University of Massachusetts
Lowell, MA 01854

Professor Joseph M. DeSimone
Department of Chemistry
The University of North
Carolina at Chapel Hill
Chapel Hill, NC 27599-3290

Dr. Jean M. Frechet
Department of Chemistry
Cornell University
Ithaca, NY 14853

Dr. Robert H. Grubbs
Department of Chemistry
California Inst. of Technol.
Pasadena, CA 91124

Professor Issifu I. Harruna
Morris Brown College
643 Martin Luther King, Jr. Drive, N.W.
Atlanta GA 30314-4140

Dr. Robert W. Lenz
Polymer Sci. and Eng. Dept.
University of Massachusetts
Amherst, MA 01002

Dr. Lon J. Mathias
Department of Polymer Science
University of Southern Mississippi
Hattiesburg MS 39406-0076

Dr. Krzysztof Matyjaszewski
Department of Chemistry
Carnegie-Mellon University
Pittsburgh, PA 15213

Pr. Alan G. MacDiarmid
Department of Chemistry
University of Pennsylvania
Chemistry Building
Philadelphia PA 19104-6323

Dr. James E. McGrath
Department of Chemistry
Virginia Polytechnic Inst.
Blacksburg, VA 24061

Dr. James A. Moore
Department of Chemistry
Rensselaer Polytechnic Inst.
Troy, NY 12180-3590

Dr. Bruce M. Novak
Department of Chemistry
University of California
Berkeley, CA 94720

Dr. Virgil Percec
Dept. of Macromolecular Sci.
Case Western Reserve Univ.
Cleveland, OH 44106-2699

Dr. Dietmar Seyferth
Department of Chemistry
Massachusetts Institute of Technology
Cambridge, MA 02139

Dr. Richard R. Shrock
Department of Chemistry, 6-331
Massachusetts Institute of Technology
77 Massachusetts Avenue
Cambridge, MA 02139

Dr. James M. Tour
Dept. of Chemistry
Univ. of South Carolina
Columbia, SC 29208

•
•
Dr. David M. Walba
Dept. of Chem. & Biochem.
Univ. of Colorado
Boulder, CO 80309

Dr. Robert West
Department of Chemistry
University of Wisconsin-Madison
Madison WI 53706

Dr. Michael E. Wright
Department of Chemistry
Utah State University
Logan, UT 84322