

AD-A268 956



12

AD

TECHNICAL REPORT ARCCB-TR-93024

**MECHANISM-DEPENDENT FRACTAL CHARACTER
OF FRACTURE SURFACES IN HIGH STRENGTH
AND TOUGHNESS ASTM A723 STEELS**

**PETER McANULTY
L.V. MEISEL
P.J. COTE**

DTIC
ELECTE
SEP 03 1993
D

JUNE 1993



**US ARMY ARMAMENT RESEARCH,
DEVELOPMENT AND ENGINEERING CENTER
CLOSE COMBAT ARMAMENTS CENTER
BENET LABORATORIES
WATERVLIET, N.Y. 12189-4050**



APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED

93-20621



DISCLAIMER

The findings in this report are not to be construed as an official Department of the Army position unless so designated by other authorized documents.

The use of trade name(s) and/or manufacturer(s) does not constitute an official indorsement or approval.

DESTRUCTION NOTICE

For classified documents, follow the procedures in DoD 5200.22-M, Industrial Security Manual, Section II-19 or DoD 5200.1-R, Information Security Program Regulation, Chapter IX.

For unclassified, limited documents, destroy by any method that will prevent disclosure of contents or reconstruction of the document.

For unclassified, unlimited documents, destroy when the report is no longer needed. Do not return it to the originator.

REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE June 1993		3. REPORT TYPE AND DATES COVERED Final	
4. TITLE AND SUBTITLE MECHANISM-DEPENDENT FRACTAL CHARACTER OF FRACTURE SURFACES IN HIGH STRENGTH AND TOUGHNESS ASTM A723 STEELS				5. FUNDING NUMBERS AMCMS: 6111.02.H610.0 PRON: LA14Z1C4NMBJ	
6. AUTHOR(S) Peter McAnulty (USMA), L.V. Meisel, and P.J. Cote					
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) U.S. Army ARDEC Benet Laboratories, SMCAR-CCB-TL Watervliet, NY 12189-4050				8. PERFORMING ORGANIZATION REPORT NUMBER ARCCB-TR-93024	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) U.S. Army ARDEC Close Combat Armaments Center Picatinny Arsenal, NJ 07806-5000				10. SPONSORING / MONITORING AGENCY REPORT NUMBER	
11. SUPPLEMENTARY NOTES					
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; distribution unlimited.				12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) The fractal character of fracture surfaces of thick-walled pressure vessels produced in the final fast fracture that terminates low cycle fatigue tests is compared with that of fracture surfaces produced in Charpy impact tests in samples of the same high strength and toughness steel (ASTM A723) alloy. Slit island analysis yielded fractal dimensions near 1.25 for the Charpy specimens, which is typical of high strength steel alloys previously studied; however, extremely high fractal dimensions near 1.30 were determined for the low cycle fatigue specimens. The distributions of island and lake areas and of island and lake perimeters on random sections exhibit hyperbolic distributions analogous to those found for geographic islands and lakes.					
14. SUBJECT TERMS Hyperbolic Distributions, Fractal Dimension, Slit Island Method, Fracture Steel				15. NUMBER OF PAGES 8	
				16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED	18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL		

TABLE OF CONTENTS

INTRODUCTION	1
EXPERIMENTAL	1
Charpy Specimen	1
Low Cycle Fatigue Specimen	1
DATA ANALYSIS	1
RESULTS	2
Slit Island Analysis	2
Area-Number Relations	3
DISCUSSION	5
REFERENCES	7

List of Illustrations

1. $\log_{10}$ (perimeter) versus $\log_{10}$ (area) for a typical Charpy fracture surface	2
2. Sorted and averaged $\log_{10}$ (perimeter) versus $\log_{10}$ (area) for all island sections in low cycle fatigue fracture surface	3
3. $\log_{10}$ (perimeter) versus $\log_{10}$ (area) for all lake sections in low cycle fatigue fracture surface	4
4. Korcak plot for island sections	5

Accession For	
NTIS OAS&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

INTRODUCTION

The fractal character of fracture surfaces produced by Charpy impact and by the final fast fracture of thick-walled pressure vessels during low cycle fatigue testing in high strength and toughness ASTM A723 (modified AISI 4340 with 0.2 percent vanadium) steels has been determined.

Substantial differences were observed in the qualitative appearance and in the fractal character of the fracture surfaces produced by the two mechanisms. The Charpy specimens were typical of high toughness steel fracture surfaces (refs 1-5) and had fractal dimension approximately 1.25, while the low cycle fatigue specimen exhibited an extremely high fractal dimension near 1.40. Since the character of the low cycle fatigue specimen fracture was atypical of fracture surfaces in high toughness steels previously studied, a thorough study of its structure was undertaken.

We follow the usual convention of giving the fractal dimension as that determined for islands and/or lakes on sections through the fracture surface. Thus, according to Mandelbrot's rule for sections, the actual fracture surface fractal dimensions are 1.0 greater than the fractal dimensions reported here.

EXPERIMENTAL

Charpy Specimen

Charpy specimens were standard notched 3/8 inch ASTM A723 bars with a nominal strength of 160 Ksi and hardness of 38 Rc. Fracture surfaces were coated with electroless nickel prior to grinding on a metallurgical polishing wheel to obtain the island and lake configuration. Perimeter and area measurements were obtained with the JAVA™ image analysis system (ref 6).

Low Cycle Fatigue Specimen

The low cycle fatigue specimen fracture surface was produced in a 10-cm inner diameter thick-walled cylinder subjected to hydraulic pressure cycling, which culminates in a final fast fracture when the fatigue crack depth exceeds the critical crack length (refs 7,8).

A large section (2 inches by 5 inches) of the fracture surface was selected for analysis. Electroless coating of the surface to protect fine detail during grinding was unnecessary because of the low magnification used for the large islands and lakes on this specimen. However, lake regions were filled with paint to enhance contrast. The images were recorded with a video camera and analyzed with the JAVA™ system (ref 6).

DATA ANALYSIS

The primary analytical technique employed in these experiments was the slit island method of Mandelbrot, Passoja, and Paullay (ref 1). Island data were accumulated, ignoring lakes within islands, and lake data were accumulated, ignoring islands within lakes.

Conventional slit island analysis was performed on the islands produced by sectioning the Charpy bars.

The low cycle fatigue specimen was more extensively studied. Conventional slit island analysis was supplemented by separate analyses of island and lake data on individual sections. The distributions of island and lake areas on individual sections and of the combined data were also fit to the Kozicki empirical law (i.e., a hyperbolic distribution function) as suggested in the discussion of diameter-number relations by Mandelbrot (ref 9). Curve fitting and computation employed MATLAB™ software (ref 10).

RESULTS

Slit Island Analysis

1. Charpy impact fracture. The log-log perimeter-area data in Figure 1 are typical of slit island results obtained from Charpy fractures in tempered martensite for ASTM A723 steels. The $\log_{10}$ (perimeter) values shown comprise about seventy islands and are linear in $\log_{10}$ (area) over about four orders of magnitude in the area (from about 10^{-5} to 10^{-1} mm²); the fractal dimension is determined to be 1.25. Values of the fractal dimension measured for Charpy impact fractures in A723 steels ranged between about 1.20 and 1.30.




Figure 1. $\log_{10}$ (perimeter) versus $\log_{10}$ (area) for a typical Charpy fracture surface. One unit of perimeter is approximately 0.1 cm and one unit of area is approximately 0.01 cm². The least-squares fit line yields $D = 1.25$.

2. Low cycle fatigue specimen fracture. Perimeter-area plots were obtained for a sequence of sections through the low cycle fatigue specimen fracture surface. Each section comprised about two hundred islands or lakes. Areas varied from about $0.5 \cdot 10^{-3}$ to 10^3 mm².

a. Island sections. The initial sections, which exhibited (essentially) only islands, and intermediate depth sections, which exhibited comparable numbers of islands and lakes, provided data for eleven separate island-only perimeter-area analyses. The data were strikingly consistent. Fractal dimension determinations on the individual sections ranged from 1.37 to 1.41; the combined data yielded 1.40. There was a trend toward lower values at deeper sections. Figure 2 shows the perimeter-area (in arbitrary units) data for the combined island data and for a typical section.




Figure 2. Sorted and averaged $\log_{10}$ (perimeter) versus $\log_{10}$ (area) for all island sections in low cycle fatigue fracture surface. The islands are sorted in order of increasing area and arranged into sets of 50 islands. Each point represents the average value for a set of 50 islands (e.g., the n th point represents the average values for islands $(50n-49)$ through $50n$ in the sorted list). The least-squares fit line yields $D = 1.395 \pm 0.004$.

b. Lake sections. The deeper sections provided data for seven separate lake perimeter-area analyses. The data were remarkably consistent among themselves and with the results of the island analyses. Fractal dimension determinations on the individual sections ranged from 1.36 to 1.39; the combined data yielded 1.37. Figure 3 exhibits the perimeter-area dependence of the combined lake data.

Area-Number Relations

Hyperbolic distributions and fractal structures are closely related. For example, in the theory of self-ordered criticality they reflect absence of intrinsic time and spatial scales, respectively. Mandelbrot's discussion (ref 9) of diameter-number relations for geographic islands defined by sea level, suggested that islands produced by sections through fractal surfaces should exhibit hyperbolic distributions. (Mandelbrot credits J. Korcak with the discovery of the existence of such distributions and refers to them as Korcak distributions.)

The generalized Korcak law, as formulated by Mandelbrot (ref 9), relates the hyperbolic area-number relation and the fractal dimension of the surface as

$$N_r(A > a) = F a^{D/2}$$

where $N_r(A > a)$ is the total number of islands of area greater than a , and D is the surface fractal dimension. Mandelbrot (ref 9) also asserts that the fractal dimension D , governing the hyperbolic distribution, can exceed the coastline fractal dimension D_c as a result of "fragmentation."




Figure 3. $\log_{10}(\text{perimeter})$ versus $\log_{10}(\text{area})$ for all lake sections in low cycle fatigue fracture surface. One unit of perimeter is approximately 2.4 cm and one unit of area is approximately 5.7 cm^2 . The least-squares fit line yields $D = 1.372 \pm 0.0041$.

1. Island sections. The number-area data accumulated for all the islands in the low cycle fatigue fracture surface are shown in Figure 4. The data are consistent with a hyperbolic distribution over three orders of magnitude in the area. Least-squares fitting yields $D \approx 1.54$, which is substantially greater than the coastline fractal dimension ($D_c = 1.40$) and would seem to imply a substantial fragmentation contribution to D . Furthermore, analyses of the hyperbolic distribution of island areas for individual sections also gave D values greater than D_c . The deviations of the deduced D values were within ± 15 percent of 1.54 over the eleven island sections.

A smaller D would be obtained for the island number-area data if one invoked a smaller "outer cutoff" on the distribution, but the data are essentially linear over the three orders of magnitude in the area over which the parameters were fit.

2. Lake sections. The lake sections were consistent with a hyperbolic distribution over about one and a half orders of magnitude; however, for the lake sections, the deduced dimension ($D \approx 1.40$) is in close accord with the coastline fractal dimension.




Figure 4. Korcak plot for island sections. The least-squares fit line through the linear portion (points 3 to 10) yields $D = 1.54 \pm 0.06$.

DISCUSSION

Perimeter-area analysis was applied to fracture surfaces produced in Charpy impact and low cycle fatigue tests in high strength and toughness ASTM A723 (modified AISI 4340 with 0.2 percent vanadium) steels. The fractal dimension of the Charpy impact fracture surfaces was determined to be approximately 1.25, which is consistent with the results of other fractal studies of fracture in high strength steels (refs 1-5). However, the fractal dimension was determined to be approximately 1.39 for low cycle fatigue fracture, an extremely high value for fracture in a high strength and toughness steel alloy.

The major difference in the two experiments is the scale over which the fractures were generated. The Charpy fracture surfaces were studied under a microscope and island areas ranged from about 10^{-5} to about 10^{-2} mm^2 . The low cycle fatigue specimen fracture surfaces studied were about 10 cm across, and the island area ranged from about $0.5 \cdot 10^{-3}$ to about 10^3 mm^2 . There was approximately one order of magnitude overlap in the ranges of area or perimeter.

The region studied in the low cycle fatigue specimen fracture was more than 10 mm from the initiation of fracture, while the Charpy fracture surface studied was within about 0.3 mm from the point of initiation of the fracture.

The rate of crack growth in the Charpy test and in the final fast fracture of the low cycle fatigue specimen are presumed to be comparable.

Since the higher fractal dimension is associated with a higher degree of complexity, a tentative conclusion from these data is that the complexity of the fracture surfaces increases with volume available for fracture.

The distributions of areas and perimeters of islands and lakes produced by sectioning the low cycle fatigue specimen fracture surface were hyperbolic in accord with the principle, the Korcak law, which Mandelbrot advanced to describe the distribution of geographic islands.

REFERENCES

1. B.B. Mandelbrot, D.E. Passoja, and A.J. Paulley, *Nature*, Vol. 308, 1984, p. 721.
2. E.E. Underwood and K.B. Banerji, *Mat. Sci. Eng.*, Vol. 80, 1986, p. 1.
3. Z.Q. Mu and C.W. Lung, *J. Phys. D: Appl. Phys.*, Vol. 21, 1988, p. 848.
4. C.S. Pande, L.E. Richards, N. Louat, B.D. Dempsey, and A.J. Schwoeble, *Acta Met.*, Vol. 35, 1987, p. 1633.
5. C.W. Lung and Z.Q. Mu, *Phys. Rev. B*, Vol. 38, 1988, p. 11781.
6. JAVA, Jandel Scientific, 65 Koch Road, Carte Madera, CA 94925.
7. T.E. Davidson and J.F. Throop, in: *Application of Fracture Mechanics to Design of High Pressure Vessels* (J.J. Burke and V. Weiss, eds.), Plenum Publishing, New York, 1978.
8. J.A. Kapp and J.H. Underwood, *Exp. Mech.*, Vol. 22, 1982, p. 96.
9. B.B. Mandelbrot, *Fractal Geometry of Nature*, Freeman, New York, 1983.
10. MATLAB, The Math Works, 21 Eliot Street, Natick, MA 01760.

TECHNICAL REPORT INTERNAL DISTRIBUTION LIST

	NO. OF COPIES
CHIEF, DEVELOPMENT ENGINEERING DIVISION	
ATTN: SMCAR-CCB-DA	1
-DC	1
-DI	1
-DR	1
-DS (SYSTEMS)	1
CHIEF, ENGINEERING SUPPORT DIVISION	
ATTN: SMCAR-CCB-S	1
-SD	1
-SE	1
CHIEF, RESEARCH DIVISION	
ATTN: SMCAR-CCB-R	2
-RA	1
-RE	1
-RM	1
-RP	1
-RT	1
TECHNICAL LIBRARY	5
ATTN: SMCAR-CCB-TL	
TECHNICAL PUBLICATIONS & EDITING SECTION	3
ATTN: SMCAR-CCP TL	
OPERATIONS DIRECTORATE	1
ATTN: SMCWV-ODP-P	
DIRECTOR, PROCUREMENT DIRECTORATE	1
ATTN: SMCWV-PP	
DIRECTOR, PRODUCT ASSURANCE DIRECTORATE	1
ATTN: SMCWV-QA	

NOTE: PLEASE NOTIFY DIRECTOR, BENET LABORATORIES, ATTN: SMCAR-CCB-TL, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST

	<u>NO. OF COPIES</u>		<u>NO. OF COPIES</u>
ASST SEC OF THE ARMY RESEARCH AND DEVELOPMENT ATTN: DEPT FOR SCI AND TECH THE PENTAGON WASHINGTON, D.C. 20310-0103	1	COMMANDER ROCK ISLAND ARSENAL ATTN: SMCRI-ENM ROCK ISLAND, IL 61299-5000	1
ADMINISTRATOR DEFENSE TECHNICAL INFO CENTER ATTN: DTIC-FDAC CAMERON STATION ALEXANDRIA, VA 22304-6145	12	MIAC/CINDAS PURDUE UNIVERSITY P.O. BOX 2634 WEST LAFAYETTE, IN 47906	1
COMMANDER US ARMY ARDEC ATTN: SMCAR-AEE	1	COMMANDER US ARMY TANK-AUTMV R&D COMMAND ATTN: AMSTA-ODL (TECH LIB) WARREN, MI 48397-5000	1
SMCAR-AES, BLDG. 321	1	COMMANDER US MILITARY ACADEMY	1
SMCAR-AET-O, BLDG. 351N	1	ATTN: DEPARTMENT OF MECHANICS WEST POINT, NY 10996-1792	
SMCAR-CC	1		
SMCAR-CCP-A	1		
S -FSA	1		
SMCAR-FSM-E	1	US ARMY MISSILE COMMAND REDSTONE SCIENTIFIC INFO CTR	2
SMCAR-FSS-D, BLDG. 94	1	ATTN: DOCUMENTS SECT, BLDG. 4484 REDSTONE ARSENAL, AL 35898-5241	
SMCAR-IMI-I (STINFO) BLDG. 59	2		
PICATINNY ARSENAL, NJ 07806-5000			
DIRECTOR US ARMY BALLISTIC RESEARCH LABORATORY ATTN: SLCBR-DD-T, BLDG. 305	1	COMMANDER US ARMY FGN SCIENCE AND TECH CTR ATTN: DRXST-SD	1
ABERDEEN PROVING GROUND, MD 21005-5066		220 7TH STREET, N.E. CHARLOTTESVILLE, VA 22901	
DIRECTOR US ARMY MATERIEL SYSTEMS ANALYSIS ACTV ATTN: AMXSY-MP	1	COMMANDER US ARMY LABCOM MATERIALS TECHNOLOGY LAB ATTN: SLCMT-IML (TECH LIB)	2
ABERDEEN PROVING GROUND, MD 21005-5071		WATERTOWN, MA 02172-0001	
DIRECTOR US ARMY RESEARCH LABORATORY ATTN: AMSRL-WT-PD (DR. B. BURNS)	1		
ABERDEEN PROVING GROUND, MD 21005-5066			

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET LABORATORIES, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

TECHNICAL REPORT EXTERNAL DISTRIBUTION LIST (CONT'D)

	NO. OF <u>COPIES</u>		NO. OF <u>COPIES</u>
COMMANDER US ARMY LABCOM, ISA ATTN: SLCIS-IM-TL 2800 POWDER MILL ROAD ADELPHI, MD 20783-1145	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/MN EGLIN AFB, FL 32542-5434	1
COMMANDER US ARMY RESEARCH OFFICE ATTN: CHIEF, IPO P.O. BOX 12211 RESEARCH TRIANGLE PARK, NC 27709-2211	1	COMMANDER AIR FORCE ARMAMENT LABORATORY ATTN: AFATL/MNF EGLIN AFB, FL 32542-5434	1
DIRECTOR US NAVAL RESEARCH LAB ATTN: MATERIALS SCI & TECH DIVISION CODE 26-27 (DOC LIB) WASHINGTON, D.C. 20375	1 1		

NOTE: PLEASE NOTIFY COMMANDER, ARMAMENT RESEARCH, DEVELOPMENT, AND ENGINEERING CENTER, US ARMY AMCCOM, ATTN: BENET LABORATORIES, SMCAR-CCB-TL, WATERVLIET, NY 12189-4050, OF ANY ADDRESS CHANGES.

**END
FILMED**

DATE:

9-93

DTIC