

AD-A269 927



WL-TR-93-4005




**IMPLEMENTATION OF A NONISOTHERMAL UNIFIED INELASTIC-STRAIN
THEORY INTO ADINA6.0 FOR A TITANIUM ALLOY - USER GUIDE**

Joseph L. Kroupa
University of Dayton Research Institute
300 College Park
Dayton, OH 45469-0128

JANUARY 1993

INTERIM REPORT FOR JANUARY 1992 to DECEMBER 1992



Approved for public release; distribution is unlimited.

MATERIALS DIRECTORATE
WRIGHT LABORATORY
AIR FORCE MATERIEL COMMAND
WRIGHT-PATTERSON AIR FORCE BASE, OHIO 45433-7734

93--22495



NOTICE

When Government drawings, specifications, or other data are used for any purpose other than in connection with a definitely Government-related procurement, the United States Government incurs no responsibility or any obligation whatsoever. The fact that the government may have formulated or in any way supplied the said drawings, specifications, or other data, is not to be regarded by implication, or otherwise in any manner construed, as licensing the holder, or any other person or corporation; or as conveying any rights or permission to manufacture, use, or sell any patented invention that may in any way be related thereto.

This report is releasable to the National Technical Information Service (NTIS). At NTIS, it will be available to the general public, including foreign nations.


This technical report has been reviewed and is approved for publication.



JAY R. JIRA
Project Engineer
Materials Behavior Branch



ALLAN W. GUNDERSON
Branch Chief
Materials Behavior Branch
Metals and Ceramics Division



NORMAN M. GEYER
Acting Deputy Chief
Metals and Ceramics Division

If your address has changed, if you wish to be removed from our mailing list, or if the addressee is no longer employed by your organization please notify WL/MLLN, Wright-Patterson AFB OH 45433-7817 to help us maintain a current mailing list.

Copies of this report should not be returned unless return is required by security considerations, contractual obligations, or notice on a specific document.

REPORT DOCUMENTATION PAGE			Form Approved OMB No. 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE January 1993		3. REPORT TYPE AND DATES COVERED Interim, January 1992 - December 1992
4. TITLE AND SUBTITLE Implementation of a Nonisothermal Unified Inelastic-Strain Theory into ADINA6.0 for a Titanium Alloy-User Guide			5. FUNDING NUMBERS C: F33615-91-C-5606 PR: 2302 TA: P1 WU: 03 PE: 62102F	
6. AUTHOR(S) Joseph L. Kroupa* and Richard W. Neu**				
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) * University of Dayton Research Institute 300 College Park Dayton, OH 45469-0128 **Wright Laboratory			8. PERFORMING ORGANIZATION REPORT NUMBER	
9. SPONSORING / MONITORING AGENCY NAME(S) AND ADDRESS(ES) Materials Directorate Wright Laboratory Air Force Materiel Command Wright Patterson AFB OH 45433-7734			10. SPONSORING / MONITORING AGENCY REPORT NUMBER WL-TR-93-4005	
11. SUPPLEMENTARY NOTES				
12a. DISTRIBUTION / AVAILABILITY STATEMENT Approved for public release; Distribution is unlimited.			12b. DISTRIBUTION CODE	
13. ABSTRACT (Maximum 200 words) Simulations with many modern aerospace materials require realistic mechanical response models for use in isothermal and nonisothermal applications. One such model is a unified inelastic-strain theory which has been applied to capture the strain-rate sensitivity and time dependent behavior of the titanium alloy Timetal 21S (formerly B21S). The Bodner-Partom form of unified theory satisfactorily describes the B21S stress-strain response for a range of temperatures from 23°C to 815°C and strain rate from 10 ⁻³ /s to 1.X10 ⁻⁷ /s. Practical use of the theory in finite element applications depends on advanced numerical algorithms that rapidly solve the inherently "stiff" constitutive equations. Special "user-defined" subroutines provide the framework for the incorporation of these numerical algorithms into ADINA6.0, a general purpose finite element package. This user-guide contains a brief overview of the theory, the B21S material parameters, subroutine structure, variable nomenclature, and numerical algorithms. Test cases are described to illustrate the numerical integration schemes and provide guidance for error management. The appendices contain hard-copies of the subroutines for two- and three-dimensional elements.				
14. SUBJECT TERMS B21S, Finite element method, ADINA, Unified inelastic strain theory, Bodner-Partom, Timetal 21S			15. NUMBER OF PAGES 87	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

Foreword

Since the writing of this document, the material referenced within as $\beta 21S$ has been trademarked as TIMETAL21S. The work documented in this report has been targeted toward the use of TIMETAL21S with the Bodner-Partom theories; however, much of the final product is applicable to any material response model implemented and verified in ADINA6.0. Similarly, the algorithms presented within are explicitly written and presented for TIMETAL21S; however, they can be easily adopted for any visco-elastic-plastic material with extensive strain-rate sensitivity or time dependent behavior.

SECRETED 1

Accession For

NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	

By _____

Distribution _____

Availability _____

Dist _____ Special _____

A-1

Table of Contents

Section	Content	Page
1.0	Introduction	1
2.0	Bodner-Partom Constitutive Model	2
2.1	Theory	2
2.2	β 21S Material Parameters	6
3.0	Installation of the Subroutines	9
4.0	Structure and Algorithms	11
4.1	Subroutines and Common Blocks	11
4.2	Internal Variable Names	14
4.3	Numerical Algorithms	20
5.0	Example, Verification and Errors	22
5.1	Numerical Example	22
5.2	Solution Verification	24
5.3	Solution Error	30
6.0	References	36
APPENDICES		
A.	User-Defined Subroutines for Two-Dimensional Axisymmetric Elements	38
B.	User-Defined Subroutines for Three-Dimensional Brick Elements	58
C.	ADINAIN3.0 Input File for Verification Test Case 1	77
D.	<i>Mathematica</i> Results for Verification Test Case 1	79
E.	<i>Mathematica</i> Results for Verification Test Case 2	80
F.	<i>Mathematica</i> Results for Verification Test Case 3	81
G.	<i>Mathematica</i> Results for Verification Test Case 4	82
H.	<i>Mathematica</i> Results for Verification Test Case 5	84

List of Figures

Figure	Title	Page
1	Numerical Algorithm for Solving the Bodner-Partom Equations	21
2	Stress-Strain Response and Finite Element Solution Deviation From <i>Mathematica</i> for Test Case 1	25
3	Stress-Strain Response and Finite Element Solution Deviation From <i>Mathematica</i> for Test Case 2	26
4	Stress-Strain Response and Finite Element Solution Deviation From <i>Mathematica</i> for Test Case 3	26
5	Temperature Profile and Stress Response for Non-Isothermal Test Case 4	28
6	Stress-Strain Response and Finite Element Solution Deviation From <i>Mathematica</i> for Test Case 4	28
7	Temperature Profile and Stress Response for Non-Isothermal Test Case 5	29
8	Stress-Strain Response and Finite Element Solution Deviation From <i>Mathematica</i> for Test Case 5	29
9	Effects of Localized Tolerance Parameter TOLER on Finite Element Solution Deviation from <i>Mathematica</i>	32
10	Effects of Major Time Step NSTEP on Finite Element Solution Deviation from <i>Mathematica</i>	33
11	Effects of Sub-Incrementation Parameter XINTER on Finite Element Solution Deviation from <i>Mathematica</i>	33

List of Tables

Tables	Title	Page
1	Material Parameters in Bodner-Partom Constitutive Model	6
2	Bodner-Partom Material Parameters for β 21S	8
3	Subroutine Names and Functions	12
4	Internal Variables of Common Block MATCONST	13
5	State Variables of Common Blocks BPSTAT2 and BPSTAT3	14
6	ADINA Variables Supplied to CUSER2 and CUSER3	15
7	Internal Variables in CUSER2 and CUSER3	18
8	Internal Variables in DBODNER2 and DBODNER3	19
9	Variable Names in ADINAIN3.0 Input File	23
10	Verification Test Cases	25
11	Effects of Finite Element Solution Parameters on CPU time and Solution Deviation	35

Section 1

Introduction

To adequately describe the strain-rate sensitivity and creep behavior of $\beta 21S$ during isothermal and nonisothermal load conditions requires a unified inelastic-strain theory. The unified inelastic-strain theory consisting of a Bodner-Partom flow rule [1] with modifications can adequately model the response of $\beta 21S$. Due to the advanced nature of these theories, many finite element programs do not include these formulations directly into their codes. However, general purpose finite element programs, such as ADINA6.0 [2], do allow user-defined subroutines that can be written to solve unified inelastic-strain theories. This manual describes this unified inelastic strain theory for $\beta 21S$ and provides the associated user-defined subroutines for use with ADINA6.0. The manual is designed to assist the user with implementing these subroutines into ADINA6.0 or modifying the algorithms within these subroutines for use with other material behavior models or finite element codes. These subroutines and associated data files given in the appendices are available by electric mail or on a magnetic medium from the authors.

Section 2

Bodner-Partom Constitutive Model

This section presents the Bodner-Partom constitutive equations and the material parameters that describe the $\beta 21S$ response. Several formulations of the Bodner-Partom model can characterize inelastic deformation under a variety of conditions which may account for anisotropic, isothermal, and/or non-isothermal material response. The formulation presented in the Section 2.1 parallels the previous isotropic nonisothermal theory of Chan, Bodner, and Lindholm [3,4,5]. The terminology is similar to that of Chan and Lindholm [6]. Section 2.2 contains the material parameters that characterize the $\beta 21S$ material.

2.1 Theory

The first assumption in this analysis is the decomposition of the total strain, ϵ_{ij}^{tot} , into elastic, thermal, and inelastic components. This decomposition is expressed as:

$$\epsilon_{ij}^{tot} = \epsilon_{ij}^{el} + \epsilon_{ij}^{th} + \epsilon_{ij}^{in}. \quad \text{Eq. 1}$$

The elastic strains, ϵ_{ij}^{el} , depend on the current stress state, elastic modulus E , and Poisson's ratio ν . The thermal strain components, ϵ_{ij}^{th} , equal the product of the coefficient of thermal expansion and the difference between the current and reference temperatures. The Bodner-Partom flow rule governs the evolution of the inelastic strains, ϵ_{ij}^{in} .

As opposed to other unified inelastic strain formulations, this theory describes the directional (kinematic) hardening with a special directional hardening term. Other theories represent directional hardening phenomena with a "back-stress" modified equivalent stress [7,8,9]. Introduction of the directional hardening term alters the Bodner-Partom flow rule by replacing the previously known variable "drag-stress" with the sum of isotropic and directional hardening terms, Z^I and Z^D , respectively. These two hardening terms enter into the inelastic strain rate equation or flow law:

$$\dot{\epsilon}_{ij}^{in} = D_0 \exp \left\{ -\frac{1}{2} \left(\frac{(Z^I + Z^D)^2}{3J_2} \right)^n \right\} \frac{s_{ij}}{\sqrt{J_2}}, \quad \text{Eq. 2}$$

where D_0 is the limiting strain rate, s_{ij} are the components of deviatoric stress, and $J_2 = s_{ij} s_{ij} / 2$.

The evolutions of Z^I and Z^D have similar empirical forms. Each equation consists of a hardening term, a thermal recovery term, and a temperature rate term. The isotropic hardening evolution equation with these three terms is:

$$\begin{aligned} \dot{Z}^I = & m_1(Z_1 - Z^I) \dot{W}^{in} - A_1 Z_1 \left(\frac{Z^I - Z_2}{Z_1} \right)^{r_1} \\ & + \left(\left(\frac{Z^I - Z_2}{Z_1 - Z_2} \right) \frac{\partial Z_1}{\partial T} + \left(\frac{Z_1 - Z^I}{Z_1 - Z_2} \right) \frac{\partial Z_2}{\partial T} \right) \dot{T}, \end{aligned} \quad \text{Eq. 3}$$

where the inelastic work rate is given by:

$$\dot{W}^{in} = \sigma_{ij} \dot{\epsilon}_{ij}^{in}. \quad \text{Eq. 4}$$

The initial isotropic hardening, $Z^I(0)$, is Z_0 . The material parameters associated with the isotropic hardening evolution are m_1 , Z_0 , Z_1 , Z_2 , A_1 , and r_1 . The thermal differential terms $\frac{\partial Z_1}{\partial T}$ and $\frac{\partial Z_2}{\partial T}$ appropriately scale the isotropic hardening variable when inelastic deformation and thermal recovery do not occur during nonisothermal conditions, thus preventing Z^I from passing through maximum or minimum values with temperature changes. The treatment of these thermal differential terms is more consistent with the work of McDowell [10] and others [11,12,13,14] than those proposed by Chan, Lindholm and Bodner [4]. The thermal differential terms appearing in the user-defined subroutines of Appendices A and B reflect the fact that Z_1 is temperature independent for β_{21S} ; i.e., $\frac{\partial Z_1}{\partial T}=0$.

The scalar product of a state variable, β_{ij} , and a unit stress vector u_{ij} yields the magnitude of the directional hardening term:

$$Z^D = \beta_{ij} u_{ij}, \quad \text{Eq. 5}$$

where:

$$\dot{\beta}_{ij} = m_2(Z_3 u_{ij} - \beta_{ij}) \dot{W}^{in} - A_2 Z_1 \left(\frac{\sqrt{\beta_{kl} \beta_{kl}}}{Z_1} \right)^{r_2} v_{ij} + \frac{\beta_{ij}}{Z_3} \frac{\partial Z_3}{\partial T} \dot{T}, \quad \text{Eq. 6}$$

$$u_{ij} = \frac{\sigma_{ij}}{\sqrt{\sigma_{kl} \sigma_{kl}}}, \quad \text{Eq. 7}$$

and:

$$v_{ij} = \frac{\beta_{ij}}{\sqrt{\beta_{kl} \beta_{kl}}}. \quad \text{Eq. 8}$$

The initial directional hardening variable, $Z^D(0)$ is set to zero. The material constants associated with the directional hardening evolution equation are m_2 , Z_3 , A_2 , and r_2 . The temperature differential term $\frac{\partial Z_3}{\partial T}$ appropriately scales the directional hardening variable when inelastic deformation and thermal recovery do not occur during nonisothermal conditions. In particular, without these differential terms the directional hardening accrued at one temperature may exceed the limiting value Z_3 at another temperature, which is not physically realistic.

Table 1 summarizes the 15 material parameters that characterize the strain-rate sensitivity and time-dependent behavior of $\beta 21S$. The number of material parameters is effectively less than those in Table 1 after applying the usual assumptions: $A_1 = A_2$, $r_1 = r_2$, and $Z_0 = Z_2$. The temperature dependency of these constants is specific to $\beta 21S$. Other materials, such as Mar-M47 or B1900+Hf [5], require different temperature-dependent parameters to represent their particular response.

Table 1

Material Parameters in Bodner-Partom Constitutive Model

Parameter	Units	Description	Temperature Dependency
E	MPa	Elastic modulus	yes
ν	---	Poisson's ratio	no
α	1/°C	Coefficient of thermal expansion	yes
D_0	s^{-1}	Limiting shear strain rate	no
Z_0	MPa	Initial value of the isotropic hardening variable	yes
Z_1	MPa	Limiting (maximum) value of Z	no
Z_2	MPa	Fully recovered (minimum) value of Z^I	yes
Z_3	MPa	Limiting (maximum) value of Z^D	yes
m_1	MPa^{-1}	Hardening rate coefficient of Z^I	yes
m_2	MPa^{-1}	Hardening rate coefficient of Z^D	yes
n	---	Strain rate sensitivity parameter	yes
A_1	s^{-1}	Recovery coefficient for Z^I	yes
A_2	s^{-1}	Recovery coefficient for Z^D	yes
r_1	---	Recovery exponent for Z^I	yes
r_2	---	Recovery exponent for Z^D	yes

2.2 β 21S Material Parameters

The material parameters for the Bodner-Partom model with directional hardening were determined from β 21S using monotonic, cyclic, and creep test data [15]. The parameters are valid for a wide window of strain rates (10^{-3} to 10^{-7} 1/s) and temperatures (23° - 815°C). The strategy for determining the parameters involves a number of steps. First, the temperature-dependent

parameters are identified and the values of the temperature-independent parameters are estimated. Then at each temperature where experimental data are available, the temperature-dependent parameters are determined through an iterative process to minimize the differences between the model simulations and experiments. *Mathematica* [16] is used to generate the model simulations. Similar to other inelastic strain theories, the set of material parameter for any particular load case is not unique. Thus, for a given set of experimental load responses, a range of values are suitable for each material parameter.

The resulting set of temperature-dependent parameters becomes continuous with temperature as the range of possible values is decreased for each parameter. The response can be very sensitive to small changes in some of the material parameters with temperature, especially in the transition regimes between different deformation mechanisms. For $\beta 21S$, a transition region for inelastic behavior occurs between 482°C for plasticity and at 650°C for power law creep. Thus, an anomalous change in the saturated stress level can occur if linear interpolation of material parameters is used within this transition region.

Since no experimental data are available within this transition region, values for temperature-dependent parameters are chosen between 482°C and 650°C so that the resulting saturated stress is smooth and continuous with temperature, thus reducing the anomalous effects of linear interpolation. The final version of the material parameters (version 4.0) for $\beta 21S$ are shown in Table 2.

Table 2

Bodner-Partom Material Parameters for $\beta 215$ Temperature-Independent Constants

$m_1 = 0 \text{ MPa}^{-1}$ (no isotropic hardening)	$Z_1 = 1600 \text{ MPa}$
$r_1 = r_2 = 3$	$D_0 = 1 \times 10^4 \text{ s}^{-1}$
$n = 0.34$	

Temperature-Dependent Constants

Temp.	E	α^*	n	$Z_0 = Z_2$	Z_3	m_2	$A_1 = A_2$
$^{\circ}\text{C}$	MPa	$10^{-6}/^{\circ}\text{C}$		MPa	MPa	MPa^{-1}	s^{-1}
23	112000	6.31	4.8	1550	100	0.35	0
260	108000	7.26	3.5	1300	300	0.35	0
315	ϕ	ϕ	$\diamond$	$\diamond$	390	$\diamond$	ϕ
365	ϕ	ϕ	$\diamond$	$\diamond$	500	$\diamond$	ϕ
415	ϕ	ϕ	$\diamond$	$\diamond$	660	$\diamond$	ϕ
465	ϕ	ϕ	$\diamond$	$\diamond$	960	$\diamond$	ϕ
482	98100	8.15	1.7	1100	1100	5	0.0076
500	ϕ	ϕ	1.5	$\diamond$	1300	$\diamond$	ϕ
525	ϕ	ϕ	1.28	$\diamond$	1670	$\diamond$	ϕ
550	ϕ	ϕ	1.1	$\diamond$	2100	$\diamond$	ϕ
575	ϕ	ϕ	0.97	$\diamond$	2600	$\diamond$	ϕ
600	ϕ	ϕ	0.82	$\diamond$	3700	10	ϕ
650	86600	8.83	0.74	1000	3800	10	0.21
760	77200	9.27	0.58	600	4000	15	1.0
815	72000	9.49	0.55	300	4100	30	2.0

* Secant α with $T_0 = 25^{\circ}\text{C}$

$\diamond$ - Linear interpolate between values given in table.

ϕ - Use functions to determine values.

Bold were values determined based on experiments.

Italics are values that describe smooth and continuous saturated stress change.

Functions

$$E = 112000 + 0.591 T - 0.061 T^2 \quad T \text{ in } ^{\circ}\text{C}$$

$$\alpha = 6.22 \times 10^{-6} + 4.01 \times 10^{-9} T \quad T \text{ in } ^{\circ}\text{C}$$

$$A_1 = A_2 = 5.8 \times 10^5 \exp\left(\frac{-1.37 \times 10^4}{T + 273}\right) \quad T \text{ in } ^{\circ}\text{C}$$

Section 3

Installation of the Subroutines

Included with the delivered version of ADINA 6.0 are overlay files that allow users to incorporate new segments of code into certain regions within ADINA's algorithms. Two particular overlay files, ovl030u.f and ovl040u.f, contain examples of user-defined subroutines that incorporate alternative material response models into ADINA. Within these two files, the user-defined subroutines, CUSER2 and CUSER3, contain sections of code that are modified to implement the Bodner-Partom model into ADINA's two- and three-dimensional elements, respectively. The Bodner-Partom versions of the user-defined subroutines for the two-dimensional axisymmetric and three-dimensional brick elements reside in deliverable files, cuser2_dbeta.f and cuser3_dbeta.f, respectively (see Appendices A and B). The last step of the installation process is to integrate the subroutines within these two files into ADINA's numerical algorithms.

Integrating the Bodner-Partom user-defined subroutines into ADINA6.0 can be accomplished by several methods. One method is replacing the subroutines within the overlay files from ADINA with those of cuser2_dbeta.f and cuser3_dbeta.f. Another method consists of linking new object code over the pre-existing object code. In particular, subroutines of files cuser2_dbeta.f and cuser3_dbeta.f are compiled for produce two object files. These object files are then linked with ADINA's object code to generate a new executable version of ADINA that contains the Bodner-Partom algorithms. Unfortunately, each linker (or loader) is machine dependent. For example, some linkers may declare

multiple subroutine declarations and cease the operation. Renaming or replacing the subroutines CUSER2 and CUSER3 in overlay files, ovl030u.f and ovl040u.f, respectively, will correct these errors. Refer to your FORTRAN77 manual to determine the details of your particular linker or segment loader.

To avoid a common error, check the precision (single or double) of the existing user-subroutines found in ADINA's overlay files (e.g., olv030u.f). Then, modify the variable precision of the subroutines in files cuser2_dbeta.f and cuser3_dbeta.f to be of the same precision as found in the overlay files.

Section 4

Structure and Algorithms

This section describes the structure and numerical algorithms of the Bodner-Partom modified subroutines which characterize the strain-rate sensitivity and creep behavior of $\beta 21S$. Several tables briefly describe subroutine nomenclature and variable usage. Then, the numerical algorithm that solve the Bodner-Partom equations is outlined. Hard copies of the subroutines described in this section reside in the files `cuser2_dbeta.f` and `cuser3_dbeta.f` for the two-dimensional axisymmetric and three-dimensional brick elements, respectively. (see Appendices A and B). Subroutine structure and variables usage are identical for the two-dimensional and three-dimensional elements. Thus the details are only presented for the two-dimensional case. The names appended with 2 and 3 designate the two- and three- dimensional case, respectively. For example, `CUSER2` and `CUSER3` are user-defined subroutines for the two- and three-dimensional cases, respectively.

4.1 Subroutines and Common Blocks

The functionality of subroutines found in `cuser2_dbeta.f` are summarized in Table 3. Subroutines `IUSER` and `USER2` appear in the overlay file `ovl030u.f` which is supplied with the ADINA6.0 [2]. Subroutine `CUSER2` has four major functions that integrate new material behavior models into the ADINA code. The four functions include -- 1) the initialization of internal state variables, 2) the determination of new states from previous strains and current incremental strains, 3) the computation of incremental stiffness matrix, D , and 4) output of

the converged solution. A minor function of CUSER2 is to retrieve and store state variables from ADINA's working variable, ARRAY. Subroutine STGET2 retrieves while STPUT2 stores these variables from ARRAY. DBODNER2 contain the numerical algorithms that solve the Bodner-Partom constitutive equations found in Section 2.1

Table 3

Subroutine Names and Functions

Subroutine*	Called From	Function
CUSER2	IUSER2 and USER2	to determine stresses from user-defined material behavior models
STGET2	CUSER2	to retrieve state variables from working variable ARRAY
STPUT2	CUSER2	to store state variables from working variable ARRAY
DBODNER2	CUSER2	to solve the constitutive equations of the Bodner Partom model

*Two-dimensional subroutines are listed. The three-dimensional subroutines are designated with a suffix 3 rather than a 2.

The two common blocks MATCONST and BPSTAT2 retain values of certain variables entering from other subroutines. MATCONST transfers material constants and associated temperature differentials between CUSER2 and DBODNER2. Table 4 lists variables that are in common block MATCONST. MATCONST is the same common block in the two-dimensional element as found in the three-dimensional elements. Common block BPSTAT2 transfers the values of the internal state variables (e.g., inelastic strain, isotropic hardening, etc.) between all the subroutines. Table 5 contains the state variables of common block BPSTAT2 and BPSTAT3.

Table 4

Internal Variables of Common Block MATCONST

Variable Name	Symbol	Variable Description
E	E	elastic modulus, CTD(1)
AN	n	kinetic parameter, CTD(2)
Z0,Z2	Z ₀ , Z ₂	fully recovered (minimum) value of isotropic hardening, CTD(3)
Z3	Z ₃	limiting (maximum) value of directional hardening, CTD(4)
AM2	m ₂	hardening rate coefficient of directional hardening, CTD(5)
A1, A2	A ₁ , A ₂	thermal recovery coefficient for hardening, (determined by CTD(6) and CTD(7))
AM1	m ₁	isotropic hardening rate coefficient, CTI(1)
Z1	Z ₁	limiting value of isotropic hardening, CTI(2)
R1, R2	r ₁ , r ₂	thermal recovery exponent for hardening, CTI(3)
D0	D ₀	limiting inelastic strain rate, CTI(4)
ANU	v	Poisson's ratio, CTI(5)
G	G	shear modulus
AK	K	bulk modulus
DAM2	$\frac{\partial m_2}{\partial T} \frac{\partial T}{\partial t} dt$	differential am2 with solution increment
DAN	$\frac{\partial n}{\partial T} \frac{\partial T}{\partial t} dt$	differential an with solution increment
DZ0	$\frac{\partial Z_0}{\partial T} \frac{\partial T}{\partial t} dt$	differential Z ₀ with solution increment
DZ2	$\frac{\partial Z_2}{\partial T} \frac{\partial T}{\partial t} dt$	differential Z ₂ with solution increment
DZ3	$\frac{\partial Z_3}{\partial T} \frac{\partial T}{\partial t} dt$	differential Z ₃ with solution increment
DA1	$\frac{\partial A_1}{\partial T} \frac{\partial T}{\partial t} dt$	differential A ₁ with solution increment
DA2	$\frac{\partial A_2}{\partial T} \frac{\partial T}{\partial t} dt$	differential A ₂ with solution increment
DG	$\frac{\partial G}{\partial T} \frac{\partial T}{\partial t} dt$	differential shear modulus with solution increment
DK	$\frac{\partial K}{\partial T} \frac{\partial T}{\partial t} dt$	differential bulk modulus with solution increment

Table 5

State Variables of Common Blocks BPSTAT2 and BPSTAT3

Variable Name	Symbol	Variable Description
EIN	ϵ_{ij}^{in}	components of inelastic strain
ZI	ZI	current isotropic drag stress
SIGEFF	$\sqrt{3}J_2$	effective stress
ZD	ZD	current magnitude of directional drag stress
BETA	β_{ij}	components of directional drag stress
EPS0	---	mechanical strain at the beginning of ADINA's time TAU

4.2 Internal Variable Names

This section summarizes the internal variables of the user-defined subroutines described in the previous section (4.1). Table 6 presents ADINA6.0 internal variables which enter into CUSER2 and CUSER3 from subroutines USER2 and USER3, respectively. Table 7 reviews the variables found within CUSER2 and CUSER3, while Table 8 lists the variables found in DBODNER2 and DBODNER3.

Some variables change values at certain locations within the numerical scheme. For example, the variable STRESS may have a different value when exiting subroutines CUSER2 than entering. The values of such variables depend on solution control variables -- TIME, TAU, INTER, and KTR. The variable TIME

refers to the time at the beginning of a major time step, NSTEP. TAU is the value of time at the beginning of a sub-incremental time step. INTER and KTR are control variables for ADINA's sub-incremental solution scheme. ADINAIN3.0 manuals [17] provide details of this sub-incremental solution scheme. Variables, DT and DTAU, refer to major and sub-incremental time steps sizes, respectively.

Table 6
ADINA Variables Supplied to CUSER2 and CUSER3

Variable Name	Variable Description
KEY = 1	initialize the working arrays during input phase
KEY = 2	calculate element stresses
KEY = 3	calculate the stress/strain matrix
KEY = 4	print stresses and other desired variables during stress print-out
NG	element group number
NEL	element number
IPT	integration point number
IT2D	2d element type identifier
IT2D EQ.0	axisymmetric (in y-z plane)
IT2D EQ.1	plane strain (in y-z plane)
IT2D EQ.2	plane stress (in y-z plane)
IT2D EQ.3	plane stress (in 3/d space)
STRESS	stress components, received at time TAU and updated to time TAU+DTAU
EPS	total strain components at time TIME.
STRAIN	total strain components at time TIME+DT.
DEPS	subdivided incremental mechanical strain components (total incremental strain minus incremental thermal strains)
DEPST	components of sub incremental thermal strain
THSTR1	total thermal strain at time TAU
THSTR2	total thermal strain at time TAU+DTAU
INTER	number of subdivisions for the strain increments

Table 6 (continued)
ADINA Variables Supplied to CUSER2 and CUSER3

Variable Name	Variable Description
KTR KTR = 1 KTR = INTER	current subdivision number for first subdivision for last subdivision
SCP	solution control parameters
SCP(1)	relaxation factor
SCP(2)	Bodner-Partom convergence tolerance
SCP(3)	element number for special history output
SCP(4)	Gauss point for special history output
ARRAY	working array (real) for user-defined state variables at time TAU and updated by user-supplied coding to correspond to time TAU+DTAU
IARRAY	working array (integer) for user-defined state variables at time TAU and updated by user-supplied coding to correspond to time TAU+DTAU
D	stress/strain matrix , to be calculated by user-supplied coding
ALFA	coefficient of thermal expansion at time TAU
CTD	temperature-dependent material constants at time TAU
CTD(1)	elastic modulus, E
CTD(2)	kinetic parameter, n
CTD(3)	fully recovered (minimum) value of isotropic hardening, Z_0, Z_2
CTD(4)	limiting (maximum) value of directional hardening, Z_3
CTD(5)	hardening rate coefficient of directional hardening, m_2
ALFAA	coefficient of thermal expansion at time TAU+DTAU
CTDD	temperature-dependent material constants (same as CTD) at time TAU+DTAU
CTI	temperature-independent material constants
CTI(1)	isotropic hardening rate coefficient, m_1
CTI(2)	limiting value of isotropic hardening, Z_1
CTI(3)	recovery coefficient for drag hardening, r_1, r_2

Table 6 (continued)
ADINA Variables Supplied to CUSER2 and CUSER3

Variable Name	Variable Description
CTI(4)	limiting inelastic strain rate, D_0
CTI(5)	Poisson's ratio, ν
CTI(6)	coefficient for recover coefficient (functional form for A_1 , A_2)
CTI(7)	exponential for recover coefficient (functional form for A_1 , A_2)
TMP1	temperature at integration point IPT at time TAU
TMP2	temperature at integration point IPT at time TAU+DTAU
TIME	time at current step
DT	time step increment
INTEG	integration parameter for stress integration
ISUBM	flag for continuation of subdivision in time step
INDNL	flag for element formulation

Table 7
Internal Variables in CUSER2 and CUSER3

Variable Name	Variable Description
RELAX	relaxation factor, SCP(1)
TOLER	Bodner-Partom convergence tolerance, SCP(2)
HINT	Gauss point for special history output, SCP(3)
HELE	element number for special history output, SCP(4)
E	elastic modulus, CTD(1)
AN	kinetic parameter, CTD(2)
Z0,Z2	fully recovered (minimum) value of isotropic hardening, CTD(3)
Z3	limiting (maximum) value of directional hardening, CTD(4)
AM2	hardening rate coefficient of directional hardening, CTD(5)
AM1	isotropic hardening rate coefficient, CTI(1)
Z1	limiting value of isotropic hardening, CTI(2)
R1,R2	recovery exponent for hardening, CTI(3)
D0	limiting inelastic strain rate, CTI(4)
ANU	Poisson's ratio, CTI(5)
DTAU	time increment step
G	shear modulus
AK	bulk modulus
ALPHA1	biaxial model parameter (not used)
DAM2	differential am2 with solution increment
DAN	differential an with solution increment
DZ0	differential Z ₀ with solution increment
DZ2	differential Z ₂ with solution increment
DZ3	differential Z ₃ with solution increment
DA1	differential A ₁ with solution increment
DA2	differential A ₂ with solution increment
DG	differential shear modulus with solution increment
DK	differential bulk modulus with solution increment

Table 8
Internal Variables in DBODNER2 and DBODNER3

Variable Name	Variable Description
DEVEPS	deviatoric strains
EPS	mechanical strains (total minus thermal)
AVGEPS	average (mean) normal strain
DDEPS	sub-incremental deviatoric strains
DEIEFF	effective inelastic strain increment
DEPS	incremental mechanical strain (total minus thermal)
DEPSI	incremental inelastic deviatoric strain
DEVSIG	deviatoric stress
ICOUNT	iteration loop counter
ISUB	number of sub-increments within DBODNER2
RELAX	relaxation factor for new stress estimate
TOLER	tolerance for convergence
SIGNEW	effective stress of previously converged stress state
SIGOLD	old estimate effective stress
SIGEST	new effective stress estimate
SIGHYD	hydrostatic (mean) stress
STRES0	stress of previously converged stress state
STRESS	current stress
TIME	current time value
EINEST	estimated inelastic strains
EIN0(4)	inelastic strains of previously converged stress state
BETADOT	directional drag stress rate vector
BETAEST	estimated directional drag stress vector
BETA0(4)	directional drag stress of previously converged stress state
U, V	directional unit vectors
ZIEST	estimated isotropic drag stress

4.3 Numerical Algorithms

The algorithms that solve the Bodner-Partom constitutive equations consist of a mixture of iteration loops and sub-incremental schemes. This hybrid combination of iterations and sub-incrementation works well for the inherently "stiff" nature of the Bodner-Partom differential equations and β_{215} material parameters. The algorithms discussed in this section are found in subroutines DBODNER2 and DBODNER3.

The algorithm, as shown in Figure 1, consists of two iteration loops and a sub-incremental solution scheme. Prior to sub-incremental integration, state variable values assume their pre-incremental values; the number of sub-increments (ISUB) initializes to one; and constant rate variables get scale by TFACTOR. The integration of the sub-incremental loop begins at Step III. The primary iteration loop starts at step III.D and converges on stress, inelastic strain, isotropic hardening and the directional hardening parameters. Preliminary investigations on convergence found that the rate equations for β_{ij} , Eq. (6) strongly depend on the current value of β_{ij} , thus making convergence on β_{ij} difficult. The value for Z^D often diverges during the primary iteration loop. The second iteration loop, starting to Step III.D.3, saves computational time by determining Z^D divergence more quickly than the primary iteration loop, since the second loop avoids several numerical operations found in the primary iteration loop. Non-convergent solutions, as defined by a maximum limit set on iteration steps, return to the beginning of the sub-incremental integration (Step I) with an increase in the number of sub-increments, ISUB. When the maximum number of sub-incremental step equals 128, the solution solver ceases operation and prints a diagnostic debugging output.

- I. Store variable at the beginning of solution increment
 - A. state variables
 - B. temperature-dependent material parameters
- II. Initialize variables for sub-incremental solution step cutting of ISUB
 - A. initialize estimated new values for state variables
 - B. restore material parameters from Step I
 - C. determine new material parameters rates by factors of ISUB
 - D. restore state variables to values from Step I
- III. Begin sub-incremental solution integration
 - A. update all temperature-dependent parameters to end of sub-incremental step
 - B. update deviatoric and mean mechanical strains
 - C. step iteration counter ICOUNT
 - D. begin primary iteration loop
 1. estimate inelastic strain increment (engineering inelastic shear strains are computed)
 2. compute new stress state and inelastic work rate
 3. begin secondary iteration loop on directional hardening variable BETA
 - a. compute beta rate
 - b. compute new estimate for beta
 - c. check for convergence of beta
 - (1) if converged, then continue
 - (2) if not, then increase cutting factor ISUB by factor of 2.0 and precede to Step II.A
 - d. stop solution for excessive number of time cuts
 4. compute new estimate for isotropic hardening
 5. check for convergence of effective stress, incremental inelastic strains, isotropic and directional hardening
 - a. if converged, then continue with conclude current sub-increment via. STEP III.E
 - b. if not, make new estimate for effective stress and increase iteration count ICOUNT BY 1.
 - c. check for excessive iteration count
 - (1) if excessive, then increase cutting factor ISUB by factor of 2.0 and precede to Step II.A
 - (2) if not, to Step III.D
 - E. Update converged solution with estimates, then continue a STEP III.A
- IV. Complete all sub-incremental cycles and then return to CUSER2 (or CUSER3)

Figure 1 Numerical Algorithm for Solving of Bodner-Partom Equations.

Section 5

Example, Verification and Errors

This section provides an example of the application of the Bodner-Partom user-defined subroutines with the $\beta 21S$ material parameters. The example ADINAIN3.0 input file for a simple test case. This section also presents several numerical exercises that serve as a basis for comparisons of results from an independent solution source with those from the finite element method. The difference between the results from these two solution sources are measures of accuracy for these algorithms and associated integration schemes. The last part of this section presents an investigation that guides the users of these subroutines to minimize errors effectively.

5.1 Numerical Example

The file, vcase1.in, (see Appendix C) is an example ADINAIN3.0 input file that contains the required $\beta 21S$ material parameters. ADINA6.0 preprocessor ADINAIN3.0 generates a data file that executes the user-defined subroutines that were implemented into ADINA6.0. The example consists of an axisymmetric element unidirectionally loaded at a constant strain rate of $833.3 \times 10^{-6}/s$ and constant temperature of $25^{\circ}C$, which has the same conditions of verification test case 1 (discussed below). Input of the $\beta 21S$ material properties starts with the string "MATERIAL 1 USER ..." (see Appendix C). The cards that refer to material and solution parameters are described in Table 9 [17]. In these example analyses, the thermal expansion coefficients are set to zero, since the comparisons made here only consider mechanical strain (total strain minus thermal strain).

Table 9 [17]

Variable Names in ADINAIN3.0 Input File

Variable Name*	Variable Description
ALFA	coefficient of thermal expansion
CTD(1)	elastic modulus, E
CTD(2)	kinetic parameter, n
CTD(3)	fully recovered (minimum) value of isotropic hardening, Z_0, Z_2
CTD(4)	limiting (maximum) value of directional hardening, Z_3
CTD(5)	hardening rate coefficient of directional hardening, m_2
CTI(1)	isotropic hardening rate coefficient, m_1
CTI(2)	limiting value of isotropic drag stress, Z_1
CTI(3)	thermal recovery exponent for hardening, r_1, r_2
CTI(4)	limiting inelastic strain rate, D_0
CTI(5)	Poisson's ratio, ν
CTI(6)	coefficient for thermal recovery's functional form of A_1 and A_2
CTI(7)	exponential for thermal recovery's functional form for A_1 and A_2
XINTER	number of incremental subdivisions of NSTEP
SCP(1)	relaxation factor
SCP(2)	Bodner Partom convergence tolerance, TOLER
SCP(3)	element number for special history output 'fort.53'
SCP(4)	Gauss point for special history output file 'fort.53'

*User-defined material parameters as described in ADINAIN3.0 manual [17]

5.2 Solution Verification

This section presents five comparisons of the finite element results with those obtained through an independent solution source. These test cases consist of three isothermal and two nonisothermal simulations. The accuracy measure for this investigation is percent deviation of the finite element stress solution from *Mathematica* [16], which has an associated error of approximately 10^{-4} percent. The percent stress deviation, %D, is written as:

$$\%D = 100\% * \left| \frac{\sigma_{FE} - \sigma_{math}}{\sigma_{math}} \right|. \quad \text{Eq. (9)}$$

Where σ_{FE} and σ_{math} are the stresses obtained from the finite element and *Mathematica* solutions, respectively. The two- and three-dimensional finite element stress solutions are identical, thus only one finite element solution deviation is shown.

All test cases simulate monotonically loaded elements with constant mechanical strain rates of either $833.3 \times 10^{-6}/s$ or $8.33 \times 10^{-6}/s$. Table 10 summarizes all the test conditions and location in the appendices of the *Mathematica* solution files used in the comparisons. The data in these files appear in Appendices D through H. Figures 2, 3 and 4 illustrate the stress-strain response and the finite element stress deviation from *Mathematica* for isothermal Test Cases 1, 2, and 3, respectively. Overall, the isothermal load cases show that the finite element and *Mathematica* solutions are well within 0.5 percent of predicting the same response.

Table 10

Verification Test Cases

Test Case Number	Temperature (°C)	Thermal Condition	Strain Rate (10 ⁻⁶ /s)	<i>Mathematica</i> Solution File	Appendix
1	25	isothermal	833.3	vcase1.math	D
2	650	isothermal	833.3	vcase2.math	E
3	650	isothermal	8.333	vcase3.math	F
4	25/482/25	non-isothermal	833.3	vcase4.math	G
5	650/760/650	non-isothermal	833.3	vcase5.math	H




Figure 2 Stress-Strain Response and Finite Element Solution Deviation from *Mathematica* for Test Case 1




Figure 3 Stress-Strain Response and Finite Element Solution Deviation from *Mathematica* for Test Case 2




Figure 4 Stress-Strain Response and Finite Element Solution Deviation from *Mathematica* for Test Case 3

The nonisothermal test cases are constant strain-rate tensile simulations with changes in temperatures at prescribed strain levels. These non-isothermal loading profiles provide an excellent basis to evaluate the various forms of state-variable temperature differentials (e.g., $\frac{\partial Z_1}{\partial T}$, $\frac{\partial Z_2}{\partial T}$ and $\frac{\partial Z_3}{\partial T}$). The temperature profile and stress-strain response of Test Case 4 are illustrated in Figure 5 with the associated finite element solution deviation from *Mathematica* presented in Figure 6. The temperature profile and stress response for Test Case 5 are shown in Figure 7 with solution deviation given in Figure 8. Overall, the finite element and mathematica stresses are well within 0.5 percent of predicting the same response for the nonisothermal segments of the loading. During the nonisothermal periods of loading the percent deviation increases slightly, which is more evident in Test Case 5 than in of Test Case 4. For practical use, more solution increments and/or smaller convergence tolerances may be required to achieve the same level accuracy for non isothermal loading segments as those obtained during isothermal periods, especially at elevated temperatures.




Figure 5 Temperature Profile and Stress Response for Non-Isothermal Test Case 4




Figure 6 Stress-Strain Response and Finite Element Solution Deviation from *Mathematica* for Test Case 4




Figure 7 Temperature Profile and Stress Response for Non-Isothermal Test Case 5




Figure 8 Stress-Strain Response and Finite Element Solution Deviation from *Mathematica* for Test Case 5

5.3 Solution Error

Preliminary investigations with Test Case 5 revealed an unacceptable deviation between finite element and *Mathematica* solutions (2.9%). The poor correlation occurred when Test Case 5 consisted of 48 solution increments, rather than the 96 increment case shown in Figure 8. The nature of the excessive solution deviation is determined as each solution parameter is systematically changed. The investigation considers two types of solution parameters -- iteration convergence tolerances and solution increment number.

Iteration convergence tolerances occur at two different levels within the numerical algorithms -- global and local. Global tolerance DNORM is a measure of convergence on displacements and forces (energy) within the entire system of nodes and elements for each major time step, NSTEP. On the local level, within the Bodner-Partom iteration schemes (see Section 4.3) the tolerance parameter TOLER measures the accuracy of the converged stress state for strain increments sent to each elemental Gauss point.

The global parameter DNORM is not a direct measure of solution convergence tolerance within ADINA. Convergence occurs when the change in displacement, $|d\underline{u}|$, for each global iteration estimate becomes relatively small compared to DNORM, which is expressed as:

$$\frac{|d\underline{u}|}{DNORM} \leq DTOL. \quad \text{Eq. (10)}$$

With the displacement tolerance DTOL set constant, a change in DNORM directly alters the solution tolerance. Since, DNORM parameter has no standard default value within ADINA, this investigation considers variations in DNORM rather than DTOL. The previously completed analyses of Section 5.2 used a DNORM base-line value of 1.0×10^{-5} . Values of DNORM for this investigation are 1.0×10^{-3} and 1.0×10^{-4} . The change of DNORM to 1.0×10^{-3} or 1.0×10^{-4} produces a only a small change in stress solution (less than 0.1%).

The changes in the localized tolerance parameter TOLER within the Bodner-Partom iteration loops, results in minor shift in the solution (0.25%), as illustrated in Figure 9. Overall, the tighter tolerances of DNORM and TOLER still produced unacceptable levels of solution deviation from *Mathematica*. Note that in change in TOLER from 0.001 to 0.00001 did increase the finite element solution running time from 122 to 431 CPU seconds*, respectively, as shown in Table 11. Based on the marked debit in computational efficiency with little increase in solution accuracy, increasing TOLER for a more accurate solution is not practical. However, the TOLER at and above 0.001 can produce non-convergent solutions, especially if the finite element configuration contains additional non-linearities (e.g. gap elements). A smaller values for TOLER to may be required to achieve convergence for these highly non linear solutions.

* CPU time on a Sun Sparc Station II with 4/75 processor




Figure 9 Effects of Localized Tolerance Parameter, TOLER, on Finite Element Solution Deviation from *Mathematica*.

ADINA's integration scheme has two different levels of incrementing the solution -- major and minor. The global convergence of displacements occurs at the major solution increment, NSTEP. The minor solution increment sub-divides the major increment by XINTER for quicker integration of the nonlinear material models. Increasing either NSTEP or XINTER decreases the solution deviation, as shown in Figures 10 and 11, respectively. The decrease of solution deviation with increases in solution time steps is more significant than changes caused by increasing the tolerance parameters.




Figure 10 Effect of Major Time Step NSTEP on Finite Element Solution Deviation from *Mathematica*.




Figure 11 Effect of Sub-incremental Parameter XINTER on Finite Element Solution Deviation from *Mathematica*.

To summarize, this error investigation only considers a simple unidirectional test case during nonisothermal loading; however, knowledge of the results will save time and effort when conducting similar error investigation for more complex cases. First, note that the errors associated with isothermal conditions are quite small compared to those of nonisothermal loading periods, even with a few time steps. For the nonisothermal Test Case 5, Table 11 presents a summary of finite element solution parameters and their effects on computer CPU* time and solution deviation. Increases in solution tolerances DNORM and TOLER do not significantly change the resulting stress error; however, CPU time did increase. Increases in number of solution increments, NSTEP or XINTER, significantly decrease the solution error, while CPU time remains relatively constant. Overall, the most accurate solution per CPU time occurs with increased number of major time steps, NSTEP.

*CPU time on a Sun Sparc Station II with 4/75 processor

Table 11

Effects of Finite Element Solution Parameters
on CPU* Time and Solution Deviation

NSTEP	DNORM	XINTER	TOLER	CPU Time (s)	Maximum Percent Deviation
48	1.0×10^{-5}	10	0.0001	206	2.96
48	1.0×10^{-4}	10	0.0001	173	3.02
48	1.0×10^{-3}	10	0.0001	149	3.02
48	1.0×10^{-5}	5	0.0001	180	6.51
48	1.0×10^{-5}	20	0.0001	204	1.25
48	1.0×10^{-5}	10	0.001	122	3.16
48	1.0×10^{-5}	10	0.00001	432	3.23
96	1.0×10^{-5}	10	0.0001	200	1.25
192	1.0×10^{-5}	10	0.0001	179	0.362
384	1.0×10^{-5}	10	0.0001	231	0.0478
<i>Mathematica</i>	---	---	---	2638	---

* CPU time on a Sun Sparc Station II with 4/75 processor

Section 6

References

- (1) Bodner, S.R., and Partom, Y., "Constitutive Equations for Elastic-Viscoplastic Strain Hardening Materials," ASME Journal of Applied Mechanics, Vol. 42, 1975, p.385.
- (2) Bathe, K.J., "Finite Elements in CAD and ADINA," Nuclear Engineering and Design, Vol. 98, 1986, pp.57-67.
- (3) Chan, K.S., Bodner, S.R., and Lindholm, U.S., "Phenomenological Modeling of Hardening and Thermal Recovery in Metals," ASME Journal of Engineering Materials and Technology, Vol. 110, January 1988, pp.1-8.
- (4) Chan, K.S., Lindholm, U.S., Bodner, S.R., and Nagy, A., "High Temperature Inelastic Deformation of the B1900+Hf Alloy Under Multiaxial Loading: Theory and Experiment," ASME Journal of Engineering Materials and Technology, Vol. 112, January 1990, pp. 7-14.
- (5) Chan, K.S., Lindholm, U.S., Bodner, S.R., "Constitutive Modeling for Isotropic Materials (HOST), NASA CR-182132 (SwRI-7576), NASA Lewis June 1988.
- (6) Chan, K.S. and Lindholm, U.S. "Inelastic Deformation Under Nonisothermal Loading," ASME Journal of Engineering Materials and Technology, Vol. 112, January 1990, pp.15-25.
- (7) Sherwood, J.A. and Boyle, M.J., "Investigation of the Thermomechanical Response of a Titanium Aluminide/Silicon Carbide Composite Using a Unified State Variable Model in ADINA," Computers and Structures, Vol. 40, 1991, pp.257-269.
- (8) Ramaswamy, V.G., Stouffer, D.C., and Laflen, J.H., "A Unified Constitutive Model for the Inelastic Uniaxial Response of Rene'80 at Temperatures Between 538C and 982C," Transactions of the ASME, Vol. 112, July 1990, pp. 280-286.
- (9) Stouffer, D.C., Ramaswamy, V.G., Laflen, J.H., Van Stone, R.H., and Williams, R., "A Constitutive Model for the Inelastic Multiaxial Response of Rene'80 at 871C and 982C," ASME Journal of Engineering Materials and Technology, Vol. 112, April 1990, pp.241-246.

References (Continued)

- (10) McDowell, D.L., "A Bounding Surface Theory for Cyclic Thermoplasticity," ASME Journal of Engineering Materials and Technology, Vol. 114, July 1992, pp. 297-303.
- (11) Walker, K. P., "Research and Development Program for Nonlinear Structural Modeling with Advanced Time-Temperature Dependent Constitutive Relationships," NASA Report CR-165533, 1981.
- (12) Freed, A. D., "Thermoviscoplastic Model With Application to Copper," NASA Report TP-2845, 1988.
- (13) Chaboche, J. L., "Constitutive Equations for Cyclic Plasticity and Cyclic Viscoplasticity," International Journal of Plasticity, Vol. 5, 1989, pp. 247-302.
- (14) Wang, J.-D. and Ohno, N., "Two Equivalent Forms of Nonlinear Kinematic Hardening: Application to Nonisothermal Plasticity," International Journal of Plasticity, Vol. 7, 1991, pp. 637-650.
- (15) Ashbaugh, N.E., and Khobaib, M., Unpublished Data, University of Dayton Research Institute, Dayton, Ohio.
- (16) Wolfram, S., Mathematica-A System for Doing Mathematics by Computer, Sec. Ed., 1991, Addison-Westley Publishing Company, Inc., Redwood City, CA.
- (17) ADINA-IN for ADINA Users Manual, Report ARD 90-4, ADINA R&D. Inc., September 1990, 71 Elton Ave, Watertown, MA., 02172.

Appendix A

User-Defined Subroutines for Two-Dimensional Axisymmetric Elements (file cuser2_dbeta.f)

```

SUBROUTINE CUSER2 (NG,NEL,IPT,IT2D,STRESS,EPS,STRAIN,DEPS,DEPST,
A      THSTR1,THSTR2,KTR,INTER,SCP,ARRAY,IARRAY,D,
B      ALFA,CTD,ALFAA,CTDD,CTI,TMP1,TMP2,TIME,DTAU,
C      PHIST,PRST,ANGLE,DPSP,INTEG,ISUBM,INDNL,KEY)

C'I
C'I
C'I
C'I THIS SUBROUTINE IS TO BE SUPPLIED BY THE USER TO CALCULATE
C'I THE STRESSES AND CONSTITUTIVE MATRIX OF A SPECIAL MATERIAL.
C'I
C'I THIS SUBROUTINE IS CALLED IN USER2 FOR EACH INTEGRATION POINT
C'I FOR EACH 2-D SOLID ELEMENT TO PERFORM THE FOLLOWING OPERATIONS :
C'I
C'I KEY.EQ.1 INITIALIZE THE WORKING ARRAYS DURING INPUT PHASE
C'I
C'I KEY.EQ.2 CALCULATE ELEMENT STRESSES
C'I
C'I KEY.EQ.3 CALCULATE THE STRESS/STRAIN MATRIX
C'I
C'I KEY.EQ.4 PRINT CALCULATED STRESSES AND OTHER DESIRED
C'I VARIABLES DURING STRESS PRINT-OUT
C'I
C'I
C'I THE FOLLOWING VARIABLES ARE USED TO PERFORM THE ABOVE OPERATIONS :
C'I
C'I NG          ELEMENT GROUP NUMBER
C'I
C'I NEL          ELEMENT NUMBER
C'I
C'I IPT          INTEGRATION POINT NUMBER
C'I
C'I IT2D          2D ELEMENT TYPE IDENTIFIER ( NPAR(5) )
C'I                EQ.0  AXISYMMETRIC (IN Y-Z PLANE)
C'I                EQ.1  PLANE STRAIN (IN Y-Z PLANE)
C'I                EQ.2  PLANE STRESS (IN Y-Z PLANE)
C'I                EQ.3  PLANE STRESS (IN 3/D SPACE)
C'I
C'I STRESS(4)      STRESS COMPONENTS, RECEIVED AT TIME TAU
C'I                AND UPDATED BY USER-SUPPLIED CODING TO
C'I                CORRESPOND TO TIME TAU+DTAU
C'I
C'I EPS(4)         TOTAL STRAIN COMPONENTS AT TIME T.
C'I                IN CASE OF LARGE STRAIN FORMULATION
C'I                (U.L.H.), EPS(4) ARE ELASTIC STRAINS AT
C'I                TIME T.

```

C*I
C*I STRAIN(4) TOTAL STRAIN COMPONENTS AT TIME T+DT.
C*I IN CASE OF U.L.H. :
C*I A) FOR KEY.EQ.2 - ELASTIC STRAINS
C*I AT TIME TAU+DTAU (FOR KTR.EQ.0 -
C*I TRIAL ELASTIC STRAINS)
C*I B) FOR KEY.GT.2 - ELASTIC STRAINS AT
C*I TIME T+DT
C*I
C*I DEPS(4) SUBDIVIDED INCREMENTAL STRAIN COMPONENTS
C*I $DEPS(I) = (STRAIN(I) - EPS(I)) / INTER$
C*I - DEPST(I)
C*I (PASSED TO SUBROUTINE CUSER2 BY THE
C*I PROGRAM ADINA)
C*I
C*I DPSP(4) INCREMENT OF INELASTIC STRAIN (PLASTIC
C*I AND/OR CREEP AND/OR VISCOPLASTIC, ETC.)
C*I IN THE SUBDIVISION. CALCULATED BY USER-
C*I SUPPLIED CODING AND PASSED TO THE PROGRAM
C*I ADINA. USED FOR U.L.H. ONLY.
C*I
C*I DEPST(4) COMPONENTS OF SUBINCREMENTAL THERMAL
C*I STRAIN
C*I (PASSED TO SUBROUTINE CUSER2 BY THE
C*I PROGRAM ADINA)
C*I
C*I THSTR1(4) TOTAL THERMAL STRAIN AT TIME TAU
C*I FOR KEY.EQ.4 - THERMAL STRAIN AT TIME T
C*I
C*I THSTR2(4) TOTAL THERMAL STRAIN AT TIME TAU+DTAU
C*I FOR KEY EQ.4 - THERMAL STRAIN AT TIME T+DT
C*I
C*I INTER NUMBER OF SUBDIVISIONS FOR THE STRAIN
C*I INCREMENTS (INTER = INT(PROP(123)))
C*I
C*I KTR CURRENT SUBDIVISION NUMBER
C*I EQ.0 CALCULATION OF TRIAL ELASTIC
C*I STATE, IN CASE INTEG=1
C*I EQ.1 FOR FIRST SUBDIVISION
C*I EQ.INTER FOR LAST SUBDIVISION
C*I
C*I SCP(4) SOLUTION CONTROL PARAMETERS
C*I
C*I ARRAY(60) WORKING ARRAY (REAL) , RECEIVED AT
C*I TIME TAU AND UPDATED BY USER-SUPPLIED
C*I CODING TO CORRESPOND TO TIME TAU+DTAU
C*I
C*I IARRAY(2) WORKING ARRAY (INTEGER) , RECEIVED AT
C*I TIME TAU AND UPDATED BY USER-SUPPLIED
C*I CODING TO CORRESPOND TO TIME TAU+DTAU
C*I
C*I D(4,4) STRESS/STRAIN MATRIX , TO BE CALCULATED

C'I		BY USER-SUPPLIED CODING
C'I		
C'I	ALFA	COEFFICIENT OF THERMAL EXPANSION AT
C'I		TIME TAU
C'I		
C'I	CTD(5)	TEMPERATURE-DEPENDENT MATERIAL CONSTANTS
C'I		AT TIME TAU
C'I		
C'I	ALFAA	COEFFICIENT OF THERMAL EXPANSION AT
C'I		TIME TAU+DTAU
C'I		
C'I	CTDD(5)	TEMPERATURE-DEPENDENT MATERIAL CONSTANTS
C'I		AT TIME TAU+DTAU
C'I		
C'I	CTI(8)	TEMPERATURE-INDEPENDENT MATERIAL CONSTANTS
C'I		
C'I	TMP1	TEMPERATURE AT INTEGRATION POINT IPT AT
C'I		TIME TAU. FOR KEY.EQ.4 - TEMPERATURE AT
C'I		TIME T
C'I		
C'I	TMP2	TEMPERATURE AT INTEGRATION POINT IPT AT
C'I		TIME TAU+DTAU. FOR KEY.EQ.4 - TEMPERATURE
C'I		AT TIME T+DT
C'I		
C'I	TIME	TIME AT CURRENT STEP , T+DT
C'I		
C'I	DT	TIME STEP INCREMENT , DT
C'I		
C'I	PHIST(3,3)	MATRIX CONTAINING DIRECTION COSINES OF
C'I		PRINCIPAL STRETCH DIRECTIONS, IN CASE OF
C'I		U.L.H. FORMULATION
C'I		
C'I	PRST(3)	PRINCIPAL STRETCHES, IN CASE OF U.L.H.
C'I		
C'I	ANGLE(2)	ANGLES OF THE FIRST AND SECOND (IN PLANE)
C'I		PRINCIPAL STRETCH DIRECTIONS WITH RESPECT
C'I		TO Y-AXIS, U.L.H.
C'I		
C'I	INTEG	INTEGRATION PARAMETER FOR STRESS
C'I		INTEGRATION
C'I		EQ.0 - FORWARD INTEGRATION
C'I		EQ.1 - BACKWARD INTEGRATION
C'I		(RETURN MAPPING)
C'I		
C'I	ISUBM	FLAG FOR CONTINUATION OF SUBDIVISION
C'I		IN TIME STEP, APPLICABLE FOR INTEG.EQ.1
C'I		EQ.0 - CONTINUATION
C'I		EQ.-1 - STOP OF SUBDIVISION
C'I		IN THE USER-SUPPLIED CODING THE FLAG
C'I		(INITIALLY EQ.0) MUST BE SET TO -1
C'I		WHEN CRITERIA FOR STOPPING SUBDIVISIONS
C'I		ARE REACHED

```

C*I
C*I  INDNL          FLAG FOR ELEMENT FORMULATION (NPAR(3))
C*I          EQ.1 - MATERIALLY NONLINEAR ONLY (M.N.O.)
C*I          EQ.2 - LARGE DISPLACEMENTS AND SMALL
C*I          STRAINS (T.L.)
C*I          EQ.3 - LARGE DISPLACEMENTS AND LARGE
C*I          STRAINS (U.L.H.)
C*I
C*I
C*I
C*I  NOTE THAT THE VARIABLES PASSED TO THE SUBROUTINE WHEN KEY=3,4
C*I  ARE THESE CALCULATED LAST: I.E., CALCULATED IN THE LAST
C*I  SUBDIVISION WHEN KEY=2. HENCE THESE VARIABLES ARE NOT
C*I  CALCULATED WHEN KEY=3,4.
C*I
C*I
C*I
C      IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C
C      DIMENSION STRESS(4),STRAIN(4),DEPS(4),ARRAY(60),IARRAY(2),D(4,4),
A      CTD(5),CTI(8),EPS(4),SCP(4)
C      DIMENSION CTDD(5),DEPST(4),THSTR1(4),THSTR2(4)
C      DIMENSION PHIST(3,3),PRST(3),ANGLE(2),DPSP(4)
C
C
C      REAL*8  DTAU
C      TIME INCREMENT STEP, DT
C      REAL*8  E
C      ELASTIC MODULUS
C      REAL*8  EIDFF
C      EFFECTIVE INELASTIC STRAIN RATE
C      REAL*8  G
C      SHEAR MODULOUS
C      INTEGER HINT
C      INTEGRATION POINT WRITTEN TO HISTORY FILE
C      INTEGER HELE
C      ELEMENT NUMBER ASSOCIATED WITH HIPT
C      INTEGER I
C      DO LOOP COUNTER
C      INTEGER J
C      DO LOOP COUNTER
C
C      DIRECTIONAL BODNER-PARTOM MATERIAL CONSTANTS:
C
C      TEMPERATURE INDEPENDENT CONSTANTS
C
C      REAL*8  AM1
C      REAL*8  Z1
C      REAL*8  R1
C      REAL*8  R2
C      REAL*8  D0
C      REAL*8  ALPHA1
C

```

```

C  TEMPERATURE INDEPENDENT CONSTANTS
C
REAL*8  AN
REAL*8  AM2
REAL*8  Z0
REAL*8  Z2
REAL*8  Z3
REAL*8  A1
REAL*8  A2

C
C  TEMPERATURE DIFFERENTIALS
C
REAL*8  DAM2
REAL*8  DAN
REAL*8  DZ0
REAL*8  DZ2
REAL*8  DZ3
REAL*8  DA1
REAL*8  DA2

C
COMMON /MATCONST/ E, G, AK, DG, DK,
&      AM1, AM2, ALPHA1, DAM2,
&      Z1, Z3, R1, R2, D0,
&      AN, Z0, Z2, A1, A2,
&      DAN, DZ0, DZ2, DZ3, DA1, DA2

C
C  COMMON BLOCK FOR STATE VARIABLES
C
COMMON /BPSTAT2/ EIN(4), ZI, SIGEFF, BETA EFF, EPEFF, ALPHA,
&      ZD, BETA(4), EPS0(4)

C
C  RECALL STATE VARIABLES AT TIME TAU
C
CALL STGET2(ARRAY)

C
GO TO (1,2,3,4), KEY

C*I
C*I
C*I  KEY = 1
C*I
C*I  INITIALIZE COMPONENTS OF REAL AND INTEGER WORKING ARRAYS
C*I  ( INITIALIZE ARRAY(60) AND IARRAY(2) )
C*I
1 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING
C
C
C  INITIALIZE STATE VARIABLES
C
EIN(1) = 0.0
EIN(2) = 0.0

```

```

EIN(3) = 0.0
EIN(4) = 0.0
BETA(1) = 0.0
BETA(2) = 0.0
BETA(3) = 0.0
BETA(4) = 0.0
ZI = CTD(3)
SIGEFF = 0.0
EPEFF = 0.0
BETAEFF = 0.0
ALPHA = 0.0
ZD = 0.0
C
C   STORE STATE VARIABLES
C
C   CALL STPUT2(ARRAY)
C*I
C   RETURN
C*I
C*I
C*I KEY = 2
C*I
C*I INTEGRATION OF ELEMENT STRESSES
C*I ( CALCULATE STRESS(4) )
C*I
C   2 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING
C*I
C   BODNER-PARTOM MATERIAL
C
C   FOR 2-D SOLID ELEMENT
C
C   GET CURRENT VALUES OF MATERIAL CONSTANTS FOR GIVEN TEMPERATURE
C
C   AM1 = CTI(1)
C   Z1 = CTI(2)
C   R1 = CTI(3)
C   R2 = CTI(3)
C   D0 = CTI(4)
C   ANU = CTI(5)
C   ALPHA1 = CTI(8)
C
C   A1 = CTI(6) * EXP(-CTI(7)/(TMP1+273.))
C   A2 = A1
C   DA1 = CTI(6) * EXP(-CTI(7)/(TMP2+273.))-A1
C   DA2 = DA1
C
C   G = CTD(1)/(2.*(1.+ ANU))
C   DG = CTDD(1)/(2.*(1.+ ANU)) - G
C
C   AK = CTD(1)/(1.-2.* ANU)

```

```

      DK = CTDD(1)/(1.-2.* ANU) - AK
C
      AN = CTD(2)
      DAN = CTDD(2)-CTD(2)
C
      Z2 = CTD(3)
      DZ0 = CTDD(3)-CTD(3)
      DZ2 = CTDD(3)-CTD(3)
C
      Z3 = CTD(4)
      DZ3 = CTDD(4)-CTD(4)
C
      AM2 = CTD(5)
      DAM2 = CTDD(5)-CTD(5)
C
      RELAX = SCP(1)
      TOLER = SCP(2)
      HINT = IFIX(SCP(3))
      HELE = IFIX(SCP(4))
C
C   COMPUTE INCREMENTAL STRAINS WITH INCREMENTAL THERMAL STRAINS
C
      IF (KTR.EQ. 1) THEN
        DO 20 I = 1,4
20      EPS0(I) = EPS(I) - THSTR1(I)
        ENDIF
C
      DTAU1 = DTAU / FLOAT( INTER )
C
C   CALCULATE INCREMENTAL STRESSES AND UPDATE STRESS VECTOR
C
      CALL DBODNER2 ( DEPS, STRESS, DTAU1,
+      NEL, IPT, KTR, TIME, INTER, RELAX, TOLER )
C
      DO 30 I = 1,4
30      EPS0(I) = EPS0(I) + DEPS(I)
C
C-----
C   STORE STATE VARIABLES AT TIME TAU + DTAU
C
      CALL STPUT2(ARRAY)
C
      RETURN
C*I
C*I
C*I
C*I KEY = 3
C*I
C*I FORM CONSTITUTIVE LAW
C*I ( CALCULATE D(4,4) )
C*I
      3 CONTINUE

```

```

C*I
C*I *** INSERT USER-SUPPLIED CODING
C
C-----
C
C UPDATE THE CONSTITUTIVE MATRIX
C
C-----
C
C-----
C
C THE TEMPERATURE DEPENDENT ELASTIC MATRIX IS DETERMINED
C WITHOUT A PLASTIC CORRECTION
C
  E = CTDD(1)
  ANU = CTI(5)
C
  A1 = E/(1.+ANU)
  C1 = A1*0.5
  A1 = A1/(1.-2.*ANU)
  B1 = A1*ANU
C
  DO 315 I=1,4
  DO 315 J=1,4
315  D(I,J) = 0
C
  D(1,1) = A1
  D(1,2) = B1
  D(1,4) = B1
  D(2,1) = B1
  D(2,2) = A1
  D(2,4) = B1
  D(3,3) = C1
  D(4,1) = B1
  D(4,2) = B1
  D(4,4) = A1
C
C STORE STATE VARIABLES AT TIME TAU + DTAU
C
  CALL STPUT2(ARRAY)
C
  RETURN
C
C*I
C*I KEY = 4
C*I
C*I PRINTING OF ELEMENT RESPONSE
C*I ( PRINT STRESS(4),STRAIN(4) )
C*I
  4 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING

```

```

C*I
C*I
C
  IF((NEL.EQ.HELE).AND.(IPT.EQ.HINT)) THEN
7006 FORMAT(2(1X,F8.1),12(1X,E11.4))
    ZMECHS = STRAIN(2) - THSTR2(2)
    ZTOT = ZI+ZD
    WRITE(53,7006) TIME,TMP2,STRESS,EIN,ZMECHS,
    &      SIGEFF
    ENDIF
C
C  PRINT HEADING AND ELEMENT NUMBER
C
  IF(IPT.EQ.1) WRITE(6,9001) NEL
C
C  PRINT STRESSES
C
  MODE = ' ELASTIC'
  IF (EIDIFF.GT.1.E-9) MODE='INELASTIC'
  WRITE(6,9002) IPT,STRESS,SIGEFF,MODE,STRAIN,EIDIFF
C
C  FORMAT STATEMENTS
C
9001 FORMAT (//,4X,3HNEL,4X,3HIPT,6X,9HSTRESS-YY,6X,
+      9HSTRESS-ZZ,6X,9HSTRESS-YZ,
+      6X,9HSTRESS-XX,4X,11HEFF. STRESS,/,
+      20X,9HSTRAIN-YY,6X,
+      9HSTRAIN-ZZ,6X,9HSTRAIN-YZ,
+      6X,9HSTRAIN-XX,4X,6HEIDIFF,/,/,I7)
9002 FORMAT (7X,I7,5(2X,1PE13.6),3X,A9,/,14X,5(2X,E13.6))
  IF((NEL.EQ.1).AND.(NG.EQ.HNG).AND.(IPT.EQ.1)) THEN
    REWIND(55)
  ENDIF
C
  CALL STPUT2(ARRAY)
C
  RETURN
  END
C
  SUBROUTINE DBODNER2 ( DEPS, STRESS, DTAU,
+      NEL, IPT, KTR, TIME, INTER, RELAX, TOLER)
C
  IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C-----
C
  REAL*8  DEVEPS(4)
  REAL*8  EPS(4)
C
  REAL*8  AVGEPS
C  AVERAGE NORMAL STRAIN INCREMENT AT TIME T
  REAL*8  DDEPS(4)
C  SUBINCREMENTAL DEVITRIC STRAINS

```

REAL*8	DEIEFF
C	EFFECTIVE INELASTIC STRAIN INCREMENT
REAL*8	DEPS(4)
C	INCREMENTAL TOTAL STRAIN VECTOR
REAL*8	DEPSI(4)
C	INELASTIC PORTION OF THE DEVIATORIC STRAIN
C	VECTOR
REAL*8	DEVSIG(4)
C	DEVIATORIC STRESS VECTOR OF THE STRESS STATE
C	AT TIME T
INTEGER	ICOUNT
C	ITERATION LOOP COUNTER
REAL*8	FACT1
C	INTEGER FACTOR
REAL*8	FACT2
C	INTEGER FACTOR
INTEGER	INTER
C	NUMBER OF SUBINCREMENTS
INTEGER	IPT
C	GAUSS POINT
INTEGER	ISUB
C	NUMBER OF SUBINCREMENTS WITHIN C
INTEGER	KTR
C	CURRENT SUBDIVISION NUMBER
C	EQ. 1 FOR FIRST SUBDIVISION
C	EQ. 2 FOR LAST SUBDIVISION
INTEGER	NEL
C	ELEMENT NUMBER
REAL*8	RELAX
C	RELAXATION FACTOR FOR NEW STRESS ESTIMATE
REAL*8	TOLER
C	TOLERANCE FOR CONVERGENCE
REAL*8	SIGNEW
C	NEW EFFECTIVE STRESS
REAL*8	SIGOLD
C	INITIAL EFFECTIVE STRESS
REAL*8	SIGEST
C	EFFECTIVE STRESS FOR TIME STEP SIZE OF DT/JINT
REAL*8	SIGHYD
C	HYDROSTATIC STRESS
REAL*8	SIGMAX
C	MAXIMUM ABSOLUTE VALUE OF EITHER SIGEFF OR SIGEFZ
C	FOR INVESTIGATING CONVERGENCE
REAL*8	STRES0(4)
C	STRESS VECTOR AT TIME TAU
REAL*8	STRESS(4)
C	STRESS VECTOR AT TIME TAU+DTAUT
REAL*8	TIME
C	CURRENT TIME VALUE
REAL*8	EINEST(4)
C	ESTIMATED PLASTIC STRAINS
REAL*8	EIN0(4)

```

C      PLASTIC STRAINS AT TIME TAU
C      REAL*8  BETADOT(4)
C      BETA RATE VECTOR
C      REAL*8  BETAEST(4)
C      ESTIMATED BETA VECTOR
C      REAL*8  BETA0(4)
C      BETA VECTOR AT TIME TAU
C      REAL*8  U(4), V(4)
C      TEMPERATURE VECTOR
C      REAL*8  ALEST
C      ESTIMATED ALPHA
C      REAL*8  ZIEST
C      ESTIMATED ISOTROPIC DRAG STRESS
C
C      -----
C
C      COMMON /MATCONST/ E, G, AK, DG, DK,
&      AM1, AM2, ALPHA1, DAM2,
&      Z1, Z3, R1, R2, D0,
&      AN, Z0, Z2, A1, A2,
&      DAN, DZ0, DZ2, DZ3, DA1, DA2
C
C      COMMON /BPSTAT2/ EIN(4), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&      ZD, BETA(4), EPS0(4)
C
C      SQRT3 = SQRT(3.)
C
C      STORE OLD STATE VARIABLES
C
C      DO 10 I=1,4
C      STRES0(I) = STRESS(I)
C      EIN0(I) = EIN(I)
C      BETA0(I) = BETA(I)
10  CONTINUE
C
C      ZI0 = ZI
C      ALPHA0 = ALPHA
C      ZD0 = ZD
C
C      STORE OLD MATERIAL CONSTANTS
C
C      G0 = G
C      AK0 = AK
C      Z00 = Z0
C      Z20 = Z2
C      Z30 = Z3
C      A10 = A1
C      A20 = A2
C      AM20 = AM2
C
C      INITIALIZE OTHER VARIABLES
C

```

```

      ISUB = 1
      IDBUG = 0
C
C  INITIALIZE VARIABLES FOR SUB-TIME CUTTING
C
100 CONTINUE
C
      SIGEST = SIGEFF
      SIGOLD = SIGEST
      BOLD = BETAEFF
      ZI = ZI0
      ZIEST = ZI0
      ZD = ZD0
      ALPHA = ALPHA0
      AVGEPS = AVGEPS0
C
C  RESTORE OLD MATERIAL CONSTANTS
C
      G = G0
      AK = AK0
      Z0 = Z00
      Z2 = Z20
      Z3 = Z30
      A1 = A10
      A2 = A20
      AM2 = AM20
C
C  UPDATE NEW RATE MATERIAL CONSTANTS WITH SUBINCREMENT ISUB
C
      TFACTOR = 1./ ISUB
C
      DTSUB = DTAU * TFACTOR
      DGSUB = DG * TFACTOR
      DKSUB = DK * TFACTOR
      DANSUB = DAN * TFACTOR
      DZ0SUB = DZ0 * TFACTOR
      DZ2SUB = DZ2 * TFACTOR
      DZ3SUB = DZ3 * TFACTOR
      DA1SUB = DA1 * TFACTOR
      DA2SUB = DA2 * TFACTOR
      DAM2SUB = DAM2 * TFACTOR
C
C  COMPUTE DEVITRIC STRESS AND SUBINCREMENTAL DEVITRIC AND
C  VOLUMETRIC STRAIN RATES
C
      SIGHYD = (STRES0(1) + STRES0(2) + STRES0(4)) / 3.0
      DO 20, I = 1,4
C
      EIN(I) = EIN0(I)
      BETA(I) = BETA0(I)
      BETAEST(I) = BETA0(I)
C

```

```

      IF (I.EQ.3) THEN
      FACT1 = 0.
      ELSE
      FACT1 = 1.
      ENDIF
C
      DEVSIG(I) = STRES0(I) - FACT1*SIGHYD
      DDEPS(I) = DEPS(I) * TFACTOR
      EPS(I) = EPS0(I)
C
20  CONTINUE
C
C
      DO 200 JSUB=1,JSUB
C
C   UPDATE ALL TEMPERATURE DEPENDENT MATERIAL CONSTANTS TO
C   END OF SUBTIME INCREMENT STEP
C
      G = G + DGSUB
      AK = AK + DKSUB
      AN = AN + DANSUB
      Z0 = Z0 + DZ0SUB
      Z2 = Z2 + DZ2SUB
      Z3 = Z3 + DZ3SUB
      A1 = A1 + DA1SUB
      A2 = A2 + DA2SUB
      AM2 = AM2 + DAM2SUB
C
      AVGEPS = (EPS(1)+DDEPS(1) +
&      EPS(2)+DDEPS(2) +
&      EPS(4)+DDEPS(4)) / 3.0
C
      DO 30 I = 1,4
      EPS(I) = EPS(I) + DDEPS(I)
C
      IF (I.EQ. 3) THEN
      DEVEPS(I) = EPS(I)
      ELSE
      DEVEPS(I) = EPS(I) - AVGEPS
      ENDIF
30  CONTINUE
C
      ICOUNT = 0
C
300 CONTINUE
C
      ZTOT = Z1EST + ZD
C
      IF(SIGEST .LE. 1.E-12) THEN
      SIGEST = 1.E-12
      DEIEFF = 0.0
      ELSE

```

```

      XTMP1 = (ZTOT/SIGEST)**2
      XTMP2 = -0.5*XTMP1**AN
      DEIEFF = D0*EXP(XTMP2)
      ENDIF
C
      XLAM = SQRT3 * DEIEFF/SIGEST
C
      DEIEFF = DEIEFF * DTSUB
C
      SIGNEW = 0.
      SSUM = 0.
      PWDOT = 0.
C
      DO 40 I=1,4
        IF (I.EQ.3) THEN
          FACT1 = 2
          FACT2 = 0
          FACT3 = 0.5
        ELSE
          FACT1 = 1
          FACT2 = 1
          FACT3 = 1
        ENDIF
C
      C ESTIMATE PLASTIC STRAINS AND STRESSES
      C (ENGINEERING PLASTIC SHEAR STRAINS ARE COMPUTED)
      C
        DEPSI(I) = XLAM * DEVSIG(I) * FACT1
      C
      C COMPUTE THERMAL DIFFERENTIAL TERMS
      C
        THETA3 = 0.
      C
        EINEST(I) = EIN(I) + (DEPSI(I) * DTSUB) + THETA3
      C
        DEVSIG(I) = 2.*G*(DEVEPS(I)-EINEST(I)) * FACT3
      C
        STRESS(I) = DEVSIG(I) + FACT2 * AK * AVGEPS
      C
        PWDOT = PWDOT + (STRESS(I)*DEPSI(I))
      C
        SIGNEW = SIGNEW + FACT1 * DEVSIG(I)**2
        SSUM = SSUM + FACT1 * STRESS(I)**2
      C
      40 CONTINUE
      C
        SIGNEW = SQRT(1.5*SIGNEW)
        SSUM = SQRT(SSUM)
      C
        IBCOUNT = 0
      41 BNEW = 0.0
      C

```

```

      DO 42 I=1,4
        IF (I.EQ.3) THEN
          FACT1 = 2
        ELSE
          FACT1 = 1
        ENDIF
C
42  BNEW  = BNEW  + FACT1 * BETAEST(I)**2
    BNEW  = SQRT(BNEW)
C
      DO 43 I=1,4
C
C COMPUTE DRAG STRESS VECTORS
C
      V(I) = BETAEST(I)
      IF(BNEW .GT. 1.E-15) V(I) = BETAEST(I)/ BNEW
      U(I) = STRESS(I)
      IF(SSUM .GT. 1.E-15) U(I) = STRESS(I) / SSUM
C
43  CONTINUE
C
      BSSUM1 = 0.
      BSSUM2 = 0.
      ZD     = 0.
C
      DO 44 I = 1,4
        IF (I.EQ.3) THEN
          FACT=2
        ELSE
          FACT=1
        ENDIF
C
      BTERM1 = (Z3 * U(I) - BETAEST(I)) * PWDOT
      BTERM2 = Z1 * V(I) * ((BNEW/Z1)**R2)
C
      THETA2 = BETAEST(I) * DZ3SUB / Z3
C
      BETADOT(I) = AM2*BTERM1 - A2*BTERM2
C
      BETAEST(I) = BETA(I) + BETADOT(I)*DTSUB + THETA2
C
      ZD = ZD + BETAEST(I) * U(I) * FACT
CBIAXI  BSSUM1 = BSSUM1 + BETADOT(I) * BETADOT(I) * FACT
CBIAXI  BSSUM2 = BSSUM2 + BETAEST(I) * BETADOT(I) * FACT
44  CONTINUE
C
C SPECIAL TRAP FOR BETA SNAP REVERSALS AT HIGH STRAIN RATES
C
      ZTOT = ZD + ZIEST
      IF(ZTOT .LT. 0) THEN
        BSCALE = ZIEST / ABS(ZD)
        ZD = ZD * BSCALE * 0.5

```

```

      DO 45 I = 1,4
45    BETAEST(I) = BETAEST(I) * BSCALE * 0.5
      ENDIF
C
      BERROR = DABS(BNEW-BOLD2)
      BMAX = DMAX1(BNEW,BOLD2)
      IF( BMAX .GT. TOLER)
& BERROR = BERROR / BMAX
C
      BOLD2 = BNEW
C
      IF (BERROR .GT. TOLER) THEN
        IBCOUNT = IBCOUNT + 1
        IF (IBCOUNT .GT. 5) THEN
          ISUB = ISUB * 2
          IF(ISUB .GT. 64) IDBUG = 1
          IF(ISUB .GT. 128) THEN
            WRITE (6,*) ' BETA REFUSES TO CONVERGE '
            STOP
          ELSE
            GOTO 100
          ENDIF
        ENDIF
      ENDIF
      GO TO 41
    ENDIF

C
CBIAXI  IF(BSSUM1 .LT. 1.0E-12) BSSUM1 = 1.E-12
CBIAXI  VVDOT = BSSUM2 / BSSUM1
C
CBIAXI  IF(ABS(VVDOT) .LE. 1.) THEN
CBIAXI    THETA = ACOS(VVDOT)
CBIAXI  ELSEIF( VVDOT .GT. 1.) THEN
CBIAXI    THETA = 0.
CBIAXI  ELSE
CBIAXI    THETA = 3.141592654
CBIAXI  ENDIF
C
CBIAXI  ALDOT = AM2 * (ALPHA1*SIN(THETA)-ALPHA) * PWDOT
C
CBIAXI  ALEST = ALPHA + ALDOT * DTSUB
C
      ZTERM1 = Z1*(ABS(ZIEST-Z2)/Z1)**R1
C
      THETA1 = DZ2SUB
C
CBIAXI  ZIDOT = AM1*(Z1+ALEST*Z3-ZIEST)*PWDOT
CBIAXI  & - A1*ZTERM1
C
      ZIDOT = AM1*(Z1-ZIEST)*PWDOT
& - A1*ZTERM1
C
C  COMPUTE UPDATED ZTOT VALUE

```

```

C
  ZIEST = ZI + ZIDOT*DTSUB + THETA1
C
C  NOW INVESTIGATE CONVERGENCE
C
  ERROR = DABS(SIGEST-SIGNEW)
  SIGMAX = DMAX1(SIGNEW,SIGEST)
  IF( SIGMAX .GT. TOLER)
    & ERROR = ERROR / SIGMAX
C
  DEPERR = DABS(DEIEFF-DOLD)
  DEPMAX = DMAX1(DEIEFF,DOLD)
  IF( DEPMAX .GT. TOLER)
    & DEPERR = DEPERR / DEPMAX
C
  ZERROR = DABS(ZIEST-ZOLD)
  ZMAX = DMAX1(ZIEST,ZOLD)
  IF( ZMAX .GT. TOLER)
    & ZERROR = ZERROR / ZMAX
C
  ERROR = ERROR + DEPERR + BERROR + ZERROR
C
  IF (IDBUG .EQ. 1) THEN
    WRITE(6,*) ' TIME KTR ICOUNT AND ISUB ',TIME, KTR,ICOUNT,ISUB
    WRITE(6,*)
    WRITE(6,*) 'SIG EST NEW SERR ', SIGEST,SIGNEW,ERROR
    WRITE(6,*) 'DEP OLD NEW EPERR ', DOLD,DEIEFF,DEPERR
    WRITE(6,*) 'B OLD NEW BERR ', BOLD,BNEW,BERROR
    WRITE(6,*) 'Z OLD NEW ZERR ', ZOLD,ZIEST,ZERROR
    WRITE(6,*)
  ENDIF
C
C  CHECK FOR CONVERGENCE
C
  IF( ERROR.GT. TOLER) THEN
C
C  NONCONVERGENT SOLUTION ARRIVES HERE
C
    SIGEST = SIGOLD*(1.-RELAX) + SIGNEW * (RELAX)
    SIGOLD = SIGEST
    DOLD = DEIEFF
    BOLD = BNEW
    ZOLD = ZIEST
C
C  UPDATE AND CHECK CONVERGENCE COUNT
C
    ICOUNT = ICOUNT+1
C
    IF (ICOUNT .GT. 30) THEN
C
C  MAKE ADDITIONAL TIME-STEP CUTS
C

```

```

      ISUB = ISUB * 2
C
      IF (ISUB .EQ. 128) IDBUG = 1
C
C TERMINATE NONCONVERGE SOLUTIONS
C
      IF (ISUB .GT. 128) THEN
        WRITE(6,*) ' SOLUTION REFUSED TO CONVERGE '
        STOP
      ENDIF
C
C RESTART ITERATION SCHEME WITH NEW TIME-STEP CUT
C
      GOTO 100
C
      ENDIF
C
      GOTO 300
C
      ELSE
C
C CONVERGENCE SOLUTION ARRIVES HERE
C
      ALPHA = ALEST
      ZI = ZIEST
C
      DO 50 I = 1, 4
        EIN(I) = EINEST(I)
        BETA(I) = BETAEST(I)
50    CONTINUE
C
      ENDIF
C
C END OF SUBTIME LOOPS
C
200  CONTINUE
C
      SIGEFF = SIGEST
      BETAEFF = BNEW
C
C
C DEBUG OUTPUT STATEMENTS
C
CJOE2  IF (IPT .EQ. 1 .AND. KTR .EQ. INTER) THEN
C
CJOE2  WRITE(6,*) ' TIME KTR ICOUNT AND ISUB ',TIME,KTR,ICOUNT,ISUB
CJOE2  WRITE(6,*)
CJOE2  WRITE(6,*) 'SIG EST NEW SERROR ', SIGEST,SIGNEW,SERROR
CJOE2  WRITE(6,*) 'DEP OLD NEW EPERROR ', DOLD,DEIEFF,DEPERR
CJOE2  WRITE(6,*) 'B OLD NEW BERROR ', BOLD,BNEW,BERROR
CJOE2  WRITE(6,*) 'Z OLD NEW ZERROR ', ZOLD,ZIEST,ZERROR
CJOE2  WRITE(6,*)

```

```

CJOE2 WRITE(6,*) ' FOR ELEMENT AND G POINT ', NEL, IPT
CJOE2 WRITE(6,*)
CJOE2 WRITE(6,*) ' EINEST ', EINEST
CJOE2 WRITE(6,*) ' STRESS ', STRESS
CJOE2 WRITE(6,*) ' BETAEST ', BETAEST
CJOE2 WRITE(6,*) ' ZIEST, DEIEFF, ZD ', ZIEST, DEIEFF, ZD
C
CJOE2  ENDIF
C
  RETURN
  END
C
  SUBROUTINE STGET2(ARRAY)
C
  IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C
  REAL*8 ARRAY(60)
C
  COMMON /BPSTAT2/ EIN(4), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&      ZD, BETA(4), EPS0(4)
C
  EIN(1) = ARRAY(1)
  EIN(2) = ARRAY(2)
  EIN(3) = ARRAY(3)
  EIN(4) = ARRAY(4)
  BETA(1) = ARRAY(5)
  BETA(2) = ARRAY(6)
  BETA(3) = ARRAY(7)
  BETA(4) = ARRAY(8)
  ZI  = ARRAY(9)
  SIGEFF = ARRAY(10)
  EPEFF = ARRAY(11)
  BETAEFF = ARRAY(12)
  ALPHA = ARRAY(13)
  ZD  = ARRAY(14)
  EPS0(1) = ARRAY(15)
  EPS0(2) = ARRAY(16)
  EPS0(3) = ARRAY(17)
  EPS0(4) = ARRAY(18)
C
  RETURN
  END
C
  SUBROUTINE STPUT2(ARRAY)
C
  IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C
  REAL*8 ARRAY(60)
C
  COMMON /BPSTAT2/ EIN(4), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&      ZD, BETA(4), EPS0(4)
C

```

```
ARRAY(1) = EIN(1)
ARRAY(2) = EIN(2)
ARRAY(3) = EIN(3)
ARRAY(4) = EIN(4)
ARRAY(5) = BETA(1)
ARRAY(6) = BETA(2)
ARRAY(7) = BETA(3)
ARRAY(8) = BETA(4)
ARRAY(9) = ZI
ARRAY(10) = SIGEFF
ARRAY(11) = EPEFF
ARRAY(12) = BETAEFF
ARRAY(13) = ALPHA
ARRAY(14) = ZD
ARRAY(15) = EPS0(1)
ARRAY(16) = EPS0(2)
ARRAY(17) = EPS0(3)
ARRAY(18) = EPS0(4)
```

C

```
RETURN
END
```

C

Appendix B

User-Defined Subroutines for Three-Dimensional Brick Elements (file cuser3_dbeta.f)

```
SUBROUTINE CUSER3 (NG,NEL,IPT,STRESS,EPS,STRAIN,DEPS,DEPST,  
A      THSTR1,THSTR2,KTR,INTER,SCP,ARRAY,IARRAY,D,  
B      ALFA,CTD,ALFAA,CTDD,CTI,TMP1,TMP2,TIME,DTAU,  
C      PHIST,PRST,PHIST1,DPSP,INTEG,ISUBM,INDNL,KEY)  
C*I  
C*I  
C*I  
C*I THIS SUBROUTINE IS TO BE SUPPLIED BY THE USER TO CALCULATE  
C*I THE STRESSES AND CONSTITUTIVE MATRIX OF A SPECIAL MATERIAL.  
C*I  
C*I THIS SUBROUTINE IS CALLED IN USER2 FOR EACH INTEGRATION POINT  
C*I FOR EACH 3-D SOLID ELEMENT TO PERFORM THE FOLLOWING OPERATIONS :  
C*I  
C*I KEY.EQ.1 INITIALIZE THE WORKING ARRAYS DURING INPUT PHASE  
C*I  
C*I KEY.EQ.2 CALCULATE ELEMENT STRESSES  
C*I  
C*I KEY.EQ.3 CALCULATE THE STRESS/STRAIN MATRIX  
C*I  
C*I KEY.EQ.4 PRINT CALCULATED STRESSES AND OTHER DESIRED  
C*I VARIABLES DURING STRESS PRINT-OUT  
C*I  
C*I  
C*I THE FOLLOWING VARIABLES ARE USED TO PERFORM THE ABOVE OPERATIONS :  
C*I  
C*I NG      ELEMENT GROUP NUMBER  
C*I  
C*I NEL     ELEMENT NUMBER  
C*I  
C*I IPT     INTEGRATION POINT NUMBER  
C*I  
C*I STRESS(6)  STRESS COMPONENTS, RECEIVED AT TIME TAU  
C*I            AND UPDATED BY USER-SUPPLIED CODING TO  
C*I            CORRESPOND TO TIME TAU+DTAU  
C*I  
C*I EPS(6)     TOTAL STRAIN COMPONENTS AT TIME T.  
C*I            IN CASE OF LARGE STRAIN FORMULATION  
C*I            (U.L.H.), EPS(4) ARE ELASTIC STRAINS AT  
C*I            TIME T.  
C*I  
C*I STRAIN(6)   TOTAL STRAIN COMPONENTS AT TIME T+DT.  
C*I            IN CASE OF U.L.H. :  
C*I            A) FOR KEY.EQ.2 - ELASTIC STRAINS  
C*I            AT TIME TAU+DTAU (FOR KTR.EQ.0 -
```

C*I TRIAL ELASTIC STRAINS)
 C*I B) FOR KEY.GT.2 - ELASTIC STRAINS AT
 C*I TIME T+DT
 C*I
 C*I DEPS(6) SUBDIVIDED INCREMENTAL STRAIN COMPONENTS
 C*I $DEPS(I) = (STRAIN(I) - EPS(I)) / INTER$
 C*I - DEPST(I)
 C*I (PASSED TO SUBROUTINE CUSER2 BY THE
 C*I PROGRAM ADINA)
 C*I
 C*I DPSP(6) INCREMENT OF INELASTIC STRAIN (PLASTIC
 C*I AND/OR CREEP AND/OR VISCOPLASTIC, ETC.)
 C*I IN THE SUBDIVISION. CALCULATED BY USER-
 C*I SUPPLIED CODING AND PASSED TO THE PROGRAM
 C*I ADINA. USED FOR U.L.H. ONLY.
 C*I
 C*I DEPST(6) COMPONENTS OF SUBINCREMENTAL THERMAL
 C*I STRAIN
 C*I (PASSED TO SUBROUTINE CUSER2 BY THE
 C*I PROGRAM ADINA)
 C*I
 C*I THSTR1(6) TOTAL THERMAL STRAIN AT TIME TAU
 C*I FOR KEY.EQ.4 - THERMAL STRAIN AT TIME T
 C*I
 C*I THSTR2(6) TOTAL THERMAL STRAIN AT TIME TAU+DTAU
 C*I FOR KEY EQ.4 - THERMAL STRAIN AT TIME T+DT
 C*I
 C*I INTER NUMBER OF SUBDIVISIONS FOR THE STRAIN
 C*I INCREMENTS (INTER = INT(PROP(123))
 C*I
 C*I KTR CURRENT SUBDIVISION NUMBER
 C*I EQ.0 CALCULATION OF TRIAL ELASTIC
 C*I STATE, IN CASE INTEG=1
 C*I EQ.1 FOR FIRST SUBDIVISION
 C*I EQ.INTER FOR LAST SUBDIVISION
 C*I
 C*I SCP(4) SOLUTION CONTROL PARAMETERS
 C*I
 C*I ARRAY(60) WORKING ARRAY (REAL) , RECEIVED AT
 C*I TIME TAU AND UPDATED BY USER-SUPPLIED
 C*I CODING TO CORRESPOND TO TIME TAU+DTAU
 C*I
 C*I IARRAY(2) WORKING ARRAY (INTEGER) , RECEIVED AT
 C*I TIME TAU AND UPDATED BY USER-SUPPLIED
 C*I CODING TO CORRESPOND TO TIME TAU+DTAU
 C*I
 C*I D(6,6) STRESS/STRAIN MATRIX , TO BE CALCULATED
 C*I BY USER-SUPPLIED CODING
 C*I
 C*I ALFA COEFFICIENT OF THERMAL EXPANSION AT
 C*I TIME TAU
 C*I
 C*I CTD(5) TEMPERATURE-DEPENDENT MATERIAL CONSTANTS
 C*I AT TIME TAU

C*I
 C*I ALFAA COEFFICIENT OF THERMAL EXPANSION AT
 C*I TIME TAU+DTAU
 C*I
 C*I CTDD(5) TEMPERATURE-DEPENDENT MATERIAL CONSTANTS
 C*I AT TIME TAU+DTAU
 C*I
 C*I CTI(8) TEMPERATURE-INDEPENDENT MATERIAL CONSTANTS
 C*I
 C*I TMP1 TEMPERATURE AT INTEGRATION POINT IPT AT
 C*I TIME TAU. FOR KEY.EQ.4 - TEMPERATURE AT
 C*I TIME T
 C*I
 C*I TMP2 TEMPERATURE AT INTEGRATION POINT IPT AT
 C*I TIME TAU+DTAU. FOR KEY.EQ.4 - TEMPERATURE
 C*I AT TIME T+DT
 C*I
 C*I TIME TIME AT CURRENT STEP , T+DT
 C*I
 C*I DT TIME STEP INCREMENT , DT
 C*I
 C*I PHIST(3,3) MATRIX CONTAINING DIRECTION COSINES OF
 C*I PRINCIPAL STRETCH DIRECTIONS, IN CASE OF
 C*I U.L.H. FORMULATION
 C*I
 C*I PRST(3) PRINCIPAL STRETCHES, IN CASE OF U.L.H.
 C*I
 C*I PHIST1(3) DIRECTION COSINES OF THE FIRST PRINCIPAL
 C*I STRETCH (STRETCH WHICH HAS MAXIMUM
 C*I DEVIATION FROM 1.0)
 C*I
 C*I INTEG INTEGRATION PARAMETER FOR STRESS
 C*I INTEGRATION
 C*I EQ.0 - FORWARD INTEGRATION
 C*I EQ.1 - BACKWARD INTEGRATION
 C*I (RETURN MAPPING)
 C*I
 C*I ISUBM FLAG FOR CONTINUATION OF SUBDIVISION
 C*I IN TIME STEP, APPLICABLE FOR INTEG.EQ.1
 C*I EQ.0 - CONTINUATION
 C*I EQ.-1 - STOP OF SUBDIVISION
 C*I IN THE USER-SUPPLIED CODING THE FLAG
 C*I (INITIALLY EQ.0) MUST BE SET TO -1
 C*I WHEN CRITERIA FOR STOPPING SUBDIVISIONS
 C*I ARE REACHED
 C*I
 C*I INDNL FLAG FOR ELEMENT FORMULATION (NPAR(3))
 C*I EQ.1 - MATERIALLY NONLINEAR ONLY (M.N.O.)
 C*I EQ.2 - LARGE DISPLACEMENTS AND SMALL
 C*I STRAINS (T.L.)
 C*I EQ.3 - LARGE DISPLACEMENTS AND LARGE
 C*I STRAINS (U.L.H.)
 C*I
 C*I

C*1 NOTE THAT THE VARIABLES PASSED TO THE SUBROUTINE WHEN KEY=3,4
 C*1 ARE THESE CALCULATED LAST: I.E., CALCULATED IN THE LAST
 C*1 SUBDIVISION WHEN KEY=2. HENCE THESE VARIABLES ARE NOT
 C*1 CALCULATED WHEN KEY=3,4.

C*1
 C*1
 C*1

IMPLICIT DOUBLE PRECISION (A-H,O-Z)

C

DIMENSION STRESS(6),STRAIN(6),DEPS(6),ARRAY(60),IARRAY(2),D(6,6),

A CTD(5),CTI(8),EPS(6),SCP(4)

DIMENSION CTDD(5),DEPST(6),THSTR1(6),THSTR2(6)

DIMENSION PHIST(3,3),PRST(3),PHIST1(3),DPSP(6)

C

C

REAL*8 DTAU

C

TIME INCREMENT STEP, DT

REAL*8 E

C

ELASTIC MODULUS

REAL*8 G

C

SHEAR MODULOUS

INTEGER HINT

C

INTEGRATION POINT WRITTEN TO HISTORY FILE

INTEGER HELE

C

ELEMENT NUMBER ASSOCIATED WITH HIPT

INTEGER I

C

DO LOOP COUNTER

INTEGER J

C

DO LOOP COUNTER

C

DIRECTIONAL BODNER-PARTOM MATERIAL CONSTANTS:

C

TEMPERATURE INDEPENDENT CONSTANTS

C

REAL*8 AM1

REAL*8 Z1

REAL*8 R1

REAL*8 R2

REAL*8 D0

REAL*8 ALPHA1

C

TEMPERATURE INDEPENDENT CONSTANTS

C

REAL*8 AN

REAL*8 AM2

REAL*8 Z0

REAL*8 Z2

REAL*8 Z3

REAL*8 A1

REAL*8 A2

C

TEMPERATURE DIFFERENTIALS

C

REAL*8 DAM2

```

REAL*8  DAN
REAL*8  DZ0
REAL*8  DZ2
REAL*8  DZ3
REAL*8  DA1
REAL*8  DA2
C
COMMON /MATCONST/ E, G, AK, DG, DK,
&      AM1, AM2, ALPHA1, DAM2,
&      Z1, Z3, R1, R2, D0,
&      AN, Z0, Z2, A1, A2,
&      DAN, DZ0, DZ2, DZ3, DA1, DA2
C
C  COMMON BLOCK FOR STATE VARIABLES
C
COMMON /BPSTAT3/ EIN(6), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&      ZD, BETA(6), EPS0(6)
C
C  RECALL STATE VARIABLES AT TIME TAU
C
CALL STGET3(ARRAY)
C
GO TO (1,2,3,4), KEY
C*I
C*I
C*I  KEY = 1
C*I
C*I  INITIALIZE COMPONENTS OF REAL AND INTEGER WORKING ARRAYS
C*I  ( INITIALIZE ARRAY(60) AND IARRAY(2) )
C*I
1 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING
C*I
C*I
C  INITIALIZE STATE VARIABLES
C
EIN(1) = 0.0
EIN(2) = 0.0
EIN(3) = 0.0
EIN(4) = 0.0
EIN(5) = 0.0
EIN(6) = 0.0
BETA(1) = 0.0
BETA(2) = 0.0
BETA(3) = 0.0
BETA(4) = 0.0
BETA(5) = 0.0
BETA(6) = 0.0
ZI  = CTD(3)
SIGEFF = 0.0
EPEFF  = 0.0
BETAEFF = 0.0
ALPHA  = 0.0

```

```

      ZD  = 0.0
C
C   STORE STATE VARIABLES
C
C   CALL STPUT3(ARRAY)
C
C   RETURN
C*I
C*I
C*I KEY = 2
C*I
C*I INTEGRATION OF ELEMENT STRESSES
C*I ( CALCULATE STRESS(6) )
C*I
      2 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING
C*I
C*I
C   BODNER-PARTOM MATERIAL
C
C   FOR 3-D SOLID ELEMENT
C
C   GET CURRENT VALUES OF MATERIAL CONSTANTS FOR GIVEN TEMPERATURE
C
C
      AM1 = CTI(1)
      Z1  = CTI(2)
      R1  = CTI(3)
      R2  = CTI(3)
      D0  = CTI(4)
      ANU = CTI(5)
      ALPHA1 = CTI(8)
C
      A1 = CTI(6) * EXP(-CTI(7)/(TMP1+273.))
      A2 = A1
      DA1 = CTI(6) * EXP(-CTI(7)/(TMP2+273.))-A1
      DA2 = DA1
C
      G  = CTD(1)/(2.*(1.+ ANU))
      DG = CTDD(1)/(2.*(1.+ ANU)) - G
C
      AK = CTD(1)/(1.-2.* ANU)
      DK = CTDD(1)/(1.-2.* ANU) - AK
C
      AN = CTD(2)
      DAN = CTDD(2)-CTD(2)
C
      Z2 = CTD(3)
      DZ0 = CTDD(3)-CTD(3)
      DZ2 = CTDD(3)-CTD(3)
C
      Z3 = CTD(4)
      DZ3 = CTDD(4)-CTD(4)

```

```

C
  AM2 = CTD(5)
  DAM2 = CTDD(5)-CTD(5)
C
  RELAX = SCP(1)
  TOLER = SCP(2)
  HINT = IFIX(SCP(3))
  HELE = IFIX(SCP(4))
C
C  COMPUTE INCREMENTAL STRAINS WITH INCREMENTAL THERMAL STRAINS
C
  IF (KTR.EQ. 1) THEN
    DO 20 I = 1,6
20   EPS0(I) = EPS(I) - THSTR1(I)
    ENDIF
C
  DTAU1 = DTAU / FLOAT( INTER )
C
C  CALCULATE INCREMENTAL STRESSES AND UPDATE STRESS VECTOR
C
  CALL DBODNER3 ( DEPS, STRESS, DTAU1,
+               NEL, IPT, KTR, TIME, INTER, RELAX, TOLER )
C
  DO 30 I = 1,6
30   EPS0(I) = EPS0(I) + DEPS(I)
C
C-----
C  STORE STATE VARIABLES AT TIME TAU + DTAU
C
  CALL STPUT3(ARRAY)
C
  RETURN
C*I
C*I
C*I
C*I KEY = 3
C*I
C*I FORM CONSTITUTIVE LAW
C*I ( CALCULATE D(6,6) )
C*I
  3 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING
C*I
C
C
C  THE TEMPERATURE DEPENDENT ELASTIC MATRIX IS DETERMINED
C  WITHOUT A PLASTIC STRAIN CORRECTION
C
  E = CTDD(1)
  ANU = CTI(5)
C
  DDT = DTAU/FLOAT(INTER)
C

```

```

DO 315 I = 1,6
DO 315 J = 1,6
315 D(I,J) = 0.D0
CM = E/(1. - 2.*ANU)
AE = (1. + ANU)/E
CP = AE
C
C   IN CASE CORRECTION FOR VISCOPLASTIC FLOW IN THE TIME STEP,
C   CORRECT THE CONSTANT CP
C
CJOE IF (EST.GT.YLD) CP = CP + 1.5*DDT*GAMA*(EST/YLD - 1.)/EST
CP = 1./CP
C11 = (CM + 2.*CP)/3.
C12 = (CM - CP)/3.
D(1,1) = C11
D(1,2) = C12
D(1,3) = C12
D(2,2) = C11
D(2,3) = C12
D(3,3) = C11
D(4,4) = 0.5*CP
D(5,5) = D(4,4)
D(6,6) = D(5,5)
DO 320 I = 1,3
DO 320 J = 1,3
320 D(J,I) = D(I,J)
C
C   RETURN
C*I
C*I
C*I KEY = 4
C*I
C*I PRINTING OF ELEMENT RESPONSE
C*I ( PRINT STRESS(6),STRAIN(6) )
C*I
C   4 CONTINUE
C*I
C*I *** INSERT USER-SUPPLIED CODING
C*I
C*I
C   IF((NEL.EQ.HELE).AND.(IPT.EQ.HINT)) THEN
7006 FORMAT(2(1X,F8.1),12(1X,E11.4))
ZMECHS = STRAIN(1) - THSTR2(1)
ZTOT = ZI+ZD
WRITE(53,7006) TIME,TMP2,STRESS(1),STRESS(2),
+ STRESS(3),ZTOT,ZI,ZD,ZMECHS,SIGEFF
ENDIF
C
C   PRINT HEADING AND ELEMENT NUMBER
C
C   IF (NEL.EQ.1 .AND. IPT.EQ.1) THEN
WRITE (6,9000)
ENDIF
IF (IPT.EQ.1) WRITE (6,9002) NEL

```

```

C
C PRINT STRESSES
C
C WRITE (6,9003) IPT,STRESS,SIGEFF,STRAIN,TMP2
C
C FORMAT STATEMENTS
C
9000 FORMAT (//,4X,3HNEL,2X,3HIPT,6X,9HSTRESS-XX,6X,
1 9HSTRESS-YY,6X,9HSTRESS-ZZ,6X,9HSTRESS-XY,6X,
2 9HSTRESS-XZ,6X,9HSTRESS-YZ,4X,
2 11H EFF STRESS, /
3 17X,9HSTRAIN-XX,6X,
1 9HSTRAIN-YY,6X,9HSTRAIN-ZZ,6X,9HSTRAIN-XY,6X,
2 9HSTRAIN-XZ,6X,9HSTRAIN-YZ,4X,
2 11HTEMPERATURE, /)
9002 FORMAT (/ I7 /)
9003 FORMAT (7X,I5,7(2X,E13.6)/13X,7(2X,E13.6),/)
9004 FORMAT (7X,I5,8(2X,E13.6)/27X,3(2X,E13.6),30X,2(2X,E13.6) /
1 27X, 3(2X,E13.6) /)
C
C CALL STPUT3(ARRAY)
C
C RETURN
C*FILE END
C END
C
C SUBROUTINE DBODNER3 ( DEPS, STRESS, DTAU,
+ NEL, IPT, KTR, TIME, INTER, RELAX, TOLER)
C
C IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C-----
C
C REAL*8 DEVEPS(6)
C REAL*8 EPS(6)
C
C REAL*8 AVGEPS
C AVERAGE NORMAL STRAIN INCREMENT AT TIME T
C REAL*8 DDEPS(6)
C SUBINCREMENTAL DEVITRIC STRAINS
C REAL*8 DEIEFF
C EFFECTIVE INELASTIC STRAIN INCREMENT
C REAL*8 DEFS(6)
C INCREMENTAL TOTAL STRAIN VECTOR
C REAL*8 DEPSI(6)
C INELASTIC PORTION OF THE DEVIATORIC STRAIN
C VECTOR
C REAL*8 DEVSIG(6)
C DEVIATORIC STRESS VECTOR OF THE STRESS STATE
C AT TIME T
C INTEGER ICOUNT
C ITERATION LOOP COUNTER
C REAL*8 FACT1
C INTEGER FACTOR
C REAL*8 FACT2

```

```

C      INTEGER FACTOR
C      INTEGER  INTER
C      NUMBER OF SUBINCREMENTS
C      INTEGER  IPT
C      GAUSS POINT
C      INTEGER  ISUB
C      NUMBER OF SUBINCREMENTS WITHIN C
C      INTEGER  KTR
C      CURRENT SUBDIVISION NUMBER
C      EQ. 1 FOR FIRST SUBDIVISION
C      EQ. 2 FOR LAST SUBDIVISION
C      INTEGER  NEL
C      ELEMENT NUMBER
C      REAL*8  RELAX
C      RELAXATION FACTOR FOR NEW STRESS ESTIMATE
C      REAL*8  TOLER
C      TOLERANCE FOR CONVERGENCE
C      REAL*8  SIGNEW
C      NEW EFFECTIVE STRESS
C      REAL*8  SIGOLD
C      INITIAL EFFECTIVE STRESS
C      REAL*8  SIGEST
C      EFFECTIVE STRESS FOR TIME STEP SIZE OF DT/JINT
C      REAL*8  SIGHYD
C      HYDROSTATIC STRESS
C      REAL*8  SIGMAX
C      MAXIMUM ABSOLUTE VALUE OF EITHER SIGEFF OR SIGEFZ
C      FOR INVESTIGATING CONVERGENCE
C      REAL*8  STRES0(6)
C      STRESS VECTOR AT TIME TAU
C      REAL*8  STRESS(6)
C      STRESS VECTOR AT TIME TAU+DTAUT
C      REAL*8  TIME
C      CURRENT TIME VALUE
C      REAL*8  EINEST(6)
C      ESTIMATED PLASTIC STRAINS
C      REAL*8  EIN0(6)
C      PLASTIC STRAINS AT TIME TAU
C      REAL*8  BETADOT(6)
C      BETA RATE VECTOR
C      REAL*8  BETAEST(6)
C      ESTIMATED BETA VECTOR
C      REAL*8  BETA0(6)
C      BETA VECTOR AT TIME TAU
C      REAL*8  U(6), V(6)
C      DIRECTIONAL VECTORS
C      REAL*8  ALEST
C      ESTIMATED ALPHA
C      REAL*8  ZIEST
C      ESTIMATED ISOTROPIC DRAG STRESS
C
C-----
C
COMMON /MATCONST/ E, G, AK, DG, DK,

```

```

&      AM1, AM2, ALPHA1, DAM2,
&      Z1, Z3, R1, R2, D0,
&      AN, Z0, Z2, A1, A2,
&      DAN, DZ0, DZ2, DZ3, DA1, DA2
C
COMMON /BPSTAT3/ EIN(6), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&      ZD, BETA(6), EPS0(6)
C
SQRT3 = SQRT(3.)
C
C STORE OLD STATE VARIABLES
C
DO 10 I=1,6
STRES0(I) = STRESS(I)
EIN0(I) = EIN(I)
BETA0(I) = BETA(I)
10 CONTINUE
C
ZI0 = ZI
ALPHA0 = ALPHA
ZD0 = ZD
C
C STORE OLD MATERIAL CONSTANTS
C
G0 = G
AK0 = AK
Z00 = Z0
Z20 = Z2
Z30 = Z3
A10 = A1
A20 = A2
AM20 = AM2
C
C INITIALIZE OTHER VARIABLES
C
ISUB = 1
IDBUG = 0
C
C INITIALIZE VARIABLES FOR SUB-TIME CUTTING
C
100 CONTINUE
C
SIGEST = SIGEFF
SIGOLD = SIGEST
BOLD = BETAEFF
ZI = ZI0
Ziest = ZI0
ZD = ZD0
ALPHA = ALPHA0
AVGEPS = AVGEPS0
C
C RESTORE OLD MATERIAL CONSTANTS
C
G = G0

```

```

AK = AK0
Z0 = Z00
Z2 = Z20
Z3 = Z30
A1 = A10
A2 = A20
AM2 = AM20
C
C UPDATE NEW RATE MATERIAL CONSTANTS WITH SUBINCREMENT ISUB
C
  TFACTOR = 1./ ISUB
C
  DTSUB = DTAU * TFACTOR
  DGSUB = DG * TFACTOR
  DKSUB = DK * TFACTOR
  DANSUB = DAN * TFACTOR
  DZ0SUB = DZ0 * TFACTOR
  DZ2SUB = DZ2 * TFACTOR
  DZ3SUB = DZ3 * TFACTOR
  DA1SUB = DA1 * TFACTOR
  DA2SUB = DA2 * TFACTOR
  DAM2SUB = DAM2 * TFACTOR
C
C COMPUTE DEVITRIC STRESS AND SUBINCREMENTAL DEVITRIC AND
C   VOLUMETRIC STRAIN RATES
C
  SIGHYD = (STRES0(1) + STRES0(2) + STRES0(3)) / 3.0
  DO 20, I = 1,6
C
    EIN(I) = EIN0(I)
    BETA(I) = BETA0(I)
    BETAEST(I) = BETA0(I)
C
    IF (I.GT.3) THEN
      FACT1 = 0.
    ELSE
      FACT1 = 1.
    ENDIF
C
    DEVSIG(I) = STRES0(I) - FACT1*SIGHYD
    DDEPS(I) = DEPS(I) * TFACTOR
    EPS(I) = EPS0(I)
C
  20 CONTINUE
C
C
C DO 200 JSUB=1,ISUB
C
C   UPDATE ALL TEMPERATURE DEPENDENT MATERIAL CONSTANTS TO
C   END OF SUBTIME INCREMENT STEP
C
  G = G + DGSUB
  AK = AK + DKSUB
  AN = AN + DANSUB

```

```

Z0 = Z0 + DZ0SUB
Z2 = Z2 + DZ2SUB
A1 = A1 + DA1SUB
A2 = A2 + DA2SUB
AM2 = AM2 + DAM2SUB
C
AVGEPS = (EPS(1)+DDEPS(1) +
&      EPS(2)+DDEPS(2) +
&      EPS(3)+DDEPS(3)) / 3.0
C
DO 30 I = 1,6
EPS(I) = EPS(I) + DDEPS(I)
C
IF (I.GT. 3) THEN
DEVEPS(I) = EPS(I)
ELSE
DEVEPS(I) = EPS(I) - AVGEPS
ENDIF
30 CONTINUE
C
ICOUNT = 0
C
300 CONTINUE
C
ZTOT = ZIEST + ZD
C
IF(SIGEST.LE. 1.E-12) THEN
SIGEST = 1.E-12
DEIEFF = 0.0
ELSE
XTMP1 = (ZTOT/SIGEST)**2
XTMP2 = -0.5*XTMP1**AN
DEIEFF = D0*EXP(XTMP2)
ENDIF
C
XLAM = SQRT3 * DEIEFF/SIGEST
C
DEIEFF = DEIEFF * DTSUB
C
SIGNEW = 0.
SSUM = 0.
PWDOT = 0.
C
DO 40 I=1,6
IF (I.GT.3) THEN
FACT1 = 2
FACT2 = 0
FACT3 = 1
ELSE
FACT1 = 1
FACT2 = 1
FACT3 = 2
ENDIF
C

```

```

C ESTIMATE PLASTIC STRAINS AND STRESSES
C (ENGINEERING PLASTIC SHEAR STRAINS ARE COMPUTED)
C
    DEPSI(I) = XLAM * DEVSIG(I) * FACT1
C
C COMPUTE THERMAL DIFFERENTIAL TERMS
C
    THETA3 = 0.
C
    EINEST(I) = EIN(I) + (DEPSI(I) * DTSUB) + THETA3
C
    DEVSIG(I) = FACT3 * G * (DEVEPS(I) - EINEST(I))
C
    STRESS(I) = DEVSIG(I) + FACT2 * AK * AVGEPS
C
    PWDOT = PWDOT + (STRESS(I) * DEPSI(I))
C
    SIGNEW = SIGNEW + FACT1 * DEVSIG(I)**2
    SSUM = SSUM + FACT1 * STRESS(I)**2
C
40 CONTINUE
C
    SIGNEW = SQRT(1.5 * SIGNEW)
    SSUM = SQRT(SSUM)
C
    IBCOUNT = 0
41 BNEW = 0.0
C
    DO 42 I=1,6
        IF (I.GT.3) THEN
            FACT1 = 2
        ELSE
            FACT1 = 1
        ENDIF
C
42 BNEW = BNEW + FACT1 * BETAEST(I)**2
    BNEW = SQRT(BNEW)
C
    DO 43 I=1,6
C
C COMPUTE DRAG STRESS VECTORS
C
        V(I) = BETAEST(I)
        IF (BNEW .GT. 1.E-15) V(I) = BETAEST(I) / BNEW
        U(I) = STRESS(I)
        IF (SSUM .GT. 1.E-15) U(I) = STRESS(I) / SSUM
C
43 CONTINUE
C
    BSSUM1 = 0.
    BSSUM2 = 0.
    ZD = 0.
C
    DO 44 I = 1,6

```

```

      IF (I.GT.3) THEN
        FACT=2
      ELSE
        FACT=1
      ENDIF
C
      BTERM1 = (Z3 * U(I) - BETAEST(I)) * PWDOT
      BTERM2 = Z1 * V(I) * ((BNEW/Z1)**R2)
C
      THETA2  = BETAEST(I) * DZ3SUB / Z3
C
      BETADOT(I) = AM2*BTERM1 - A2*BTERM2
C
      BETAEST(I) = BETA(I) + BETADOT(I)*DTSUB + THETA2
C
      ZD = ZD + BETAEST(I) * U(I) * FACT
CBIAXI  BSSUM1 = BSSUM1 + BETADOT(I) * BETADOT(I) * FACT
CBIAXI  BSSUM2 = BSSUM2 + BETAEST(I) * BETADOT(I) * FACT
44  CONTINUE
C
C SPECIAL TRAP FOR BETA SNAP REVERSALS AT HIGH STRAIN RATES
C
      ZTOT = ZD + ZIEST
      IF(ZTOT.LT. 0) THEN
        BSCALE = ZIEST / ABS(ZD)
        ZD = ZD * BSCALE * 0.5
        DO 45 I = 1,6
45    BETAEST(I) = BETAEST(I) * BSCALE * 0.5
      ENDIF
C
      BERROR = DABS(BNEW-BOLD2)
      BMAX = DMAX1(BNEW,BOLD2)
      IF( BMAX.GT. TOLER)
& BERROR = BERROR / BMAX
C
      BOLD2 = BNEW
C
      IF (BERROR.GT. TOLER) THEN
        IBCOUNT = IBCOUNT + 1
        IF (IBCOUNT.GT. 5) THEN
          ISUB = ISUB * 2
          IF (ISUB.GT. 64) IDBUG = 1
          IF (ISUB.GT. 128) THEN
            WRITE (6,*) ' BETA REFUSES TO CONVERGE '
            STOP
          ELSE
            GOTO 100
          ENDIF
        ENDIF
      ENDIF
      GO TO 41
      ENDIF
C
CBIAXI  IF(BSSUM1.LT. 1.0E-12) BSSUM1 = 1.E-12
CBIAXI  VVDOT = BSSUM2 / BSSUM1

```

```

C
CBIAXI  IF(ABS(VVDOT) .LE. 1.) THEN
CBIAXI    THETA = ACOS(VVDOT)
CBIAXI  ELSEIF( VVDOT .GT. 1.) THEN
CBIAXI    THETA = 0.
CBIAXI  ELSE
CBIAXI    THETA = 3.141592654
CBIAXI  ENDIF
C
CBIAXI  ALDOT = AM2 * (ALPHA1*SIN(THETA)-ALPHA) * PWDOT
C
CBIAXI  ALEST = ALPHA + ALDOT * DTSUB
C
C      ZTERM1 = Z1*(ABS(ZIEST-Z2)/Z1)**R1
C
C      THETA1 = DZ2SUB
C
CBIAXI  ZIDOT = AM1*(Z1+ALEST*Z3-ZIEST)*PWDOT
CBIAXI  &    - A1*ZTERM1
C
C      ZIDOT = AM1*(Z1-ZIEST)*PWDOT
C      &    - A1*ZTERM1
C
C      COMPUTE UPDATED ZTOT VALUE
C
C      ZIEST = ZI + ZIDOT*DTSUB + THETA1
C
C      NOW INVESTIGATE CONVERGENCE
C
C      SERROR = DABS(SIGEST-SIGNEW)
C      SIGMAX = DMAX1(SIGNEW,SIGEST)
C      IF( SIGMAX .GT. TOLER)
C      & SERROR = SERROR / SIGMAX
C
C      DEPERR = DABS(DEIEFF-DOLD)
C      DEPMAX = DMAX1(DEIEFF,DOLD)
C      IF( DEPMAX .GT. TOLER)
C      & DEPERR = DEPERR / DEPMAX
C
C      ZERROR = DABS(ZIEST-ZOLD)
C      ZMAX = DMAX1(ZIEST,ZOLD)
C      IF( ZMAX .GT. TOLER)
C      & ZERROR = ZERROR / ZMAX
C
C      ERROR = SERROR + DEPERR + BERROR + ZERROR
C
C      IF (IDBUG .EQ. 1) THEN
C      WRITE(6,*) ' TIME KTR ICOUNT AND ISUB ',TIME, KTR,ICOUNT,ISUB
C      WRITE(6,*) ' STRESS ', STRESS
C      WRITE(6,*) ' SIG EST NEW SERR ', SIGEST,SIGNEW,SERROR
C      WRITE(6,*) ' DEP OLD NEW EPERR ', DOLD,DEIEFF,DEPERR
C      WRITE(6,*) ' B OLD NEW BERR ', BOLD,BNEW,BERROR
C      WRITE(6,*) ' Z OLD NEW ZERR ', ZOLD,ZIEST,ZERROR
C      WRITE(6,*)

```

```

      ENDIF
C
C CHECK FOR CONVERGENCE
C
      IF( ERROR.GT. TOLER) THEN
C
C NONCONVERGENT SOLUTION ARRIVES HERE
C
      SIGEST = SIGOLD*(1.-RELAX) + SIGNEW * (RELAX)
      SIGOLD = SIGEST
      DOLD = DEIEFF
      BOLD = BNEW
      ZOLD = ZIEST
C
C UPDATE AND CHECK CONVERGENCE COUNT
C
      ICOUNT = ICOUNT+1
C
      IF (ICOUNT .GT.30) THEN
C
C MAKE ADDITIONAL TIME-STEP CUTS
C
      ISUB = ISUB * 2
C
      IF (ISUB .EQ. 128) IDBUG = 1
C
C TERMINATE NONCONVERGE SOLUTIONS
C
      IF (ISUB .GT. 128) THEN
        WRITE(6,*) ' SOLUTION REFUSED TO CONVERGE '
        STOP
      ENDIF
C
C RESTART ITERATION SCHEME WITH NEW TIME-STEP CUT
C
      GOTO 100
C
      ENDIF
C
      GOTO 300
C
      ELSE
C
C CONVERGENCE SOLUTION ARRIVES HERE
C
      ALPHA = ALEST
      ZI = ZIEST
C
      DO 50 I = 1, 6
        EIN(I) = EINEST(I)
        BETA(I) = BETAEST(I)
50    CONTINUE
C
      ENDIF

```

```

C
C END OF SUBTIME LOOPS
C
200 CONTINUE
C
    SIGEFF = SIGEST
    BETAEFF = BNEW
C
C
C DEBUG OUTPUT STATEMENTS
C
CJOE2 IF (NEL .EQ. 1 .AND. IPT .EQ. 1 .AND. KTR .EQ. INTER) THEN
C
CJOE2 WRITE(6,*) ' TIME KTR ICOUNT ISUB IPT ',TIME, KTR,ICOUNT,ISUB,IPT
CJOE2 WRITE(6,*)
CJOE2 WRITE(6,*) 'SIG EST NEW SERROR ', SIGEST,SIGNEW,SERROR
CJOE2 WRITE(6,*) 'DEP OLD NEW EPERROR ', DOLD,DEIEFF,DEPERR
CJOE2 WRITE(6,*) 'B OLD NEW BERROR ', BOLD,BNEW,BERROR
CJOE2 WRITE(6,*) 'Z OLD NEW ZERROR ', ZOLD,ZIEST,ZERROR
CJOE2 WRITE(6,*)
CJOE2 WRITE(6,*) ' FOR ELEMENT AND G POINT ', NEL, IPT
CJOE2 WRITE(6,*)
CJOE2 WRITE(6,*) ' EINEST ', EINEST
CJOE2 WRITE(6,*) ' STRESS ', STRESS
CJOE2 WRITE(6,*) ' DEVSIG ', DEVSIG
CJOE2 WRITE(6,*) ' STRAIN ', EPS
CJOE2 WRITE(6,*) ' BETAEST ', BETAEST
CJOE2 WRITE(6,*) ' ZIEST, DEIEFF, ZD ', ZIEST, DEIEFF, ZD
C
CJOE2 ENDIF
C
    RETURN
    END
C
SUBROUTINE STGET3(ARRAY)
C
    IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C
    REAL*8 ARRAY(60)
C
    COMMON /BPSTAT3/ EIN(6), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&      ZD, BETA(6), EPS0(6)
C
    EIN(1) = ARRAY(1)
    EIN(2) = ARRAY(2)
    EIN(3) = ARRAY(3)
    EIN(4) = ARRAY(4)
    EIN(5) = ARRAY(5)
    EIN(6) = ARRAY(6)
    BETA(1) = ARRAY(7)
    BETA(2) = ARRAY(8)
    BETA(3) = ARRAY(9)
    BETA(4) = ARRAY(10)
    BETA(5) = ARRAY(11)

```

```

BETA(6) = ARRAY(12)
ZI      = ARRAY(13)
SIGEFF  = ARRAY(14)
EPEFF   = ARRAY(15)
BETAEFF = ARRAY(16)
ALPHA   = ARRAY(17)
ZD      = ARRAY(18)
EPS0(1) = ARRAY(19)
EPS0(2) = ARRAY(20)
EPS0(3) = ARRAY(21)
EPS0(4) = ARRAY(22)
EPS0(5) = ARRAY(23)
EPS0(6) = ARRAY(24)
C
  RETURN
  END
C
SUBROUTINE STPUT3(ARRAY)
C
  IMPLICIT DOUBLE PRECISION ( A-H,O-Z )
C
  REAL*8 ARRAY(60)
C
  COMMON /BPSTAT3/ EIN(6), ZI, SIGEFF, BETAEFF, EPEFF, ALPHA,
&          ZD, BETA(6), EPS0(6)
C
  ARRAY(1) = EIN(1)
  ARRAY(2) = EIN(2)
  ARRAY(3) = EIN(3)
  ARRAY(4) = EIN(4)
  ARRAY(5) = EIN(5)
  ARRAY(6) = EIN(6)
  ARRAY(7) = BETA(1)
  ARRAY(8) = BETA(2)
  ARRAY(9) = BETA(3)
  ARRAY(10) = BETA(4)
  ARRAY(11) = BETA(5)
  ARRAY(12) = BETA(6)
  ARRAY(13) = ZI
  ARRAY(14) = SIGEFF
  ARRAY(15) = EPEFF
  ARRAY(16) = BETAEFF
  ARRAY(17) = ALPHA
  ARRAY(18) = ZD
  ARRAY(19) = EPS0(1)
  ARRAY(20) = EPS0(2)
  ARRAY(21) = EPS0(3)
  ARRAY(22) = EPS0(4)
  ARRAY(23) = EPS0(5)
  ARRAY(24) = EPS0(6)
C
  RETURN
  END
C

```

Appendix C

ADINAIN3.0 Input File for Verification Test Case 1 (file vcase1.in)

```

FEPROGRAM ADINA
DATABASE CREATE FILEUNIT=1
HEADING 'Test case 1 of Directional Bodner-Partom with Beta21s'
*
MASTER IDOF=100111 REACTIONS=YES MTOTK=500 NSTEP=48 DT=1.0,
  MODEX=EX IPRINT=48
ANALYSIS TYPE=STATIC
ITERATION METHOD=FULL NEWTON LINE-SEARCH=YES
TOLERANCE TYPE=ED DNORM=1.e-5
* Displacement Loading with time (strain rate = 833.3e-6/s)
TIMEFUNCTION 1
  0.0 0.0
  48.0 0.04
* Temperature with time
TIMEFUNCTION 2
  0.0 25.0
  48.0 25.0
*
PRINTOUT VOLUME=MAX
*
PORTHOLE VOLUME=MAX FORMATTED=YES
*
SYSTEM 1 CARTESIAN
COORDINATES
ENTRIES NODE ZL YL
  1 0.100E+1 0.100E+1
  2 0.100E+1 0.000E-0
  3 0.000E-0 0.000E-0
  4 0.000E-0 0.100E+1
*
*
* Bodner Partom Test Material for b21S
* with no Thermal Expansion
*
MATERIAL 1 USER CT11=0.00 CT12=1600. CT13=3. CT14=1.e4,
  CT15=0.34 CT16=5.8e5 CT17=1.37e4 CT18=0.0,
  SCP1=0.75 SCP2=0.0001 SCP3=1 SCP4=1,
  XINTER=10 TREF=25.
*Temp(C) Expans(1/C) Elastic(MPa) n z0(1/s) z3(MPa) m2(1/MPa)
23.000 0.0000e-6 112000. 4.8000 1550.0 100.0 0.350
260.00 0.0000e-6 108030. 3.5000 1300.0 300.0 0.350
315.00 0.0000e-6 106130. 3.0540 1250.4 390.0 1.502
365.00 0.0000e-6 104090. 2.6490 1205.4 500.0 2.549
415.00 0.0000e-6 101740. 2.2430 1160.4 660.0 3.597
465.00 0.0000e-6 99085. 1.8380 1115.3 960.0 4.644

```

482.00	0.0000e-6	98113.	1.7000	1100.0	1100.0	5.000
500.00	0.0000e-6	97045.	1.5000	1089.3	1300.0	5.763
525.00	0.0000e-6	95497.	1.2800	1074.4	1670.0	6.822
550.00	0.0000e-6	93873.	1.1000	1059.5	2100.0	7.881
575.00	0.0000e-6	92172.	0.9700	1044.6	2600.0	8.941
600.00	0.0000e-6	90395.	0.8200	1029.8	3700.0	10.000
650.00	0.0000e-6	86612.	0.7400	1000.0	3800.0	10.000
760.00	0.0000e-6	77216.	0.5800	600.0	4000.0	15.000
815.00	0.0000e-6	71964.	0.5500	300.0	4100.0	30.000
900.00	0.0000e-6	63122.	0.5500	300.0	4300.0	30.000

*
*
EGROUP 1 TWODSOLID SUBTYPE=AXISYMMETRIC MATERIAL=1
GSURFACE N1=1,N2=2,N3=3,N4=4,EL1=1,EL2=1,NODES=4
*
BOUNDARIES IDOF=110111 TYPE=NODES
2
*
BOUNDARIES IDOF=111111 TYPE=NODES
3
*
BOUNDARIES IDOF=101111 TYPE=NODES
4
*
INITIAL TEMPERATURES
1 25. STEP 1 TO 4 25.
*
LOADS TEMPERATURE
1 1. 2 0 STEP 1 TO 4 1. 2 0
*
LOADS DISPLACEMENTS
1 3 1.0 1
2 3 1.0 1
*
* ADINA INPUT FILE CREATE
ADINA
END

Appendix D

Mathematica Results for Verification Test Case 1 (file vcase1.math)

Strain	Stress (MPa)	Strain	Stress (MPa)
0.0000000	0.0000	0.031665	1146.7
0.0008333	93.330	0.032499	1146.7
0.0016666	186.66	0.033332	1146.7
0.0024999	279.99	0.034165	1146.7
0.0033332	373.32	0.034999	1146.7
0.0041665	466.65	0.035832	1146.7
0.0049998	559.98	0.036665	1146.7
0.0058331	653.31	0.037499	1146.7
0.0066664	746.64	0.038332	1146.7
0.0074997	839.97	0.039165	1146.7
0.0083330	933.30	0.039998	1146.7
0.0091663	1026.6		
0.0099996	1083.9		
0.010833	1098.6		
0.011666	1110.4		
0.012500	1119.6		
0.013333	1126.7		
0.014166	1132.0		
0.014999	1136.0		
0.015833	1138.9		
0.016666	1141.1		
0.017499	1142.7		
0.018333	1143.8		
0.019166	1144.6		
0.019999	1145.2		
0.020832	1145.6		
0.021666	1145.9		
0.022499	1146.2		
0.023332	1146.3		
0.024166	1146.4		
0.024999	1146.5		
0.025832	1146.6		
0.026666	1146.6		
0.027499	1146.7		
0.028332	1146.7		
0.029166	1146.7		
0.029999	1146.7		
0.030832	1146.7		

Appendix E

Mathematica Results for Verification Test Case 2 (file vcase2.math)

Strain	Stress (MPa)	Strain	Stress (MPa)
0.0000000	0.0000	0.031665	140.38
0.0008333	72.106	0.032499	140.38
0.0016666	121.44	0.033332	140.38
0.0024999	138.00	0.034165	140.38
0.0033332	140.14	0.034999	140.38
0.0041665	140.36	0.035832	140.38
0.0049998	140.38	0.036665	140.38
0.0058331	140.38	0.037499	140.38
0.0066664	140.38	0.038332	140.38
0.0074997	140.38	0.039165	140.38
0.0083330	140.38	0.039998	140.38
0.0091663	140.38		
0.0099996	140.38		
0.010833	140.38		
0.011666	140.38		
0.012500	140.38		
0.013333	140.38		
0.014166	140.38		
0.014999	140.38		
0.015833	140.38		
0.016666	140.38		
0.017499	140.38		
0.018333	140.38		
0.019166	140.38		
0.019999	140.38		
0.020832	140.38		
0.021666	140.38		
0.022499	140.38		
0.023332	140.38		
0.024166	140.38		
0.024999	140.38		
0.025832	140.38		
0.026666	140.38		
0.027499	140.38		
0.028332	140.38		
0.029166	140.38		
0.029999	140.38		
0.030832	140.38		

Appendix F

Mathematica Results for Verification Test Case 3 (file vcase3.math)

Strain	Stress (MPa)	Strain	Stress (MPa)
0.0000000	0.0000	0.031665	140.38
0.0008333	72.106	0.032499	140.38
0.0016666	121.44	0.033332	140.38
0.0024999	138.00	0.034165	140.38
0.0033332	140.14	0.034999	140.38
0.0041665	140.36	0.035832	140.38
0.0049998	140.38	0.036665	140.38
0.0058331	140.38	0.037499	140.38
0.0066664	140.38	0.038332	140.38
0.0074997	140.38	0.039165	140.38
0.0083330	140.38	0.039998	140.38
0.0091663	140.38		
0.0099996	140.38		
0.010833	140.38		
0.011666	140.38		
0.012500	140.38		
0.013333	140.38		
0.014166	140.38		
0.014999	140.38		
0.015833	140.38		
0.016666	140.38		
0.017499	140.38		
0.018333	140.38		
0.019166	140.38		
0.019999	140.38		
0.020832	140.38		
0.021666	140.38		
0.022499	140.38		
0.023332	140.38		
0.024166	140.38		
0.024999	140.38		
0.025832	140.38		
0.026666	140.38		
0.027499	140.38		
0.028332	140.38		
0.029166	140.38		
0.029999	140.38		
0.030832	140.38		

Appendix G

Mathematica Results for Verification Test Case 4 (file vcase4.math)

Strain	Stress (MPa)	Temp (°C)	Strain	Stress (MPa)	Temp (°C)
0.00000000	0.0000	25.000	0.032500	787.03	482.00
0.00083333	93.333	25.000	0.033333	787.03	482.00
0.0016667	186.67	25.000	0.034167	787.03	482.00
0.0025000	280.00	25.000	0.035000	787.03	482.00
0.0033333	373.33	25.000	0.035833	787.03	482.00
0.0041667	466.67	25.000	0.036667	787.03	482.00
0.0050000	560.00	25.000	0.037500	787.03	482.00
0.0058333	653.33	25.000	0.038333	787.03	482.00
0.0066667	746.67	25.000	0.039167	787.03	482.00
0.0075000	840.00	25.000	0.040000	787.03	482.00
0.0083333	933.33	25.000	0.040833	787.03	482.00
0.0091667	1026.7	25.000	0.041667	787.03	482.00
0.0100000	1083.9	25.000	0.042500	787.03	482.00
0.010833	1098.6	25.000	0.043333	787.03	482.00
0.011667	1110.4	25.000	0.044167	787.03	482.00
0.012500	1119.6	25.000	0.045000	787.03	482.00
0.013333	1126.7	25.000	0.045833	787.03	482.00
0.014167	1132.0	25.000	0.046667	787.03	482.00
0.015000	1136.0	25.000	0.047500	787.03	482.00
0.015833	1138.9	25.000	0.048333	787.03	482.00
0.016667	1141.1	25.000	0.049167	787.03	482.00
0.017500	1142.7	25.000	0.050000	787.03	482.00
0.018333	1143.8	25.000	0.050833	821.57	443.90
0.019167	1144.6	25.000	0.051667	843.77	405.80
0.020000	1145.2	25.000	0.052500	879.05	367.80
0.020833	1122.6	63.100	0.053333	913.54	329.70
0.021667	1097.2	101.20	0.054167	945.70	291.60
0.022500	1070.3	139.30	0.055000	975.69	253.50
0.023333	1041.9	177.30	0.055833	1008.1	215.40
0.024167	1011.7	215.40	0.056667	1038.7	177.30
0.025000	979.53	253.50	0.057500	1067.4	139.30
0.025833	949.64	291.60	0.058333	1094.6	101.20
0.026667	917.28	329.70	0.059167	1120.3	63.100
0.027500	882.53	367.80	0.060000	1144.7	25.000
0.028333	850.18	405.80	0.060833	1146.7	25.000
0.029167	825.88	443.90	0.061667	1146.7	25.000
0.030000	790.59	482.00	0.062500	1146.7	25.000
0.030833	787.05	482.00	0.063333	1146.7	25.000
0.031667	787.03	482.00	0.064167	1146.7	25.000

Strain	Stress (MPa)	Temp (°C)
0.065000	1146.7	25.000
0.065833	1146.7	25.000
0.066667	1146.7	25.000
0.067500	1146.7	25.000
0.068333	1146.7	25.000
0.069167	1146.7	25.000
0.070000	1146.7	25.000
0.070833	1146.7	25.000
0.071667	1146.7	25.000
0.072500	1146.7	25.000
0.073333	1146.7	25.000
0.074167	1146.7	25.000
0.075000	1146.7	25.000
0.075833	1146.7	25.000
0.076667	1146.7	25.000
0.077500	1146.7	25.000
0.078333	1146.7	25.000
0.079167	1146.7	25.000
0.080000	1146.7	25.000

Appendix H

Mathematica Results for Verification Test Case 5 (file vcase5.math)

Strain	Stress (MPa)	Temp (°C)	Strain	Stress (MPa)	Temp (°C)
0.0000	0.0000	650.00	0.016250	130.64	760.00
0.00041667	36.095	650.00	0.016667	129.59	760.00
0.00083333	72.190	650.00	0.017083	129.05	760.00
0.0012500	104.07	650.00	0.017500	128.76	760.00
0.0016667	133.08	650.00	0.017917	128.62	760.00
0.0020833	162.60	650.00	0.018333	128.54	760.00
0.0025000	192.14	650.00	0.018750	128.50	760.00
0.0029167	221.16	650.00	0.019167	128.48	760.00
0.0033333	249.09	650.00	0.019583	128.47	760.00
0.0037500	275.30	650.00	0.020000	128.46	760.00
0.0041667	299.15	650.00	0.020417	128.46	760.00
0.0045833	320.03	650.00	0.020833	128.46	760.00
0.0050000	337.52	650.00	0.021250	128.46	760.00
0.0054167	351.44	650.00	0.021667	128.46	760.00
0.0058333	361.94	650.00	0.022083	128.46	760.00
0.0062500	369.48	650.00	0.022500	128.46	760.00
0.0066667	374.65	650.00	0.022917	128.46	760.00
0.0070833	378.08	650.00	0.023333	128.46	760.00
0.0075000	380.30	650.00	0.023750	128.46	760.00
0.0079167	381.71	650.00	0.024167	128.46	760.00
0.0083333	382.60	650.00	0.024583	128.46	760.00
0.0087500	383.15	650.00	0.025000	128.46	760.00
0.0091667	383.49	650.00	0.025417	134.59	750.80
0.0095833	383.70	650.00	0.025833	144.80	741.70
0.0100000	383.83	650.00	0.026250	157.42	732.50
0.010417	374.19	659.20	0.026667	171.74	723.30
0.010833	357.33	668.30	0.027083	187.43	714.20
0.011250	336.61	677.50	0.027500	204.29	705.00
0.011667	314.21	686.70	0.027917	222.20	695.80
0.012083	291.34	695.80	0.028333	241.07	686.70
0.012500	268.60	705.00	0.028750	260.85	677.50
0.012917	246.28	714.20	0.029167	281.50	668.30
0.013333	224.60	723.30	0.029583	302.96	659.20
0.013750	203.67	732.50	0.030000	325.21	650.00
0.014167	183.61	741.70	0.030417	341.88	650.00
0.014583	164.50	750.80	0.030833	354.79	650.00
0.015000	146.43	760.00	0.031250	364.38	650.00
0.015417	136.98	760.00	0.031667	371.18	650.00
0.015833	132.73	760.00	0.032083	375.79	650.00

Strain	Stress (MPa)	Temp (°C)
0.032500	378.83	650.00
0.032917	380.78	650.00
0.033333	382.01	650.00
0.033750	382.78	650.00
0.034167	383.26	650.00
0.034583	383.56	650.00
0.035000	383.74	650.00
0.035417	383.86	650.00
0.035833	383.93	650.00
0.036250	383.97	650.00
0.036667	383.99	650.00
0.037083	384.01	650.00
0.037500	384.02	650.00
0.037917	384.03	650.00
0.038333	384.03	650.00
0.038750	384.03	650.00
0.039167	384.04	650.00
0.039583	384.04	650.00
0.040000	384.04	650.00