



12
AD-A271 933



A COMPARISON OF SULFURIC ACID/BORIC ACID ANODIZE AND CHROMIC ACID ANODIZE PROCESSES

Stephen J. Spadafora and Frank R. Pepe*
Aerospace Materials Division
Air Vehicle and Crew Systems Technology Department
NAVAL AIR WARFARE CENTER
AIRCRAFT DIVISION WARMINSTER
P.O. Box 5152
Warminster, PA 18974-0591

(*Jaylords Inc.
1080 N. Delaware Ave.
Philadelphia, PA 19125)



22 JUNE 1993

FINAL REPORT

Period Covering March 1992 To June 1993
Program Element No. 0603721N
Work Unit No. 100337

Approved for Public Release; Distribution is Unlimited

Prepared for:
NAVAL AIR SYSTEMS COMMAND
Washington, DC 20361-0001

93-27287



93 11 5 15 4

NOTICES

REPORT NUMBERING SYSTEM — The numbering of technical project reports issued by the Naval Air Warfare Center, Aircraft Division, Warminster is arranged for specific identification purposes. Each number consists of the Center acronym, the calendar year in which the number was assigned, the sequence number of the report within the specific calendar year, and the official 2-digit correspondence code of the Functional Department responsible for the report. For example: Report No. NAWCADWAR-92001-80 indicates the first Center report for the year 1992 and prepared by the Air Vehicle and Crew Systems Technology Department. The numerical codes are as follows:

CODE	OFFICE OR DEPARTMENT
00	Commanding Officer, NAWCADWAR
01	Technical Director, NAWCADWAR
05	Computer Department
10	AntiSubmarine Warfare Systems Department
20	Tactical Air Systems Department
30	Warfare Systems Analysis Department
50	Mission Avionics Technology Department
60	Air Vehicle & Crew Systems Technology Department
70	Systems & Software Technology Department
80	Engineering Support Group
90	Test & Evaluation Group

PRODUCT ENDORSEMENT — The discussion or instructions concerning commercial products herein do not constitute an endorsement by the Government nor do they convey or imply the license or right to use such products.

Reviewed By: Arthur Fletcher Date: 7/9/93
Branch Head

Reviewed By: Arthur Fletcher (ACTING) Date: 7/9/93
Division Head

Reviewed By: Michael J. King Date: 7/12/93
Director/Deputy Director

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

REPORT DOCUMENTATION PAGE				Form Approved OMB No 0704-0188	
1a REPORT SECURITY CLASSIFICATION Unclassified			1b RESTRICTIVE MARKINGS N/A		
2a SECURITY CLASSIFICATION AUTHORITY N/A			3 DISTRIBUTION AVAILABILITY OF REPORT Distribution Unlimited Approved for Public Release		
2b DECLASSIFICATION/DOWNGRADING SCHEDULE N/A					
4 PERFORMING ORGANIZATION REPORT NUMBER(S) NAWCADWAR-93042-60			5 MONITORING ORGANIZATION REPORT NUMBER(S)		
6a NAME OF PERFORMING ORGANIZATION Air Vehicle and Crew Systems Technology Department		6b OFFICE SYMBOL (If applicable) 6062	7a NAME OF MONITORING ORGANIZATION		
6c ADDRESS (City, State, and ZIP Code) Naval Air Warfare Center Aircraft Division Warminster, P.O. Box 5152 Warminster, PA 18974-0591			7b ADDRESS (City, State, and ZIP Code)		
8a NAME OF FUNDING/SPONSORING ORGANIZATION Naval Air Systems Command		8b OFFICE SYMBOL (If applicable)	9 PROCUREMENT INSTRUMENT IDENTIFICATION NUMBER		
8c ADDRESS (City, State, and ZIP Code) 1213 Jefferson Davis Highway Crystal Gateway 4, Suite 1414 (Code 09Y3B) Arlington, VA 22202			10 SOURCE OF FUNDING NUMBERS		
			PROGRAM ELEMENT NO 0603721N	PROJECT NO	TASK NO
					WORK UNIT ACCESSION NO 100337
11 TITLE (Include Security Classification) A Comparison of Sulfuric Acid/Boric Acid Anodize and Chromic Acid Anodize Processes					
12 PERSONAL AUTHOR(S) Stephen J. Spadafora and Frank R. Pepe					
13a TYPE OF REPORT Final		13b TIME COVERED FROM Mar 92 TO Jun 93		14 DATE OF REPORT (Year, Month, Day) 1993 June 22	
15 PAGE COUNT					
16 SUPPLEMENTARY NOTATION					
17 COSATI CODES			18 SUBJECT TERMS (Continue on reverse if necessary and identify by block number)		
FIELD	GROUP	SUB GROUP	Inorganic Coatings Surface Pretreatments Anodic Films Environmentally Compliant Materials Organic Coatings		
11	03				
19 ABSTRACT (Continue on reverse if necessary and identify by block number) Chromic acid anodizing (CAA) is an aluminum surface pretreatment currently used on Navy aircraft and weapon systems. This anodize process forms a thick oxide film which provides protection against environmental degradation. This is particularly important due to the severely corrosive naval aviation operational environment. Chromium VI, however, is a carcinogen and its wide spread use as a corrosion inhibitor in this process is being restricted. The Navy has targeted chromated maintenance operations for reduction of hazardous waste generation. Several alternative candidates have been identified: Phosphoric Acid Anodizing, Boeing Aerospace Corp.'s Boric-Sulfuric Acid Anodize (SBAA) and thin film sulfuric acid anodizing. The Boeing SBAA process was selected for optimization and service demonstration. The Naval Air Warfare Center Aircraft Division Warminster analyzed the performance properties of SBAA and CAA both sealed and unsealed on various substrates with and without standard Navy coating					
20 DISTRIBUTION AVAILABILITY OF ABSTRACT ☒ UNCLASSIFIED/UNLIMITED ☐ SAME AS ORIGIN ☐ DTIC USERS			21 ABSTRACT SECURITY CLASSIFICATION Unclassified		
22a NAME OF RESPONSIBLE INDIVIDUAL Stephen J. Spadafora			22b TELEPHONE (Include Area Code) (215) 441-2704		22c OFFICE SYMBOL 6062E

UNCLASSIFIED

SECURITY CLASSIFICATION OF THIS PAGE

19. Abstract (Continued)

systems. The results of this program show that SBAA effectively provides equivalent corrosion resistance and paint adhesion while maintaining the existing mechanical properties provided by CAA. Replacement of CAA eliminates the need for expensive control equipment required by 1994 under current AQMD laws, resulting in \$M's in cost avoidance for the Navy.

UNCLASSIFIED

TABLE OF CONTENTS

RECEIVED 5

Accession For	
NTIS GRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification _____	
By _____	
Distribution/ _____	
Availability Codes	
Dist	Avail and/or Special
A-1	

LIST OF TABLES

	<u>Page</u>
TABLE 1. ORGANIC COATINGS SPECIFICATIONS.....	4
TABLE 2. ASTM D3359 ADHESION RATINGS.....	4
TABLE 3. COATING WEIGHT RESULTS.....	6
TABLE 4. ADHESION/WATER RESISTANCE TEST RESULTS.....	6
TABLE 5. 5% SALT SPRAY RESULTS FOR UNPAINTED PANELS.....	8
TABLE 6. CORROSION RESISTANCE TEST RESULTS (5% SALT SPRAY)...	8
TABLE 7. CORROSION RESISTANCE TEST RESULTS (SO ₂ /SALT SPRAY)...	9

INTRODUCTION

With the recent increase in environmental awareness, federal, state and local environmental agencies (EPA, California's Air Quality Management Districts (AQMD), etc.) have issued legislation governing the handling, use and disposal of hazardous materials and wastes. National regulations such as the Clean Air and Water Acts, Resource Conservation and Recovery Act, and local rules like California's South Coast AQMD Rule #1169 limit or prohibit the hazardous emissions generated from the use of these materials. The Department of Defense (DoD) has determined that the majority of hazardous materials and hazardous waste generated by the DOD comes from its maintenance depots and operations (Ref 1). The bulk of these hazardous compounds are associated with cleaning, pretreating, plating, painting and paint removal processes. Chromium is one of the major components in the waste generated from these processes. A national regulation on emissions from chromium electroplating operations is being pursued by the Environmental Protection Agency (Ref 2) with limits similar to the SCAQMD Rule #1169. Chromic acid anodizing is a common surface pretreatment for aluminum, which is currently used on Navy aircraft, weapon platforms and ground support equipment. This anodize process forms a thick oxide film which provides more protection against chemical degradation than chemical conversion coatings. MIL-A-8625E "Anodic Coatings, for Aluminum and Al Alloys" Type I covers the performance requirements of chromic acid anodizing (CAA). While this chromated anodize process offers satisfactory performance, future restrictions necessitate the elimination of chromium emissions from this process.

Two approaches are available to attain this goal. One approach is through the incorporation of process emission controls. The other approach is to eliminate the source of the hazardous material (i.e. CAA). This can be accomplished by material substitution or by the use of alternative technologies, which provide the same overall properties. While both of these methods reduce the amount of hazardous material released, only the former solves disposal and handling concerns. In addition, the elimination approach to chromic acid anodizing will significantly reduce the total amount of chromium emitted from Navy operations and is in direct support of Navy and DOD hazardous waste minimization policies and directives. The need for expensive control equipment required by 1994 under current AQMD laws would be eliminated, resulting in significant cost avoidance. Control equipment for the six Navy Depots was initially estimated at \$4.5-6M for capital costs and \$2.5-4M for annual operating costs. An adequate replacement would provide protection against excessive environmental degradation. This is particularly important considering the severely deleterious environment in which the Navy operates, as well as the cost of the aircraft, weapon systems and ground support equipment.

The Naval Air Warfare Center Aircraft Division at Warminster (NAVAIRWARCENACDIVWAR) has an extensive environmental materials program aimed at the elimination of hazardous materials from Navy aerospace processes (Ref 3). An evaluation effort under these programs was established at NAVAIRWARCENACDIVWAR to demonstrate an alternative technology as a replacement for CAA. The following is a description of this program.

DESCRIPTION OF SURFACE PREPARATION AND ANODIZE PROCESSES

Surface preparation is an essential step in the process of forming protective pretreatments for aluminum. Surface preparation consists of several steps: cleaning, etching (optional) and deoxidizing. Alkaline cleaners, etchants and deoxidizers were used to remove organic contaminants and any remaining surface oxides prior to chemical treating. The materials used in the preparation of the test specimens were non-silicated, non-chromated alternatives which are described in reference 4. The chromic acid anodizing control process used in this investigation is covered by MIL-A-8625E Type I. Specific details on chromic acid anodizing of aluminum are provided in references 5-6.

Two potential alternatives have been identified for replacement of chromic acid anodizing. These alternatives are: Boeing Aerospace Corp's Boric Sulfuric Acid Anodize (SBAA) and thin film sulfuric acid anodizing (Refs 7 - 9). During the initial stage of this effort, the available test data on the two processes was analyzed. Due to the greater volume of existing SBAA data, this process was selected for demonstration.

To evaluate this process, a laboratory scale sulfuric/boric acid anodize process line was set up at NAVAIRWARCENACDIVWAR. This operation was used to analyze the performance properties of sulfuric/boric acid anodizing in comparison to chromic acid anodizing, both sealed and unsealed on various substrates. These films were examined as pretreatments for standard Navy coatings using the procedures described below. Also, the fatigue characteristics of the SBAA and CAA oxides were characterized to determine any detrimental effects. Several coating weights were examined for their effect of fatigue life degradation. A test report on the full scale fatigue tests is being prepared as a separate document, however a summary of the tests is included in Appendix A.

In addition, a 3,200 gallon production scale SBAA line was installed at the North Island Naval Aviation Depot in San Diego, CA. This facility was used to process selected test components for evaluation and optimization of the SBAA process. These results were used to determine the effectiveness of this non-chrome alternative to provide equivalent corrosion resistance and paint adhesion, while maintaining the existing mechanical properties provided by chromic acid anodizing.

EXPERIMENTAL

The performance of both the SBAA and CAA processes was evaluated on common aluminum alloys and with standard Navy coating systems. Physical performance tests (i.e. bare and painted corrosion resistance, coating adhesion, coating weights, etc.) were used to evaluate the anodize films. The following is a description of the substrates, coatings, and experimental procedures used in this investigation.

Materials

With the exception of those panels which were used to determine coating weights, the substrates used in this study were bare 2024 T-3 and 7075 T-6 aluminum alloys. Table 1 lists the coatings applied to these substrates in this investigation. Sets of test specimens were prepared at NAVAIRWARCENACDIVWAR and North Island NADEP following the manufacturers' recommended procedures. A non-silicated, non-chromated alkaline cleaner and non-chromated deoxidizer were used in the preparation of all specimens (Turco's 4215-NC-LT and Smut-Go-NCB products, respectively). Chromic acid anodized control specimens represent a common pretreatment found on military aircraft prior to painting.

Anodize Seals

The chromic acid anodized specimens were sealed using the standard 5% dichromate seal at 93°C for 15 minutes as specified in MIL-A-8625E. The sulfuric/boric acid anodize specimens were sealed with a dilute chromic acid seal described in reference 7.

Experimental Procedures

Coating Weight Determination

Coating weights of the anodize films were obtained using the test procedure outlined in MIL-A-8625E. Weights for sealed and unsealed films were determined on several different alloys. Both anodize processes were included and weights were recorded in mg/ft².

Adhesion and Water Resistance

Adhesion of organic coating systems to the anodize films was evaluated using two methods: wet tape adhesion and scrape adhesion. The wet tape test is a modified version of the American Society for Testing and Materials ASTM D 3359, method A. This test was performed by immersing a specimen in distilled water for a period of time at a specific temperature. Three immersion conditions were used for this test: 24 hours at 23°C, 96 hours at 49°C, and 168 hours at 65°C. Upon removal, two parallel scribes, 3/4 inch apart, were cut through the coating and into the substrate. An "X" was subsequently scribed through the coating between the two initial scribes. A strip of 3M 250 masking tape was applied firmly to the coating surface perpendicular to the scribe lines and immediately removed with one quick motion. The specimens were examined for removal and uplifting of the coating from the substrate and the adhesion rating was recorded. Table 2 gives the performance description for these adhesion ratings. In addition, the water resistance of the pretreatment/coating systems was characterized by examining the test panels for softening, uplifting, blistering, and other coating defects and substrate corrosion which may have resulted from the exposure.

The scrape test was performed in accordance with ASTM D 2197, method A on specimens with a section of the substrate surface exposed. The instrument used to perform this test was a SG-1605 Scrape Adhesion Test Apparatus manufactured by Gardner Laboratory. The test was performed by guiding a weighted stylus at a 45° angle to the

TABLE 1: ORGANIC COATINGS SPECIFICATIONS

1. MIL-P-23377D, Type 1 "Primer Coatings, Epoxy Polyamide, Chemical and Solvent Resistant." Film thickness: 15.2 to 22.9 microns (0.0006 to 0.0009 inches).
2. MIL-P-85582A, Type 1 "Primer Coatings: Epoxy, Waterborne." Film thickness: 15.2 to 22.9 microns (0.0006 to 0.0009 inches).
3. TT-P-2760, Type 1 "Primer Coating: Polyurethane, Elastomeric." Film thickness: 20.3 to 30.5 microns (0.0008 to 0.0012 inches).
4. MIL-P-23377D, Type 1, Film thickness: 15.2 to 22.9 microns (0.0006 to 0.0009 inches).
MIL-C-85285B, Type 1, "Coating: Polyurethane, High Solids." Film thickness: 45.7 to 55.9 microns (0.0018 to 0.0022 inches).

The above coatings were applied by conventional air spray and were allowed to cure for seven days prior to testing.

TABLE 2. ASTM D3359 ADHESION RATINGS

Rating	Description
5A	No peeling or removal
4A	Trace peeling or removal along incisions
3A	Jagged removal along incisions up to 1/16 in. (1.6 mm) on either side
2A	Jagged removal along most of incisions up to 1/8 in. (3.2 mm) on either side
1A	Removal from most of the area of the X under the tape
0A	Removal beyond the area of the X

specimen along the exposed substrate into the coating system. The scrape adhesion was recorded as the heaviest weight used without shearing the coating from the substrate.

Corrosion Resistance

Five aluminum specimens 3"x10" of each anodize process were exposed in 5% salt spray (ASTM B 117) for 336 hours. Upon removal, the panels were inspected for evidence of corrosion. In addition, four aluminum specimens of each unsealed anodize film/coating system were scribed with a figure "X" through the coating into the substrate. Two specimens were exposed in 5% salt spray (ASTM B 117) for 2000 hours and two were exposed in SO₂/salt spray (ASTM G 85) for 500 hours. The panels were then inspected for corrosion in the scribe area and blistering of the coating. Subsequently, one panel from each exposure was chemically treated to remove the organic coating without disturbing the substrate and the specimen was examined for corrosion.

RESULTS AND DISCUSSION

Test panels were processed with non-chromate cleaners and deoxidizers, then chromic acid anodized or sulfuric/boric acid anodized. Coating adhesion, water resistance, & corrosion tests were performed using MIL-P-23377 epoxy primer, MIL-P-85582 epoxy/waterborne primer, and TT-P-2760 polyurethane/elastomeric primer. Also, tested were specimens primed with MIL-P-23377 and topcoated with MIL-C-85285 high solids polyurethane. These coatings are described in references 10-13. All materials met the corrosion resistance and coating adhesion requirements of MIL-A-8625 anodic coatings, for aluminum and aluminum alloys. The following is a summary and discussion of the results.

Coating Weights

Table 3 shows coating weights for the two anodize processes on different aluminum alloys. Coating weight gives an indication of oxide film thickness and is determined by processing variables such as amps/ft², time, etc. Both processes resulted in films within the current proposed limits (200-700 mg/ft²) for the F revision of MIL-A-8625 specification. Some of the sealed SBAA specimens were not evaluated due to a problem (leak) with the seal tank in the demonstration process line. However, the relative coating weights for unsealed specimens indicate that these would be in line with the proposed limits.

Adhesion/Water Resistance

Enhanced coating adhesion is one of the primary function of a surface pretreatment. These coating adhesion tests were performed on unsealed anodize films immediately after the 7 day cure time for the coatings. With further aging of the finishing system, adhesion normally improves, so these results are considered the minimum values. The results of the adhesion/water resistance tests are provided in Table 4. A standard aerospace requirement for scrape adhesion is 3 kg. The scrape adhesion results for chromic acid anodize ranged from 0.5 Kg to >10.5 Kg. This indicated that other factors (such as the coating edge effects, pretreatment thickness,

TABLE 3. COATING WEIGHT RESULTS

AL ALLOY	Sulfuric/Boric Acid Anodize Coating Weight (mg/ft ²)	Chromic Acid Anodize Coating Weight (mg/ft ²)
2024-T3 (Sealed)	372.8	576.4
7075-T6 (Sealed)	576.0	567.2
6061-T6 (Sealed)	-----	366.9
7075-T6 Alclad (Sealed)	-----	436.3
3003 (Sealed)	-----	359.5
1100 (Sealed)	-----	449.6
2024-T3 (Unsealed)	150.9	416.0
7075-T6 (Unsealed)	429.9	315.5
6061-T6 (Unsealed)	568.8	370.9
7075-T6 Alclad (Unsealed)	635.5	421.1
3003 (Unsealed)	488.5	357.1
1100 (Unsealed)	584.5	428.8

TABLE 4. ADHESION/WATER RESISTANCE TEST RESULTS

ALLOY/ COATING	Sulfuric/Boric Acid Anodize				Chromic Acid Anodize			
	SCRAPE	WET TAPE	WET TAPE	WET TAPE	SCRAPE	WET TAPE	WET TAPE	WET TAPE
	(Kg)	(24*)	(96)	(168)	(Kg)	(24)	(96)	(168)

2024-T3 Al Alloy

MIL-P-23377	3.0	5A	5A	5A	2.0	5A	5A	5A
MIL-P-85582	1.5	5A	5A	5A	2.0	5A	5A	5A
TT-P-2760	1.5	5A	5A	5A	0.5	5A	5A	5A
23377/MIL-C-85285	---	5A	5A	5A	---	5A	5A	5A

7075-T6 Al Alloy

MIL-P-23377	7.0	5A	5A	5A	10.5	5A	5A	5A
MIL-P-85582	2.0	5A	5A	5A	2.5	5A	5A	5A
TT-P-2760	1.5	5A	5A	5A	0.5	5A	5A	5A
23377/MIL-C-85285	---	5A	5A	5A	---	5A	5A	5A

--- Test not performed

* Hours immersion in deionized distilled water

Results are for panels processed at NADEP North Island, San Diego, CA

pre-paint surface cleanliness, etc.) affected the outcome of the tests. The results from the sulfuric/boric acid anodized process ranged from 1.5 Kg to 7.0 Kg and was comparable to chromic acid anodizing. The 24 hour tape tests performed on these processes showed adhesion values of 5A for all three primers evaluated. These results indicate virtually no susceptibility to coating-substrate disbondment upon exposure to water. In the expanded adhesion tests (4 & 7 days) both anodize processes, with various coating systems, continued to exhibit excellent adhesion & water resistance. This is evidenced by the tape test 5A results after extended immersion in water.

Nate Corrosion Resistance

Sealed, unpainted specimens from both processes were exposed to 5% salt spray (ASTM B117) on 60° racks and examined at 24 hour intervals for evidence of corrosion. Total exposure time was 336 hours. These results are summarized in Table 5. Both anodic processes on all alloy specimens passed 336 hours of exposure without any evidence of surface corrosion, indicating excellent anodic coating performance.

Painted Corrosion Resistance

Corrosion resistance is an important property for Navy aircraft coatings due to the severe operational environment in which the aircraft are deployed. Therefore, most aircraft primer specifications have a minimum of 1000 hours exposure to salt spray as the corrosion resistance requirement. The anodic coating plays an integral role in meeting this requirement by maintaining the integrity of the coating/substrate interface. To evaluate this property, painted specimens for both anodize processes were exposed to 5% salt spray (ASTM B117) and examined for corrosion in the scribe area and blistering of the coating. These results are summarized in Table 6. Both of the anodize processes, with all three primers and the epoxy primer/polyurethane topcoat coating system, passed 1000 hours of exposure. There were little to no corrosion products in the scribe and no blistering of the coatings.

Since both systems performed well for over 1000 hours on both substrates, the test was continued for another 1000 hours. At 1500 hours and 2000 hours, there were little to no corrosion products in the scribe or blistering of the coating on any of the specimens. Subsequently, the coatings were carefully removed from the surface with a chemical stripper, without disturbing the underlying substrate. Upon further examination, there was no evidence of underlying corrosion on these panels. At 2000 hours, all of the primed and primed/topcoated specimens passed the corrosion test requirements.

Painted specimens exposed to 80% salt spray (ASTM G85) were also examined for damage to the coating and corrosion in and away from the scribe, and these results are summarized in Table 7. The 80% salt spray environment simulates industrial stack gases, such as those found on diesel powered aircraft carriers, and it is an extremely aggressive environment. Most aircraft coating specifications do not have exposure to 80% salt spray as a corrosion

TABLE 5. 5% NACL SALT SPRAY RESULTS FOR UNPAINTED PANELS

ALLOY	-	ANODIZE PROCESS	336 HOUR TEST RESULTS
2024-T3	-	Sulfuric/Boric	No surface corrosion
2024-T3	-	Chromic	No surface corrosion
7075-T6	-	Sulfuric/Boric	No surface corrosion
7075-T6	-	Chromic	No surface corrosion

Results for panels processed at NADEP North Island

TABLE 6. CORROSION RESISTANCE TEST RESULTS (5% SALT SPRAY)

ALLOY/ COATING	SULFURIC/BORIC ACID ANODIZE HOURS OF EXPOSURE				CHROMIC ACID ANODIZE HOURS OF EXPOSURE			
	500	1000	1500	2000	500	1000	1500	2000
2024-T3 Al Alloy								
MIL-P-23377	P	P	P	P	P	P	P	P
MIL-P-85582	P	P	P	P	P	P	P	P
TT-P-2760	P	P	P	P	P	P	P	P
23377/MIL-C-85285	P	P	P	P	P	P	P	P
7075-T6 Al Alloy								
MIL-P-23377	P	P	P	P	P	P	P	P
MIL-P-85582	P	P	P	P	P	P	P	P
TT-P-2760	P	P	P	P	P	P	P	P
23377/MIL-C-85285	P	P	P	P	P	P	P	P

- P = Pass (no blistering, pitting or uplifting of coating, but trace amounts of corrosion permitted in scribe)
 + = Borderline Pass (some corrosion in scribe, but no blistering or pitting on panel)
 - = Borderline Failure (corrosion in scribe with initiation of blistering or pitting on panel)
 F = Failure (corrosion and/or blistering in scribe and on panel surface)

Results are for panels processed at NADEP North Island, San Diego, CA

TABLE 7. CORROSION RESISTANCE TEST RESULTS (SO₂/SALT SPRAY)

ALLOY/ PRETREATMENT	SULFURIC/BORIC ACID ANODIZE HOURS OF EXPOSURE			CHROMIC ACID ANODIZE HOURS OF EXPOSURE		
	168	336	500	168	336	500
2024-T3 Al Alloy						
MIL-P-23377	P	P	F	P	P	F
MIL-P-85582	F			F		
TT-P-2760	F			F		
23377/MIL-C-85285	P	+	-	P	+	-
7075-T6 Al Alloy						
MIL-P-23377	P	+	-	P	-	-
MIL-P-85582	-	F		+	F	
TT-P-2760	F			F		
23377/MIL-C-85285	P	F		P	-	F

(P = Pass, + = Borderline Pass, - = Borderline Failure, F = Failure)

Results are for panels processed at NADEP North Island, San Diego, CA

resistance requirement, therefore, the exposure periods selected were based on differences in finishing system performance.

Primed panels, after being exposed for 168 hours, were examined for signs of corrosion. All specimens (both alloys & both processes) primed with MIL-P-85582 and primed with TT-P-2760 had some scribe corrosion and slight blistering of the coating at 168 hours. These primer specimens failed, except for the MIL-P-85582 on 7075 which was a borderline result for both processes. All MIL-P-23377 primed specimens passed at 168 hours. Primed and topcoated 7075 specimens with both processes failed completely at 500 hours or less, while the primed and topcoated 2024 specimens with both processes were considered a borderline fail at 500 hours. Here again both anodize processes failed at relatively the same exposure time.

In general, the corrosion resistance of the sulfuric/boric acid anodize processed specimens in combination with the standard epoxy primer or the epoxy primer/polyurethane topcoat coating systems was equivalent to the performance of the chromic acid anodize controls. This equivalent performance for this non-chromated anodic coating as compared to the chromated anodic coating, is due to a high degree of interfacial integrity between the coating and substrate.

Finally, the fatigue results in Appendix A show that the SBAA process provided equivalent fatigue characteristics to the CAA process. A statistical analysis of variance performed on the results showed no significant differences in performance between the two anodize processes, although the mean value for fatigue life of the SBAA appeared to be slightly better than CAA.

SUMMARY

The goal of this project was to demonstrate a non-chromated alternative for chromic acid anodizing used on current aerospace structures. The results from this evaluation show that the two anodize processes have comparable performance properties. Having successfully demonstrated this process at the North Island Naval Aviation Depot, the full scale use as an alternative to chromic acid anodizing is being pursued. Transitioning and full implementation of this process for use in fleet maintenance operations is being accomplished through the modification of the MIL-A-8625 military specification. The use of this non-chromated process will allow the Navy to meet stringent environmental standards while maintaining operational readiness and efficiency of system performance. In addition, significant cost savings (\$M) will be recognized by avoiding the need to implement emission control equipment.

ACKNOWLEDGMENT

The authors would like to express their appreciation to Mr. Peter J. Sabatini, Mr. William J. Green, Mr. Donald J. Hirst and Mr. John Deitzel for their contributions to this effort. Without their dedication and inspiration this work would not have been possible.

REFERENCES

1. "DoD Hazardous Waste Minimization Efforts," Col. K. Cornelius, Presentation at the Fifth Aerospace Hazardous Waste Minimization Conference, Costa Mesa, CA, May 1990.
2. "Background and Status of Chromium Electroplating MACT Standard," Lalit Banker, Presentation at the Seventh Aerospace Hazardous Waste Minimization Conference, St Louis, MO, Oct 1992.
3. "Naval Air Warfare Center Aircraft Division at Warminster Environmental Materials Program Phase I," S.J. Spadafora, C.R. Hegedus, K.J. Clark, A.T. Eng, D.F. Pulley, D.J. Hirst, W.J. Green, D.L. Gauntt, P.J. Sabatini and F.R. Pepe, Naval Air Warfare Center Aircraft Division Warminster, Report #NAWCADWAR-92075-60, Warminster, PA. 24 June 1992.
4. "Non-Chromated Surface Pretreatments for Aluminum," S.J. Spadafora, Naval Air Warfare Center Aircraft Division Warminster, Report #NAWCADWAR-92077-60, Warminster, PA. 18 August 1992.
5. "The Surface Treatment and Finishing of Aluminum and Its Alloys," S. Wernick, R. Pinner, and P.G. Sheasby, Finishing Publications Limited, Fifth Edition, Vol. 1, pp. 289-365 & 430-441, 1987.
6. "Sulfuric and Chromic Acid Anodizing of Aluminum," W. C. Cochran, ELECTROPLATING ENGINEERING HANDBOOK, L.J. Durney - Ed., Van Nostrand Reinhold Co., 1984.
7. "Boric Acid - Sulfuric Acid Anodizing Process Development (BAC 5632)," Y. Moji, Boeing Report No. D6-55313TN, February 6, 1990.
8. "Corrosion Resistance and Paint Adhesion Evaluation of Sealed Sulfuric/Boric Acid Anodize Coatings," M. Howard, Rohr Industries Report No. RHR-90-194, December, 1990.
9. "Effect of Anodic Film Type (Thin Film Sulfuric vs Chromic Acid) on Fatigue Life of Aluminum Alloys," T.C. Chang, McDonnell Douglas Report No. MDC-K5784, January 28, 1991.
10. "AGARD Corrosion Handbook, Volume 2, Aircraft Corrosion Control Documents: A Descriptive Catalogue," J.J. DeLuccia, R.D. Gergar, and E.J. Jankowsky, AGARDograph No. 278, North Atlantic Treaty Organization (NATO), March 1987.
11. "A Handbook of Protective Coatings For Military and Aerospace Equipment," S.J. Ketcham, TPC Publication 10, National Association of Corrosion Engineers (NACE), 1983.
12. "Corrosion Preventive Primers For Military Equipment," S.J. Spadafora, C.R. Hegedus, and D.F. Pulley, National Association of Corrosion Engineer's Corrosion 85 Conference, Paper No. 194, Boston Massachusetts, March 1985.
13. "A Review of Organic Coating Technology For U.S. Navy Aircraft," C.R. Hegedus, D.F. Pulley, S.J. Spadafora, A.T. Eng, and D.J. Hirst, Journal of Coatings Technology, November, 1989.

APPENDIX A

FATIGUE TEST RESULTS*

ANODIZE PROCESS	COATING WEIGHT (mg/sq ft)	MEAN FATIGUE LIFE (Cycles)
None	N/A (Baseline)	93,000
SBAA	200	74,000
CAA	200	67,900
SBAA	500	67,500
CAA	500	64,400

* See Test Report for More Details

Rockwell International Corp. Science Center Attn: M. Kendig P.O. Box 1085 1049 Camino Dos Rios Thousand Oaks, CA 91360	1
Rohr Industries Inc. Attn: R. Werley 8200 Arlington Ave. Riverside, CA 92503-1499	1
Sanchem Inc Attn: J. Flicher 1600 S. Canal St. Chicago, IL 60616	1
USBI (United Technologies) Attn: M. G. Murphree P.O. Box 1900 Hunstville, Alabama 35807	1
Warner-Robbins Air Logistics Command (MEMC, MMTRC) Robbins AFB, GA 31098	2
Wright Aeronautical Laboratories (MLSA) Wright-Patterson AFB, OH 45433-6533	1
NAVAIRWARCENACDIWAR (50 for 6062, 3 for 8131, 1 for 60C2)	54

Naval Air Warfare Center (9321) Aircraft Division Lakehurst, NJ 08733-5100	1
Naval Aviation Depot (342) Naval Air Station Alameda, CA 94501	1
Naval Aviation Depot (343) Naval Air Station Jacksonville, FL 32212-0016	1
Naval Aviation Depot (343) Naval Air Station Norfolk, VA 23511-5188	1
Naval Aviation Depot (342) Naval Air Station Pensacola, FL 32508	1
Naval Aviation Depot (34210) Naval Air Station, North Island San Diego, CA 92135-5100	1
Naval Civil Engineering Laboratory (L52) Port Hueneme, CA 93043	1
Naval Facilities Engineering Command (032, 183) Attn: J. Kaminski 200 Stoval St. Alexandria, VA 22302-2300	2
Naval Research Laboratory (6120, 6123, 6124) 4555 Overlook Ave. Washington, DC 20375	3
Naval Sea Systems Command (SEA-05M1) Washington, DC 20362	1
Naval Surface Weapons Center (R33) Silver Spring, MD 20903-5000	1
Office Of Naval Research (431, 12) 800 N. Quincy St. Arlington, VA 22217-5000	2
Ocean City Research Corp. Attn: M. Ingle 1745 Jefferson Davis Hwy., Suite 609 Arlington, VA 22202	1
Radian Corp. Attn: K. Cook 2455 Horsepen Rd., Suite 250 Herndon, VA 22071	1

General Services Administration Paint & Chemicals Commodity Center Attn: A. Fainer Auburn, WA 98001	1
Grumman Aircraft Systems Attn: L. Troupia Bethpage, NY 11714-3582	1
Hughes Aircraft Co. Attn: J. Rosengard/J. Lum Bldg E1, MS-F157 P.O.Box 902 El Segundo, CA 90245	1
Idaho National Engineering Laboratory Attn: W. Schutte P.O. Box 1625 Idaho Falls, ID 83415-3940	1
Lead Maintenance Technology Center for Environment Naval Air Station Jacksonville, FL 32212-0016	1
Lehigh University Attn: Dr.R. Granata Bethlehem, PA 18015	1
Lockheed-GA Attn: B. Bradley 86 S. Cobb Dr., Dept 72-27 Marietta A 30063	1
Marine Air Station (342) Cherry Point, NC 28533-5030	1
Martin Marietta Labs Attn: J. Venables 1450 S. Rolling Rd. Baltimore, MD 21227	1
McDonnell Douglas Aircraft Co. Attn: S. Toepke P.O. Box 516 St. Louis, MO 63166-0516	1
National Bureau of Standards Attn: M. McKnight Washington, DC 20234	1
Naval Air Station (AIRLANT-528) Norfolk, VA 23511-5188	1
Naval Air Station, North Island (AIRPAC-7412) San Diego, CA 92135-5100	1
Naval Air Systems Command (AIR-41123, AIR-5304, AIR-09Y3) Washington, DC 20361	3

DISTRIBUTION LIST

	<u>Copies</u>
Army Aviation Systems Command (DRDAV-DS) 4300 Goodfellow Blvd. St. Louis, MO 63120-1798	1
Army Belvoir Research & Development Center (STRBE-VO) Fort Belvoir, VA 22060-5606	1
Army Materials Command (AMCCE-BD) 5001 Eisenhower Ave. Alexandria, VA 22333	1
Army Research Laboratory (MS EMM) Watertown, MA 02172	1
Betz MetChem Attn: R. Iezzi 4636 Somerton Rd. Trevose, PA 19053-6783	1
Boeing Aerospace & Electronics Attn: J. Golden P.O. Box 3999, MS 82-32 Seattle, WA 98124-2499	1
Center For Naval Analyses 4401 Font Ave P.O. Box 16268 Alexandria, VA 22302-0268	1
Crown Metro/Dexter Attn: F. Shuster East Water St. Waukegan, IL 60085	1
David Taylor Research Center (2813, 2841) Annapolis, MD 21402-5067	2
Defense Technical Information Center Bldg #5, Cameron Station Attn: Administrator Alexandria, VA 22314	12
Deft Inc. Attn: B. Levine 17451 Von Karman Ave. Irvine, CA 92714	1
Douglas Aircraft Co. Attn: L. Bruce Mail Code 36-14 3855 Lakewood Blvd. Long Beach, CA 90846	1