

AD-A273 332



REPORT DOCUMENTATION PAGE			Form Approved OMB No 0704-0188	
Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.				
1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE 11/22/93	3. REPORT TYPE AND DATES COVERED Technical Report	
4. TITLE AND SUBTITLE Synthesis of Molecular Wires by a Novel Divergent/Convergent Approach.			5. FUNDING NUMBERS G- N00014-89-J3062 R&T 4132084	
6. AUTHOR(S) Tour, J. M.; Schumm, J. S.			93-29299 	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Department of Chemistry and Biochemistry University of South Carolina Columbia, SC 29208				
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) Department of the Navy Office of Naval Research 800 North Quincy Street Arlington, VA 22217-5000			10. SPONSORING/MONITORING AGENCY REPORT NUMBER 26	
11. SUPPLEMENTARY NOTES <i>Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.) 1993, 34(2), 368.</i>				
12a. DISTRIBUTION/AVAILABILITY STATEMENT Reproduction in whole or in part is permitted for any purpose of the United States Government. This document has been approved for public release and sale; its distribution is unlimited.			12b. DISTRIBUTION CODE DTIC S ELECTE DEC 01 1993 A	
13. ABSTRACT (Maximum 200 words) Described is the synthesis of oligo(2-ethylphenyl-ethynylene)s and oligo(2-(3'-ethylheptyl)phenyl-ethynylene)s via an iterative divergent convergent approach. Synthesized were the monomer, dimer, tetramer, and octamer of the ethyl derivative and the monomer, dimer, tetramer, octamer, and 16-mer of the ethylheptyl derivative. The 16-mer is 128 Å long. At each stage in the iteration, the length of the framework doubles. Only three sets of reaction conditions are needed for the entire iterative synthetic sequence; an iodination, a protodesilylation, and a Pd/Cu-catalyzed cross coupling. The oligomers were characterized spectroscopically and by mass spectrometry.				
14. SUBJECT TERMS			15. NUMBER OF PAGES	
			16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT Unclassified	18. SECURITY CLASSIFICATION OF THIS PAGE Unclassified	19. SECURITY CLASSIFICATION OF ABSTRACT Unclassified	20. LIMITATION OF ABSTRACT UL	

OFFICE OF NAVAL RESEARCH

GRANT : N00014-89-J-3062

R&T Code 4132084

Technical Report No. 26

Synthesis of Molecular Wires by a Novel Divergent/Convergent Approach

by

Tour, J. M.; Schumm, J. S.

Accepted for Publication in

Polym. Prepr. (Am. Chem. Soc., Div. Polym. Chem.)

Department of Chemistry and Biochemistry
University of South Carolina
Columbia, SC 29208

November 22, 1993

Reproduction in whole, or in part, is permitted for any purpose of the United States Government

This document has been approved for public release and sale; its distribution is unlimited.

DTIC QUALITY INSPECTED 8


Accession For	
NTIS CRA&I	☒
DTIC TAB	☐
Unannounced	☐
Justification	
By	
Distribution /	
Availability Codes	
Dist	Avail and/or Special
A-1	

Synthesis of Molecular Wires by a Novel Divergent/Convergent Approach

James M. Tour* and Jeffry S. Schumm
Department of Chemistry and Biochemistry
University of South Carolina
Columbia, South Carolina 29208

Since the time of the first room-filling computers, there has been a tremendous drive to compress the size of computing instruments. In order to bring this desire to its extreme, it was conceived that one may be able to construct a single molecule that could function as a self-contained electronic device.¹ We have identified an approach which would allow the rapid synthesis of conjugated oligomers ("molecular wires") through the use of a novel divergent/convergent synthetic approach. Here we outline a methodology that should permit the rapid synthesis of molecular wires with dimensions needed for adhesion between a patterned electronic assembly. Hence, the feasibility of conduction on single or small molecular arrays may soon be experimentally addressed.


A schematic representation of the conducting system that we hope to construct is shown below. The nonofabricated portion will consist of two metallic probes on opposite sides of a selected binding surface. The target molecules may be spontaneously deposited, by self-assembly, from solution onto the binding surface and will bridge the gap between the metallic contacts by selectively attaching to the two metal probes. Ultimately, the "molecular alligator clips" will be, for example, thiols which will bind to gold probes while the "molecular staples" could be hydroxyl groups that would bind to an oxide surface below.



The conjugated oligomers that we are constructing are well-defined homogeneous materials that are fully characterized. We hope to ultimately construct oligomers ~ 100 Å long; on the order of the resolution of current patterning techniques. Additionally, we hope to construct oligomers that are air and light stable to facilitate the assembly and fabrication.

An outline of the synthetic sequence is shown in Scheme 1. The synthesis of the oligomers begins with the

Scheme 1




formation of a monomer unit with different functional groups on the ends. The ends must be complimentary so that they will undergo a coupling reaction to give a dimeric species. The dimer would then be divided into two portions, the ends converted to the aforementioned complimentary end units, then coupled to afford the tetrameric species. This


process would then continue until the desired length of "molecular wire" is reached by doubling the length of the oligomer at each coupling stage.

The synthesis of the first oligomer (Scheme 2) began

Scheme 2




with the conversion of 3-bromothiophene to the hydroxyethyl derivative by the use of *t*-butyllithium and ethylene oxide. The subsequent alcohol was cleanly iodinated by the procedure of Uhlenbroek² in 81% yield. The iodide was then coupled with trimethylsilylacetylene in the presence of Pd(0) and Cu(I) in 81% yield.³ The new alkyne was then deprotected with K₂CO₃ in methanol and coupled with alkyne 1 in the presence of a Pd(0)/Cu(I) catalyst to afford 2 in 51% yield. 1 was prepared as shown in eq 1.



It was necessary to take one half of 2 and protect the alcohol in order to cleanly iodinate the terminal thiophene unit. A second portion of 2 had the terminal trimethylsilyl unit removed with fluoride and the two halves are then coupled under Pd(0)/Cu(I) conditions³ to afford the tetramer (Scheme 3). We experienced some problems with


Scheme 3



decomposition of the free acetylene at the dimer stage and again upon deprotection of the tetramer. This problem occurred regardless of the method of deprotection (K₂CO₃/MeOH or TBAF/THF) on the dimer and tetramer. Oxidative coupling afforded a head-to-head dimer ~50 Å long. Based on these results, we began investigating a phenylene-ethynylene system which should be more stable to air but would still allow for the divergent/convergent synthetic approach.

The synthesis of the phenylene-ethynylene monomer is shown in Scheme 4. Reduction of 3'-aminoacetophenone


Scheme 4



afforded a nearly quantitative yield of the 3-ethylaniline which was protected with acetic anhydride in 86% yield (over 2 steps). The acylation was accomplished in 50% yield after purification by flash chromatography.⁴ The acetamide was then deprotected with hot 3 N HCl in quantitative yield.⁵ The next step in the synthetic sequence was the functional interconversion of the amine to a group that could function both as a protecting group and be converted to a halogen for cross-coupling. Moore has shown that amines can be converted to triazenes through the diazonium ion.⁶ This was accomplished with NaNO_2 followed by quenching with HNEt_2 to afford the triazene in 95% yield. The ketone was then converted to the silylalkyne **3** via the phosphate enolate.⁷

With the synthesis of the monomer unit **3** completed, the divergent/convergent route could be conducted (Scheme 5). Monomer **3** was divided into two parts and the first part was iodinated to afford **4** in 74% yield. The other portion of **3** was deprotected to give the **5** in 98% yield.

Scheme 5



Coupling of 4 and 5 afforded the dimer 6 in 70% yield. The rest of the sequence proceeded in a similar fashion to afford the tetramer 7 (30 Å long) we have carried out the dimerization in an attempt to make the octameric species which is 60 Å long. However, the insolubility of the system prevented adequate characterization and it became evident that a more soluble system would be needed if we were to ultimately synthesize the desired 16-mer. Therefore, we are currently investigating a similar synthesis with other side chains that would enhance the solubility properties at the larger oligomeric stages.

In conclusion, we have developed a synthetic sequence that allows the rapid formation of some well-characterized oligomers of known constitution and length for use in nanofabrication technology. This novel divergent/convergent procedure should be amenable to other such systems.

Acknowledgments. We are grateful for support from the Office of Naval Research, the Defense Advanced Research Projects Agency, the National Science Foundation (EHR-91-08772, DMR-9158315), and generous industrial contributors to the NSF Presidential Young Investigator Award (1991-96): Hercules, IBM, Ethyl, Shell, and Eli Lilly Corporations. We also thank Molecular Design Ltd. for the use of their synthetic data base.

1) a. Bowden, M. J. in *Electronics and Photonic Applications of Polymers*; Bowden, M. J.; Turner, S. R., Eds.; (Advances in Chemistry, 218) American Chemical Society: Washington DC, 1988. b. *Molecular Electronic Devices*; Carter, F. L., Ed.; Marcel Dekker: New York, 1982. c. *Molecular Electronic Devices II*; Carter, F. L., Ed.; Marcel Dekker: New York, 1984. d. For a recent presentation of the potential and abstacles for moloecular electronic device fabrication, see: Miller, J. S. *Adv. Mater.* 1990, 2, 378, 495, 601.

2) Uhlenbroek, J. H.; Bijloo, J. D. *Rec. Trav. Chim.* 1960, 79, 1181.

3) Suffert, J.; Ziessel, R. *Tetrahedron Lett.* 1991, 32, 757.

4) Oki, M. *Bull. Chem. Soc. Jpn.* 1957, 30, 508.

5) Khorana, H. G.; Turner, A. F.; Vizsoly, J. P. *J. Am. Chem. Soc.* 1961, 83, 686.

6) a) Moore, J. S.; Zhang, J.; Aquarre, R. A. *J. Am. Chem. Soc.* 1992, 114, 2273. b) Moore, J. S.; Weinstein, E. J.; Wu, Z. *Tetrahedron Lett.* 1991, 32, 2465.

7) Negishi, E.; King, A. O.; Tour, J. M. *Org. Synth.* 1985, 64, 44.