

AD-A274 721



AD

AD-E402 528


Technical Report ARAED-TR-93020

# THERMAL CONDUCTIVITY OF PAX 2A EXPLOSIVE BY DSC

Joel Harris

DTIC  
ELECTE  
JAN 13 1994  
S E D

December 1993



US ARMY  
ARMAMENT MUNITIONS  
& CHEMICAL COMMAND  
ARMAMENT RDE CENTER

## U.S. ARMY ARMAMENT RESEARCH, DEVELOPMENT AND ENGINEERING CENTER

Armament Engineering Directorate

Picatinny Arsenal, New Jersey

Approved for public release; distribution is unlimited.

94-01449



94 1 12 042

The views, opinions, and/or findings contained in this report are those of the authors(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

The citation in this report of the names of commercial firms or commercially available products or services does not constitute official endorsement by or approval of the U.S. Government.

Destroy this report when no longer needed by any method that will prevent disclosure of its contents or reconstruction of the document. Do not return to the originator.

|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |                                                             |                                                            |                                                                                       |                                           |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------|------------------------------------------------------------|---------------------------------------------------------------------------------------|-------------------------------------------|
| <b>REPORT DOCUMENTATION PAGE</b>                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |                                                             |                                                            | Form Approved OMB No. 0704-0188                                                       |                                           |
| Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operation and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503. |                                                             |                                                            |                                                                                       |                                           |
| 1. AGENCY USE ONLY (Leave blank)                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                          |                                                             | 2. REPORT DATE<br>December 1993                            |                                                                                       | 3. REPORT TYPE AND DATES COVERED<br>Final |
| 4. TITLE AND SUBTITLE<br><br>THERMAL CONDUCTIVITY OF PAX 2A EXPLOSIVE BY DSC                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |                                                             |                                                            | 5. FUNDING NUMBERS                                                                    |                                           |
| 6. AUTHOR(S)<br><br>Joel Harris                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |                                                             |                                                            |                                                                                       |                                           |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESSES(S)<br><br>ARDEC, AED<br>Energetics and Warheads Division (SMCAR-AEE-W)<br>Picatinny Arsenal, NJ 07806-5000                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                               |                                                             |                                                            | 8. PERFORMING ORGANIZATION<br>REPORT NUMBER<br><br>Technical Report<br>ARAED-TR-93020 |                                           |
| 9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(S)<br><br>ARAED, IMD<br>STINFO Br (SMCAR-IMI-I)<br>Picatinny Arsenal, NJ 07806-5000                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   |                                                             |                                                            | 10. SPONSORING/MONITORING<br>AGENCY REPORT NUMBER                                     |                                           |
| 11. SUPPLEMENTARY NOTES                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   |                                                             |                                                            |                                                                                       |                                           |
| 12a. DISTRIBUTION/AVAILABILITY STATEMENT<br><br>Approved for public release; distribution is unlimited.                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                   |                                                             |                                                            | 12b. DISTRIBUTION CODE                                                                |                                           |
| 13. ABSTRACT (Maximum 200 words)<br><br>A technique to determine the coefficient of thermal conductivity by Differential Thermal Calorimetry (DSC) was developed. The thermal conductivity for teflon (polytetrafluoroethylene), high melt explosive (HMX), and PAX-2A explosive were determined. The thermal conductivity values determined for teflon and HMX agree with those found in literature; whereas, the value for PAX-2A was determined to be $14.26 \pm 0.26 \times 10^{-4}$ calories/cm-s-°C.                                                                                                                                                                                                                |                                                             |                                                            |                                                                                       |                                           |
| 14. SUBJECT TERMS<br><br>Differential thermal calorimetry    HMX    Teflon    PAX 2A<br>Thermal conductivity                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                              |                                                             |                                                            | 15. NUMBER OF PAGES<br><br>12                                                         |                                           |
|                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                           |                                                             |                                                            | 16. PRICE CODE                                                                        |                                           |
| 17. SECURITY CLASSIFICATION<br>OF REPORT<br>UNCLASSIFIED                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                                  | 18. SECURITY CLASSIFICATION<br>OF THIS PAGE<br>UNCLASSIFIED | 19. SECURITY CLASSIFICATION<br>OF ABSTRACT<br>UNCLASSIFIED | 20. LIMITATION OF ABSTRACT<br><br>SAR                                                 |                                           |

## CONTENTS

|                        | Page |
|------------------------|------|
| Object                 | 1    |
| Introduction           | 1    |
| Experimental Procedure | 1    |
| Results                | 1    |
| Discussion of Results  | 2    |
| Conclusion             | 2    |
| References             | 6    |
| Distribution List      | 9    |

DTIC QUALITY INSPECTED 8

|                     |                                     |
|---------------------|-------------------------------------|
| Accession For       |                                     |
| NTIS CRA&I          | <input checked="" type="checkbox"/> |
| DTIC TAB            | <input checked="" type="checkbox"/> |
| Unannounced         | <input type="checkbox"/>            |
| Justification ..... |                                     |
| By .....            |                                     |
| Distribution /      |                                     |
| Availability Codes  |                                     |
| Dist                | Avail and/or<br>Special             |
| A-1                 |                                     |

## OBJECT

To determine coefficient of thermal conductivity of explosive PAX-2A.

## INTRODUCTION

Thermal conductivity is a parameter of energetic materials which is required in order to do determinations of critical temperatures and ballistic calculations. In the past, before the existence of Differential Scanning Calorimeters (DSC), large test samples were required. Such procedures which involve large samples were both hazardous and time consuming. The DSC method requires only a 1/4 in. pellet of material and only a few hours time depending on time spent in calibration and repetitive experiments. The method makes use of a Perkin-Elmer DSC-2, although any DSC type instrument would do.

## EXPERIMENTAL PROCEDURE

The apparatus for thermal conductivity measurements appears in figure 1. The temperature at the bottom of the pellet is measured by a calibrated resistance wire attached to the sample holder of the DSC cell. Since the DSC cell consists of two cells, the instrument sends power into the cell with the pellet in order to equalize the temperature in both cells. The power is equal to the energy being conducted away by the pellet and proportional to the thermal conductivity of the pellet. A thin layer of conductive grease is rubbed on the bottom and top of each pellet to ensure good thermal contact. A copper fuse cup on top of the pellet conducts the heat to a copper-constantan thermocouple through an insulator in order to measure the temperature at the top of the pellet. The power surge is measured as a deflection on a Perkin-Elmer 056 two pen recorder. The other pen records the millivolt response from the thermocouple.

## RESULTS

The data from the above measurements (deflection and temperatures) are fitted into the following equation

$$k = \frac{dq/dt \times L}{A \times (T_1 - T_2)}$$

as derived in reference 1 and compiled in table 1.

k = Thermal conductivity at test temperature (10<sup>-4</sup> cal/cm sec-°C)

$dq/dt$  = Heat flux cal/s (deflection mcal) X DSC range (mcal)

$L$  = Length of pellet (in.)

$A$  = Area of pellet surface (in.)

$T_1 - T_2$  = Temperature difference °C

Results from other sources are also included in table 1 for high melt explosive (HMX) and teflon (PTE).

## **DISCUSSION OF RESULTS**


There is generally a paucity of thermal conductivity data in the literature. Values found for PTE vary with the method used. Values found in references 2 through 4 appear similar to values in table 1. The value found for HMX with 0.5 % wax in the table compares favorably with the values for HMX listed in reference 5, although the HMX pellets in the two reports have different densities.

## **CONCLUSION**

A Differential Scanning Calorimeter Instrument can be used to accurately determine the thermal conductivity of 1/4 in. pellets of materials.

### Table 1. Thermal conductivity data

[illegible]



SCALE 1:1

Figure 1. Thermal conductivity accessory

## REFERENCES

1. Zemansky, M. W., Heat and Thermodynamics, McGraw-Hill, New York, p. 80-82, 1957.
2. Hillstrom, W. W., Ballistic Research Laboratory Interim Report No.598, Aberdeen Proving Ground, Maryland p. 19, 20, 1978.
3. Brennan, W. P., Princeton University Ph.D, University Microfilms, Ann Arbor, Michigan (71-25, 930) p 82, 1971.
4. Hsu, K. L.; Kline, D. E.; and Tomlinson, J. N., J. Appl. Polymer Sci. **9**, p 3567, 1965.
5. Dobratz, B. M., "LLNL Explosives Handbook," UCRL-52997, p 6.2, 1960.

## **DISTRIBUTION LIST**

### **Commander**

**Armament Research, Development and Engineering Center**

**U.S. Army Armament, Munitions and Chemical Command**

**ATTN: SMCAR-IMI-I (3)**  
**SMCAR-AEE (3), Diane M. Cece (1)**  
**SMCAR-AEE-B (5)**  
**SMCAR-AEE-W (5)**  
**SMCAR-AEE-WE, J. Harris (10)**  
**SMCAR-GCL**

**Picatinny Arsenal, NJ 07806-5000**

### **Administrator**

**Defense Technical Information Center**

**ATTN: Accessions Division (12)**

**Cameron Station**

**Alexandria, VA 22304-6145**

### **Director**

**U.S. Army Material Systems Analysis Activity**

**ATTN: AMXSY-MP**

**Aberdeen Proving Ground, MD 21005-5066**

### **Commander**

**Chemical/Biological Defense Agency**

**U.S. Army Armament, Munitions and Chemical Command**

**ATTN: AMSCB-CII, Library**

**Aberdeen Proving Ground, MD 21010-5423**

### **Director**

**U.S. Army Edgewood Research, Development and Engineering Center**

**ATTN: SCBRD-RTB (Aerodynamics Technology Team)**

**Aberdeen Proving Ground, MD 21010-5423**

### **Director**

**U.S. Army Research Laboratory**

**ATTN: AMSRL-OP-CI-B, Technical Library**

**Aberdeen Proving Ground, MD 21005-5066**

**Chief**  
**Benet Weapons Laboratory, CCAC**  
**Armament Research, Development and Engineering Center**  
**U.S. Army Armament, Munitions and Chemical Command**  
**ATTN: SMCAR-CCB-TL**  
**Watervliet, NY 12189-5000**

**Director**  
**U.S. Army TRADOC Analysis Command-WSMR**  
**ATTN: ATRC-WSS-R**  
**White Sands Missile Range, NM 88002**