

**AD-A283 490**




**RL-NP-92-4**  
**Final Technical Report**  
**August 1992**



**THE FABRICATION OF RIDGE  
WAVEGUIDED PHOTONIC CIRCUITS WITH  
CHEMICALLY ASSISTED ION BEAM  
ETCHED MIRRORS**

**Cornell University**

**Paul D. Swanson, Stuart I. Libby, and Michael A. Parker**



*APPROVED FOR PUBLIC RELEASE; DISTRIBUTION UNLIMITED.*

**94-26095**



*1698*

**94 8 17 106**

**Rome Laboratory  
Air Force Materiel Command  
Griffiss Air Force Base, New York**

**DTIC QUALITY INSPECTED 1**

Unedited version of this report, RL-NP-92-4 dated August 1992 is being sent to the Defense Technical Information Center (DTIC) for archiving and subsequent referral through the DTIC Technical Report Data Base.

RL-NP-92-4 has been reviewed by the Rome Laboratory Public Affairs Office (PA) and is releasable to the National Technical Information Service (NTIS). At NTIS it will be releasable to the general public, including foreign nations.

RL-NP-92-4 has been reviewed and is approved for publication.

APPROVED:

*Michael A. Parker*

MICHAEL A. PARKER  
Project Engineer

FOR THE COMMANDER:

*Donald W. Hanson*

DONALD W. HANSON  
Director of Surveillance & Photonics

|                     |                      |                                     |
|---------------------|----------------------|-------------------------------------|
| Accession For       |                      |                                     |
| NTIS                | CRA&I                | <input checked="" type="checkbox"/> |
| DTIC                | TAB                  | <input type="checkbox"/>            |
| Unannounced         |                      | <input type="checkbox"/>            |
| Justification ..... |                      |                                     |
| By .....            |                      |                                     |
| Distribution /      |                      |                                     |
| Availability Codes  |                      |                                     |
| Dist                | Avail and/or Special |                                     |
| A-1                 |                      |                                     |

# REPORT DOCUMENTATION PAGE

Form Approved  
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

|                                                                                                                                                                                                                                                                           |                                                             |                                                            |                                  |                                                                                                                     |  |
|---------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------------|-------------------------------------------------------------|------------------------------------------------------------|----------------------------------|---------------------------------------------------------------------------------------------------------------------|--|
| 1. AGENCY USE ONLY (Leave Blank)                                                                                                                                                                                                                                          |                                                             | 2. REPORT DATE<br>August 1992                              |                                  | 3. REPORT TYPE AND DATES COVERED<br>Final Apr 90 - Feb 91                                                           |  |
| 4. TITLE AND SUBTITLE<br>THE FABRICATION OF RIDGE WAVEGUIDED PHOTONIC CIRCUITS WITH CHEMICALLY ASSISTED ION BEAM ETCHED MIRRORS                                                                                                                                           |                                                             |                                                            |                                  | 5. FUNDING NUMBERS<br>C - F30602-88-D-0025, 0039<br>PE - 62702F<br>PR - 4600<br>TA - P3<br>WU - PO<br>Task P-O-6022 |  |
| 6. AUTHOR(S)<br>Paul D. Swanson/Cornell University<br>Stuart I. Libby and Michael A. Parker (Rome Laboratory)                                                                                                                                                             |                                                             |                                                            |                                  |                                                                                                                     |  |
| 7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)<br>Cornell University<br>212 Phillips Hall<br>Ithaca NY 14853                                                                                                                                                          |                                                             |                                                            |                                  | 8. PERFORMING ORGANIZATION<br>REPORT NUMBER<br>N/A                                                                  |  |
| 9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)<br>Rome Laboratory (OCPB)<br>25 Electronic Pky<br>Griffiss AFB NY 13441-4515                                                                                                                                      |                                                             |                                                            |                                  | 10. SPONSORING/MONITORING<br>AGENCY REPORT NUMBER<br>RL-NP-92-4                                                     |  |
| 11. SUPPLEMENTARY NOTES<br>Rome Laboratory Project Engineer: Michael A. Parker/OCPB/(315) 330-7671<br>Prime Contractor: Georgia Tech Research Corporation                                                                                                                 |                                                             |                                                            |                                  |                                                                                                                     |  |
| 12a. DISTRIBUTION/AVAILABILITY STATEMENT<br>Approved for public release; distribution unlimited.                                                                                                                                                                          |                                                             |                                                            |                                  | 12b. DISTRIBUTION CODE                                                                                              |  |
| 13. ABSTRACT (Maximum 200 words)<br>The fabrication of etched ridge waveguide based monolithically integrated photonic circuits is described. Etched mirrors are created at the same time as the etched ridge waveguides by means of a one-step two-level etch technique. |                                                             |                                                            |                                  |                                                                                                                     |  |
| 14. SUBJECT TERMS<br>Waveguides, semiconductor lasers, fabrication, opto electronics, photonics                                                                                                                                                                           |                                                             |                                                            |                                  | 15. NUMBER OF PAGES<br>20                                                                                           |  |
|                                                                                                                                                                                                                                                                           |                                                             |                                                            |                                  | 16. PRICE CODE                                                                                                      |  |
| 17. SECURITY CLASSIFICATION<br>OF REPORT<br>UNCLASSIFIED                                                                                                                                                                                                                  | 18. SECURITY CLASSIFICATION<br>OF THIS PAGE<br>UNCLASSIFIED | 19. SECURITY CLASSIFICATION<br>OF ABSTRACT<br>UNCLASSIFIED | 20. LIMITATION OF ABSTRACT<br>UL |                                                                                                                     |  |

## **Table of Contents**

|                                  |    |
|----------------------------------|----|
| I. Introduction.....             | 1  |
| II. Etched Ridge Waveguides..... | 1  |
| III. Processing.....             | 3  |
| IV. Conclusion.....              | 10 |
| References.....                  | 11 |

## I. Introduction

Discreet GaAs-AlGaAs laser diodes have already proven to be highly useful and commercially viable photonic devices. The next logical step in the evolution of this family of devices is the monolithic integration of photonic devices based on a laser diode heterostructure. The standard optical waveguide structure used to confine and amplify light within a diode laser can also be used as a saturable absorber<sup>1</sup>, electro-optic modulator<sup>2</sup>, detector<sup>3</sup>, and passive waveguide<sup>4</sup>. Applications range from Q-switched and bistable lasers to optical switching and optical logic. This paper reviews the processing techniques used to fabricate laser based logic devices comprised of chemically assisted ion beam etched (CAIBE) waveguides and mirrors.<sup>5,6,7</sup> A brief discussion of principles of guiding within an etched ridge waveguide will precede a chronology of the processing steps.

## II. Etched Ridge Waveguides

In order for monolithically integrated optical devices to function, light must be routed to, and confined in each device in accordance with the over all "photonic circuit". The photonic circuits whose fabrication is described in this paper use etched ridge waveguides for both of these requirements. Etched ridge waveguides use index guiding to confine light in the vertical direction and "strip loading" to confine light in the lateral direction. In both cases light is confined by having, at some

distance from the center of the waveguide, a purely imaginary phase constant in the direction normal to the direction of propagation. By definition, this creates an exponential decay of intensity with distance from the center of the guide. This exponential decay is the result of light traveling in phase, along the boundary between a region experiencing a high index of refraction (the core) and a region with a lower index of refraction (the cladding). Since the wave equation for light dictates that the square of the magnitude of the phase constant vector for light traveling in a given material equals the square of the product of the index of refraction and the free space propagation constant,

$$B_x^2 + B_y^2 + B_z^2 = (nk_0)^2, \quad (1)$$

it follows that, in order for light traveling in both the core and cladding to be constantly in phase ( $B_{z\text{core}} = B_{z\text{cladding}}$ ), the phase constants in the directions normal to propagation must be real in the higher index core and imaginary in the lower index cladding. A standard laser heterostructure confines light in the vertical direction in this manner by using planar epitaxially grown layers of varying index of refraction. The strip loading in an etched ridge laser is formed by etching down to just above the planar core on either side of the waveguide. This produces

the equivalent of a slight lateral index drop in the side regions by lowering the phase constant in the direction of propagation of their possible vertical modes.<sup>8</sup> This is more desirable than etching all the way through the core because the smaller index drop allows for wider, and therefore easier to fabricate, single mode lasers.

### III. Processing


The laser logic device being fabricated requires etched regions of two different depths: a deep etch that extends well into the lower cladding region for the laser mirrors, and a shallow etch to delineate the waveguides. In order to create an effective lateral index difference, the shallow etch should be within 100 nm of the top of the planar waveguide's core.<sup>9</sup> Both etch depths can be achieved with a single etch by depositing a material which etches slowly in the CAIBE over the shallow etch regions.<sup>6</sup> When this material is totally etched away, the previously uncovered deep etch regions will have already etched down to the difference between the two etch depths. A single layer of  $\text{SiO}_2$  can be used as both the etch retarding layer and insulation between the contact pads and the semiconductor. Chromium, whose etch rate in the CAIBE is almost negligible, is used to mask regions which require no etching. These regions correspond to the regions to be metallized, namely the ohmic

contacts on top of the waveguides and the electrical contact pads. For this reason the chromium etch mask is delineated at the same time as the p-type ohmic contact metallization. The entire process requires only two photo-lithographic mask steps. A chronology of the design and processing steps developed at Cornell University utilizing the National Nanofabrication Facility are as follows:<sup>6</sup>

1. The masks used to delineate the  $\text{SiO}_2$  and the metallization are laid out on a CAD system.
2. The photolithographic masks are generated using a Mann 360F Pattern Generator.
3. The wafers to be processed are cleaned and dried. These include the laser heterostructure wafers (see Figure 1), along with blank GaAs substrates used for etch depth calibration.  $\text{SiO}_2$  is grown on the wafers. The desired thickness of the  $\text{SiO}_2$  is determined by the etch rate of both  $\text{SiO}_2$  and GaAs/AlGaAs in the CAIBE by the following equation:


$$T_{\text{SiO}_2} = R_{\text{SiO}_2} ( D / R_{\text{GaAs}} ) , \quad (2)$$

where  $R_{\text{SiO}_2}$  is the  $\text{SiO}_2$  etch rate,  $R_{\text{GaAs}}$  is the average heterostructure etch rate, and  $D$  is the difference in etch depths.




**Figure 1.** A standard epitaxially grown laser heterostructure, utilizing multiple quantum wells in its active region.

4. Photo-resist is spun on and the first mask pattern is transferred onto the wafers, leaving exposed the areas which are to be deep etched or ohmicly contacted.
5. The wafers are placed in a reactive ion etcher and the  $\text{SiO}_2$  in the exposed areas is etched away, using a  $\text{CHF}_3$  plasma. While still in the reactive ion etcher, the photo resist is removed with an oxygen plasma. (See Figure 2a.)
6. In order to improve the ohmic contact, a shallow Zn diffusion is used to dope the contact regions p+.  $\text{ZnAs}_3$  is used to form a Zn vapor source during an open ampule diffusion, lasting 9 minutes at 650 degrees centigrade. The patterned  $\text{SiO}_2$  on the wafers insure that only the areas to be p-contacted are doped p+. Since the diffusion is shallow, (~300 nm) the Zn diffusion in the regions to be deep etched is without consequence to the final device.
7. After the diffusion, a new layer of 5214 photo resist is spun on the wafers and the metallization pattern is transferred to the photo resist. Using the negative reversal process for 5214, the areas to be metallized are left uncovered.



**Figure 2.** Cross sections and top views of two intersecting laser cavities during progressive stages in fabrication: (a) After the patterning of the  $\text{SiO}_2$  etch retarding mask, (b) After the patterning of the ohmic contact metallization / chrome etch mask, and (c) After etching in the CAIBE.

8. A standard GaAs p-type ohmic contact metallization, followed by a 100 nm of chromium, is evaporated onto the sample. The pre-alloyed ohmic contact metallization consists of 20 nm of titanium, 20 nm of platinum, and 200 nm of gold.
9. Soaking in acetone lifts off the metallization in the regions to be etched. (See Figure 2b.)
10. The wafers are dry etched in the CAIBE, starting with the blank GaAs substrates in order to calibrate the etch rates. (See Figure 2c.) The deep and shallow etches, as seen by a scanning electron microscope, is shown in Figure 3.
11. Using 3 micron  $\text{AlO}_3$  grit, the backs of the wafers are then lapped down such that the final wafer thickness is approximately 150 microns.
12. The samples are cleaned and dried. A standard n-type ohmic contact metallization is evaporated on the backs of the wafers (10 nm of nickel, 40 nm of germanium, 80 nm of gold, 50 nm of silver, and 80 nm of gold).
13. The wafers are then placed in an alloying oven at 360 degrees centigrade for 60 seconds in order to alloy the ohmic contacts.



**Figure 3.** A total reflection mirror at the end of an etched ridge waveguide, as seen by a scanning electron microscope. The unintentional tree-like structures in the deeply etched region do not effect the performance of the mirror.

14. The wafers are now ready to be cleaved and tested.

Even with etched laser mirrors, cleaving may be required in order to access the optical output.

Discussions of the test methods used as well as the design and testing of specific photonic circuits have been published separately.<sup>1,10</sup>

#### IV. Conclusion

Photonic circuits utilizing etched ridge waveguides in conjunction with deep etched mirrors can be fabricated in a self aligned process which avoids photo lithography on previously etched surfaces. This is accomplished by using an etch retarding mask to facilitate two etch depths during a single run in the CAIBE. Since the contact metallization and the un-etched region coincide, only two photo lithography masks are needed for this process.

## REFERENCES

1. M.A. Parker, S.I. Libby, P.D. Swanson, *The Components of an Optical RS Flip-Flop for an Integrated Optical Processor*, USAF Technical Report, 1992 (in preparation).
2. C.M. Herzinger, P.D. Swanson, T.K. Tang, T.M. Cockerill, L.M. Miller, M.E. Givens, T.A. DeTemple, J.J. Coleman, and J.P. Leburton, *Electroabsorption properties of a single GaAs quantum well*, Phys. Rev. B, Vol. 44, Dec. 1991, p. 13478.
3. K.P. Jackson, Ch. Harder, P. Buchmann, and K. Datwyler, *High-Speed Characterization of a Monolithically Integrated GaAs-AlGaAs Quantum-well Laser-Detector*. IEEE Photon. Technol. Lett., Vol 2, 1990, p. 832
4. A. Ajisawa, M. Fujiwara, J. Shimizu, M. Sugimoto, M. Uchida, Y. Ohta, *Monolithically Integrated Optical Gate 2x2 Matrix Switch Using GaAs/AlGaAs Multiple Quantum Well Structure*. Electron. Lett., Vol. 23, 1987, p. 1121
5. W.J. Grande and C.L. Tang, *Semiconductor laser logic gate suitable for monolithic integration*, Appl. Phys. Lett. Vol. 51, p. 1780, Nov. 1987.
6. W.J. Grande, W.D. Braddock, J.R. Shealy, and C.L. Tang, *One-step two-level etching technique for monolithic integrated optics*, Appl. Phys. Lett. Vol. 51, p. 2189, Dec. 1987.
7. W.J. Grande, J.E. Johnson, and C.L. Tang, *Characterization of etch rate and anisotropy in the temperature-controlled chemically assisted ion beam etching of GaAs*, J. Vac. Sci. Technol. B, Vol. 8, p. 1075, Sep/Oct 1990.
8. D. Marcuse, Theory of Dielectric Optical Waveguides. Academic Press, inc., New York, pp. 330-334. 1991
9. C.F. Lin, *A New Technique for Monitoring Etching Depth in the Fabrication of Ridge-waveguide Lasers*, M.S. Thesis, Cornell University, May 1989.
10. S.I. Libby, P.D. Swanson, M.A. Parker, *Optical, Logic Gate, and Component Analysis Techniques*, USAF Technical Report, 1992 (in preparation).

***MISSION***  
***OF***  
***ROME LABORATORY***

**Mission.** The mission of Rome Laboratory is to advance the science and technologies of command, control, communications and intelligence and to transition them into systems to meet customer needs. To achieve this, Rome Lab:

- a. Conducts vigorous research, development and test programs in all applicable technologies;
- b. Transitions technology to current and future systems to improve operational capability, readiness, and supportability;
- c. Provides a full range of technical support to Air Force Materiel Command product centers and other Air Force organizations;
- d. Promotes transfer of technology to the private sector;
- e. Maintains leading edge technological expertise in the areas of surveillance, communications, command and control, intelligence, reliability science, electro-magnetic technology, photonics, signal processing, and computational science.

The thrust areas of technical competence include: Surveillance, Communications, Command and Control, Intelligence, Signal Processing, Computer Science and Technology, Electromagnetic Technology, Photonics and Reliability Sciences.