

AD-A285 249



DOCUMENTATION PAGE

Dist. A

Form Approved

OMB No. 0704-0188

①

Limit on cost material to average 10% per response, including the time for reviewing instructions, preparing existing data, gathering and reviewing the literature, and completing and reviewing the report. Information on the limits regarding the cost of material and the time for completing this burden is available from Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

2. REPORT DATE		3. REPORT TYPE AND DATES COVERED	
		FINAL 01 Nov 90 TO 31 Mar 94	
4. TITLE AND SUBTITLE		5. FUNDING NUMBERS	
ULTRASTRUCTURE PROCESSING AND PROPERTIES OF HIGH PERFORMANCE		AFOSR-91-0078	
6. AUTHOR(S)		61102F	
Edwin L. Thomas		2303/CS	
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES)		8. PERFORMING ORGANIZATION REPORT NUMBER	
Massachusetts Institute of Technology Dept of Materials Science & Engineering Room 13-5094 Cambridge MA 02139		AFOSR-TR-91-0609	
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES)		10. SPONSORING/MONITORING AGENCY REPORT NUMBER	
AFOSR/NL 110 Duncan Ave Suite B115 Bolling AFB DC 20332-0001 Dr Lee			
11. SUPPLEMENTARY NOTES			
12a. DISTRIBUTION/AVAILABILITY STATEMENT		12b. DISTRIBUTION CODE	
Approved for public release; distribution unlimited.		A	
13. ABSTRACT (Maximum 200 words)			
The proposal was directed towards the fundamental understanding of two areas of polymer materials: 1) Phase Transformations and Microstructure, 2) Ultrastructure and Mechanical Properties. Years 1 and 2 were primarily concerned with rigid rod PBX-type materials. During Year 2 and especially in Year 3 emphasis was redirected toward technique development (AFM and LVHSEM) for materials characterization, and materials processing (roll casting of block copolymers and magnetic field alignment of liquid crystalline polymers). As well, efforts shifted to block copolymer materials during the second half of the grant. Collaborative efforts with Professor P. Prasad at the University of Buffalo (sol-gel composites) and Professors S. Gruner and P. Chaikin at Princeton University (phase transitions and nanolithographic uses of block copolymers) were quite successful.			
14. SUBJECT TERMS		15. NUMBER OF PAGES	
		16. PRICE CODE	
17. SECURITY CLASSIFICATION OF REPORT		18. SECURITY CLASSIFICATION OF THIS PAGE	
(U)		(U)	
19. SECURITY CLASSIFICATION OF ABSTRACT		20. LIMITATION OF ABSTRACT	
(U)		(U)	

NSN 7540-01-280-5500

Standard Form 298 (Rev. 1-89)
Prescribed by ANSI Std. Z39-18
298-102

94-31481



DTIC QUALITY INSPECTED 2

AFOSR 91-0078

11/1/90 - 3/31/94

[illegible]

The proposal was directed towards the fundamental understanding of two areas of polymer materials:

- 1) Phase Transformations and Microstructure
- 2) Ultrastructure and Mechanical Properties

Years 1 and 2 were primarily concerned with rigid rod PBX-type materials. During Year 2 and especially in Year 3 emphasis was redirected toward technique development (AFM and LVHRSEM) for materials characterization, and materials processing (roll casting of block copolymers and magnetic field alignment of liquid crystalline polymers). As well, efforts shifted to block copolymer materials during the second half of the grant. Collaborative efforts with Professor P. Prasad at the University of Buffalo (sol-gel composites) and Professors S. Gruner and P. Chaikin at Princeton University (phase transitions and nanolithographic uses of block copolymers) were quite successful.

Overall, this grant resulted in 21 publications, with 6 additional papers submitted for publication. 5 graduate students and 5 post-doctoral research associates were fully or partially supported by AFOSR funds.

In this initial period of this grant we focussed on structure and properties rigid rod materials. We classified the grain boundary structure of rigid rod fibers and experimentally determined the various types of grain boundaries in PBO fibers [1]. The structure of the fibers is known to be influenced by the spinning process and a study of the PBT/PPA/H₂O system demonstrated the key role crystal solvates can play during the coagulations process [2].

14 SEP 1964

Collaborative work on sol-gel prepared PPV-silica composite films helped establish the morphology as a function of processing conditions and for correlation with χ^3 behavior [3].

A novel roll-casting technique was developed during the second year of the grant and applied to diblocks and diblock/homopolymer blends [4,5]. The technique yields extremely highly oriented films of up to 12 cm wide, 4 cm long and 1 mm thick. Such films approximate "single crystals" of hexagonally packed minority component cylinders in the majority matrix (cylindrical diblock composition) or layered films of lamellae. These are nearly structurally perfect specimens and are being used as model materials for physical property measurements. This area is a key area for future exploitation as it contains a good mix of basic science and applied engineering.

In the later portion of the grant period, we also demonstrated controlled organization of block copolymer microdomains in ultra thin films [6]. Here, two-dimensional patterns are formed in films quiescently cast or spin cast. Such structures might potentially be used as templates for nanolithography, at a length scale not easily accessed by electron beam methods.

Building on our grain boundary work in rigid rod materials we undertook an investigation of grain boundary structure in lamellar diblocks. A series of papers [7-9] describe the classification of the two general types of twist and tilt boundaries, their experimental verification via TEM of thin sections, the excellent correspondence with the data of two-dimensional simulation projections using candidate minimal surface models for the grain boundary geometry and justification of the various structure by theoretical modeling.

Temperature driven order-order phase transitions in block copolymers were theoretically predicted in 1980 but only in the last two years were any such transitions experimentally observed. We discovered a lamellar to cylindrical transition upon increasing temperature and demonstrated thermal reversibility [10]. Another order-order transition was discovered, in which the high temperature phase was a completely new microdomain morphology: the gyroid [11]. We wrote an invited review on phase morphology in block copolymer systems highlighting order-order transitions for the December, 1993 meeting of the

Royal Society in London [12]. The new gyroid phase is a bicontinuous phase with cubic ($Ia\bar{3}d$, space group #230) symmetry. Much remains to be done in this area to understand the physical properties of the new phase.

We also worked on processing-structure relationships of liquid crystalline polymers. A collaboration with researchers at WPAFB provided an explanation for the image contrast in cholesteric LCPs viewed in TEM and with AFM [13]. Development of uniform texture is an area which needs to be understood in order for LCP materials to realize their great potential as optical materials. We have employed high magnetic fields to align and reorient LCP materials. The development and evolution of Néel inversion walls was successfully followed using light microscopy and AFM [15]. Our approach allowed us to measure the splay and bend elastic constants. Finally, we have helped pioneer low voltage, high resolution SEM to polymer morphology studies [16].

3. References

- [1] D. C. Martin and E. L. Thomas, *Macromolecules*, 24, 2450-2460 (1991), "Ultrastructure of Poly(para phylene benzobisoxazole) Fibers"
- [2] Y. Cohen, Y. Saruyama and E. L. Thomas, *Macromolecules* 24, 1161-1167 (1991), "Crystal Solvates in the Poly (p-phenylene(benzobisthiazole))/ polyphosphoric acid/water System"
- [3] F. Embs, C. Wung, P. Prasad and E. L. Thomas, *Polymer* , 34, 4607 (1993), "Structure and Morphology of Sol-Gel Prepared Polymer-Ceramic-Composite Thin Films."
- [4] R. J Albalak and E. L. Thomas, *J. Polym. Sci., Polym. Phys. Ed.*, 31, 37-46 (1993), "Microphase Separation of Block Copolymer Solutions in a Flow Field."
- [5] R. Albalak and E. L. Thomas, *J. Polym. Sci., Polymer Physics Ed.*, 32, 341 (1994), "Roll Casting of Block Copolymers and of Block Copolymer - Homopolymer Blends."

- [6] P. Mansky, P. Chaikin and E. L. Thomas, *J. Materials Science*, submitted May 1994, "Monolayer Films of Diblock Copolymer Microdomains for Nanolithographic Applications."
- [7] S. Gido, J. Gunther, D. Hoffman and E. L. Thomas, *Macromolecules*, 26, 4506 (1993), "Lamellar Diblock Copolymer Grain Boundary Morphology: 1. Twist Boundary Characterization."
- [8] S. Gido and E. L. Thomas, *Macromolecules*, 27, 849-861 (1994), "Lamellar Diblock Copolymer Grain Boundary Morphology: 2. Scherk Twist Boundary Energy Calculations."
- [9] S. P. Gido and E. L. Thomas, *Macromolecules*, in press, "Lamellar Diblock Copolymer Grain Boundary Morphology: 4. Tilt Boundaries."
- [10] D. Hajduk, S. Gruner, P. Rangarajan, R. Register, L. Fetters, C. Honeker, and R. Albalak and E. L. Thomas, *Macromolecules*, 27, 490-501 (1994), "Observation of a Reversible Thermotropic Order-Order Transition in a Diblock Copolymer."
- [11] D. Hajduk, P. Harper, S. Gruner, C. Honeker, G. Kim, E. Thomas and L. Fetters, *Macromolecules*, 27, 4063-4075, "The Gyroid: A New Equilibrium Morphology in Weakly Segregated Diblock Copolymers."
- [12] R. Lescanec and E. L. Thomas, *Phil. Trans. R. Soc., London A*, 348, 149-166, "Phase Morphology in Block Copolymer Systems."
- [13] T. Bunning, D. Vezie, P. Lloyd, P. Haaland, W. Adams and E. L. Thomas, *Molecular Crystals and Liquid Crystals*, 16, 769-791 (1994), "Cholesteric Liquid Crystals: Image Contrast in the TEM."
- [14] D.-K. Ding, V. Percec and E. L. Thomas, *Macromolecules*, submitted January 1994, "Structure and Dynamics of Inversion Walls in a Liquid Crystal Polyether."
- [15] D.L. Vezie, W. W. Adams and E. L. Thomas, *Polymer*, submitted February 1994, "Low Voltage, High Resolution SEM: A New Characterization Technique for Polymer Morphology."

4.0 Cumulative List of Publications

D. C. Martin and E. L. Thomas, *Macromolecules*, 24, 2450-2460 (1991), "Ultrastructure of Poly(para phylene benzobisoxazole) Fibers."

Y. Cohen, Y. Saruyama and E. L. Thomas, *Macromolecules* 24, 1161-1167 (1991), "Crystal Solvates in the Poly (p-phenylene(benzobisthiazole))/ polyphosphoric acid/water System."

D. C. Martin and E. L. Thomas, *J. Materials Sci.*, 26, 5171-5183 (1991), "Micromechanisms of Kinking in Rigid Rod Polymer Fibers."

D. C. Martin and E. L. Thomas, *Philosophical Magazine A*, 64, 903-922 (1991), "Grain Boundaries in Extended-Chain Polymers: Theory and Experiment."

W. Zhang and E. L. Thomas, *Polymer Communications* 32, 4883-487 (1991), "Monomer Image of Poly(p-xylylene) Crystal at 0.18 Nanometer Resolution."

W. Zhang and E. L. Thomas, *Journal of Polymer Science (Physics)*, 30, 1285-1290 (1992), "Direct Imaging of Smectic B Phase of Poly(p-Xylylene)."

R. J Albalak and E. L. Thomas, *J. Polym. Sci., Polym. Phys. Ed.*, 31, 37-46 (1993), "Microphase Separation of Block Copolymer Solutions in a Flow Field."

D. Schwark, D. Vezie, J. Reffner and B. Annis and E. L. Thomas, *Journal of Materials Science Letters*, 11, 352-355 (1992), "Characterization of the Surface Morphology of Diblock Copolymers via Low-Voltage, High Resolution Scanning Electron Microscopy and Atomic Force Microscopy."

F. Embs, A. Gittinger, and L. Dulog and E. L. Thomas, *Thin Solid Films*, 237, 217-224 (1994), "Structure and Morphology of Langmuir-Blodgett Films of Rod-Like Poly (phthalocyaninatogermoxane)s by Transmission Electron Microscopy."

Albalak, R. J. and E. L. Thomas, "Roll Casting of Block Copolymers and of Block Copolymer - Homopolymer Blends." *J. Polym. Sci., Polymer Physics Ed.*, 32, 341 (1994).

Embs, F., C. Wung, P. Prasad and E. L. Thomas, "Structure and Morphology of Sol-Gel Prepared Polymer-Ceramic-Composite Thin Films." *Polymer*, 34, 4607 (1993).

Embs, F., A. Gittinger, L. Dulog and E. L. Thomas, "Structure and Morphology of Langmuir-Blodgett Films of Rod-Like Poly (phthalocyaninatogermoxane)s by Transmission Electron Microscopy." *Thin Solid Films*, 237, 217-224 (1994).

Gido, S., J. Gunther, D. Hoffman and E. L. Thomas, "Lamellar Diblock Copolymer Grain Boundary Morphology: 1. Twist Boundary Characterization." *Macromolecules*, 26, 4506 (1993).

Ding, D.-K., and E. L. Thomas, "Influence of Elastic Anisotropy on the Structure of Néel Inversion Walls in Liquid Crystals." *Macromolecules*, 26, 6531 (1993).

Ding, D.-K., and E. L. Thomas, "Structures of Point Integer Disclinations and Their Annihilation Behavior in Thermotropic Liquid Crystal Polyesters." *Molecular Crystals and Liquid Crystals*, 241, 103-117 (1994).

Hajduk, D., S. Gruner, P. Rangarajan, R. Register, L. Fetters, C. Honeker, and R. Albalak and E. L. Thomas, "Observation of a Reversible Thermotropic Order-Order Transition in a Diblock Copolymer." *Macromolecules*, 27, 490-501 (1994).

Gido, S., and E. L. Thomas, "Lamellar Diblock Copolymer Grain Boundary Morphology: 2. Scherk Twist Boundary Energy Calculations." *Macromolecules*, 27, 849-861 (1994).

Winey, K., D. Gobran, Z. Xu, L. Fetters, and E. L. Thomas, "Compositional Dependence of the Order-Disorder Transitions in Diblock Copolymers." *Macromolecules*, 27, 2392-2397 (1994).

Bunning, T., D. Vezie, P. Lloyd, P. Haaland, W. Adams, and E. L. Thomas, "Cholesteric Liquid Crystals: Image Contrast in the TEM." *Molecular Crystals and Liquid Crystals*, 16, 769-791 (1994).

Hajduk, D., P. Harper, S. Gruner, C. Honeker, G. Kim, E. Thomas and L. Fetters, "The Gyroid: A New Equilibrium Morphology in Weakly Segregated Diblock Copolymers." *Macromolecules*, 27, 4063-4075 (1994).

Thomas, E. L. and R. Lescanec, "Phase Morphology in Block Copolymer Systems." *Phil. Trans. R. Soc., London A*, 348, 149-166 (1994).

Papers Submitted for Publication:

Ding, D.-K., V. Percec, and E. L. Thomas, "Structure and Dynamics of Inversion Walls in a Liquid Crystal Polyether." *Macromolecules*, submitted January 1994.

Gido, S. and E.L. Thomas, "Lamellar Diblock Copolymer Grain Boundary Morphology: 4. Tilt Boundaries." *Macromolecules*, accepted July, 1994.

D.L. Vezie, W. W. Adams and E. L. Thomas, "Low Voltage, High Resolution SEM: A New Characterization Technique for Polymer Morphology." *Polymer*, submitted February 1994.

P. Mansky, P. Chaikin and E. L. Thomas, "Monolayer Films of Diblock Copolymer Microdomains for Nanolithographic Applications." *J. Materials Science*, submitted May 1994.