


REPORT DOCUMENTATION PAGE

Form Approved
OMB No. 0704-0188

Public reporting burden for this collection of information is estimated to average 1 hour per response, including the time for reviewing instructions, searching existing data sources, gathering and maintaining the data needed, and completing and reviewing the collection of information. Send comments regarding this burden estimate or any other aspect of this collection of information, including suggestions for reducing this burden, to Washington Headquarters Services, Directorate for Information Operations and Reports, 1215 Jefferson Davis Highway, Suite 1204, Arlington, VA 22202-4302, and to the Office of Management and Budget, Paperwork Reduction Project (0704-0188), Washington, DC 20503.

1. AGENCY USE ONLY (Leave blank)		2. REPORT DATE	3. REPORT TYPE AND DATES COVERED <i>Final 4 Feb 91-3 May 94</i>
4. TITLE AND SUBTITLE Macromolecular Characterization and Solution Behavior of Polymer Additives			5. FUNDING NUMBERS <i>DAAL03-91-G-0040</i>
6. AUTHOR(S) Ben Chu			
7. PERFORMING ORGANIZATION NAME(S) AND ADDRESS(ES) Chemistry Department State University of New York at Stony Brook Stony Brook, NY 11794-3400			
9. SPONSORING/MONITORING AGENCY NAME(S) AND ADDRESS(ES) U. S. Army Research Office P. O. Box 12211 Research Triangle Park, NC 27709-2211			10. SPONSORING/MONITORING AGENCY REPORT NUMBER <i>ARO 28153.9-CH</i>

11. SUPPLEMENTARY NOTES
The view, opinions and/or findings contained in this report are those of the author(s) and should not be construed as an official Department of the Army position, policy, or decision, unless so designated by other documentation.

12a. DISTRIBUTION/AVAILABILITY STATEMENT Approved for public release; distribution unlimited.	12b. DISTRIBUTION CODE
--	------------------------

13. ABSTRACT (Maximum 200 words)
In the ARO project, several aspects of polymer rheology and microstructures were investigated by using a variety of physical techniques, including the development of a new magnet-enhanced optical falling needle/sphere rheometer. From studies of rheological properties and association behavior of mixtures of poly(isobutyl methacrylate-tert-butyl aminoethyl methacrylate) and an ionomer in solution, and of random copolymers of styrene with sodium-2-acrylamido-2-methylpropane sulphonate, it becomes clear that structures of associative polymers can best be approached by using well-defined block copolymers. Furthermore, the ionic interactions deserve special examination in view of ion cluster formation and long-range inhomogeneities which are present often because of processing procedures.
A series of studies of block copolymers, including lightly sulfonated polystyrene-b-poly(tert butylstyrene) and triblock poly(oxyethylene-oxypropylene-oxyethylene) in nonpolar (xylene), polar (water) and water/o-xylene mixtures. The size, shape and aggregation number were determined by using laser light scattering, small angle x-ray scattering and transient electric birefringence techniques.

14. SUBJECT TERMS rheology of interacting polymers DTIC QUALITY INSPECTED 5 association behavior of polymer additives and of block copolymers			15. NUMBER OF PAGES
17. SECURITY CLASSIFICATION OF REPORT UNCLASSIFIED			16. PRICE CODE
18. SECURITY CLASSIFICATION OF THIS PAGE UNCLASSIFIED	19. SECURITY CLASSIFICATION OF ABSTRACT UNCLASSIFIED	20. LIMITATION OF ABSTRACT UL	

19941129 073

3

Macromolecular Characterization and Solution Behavior
of Polymer Additives

Final Report

Ben Chu

June 10, 1994

Accession For	
NTIS CRA&I	<input checked="" type="checkbox"/>
DTIC TAB	<input type="checkbox"/>
Unannounced	<input type="checkbox"/>
Justification	
By	
Distribution/	
Availability Codes	
Dist	Avail and/or Special
A-1	

U.S. Army Research Office

Contract #DAAL03-91-G-0040

Chemistry Department
State University of New York at Stony Brook

FOREWORD

Polymer additives are used to influence rheological properties of fluids. In order to increase the effectiveness of polymer additives, one needs to take advantage of intermolecular interactions so as to enhance the supramolecular formation of polymer additives. The aims of our projects were

1. to devise new methods for the characterization of polymer additives
2. to determine the structure of interactive polymer systems, and
3. to understand the factors which govern supramolecular formation.

1. New Method for Polymer Additives Characterization.

Polymer additives tend to form supramolecules which effectively change the fluid viscosity. A magnet enhanced optical falling needle/sphere rheometer [3] was developed to study the viscosity of highly viscous fluids [10] in the presence of polymer additives.

2. Structure of Interactive Polymer Systems

From rheological studies on the association behavior of mixtures of poly(isobutyl methacrylate-tert-butylaminoethyl methacrylate) and an ionomer in solution [1] and of random copolymers of styrene with sodium-2-acrylamido-2-methylpropane sulphonate [2], it became clear that ill-defined polymers could never yield sufficiently detailed information on the pertinent factors governing the supramolecular formation in a quantitative manner. Thus, well-defined block copolymers were chosen to further the studies.

For interacting polymers, the phase diagram could be complex [4]. Even the polymer in the melt state could have microstructures [8], in the presence of long range inhomogeneities [5]. Time-resolved SAXS was used to study the crystallization kinetics of poly(aryl ether ether ketone) [6].

3. Factors Governing Supramolecular Formation

For diblock copolymers of styrene and tert-butyl styrene in N,N-dimethyl acetamide [7], micelle formation could be induced by temperature changes. The essential factors could be separated to chain length, chain ratio, chain architecture and solvent quality. By changing the temperature [7] or by changing the solvent quality [15] from addition of a nonsolvent, to one of the two blocks [11],[13], polymer micelles are formed in order to minimize the free energy [16]. Like polymer additives, the supramolecular formation can be controlled from a combination of these factors. Unfortunately, only limited theoretical

development and computer simulation have been attempted to address this complex problem.

FINAL REPORT

Statement of the Problem

1. To use transient electric birefringence in order to study the shape of model polymer additives.
2. To combine rheology with optical and scattering techniques to study the structure and dynamics of supramolecules.
3. To study polymer interactions by varying functional groups.
4. To study the temperature dependence of polymer aggregation behavior.

Summary of Most Important Results

1. We have developed a magnet enhanced optical falling needle/sphere rheometer. Together with the magnetic needle/sphere rheometer, the viscosity and shear thinning properties of complex polymer fluids can be investigated in a closed system and at high temperatures.

2. New methodology have been developed to investigate the aggregation number, the molar mass, the size and the shape of supramolecules formed by well-defined block copolymers. In anticipation for larger size aggregates, an ultrasmall angle x-ray scattering apparatus was developed. The instrument should be ideal for structural studies of colloidal systems.

List of all Publications Acknowledging Support by the U.S. Army Research Office

1. Jian Wang, Dennis G. Peiffer, Wendel J. Shuely and Benjamin Chu, "Rheological Properties and Association Behavior of Mixtures of Poly(isobutyl methacrylate-tert-butylaminoethyl methacrylate) and an Ionomer in Solution," *Macromolecules*, **24**, 4349 (1991).
2. Zhulun Wang, Jian Wang, Benjamin Chu and Dennis G. Peiffer, "Solution Behavior of Random Copolymers of Styrene with Sodium-2-Acrylamido-2- Methylpropane Sulphonate," *J. Polym. Sci., Polym. Phys.*, **29**, 1361 (1991).
3. Benjamin Chu and Jian Wang, "Magnet Enhanced Optical Falling Needle/Sphere Rheometer," *Rev. Sci. Instrum.*, **63**, 2315 (1992).

4. Jian Wang, Alexei Khokhlov, Dennis G. Peiffer and Benjamin Chu, "Phase Equilibria in Ternary System Zinc Sulfonated Polystyrene/Poly(ethyl acrylate-4-vinyl pyridine)/THF," *Macromolecules*, Communication, **25**, 2566 (1992).
5. Benjamin Chu, Jian Wang, Yingjie Li and Dennis G. Peiffer, "Ultra-Small- Angle X-Ray Scattering of a Zinc Sulfonated Polystyrene," *Macromolecules*, Communication, **25**, 4229 (1992).
6. Jian Wang, Marta Alvarez, Wanjin Zhang, Zhongwen Wu, Yingjie Li and Benjamin Chu, "Synchrotron Small Angle X-Ray Scattering Study of Crystalline Structures and Isothermal Crystallization Kinetics of Poly(aryl ether ether ketones)," *Macromolecules*, **25**, 6943 (1992).
7. Zukang Zhou, Benjamin Chu and Dennis G. Peiffer, "Temperature Induced Micelle Formation of a Diblock Copolymer of Styrene and *tert*-Butylstyrene in *N,N*-Dimethylacetamide," *Macromolecules*, **26**, 1876 (1993).
8. Jian Wang, Yingjie Li, Dennis G. Peiffer and Benjamin Chu, "Small Angle X-Ray Scattering Investigation of Temperature Influences on Microstructures of an Ionomer," *Macromolecules*, Note, **26**, 2633 (1993).
9. Zukang Zhou, Benjamin Chu, Guangwei Wu and Dennis G. Peiffer, "Block Copolymer Ionomers: Solution Behavior in Lightly Sulfonated Polystyrene-*b*-Poly(*tert*-butylstyrene) in Polar Solvent," *Macromolecules*, **26**, 2968 (1993).
10. Benjamin Chu, Jian Wang and William H. Tuminello, "Fast Determination of Polymer Melt Viscosity by Optical Falling Needle Viscometer," *J. Appl. Polym. Sci.*, **49**, 97 (1993).
11. Guangwei Wu, Zukang Zhou and Benjamin Chu, "Water-Induced Micellar Structures of Block Copoly(oxyethylene-oxypropylene-oxyethylene) in *o*-Xylene," *J. Polym. Sci., Polym. Phys. Ed.*, **31**, 2035 (1993).
12. Zukang Zhou, Dennis G. Peiffer and Benjamin Chu, "Light Scattering Studies of Block Ionomer Aggregation Characteristics in Nonpolar Solvent," *Macromolecules*, **27**, 1428 (1994).
13. Guangwei Wu and Benjamin Chu, "Light Scattering Studies of a Block Poly(oxyethylene-oxypropylene-oxyethylene) Copolymer in Water/*o*-Xylene Mixtures," *Macromolecules*, **27**, 1766 (1994).
14. Qicong Ying, James Marecek and Benjamin Chu, "Slow Aggregation of Buckminsterfullerene (C₆₀) in Benzene Solution," *Chem. Phys. Lett.*, **219**, 1214 (1994).
15. Zukang Zhou and Benjamin Chu, "Phase Behavior and Association Properties of Poly(oxypropylene)-Poly(oxyethylene)-Poly(oxypropylene) Triblock Copolymer in

Aqueous Solution," *Macromolecules*, 27, 2025 (1994).

16. Benjamin Chu, Zukang Zhou and Guangwei Wu, "Structure and Dynamics of Polymeric Micelles in Solution," *J. Non-Cryst. Solids*, in press.

List of Personnel Supported

Visiting Research Scientists:

Dr. Jian Liu
Dr. An-Zhi Li
Dr. Yun-Zhu Luo
Dr. Jian Wang
Dr. Zukang Zhou

Graduate Students:

Kung Linliu
Jean Rousseau
Paul Harney

Research Staff Assistant:

Jane Wainio (20%)